Controls of Ambient Environment During Wafer Drying Using Proximity Head

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] The present invention relates to semiconductor wafer processing and, more particularly, to apparatuses and techniques for more efficiently applying and removing fluids from wafer surfaces while reducing contamination and decreasing wafer cleaning cost.

2. Description of the Related Art

[0002] In the semiconductor chip fabrication process, it is well-known that there is a need to process a wafer using operations such as cleaning and drying. In each of these types of operations, there is a need to effectively apply and remove fluids for the wafer operation process.

[0003] For example, wafer cleaning may have to be conducted where a fabrication operation has been performed that leaves unwanted residues on the surfaces of wafers. Examples of such a fabrication operation include plasma etching (*e.g.*, tungsten etch back (WEB)) and chemical mechanical polishing (CMP). In CMP, a wafer is placed in a holder which pushes a wafer surface against a rolling conveyor belt. This conveyor belt uses a slurry which consists of chemicals and abrasive materials to cause the polishing. Unfortunately, this process tends to leave an accumulation of slurry particles and residues at the wafer surface. If left on the wafer, the unwanted residual material and particles may cause, among other things, defects such as scratches on the wafer surface and inappropriate interactions between metallization features. In some cases, such defects may cause devices on the wafer to become inoperable. In order to avoid the undue costs of discarding wafers having inoperable devices, it is therefore necessary to clean the wafer adequately yet efficiently after fabrication operations that leave unwanted residues.

[0004] After a wafer has been wet cleaned, the wafer must be dried effectively to prevent water or cleaning fluid remnants from leaving residues on the wafer. If the cleaning fluid

on the wafer surface is allowed to evaporate, as usually happens when droplets form, residues or contaminants previously dissolved in the cleaning fluid will remain on the wafer surface after evaporation (e.g., and form water spots). To prevent evaporation from taking place, the cleaning fluid must be removed as quickly as possible without the formation of droplets on the wafer surface. In an attempt to accomplish this, one of several different drying techniques are employed such as spin drying, IPA, or Marangoni drying. All of these drying techniques utilize some form of a moving liquid/gas interface on a wafer surface which, if properly maintained, results in drying of a wafer surface without the formation of droplets. Unfortunately, if the moving liquid/gas interface breaks down, as often happens with all of the aforementioned drying methods, droplets form and evaporation occurs resulting in contaminants being left on the wafer surface. The most prevalent drying technique used today is spin rinse drying (SRD).

[0005] Figure 1A illustrates movement of cleaning fluids on a wafer 10 during an SRD drying process. In this drying process, a wet wafer is rotated at a high rate by rotation 14. In SRD, by use of centrifugal force, the water or cleaning fluid used to clean the wafer is pulled from the center of the wafer to the outside of the wafer and finally off of the wafer as shown by fluid directional arrows 16. As the cleaning fluid is being pulled off of the wafer, a moving liquid/gas interface 12 is created at the center of the wafer and moves to the outside of the wafer (i.e., the circle produced by the moving liquid/gas interface 12 gets larger) as the drying process progresses. In the example of Figure 1, the inside area of the circle formed by the moving liquid/gas interface 12 is free from the fluid and the outside area of the circle formed by the moving liquid/gas interface 12 is the cleaning fluid. Therefore, as the drying process continues, the section inside (the dry area) of the moving liquid/gas interface 12 increases while the area (the wet area) outside of the moving liquid/gas interface 12 decreases. As stated previously, if the moving liquid/gas interface 12 breaks down, droplets of the cleaning fluid form on the wafer and contamination may occur due to evaporation of the droplets. As such, it is imperative that droplet formation and the subsequent evaporation be limited to keep contaminants off of the wafer surface. Unfortunately, the present drying methods are only partially successful at the prevention of moving liquid interface breakdown.

[0006] In addition, the SRD process has difficulties with drying wafer surfaces that are hydrophobic. Hydrophobic wafer surfaces can be difficult to dry because such surfaces repel water and water based (aqueous) cleaning solutions. Therefore, as the drying process continues and the cleaning fluid is pulled away from the wafer surface, the remaining cleaning fluid (if aqueous based) will be repelled by the wafer surface. As a result, the aqueous cleaning fluid will want the least amount of area to be in contact with the hydrophobic wafer surface. Additionally, the aqueous cleaning solution tends cling to itself as a result of surface tension (i.e., as a result of molecular hydrogen bonding). Therefore, because of the hydrophobic interactions and the surface tension, balls (or droplets) of aqueous cleaning fluid forms in an uncontrolled manner on the hydrophobic wafer surface. This formation of droplets results in the harmful evaporation and the contamination discussed previously. The limitations of the SRD are particularly severe at the center of the wafer, where centrifugal force acting on the droplets is the smallest. Consequently, although the SRD process is presently the most common way of wafer drying, this method can have difficulties reducing formation of cleaning fluid droplets on the wafer surface especially when used on hydrophobic wafer surfaces. Certain portion of the wafer may have different hydrophobic properties.

[0007] Figure 1B illustrates an exemplary wafer drying process 18. In this example a portion 20 of the wafer 10 has a hydrophilic area and a portion 22 has a hydrophobic area. The portion 20 attracts water so a fluid 26 pools in that area. The portion 22 is hydrophobic so that area repels water and therefore there can be a thinner film of water on that portion of the wafer 10. Therefore, the hydrophobic portions of the wafer 10 often dries more quickly than the hydrophilic portions. This may lead to inconsistent wafer drying that can increase contamination levels and therefore decrease wafer production yields.

[0008] Therefore, there is a need for a method and an apparatus that avoids the prior art by enabling optimized fluid management and application to a wafer that reduces contaminating deposits on the wafer surface. Such deposits as often occurs today reduce the yield of acceptable wafers and increase the cost of manufacturing semiconductor wafers.

SUMMARY OF THE INVENTION

[0009] Broadly speaking, the present invention fills these needs by providing a substrate processing apparatus that is capable of removing fluids in an effective manner on wafer surfaces while at the same time reducing wafer contamination. It should be appreciated that the present invention can be implemented in numerous ways, including as a process, an apparatus, a system, a device or a method. Several inventive embodiments of the present invention are described below.

[0010] In one embodiment, a method for processing a substrate is provided which includes generating a fluid meniscus to process the substrate and applying the fluid meniscus to a surface of the substrate. The method further includes reducing evaporation of fluids from a surface in the substrate processing environment.

[0011] In another embodiment, a method for processing a substrate is provided which includes generating a fluid meniscus to process the substrate and applying the fluid meniscus to a surface of the substrate. The method also includes managing a substrate processing environment so evaporation of fluids from a surface in the substrate processing environment is reduced.

[0012] In yet another embodiment, an apparatus for processing a substrate is provided which includes a proximity head capable of generating a fluid meniscus to process a substrate surface and a chamber configured to house the proximity head where the chamber also configured to be supplied with an environmental control gas.

[0013] In another embodiment, an apparatus for processing a substrate is provided which includes a proximity head capable of generating a fluid meniscus to process a substrate surface, and a conduit located on a surface of the proximity head configured to apply an environmental control gas to a region on a leading edge side of the proximity head.

[0014] The advantages of the present invention are numerous. Most notably, the apparatuses and methods described herein efficiently process (e.g., clean, dry, etc.) that involves optimal management of fluid application and removal from the wafer) semiconductor wafer while reducing unwanted fluids and contaminants remaining on a wafer surface. Consequently, wafer processing and production may be increased and higher wafer yields may be achieved due to efficient wafer processing.

[0015] The present invention enables optimal wafer processing through the generation and use of a fluid meniscus along with intelligent management of fluid evaporation from the wafer. Specifically, the relative humidity level of the atmosphere surrounding the wafer processing region may be managed so, for example, the relative humidity level of the atmosphere is at a high level. Therefore, when the relative humidity level of the wafer processing region is high, the fluid evaporation of the wafer is highly manageable. The entire wafer processing chamber may have a controlled atmosphere with a high relative humidity level. Additionally, a limited region around the wafer may have a controlled relative humidity level thereby keeping the fluid evaporation from the wafer at a manageable level.

[0016] Other aspects and advantages of the present invention will become apparent from the following detailed description, taken in conjunction with the accompanying drawings, illustrating by way of example the principles of the present invention.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] The present invention will be readily understood by the following detailed description in conjunction with the accompanying drawings. To facilitate this description, like reference numerals designate like structural elements.

[0018] Figure 1A illustrates movement of cleaning fluids on a wafer during an SRD drying process.

[0019] Figure 1B illustrates an exemplary wafer drying process.

[0020] Figure 2A shows a wafer processing system in accordance with one embodiment of the present invention.

[0021] Figure 2B shows the region which has different portions with different evaporation rates in accordance with one embodiment of the present invention.

[0022] Figure 3 illustrates a proximity head during a wafer processing operation in accordance with one embodiment of the present invention.

[0023] Figure 4 shows a wafer processing chamber in accordance with one embodiment of the present invention.

[0024] Figure 5 shows a wafer processing environment in accordance with one embodiment of the present invention.

[0025] Figure 6 illustrates a wafer processing environment in accordance with one embodiment of the present invention.

[0026] Figure 7 shows a wafer cleaning and drying system in accordance with one embodiment of the present invention.

[0027] Figure 8A illustrates a proximity head performing a drying operation in accordance with one embodiment of the present invention.

[0028] Figure 8B shows a top view of a portion of a proximity head in accordance with one embodiment of the present invention.

[0029] Figure 8C illustrates an inlets/outlets pattern of a proximity head in accordance with one embodiment of the present invention.

[0030] Figure 8D illustrates another inlets/outlets pattern of a proximity head in accordance with one embodiment of the present invention.

[0031] Figure 8E illustrates a further inlets/outlets pattern of a proximity head in accordance with one embodiment of the present invention.

DETAILED DESCRIPTION

[0032] An invention for methods and apparatuses for processing a substrate is disclosed. In the following description, numerous specific details are set forth in order to provide a thorough understanding of the present invention. It will be understood, however, by one of ordinary skill in the art, that the present invention may be practiced without some or all of these specific details. In other instances, well known process operations have not been described in detail in order not to unnecessarily obscure the present invention.

[0033] While this invention has been described in terms of several preferable embodiments, it will be appreciated that those skilled in the art upon reading the preceding specifications and studying the drawings will realize various alterations, additions, permutations and equivalents thereof. It is therefore intended that the present invention includes all such alterations, additions, permutations, and equivalents as fall within the true spirit and scope of the invention.

[0034] The figures below illustrate embodiments of an exemplary wafer processing system. Specifically, the figures below illustrate embodiments of an exemplary wafer processing system using proximity heads to generate a fluid meniscus in a controlled

environment that reduces humidity levels in the wafer processing environment (also known as a substrate processing environment). It should be appreciated that the systems described here are exemplary, and that any other suitable type of configuration that would enable movement of the proximity head(s) into close proximity to the wafer may be utilized with a controlled environment may be utilized. In the embodiments shown, the proximity head(s) may move in a linear fashion from a center portion of the wafer to the edge of the wafer. It should be appreciated that other embodiments may be utilized where the proximity head(s) move in a linear fashion from one edge of the wafer to another diametrically opposite edge of the wafer, or other non-linear movements may be utilized such as, for example, in a radial motion, in a circular motion, in a spiral motion, in a zig-zag motion, etc. The motion may also be any suitable specified motion profile as desired by a user. In addition, in one embodiment, the wafer may be rotated and the proximity head moved in a linear fashion so the proximity head may process all portions of the wafer. It should also be understood that other embodiments may be utilized where the wafer is not rotated but the proximity head is configured to move over the wafer in a fashion that enables processing of all portions of the wafer. In addition, the proximity head and the wafer processing system described herein may be utilized to clean and dry any shape and size of substrates such as for example, 200 mm wafers, 300 mm wafers, flat panels, etc. It should also be appreciated that a fluid meniscus can be supported and moved (e.g., onto, off of and across a wafer) with a proximity head.

[0035] Figure 2A shows a wafer processing system 100 in accordance with one embodiment of the present invention. The system 100 includes proximity heads 106a and 106b which may generate a fluid meniscus as discussed herein. In one embodiment the proximity head 106a is in close proximity above the wafer and the proximity head 106b is in close proximity below the wafer in close proximity to the wafer. It should also be appreciated that the system 100 may be configured in any suitable manner as long as the proximity head(s) may be moved in close proximity to the wafer to generate and control a meniscus. It should also be understood that close proximity may be any suitable distance from the wafer as long as a meniscus may be maintained. In one embodiment, the proximity heads 106a and 106b (as well as any other proximity head described herein) may each be located between about 0.1 mm to about 10 mm from the wafer to generate

the fluid meniscus on the wafer surface. In a preferable embodiment, the proximity heads 106a and 106b (as well as any other proximity head described herein) may each be located bout 0.5 mm to about 4.5 mm from the wafer to generate the fluid meniscus on the wafer surface, and in more preferable embodiment, the proximity heads 106a and 106b (as well as any other proximity head described herein) may be located about 2 mm from the wafer to generate the fluid meniscus on the wafer surface.

[0036] In one embodiment, the system 100, the proximity heads 106a and 106b may be moved from processed to unprocessed portions of the wafer. It should be appreciated that the proximity heads 106a and 106b may be movable in any suitable manner that would enable movement of the proximity heads 106a and 106b to process the wafer as desired. It should be understood that although the wafer processing system 100 is shown with the proximity heads 106a and 106b, that any suitable number of proximity heads may be utilized such as, for example, 1, 2, 3, 4, 5, 6, etc. The proximity heads 106a and/or 106b of the wafer processing system 100 may also be any suitable size or shape as shown by, for example, any of the proximity heads as described herein. The different configurations described herein generate a fluid meniscus between the proximity head and the wafer. The fluid meniscus may be moved across the wafer to process the wafer by applying fluid to the wafer surface and removing fluids from the surface. In such a way, depending on the fluids applied to the wafer, cleaning, drying, etching, and/or plating may be accomplished. Therefore, the proximity heads 106a and 106b can have any numerous types of configurations as shown herein or other configurations that enable the processes described herein. It should also be appreciated that the system 100 may process one surface of the wafer or both the top surface and the bottom surface of the wafer.

[0037] In addition, besides processing the top and/or bottom surfaces of the wafer, the system 100 may also be configured to process one side of the wafer with one type of process (e.g., etching, cleaning, drying, plating, etc.) and process the other side of the wafer using the same process or a different type of process by inputting and outputting different types of fluids or by using a different configuration meniscus. The proximity heads can also be configured to process the bevel edge of the wafer in addition to processing the top and/or bottom of the wafer. This can be accomplished by moving the meniscus off (or onto) the edge the wafer which processes the bevel edge. It should also

be understood that the proximity heads 106a and 106b may be the same type of apparatus or different types of proximity heads.

[0038] In an exemplary wafer processing operation, the unprocessed areas of the wafer may be presented to the proximity heads 106a and 106b through both the linear motion of the proximity heads 106a and 106b and through the rotation of the wafer 108. The wafer processing operation itself may be conducted by at least one of the proximity heads. Consequently, in one embodiment, processed portions of the wafer 108 would expand from a center region to the edge region of the wafer 108 in a spiral movement as the processing operation progresses. In another embodiment, when the proximity heads 106a and 106b are moved from the periphery of the wafer 108 to the center of the wafer 108, the processed portions of the wafer 108 would expand from the edge region of the wafer 108 to the center region of the wafer 108 in a spiral movement.

[0039] In an exemplary processing operation, it should be understood that the proximity heads 106a and 106b may be configured to dry, clean, etch, and/or plate the wafer 108. In an exemplary drying embodiment, the at least one of first inlet may be configured to input deionized water (DIW) (also known as a DIW inlet), the at least one of a second inlet may be configured to input N_2 carrier gas containing isopropyl alcohol (IPA) in vapor form (also known as IPA inlet), and the at least one outlet may be configured to remove fluids from a region between the wafer and a particular proximity head by applying vacuum (also known as vacuum outlet). It should be appreciated that although IPA vapor is used in some of the exemplary embodiments, any other type of vapor may be utilized such as for example, nitrogen, any suitable alcohol vapor, organic compounds, volatile chemicals, etc. that may be miscible with water. It should be appreciated that the any suitable alcohol can be any suitable carbon-based chemical with a hydroxy group attached to a saturated carbon atom.

[0040] In an exemplary cleaning embodiment, a cleaning solution may be substituted for the DIW such as, for example, SC-1, SC-2, etc. In addition, other types of solutions may be inputted into the first inlet and the second inlet depending on the processing operation desired.

[0041] It should be appreciated that the inlets and outlets located on a face of the proximity head may be in any suitable configuration as long as a stable meniscus as

described herein may be utilized. In one embodiment, the at least one N_2/IPA vapor inlet may be adjacent to the at least one vacuum outlet which is in turn adjacent to the at least one processing fluid inlet to form an IPA-vacuum-processing fluid orientation. It should be appreciated that other types of orientations such as IPA-processing fluid-vacuum, processing fluid-vacuum-IPA, vacuum-IPA-processing fluid, etc. may be utilized depending on the wafer processes desired and what type of wafer processing mechanism is sought to be enhanced. In another embodiment, the IPA-vacuum-processing fluid orientation may be utilized to intelligently and powerfully generate, control, and move the meniscus located between a proximity head and a wafer to process wafers. The processing fluid inlets, the N_2/IPA vapor inlets, and the vacuum outlets may be arranged in any suitable manner if the above orientation is maintained. For example, in addition to the N_2/IPA vapor inlet, the vacuum outlet, and the processing fluid inlet, in an additional embodiment, there may be additional sets of IPA vapor outlets, processing fluid inlets and/or vacuum outlets depending on the configuration of the proximity head desired. It should be appreciated that the exact configuration of the IPA-vacuum-processing fluid orientation may be varied depending on the application. For example, the distance between the IPA input, vacuum, and processing fluid input locations may be varied so the distances are consistent or so the distances are inconsistent. In addition, the distances between the IPA input, vacuum, and processing fluid output may differ in magnitude depending on the size, shape, and configuration of the proximity head 106a and the desired size of a process meniscus (i.e., meniscus shape and size). In addition, exemplary IPA-vacuum-processing fluid orientation may be found as described further herein.

[0042] In one embodiment, the proximity heads 106a and 106b may be positioned in close proximity to a top surface and a bottom surface respectively of the wafer 108 and may utilize the IPA and DIW inlets and a vacuum outlet(s) to generate wafer processing meniscuses in contact with the wafer 108 which are capable of processing the top surface and the bottom surface of the wafer 108. The wafer processing meniscus may be generated in accordance with the descriptions herein. At substantially the same time the IPA and the processing fluid is inputted, a vacuum may be applied in close proximity to the wafer surface to remove the IPA vapor, the processing fluid, and/or the fluids that

may be on the wafer surface. It should be appreciated that although IPA is utilized in the exemplary embodiment, any other suitable type of vapor may be utilized such as for example, any suitable vapor of alcohol, ketone, ether, hexanol, ethyl glycol, organic compounds, etc. that may be miscible with water. These fluids may also be known as surface tension reducing fluids. The portion of the processing fluid that is in the region between the proximity head and the wafer is the meniscus. It should be appreciated that as used herein, the term "output" can refer to the removal of fluid from a region between the wafer 108 and a particular proximity head, and the term "input" can be the introduction of fluid to the region between the wafer 108 and the particular proximity head.

[0043] In one embodiment, the system 100 further includes a fluid supply distributor 120 that can supply to and remove fluids from the proximity heads 106a and 106b. It should be appreciated that the fluid supply distributor 120 may be any suitable apparatus that can supply and receive fluids in an organized manner such as, for example, a manifold. In one embodiment, the fluid supply distributor 120 receives fluid from a fluid supply 122. The fluid supply 122 may be managed and controlled by a fluid supply control 124 which may be any suitable hardware/software that can manage fluid input to the proximity heads 106a and 106b. The proximity heads 106a and 106b may produce meniscus 104 that may process the wafer 108.

[0044] In one exemplary wafer processing operation, the wafer 108 may have different portions therein that can have different evaporation rates. For example, fluid 150 may accumulate on portions of the wafer 108 with slower evaporation rates as compared with other portions of the wafer 108 with a higher evaporation rates. Higher evaporation rates may occur when portions of the wafer 108 are hydrophobic (repels water molecules) and therefore results in a thinner film of fluid than portions of the wafer 108 that are hydrophilic (attracts water). Consequently, when the film of fluid such as, for example, water is thinner, there may be less layers of water molecules to evaporate from the surface resulting in exposed contaminated dried areas due to uncontrolled evaporation.

[0045] In one embodiment of the system 100, fluid sensors 112 may detect portions of the wafer that have thinner layers of fluid and therefore, through in situ metrology different wafer locations with different fluid evaporation rates may be detected. It should be

appreciated that any suitable manner of in situ metrology may be utilized which can detect the thickness of the fluid film on the wafer 108. A region 180 as discussed further in detail in reference to Figure 2B has different portions with different evaporation rates as can be detected by the fluid sensors 112 through the determination of fluid thickness. Environmental management may be conducted to reduce the problems of variable fluid evaporation rates from the wafer surface.

[0046] As discussed below, the environment of a wafer processing region (e.g., atmosphere immediately around a region of the wafer which the meniscus 104 is processing or is about to process) (also know as a substrate processing environment) may be controlled and managed in an intelligent manner so humidity is kept at a high level. In addition, the chamber where the wafer is being processed can be controlled and managed to keep the humidity in the chamber at a high level. Therefore, by intelligently managing the environment in the wafer processing region to keep humidity at an optimal level, the fluid evaporation rate from the wafer 108 may be decreased thereby reducing uncontrolled drying of wafer regions.

[0047] Figure 2B shows the region 180 which has different portions with different evaporation rates in accordance with one embodiment of the present invention. In one embodiment, the region 180 includes the fluid 150 near the proximity head 106 as the proximity head 106 (as shown in Figure 2A) moves toward the region 180. The fluid 150 includes a portion 152 which shows evaporation and reassimilation of water molecules to and from the portion 152. The portion 152 therefore may includes evaporating liquid molecules 200 and reassimilating liquid molecules 202. In one embodiment, the liquid molecules are water molecules. The region 180 also shows areas of the wafer 108 without the fluid 150 that has a more hydrophobic region and therefore has already dried before the area with the fluid 150. In the area without the fluid 150, evaporating molecules 200 counteract the reassimilating molecules 200 and therefore that surface of the wafer 108 stays dry.

[0048] Figure 3 illustrates a proximity head 106 during a wafer processing operation in accordance with one embodiment of the present invention. In one embodiment, the proximity head 106 may produce a fluid meniscus to process the wafer 108. In one embodiment of a drying operation, the proximity head 106 includes inlets 302 and 306

which may input IPA/N_2 and deionized water (DIW) respectively. An outlet 304 may generate vacuum which can remove the IPA/N_2 and the DIW (as well as any other fluid on the wafer 108) from a surface of the wafer 108. In such an exemplary embodiment, the proximity head 106 may process the wafer 108 so a wet region 270 can be dried to generate a dry region 250. In one example, a region 272 is a just recently dried region processed by the proximity head 106, and a region 274 is a portion of the surface of the wafer 108 yet to be processed. In one example, the region 274 may have fluid 278 which includes portions of the wafer surface that has different drying rates. The different drying rates may be generated due to wafer surface variations such as hydrophobic and hydrophilic regions. In another example, different drying rates may be generated by IPA/N_2 application to the wafer 108 during the processing of the region 272. During such processing, IPA/N_2 that is being applied to the region 272 of the wafer 108 may overflow into an adjacent region such as the region 274. Therefore, the application of IPA/N_2 may create a condition where a higher evaporation rate may occur in the region 274. By managing the humidity of the atmosphere of the region where the wafer 108 is being processed, the evaporation rate of nearly all regions of the wafer 108 may be managed and therefore, the contamination of the wafer 108 may be reduced due to the controlled drying of the wafer 108.

[0049] Figure 4 shows a wafer processing chamber 300 in accordance with one embodiment of the present invention. The chamber 300 includes proximity heads 106 attached to arms 105 which may move the proximity heads 106 into close proximity to the wafer 108 for wafer processing operations such as, for example, cleaning, drying, etc. The proximity heads 106 may produce meniscus 104 that can process a surface of the wafer 108. Exemplary meniscus may be generated by apparatuses and methodology as described further herein to process the wafer 108.

[0050] In one embodiment, the wafer processing chamber 300 includes a HEPA filter 302 that may supply substantially purified atmosphere to the chamber 300. In one embodiment, the HEPA filter 302 may purify air supplied through input 310. In another embodiment, the HEPA filter 302 may purify any suitable type of atmosphere such as, for example, IPA/N_2, Ar, N_2, O_2, O_2/N_2, He, Ne, Xe, etc. It should be appreciated that the term atmosphere may be any suitable gas that can carry the desired amount of relative

humidity. The chamber 300 may also include inputs 306 which may provide a atmosphere with a controlled level of humidity. In one embodiment, the inputs 306 may supply gas with a high enough relative humidity level to decrease evaporation from the wafer 108. It should be appreciated that any suitable type of inert gas or vapor may be utilized as a carrier gas for carrying the high relative humidity level such as, for example, IPA/N_2, N_2, air (CDA), Ar, O_2/N_2, O_2, etc. In another embodiment, the chamber 300 may be supplied with atmosphere, such as, for example air, that has between 10% to about 100% relative humidity. In a preferable embodiment, the atmosphere that is supplied to the chamber 300 may have greater than 80% relative humidity. Therefore, in one embodiment, a controlled environment 304 of the processing chamber 300 may include an atmosphere with a high level of relative humidity in conjunction with meniscus 104 generated by the proximity heads 106 to intelligently and powerfully control wafer processing operations through the management of fluid evaporation from the wafer surface.

[0051] Figure 5 shows a wafer processing environment 400 in accordance with one embodiment of the present invention. In one embodiment, the wafer processing environment 400 includes a control envelope 404 which encompasses the region where the relative humidity is controlled so that, in one embodiment, the atmosphere in that region has a high level of relative humidity. In a preferable embodiment, the atmosphere may contain enough humidity so liquid molecules (e.g., water molecules) evaporating into the atmosphere is the same or less than the liquid molecules being assimilated back into liquid form on the wafer surface.

[0052] In one embodiment, the control envelope 404 may be generated through application of a suitable gas with a high relative humidity through inlet 402 of the proximity head 106. In another embodiment, the inlet 402 may apply vapor to maintain some concentration of a particular liquid in water such as, for example, IPA/N_2, acetone, any suitable type of alcohol, etc. including the azeotropic mixtures. It should be understood that although IPA is discussed in exemplary embodiments, that other types of chemicals may be utilized that enables the methodology discussed herein. It should be appreciated that the any suitable alcohol can be any suitable chemical compound that includes carbon and a hydroxy group. An azeotropic ratio means that the ratio of the

chemical composition of a liquid mixture is the same as the ratio of chemical composition of the vapor from the liquid mixture. As described herein the gas with the high relative humidity and the vapor/gas that may maintain some concentration of a particular liquid (e.g. IPA) in water may be known as an environmental control gas. In one embodiment, IPA/N_2 vapor may be applied to water on the wafer surface through the inlet 401 to maintain some concentration of IPA in the water including the azeotropic mixture on the wafer surface. This may intelligently and powerfully reducing unwanted evaporation from the wafer surface. In one embodiment, the inlet 402 may be on a leading edge of the proximity head 106 and may apply the gas with a high relative humidity to the wafer 108. When high relative humidity gas is applied to water on the wafer surface, the evaporation rate is decreased thereby decreasing unwanted wafer drying. The leading edge of the proximity head 106 is a region where the proximity head encounters unprocessed wafer surface such as wafer surface with fluid 278 within wafer region 406. It should be appreciated that the gas with a high level of relative humidity may be applied at or near the control envelope in any suitable fashion from any suitable location by any suitable apparatus. Therefore, the inlet 402 is just an exemplary embodiment that can apply controlled gas to reduce evaporation of fluids on the wafer surface. In this way the wafer region 406 may be kept in a controlled evaporative state before wafer processing of that particular region begins.

[0053] In addition, in one embodiment, the level of relative humidity in the control envelope may be managed through varying the flow rate of a gas with high relative humidity or by applying a gas that may maintain some concentration of a particular liquid (e.g., IPA) in water including the azeotropic mixture. In such an embodiment, the flow rate of the gas with high relative humidity may be increased thereby increasing the overall liquid level in the control enveloped 404. It should be appreciated that any suitable type of gas that may generate the desired level of evaporative rate of a fluid on surface of the wafer can be utilized. In one embodiment, when a gas with a high relative humidity is used, a relative humidity higher than 50% can be utilized to manage the wafer processing environment to reduce unwanted drying and lower contamination levels on wafers. In another embodiment, a relative humidity of the gas may be between 90% and 100%, and in a preferable embodiment, a gas with a relative humidity of about 100% may be used.

[0054] Figure 6 illustrates a wafer processing environment 400' in accordance with one embodiment of the present invention. The wafer processing environment 400', in one embodiment, includes substantially all of the wafer processing chamber 300. The wafer processing environment 400' may be generated by inputting gas(es) with a high relative humidity from a wafer processing environment generator 500. In another embodiment of the wafer processing environment generator 500, gas(es) that may maintain an some concentration of particular liquid in water may be inputted into the wafer processing environment 400'. In one particular embodiment, a specific concentration of IPA including the azeotropic concentration may be maintained in water. It should be appreciated that the wafer processing environment generator 500 may be any suitable apparatus that can input gas(es) and that can manage and control the evaporative rate of fluids within the chamber 300. It should also be understood that the any suitable gas may be utilized that can carry a high level of relative humidity such as, for example, clean dry air (CDA), N_2, Ar, etc. In one embodiment, the wafer processing environment generator 500 may input a gas that may have from 50% relative humidity to about 100% relative humidity. In another embodiment, the relative humidity is between about 90% to about 100%, and preferably the gas may have about 100% relative humidity.

[0055] In one embodiment, the wafer processing environment generator 500 is a bubbler 502 which is at least partially filled with liquid 504. It should be appreciated that the liquid 504 may be any suitable liquid or combination of liquids that can generate a gas/vapor with a high relative humidity when a gas is passed through the liquid 504. In one embodiment, an input 506 such as, for example, a tube may be apply a gas 508 to the liquid 504. It should be appreciated that the liquid 504 may be any suitable type of liquid that may optionally include any suitable mixture, including azotropic mixtures such as, for example DIW and HCl, DIW and HF, DIW and IPA, etc. In one embodiment, the liquid may be DIW while in another embodiment, the liquid 504 may be DIW and liquid IPA. In yet another embodiment the liquid 504 may be IPA. The gas 508 may pass through the liquid 504 and then bubble up as a vapor 510 which may be gas or the gas with a high relative humidity. In one embodiment, by exposing gas 508 to the liquid 504 during the bubble-up process, the gas 508 may be infused with high relative humidity content to generate the vapor 510. The vapor 510 may then be inputted into the chamber

300 to generate the wafer processing environment 400'. Once the gas 508 has been inputted into the chamber 300, the humidity level of the atmosphere in the chamber 300 may be increased thereby decreasing the evaporation rate of fluids within the chamber 300. Therefore, fluids on the wafer 108 being processed by the meniscus 104 may have a low evaporative rate. To put it another way, fluids on the wafer 108 are managed to prevent or reduce the generation of a thin film of fluid in unprocessed portions of the wafer 108. By increasing the concentration of the humidifying solute in the gas 508, the amount of fluid molecules evaporating into the atmosphere from the unprocessed wafer surface may be made substantially equal to the amount of fluid molecules hitting the wafer surface and staying on the wafer surface thereby reducing unwanted evaporation/drying.

[0056] It should be appreciated that in the embodiments described herein, other atmospheric conditions such as ambient temperature, barometric pressure, etc. may affect the degree of evaporative loss of fluid from a wafer surface. Therefore, it should be understood that for each different type of atmospheric condition, different levels of humidity may be needed to achieve a controlled decrease of unwanted evaporative fluid loss from the wafer.

[0057] The following figures describe an exemplary wafer processing system with an exemplary proximity head that can generate a fluid meniscus. It should be appreciated that any suitable type of system with any suitable type of proximity head that can generate a fluid meniscus can be used with the embodiments of the present invention described herein.

[0058] Figure 7 shows a wafer processing system 1100 in accordance with one embodiment of the present invention. It should be appreciated that any suitable manner of holding or moving the wafer can be used such as, for example, rollers, pins, platen, etc. The system 1100 may include rollers 1102a, 1102b, and 1102c which can hold and rotate a wafer to enable wafer surfaces to be processed. The system 1100 may also include proximity heads 106a and 106b that, in one embodiment, can be attached to an upper arm 1104a and to a lower arm 1104b respectively. The upper arm 1104a and the lower arm 1104b can be a part of a proximity head carrier assembly 1104 which enables substantially linear movement of the proximity heads 106a and 106b along a radius of the

wafer. In one embodiment the proximity head carrier assembly 1104 may be configured to hold the proximity head 106a above the wafer and the proximity head 106b below the wafer in close proximity to the wafer. This may be accomplished by having the upper arm 1104a and the lower arm 1104b be movable in a vertical manner so once the proximity heads are moved horizontally into a location to start wafer processing, the proximity heads 106a and 106b can be moved vertically to a position in close proximity to the wafer. In another embodiment, the fluid meniscus may be formed between the two proximity heads 104a and 104b and moved onto the top and bottom surface of the wafer. The upper arm 1104a and the lower arm 1104b may be configured in any suitable way so the proximity heads 106a and 106b can be moved to enable wafer processing as described herein. It should also be appreciated that the system 1100 may be configured in any suitable manner as long as the proximity head(s) may be moved in close proximity to the wafer to generate and control a meniscus on the wafer surface. In another exemplary embodiment, the proximity head 106 may be located at a first end of an arm which rotates around an axis defined by a second end of the arm. Therefore, in such an embodiment, the proximity head may be moved in an arc over the surface of the wafer. In yet another embodiment, the arm may be moved in a combination of a rotational movement and a linear movement. Although shown with a proximity head 106 for each side of the wafer, a single head can be used for a single side of a wafer. Other surface preparation processes can be performed on sides where no proximity head 106 is used, such as a wafer scrub brush.

[0059] In another embodiment, the system 1100 may include a proximity head docking station that has a transition surface adjacent to the wafer. In such an embodiment, the fluid meniscus may transition between a docking station and the surface of the wafer while in a controlled and managed state. Again, if only one side of the wafer is desired to be processed, one arm with one proximity head may be utilized.

[0060] Figure 8A illustrates a proximity head 106 performing a wafer processing operation in accordance with one embodiment of the present invention. The proximity head 106, in one embodiment, moves while in close proximity to the top surface 108a of the wafer 108 to conduct the wafer processing operation. It should be appreciated that depending on the type of fluid applied to the wafer 108, the fluid meniscus 104 generated

by the proximity head 106 on the wafer surface 108a may be any suitable wafer processing operation such as, for example, cleaning, rinsing, drying, etching, plating, etc. It should be appreciated that the proximity head 106 may also be utilized to process the bottom surface 108b of the wafer 108. In one embodiment, the wafer 108 may be rotated so the proximity head 106 may be moved while fluid meniscus processes the top surface 108a. In another embodiment, the wafer 108 may be held still while the proximity head 106 generates the fluid meniscus on the wafer surface. Then the proximity head may move or scan over the wafer surface and therefore move the fluid meniscus along the surface of the wafer. In yet another embodiment, the proximity head 106 may be made large enough so the fluid meniscus encompasses the surface area of the entire wafer. In such an embodiment, by applying the fluid meniscus to the surface of the wafer the entire surface of the wafer may be processed without movement of the proximity head.

[0061] In one embodiment, the proximity head 106 includes source inlets 1302 and 1306 and a source outlet 1304. In such an embodiment, isopropyl alcohol vapor in nitrogen gas IPA/N_2 1310 may be applied to the wafer surface through a source inlet 1302, vacuum 1312 may be applied to the wafer surface through a source outlet 1304, and a processing fluid 1314 may be applied to the wafer surface through a source inlet 1306.

[0062] In one embodiment, the application of the IPA/N_2 1310 and the processing fluid 1314 in addition to the application of the vacuum 1312 to remove the processing fluid 1314 and the IPA/N_2 1310 from the wafer surface 108a can generate the fluid meniscus 104. The fluid meniscus 104 may be a fluid layer defined between the proximity head 106 and the wafer surface that can be moved across a wafer surface 108a in a stable and controllable manner. In one embodiment, the fluid meniscus 104 may be defined by a constant application and removal of the processing fluid 1314. The fluid layer defining the fluid meniscus 104 may be any suitable shape and/or size depending on the size, number, shape, and/or pattern of the source inlets 1306, source outlets 1304 and source inlets 1302.

[0063] In addition, any suitable flow rates of the vacuum, IPA/N_2, vacuum, and the processing fluid may be used depending on the type of fluid meniscus desired to be generated. In yet another embodiment, depending on the distance between the proximity head 106 and the wafer surface, the IPA/N_2 may be omitted when generating and utilizing

the fluid meniscus 106. In such an embodiment, the proximity head 106 may not include the source inlet 1312 and therefore only the application of the processing fluid 1314 by the source inlet 1306 and the removal of the processing fluid 1314 by the source outlet 1304 generates the fluid meniscus 104.

[0064] In other embodiments of the proximity head 106, the processing surface of the proximity head 106 (the region of the proximity head where the source inlets and source outlets are located) may have any suitable topography depending on the configuration of the fluid meniscus to be generated. In one embodiment, the processing surface of the proximity head may be either indented or may protrude from the surrounding surface.

[0065] Figure 8B shows a top view of a portion of a proximity head 106 in accordance with one embodiment of the present invention. It should be appreciated that the configuration of the proximity head 106 as described in reference to Figure 8B is exemplary in nature. Therefore, other configurations of proximity heads may be utilized to generate the fluid meniscus as long as the processing fluid can be applied to a wafer surface and removed from the wafer surface to generate a stable fluid meniscus on the wafer surface. In addition, as discussed above, other embodiments of the proximity head 106 do not have to have the source inlet 1316 when the proximity head 106 is configured to generate the fluid meniscus without usage of N_2/IPA.

[0066] In the top view of one embodiment, from left to right are a set of the source inlet 1302, a set of the source outlet 1304, a set of the source inlet 1306, a set of the source outlet 1304, and a set of the source inlet 1302. Therefore, as N_2/IPA and processing chemistry are inputted into the region between the proximity head 106 and the wafer 108, the vacuum removes the N_2/IPA and the processing chemistry along with any fluid film and/or contaminants that may reside on the wafer 108. The source inlets 1302, the source inlets 1306, and the source outlets 1304 described herein may also be any suitable type of geometry such as for example, circular opening, triangle opening, square opening, etc. In one embodiment, the source inlets 1302 and 1306 and the source outlets 1304 have circular openings. It should be appreciated that the proximity head 106 may be any suitable size, shape, and/or configuration depending on the size and shape of the fluid meniscus 106 desired to generated. In one embodiment, the proximity head may extend less than a radius of the wafer. In another embodiment, the proximity head may be

extend more than the radius of the wafer. In another embodiment, the proximity head may extend greater than a diameter of the wafer. Therefore, the size of the fluid meniscus may be any suitable size depending on the size of a wafer surface area desired to be processed at any given time. In addition, it should be appreciated that the proximity head 106 may be positioned in any suitable orientation depending on the wafer processing operation such as, for example, horizontally, vertically, or any other suitable position in between. The proximity head 106 may also be incorporated into a wafer processing system where one or more types of wafer processing operations may be conducted.

[0067] Figure 8C illustrates an inlets/outlets pattern of a proximity head 106 in accordance with one embodiment of the present invention. In this embodiment, the proximity head 106 includes the source inlets 1302 and 1306 as well as source outlets 1304. In one embodiment, the source outlets 1304 may surround the source inlets 1306 and the source inlets 1302 may surround the source outlets 1304.

[0068] Figure 8D illustrates another inlets/outlets pattern of a proximity head 106 in accordance with one embodiment of the present invention. In this embodiment, the proximity head 106 includes the source inlets 1302 and 1306 as well as source outlets 1304. In one embodiment, the source outlets 1304 may surround the source inlets 1306 and the source inlets 1302 may at least partially surround the source outlets 1304.

[0069] Figure 8E illustrates a further inlets/outlets pattern of a proximity head 106 in accordance with one embodiment of the present invention. In this embodiment, the proximity head 106 includes the source inlets 1302 and 1306 as well as source outlets 1304. In one embodiment, the source outlets 1304 may surround the source inlets 1306. In one embodiment, the proximity head 106 does not include source inlets 1302 because, in one embodiment, the proximity head 106 is capable of generating a fluid meniscus without application of IPA/N_2. It should be appreciated that the above described inlets/outlets patterns are exemplary in nature and that any suitable type of inlets/outlets patterns may be used as long as a stable and controllable fluid meniscus can be generated.

[0070] While this invention has been described in terms of several preferable embodiments, it will be appreciated that those skilled in the art upon reading the preceding specifications and studying the drawings will realize various alterations, additions, permutations and equivalents thereof. It is therefore intended that the present

invention includes all such alterations, additions, permutations, and equivalents as fall within the true spirit and scope of the invention.

[0071] *What is claimed is:*

CLAIMS

1. A method for processing a substrate, comprising:

generating a fluid meniscus to process the substrate;

applying the fluid meniscus to a surface of the substrate; and

reducing evaporation of fluids from a surface in the substrate processing environment.

2. A method for processing a substrate as recited in claim 1, wherein reducing evaporation of fluids includes managing a substrate processing environment.

3. A method for processing a substrate as recited in claim 2, wherein managing the substrate processing environment comprises inputting a gas into the substrate processing environment to reduce an evaporation rate of fluids within the substrate processing environment.

4. A method for processing a substrate as recited in claim 3, wherein the gas has a high relative humidity.

5. A method for processing a substrate as recited in claim 4, wherein the gas with the high relative humidity is generated by transmitting gas into a liquid bath and capturing vapor that bubbles up through the liquid bath.

6. A method for processing a substrate as recited in claim 4, wherein the gas with the high relative humidity has a relative humidity between about 50% and about 100%.

7. A method for processing a substrate as recited in claim 4, wherein the gas with the high relative humidity has a relative humidity between about 90% and about 100%.

8. A method for processing a substrate as recited in claim 4, wherein the gas with the high relative humidity has a relative humidity of about 100%.

9. A method for processing a substrate as recited in claim 2, wherein managing the substrate processing environment further comprises detecting fluid thickness on the fluid surface.

10. A method for processing a substrate as recited in claim 3, wherein the gas maintains a concentration of a particular liquid in water.

11. A method for processing a substrate as recited in claim 10, wherein the particular liquid is one of an alcohol, an acetone, and an azeotropic mixture.

12. A method for processing a substrate as recited in claim 10, wherein the particular liquid is isopropyl alcohol (IPA).

13. A method for processing a substrate as recited in claim 10, wherein the gas that maintains a concentration of the particular liquid in water is an N_2 carrier gas containing isopropyl alcohol (IPA) in vapor form.

14. An apparatus for processing a substrate, comprising:

a proximity head capable of generating a fluid meniscus to process a substrate surface; and

a chamber configured to house the proximity head, the chamber also configured to be supplied with an environmental control gas.

15 An apparatus for processing a substrate as recited in claim 14 further omprising,

a wafer processing environment generator configured to generate the environmental control gas.

16. An apparatus for processing a substrate as recited in claim 14, wherein the wafer processing environment generator is a bubbler.

17. An apparatus for processing a substrate as recited in claim 16, wherein the bubbler is configured to input a gas into a liquid bath and further configured to capture the gas that has traveled through the liquid bath.

18. An apparatus for processing a substrate as recited in claim 14, wherein the environmental control gas is a high relative humidity gas.

19. An apparatus for processing a substrate as recited in claim 14, wherein the environmental control gas maintains a concentration of a particular liquid in water.

20. An apparatus for processing a substrate as recited in claim 19, wherein the particular liquid is one of isopropyl alcohol, DIW and IPA, alcohol, DIW and alcohol, ketone, and ether.

21. An apparatus for processing a substrate, comprising:

a proximity head capable of generating a fluid meniscus to process a substrate surface; and

an opening located on the surface of the proximity head configured to apply an environmental control gas to a region on a leading edge side of the proximity head.

22. An apparatus for processing a substrate as recited in claim 21, wherein the environmental control gas reduces an evaporation rate of fluids from a surface of the proximity head.

23. An apparatus for processing a substrate as recited in claim 21, wherein the environmental control gas is a high relative humidity gas.

24. An apparatus for processing a substrate as recited in claim 21, wherein the gas with a high relative humidity has a relative humidity between about 50% and about 100%.

25. An apparatus for processing a substrate as recited in claim 23, wherein the gas with the high relative humidity has a relative humidity between about 90% and about 100%.

26. An apparatus for processing a substrate as recited in claim 23, wherein the gas with the high relative humidity has a relative humidity of about 100%.

27. An apparatus for processing a substrate as recited in claim 21, wherein the environmental control gas maintains a concentration of a particular liquid in water.