

Abstract of the Disclosure

This invention provides a method of reactivating a catalyst for methacrylic acid production, which catalyst is used in production of methacrylic acid through vapor-phase oxidation of methacrolein or vapor-phase oxidative dehydrogenation of isobutyric acid, contains P and Mo, and exhibits reduced activity. The process comprises treating the catalyst, whose activity level has dropped (deteriorated catalyst), with a gas containing a nitrogen-containing heterocyclic compound (e.g., pyridine, piperidine, piperazine, quinoline).

This Sheet Has Been Replaced

