

Method for Making Photochromic Contact Lenses

This invention is related to a method for producing silicone hydrogel contact lenses having a central photochromic zone. This invention also provides silicone hydrogel contact lenses made according to a method of the invention.

BACKGROUND

Conventionally, UV-absorbing compounds have been incorporated into contact lenses to make UV-absorbing contact lenses to protect eyes from UV-radiations. Recently, there have been proposed various photochromic contact lenses for protecting eyes from UV-radiations (see, e.g., U.S. Pat. Nos. 4681412, 6017121, 6174464, 6224945, 7261844, 7368072, 7556750, 7560056, 7584630, 7641337, 7999989, 8158037, 8697770, 8741188, 9052438, 9097916, 9377569, 9465234, 9904074, 10197707). Those proposed photochromic contact lenses contains photochromic compounds which are capable of undergoing a reversible color change, e.g., from "clear" to blue or other color, upon exposure to UV/HEVL radiation.

Typically, photochromic contact lenses can be obtained by adding a photochromic compound in a polymerizable composition (i.e., lens formulation) for forming the contact lenses and then by curing the polymerizable composition in contact lens molds according to a cast-molding lens manufacturing process. A conventional cast-molding lens manufacturing process comprises: one single-step curing (polymerizing) of one single polymerizable composition (lens formulation) within disposable plastic molds typically consisting of two single-use mold halves; opening molds; optionally but preferably delensing (i.e., removing cast-molded lenses from the molds); and being subjected to various post-molding processes including extraction, hydration, packaging, and sterilization, etc.

However, photochromic contact lenses obtained according to such a conventional cast-molding process have photochromic compound incorporated uniformly within the polymer matrix of the photochromic contact lenses and are, from edge-to-edge, capable of undergoing a reversible color change upon exposure to UV/HEVL-radiation. Such photochromic contact lenses are not desirable for cosmetic reasons. It would be desirable to produce a photochromic contact lens that changes color only in the central pupil region.

U.S. Pat. Nos. 7368072, 7560056, 8697770 and 9904074 disclose methods for making photochromic contact lenses only the central pupillary regions of which can undergo a reversible color change upon exposure to UV/HEVL-radiation. Those methods comprise steps of: dosing a photochromic lens-forming composition onto the central region of the molding surface of a mold half and followed by adding a clear lens-forming composition on the top of the photochromic lens-forming composition, wherein the photochromic lens-forming composition has a viscosity much higher than the clear lens-forming composition;

ming with the other mold half to form a cavity with the photochromic and clear lens-forming compositions therewithin; and curing the photochromic and clear lens-forming compositions within the cavity of the mold to form the photochromic contact lens. However, handling and dosing of a high viscous photochromic lens-forming composition could be challenging in a production environment.

Therefore, there is still a need for a method for making photochromic silicone hydrogel contact lenses only the central pupillary regions of which can undergo a reversible color change upon exposure to UV/HEVL-radiation.

SUMMARY

The invention, in some aspects, provides a method for producing silicone hydrogel contact lenses, comprising the steps of: (1) obtain a first polymerizable fluid composition and a second polymerizable fluid composition, wherein the first polymerizable fluid composition comprises at least one free-radical initiator, at least one first polymerizable material, and at least one photochromic compound, wherein said at least one polymerizable material comprises at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 5000 Daltons or higher and is present in the first polymerizable composition in an amount of about 40% by weight or more, wherein the second polymerizable fluid composition comprises said at least one free-radical initiator and at least one second polymerizable material and is free of any photochromic compound; (2) obtaining a lens mold, wherein the lens mold comprises a male mold half having a first molding surface defining the posterior surface of a contact lens to be molded and a female mold half having a second molding surface defining the anterior surface of the contact lens to be molded, wherein the female and male mold halves are configured to receive each other such that a mold cavity is formed between the first and second molding surfaces when the mold is closed; (3) applying a drop of the first polymerizable fluid composition onto the geometrical center of the first molding of the male mold half, wherein the drop has a volume of about 5 μ L or less; (4) dispensing an amount of the second polymerizable fluid composition on the second molding surface of the female mold half; (5) closing the female mold half with the male mold half having the drop adhered thereon to form a molding assembly comprising the second polymerizable composition and the drop of the first polymerizable composition within the mold cavity; (6) curing the second polymerizable fluid composition and the drop of the first polymerizable composition to form an unprocessed silicone hydrogel contact lens having a central photochromic zone that has a diameter of about 13 mm or less, is concentric with the central axis of the unprocessed silicone hydrogel contact lens; (7) separating the molding assembly into the male and female mold halves, with the unprocessed silicone hydrogel contact lens adhered onto a lens-adhered mold half which is one of the male and female

mold halves; (8) removing the unprocessed silicone hydrogel contact lens from the lens-adhered mold half; and (9) subjecting the unprocessed silicone hydrogel contact lens to post-molding processes including a hydration process and one or more other processes selected from the group consisting of extraction, surface treatment, packaging, sterilization, and combinations thereof.

The invention, in other aspects, provides silicone hydrogel contact lenses produced according to a method of the invention

BRIEF DESCRIPTION OF DRAWINGS

Figure 1 schematically illustrates a hydrogel contact lens according to a preferred embodiment of the invention.

DETAILED DESCRIPTION

Unless defined otherwise, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. Generally, the nomenclature used herein and the laboratory procedures are well known and commonly employed in the art. Conventional methods are used for these procedures, such as those provided in the art and various general references. Where a term is provided in the singular, the inventors also contemplate the plural of that term. The nomenclature used herein and the laboratory procedures described below are those well known and commonly employed in the art.

"About" as used herein means that a number referred to as "about" comprises the recited number plus or minus 1-10% of that recited number.

"Optional" or "optionally" means that the subsequently described event or circumstance can or cannot occur, and that the description includes instances where the event or circumstance occurs and instances where it does not.

"Contact Lens" refers to a structure that can be placed on or within a wearer's eye. A contact lens can correct, improve, or alter a user's eyesight, but that need not be the case. A contact lens can be of any appropriate material known in the art or later developed, and can be a soft lens, a hard lens, or a hybrid lens.

A "hydrogel contact lens" refers to a contact lens comprising a hydrogel bulk (core) material. A hydrogel bulk material can be a non-silicone hydrogel material or preferably a silicone hydrogel (SiHy) material.

A "hydrogel" or "hydrogel material" refers to a crosslinked polymeric material which has three-dimensional polymer networks (i.e., polymer matrix), is insoluble in water, but can hold at least 10% by weight of water in its polymer matrix when it is fully hydrated (or equilibrated).

A “silicone hydrogel” or “SiHy” refers to a silicone-containing hydrogel obtained by copolymerization of a polymerizable composition comprising at least one silicone-containing vinylic monomer and/or at least one silicone-containing vinylic crosslinker.

A “siloxane” or “silicone”, as known to a person skilled in the art, interchangeably refers to a moiety of $-\text{Si}-\text{O}-\text{Si}-$ where each Si atom carries at least two substituents (organic groups) or a molecule having at least one moiety of $-\text{Si}-\text{O}-\text{Si}-$.

As used in this application, the term “non-silicone hydrogel” refers to a hydrogel that is theoretically free of silicon.

“Hydrophilic,” as used herein, describes a material or portion thereof that will more readily associate with water than with lipids.

A “vinylic monomer” refers to a compound that has one sole ethylenically unsaturated group, is soluble in a solvent, and can be polymerized actinically or thermally.

The term “soluble”, in reference to a compound or material in a solvent, means that the compound or material can be dissolved in the solvent to give a solution with a concentration of at least about 0.5% by weight at room temperature (i.e., a temperature of about 22°C to about 26°C).

The term “insoluble”, in reference to a compound or material in a solvent, means that the compound or material can be dissolved in the solvent to give a solution with a concentration of less than 0.01% by weight at room temperature (as defined above).

The term “ethylenically unsaturated group” is employed herein in a broad sense and is intended to encompass any groups containing at least one $>\text{C}=\text{C}<$ group. Exemplary

ethylenically unsaturated groups include without limitation (meth)acryloyl ($-\overset{\text{O}}{\underset{\text{||}}{\text{C}}}-\overset{\text{CH}_3}{\underset{\text{|}}{\text{C}}}=\text{CH}_2$ and/or $-\overset{\text{O}}{\underset{\text{||}}{\text{C}}}-\text{CH}=\text{CH}_2$), allyl, vinyl, styrenyl, or other $\text{C}=\text{C}$ containing groups.

As used herein, “actinically” in reference to curing, crosslinking or polymerizing of a polymerizable composition, a prepolymer or a material means that the curing (e.g., crosslinked and/or polymerized) is performed by actinic irradiation, e.g., UV/visible light irradiation, or the like. Thermal curing or actinic curing methods are well-known to a person skilled in the art.

An “acrylic monomer” refers to a vinylic monomer having one sole (meth)acryloyl group. Examples of acrylic monomers includes (meth)acryloxy [or(meth)acryloyloxy] monomers and (meth)acrylamido monomers.

An “(meth)acryloxy monomer” or “(meth)acryloyloxy monomer” refers to a vinylic monomer having one sole group of $-\text{O}-\overset{\text{O}}{\underset{\text{||}}{\text{C}}}-\overset{\text{CH}_3}{\underset{\text{|}}{\text{C}}}=\text{CH}_2$ or $-\text{O}-\overset{\text{O}}{\underset{\text{||}}{\text{C}}}-\text{CH}=\text{CH}_2$.

An “(meth)acrylamido monomer” refers to a vinylic monomer having one sole group

of $-\text{NR}^0-\overset{\text{O}}{\underset{\text{CH}_3}{\text{C}}}-\overset{\text{O}}{\text{C}}=\text{CH}_2$ or $-\text{NR}^0-\overset{\text{O}}{\text{C}}-\text{CH}=\text{CH}_2$ in which R^0 is H or $\text{C}_1\text{-C}_4$ alkyl.

The term “(meth)acrylamide” refers to methacrylamide and/or acrylamide.

The term “(meth)acrylate” refers to methacrylate and/or acrylate.

An “N-vinyl amide monomer” refers to an amide compound having a vinyl group ($-\text{CH}=\text{CH}_2$) that is directly attached to the nitrogen atom of the amide group.

An “ene monomer” refers to a vinylic monomer having one sole ene group.

A “hydrophilic vinylic monomer”, a “hydrophilic acrylic monomer”, a “hydrophilic (meth)acryloxy monomer”, or a “hydrophilic (meth)acrylamido monomer”, as used herein, respectively refers to a vinylic monomer, an acrylic monomer, a (meth)acryloxy monomer, or a (meth)acrylamido monomer, which typically yields a homopolymer that is water-soluble or can absorb at least 10 percent by weight of water.

A “hydrophobic vinylic monomer”, a “hydrophobic acrylic monomer”, a “hydrophobic (meth)acryloxy monomer”, or a “hydrophobic (meth)acrylamido monomer”, as used herein, respectively refers to a vinylic monomer, an acrylic monomer, a (meth)acryloxy monomer, or a (meth)acrylamido monomer, which typically yields a homopolymer that is insoluble in water and can absorb less than 10% by weight of water.

As used in this application, the term “vinylic crosslinker” refers to an organic compound having at least two ethylenically unsaturated groups. A “vinylic crosslinking agent” refers to a vinylic crosslinker having a molecular weight of 700 Daltons or less.

A “polysiloxane segment” or “polydiorganosiloxane segment” interchangeably refers

to a polymer chain segment (i.e., a divalent radical) of $\left[\begin{array}{c} \text{R}_{\text{S}1} \\ | \\ \text{Si}-\text{O} \\ | \\ \text{R}_{\text{S}2} \end{array} \right]_{\text{SN}} \begin{array}{c} \text{R}_{\text{S}1} \\ | \\ \text{Si}- \\ | \\ \text{R}_{\text{S}2} \end{array}$ in which SN is an integer of 3 or larger and each of $\text{R}_{\text{S}1}$ and $\text{R}_{\text{S}2}$ independent of one another are selected from the group consisting of: $\text{C}_1\text{-C}_{10}$ alkyl; phenyl; $\text{C}_1\text{-C}_4$ -alkyl-substituted phenyl; $\text{C}_1\text{-C}_4$ -alkoxy-substituted phenyl; phenyl- $\text{C}_1\text{-C}_6$ -alkyl; $\text{C}_1\text{-C}_{10}$ fluoroalkyl; $\text{C}_1\text{-C}_{10}$ fluoroether; aryl; aryl $\text{C}_1\text{-C}_{18}$ alkyl; $-\text{alk}-(\text{OC}_2\text{H}_4)_{\gamma 1}-\text{OR}^0$ (in which alk is $\text{C}_1\text{-C}_6$ alkylene diradical, R^0 is H or $\text{C}_1\text{-C}_4$ alkyl and $\gamma 1$ is an integer from 1 to 10); a $\text{C}_2\text{-C}_{40}$ organic radical having at least one functional group selected from the group consisting of hydroxyl group ($-\text{OH}$), carboxyl group ($-\text{COOH}$), amino linkages of $-\text{NR}_{\text{N}1}-$, amide linkages of $-\text{CONR}_{\text{N}1}-$, amide of $-\text{CONR}_{\text{N}1}\text{R}_{\text{N}1}'$, urethane linkages of $-\text{OCONH}-$, and $\text{C}_1\text{-C}_4$ alkoxy group, or a linear hydrophilic polymer chain, in which $\text{R}_{\text{N}1}$ and $\text{R}_{\text{N}1}'$ independent of each other are hydrogen or a $\text{C}_1\text{-C}_{15}$ alkyl.

A “polydiorganosiloxane vinylic crosslinker” or “polysiloxane vinylic crosslinker” interchangeably refers to a compound comprising at least one polysiloxane segment and at least two ethylenically-unsaturated groups.

A “linear polydiorganosiloxane vinylic crosslinker” or “linear polysiloxane vinylic crosslinker” interchangeably refers to a compound comprising a main chain which includes

at least one polysiloxane segment and is terminated with one ethylenically-unsaturated group at each of the two ends of the main chain.

A “chain-extended polydiorganosiloxane vinylic crosslinker” or “chain-extended polysiloxane vinylic crosslinker” interchangeably refers to a compound comprising at least two ethylenically-unsaturated groups and at least two polysiloxane segments each pair of which are linked by one divalent radical.

The term “photochromic vinylic monomer” refers to a vinylic monomer that has one colorless (or light-colored) form and one colored form and can undergo reversible change from the colorless form (or light-colored form) (or so-called “deactivated form”) to the colored form (or so-called “activated form”) upon exposure to UV/HEVL radiation.

The term “colorless or light-colored stated” or “inactivated state” in reference to a photochromic contact lens means the original state of the photochromic contact lens before the photochromic contact lens is irradiated with UV/HEVL light. In this state, the photochromic contact lens typically is colorless or shows a faint color as observed by a naked eye.

The term “colored stated” or “activated state” in reference to a photochromic contact lens means a state of the photochromic contact lens when the photochromic contact lens is being irradiated with UV/HEVL light. In this state, the photochromic contact lens typically shows a dark color as observed by a naked eye.

The term “fluid” as used herein indicates that a material is capable of flowing like a liquid.

As used in this application, the term “clear” in reference to a polymerizable composition means that the polymerizable composition is a transparent solution or liquid mixture having a light transmissibility of 85% or greater (preferably 90% or greater) in the range between 400 nm to 700 nm.

A free radical initiator can be either a photoinitiator or a thermal initiator. A “photoinitiator” refers to a chemical that initiates free radical crosslinking/polymerizing reaction by the use of UV and/or visible light. A “thermal initiator” refers to a chemical that initiates radical crosslinking/polymerizing reaction by the use of heat energy.

The term “acyl germanium photoinitiator” refers to an organogermanium compound that is a germanium-based Norrish Type I photoinitiator and comprises at least one acrylcarbonyl group connected to germanium. Examples of such acyl germanium photoinitiators are described in U.S. Pat. Nos. 7605190 and 10324311.

As used in this application, the term “polymer” means a material formed by polymerizing/crosslinking one or more monomers or macromers or prepolymers or combinations thereof.

A “macromer” or “prepolymer” refers to a compound or polymer that contains

ethylenically unsaturated groups and has a number average molecular weight of greater than 700 Daltons.

As used in this application, the term “molecular weight” of a polymeric material (including monomeric or macromeric materials) refers to the number-average molecular weight unless otherwise specifically noted or unless testing conditions indicate otherwise. A skilled person knows how to determine the molecular weight of a polymer according to known methods, e.g., GPC (gel permeation chromatography) with one or more of a refractive index detector, a low-angle laser light scattering detector, a multi-angle laser light scattering detector, a differential viscometry detector, a UV detector, and an infrared (IR) detector; MALDI-TOF MS (matrix-assisted desorption/ionization time-of-flight mass spectroscopy); ¹H NMR (Proton nuclear magnetic resonance) spectroscopy, etc.

The term “monovalent radical” refers to an organic radical that is obtained by removing a hydrogen atom from an organic compound and that forms one bond with one other group in an organic compound. Examples include without limitation, alkyl (by removal of a hydrogen atom from an alkane), alkoxy (or alkoxyl) (by removal of one hydrogen atom from the hydroxyl group of an alkyl alcohol), thiyl (by removal of one hydrogen atom from the thiol group of an alkylthiol), cycloalkyl (by removal of a hydrogen atom from a cycloalkane), cycloheteroalkyl (by removal of a hydrogen atom from a cycloheteroalkane), aryl (by removal of a hydrogen atom from an aromatic ring of the aromatic hydrocarbon), heteroaryl (by removal of a hydrogen atom from any ring atom), amino (by removal of one hydrogen atom from an amine), etc.

The term “divalent radical” refers to an organic radical that is obtained by removing two hydrogen atoms from an organic compound and that forms two bonds with other two groups in an organic compound. For example, an alkylene divalent radical (i.e., alkylenyl) is obtained by removal of two hydrogen atoms from an alkane, a cycloalkylene divalent radical (i.e., cycloalkylenyl) is obtained by removal of two hydrogen atoms from the cyclic ring.

In this application, the term “substituted” in reference to an alkyl or an alkylenyl means that the alkyl or the alkylenyl comprises at least one substituent which replaces one hydrogen atom of the alkyl or the alkylenyl and is selected from the group consisting of hydroxyl (-OH), carboxyl (-COOH), -NH₂, sulfhydryl (-SH), C₁-C₄ alkyl, C₁-C₄ alkoxy, C₁-C₄ alkylthio (alkyl sulfide), C₁-C₄ acylamino, C₁-C₄ alkylamino, di-C₁-C₄ alkylamino, and combinations thereof.

The term “terminal ethylenically-unsaturated group” refers to one ethylenically-unsaturated group at one of the two ends of the main chain (or backbone) of an organic compound as known to a person skilled in the art.

A “blending vinylic monomer” refers to a vinylic monomer capable of dissolving both hydrophilic and hydrophobic components of a polymerizable composition to form a solution.

"Post-curing surface treatment", in reference to a SiHy contact lens, means a surface treatment process that is performed after the SiHy contact lens is formed by curing (i.e., thermally or actinically polymerizing) a SiHy lens formulation.

The term "silicone hydrogel lens formulation" or "SiHy lens formulation" interchangeably refers to a polymerizable composition that comprises all necessary polymerizable components for producing a SiHy contact lens or a SiHy material as well known to a person skilled in the art.

A "UV-absorbing vinylic monomer" refers to a compound comprising an ethylenically-unsaturated group and a UV-absorbing moiety which can absorb or screen out UV radiation in the range from 200 nm to 400 nm as understood by a person skilled in the art.

A "HEVL-absorbing vinylic monomer" refers to a compound comprising an ethylenically-unsaturated group and a HEVL-absorbing moiety which can absorb or screen out HEVL (high-energy-violet-light) radiation in the range from 380 nm to 440 nm as understood by a person skilled in the art.

"UVA" refers to radiation occurring at wavelengths between 315 and 380 nanometers; "UVB" refers to radiation occurring between 280 and 315 nanometers; "Violet" refers to radiation occurring at wavelengths between 380 and 440 nanometers.

"UVA transmittance" (or "UVA %T"), "UVB transmittance" or "UVB %T", and "violet-transmittance" or "Violet %T" are calculated by the following formula.

$$\text{UVA \%T} = \text{Average \% Transmission between 315 nm and 380 nm} \times 100$$

$$\text{UVB \%T} = \text{Average \% Transmission between 280 nm and 315 nm} \times 100$$

$$\text{Violet \%T} = \text{Average \% Transmission between 380 nm and 440 nm} \times 100$$

The intrinsic "oxygen permeability", Dk_i , of a material is the rate at which oxygen will pass through a material. As used in this application, the term "oxygen permeability (Dk)" in reference to a hydrogel (silicone or non-silicone) or a contact lens means a corrected oxygen permeability (Dk_c) which is measured at about 34-35°C and corrected for the surface resistance to oxygen flux caused by the boundary layer effect according to the procedures described in ISO 18369-4. Oxygen permeability is conventionally expressed in units of barrers, where "barrer" is defined as $[(\text{cm}^3 \text{ oxygen})(\text{cm}) / (\text{cm}^2)(\text{sec})(\text{mm Hg})] \times 10^{-9}$.

The "oxygen transmissibility", Dk/t , of a lens or material is the rate at which oxygen will pass through a specific lens or material with an average thickness of t [in units of mm] over the area being measured. Oxygen transmissibility is conventionally expressed in units of barrers/mm, where "barrers/mm" is defined as $[(\text{cm}^3 \text{ oxygen})/(\text{cm}^2)(\text{sec})(\text{mm Hg})] \times 10^{-9}$.

The term "modulus" or "elastic modulus" in reference to a contact lens or a material means the tensile modulus or Young's modulus which is a measure of the stiffness of a contact lens or a material in tension. A person skilled in the art knows well how to determine the elastic modulus of a SiHy material or a contact lens. For example, all commercial contact

lenses have reported values of elastic modulus.

An "unprocessed state" refers to a contact lens which is obtained by cast-molding of a polymerizable composition in a mold and has not been subjected to extraction and/or hydration post-molding processes (i.e., having not been in contact with water or any organic solvent or any liquid after molding).

A "male mold half" or "base curve mold half" interchangeably refers to a mold half having a molding surface that is a substantially convex surface and that defines the posterior surface of a contact lens.

A "female mold half" or "front curve mold half" interchangeably refers to a mold half having a molding surface that is a substantially concave surface and that defines the anterior surface of a contact lens.

The term "anterior surface", "front surface", "front curve surface" or "FC surface" in reference to a contact lens, as used in this application, interchangeably means a surface of the contact lens that faces away from the eye during wear. The anterior surface (front surface) is typically substantially convex.

The "posterior surface", "back surface", "base curve surface" or "BC surface" in reference to a contact lens, as used in this application, interchangeably means a surface of the contact lens or insert that faces towards the eye during wear. The posterior surface (back surface) is typically substantially concave.

A "coating" in reference to a contact lens means that the contact lens has, on its surfaces, a thin layer of a material that is different from the bulk material of the contact lens and obtained by subjecting the contact lens to a surface treatment.

"Surface modification" or "surface treatment", as used herein, means that an article has been treated in a surface treatment process, in which (1) a coating is applied to the surface of the article, (2) chemical species are adsorbed onto the surface of the article, (3) the chemical nature (e.g., electrostatic charge) of chemical groups on the surface of the article are altered, or (4) the surface properties of the article are otherwise modified. Exemplary surface treatment processes include, but are not limited to, a surface treatment by energy (e.g., a plasma, a static electrical charge, radiation, or other energy source), chemical treatments, the grafting of hydrophilic vinylic monomers or macromers onto the surface of an article, mold-transfer coating process disclosed in U.S. Pat. No. 6719929, the incorporation of wetting agents into a lens formulation for making contact lenses proposed in U.S. Pat. Nos. 6367929 and 6822016, reinforced mold-transfer coating disclosed in U.S. Pat. No. 7858000, and a hydrophilic coating composed of covalent attachment or physical deposition of one or more layers of one or more hydrophilic polymer onto the surface of a contact lens disclosed in US Pat. Nos. 8147897, 8409599, 8557334, 8529057, and 9505184.

A “hydrophilic surface” in reference to a material or a contact lens means that the material or the contact lens has a surface hydrophilicity characterized by having an averaged water contact angle of about 90 degrees or less, preferably about 80 degrees or less, more preferably about 70 degrees or less, more preferably about 60 degrees or less.

An “average contact angle” refers to a water contact angle (static water contact angle measured by Sessile Drop), which is obtained by averaging measurements of at least 3 individual contact lenses.

The term “central axis” in reference to a contact lens means a line passing through the geometrical centers of the anterior and posterior surfaces of the contact lens.

In general, the invention is directed to a method for making contact lenses, in particular, SiHy contact lenses, each of which comprises a central photochromic zone that has a diameter of about 13 mm or less and is concentric with the central axis of the contact lens.

Figure 1 schematically illustrates a SiHy contact lens of the invention. The SiHy contact lens **100** has an anterior surface **102**, an opposite posterior surface, a central axis **101**, and a central zone **110** that has a diameter **120** and is concentric with the central axis **101** of the SiHy contact lens **100**. The central zone **110** comprises at least one photochromic compound that is distributed in its back portion **112** (a portion near and including a central portion of the posterior surface) and provides the photochromic functionality to the central zone.

The invention is partly based on the discovery that such contact lenses can be produced according to a process involving: applying, in the center of the molding surface of a male mold half, a drop of a first polymerizable fluid composition containing at least one photochromic compound and a relatively-high molecular weight polysiloxane vinylic crosslinker for increasing viscosity and adhesion on the molding surface of the male mold half; dosing a second polymerizable fluid composition in a female mold half; closing the female mold half with the male mold half with the drop thereon to form a molding assembly; and curing the second polymerizable fluid composition and the drop of the first polymerizable fluid composition in the molding assembly.

It is found that by selecting the averaged molecular weight and amount of a polysiloxane vinylic monomer, one can increase the viscosity of the first polymerizable fluid composition and its adhesion on the molding surface of a male mold half sufficiently to enable a drop of the first polymerizable composition adhered on the molding surface and not to diffuse into the second polymerizable fluid composition in the female mold half when the male and female mold halves are closed to form a molding assembly. can be achieved by controlling the amount of visible light irradiation exposed on the circular layer in the female mold half (e.g., through controlling the exposure time of the the actinic irradiation). Then, the

subsequent curing step will produce silicone hydrogel contact lenses, each of which comprises a central photochromic zone that has a diameter of about 13 mm or less and is concentric with the central axis of the unprocessed silicone hydrogel contact lens.

A method of the invention can offer the following advantages. First, a method of the invention can ensure the physical integrity of produced hydrogel contact lenses. It can also avoid issue of delamination. Further, the photochromic functionality is limited in the optical zone of a contact lens, i.e., over the pupil area of an eye when being worn. Any color associated with the photochromic functionality would have minimized adverse impacts upon the cosmetic aspect of the hydrogel contact lens.

The invention, in some aspects, provides a method for producing silicone hydrogel contact lenses, comprising the steps of: (1) obtain a first polymerizable fluid composition and a second polymerizable fluid composition, wherein the first polymerizable fluid composition comprises at least one free-radical initiator, at least one first polymerizable material, and at least one photochromic compound, wherein said at least one polymerizable material comprises at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 5000 Daltons or higher (preferably about 6000 Daltons or higher, more preferably about 8000 Daltons or higher, even more preferably about 10000 Daltons or higher) and is present in the first polymerizable composition in an amount of about 40% by weight or more (preferably about 45% by weight or more, more preferably about 50% by weight or more, even more preferably about 55% by weight or more), wherein the second polymerizable fluid composition comprises said at least one free-radical initiator and at least one second polymerizable material and is free of any photochromic compound; (2) obtaining a lens mold, wherein the lens mold comprises a male mold half having a first molding surface defining the posterior surface of a contact lens to be molded and a female mold half having a second molding surface defining the anterior surface of the contact lens to be molded, wherein the female and male mold halves are configured to receive each other such that a mold cavity is formed between the first and second molding surfaces when the mold is closed; (3) applying a drop of the first polymerizable fluid composition onto the geometrical center of the first molding of the male mold half, wherein the drop has a volume of about 5 μ L or less (preferably about 4.5 μ L or less, more preferably about 4.0 μ L or less, even more preferably about 3.5 μ L or less); (4) dispensing an amount of the second polymerizable fluid composition on the second molding surface of the female mold half; (5) closing the female mold half with the male mold half having the drop adhered thereon to form a molding assembly comprising the second polymerizable composition and the drop of the first polymerizable composition within the mold cavity; (6) curing the second polymerizable fluid composition and the drop of the first polymerizable composition to form an unprocessed silicone hydrogel contact lens having a central photochromic zone that has a diameter of

about 13 mm or less, is concentric with the central axis of the unprocessed silicone hydrogel contact lens; (7) separating the molding assembly into the male and female mold halves, with the unprocessed silicone hydrogel contact lens adhered onto a lens-adhered mold half which is one of the male and female mold halves; (8) removing the unprocessed silicone hydrogel contact lens from the lens-adhered mold half; and (9) subjecting the unprocessed silicone hydrogel contact lens to post-molding processes including a hydration process and one or more other processes selected from the group consisting of extraction, surface treatment, packaging, sterilization, and combinations thereof.

Any polymerizable materials known or suitable for forming silicone hydrogel contact lenses can be used in the invention.

In a preferred embodiment, said at least one first and second polymerizable materials are a monomer mixture comprising (a) at least one silicone-containing vinylic monomer, (b) said at least one first polysiloxane vinylic crosslinker, at least one second polysiloxane vinylic crosslinker, at least one non-silicone vinylic crosslinker, or combinations thereof, (c) at least one hydrophilic vinylic monomer, (d) at least one free-radical initiator, and optionally (e) at least one component selected from the group consisting of a non-silicone hydrophobic vinylic monomer, a UV-absorbing vinylic monomer, a polymerizable UV/HEVL-absorbing compound, and combinations thereof.

Any silicone-containing vinylic monomer can be used in the invention. Examples of preferred silicone-containing vinylic monomers can be silicone-containing (meth)acrylamido monomers, silicone-containing (meth)acryloxy monomers, silicone-containing vinylcarbonato monomers, or silicone-containing vinylcarbamate monomers, each of which comprises a bis(trialkylsilyloxy)alkylsilyl group, a tris(trialkylsilyloxy)-silyl group, or a polysiloxane chain having 2 to 30 siloxane units and terminated with an alkyl, hydroxyalkyl or methoxyalkyl group. Such preferred silicone-containing vinylic monomers can be obtained from the commercial suppliers, or alternatively prepared according to known procedures, e.g., similar to those described in U.S. Pat. Nos. 5070215, 6166236, 6867245, 7214809, 8415405, 8475529, 8614261, 8658748, 9097840, 9103965, 9217813, 9315669, and 9475827, or by reacting a vinylic monomer having a reactive functional group (e.g., an acid chloride, acid anhydride, carboxyl, hydroxyl, amino, epoxy, isocyanate, aziridine, azlactone, or aldehyde group) with a siloxane-containing compound a reactive group selected from the group consisting of a hydroxyalkyl, an aminoalkyl, an alkylaminoalkyl, a carboxyalkyl, an isocyanatoalkyl, an epoxyalkyl, and an aziridinylalkyl, in the presence or absence of a coupling agent under coupling reaction conditions well known to a person skilled in the art.

In a preferred embodiment, said at least one silicone-containing vinylic monomer comprises at least one silicone-containing (meth)acrylamido monomer having a bis(trialkylsilyloxy)alkylsilyl group, a tris(trialkylsilyloxy)silyl group, or a polysiloxane chain

having 2 to 30 siloxane units and terminated with an alkyl, hydroxyalkyl or methoxyalkyl group. Examples of such preferred silicone-containing (meth)acrylamido monomers include without limitation those described later in this application.

In another preferred embodiment, said at least one silicone-containing vinylic monomer comprises at least one silicone-containing (meth)acryloxy monomer having a bis(trialkylsilyloxy)alkylsilyl group, a tris(trialkylsilyloxy)silyl group, or a polysiloxane chain having 2 to 30 siloxane units and terminated with an alkyl, hydroxyalkyl or methoxyalkyl group. Examples of such preferred silicone-containing (meth)acryloxy monomers include without limitation those described later in this application.

In accordance with the invention, said at least one first and second polysiloxane vinylic crosslinkers are different from each other and can be any polysiloxane vinylic crosslinkers. Examples of preferred polysiloxane vinylic crosslinkers include without limitation α,ω -(meth)acryloxy-terminated polydimethylsiloxanes; α,ω -(meth)acrylamido-terminated polydimethylsiloxanes; α,ω -vinyl carbonate-terminated polydimethylsiloxanes; α,ω -vinyl carbamate-terminated polydimethylsiloxanes; bis-3-methacryloxy-2-hydroxypropyloxypropyl polydimethylsiloxanes; the reaction products of glycidyl methacrylate with amino-functional polydimethylsiloxanes; the reaction products of an azlactone-containing vinylic monomer (any one of those described above) with hydroxyl-functional polydimethylsiloxanes; polysiloxane-containing macromer selected from the group consisting of Macromer A, Macromer B, Macromer C, and Macromer D described in US 5,760,100; polysiloxane vinylic crosslinkers disclosed in U.S. Pat. Nos. 4136250, 4153641, 4182822, 4189546, 4259467, 4260725, 4261875, 4343927, 4254248, 4355147, 4276402, 4327203, 4341889, 4486577, 4543398, 4605712, 4661575, 4684538, 4703097, 4833218, 4837289, 4954586, 4954587, 5010141, 5034461, 5070170, 5079319, 5039761, 5346946, 5358995, 5387632, 5416132, 5449729, 5451617, 5486579, 5962548, 5981675, 6039913, 6762264, 7423074, 8163206, 8480227, 8529057, 8835525, 8993651, 9,187,601, 10081697, 10301451, and 10465047.

One class of preferred polysiloxane vinylic crosslinkers are di-(meth)acryloyloxy-terminated polysiloxane vinylic crosslinkers each having dimethylsiloxane units and hydrophilized siloxane units each having one methyl substituent and one monovalent C_4-C_{40} organic radical substituent having 2 to 6 hydroxyl groups, more preferably a polysiloxane vinylic crosslinker of formula (H), are described later in this application and can be prepared according to the procedures disclosed in U.S. Pat. No. 10081697.

Another class of preferred polysiloxane vinylic crosslinkers are vinylic crosslinkers each of which comprises one sole polydiorganosiloxane segment and two terminal (meth)acryloyl groups, which can be obtained from commercial suppliers; prepared by reacting glycidyl (meth)acrylate (meth)acryloyl chloride with a di-amino-terminated

polydimethylsiloxane or a di-hydroxyl-terminated polydimethylsiloxane; prepared by reacting isocyanatoethyl (meth)acrylate with di-hydroxyl-terminated polydimethylsiloxanes prepared by reacting an amino-containing acrylic monomer with di-carboxyl-terminated polydimethylsiloxane in the presence of a coupling agent (a carbodiimide); prepared by reacting a carboxyl-containing acrylic monomer with di-amino-terminated polydimethylsiloxane in the presence of a coupling agent (a carbodiimide); or prepared by reacting a hydroxyl-containing acrylic monomer with a di-hydroxy-terminated polydisiloxane in the presence of a diisocyanate or di-epoxy coupling agent.

Other classes of preferred polysiloxane vinylic crosslinkers are chain-extended polysiloxane vinylic crosslinkers each of which has at least two polydiorganosiloxane segments linked by a linker between each pair of polydiorganosiloxane segments and two terminal ethylenically unsaturated groups, which can be prepared according to the procedures described in U.S. Pat. Nos. 5034461, 5416132, 5449729, 5760100, 7423074, 8529057, 8835525, 8993651, 9187601, 10301451, and 10465047.

Any non-silicone vinylic crosslinkers can be used in the invention. Examples of preferred non-silicone vinylic crosslinkers are described later in this application.

Any hydrophilic vinylic monomer can be used in the invention. Examples of preferred hydrophilic vinylic monomers are hydrophilic (meth)acrylamido monomer (as described later in this application), hydrophilic (meth)acryloxy monomer (as described later in this application), hydrophilic N-vinyl amide monomer (as described later in this application), methylene-containing pyrrolidone monomers (i.e., pyrrolidone derivatives each having a methylene group connected to the pyrrolidone ring at 3- or 5- position) (as described later in this application), vinyl ether monomers (as described later in this application), allyl ether monomers (as described later in this application), phosphorylcholine-containing vinylic monomers (as described later in this application), allyl alcohol, N-2-hydroxyethyl vinyl carbamate, N-vinyloxycarbonyl- β -alanine (VINAL), N-vinyloxycarbonyl- α -alanine, and combinations thereof.

In another preferred embodiment, said at least one hydrophilic vinylic monomer comprises at least one hydrophilic (meth)acrylamido monomer, preferably having 3 to 10 carbon atoms. Examples of preferred hydrophilic (meth)acrylamido monomers are described later in this application. It is believed that such hydrophilic (meth)acrylamido monomers can be used in increasing the glass transition temperature of a resultant silicone hydrogel material. It is also understood that any hydrophilic (meth)acrylamido monomers other than those specifically described later in this application can also be used in this invention.

In another preferred embodiment, said at least one hydrophilic vinylic monomer comprises at least one hydrophilic N-vinyl amide monomer. Examples of preferred hydrophilic N-vinyl amide monomers are described later in this application. It is understood

that any hydrophilic N-vinyl amide monomers other than those specifically described later in this application can also be used in this invention.

In another preferred embodiment, said at least one hydrophilic vinylic monomer comprises at least one hydrophilic (meth)acryloxy monomer, preferably having 3 to 10 carbon atoms. Examples of preferred hydrophilic (meth)acryloxy monomers are described later in this application. It is understood that any hydrophilic (meth)acryloxy monomers other than those specifically described later in this application can also be used in this invention.

In a preferred embodiment, the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 60% (preferably at least about 65%, more preferably at least about 70%, even more preferably at least about 75%) by weight relative to the total weight of all polymerizable materials in the first polymerizable fluid composition.

A free radical initiator can be either a photoinitiator or a thermal initiator. A "photoinitiator" refers to a chemical that initiates free radical crosslinking/polymerizing reaction by the use of light. A "thermal initiator" refers to a chemical that initiates free radical crosslinking/polymerizing reaction by the use of heat energy.


Any free-radical photoinitiators can be used in the invention. Examples of suitable free-radical photoinitiators include without limitation benzoin methyl ether, diethoxyacetophenone, a benzoylphosphine oxide, 1-hydroxycyclohexyl phenyl ketone and Darocur and Irgacur types, preferably Darocur 1173® and Darocur 2959®, Germanium-based Norrish Type I photoinitiators (e.g., those described in US 7,605,190). Examples of benzoylphosphine initiators include 2,4,6-trimethylbenzoyldiphenylphosphine oxide; bis-(2,6-dichlorobenzoyl)-4-N-propylphenylphosphine oxide; and bis-(2,6-dichlorobenzoyl)-4-N-butylphenylphosphine oxide. Reactive photoinitiators which can be incorporated, for example, into a macromer or can be used as a special monomer are also suitable. Examples of reactive photoinitiators are those disclosed in EP 632 329.

In a preferred embodiment, visible light free-radical photoinitiators are used in the invention. It is believed that the irradiation of visible lights would cause minimized degradation to a photochromic compound. Examples of preferred visible light free-radical photoinitiators include without limitation acylgermanium photoinitiators, benzoylphosphine oxide, acylphosphinate salts, and the likes.

Examples of benzoylphosphine initiators include 2,4,6-trimethylbenzoyldiphenylphosphine oxide; bis-(2,6-dichlorobenzoyl)-4-N-propylphenylphosphine oxide; and bis-(2,6-dichlorobenzoyl)-4-N-butylphenylphosphine oxide. One example of water-soluble acylphosphinate salts is Lithium phenyl (2,4,6-trimethylbenzoyl) phosphinate, available from Tokyo Chemical Industry Co., Ltd.

Any acylgermanium photoinitiators can be used in this invention, so long as they are capable of initiating a free-radical polymerization under irradiation with a light source

including a light in the region of about 420 to about 500 nm. Examples of acylgermanium photoinitiators are acylgermanium compounds described in U.S. Pat. No. 7605190. Preferably, said at least one first and/or second free-radical initiator comprises at least one of the following acylgermanium compounds.



Any thermal free-radical initiators can be used in the invention. Suitable thermal free-radical initiators are known to the skilled artisan and comprise, for example peroxides, hydroperoxides, azo-bis(alkyl- or cycloalkylnitriles), persulfates, percarbonates, or mixtures thereof. Examples of preferred thermal free-radical initiators include without limitation benzoyl peroxide, t-butyl peroxide, t-amyl peroxybenzoate, 2,2-bis(tert-butylperoxy)butane, 1,1-bis(tert-butylperoxy)cyclohexane, 2,5-Bis(tert-butylperoxy)-2,5-dimethylhexane, 2,5-bis(tert-butylperoxy)-2,5-dimethyl-3-hexyne, bis(1-(tert-butylperoxy)-1-methylethyl)benzene, 1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane, di-t-butyl-diperoxyphthalate, t-butyl hydroperoxide, t-butyl peracetate, t-butyl peroxybenzoate, t-butylperoxy isopropyl carbonate, acetyl peroxide, lauroyl peroxide, decanoyl peroxide, dicetyl peroxydicarbonate, di(4-t-butylcyclohexyl)peroxy dicarbonate (Perkadox 16S), di(2-ethylhexyl)peroxy dicarbonate, t-butylperoxy pivalate (Lupersol 11); t-butylperoxy-2-ethylhexanoate (Trigonox 21-C50), 2,4-pentanedione peroxide, dicumyl peroxide, peracetic acid, potassium persulfate, sodium persulfate, ammonium persulfate, 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile) (VAZO 33), 2,2'-Azobis[2-(2-imidazolin-2-yl)propane]dihydrochloride (VAZO 44), 2,2'-azobis(2-amidinopropane) dihydrochloride (VAZO 50), 2,2'-azobis(2,4-dimethylvaleronitrile) (VAZO 52), 2,2'-azobis(isobutyronitrile) (VAZO 64 or AIBN), 2,2'-azobis-2-methylbutyronitrile (VAZO 67), 1,1-azobis(1-cyclohexanecarbonitrile) (VAZO 88); 2,2'-azobis(2-cyclopropylpropionitrile), 2,2'-azobis(methylisobutyrate), 4,4'-Azobis(4-cyanovaleric acid), and combinations thereof. Preferably, the thermal free-radical initiator is 2,2'-azobis(isobutyronitrile) (AIBN or VAZO 64).

Any non-silicone hydrophobic vinylic monomers can be used in the invention. Examples of preferred hydrophobic non-silicone vinylic monomers can be non-silicone hydrophobic acrylic monomers (e.g., alkyl (meth)acrylates as described below, cycloalkyl (meth)acrylates as described below, phenyl methacrylate, (meth)acrylonitrile, etc.), fluorine-containing acrylic monomers (e.g., perfluorohexylethyl-thio-carbonyl-aminoethyl-methacrylate, perfluoro-substituted-C₂-C₁₂ alkyl (meth)acrylates described below, etc.), vinyl alkanooates (e.g., vinyl acetate, vinyl propionate, vinyl butyrate, vinyl valerate, etc.), vinyloxy-alkanes (e.g., vinyl ethyl ether, propyl vinyl ether, n-butyl vinyl ether, isoputyl vinyl ether,

cyclohexyl vinyl ether, t-butyl vinyl ether, etc.), substituted or unsubstituted styrenes as described below, vinyl toluene, vinyl chloride, vinylidene chloride, 1-butene, and mixtures thereof.

Any suitable perfluoro-substituted-C₂-C₁₂ alkyl (meth)acrylates can be used in the invention. Examples of perfluoro-substituted-C₂-C₁₂ alkyl (meth)acrylates include without limitation 2,2,2-trifluoroethyl (meth)acrylate, tetrafluoropropyl (meth)acrylate, hexafluoro-isopropyl (meth)acrylate, hexafluorobutyl (meth)acrylate, heptafluorobutyl (meth)acrylate, octafluoropentyl (meth)acrylate, heptadecafluorodecyl (meth)acrylate, pentafluorophenyl (meth)acrylate, and combinations thereof.

In a preferred embodiment, one or more hydrophobic non-silicone acrylic monomers and/or substituted or unsubstituted styrenes can be used in the invention as a reactive diluent (i.e., a blending vinylic monomer) for solubilizing other polymerizable components in a polymerizable composition of the invention.

Examples of such non-silicone hydrophobic acrylic monomers and substituted or unsubstituted styrenes include methyl methacrylate, ethyl methacrylate, isopropyl methacrylate, sec-butyl methacrylate, tert-butyl methacrylate, cyclohexyl methacrylate, isobornyl acrylate, isobornyl methacrylate, phenyl methacrylate, 4-tert-butylstyrene, 2-methylstyrene, styrene, 4-ethoxystyrene, 2,4-dimethylstyrene, 2,5-dimethylstyrene, 3,5-dimethylstyrene, and combinations thereof. More preferably, methyl methacrylate, tert-butyl methacrylate, cyclohexyl methacrylate, isobornyl acrylate, isobornyl methacrylate, or a combination thereof is used in the invention. Even more preferably, methyl methacrylate, tert-butyl methacrylate, cyclohexyl methacrylate, or a combination thereof is used in the invention.

The term "UV/HEVL-absorbing vinylic monomer" refers to a vinylic monomer that can absorb UV light and high-energy-violet-light (i.e., light having wavelength between 380 nm and 440 nm). Examples of UV-absorbing vinylic monomers and UV/HEVL-absorbing vinylic monomers are known to a person skilled in the art and are disclosed in the patents and patent application publications, e.g., US9315669, US 2018-0081197 A1, etc.

Any suitable UV-absorbing vinylic monomers and UV/HEVL-absorbing vinylic monomers can be used in the invention. Examples of preferred UV-absorbing and UV/HEVL-absorbing vinylic monomers include without limitation: 2-(2-hydroxy-5-vinylphenyl)-2H-benzotriazole, 2-(2-hydroxy-5-acryloyloxyphenyl)-2H-benzotriazole, 2-(2-hydroxy-3-methacrylamido methyl-5-tert octylphenyl) benzotriazole, 2-(2'-hydroxy-5'-methacrylamidophenyl)-5-chlorobenzotriazole, 2-(2'-hydroxy-5'-methacrylamidophenyl)-5-methoxybenzotriazole, 2-(2'-hydroxy-5'-methacryloxy-propyl-3'-t-butyl-phenyl)-5-chlorobenzotriazole, 2-(2'-hydroxy-5'-methacryloxypropylphenyl) benzotriazole, 2-hydroxy-5-methoxy-3-(5-(trifluoromethyl)-2H-benzo[d][1,2,3]triazol-2-yl)benzyl methacrylate (WL-1), 2-

hydroxy-5-methoxy-3-(5-methoxy-2H-benzo[d][1,2,3]triazol-2-yl)benzyl methacrylate (WL-5), 3-(5-fluoro-2H-benzo[d][1,2,3]triazol-2-yl)-2-hydroxy-5-methoxybenzyl methacrylate (WL-2), 3-(2H-benzo[d][1,2,3]triazol-2-yl)-2-hydroxy-5-methoxybenzyl methacrylate (WL-3), 3-(5-chloro-2H-benzo[d][1,2,3]triazol-2-yl)-2-hydroxy-5-methoxybenzyl methacrylate (WL-4), 2-hydroxy-5-methoxy-3-(5-methyl-2H-benzo[d][1,2,3]triazol-2-yl)benzyl methacrylate (WL-6), 2-hydroxy-5-methyl-3-(5-(trifluoromethyl)-2H-benzo[d][1,2,3]triazol-2-yl)benzyl methacrylate (WL-7), 4-allyl-2-(5-chloro-2H-benzo[d][1,2,3]triazol-2-yl)-6-methoxy-phenol (WL-8), 2-{2'-Hydroxy-3'-*tert*-5'-[3''-(4''-vinylbenzyloxy)propoxy]phenyl}-5-methoxy-2*H*-benzotriazole, phenol, 2-(5-chloro-2*H*-benzotriazol-2-yl)-6-(1,1-dimethylethyl)-4-ethenyl- (UVAM), 2-{2'-hydroxy-5'-(2-methacryloxyethyl)phenyl}-2H-benzotriazole (2-Propenoic acid, 2-methyl-, 2-[3-(2*H*-benzotriazol-2-yl)-4-hydroxyphenyl]ethyl ester, Norbloc), 2-{2'-Hydroxy-3'-*tert*-butyl-5'-[3'-methacryloyloxypropoxy]phenyl}-2*H*-benzotriazole, 2-{2'-Hydroxy-3'-*tert*-butyl-5'-[3'-methacryloyloxypropoxy]phenyl}-5-methoxy-2*H*-benzotriazole (UV13), 2-{2'-Hydroxy-3'-*tert*-butyl-5'-[3'-methacryloyloxypropoxy]phenyl}-5-chloro-2*H*-benzotriazole (UV28), 2-{2'-Hydroxy-3'-*tert*-butyl-5'-(3'-acryloyloxypropoxy)phenyl}-5-trifluoromethyl-2*H*-benzotriazole (UV23), 2-(2'-hydroxy-5-methacrylamidophenyl)-5-methoxybenzotriazole (UV6), 2-(3-allyl-2-hydroxy-5-methylphenyl)-2*H*-benzotriazole (UV9), 2-(2-Hydroxy-3-methyl-5-methylphenyl)-2*H*-benzotriazole (UV12), 2-3'-*t*-butyl-2'-hydroxy-5'-(3''-dimethylvinylsilylpropoxy)-2'-hydroxy-phenyl)-5-methoxybenzotriazole (UV15), 2-(2'-hydroxy-5'-methacryloylpropyl-3'-*tert*-butyl-phenyl)-5-methoxy-2*H*-benzotriazole (UV16), 2-(2'-hydroxy-5'-acryloylpropyl-3'-*tert*-butyl-phenyl)-5-methoxy-2*H*-benzotriazole (UV16A), 2-Methylacrylic acid 3-[3-*tert*-butyl-5-(5-chlorobenzotriazol-2-yl)-4-hydroxyphenyl]-propyl ester (16-100, CAS#96478-15-8), 2-(3-(*tert*-butyl)-4-hydroxy-5-(5-methoxy-2H-benzo[d][1,2,3]triazol-2-yl)phenoxy)ethyl methacrylate (16-102); Phenol, 2-(5-chloro-2*H*-benzotriazol-2-yl)-6-methoxy-4-(2-propen-1-yl) (CAS#1260141-20-5); 2-[2-Hydroxy-5-[3-(methacryloyloxy)propyl]-3-*tert*-butylphenyl]-5-chloro-2*H*-benzotriazole; Phenol, 2-(5-ethenyl-2H-benzotriazol-2-yl)-4-methyl-, homopolymer (9CI) (CAS#83063-87-0). In accordance with the invention, the polymerizable composition comprises about 0.1% to about 3.0%, preferably about 0.2% to about 2.5%, more preferably about 0.3% to about 2.0%, by weight of one or more UV-absorbing vinylic monomers, related to the amount of all polymerizable components in the polymerizable composition.

A first and second polymerizable fluid compositions of the invention can also comprise other necessary components known to a person skilled in the art, such as, for example, visibility tinting agent (e.g., one or more polymerizable dyes, pigments, or mixtures thereof), antimicrobial agents (e.g., silver nanoparticles), a bioactive agent (e.g., a drug, an amino acid, a polypeptide, a protein, a nucleic acid, 2-pyrrolidone-5-carboxylic acid (PCA), an alpha hydroxyl acid, linoleic and gamma linoleic acids, vitamins, or any combination thereof), leachable lubricants (e.g., a non-crosslinkable hydrophilic polymer having an

average molecular weight from 5,000 to 500,000, preferably from 10,000 to 300,000, more preferably from 20,000 to 100,000 Daltons), leachable tear-stabilizing agents (e.g., a phospholipid, a monoglyceride, a diglyceride, a triglyceride, a glycolipid, a glyceroglycolipid, a sphingolipid, a sphingo-glycolipid, a fatty acid having 8 to 36 carbon atoms, a fatty alcohol having 8 to 36 carbon atoms, or a mixture thereof), mold releasing agent, and mixtures thereof, as known to a person skilled in the art.

In accordance with the invention, the first and second polymerizable fluid compositions of the invention can be a solution, a solventless blend (i.e., a fluid composition free of any non-reactive diluent - organic solvent). It can be prepared according to any techniques known to a person skilled in the art.

A first or second polymerizable fluid composition of the invention can also be prepared from any known silicone hydrogel lens formulations. For example, a first polymerizable fluid composition can be prepared by adding at least one photochromic compound and at least one first polysiloxane vinylic crosslinker into any one of the known silicone hydrogel (SiHy) lens formulations, whereas a second polymerizable fluid composition can be any one of the known SiHy lens formulations.

Numerous SiHy lens formulations have been described in numerous patents and patent applications published by the filing date of this application and have been used in producing commercial SiHy contact lenses. Examples of commercial SiHy contact lenses include, without limitation, asmoofilcon A, balafilcon A, comofilcon A, delefilcon A, eprofilcon A, enfilcon A, fanfilcon A, galyfilcon A, lotrafilcon A, lotrafilcon B, naraofilcon A, naraofilcon B, senofilcon A, senofilcon B, senofilcon C, smaofilcon A, somofilcon A, stenfilcon A, etc..

Where a first or second polymerizable fluid composition of the invention is a solution, it can be prepared by dissolving all of the desirable components in any suitable solvent known to a person skilled in the art. Example of suitable solvents includes without limitation, water, tetrahydrofuran, tripropylene glycol methyl ether, dipropylene glycol methyl ether, ethylene glycol n-butyl ether, ketones (e.g., acetone, methyl ethyl ketone, etc.), diethylene glycol n-butyl ether, diethylene glycol methyl ether, ethylene glycol phenyl ether, propylene glycol methyl ether, propylene glycol methyl ether acetate, dipropylene glycol methyl ether acetate, propylene glycol n-propyl ether, dipropylene glycol n-propyl ether, tripropylene glycol n-butyl ether, propylene glycol n-butyl ether, dipropylene glycol n-butyl ether, tripropylene glycol n-butyl ether, propylene glycol phenyl ether dipropylene glycol dimethyl ether, polyethylene glycols, polypropylene glycols, ethyl acetate, butyl acetate, amyl acetate, methyl lactate, ethyl lactate, i-propyl lactate, methylene chloride, 2-butanol, 1-propanol, 2-propanol, menthol, cyclohexanol, cyclopentanol and exonorborneol, 2-pentanol, 3-pentanol, 2-hexanol, 3-hexanol, 3-methyl-2-butanol, 2-heptanol, 2-octanol, 2-nonanol, 2-decanol, 3-octanol, norborneol, tert-butanol, tert-amyl, alcohol, 2-methyl-2-pentanol, 2,3-dimethyl-2-

butanol, 3-methyl-3-pentanol, 1-methylcyclohexanol, 2-methyl-2-hexanol, 3,7-dimethyl-3-octanol, 1-chloro-2-methyl-2-propanol, 2-methyl-2-heptanol, 2-methyl-2-octanol, 2,2-methyl-2-nonanol, 2-methyl-2-decanol, 3-methyl-3-hexanol, 3-methyl-3-heptanol, 4-methyl-4-heptanol, 3-methyl-3-octanol, 4-methyl-4-octanol, 3-methyl-3-nonanol, 4-methyl-4-nonanol, 3-methyl-3-octanol, 3-ethyl-3-hexanol, 3-methyl-3-heptanol, 4-ethyl-4-heptanol, 4-propyl-4-heptanol, 4-isopropyl-4-heptanol, 2,4-dimethyl-2-pentanol, 1-methylcyclopentanol, 1-ethylcyclopentanol, 1-ethylcyclopentanol, 3-hydroxy-3-methyl-1-butene, 4-hydroxy-4-methyl-1-cyclopentanol, 2-phenyl-2-propanol, 2-methoxy-2-methyl-2-propanol 2,3,4-trimethyl-3-pentanol, 3,7-dimethyl-3-octanol, 2-phenyl-2-butanol, 2-methyl-1-phenyl-2-propanol and 3-ethyl-3-pentanol, 1-ethoxy-2-propanol, 1-methyl-2-propanol, t-amyl alcohol, isopropanol, 1-methyl-2-pyrrolidone, N,N-dimethylpropionamide, dimethyl formamide, dimethyl acetamide, dimethyl propionamide, N-methyl pyrrolidinone, and mixtures thereof. Preferably, a polymerizable composition is a solution of all the desirable components in water, 1,2-propylene glycol, a polyethyleneglycol having a molecular weight of about 400 Daltons or less, or a mixture thereof.

Where a first or second polymerizable fluid composition of the invention is a solventless blend, it can be prepared by mixing all polymerizable components and other necessary component. A solventless polymerizable composition typically comprises at least one blending vinylic monomer as a reactive solvent for dissolving all other polymerizable components of the solventless polymerizable composition. Examples of preferred blending vinylic monomers are described above and later in this application. Preferably, methyl methacrylate is used as a blending vinylic monomer in preparing a solventless polymerizable composition.

Any polymerizable photochromic compounds can be used in this invention. Examples of preferred polymerizable photochromic compounds include polymerizable naphthopyrans, polymerizable benzopyrans, polymerizable indenonaphthopyrans, polymerizable phenanthropyrans, polymerizable spiro(benzindoline)-naphthopyrans, polymerizable spiro(indoline)benzopyrans, polymerizable spiro(indoline)-naphthopyrans, polymerizable spiro(indoline)quinopyrans, polymerizable spiro(indoline)-pyrans, polymerizable naphthoxazines, polymerizable spirobenzopyrans; polymerizable spirobenzopyrans, polymerizable spirobenzothiopyrans, polymerizable naphthacenediones, polymerizable spirooxazines, polymerizable spiro(indoline)naphthoxazines, polymerizable spiro(indoline)pyridobenzoxazines, polymerizable spiro(benzindoline)pyridobenzoxazines, polymerizable spiro(benzindoline)naphthoxazines, polymerizable spiro(indoline)-benzoxazines, polymerizable diarylethenes, and combinations thereof, as disclosed in U.S. Pat. Nos. 4929693, 5166345 6017121, 7556750, 7584630, 7999989, 8158037, 8697770, 8741188, 9052438, 9097916, 9465234, 9904074, 10197707, 6019914, 6113814, 6149841,

6296785, and 6348604.

Various photochromic compounds are disclosed in the patents and published patent applications and can be obtained from commercial sources or prepared by following the procedures described in the patents and literatures. Examples of preferred photochromic compounds include without limitation naphthopyrans, indeno-fused naphthopyrans (i.e., indeno-naphthopyrans), heterocyclic ring-fused naphthopyrans, benzopyrans, phenanthropyrans, quinopyrans, quinolinopyrans, fluoroanthenopyrans, anthracene-fused pyrans, tetracene-fused pyrans, spiro(benzindoline)naphthopyrans, spiro(indoline)naphthopyrans, spiro(indoline)-benzopyrans, spiro(indoline)quinopyrans, spiro(indoline)pyrans, naphthoxazines, spirobenzopyrans, spirobenzothiopyrans, naphthacenediones, benzoxazines, spirooxazines, naphthoxazines, spiro(benzindoline)naphthoxazines, spiro(indoline)naphthoxazines, spiro(indoline)pyrido-benzoxazines, spiro(indoline) benzoxazines, spiro(benzindoline)-benzoxazines, spiro(benzindoline)pyridobenzoxazines, spiro(indoline)fluoranthenoxazines, spiro(indoline)-quinoxazines, spiro(piperidine-naphthopyrans, piro(indoline)pyronobenzo-xazinones, benzospiropyrans, naphthospiropyrans, spirobenzoxazine-pyrrolopyridines, spironaphthoxazine-pyrrolopyridines, spiro-oxazepin-benzoxazines, spiro-oxazepin-naphthoxazines, spiro(indoline)benzothiazoloxazines, spiro(indoline)benzopyrroloxazines, spiro(indoline)quinazolino-oxazines, spiro(indoline)-anthracenobenzoxazines, benzofuro-benzopyrans, benzothienobenzopyrans, naphthofurobenzopyrans, benzopyrano-fusednaphthopyrans, spiro(isoindoline)-naphthoxazines, spiro(isoindoline)benzoxazines, etc. Such photochromic compounds are disclosed in U.S. Pat. Nos. 3100778, 3562172, 3567605, 3578602, 3671543, 4215010, 4342668, 4440672, 4634767, 4636561, 4637698, 4699473, 4719296, 4720547, 4772700, 4784474, 4785097, 4816584, 4818096, 4826977, 4831142, 4880667, 4929693, 4931219, 4931221, 4959471, 4980089, 4986934, 5055576, 5066818, 5110922, 5114621, 5139707, 5166345, 5171636, 5180524, 5186867, 5200116, 5238931, 5238981, 5244602, 5274132; 5340857, 5369158, 5384077, 5395567, 5399687, 5405958, 5411679, 5429774, 5451344, 5458814; 5458815, 5464567, 5466398, 5514817; 5520853, 5552090, 5552091, 5565147, 5573712; 5578252, 5585042, 5623005, 5637262, 5637709, 5645767; 5650098, 5651923, 5656206; 5658500, 5658501, 5674432, 5698141, 5723072, 5728758, 5730908, 5744070, 5759450, 5783116, 5801243, 5808063, 5811034, 5831090, 5833885, 5869658; 5879592, 5891368, 5955520; 5961892; 5981634, 5998520, 6004486, 6017121, 6018059; 6019914, 6022495, 6022497; 6030555, 6034193, 6065836, 6106744, 6106744, 6107395, 6113814, 6146554; 6149841, 6153126, 6221284, 6248264; 6296785, 6315928; 6342459; 6348604, 6353102, 6414057, 6478988, 6630597, 7556750, 7584630, 7999989, 8158037, 8697770, 8698117, 8741188, 9029532, 9028728, 9052438, 9097916, 9465234, 9487499, 9904074, 10197707, 10501446, 10532997, and 10502998

and are also described in the texts, Techniques in Chemistry, Volume III. "Photochromism", Chapter 3 (Glenn H. Brown, Editor, John Wiley and Sons, Inc., New York, 1971) and in "Chromic Phenomena: Technological Applications of Colour Chemistry" (P. Bamfield, RSC Books (2001)). Derivatives of these compounds that include various Substituents can be Synthesized from this teaching by people skilled in the art.

A polymerizable photochromic compound can be obtained by reacting a reactive (meth)acrylamido or (meth)acryloxy monomer having a first reactive functional group ($-\text{COCl}$, $-\text{COBr}$, $-\text{COOH}$, $-\text{NHR}_{\text{N}_2}$, $-\text{NCO}$, $-\text{OH}$, $-\text{CHO}$, $\text{---}\text{O}$, $\text{---}\text{N}^{\text{R}_0}$, or $-\text{N}^{\text{R}_0}\text{---}$ in which R_0 is hydrogen or methyl and R_{N_2} is hydrogen, a linear or branched $\text{C}_1\text{-C}_{15}$ alkyl, cyclohexyl, cyclopentyl, a substituted or unsubstituted phenyl, or a substituted- or unsubstituted-phenyl- $\text{C}_1\text{-C}_6$ alkyl) with a reactive photochromic compound having a second reactive functional group ($-\text{COOH}$, $-\text{NHR}_{\text{N}_2}$, $-\text{N}^{\text{R}_0}\text{---}$, $\text{---}\text{N}^{\text{R}_0}$, $\text{---}\text{NH}$, $\text{---}\text{NH}$, $-\text{NCO}$, $-\text{OH}$, $-\text{SH}$, $-\text{CHO}$, $\text{---}\text{O}$, $\text{---}\text{N}^{\text{R}_0}$, or $-\text{N}^{\text{R}_0}\text{---}$, in the absence or presence of a coupling agent (i.e., having two of the reactive functional groups listed above) under well known coupling reaction conditions, to form a photochromic compound.

Non-limiting examples of coupling reactions under various reaction conditions between a pair of matching co-reactive functional groups selected from the group preferably consisting of primary group, secondary amino group, hydroxyl group, carboxyl group, acid anhydride group, aldehyde group, isocyanate group, epoxy group, aziridine group, azlactone group and thiol group, are given below for illustrative purposes. A primary/secondary amino group reacts with aldehyde or ketone group to form a Schiff base which may further be reduced into an amine bond; a primary/secondary amino group $-\text{NHR}$ (in which R is hydrogen or $\text{C}_1\text{-C}_6$ alkyl) reacts with an acid chloride or bromide group or with an acid anhydride group to form an amide linkage ($-\text{CO-NR-}$); an amino group $-\text{NHR}$ reacts with a N-hydroxysuccinimide ester group to form an amide linkage; an amino group $-\text{NHR}$ reacts with a carboxylic acid group in the presence of a coupling agent – carbodiimide (e.g., 1-ethyl-3-(3-dimethylaminopropyl) carbodiimide (EDC), N,N'-dicyclohexylcarbodiimide (DCC), 1-cyclohexyl-3-(2-morpholinoethyl)carbodiimide, diisopropyl carbodiimide, or mixtures thereof) and N-hydroxysuccinimide to form an amide linkage; an amino group $-\text{NHR}$ reacts (ring-opening) with an azlactone group to form an alkylene-diamido linkage ($-\text{CONH-CR}^1\text{R}^2\text{-(CH}_2\text{)}_{p1}\text{-CONH-}$); an amino group $-\text{NHR}$ reacts with an isocyanate group to form a urea linkage ($-\text{NR-C(O)-NH-}$ with R as defined above); an amino group $-\text{NHR}$ reacts with an epoxy or aziridine group to form an amine bond ($-\text{C-NR-}$); a hydroxyl reacts with an isocyanate to form a urethane linkage; a hydroxyl reacts with an epoxy or aziridine to form an ether linkage ($-\text{O-}$); a hydroxyl reacts with an acid chloride or bromide group or with an

acid anhydride group to form an ester linkage; a carboxyl group reacts with an epoxy group to form an ester bond; a thiol group (-SH) reacts with an isocyanate to form a thiocarbamate linkage (-N-C(O)-S-); a thiol group reacts with an epoxy or aziridine to form a thioether linkage (-S-); a thiol group reacts with an acid chloride or bromide group or with an acid anhydride group to form a thioester linkage; a thiol group reacts with an azlactone group in the presence of a catalyst to form a linkage (-CONH-CR¹R²-(CH₂)_p-CO-S-); a thiol group reacts with an ene group or vinylsulfonyl group based on thiol-ene "click" reaction under thiol-ene reaction conditions to form a thioether linkage (-S-); a thiol group reacts with a (meth)acryloyl group based on Michael Addition under appropriate reaction conditions to form a thioether linkage.

The reactions conditions for the above described coupling reactions are taught in textbooks and are well known to a person skilled in the art.

Any coupling agents, each of which has two reactive functional groups, may be used in the coupling reactions. A coupling agent having two reactive functional groups can be: a diisocyanate compound; a di-acid halide compound; a di-carboxylic acid compound; a di-carboxylic acid anhydride compound; a diamine compound; a diol compound; a di-epoxy compound; a di-aziridine compound; di-azlactone compound; a di-ene compound; a divinylsulfone compound; a di-thiol compound; a thiolactone compound; an amino acid compound; a hydroxy-containing amine compound; an amine compound having one hydroxyl or ketone group; a hydroxy-containing carboxylic acid compound; a mercaptane having a hydroxyl, carboxyl or amino group.

For example, a diisocyanate, di-carboxylic acid (preferably a di-carboxylic acid anhydride), di-aziridine, di-epoxy, or di-azlactone compound can be used in the coupling of the first and second reactive functional groups when they are different or same and are selected from the group consisting of hydroxyl, primary amino, secondary amino, and thiol groups; a di-amine, di-hydroxyl, di-thiol, hydroxy-containing amine, or hydroxy-containing thiol compound can be used in the coupling of the first and second reactive functional groups when they are different or same and are selected from the group consisting of isocyanate, epoxy, aziridine, and carboxylic acid groups; a di-epoxy compound can be used in the coupling of the first and second reactive functional groups when they both are carboxylic acid groups; a di-amine compound can be used in the coupling of the first and second reactive functional groups when they both are aldehyde groups. A person skilled in the art knows well how to select one or more coupling agents, based on selectivity and/or differential reactivity of a given reactive functional group, to link the first and second reactive functional groups to form a photochromic polydiorganosiloxane vinylic crosslinker of the invention.

Examples of commercially available di-carboxylic acid anhydrides include without

limitation succinic acid anhydride, methylsuccinic anhydride, 2,2-dimethylsuccinic anhydride, 2,3-dimethylsuccinic acid, glutaric acid anhydride, 3,3-dimethylglutaric anhydride, 2,2-dimethylglutaric anhydride, 3-methylglutaric anhydride, 3,3-tetramethylglutaric anhydride, diglycolic anhydride, adipic anhydride, etc.

Any suitable C₃-C₂₄ di-carboxylic acid compounds can be used in the invention.

Examples of preferred di-carboxylic acid compounds include without limitation a linear or branched C₃-C₂₄ aliphatic dicarboxylic acid, a C₅-C₂₄ cycloaliphatic or aliphatic-cycloaliphatic dicarboxylic acid, a C₆-C₂₄ aromatic or araliphatic dicarboxylic acid, a dicarboxylic acid which contains amino or imido groups or N-heterocyclic rings, and combinations thereof. Examples of suitable aliphatic dicarboxylic acids are: oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, undecanedioic acid, dodecanedioic acid, dimethylmalonic acid, octadecylsuccinic acid, trimethyladipic acid, and dimeric acids (dimerisation products of unsaturated aliphatic carboxylic acids, such as oleic acid). Examples of suitable cycloaliphatic dicarboxylic acids are: 1,3-cyclobutanedicarboxylic acid, 1,3-cyclopentanedicarboxylic acid, 1,3- and 1,4-cyclohexanedicarboxylic acid, 1,3- and 1,4-dicarboxylmethylcyclohexane, 4,4'-dicyclohexyldicarboxylic acid. Examples of suitable aromatic dicarboxylic acids are: terephthalic acid, isophthalic acid, o-phthalic acid, 1,3-, 1,4-, 2,6- or 2,7-naphthalenedicarboxylic acids, 4,4'-biphenyldicarboxylic acid, 2,2'-biphenyldicarboxylic acid, 4,4'-diphenylsulphone-dicarboxylic acid, 1,1,3-trimethyl-5-carboxyl-3-(p-carboxyphenyl)-indane, 4,4'-diphenyl ether-dicarboxylic acid, bis-p-(carboxylphenyl)-methane.

Any suitable diacid halides can be used in the invention. Examples of preferred diacid halide include without limitations fumaryl chloride, suberoyl chloride, succinyl chloride, phthaloyl chloride, isophthaloyl chloride, terephthaloyl chloride, sebacoyl chloride, adipoyl chloride, trimethyladipoyl chloride, azelaoyl chloride, dodecanedioic acid chloride, succinic chloride, glutaric chloride, oxalyl chloride, dimer acid chloride, and combinations thereof.

Any suitable diamines can be used in the invention. An organic diamine can be a linear or branched C₂-C₂₄ aliphatic diamine, a C₅-C₂₄ cycloaliphatic or aliphatic-cycloaliphatic diamine, or a C₆-C₂₄ aromatic or alkyl-aromatic diamine. A preferred organic diamine is N,N'-bis(hydroxyethyl)ethylenediamine, N,N'-dimethylethylenediamine, ethylenediamine, N,N'-dimethyl-1,3-propanediamine, N,N'-diethyl-1,3-propanediamine, N-methyl-1,3-diaminopropane, N-methylethylenediamine, N-ethylethylenediamine, N-isopropyl-1,3-propanediamine, N-propyl-1,3-propanediamine, N-butylethylenediamine, 2,2-dimethyl-1,3-propanediamine, 1,4-butanediamine, 1,5-pentanediamine, hexamethylenediamine, 2-Methyl-1,5-pentanediamine, 1,6-hexamethylenediamine, N,N'-dimethyl-1,6-hexamethylenediamine, 2,2,4(2,4,4)-trimethyl-1,6-hexanediamine, 1,3-diamino-2-propanol, 1,2-diaminoethane-1,2-diol, 1,1-diaminoethane-1,2-diol, 1,4-diamino-2,3-butanediol, 1,3-cyclopentanediamine, 1,4-

diaminocyclohexane, 1,3-Bis(aminomethyl)cyclohexane, 4,4'-diaminodicyclohexylmethane, 4,4'-methylenebis(2-methylcyclohexylamine), isophorone diamine (3-aminomethyl-3,5,5-trimethylcyclohexylamine), m-xylylene diamine, p-xylylene diamine, piperazine, 1-(2-aminoethyl)piperazine, 1,4-bis(3-aminopropyl)piperazine, 2-piperazinoethylamine, 1-Boc-piperazine, 4-(2-aminoethyl)-1-Boc-piperazine, 1-(2-N-Boc-aminoethyl)piperazine, 4-(2-aminoethyl)-1-Boc-piperazine, 4-aminopiperidine, 3-aminopiperidine, 4-aminomethylpiperidine, 2-aminomethylpiperidine, 1-Boc-piperidine-4-carboxaldehyde, 1-Boc-piperidine-4-acetaldehyde, etc.

Any suitable C₄-C₂₄ diisocyanates can be used in the invention. Examples of preferred diisocyanates include without limitation tetramethylene diisocyanate, pentamethylene diisocyanate, hexamethylene diisocyanate, heptamethylene diisocyanate, 1,6-diisocyanato-2,2,4-trimethylhexane, octamethylene diisocyanate, dodecamethylene diisocyanate, cyclohexane diisocyanate, 1,3-bis-(4,4'-isocyanatomethyl)cyclohexane, isophorone diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, toluene diisocyanate, 4,4'-diphenyl diisocyanate, 4,4'-diphenylmethane diisocyanate, p-phenylene diisocyanate, etc.

Any suitable di-epoxy compounds can be used in the invention. Examples of preferred di-epoxy compounds are neopentyl glycol diglycidyl ether, 1,3-butadiene diepoxide, 1,4-butanediol diglycidyl ether, 1,2,7,8-diepoxyoctane, 3,4-epoxycyclohexylmethyl-3,4-epoxy-cyclohexane, 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexane carboxylate, vinylcyclohexene dioxide, 1,6-hexanediol diglycidyl ether, glycerol diglycidyl ether, ethylene glycol diglycidyl ether, diethylene glycol diglycidyl ether, polyethylene glycol diglycidyl ether, propylene glycol diglycidyl ether, dipropylene glycol diglycidyl ether, polypropylene glycol diglycidyl ether, bis[4-(glycidyloxy)phenyl]methane, Bisphenol A diglycidyl ether (2,2-Bis[4-(glycidyloxy)phenyl]-propane), Bisphenol A propoxylate diglycidyl ether, and combinations thereof.

Any suitable C₂-C₂₄ diols (i.e., compounds with two hydroxyl groups) can be used in the invention. Examples of preferred diols include without limitation ethylene glycol, diethylene glycol, triethylene glycol, tetraethylene glycol, polyethylene glycol, propylene glycol, 1,4-butanediol, various pentanediols, various hexanediols, various cyclohexanediols, 1,4-bis(2-hydroxyethyl)piperazine, bisphenol A, bisphenol F, 4,4'-methylenediphenol, and combination thereof.

Any amino acids can be used in the invention. Examples of amino acids include without limitation glycine, proline, alanine, valine, isoleucine, leucine, 2-aminoisobutyric acid, 4-aminobutyric acid, 3-aminoisobutyric acid, 3-amino-butyric acid, β -alanine, 1-amino-3-cyclopentane carboxylic acid, 3-aminocyclohexanecarboxylic acid, pyrrolidine-3-carboxylic acid, 4-piperidinecarboxylic acid, 3-piperidinecarboxylic acid, 1-piperazineacetic acid, etc.

Examples of compounds having one amino group and one hydroxyl or aldehyde

group (or ketone group) include without limitation 1-piperazinepropanol, 2-[2-(1-piperazinyl)ethoxy]-ethanol, 4-amino-1-piperazineethanol, 4-piperidinemethanol, 1-Boc-piperidine-4-carboxaldehyde, 4-formylpiperidine, N-Boc-4-piperidineacetaldehyde, etc.

Preferred reactive (meth)acrylamido or (meth)acryloxy monomers without limitation include those described later in this application.

Preferred photochromic compounds without limitation include without limitation those compounds that are described later in this application and can be obtained from commercial suppliers or prepared according to procedures described in the patents discussed above and in the texts described above.

Lens molds for making contact lenses including hydrogel contact lenses are well known to a person skilled in the art and, for example, are employed in cast molding or spin casting. For example, a mold (for cast molding) generally comprises at least two mold sections (or portions) or mold halves, i.e. first and second mold halves. The first mold half defines a first molding (or optical) surface and the second mold half defines a second molding (or optical) surface. The first and second mold halves are configured to receive each other such that a lens-forming cavity is formed between the first molding surface and the second molding surface. The molding surface of a mold half is the cavity-forming surface of the mold and in direct contact with the polymerizable composition.

Methods of manufacturing mold sections for cast molding a contact lens are generally well known to those of ordinary skill in the art. The process of the present invention is not limited to any particular method of forming a mold. In fact, any method of forming a mold can be used in the present invention.

In general, a mold comprises at least two mold halves (or mold sections), one male half and one female mold half. The male mold half has a first molding (or optical) surface which is in direct contact with a polymerizable composition for cast molding of a contact lens and defines the posterior (concave) surface of a molded contact lens; and the female mold half has a second molding (or optical) surface which is in direct contact with the polymerizable composition and defines the anterior (convex) surface of the molded contact lens. The male and female mold halves are configured to receive each other such that a lens-forming cavity is formed between the first molding surface and the second molding surface.

The mold halves can be formed through various techniques, such as injection molding. Methods of manufacturing mold halves for cast-molding a contact lens are generally well known to those of ordinary skill in the art. The process of the present invention is not limited to any particular method of forming a mold. In fact, any method of forming a mold can be used in the present invention. The first and second mold halves can be formed through various techniques, such as injection molding or lathing. Examples of suitable

processes for forming the mold halves are disclosed in U.S. Pat. Nos. 4444711; 4460534; 5843346; and 5894002.

Virtually all materials known in the art for making molds can be used to make molds for making contact lenses. For example, polymeric materials, such as polyethylene, polypropylene, polystyrene, PMMA, Topas® COC grade 8007-S10 (clear amorphous copolymer of ethylene and norbornene, from Ticona GmbH of Frankfurt, Germany and Summit, New Jersey), or the like can be used. Other materials that allow UV light transmission could be used, such as quartz glass and sapphire.

In accordance with the invention, the first or second polymerizable fluid composition can be dispensed onto the molding surface of a female mold half according to any known techniques.

A specific amount of a second polymerizable fluid composition is typically dispensed into a female mold half by means of a dispensing device and then a male mold half is put on and the mold is closed. As the mold closes, any excess second polymerizable fluid composition is pressed into an overflow provided on the female mold half (or alternatively on the male mold half).

The molding assembly (i.e., the closed mold containing the second polymerizable fluid composition and the drop of the first polymerizable fluid composition) is subsequently cured thermally (i.e., by heating) or actinically (i.e., by actinic radiation, e.g., UV radiation and/or visible radiation) to activate the free-radical initiators, as known to a person skilled in the art, to produce a molded unprocessed silicone hydrogel contact lens.

The actinic curing of the first and second polymerizable fluid compositions in a molding assembly can be carried out by irradiating the closed molding assembly with an UV or visible light, according to any techniques known to a person skilled in the art.

In accordance with the invention, any visible light can be used in the partial curing step. Preferably, a visible light in a region between 420 nm to 500 nm is used in the invention. Light source can be any ones emitting light in the 420-500 nm range sufficient to activate acylgermanium photoinitiators. Blue-light sources are commercially available and include: the Palatray CU blue-light unit (available from Heraeus Kulzer, Inc., Irvine, Calif.), the Fusion F450 blue light system (available from TEAMCO, Richardson, Tex.), Dymax Blue Wave 200, LED light sources from Opsytec (435 nm, 445 nm, 460 nm), and the GE 24" blue fluorescent lamp (available from General Electric Company, U.S.). A preferred blue-light source is the LED from Opsytec (those described above).

The thermal curing (i.e., polymerization) of the second polymerizable fluid composition and the drop of the first polymerizable fluid composition in the molding assembly can be carried out conveniently in an oven at a temperature of from 25 to 120°C and preferably 40 to 100°C, as well known to a person skilled in the art. The reaction time

may vary within wide limits, but is conveniently, for example, from 1 to 24 hours or preferably from 2 to 12 hours. It is advantageous to previously degas the silicone-hydrogel-lens-forming composition and to carry out said copolymerization reaction under an inert atmosphere, e.g., under N₂ or Ar atmosphere.

After curing, the molds can be opened according to any techniques known to a person skilled in the art. After the mold is separated, the molded unprocessed silicone hydrogel contact lens adheres to one of the male and female mold halves.

The unprocessed silicone hydrogel contact lens adhered on the lens-adhered mold half can be removed from the lens-adhered mold half and then subject to one or more post molding processes.

For example, unprocessed silicone hydrogel contact lens can be extracted with a liquid extraction liquid medium to remove unpolymerized polymerizable components and formed and oligomers. In accordance with the invention, the extraction liquid medium is any solvent capable of dissolving the organic solvent, unpolymerized polymerizable materials, and oligomers in the dry contact lens. Water, any organic solvents known to a person skilled in the art, or a mixture thereof can be used in the invention. Preferably, the organic solvents used extraction liquid medium are water, a buffered saline, a C₁-C₃ alkyl alcohol, 1,2-propylene glycol, a polyethyleneglycol having a number average molecular weight of about 400 Daltons or less, a C₁-C₆ alkylalcohol, or combinations thereof.

The hydrogel contact lenses can also be subjected to further processes, such as, for example, surface treatment (for example, such as, plasma treatment, chemical treatments, the grafting of hydrophilic monomers or macromers onto the surface of a lens, Layer-by-layer coating, in-package crosslinking of a thermally-reactive hydrophilic polymeric material, etc.); packaging in lens packages with a packaging solution which can contain about 0.005% to about 5% by weight of a wetting agent (e.g., a hydrophilic polymer), a viscosity-enhancing agent (e.g., methyl cellulose (MC), ethyl cellulose, hydroxymethylcellulose, hydroxyethyl cellulose (HEC), hydroxypropylcellulose (HPC), hydroxypropylmethyl cellulose (HPMC), or a mixture thereof), or an in-package-coating material; sterilization such as autoclave at from 118 to 124°C for at least about 30 minutes; and the like.

Preferred surfaces treatments are LbL coating such as those described in U.S. Pat. Nos. 6451871, 6719929, 6793973, 6811805, and 6896926, plasma treatment, in-package-coating such as those disclosed in U.S. Pat. Nos. 8557334, 8529057 and 9505184. A preferred plasma treatment is those processes in which an ionized gas is applied to the surface of an article as described in U.S. Pat. Nos. 4312575 and 4632844.

The hydrogel contact lens is hydrated in water or an aqueous solution to replace the liquid extraction medium, according to any method known to a person skilled in the art.

The hydrated and/or surface-treated photochromic contact lens can further subject to

further processes, such as, for example, packaging in lens packages with a packaging solution which is well known to a person skilled in the art; sterilization such as autoclave at from 118 to 124°C for at least about 30 minutes; and the like.

Lens packages (or containers) are well known to a person skilled in the art for autoclaving and storing a soft contact lens. Any lens packages can be used in the invention. Preferably, a lens package is a blister package which comprises a base and a cover, wherein the cover is detachably sealed to the base, wherein the base includes a cavity for receiving a sterile packaging solution and the contact lens.

Lenses are packaged in individual packages, sealed, and sterilized (e.g., by autoclave at about 120°C or higher for at least 30 minutes under pressure) prior to dispensing to users. A person skilled in the art will understand well how to seal and sterilize lens packages.

A SiHy contact lens of the invention has an oxygen permeability of preferably at least about 40 barrers, more preferably at least about 60 barrers, even more preferably at least about 80 barrers (at about 35°C).

A hydrogel contact lens of the invention has an elastic modulus of about 1.5 MPa or less, preferably about 1.2 MPa or less, more preferably from about 0.3 MPa to about 1.0 MPa (at a temperature of from about 22°C to 28°C).

A hydrogel contact lens of the invention further has an equilibrium water content of from about 15% to about 75%, more preferably from about 20% to about 70% by weight, even more preferably from about 25% to about 65% by weight (at room temperature) when fully hydrated. The equilibrium water content of a photochromic contact lens can be measured according to the procedure disclosed in Example 1.

In a further aspect, the invention provides a hydrogel contact lens obtained by the method of the invention.

All of the various embodiments of the molds, polymerizable composition, and spatial limitation of radiation, and contact lens of the invention described above can be used in this aspect of the invention.

Although various embodiments of the invention have been described using specific terms, devices, and methods, such description is for illustrative purposes only. The words used are words of description rather than of limitation. It is to be understood that changes and variations may be made by those skilled in the art without departing from the spirit or scope of the present invention, which is set forth in the following claims. In addition, it should be understood that aspects of the various embodiments may be interchanged either in whole or in part or can be combined in any manner and/or used together, as illustrated below:

1. A method for producing hydrogel contact lenses, comprising the steps of:

- (1) obtain a first polymerizable fluid composition and a second polymerizable fluid composition, wherein the first polymerizable fluid composition comprises at least one first free-radical initiator, at least one first polymerizable material, and at least one photochromic compound, wherein said at least one first polymerizable material comprises at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 5000 Daltons or higher and is present in the first polymerizable composition in an amount of about 40% by weight or more, wherein the second polymerizable fluid composition comprises said at least one second free-radical initiator and at least one second polymerizable material and is free of any photochromic compound;
- (2) obtaining a lens mold, wherein the lens mold comprises a male mold half having a first molding surface defining the posterior surface of a contact lens to be molded and a female mold half having a second molding surface defining the anterior surface of the contact lens to be molded, wherein the female and male mold halves are configured to receive each other such that a mold cavity is formed between the first and second molding surfaces when the mold is closed;
- (3) applying a drop of the first polymerizable fluid composition onto the geometrical center of the first molding of the male mold half, wherein the drop has a volume of about 5 μ L or less;
- (4) dispensing an amount of the second polymerizable fluid composition on the second molding surface of the female mold half;
- (5) closing the female mold half with the male mold half having the drop adhered thereon to form a molding assembly comprising the second polymerizable composition and the drop of the first polymerizable composition within the mold cavity;
- (6) curing the second polymerizable fluid composition and the drop of the first polymerizable composition to form an unprocessed silicone hydrogel contact lens having a central photochromic zone that has a diameter of about 13 mm or less, is concentric with the central axis of the unprocessed silicone hydrogel contact lens;
- (7) separating the molding assembly into the male and female mold halves, with the unprocessed silicone hydrogel contact lens adhered onto a lens-adhered mold half which is one of the male and female mold halves;
- (8) removing the unprocessed silicone hydrogel contact lens from the lens-adhered mold half; and
- (9) subjecting the unprocessed silicone hydrogel contact lens to post-molding processes including a hydration process and one or more other processes selected from the group consisting of extraction, surface treatment, packaging, sterilization, and combinations thereof.

2. The method of embodiment 1, wherein said at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 6000 Daltons or higher.
3. The method of embodiment 2, wherein said at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 8000 Daltons or higher.
4. The method of embodiment 2 or 3, wherein said at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 10000 Daltons or higher.
5. The method of embodiment 2 or 3, wherein said at least one first polysiloxane vinylic crosslinker is present in the first polymerizable composition in an amount of about 45% by weight or more.
6. The method of embodiment 2 or 3, wherein said at least one first polysiloxane vinylic crosslinker is present in the first polymerizable composition in an amount of about 50% by weight or more.
7. The method of embodiment 2 or 3, wherein said at least one first polysiloxane vinylic crosslinker is present in the first polymerizable composition in an amount of about 55% by weight or more.
8. The method of any one of embodiments 3 to 7, wherein the drop has a volume of about 4.5 μL or less.
9. The method of any one of embodiments 3 to 7, wherein the drop has a volume of about 4.0 μL or less.
10. The method of any one of embodiments 3 to 7, wherein the drop has a volume of about 3.5 μL or less.
11. The method of embodiment 1, wherein the step of (6) curing is carried out thermally, wherein said at least one first and second free-radical initiators comprise a thermal free-radical initiator.
12. The method of embodiment 11, wherein the step of (6) curing is carried out actinically, wherein said at least one first and second free-radical initiators comprise a free-radical photoinitiator.
13. The method of any one of embodiments 1 to 12, wherein said at least one first and second polymerizable materials independent of each other further comprise: (a) at least one silicone-containing vinylic monomer, (b) at least one second polysiloxane vinylic crosslinker, at least one non-silicone vinylic crosslinker, or combinations thereof, (c) at least one hydrophilic vinylic monomer, and optionally (d) at least one component selected from the group consisting of a non-silicone hydrophobic vinylic monomer, a UV-absorbing vinylic monomer, and combinations thereof.

14. The method of embodiment 13, wherein said at least one hydrophilic vinylic monomer comprises at least one hydrophilic (meth)acrylamido monomer.
15. The method of embodiment 14, wherein said at least one hydrophilic (meth)acrylamido monomer has 3 to 8 carbon atoms.
16. The method of embodiment 14, wherein said at least one hydrophilic (meth)acrylamido monomer is selected from the group consisting of (meth)acrylamide, N-methyl (meth)acrylamide, N,N-dimethyl (meth)acrylamide, N-ethyl (meth)acrylamide, N,N-diethyl (meth)acrylamide, N-propyl (meth)acrylamide, N-isopropyl (meth)acrylamide, N-3-methoxypropyl (meth)acrylamide, N-2-hydroxyethyl (meth)acrylamide, N-3-hydroxypropyl (meth)acrylamide, N-2-hydroxypropyl (meth)acrylamide, N-2,3-dihydroxypropyl (meth)acrylamide, N-4-hydroxybutyl (meth)acrylamide, N,N-bis(2-hydroxyethyl) (meth)acrylamide, *N*-tris(hydroxymethyl) methyl (meth)acrylamide, 2-(meth)acrylamido-glycolic acid, 3-(meth)acrylamidopropionic acid, 4-(meth)acrylamido-butanoic acid, 3-(meth)acrylamido-2-methylbutanoic acid, 3-(meth)acrylamido-3-methylbutanoic acid, 2-(meth)acrylamido-2-methyl-3,3-dimethyl butanoic acid, 5-(meth)acrylamidopentanoic acid, 3-(meth)acrylamidohexanoic acid, 4-(meth)acrylamido-3,3-dimethylhexanoic acid, (3-(meth)acrylamidophenyl)boronic acid, 3-((3-methacrylamidopropyl)dimethylammonio)-propane-1-sulfonate; 3-((3-acrylamidopropyl)dimethylammonio)propane-1-sulfonate, poly(ethylene glycol)ethyl (meth)acrylamide having a number average molecular weight of up to 700, methoxy-poly(ethylene glycol)ethyl (meth)acrylamide having a number average molecular weight of up to 700, and combinations thereof.
17. The method of any one of embodiments 14 to 16, wherein said at least one hydrophilic (meth)acrylamido monomer comprises N,N-dimethyl (meth)acrylamide, N-ethyl (meth)acrylamide, N-2-hydroxyethyl (meth)acrylamide, N-3-hydroxypropyl (meth)acrylamide, N-2-hydroxypropyl (meth)acrylamide, N-2,3-dihydroxypropyl (meth)acrylamide, (meth)acrylamide, or combinations thereof.
18. The method of any one of embodiments 14 to 16, wherein said at least one hydrophilic (meth)acrylamido monomer comprises N,N-dimethyl (meth)acrylamide, N-2-hydroxyethyl (meth)acrylamide, or a combination thereof.
19. The method of any one of embodiments 13 to 18, wherein said at least one hydrophilic vinylic monomer comprises at least one hydrophilic (meth)acryloxy monomer.
20. The method of embodiment 19, wherein said at least one hydrophilic (meth)acryloxy monomer is selected from the group consisting of 2-hydroxyethyl (meth)acrylate, 3-hydroxypropyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, glycerol methacrylate (GMA), di(ethylene glycol) (meth)acrylate, tri(ethylene glycol) (meth)acrylate, tetra(ethylene glycol) (meth)acrylate, poly(ethylene glycol) (meth)acrylate having a







number average molecular weight of up to 1500, (meth)acrylic acid, ethylacrylic acid, propylacrylic acid, butylacrylic acid, trimethylammonium 2-hydroxy propyl (meth)acrylate hydrochloride, dimethylaminoethyl (meth)acrylate, ethylene glycol methyl ether (meth)acrylate, di(ethylene glycol) methyl ether (meth)acrylate, tri(ethylene glycol) methyl ether (meth)acrylate, tetra(ethylene glycol) methyl ether (meth)acrylate, C₁-C₄-alkoxy poly(ethylene glycol) (meth)acrylate having a number average molecular weight of up to 1500, and combinations thereof.



21. The method of any one of embodiments 13 to 20, wherein said at least one hydrophilic vinylic monomer comprises at least one hydrophilic N-vinyl amide monomer selected from the group consisting of N-vinylpyrrolidone, N-vinyl-3-methyl-2-pyrrolidone, N-vinyl-4-methyl-2-pyrrolidone, N-vinyl-5-methyl-2-pyrrolidone, N-vinyl-6-methyl-2-pyrrolidone, N-vinyl-3-ethyl-2-pyrrolidone, N-vinyl-4,5-dimethyl-2-pyrrolidone, N-vinyl-5,5-dimethyl-2-pyrrolidone, N-vinyl-3,3,5-trimethyl-2-pyrrolidone, N-vinyl piperidone (*aka*, N-vinyl-2-piperidone), N-vinyl-3-methyl-2-piperidone, N-vinyl-4-methyl-2-piperidone, N-vinyl-5-methyl-2-piperidone, N-vinyl-6-methyl-2-piperidone, N-vinyl-6-ethyl-2-piperidone, N-vinyl-3,5-dimethyl-2-piperidone, N-vinyl-4,4-dimethyl-2-piperidone, N-vinyl caprolactam (*aka*, N-vinyl-2-caprolactam), N-vinyl-3-methyl-2-caprolactam, N-vinyl-4-methyl-2-caprolactam, N-vinyl-7-methyl-2-caprolactam, N-vinyl-7-ethyl-2-caprolactam, N-vinyl-3,5-dimethyl-2-caprolactam, N-vinyl-4,6-dimethyl-2-caprolactam, N-vinyl-3,5,7-trimethyl-2-caprolactam, N-vinyl-N-methyl acetamide, N-vinyl formamide, N-vinyl acetamide, N-vinyl isopropylamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-ethyl formamide, and mixtures thereof.
22. The method of any one of embodiments 13 to 20, wherein said at least one hydrophilic vinylic monomer comprises N-vinylpyrrolidone and/or N-vinyl-N-methyl acetamide.
23. The method of any one of embodiments 13 to 22, wherein said at least one hydrophilic vinylic monomer comprises: (a) at least one methylene-containing pyrrolidone monomer selected from the group consisting of 1-methyl-3-methylene-2-pyrrolidone, 1-ethyl-3-methylene-2-pyrrolidone, 1-methyl-5-methylene-2-pyrrolidone, 1-ethyl-5-methylene-2-pyrrolidone, 5-methyl-3-methylene-2-pyrrolidone, 5-ethyl-3-methylene-2-pyrrolidone, 1-n-propyl-3-methylene-2-pyrrolidone, 1-n-propyl-5-methylene-2-pyrrolidone, 1-isopropyl-3-methylene-2-pyrrolidone, 1-isopropyl-5-methylene-2-pyrrolidone, 1-n-butyl-3-methylene-2-pyrrolidone, 1-tert-butyl-3-methylene-2-pyrrolidone, and combinations thereof; (b) at least one vinyl ether monomer selected from the group consisting of ethylene glycol monovinyl ether, di(ethylene glycol) monovinyl ether, tri(ethylene glycol) monovinyl ether, tetra(ethylene glycol) monovinyl ether, poly(ethylene glycol) monovinyl ether, ethylene glycol methyl vinyl ether, di(ethylene glycol) methyl vinyl ether, tri(ethylene glycol) methyl vinyl ether, tetra(ethylene glycol) methyl vinyl ether,

- poly(ethylene glycol) methyl vinyl ether, and combinations thereof; (c) at least one allyl ether monomer selected from the group consisting of ethylene glycol monoallyl ether, di(ethylene glycol) monoallyl ether, tri(ethylene glycol) monoallyl ether, tetra(ethylene glycol) monoallyl ether, poly(ethylene glycol) monoallyl ether, ethylene glycol methyl allyl ether, di(ethylene glycol) methyl allyl ether, tri(ethylene glycol) methyl allyl ether, tetra(ethylene glycol) methyl allyl ether, poly(ethylene glycol) methyl allyl ether, and combinations thereof; (d) at least one phosphorylcholine-containing vinylic monomer selected from the group consisting of (meth)acryloyloxyethyl phosphorylcholine, (meth)acryloyloxypropyl phosphorylcholine, 4-((meth)acryloyloxy)butyl-2'-(trimethylammonio)ethylphosphate, 2-[(meth)acryloylamino]-ethyl-2'-(trimethylammonio)-ethylphosphate, 3-[(meth)acryloylamino]propyl-2'-(trimethylammonio)ethylphosphate, 4-[(meth)acryloylamino]butyl-2'-(trimethylammonio)-ethylphosphate, 5-((meth)acryloyloxy)pentyl-2'-(trimethylammonio)ethyl phosphate, 6-((meth)acryloyloxy)hexyl-2'-(trimethylammonio)-ethylphosphate, 2-((meth)acryloyloxy)-ethyl-2'-(triethylammonio)ethylphosphate, 2-((meth)acryloyloxy)ethyl-2'-(tripropylammonio)ethylphosphate, 2-((meth)acryloyloxy)ethyl-2'-(tributylammonio)ethyl phosphate, 2-((meth)acryloyloxy)propyl-2'-(trimethylammonio)-ethylphosphate, 2-((meth)acryloyloxy)butyl-2'-(trimethylammonio)ethylphosphate, 2-((meth)acryloyloxy)-pentyl-2'-(trimethylammonio)ethylphosphate, 2-((meth)acryloyloxy)hexyl-2'-(trimethylammonio)ethyl phosphate, 2-(vinylloxy)ethyl-2'-(trimethylammonio)-ethylphosphate, 2-(allyloxy)ethyl-2'-(trimethylammonio)ethylphosphate, 2-(vinylloxycarbonyl)ethyl-2'-(trimethylammonio)ethyl phosphate, 2-(allyloxycarbonyl)ethyl-2'-(trimethylammonio)-ethylphosphate, 2-(vinylcarbonylamino)ethyl-2'-(trimethylammonio)-ethylphosphate, 2-(allyloxycarbonylamino)ethyl-2'-(trimethylammonio)ethyl phosphate, 2-(butenoyloxy)ethyl-2'-(trimethylammonio)ethylphosphate, and combinations thereof; (e) allyl alcohol; (f) N-2-hydroxyethyl vinyl carbamate; (g) N-vinylloxycarbonyl- β -alanine (VINAL); (h) N-vinylloxycarbonyl- α -alanine; or (i) combinations thereof.
24. The method of any one of embodiment 13 to 23, wherein said at least one silicone-containing vinylic monomer comprises at least one silicone-containing (meth)acrylamido monomer containing a tris(trialkylsiloxy)silyl group.
25. The method of embodiment 24, wherein said at least one silicone-containing (meth)acrylamido monomer containing a tris(trialkylsiloxy)silyl group is selected from the group consisting of N-[tris(trimethylsiloxy)silylpropyl] (meth)acrylamide, N-[tris(dimethylethylsiloxy)-silylpropyl] (meth)acrylamide, N-[tris(dimethylpropylsiloxy)silylpropyl] (meth)acrylamide, N-[tris(dimethylphenylsiloxy)silylpropyl] (meth)acrylamide, N-(2-hydroxy-3-(3-

(tris(trimethyl-silyloxy)silyl)propyloxy)propyl)-2-methyl (meth)acrylamide, N-(2-hydroxy-3-(3-(tris(trimethyl-silyloxy)silyl)propyloxy)propyl) (meth)acrylamide, N,N-bis[2-hydroxy-3-(3-(tris(trimethyl-silyloxy)silyl)propyloxy)propyl]-2-methyl (meth)acrylamide, N,N-bis[2-hydroxy-3-(3-(tris(trimethylsilyloxy)silyl)propyloxy)propyl] (meth)acrylamide, and combinations thereof.

26. The method of any one of embodiments 13 to 25, wherein said at least one silicone-containing vinylic monomer comprises at least one silicone-containing (meth)acrylamido monomer containing a bis(trialkylsilyloxy)-alkylsilyl group.
27. The method of embodiment 26, wherein said at least one silicone-containing (meth)acrylamido monomer containing a bis(trialkylsilyloxy)alkylsilyl group is selected from the group consisting of N-(2-hydroxy-3-(3-(bis(trimethylsilyloxy)methylsilyl)propyloxy)propyl)-2-methyl (meth)acrylamide, N-(2-hydroxy-3-(3-(bis(trimethylsilyloxy)methylsilyl)propyloxy)-propyl) (meth)acrylamide, N,N-bis[2-hydroxy-3-(3-(bis(trimethylsilyloxy)methylsilyl)-propyloxy)propyl]-2-methyl (meth)acrylamide, N,N-bis[2-hydroxy-3-(3-(bis(trimethyl-silyloxy)methylsilyl)propyloxy)-propyl] (meth)acrylamide, N-[2-hydroxy-3-(3-(t-butyl-dimethylsilyl)propyloxy)propyl]-2-methyl acrylamide, a siloxane-containing (meth)acrylamido monomer of one of formula (Ia) to (Ih), and combinations thereof,






in which R_{13} is a divalent alkylene radical of $-\text{CH}_2\text{CH}_2-$, $-\text{CH}_2\text{CH}_2\text{CH}_2-$, $-\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}_2-$, $-\overset{\text{CH}_3}{\text{CH}}-\text{CH}_2-$, $-\text{CH}_2-\overset{\text{CH}_3}{\text{CH}}-$, , , $-\overset{\text{H}_3\text{C}-\text{CH}-\text{CH}_3}{\text{CH}}-\text{CH}_2-$, $-\overset{\text{H}_3\text{C}-\text{CH}-\text{CH}_2-\text{CH}_3}{\text{CH}}-\text{CH}_2-$, $-\overset{\text{CH}_2-\text{OH}}{\text{CH}}-\text{CH}_2-$, $-\overset{\text{HO}-\text{CH}-\text{CH}_3}{\text{CH}}-\text{CH}_2-$, $-\overset{\text{H}_3\text{C}-\text{CH}-\text{CH}_2-\text{OH}}{\text{CH}}-\text{CH}_2-$, $-\overset{\text{CH}_3}{\text{C}}(\text{CH}_3)-$, or $-\text{CH}_2-\overset{\text{CH}_3}{\text{C}}(\text{CH}_3)-$, R_{14} is a divalent alkylene radical of $-\text{CH}_2\text{CH}_2-$ or $-\text{CH}_2\text{CH}_2\text{CH}_2-$, and R_{15} is a

divalent alkylene radical of $-\overset{\text{CH}_3}{\text{C}}(\text{CH}_3)-$ or $-\text{CH}_2-\overset{\text{CH}_3}{\text{C}}(\text{CH}_3)-$, R'' and R_{11} independent of each other is C_1 - C_4 alkyl, and $f1$ is an integer of from 3 to 5.

28. The method of any one of embodiments 13 to 27, wherein said at least one silicone-containing vinylic monomer comprises at least one mono-(meth)acrylamido-terminated oligo- or polysiloxane of formula (IIa)




in which R' is hydrogen or methyl, R'' independent of each other is C_1 - C_6 alkyl, $g1$ and $g2$ independent of each other are integer of 0 or 1, $h1$ is an integer of 2 to 25, R_9 and R_{10} independent of each other are a substituted or unsubstituted C_1 - C_{10} alkylene

divalent radical, Y_1 is a linkage of $-\text{NH}-\overset{\text{O}}{\text{C}}-$, $-\overset{\text{O}}{\text{C}}-\text{NH}-$, or $-\overset{\text{R}_{12}'}{\text{C}}-\overset{\text{O}}{\text{C}}-\text{O}-$ in which R_{12} and R_{12}' independent of each other are C_1 - C_6 alkyl.

29. The method of embodiment 28, wherein in formula (IIa) $h1$ is an integer of 3 to 20 (more preferably 3 to 15).
30. The method of embodiment 28 or 29, wherein in formula (IIa) R_{12} and R_{12}' independent of each other are methyl.
31. The method of any one of embodiments 28 to 30, wherein at least one mono-(meth)acrylamido-terminated oligo- or polysiloxane is selected from the group consisting of α -(meth)acryloyl-amidopropoxypropyl terminated ω - C_1 - C_4 -alkyl terminated

polydimethylsiloxane, α -N-methyl-(meth)acryloylamidopropoxypropyl terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -[3-(meth)acrylamidoethoxy-2-hydroxypropyloxy-propyl]-terminated ω -C₁-C₄-alkyl polydimethylsiloxane, α -[3-(meth)acrylamidopropoxy-2-hydroxypropyloxy-propyl]-terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -[3-(meth)acrylamido-isopropoxy-2-hydroxypropyloxypropyl]-terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -[3-(meth)acrylamidobutyloxy-2-hydroxypropyloxy-propyl]-terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -[3-(meth)acryloylamido-2-hydroxypropyloxypropyl] terminated ω -C₁-C₄-alkyl polydimethylsiloxane, α -[3-[N-methyl-(meth)acryloylamido]-2-hydroxypropyloxypropyl] terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, N-methyl-N'-(propyl-tetra(dimethylsiloxy)dimethylbutylsilane) (meth)acrylamide, N-(2,3-dihydroxypropane)-N'-(propyltetra(dimethylsiloxy)dimethyl-butylsilane) (meth)acrylamide, (meth)acryloylamido-propyltetra(dimethylsiloxy)-dimethylbutylsilane, and combinations thereof.

32. The method of any one of embodiments 13 to 31, wherein said at least one first polysiloxane vinylic crosslinker and said at least one second polysiloxane vinylic crosslinker independently of one another are selected from the group consisting of: an α,ω -(meth)acryloxy-terminated polydimethylsiloxane; an α,ω -(meth)acrylamido-terminated polydimethylsiloxane; an α,ω -vinyl carbonate-terminated polydimethylsiloxane; an α,ω -vinyl carbamate-terminated polydimethylsiloxane; a bis-3-methacryloxy-2-hydroxypropyloxypropyl polydimethylsiloxane; a reaction product of glycidyl methacrylate with a di-amino-functionalized polydimethylsiloxane; a reaction product of an azlactone-containing vinylic monomer with a di-hydroxyl-functionalized polydimethylsiloxane; and combinations thereof.
33. The method of any one of embodiments 13 to 31, wherein said at least one first polysiloxane vinylic crosslinker and said at least one second polysiloxane vinylic crosslinker independently of one another comprises at least one polysiloxane vinylic crosslinker of formula (H)



in which:






d₁ is an integer of from 30 to 500 and d₂ is an integer of from 1 to 75, provided that d₂/d₁ is from about 0.035 to about 0.15 (preferably from about 0.040 to about 0.12, even more preferably from about 0.045 to about 0.10);

X_{h1} is O or NR_{hN} in which R_{hN} is hydrogen or C₁-C₁₀-alkyl;

R_{h0} is hydrogen or methyl;

R_{h1} and R_{h2} independently of each other are a substituted or unsubstituted C_1-C_{10} alkylene divalent radical or a divalent radical of $-R_{h4}-O-R_{h5}-$ in which R_{h4} and R_{h5} independently of each other are a substituted or unsubstituted C_1-C_{10} alkylene divalent radical;

R_{h3} is a monovalent radical of any one of formula (H-a) to (H-e)



$k1$ is zero or 1; $m1$ is an integer of 2 to 4; $m2$ is an integer of 1 to 5; $m3$ is an integer of 3 to 6; $m4$ is an integer of 2 to 5;

R_{h6} is hydrogen or methyl;

R_{h7} is a C_2-C_6 hydrocarbon radical having $(m2+1)$ valencies;

R_{h8} is a C_2-C_6 hydrocarbon radical having $(m4+1)$ valencies;

R_{h9} is ethyl or hydroxymethyl;

R_{h10} is methyl or hydromethyl;

R_{h11} is hydroxyl or methoxy;

X_{h1} is a sulfur linkage of $-S-$ or a tertiary amino linkage of $-NR_{h12}-$ in which R_{h12} is C_1-C_1 alkyl, hydroxyethyl, hydroxypropyl, or 2,3-dihydroxypropyl; and


X_{h2} is a linkage of $^-\text{NR}_{h13}-\overset{\text{O}}{\underset{\text{O}}{\text{C}}}-$ or $-\overset{\text{O}}{\underset{\text{O}}{\text{C}}}-\text{NR}_{h13}-$ in which R_{h13} is hydrogen or C_1-C_{10} alkyl.

34. The method of any one of embodiments 13 to 31, wherein said at least one first polysiloxane vinylic crosslinker and said at least one second polysiloxane vinylic crosslinker independently of one another comprises (i) at least one polysiloxane vinylic crosslinker having one sole polydiorganosiloxane segment and two terminal ethylenically-unsaturated groups selected from the group consisting of (meth)acryloyloxy groups, (meth)acryloylamino groups, vinyl carbonate groups, vinylcarbamate groups; and/or (ii) at least one chain-extended polysiloxane vinylic crosslinker having at least two polydiorganosiloxane segment and a covalent linker

between each pair of polydiorganosiloxane segments and two two terminal ethylenically-unsaturated groups selected from the group consisting of (meth)acryloyloxy groups, (meth)acryloylamino groups, vinyl carbonate groups, vinylcarbamate groups.



35. The method of any one of embodiments 13 to 31, wherein said at least one first polysiloxane vinylic crosslinker and said at least one second polysiloxane vinylic crosslinker independently of one another comprises (i) at least one polysiloxane vinylic crosslinker selected from the group consisting of α,ω -bis[3-(meth)acrylamidopropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxyethoxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxy-propyloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxy-isopropyloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxybutyloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acrylamidoethoxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acrylamidopropyloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acrylamido-isopropyloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acrylamidobutyloxy-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxyethylamino-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxypropylamino-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acryloxybutylamino-2-hydroxypropyloxy-propyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acrylamidoethylamino-2-hydroxypropyloxy-propyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acrylamido-propylamino-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[3-(meth)acrylamide-butylamino-2-hydroxypropyloxypropyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acryloxy-2-hydroxypropyloxy-ethoxypropyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acryloxy-2-hydroxypropyl-N-ethylaminopropyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acryloxy-2-hydroxypropyl-aminopropyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acryloxy-2-hydroxypropyloxy-(polyethylenoxy)propyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acryloxyethylamino-carbonyloxyethoxy-propyl]-terminated polydimethylsiloxane, α,ω -bis[(meth)acryloxyethylamino-carbonyloxy-(polyethylenoxy)propyl]-terminated polydimethylsiloxane, and combinations thereof.
36. The method of any one of embodiments 13 to 31, wherein said at least one first

polysiloxane vinylic crosslinker and said at least one second polysiloxane vinylic crosslinker independently of one another comprises at least one polysiloxane vinylic



crosslinker having a polymer chain segment (i.e., a divalent radical) of which SN is an integer of 3 or larger and each of RS₁ and RS₂ independent of one another are selected from the group consisting of: C₁-C₁₀ alkyl; phenyl; C₁-C₄-alkyl-substituted phenyl; C₁-C₄-alkoxy-substituted phenyl; phenyl-C₁-C₆-alkyl; C₁-C₁₀ fluoroalkyl; C₁-C₁₀ fluoroether; aryl; aryl C₁-C₁₈ alkyl; -alk-(OC₂H₄)_{γ1}-OR^o (in which alk is C₁-C₆ alkylene diradical, R^o is H or C₁-C₄ alkyl and γ1 is an integer from 1 to 10); a C₂-C₄₀ organic radical having at least one functional group selected from the group consisting of hydroxyl group (-OH), carboxyl group (-COOH), amino linkages of -NR_{N1}-, amide linkages of -CONR_{N1}-, amide of -CONR_{N1}R_{N1}', urethane linkages of -OCONH-, and C₁-C₄ alkoxy group, or a linear hydrophilic polymer chain, in which R_{N1} and R_{N1}' independent of each other are hydrogen or a C₁-C₁₅ alkyl.

37. The method of any one of embodiments 13 to 31, wherein said at least one first polysiloxane vinylic crosslinker and said at least one second polysiloxane vinylic crosslinker independently of one another comprises at least one polysiloxane vinylic crosslinker of formula (1) or (2)



in which:

R₀ is H or methyl;

v₁ is an integer of from 30 to 500; v₂ and v₃ independent of each other are an

integer of from 5 to 100; ω₂ and ω₃ independent of each other are an integer of from 1 to 15;

a₁ and g₁ independent of each other is zero or 1;

L₁ is a C₂-C₈ alkylene divalent radical or a divalent radical of -L₁'-X₁-L₁"-,

-{C₂H₄O}_{q1}-L₁"-, -{C₂H₄O}_{q1}-CONH-L₁"-, -L₁'-NHCOO-{C₂H₄O}_{q1}-L₁"-,

-CH₂-CH(OH)-CH₂-X₁'-{C₂H₄O}_{q2}-L₁"-, -L₁'-X₁'-CH₂-CH(OH)-CH₂-O-L₁"-, or

-{C₂H₄O}_{q1}-CH₂-CH(OH)-CH₂-O-L₁"-;

L_1' is a C_2 - C_8 alkylene divalent radical which has zero or one hydroxyl group;

L_1'' is C_3 - C_8 alkylene divalent radical which has zero or one hydroxyl group;

L_2 is a divalent radical of $-\text{C}_2\text{H}_4-\text{NHCO}-\text{O}-\{\text{C}_2\text{H}_4\text{O}\}_{q_2}-L_3'-$,

$\{\text{C}_2\text{H}_4\text{O}\}_{q_1}-\text{CONH}-R_2-\text{NHCO}-\text{O}-\{\text{C}_2\text{H}_4\text{O}\}_{q_2}-L_3'-$,

$-\text{R}_3-\text{O}-\text{CONH}-R_2-\text{NHCO}-\text{O}-\{\text{C}_2\text{H}_4\text{O}\}_{q_2}-L_3'-$, $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-\text{O}-\{\text{C}_2\text{H}_4\text{O}\}_{q_2}-L_3'-$, or

$-\{\text{C}_2\text{H}_4\text{O}\}_{q_2}-L_3'-$;

L_3 is a divalent radical of

$-L_3'-\text{O}-\{\text{C}_2\text{H}_4\text{O}\}_{q_2}-\text{CONH}-R_2-\{\text{NHCO}-\text{PE}-\text{CONH}-R_2\}_{g_1}-\text{NHCO}-\{\text{OC}_2\text{H}_4\}_{q_2}-\text{O}-L_3'-$ in which

PE is a divalent radical of

$-\{\text{CH}_2\text{CH}_2\text{O}\}_{q_3}-Z_0-\text{CF}_2-\{\text{OCF}_2\}_x-\{\text{OCF}_2\text{CF}_2\}_y-\text{OCF}_2-Z_0-\{\text{OCH}_2\text{CH}_2\}_{q_3}-$ or

$-Z_0-\{\text{CH}_2\text{CH}_2\text{O}\}_{q_4}-\left(\text{CH}_2-\overset{\text{CH}_3}{\underset{|}{\text{CH}}}-\text{O}\right)_{q_5}-\left(\text{CH}_2-\overset{\text{C}_2\text{H}_5}{\underset{|}{\text{CH}}}-\text{O}\right)_{q_6}-Z_0-$;

L_3' is C_3 - C_8 alkylene divalent radical;

R_2 is a C_4 - C_{14} hydrocarbon divalent radical;



R_3 is a C_2 - C_6 alkylene divalent radical;

X_0 , X_1' , and X_{01} independent of one another are O or NR_1 ;

X_1 is O, NR_1 , NHCOO , OCONH , CONR_1 , or NR_1CO ;

Z_0 is a direct bond or a C_1 - C_{12} alkylene divalent radical.

38. The method of any one of embodiments 13 to 37, wherein said at least one silicone-containing vinylic monomer comprises at least one silicone-containing vinylic monomer of formula (M1) or (M2):



in which: a_{M1} is zero or 1; R_{M0} is H or methyl; X_{M0} is O or NR_{M1} ; L_{M1} is a C_2 - C_8 alkylene

divalent radical or a divalent radical of $-\text{L}_{M1}'-\text{X}_{M1}-\text{L}_{M1}''-$, $\{\text{C}_2\text{H}_4\text{O}\}_{v1}-\text{CONH}-\text{L}_{M1}''-$,

$\{\text{C}_2\text{H}_4\text{O}\}_{v1}-\text{L}_{M1}''-$, $-\text{L}_{M1}'-\text{NHCOO}-\{\text{C}_2\text{H}_4\text{O}\}_{v1}-\text{L}_{M1}''-$, $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-\text{X}_{M1}'-\{\text{C}_2\text{H}_4\text{O}\}_{v2}-\text{L}_{M1}''-$,

$-L_{M1}'-X_{M1}'-CH_2-CH(OH)-CH_2-O-L_{M1}''-$, or $\left\{C_2H_4O\right\}_{v1}-CH_2-CH(OH)-CH_2-O-L_{M1}''-$; L_{M1}' is a C₂-C₈ alkylene divalent radical which has zero or one hydroxyl group; L_{M1}'' is C₃-C₈ alkylene divalent radical which has zero or one hydroxyl group; X_{M1} is O, NR_{M1}, NHCOO, OCONH, CONR_{M1}, or NR_{M1}CO; R_{M1} is H or a C₁-C₄ alkyl having 0 to 2 hydroxyl group; R₁₁ and R₁₂ independent of each other are a C₁-C₆ alkyl; X_{M1}' is O or NR₁; v₁ is an integer of 1 to 30; v₂ is an integer of 0 to 30; n₁ is an integer of 3 to 40; and r₁ is an integer of 2 or 3.

39. The method of embodiment 38, wherein said at least one silicone-containing vinylic monomer comprises tris(trimethylsilyloxy)silylpropyl (meth)acrylate, [3-(meth)acryloxy-2-hydroxypropyloxy]propylbis(trimethylsiloxy)methylsilane, [3-(meth)acryloxy-2-hydroxypropyloxy]propylbis(trimethylsiloxy)butylsilane, 3-(meth)acryloxy-2-(2-hydroxyethoxy)propyloxypropylbis(trimethylsiloxy)methylsilane, 3-(meth)acryloxy-2-hydroxypropyloxypropyltris(trimethylsiloxy)silane, N-2-(meth)acryloxyethyl-O-(methylbis(trimethylsiloxy)-3-propyl)silyl carbamate, 3-(trimethylsilyl)propylvinyl carbonate, 3-(vinyloxycarbonylthio)propyltris(trimethylsiloxy)silane, 3-[tris(trimethylsiloxy)silyl]-propylvinyl carbamate, 3-[tris(trimethylsiloxy)silyl] propyl allyl carbamate, 3-[tris(trimethylsiloxy)silyl]-propyl vinyl carbonate, or a combination thereof.
40. The method of any one of embodiments 13 to 37, wherein said at least one silicone-containing vinylic monomer comprises at least one silicone-containing vinylic monomer selected from the group consisting of α-(meth)acryloxypropyl terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-(meth)acryloxy-2-hydroxypropyloxypropyl terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-(2-hydroxyl-methacryloxypropyloxypropyl)-ω-C₁-C₄-alkyl-decamethylpentasiloxane, α-[3-(meth)acryloxyethoxy-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[3-(meth)acryloxy-propyloxy-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[3-(meth)acryloxyisopropoxy-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[3-(meth)acryloxybutyloxy-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[3-(meth)acryloxyethylamino-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[3-(meth)acryloxypropylamino-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[3-(meth)acryloxy-butylamino-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-(meth)acryloxy-(polyethylenoxy)-2-hydroxypropyloxypropyl]-terminated ω-C₁-C₄-alkyl terminated polydimethylsiloxane, α-[(meth)acryloxy-2-hydroxypropyloxy-ethoxypropyl]-terminated ω-C₁-C₄-alkyl terminated

polydimethylsiloxane, α -[(meth)acryloxy-2-hydroxypropyl-N-ethylaminopropyl]-terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -[(meth)acryloxy-2-hydroxypropyl-aminopropyl]-terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -[(meth)acryloxy-2-hydroxypropyloxy-(polyethylenoxy)propyl]-terminated ω -C₁-C₄-alkyl terminated polydimethylsiloxane, α -vinyl carbonate-terminated ω -C₁-C₄-alkyl-terminated polydimethylsiloxanes, α -vinyl carbamate-terminated ω -C₁-C₄-alkyl-terminated polydimethylsiloxane, or a mixture thereof.

41. The method of any one of embodiments 13 to 40, wherein the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 60% by weight relative to the total weight of all polymerizable materials present in the monomer mixture.
42. The method of any one of embodiments 13 to 40, wherein the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 65% by weight relative to the total weight of all polymerizable materials present in the monomer mixture.
43. The method of any one of embodiments 13 to 40, wherein the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 70% by weight relative to the total weight of all polymerizable materials present in the monomer mixture.
44. The method of any one of embodiments 13 to 40, wherein the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 75% by weight relative to the total weight of all polymerizable materials present in the monomer mixture.
45. The method of any one of embodiments 1 to 44, wherein said at least one first and second polymerizable materials independent of each other comprises at least one non-silicone vinylic crosslinker.
46. The method of any one of embodiments 1 to 44, wherein said at least one first and second polymerizable materials independent of each other comprises at least one non-silicone vinylic crosslinker selected from the group consisting of ethyleneglycol di-(meth)acrylate, diethyleneglycol di-(meth)acrylate, triethyleneglycol di-(meth)acrylate, tetraethyleneglycol di-(meth)acrylate, glycerol di-(meth)acrylate, 1,3-propanediol di-(meth)acrylate, 1,3-butanediol di-(meth)acrylate, 1,4-butanediol di-(meth)acrylate, glycerol 1,3-diglycerolate di-(meth)acrylate, ethylenebis[oxy(2-hydroxypropane-1,3-diyl)] di-(meth)acrylate, bis[2-(meth)acryloxyethyl] phosphate, trimethylolpropane di-(meth)acrylate, and 3,4-bis[(meth)acryloyl]tetrahydrofuran, diacrylamide (i.e., N-(1-oxo-2-propenyl)-2-propenamide), dimethacrylamide (i.e., N-(1-oxo-2-methyl-2-propenyl)-2-methyl-2-propenamide), N,N-di(meth)acryloyl-N-methylamine, N,N-di(meth)acryloyl-N-

ethylamine, N,N'-methylene bis(meth)acrylamide, N,N'-ethylene bis(meth)acrylamide, N,N'-dihydroxyethylene bis(meth)acrylamide, N,N'-propylene bis(meth)acrylamide, N,N'-2-hydroxypropylene bis(meth)acrylamide, N,N'-2,3-dihydroxybutylene bis(meth)acrylamide, 1,3-bis(meth)acrylamide-propane-2-yl dihydrogen phosphate (i.e., N,N'-2-phosphonyloxypropylene bis(meth)acrylamide), piperazine diacrylamide (or 1,4-bis(meth)acryloyl piperazine), tetraethyleneglycol divinyl ether, triethyleneglycol divinyl ether, diethyleneglycol divinyl ether, ethyleneglycol divinyl ether, triallyl isocyanurate, triallyl cyanurate, trimethylopropane trimethacrylate, pentaerythritol tetramethacrylate, bisphenol A dimethacrylate, and combinations thereof.

47. The method of any one of embodiments 1 to 44, wherein said at least one first and second polymerizable materials independent of each other comprises at least one non-silicone vinylic crosslinker selected from the group consisting of tetra(ethyleneglycol) di-(meth)acrylate, tri(ethyleneglycol) di-(meth)acrylate, ethyleneglycol di-(meth)acrylate, di(ethyleneglycol) di-(meth)acrylate, tetraethyleneglycol divinyl ether, triethyleneglycol divinyl ether, diethyleneglycol divinyl ether, ethyleneglycol divinyl ether, triallyl isocyanurate, triallyl cyanurate, or a combination thereof.
48. The method of any one of embodiments 1 to 47, wherein said at least one first and second polymerizable materials independent of each other comprises at least one non-silicone hydrophobic vinylic monomer.
49. The method of any one of embodiments 1 to 47, wherein said at least one first and second polymerizable materials independent of each other comprises at least one C₁-C₈ alkyl (meth)acrylate, at least one C₅-C₁₆ cycloalkyl (meth)acrylate, at least one aryl methacrylate, (meth)acrylonitrile, at least one fluorine-containing acrylic monomer, at least one vinyl alkanoate, at least one vinyloxyalkane, at least one substituted or unsubstituted styrene, vinyl toluene, vinyl chloride, vinylidene chloride, 1-butene, or combinations thereof.
50. The method of embodiment 49, wherein said at least one vinyl alkanoate is selected from the group consisting of vinyl acetate, vinyl propionate, vinyl butyrate, vinyl valerate, and combinations thereof, wherein said at least one vinyloxyalkane is selected from the group consisting of vinyl ethyl ether, propyl vinyl ether, n-butyl vinyl ether, isoputyl vinyl ether, cyclohexyl vinyl ether, t-butyl vinyl ether, and combinations thereof, wherein said at least one fluorine-containing acrylic monomer is selected from the group consisting of 2,2,2-trifluoroethyl (meth)acrylate, tetrafluoropropyl (meth)acrylate, hexafluoro-iso-propyl (meth)acrylate, hexafluorobutyl (meth)acrylate, heptafluorobutyl (meth)acrylate, octafluoropentyl (meth)acrylate, heptafluorodecyl (meth)acrylate, pentafluorophenyl (meth)acrylate, perfluorohexylethyl-thio-carbonyl-aminoethyl-methacrylate, and combinations thereof.

51. The method of any one of embodiments 1 to 47, wherein said at least one first and second polymerizable materials independent of each other comprises methyl methacrylate, ethyl methacrylate, isopropyl methacrylate, sec-butyl methacrylate, tert-butyl methacrylate, cyclohexyl methacrylate, isobornyl acrylate, isobornyl methacrylate, phenyl methacrylate, 4-tert-butylstyrene, 2-methylstyrene, styrene, 4-ethoxystyrene, 2,4-dimethylstyrene, 2,5-dimethylstyrene, 3,5-dimethylstyrene, or combinations thereof.
52. The method of any one of embodiments 1 to 47, wherein said at least one first and second polymerizable materials independent of each other comprises methyl methacrylate, tert-butyl methacrylate, cyclohexyl methacrylate, isobornyl acrylate, isobornyl methacrylate, or combinations thereof.
53. The method of any one of embodiments 1 to 47, wherein said at least one first and second polymerizable materials independent of each other comprises methyl methacrylate, tert-butyl methacrylate, cyclohexyl methacrylate, or combinations thereof.
54. The method of any one of embodiments 1 to 53, wherein said at least one first and second polymerizable materials independent of each other comprises at least one UV-absorbing vinylic monomer.
55. The method of any one of embodiments 1 to 53, wherein said at least one first and second polymerizable materials independent of each other comprises 2-[2'-hydroxy-5'-(2-methacryloxyethyl)phenyl]-2H-benzotriazole (Norbloc).
56. The method of any one of embodiments 1 to 55, wherein said at least one photochromic compound comprises a naphthopyran, an indeno-fused naphthopyran (i.e., indeno-naphthopyran), a heterocyclic ring-fused naphthopyran, a benzopyran, a phenanthropyran, a quinopyran, a quinolinopyran, a fluoroanthropyran, an anthracene-fused pyran, a tetracene-fused pyran, a spiro(benzindoline) naphthopyran, a spiro(indoline)naphthopyran, a spiro(indoline)benzopyran, a spiro(indoline)quinopyran, a spiro(indoline)pyran, a naphthoxazine, a spirobenzopyran, a spirobenzothiopyran, a naphthacenedione, a benzoxazine, a spirooxazine, a naphthoxazine, a spiro(benzindoline)naphthoxazine, a spiro(indoline)naphthoxazine, a spiro(indoline)pyrido-benzoxazine, a spiro(indoline)benzoxazine, a spiro(benzindoline)benzoxazine, a spiro(benzindoline)pyridobenzoxazine, a spiro(indoline)fluoranthroxazine, a spiro(indoline)-quinoxazine, a spiropiperidine-naphthopyran, a piro(indoline)pyronobenzoxazinone, a benzospiropyran, a naphthospiropyran, a spirobenzoxazine-pyrrolopyridine, a spironaphthoxazine-pyrrolopyridine, a spiro-oxazepin-benzoxazine, a spiro-oxazepin-naphthoxazine, a spiro(indoline)benzothiazoloxazine, a spiro(indoline)benzopyrroloxazine, a spiro(indoline)quinazolinoxazine, a spiro(indoline)-anthracenobenzoxazine, a benzofurobenzopyran, a benzothienobenzopyran, a naphthofurobenzopyran, a benzopyrano-fused

naphthopyran, a spiro(isoindoline)-naphthoxazine, a spiro(isoindoline)benzoxazine, or a mixture thereof.

57. The method of any one of embodiments 1 to 56, wherein said at least one photochromic compound is polymerizable (i.e., comprising an ethylenically-unsaturated group).
58. The method of embodiment 57, wherein said at least one photochromic compound is a coupling reaction product of a reactive (meth)acrylamido or (meth)acryloxy monomer having a first reactive functional group and a reactive photochromic compound have a second reactive functional group in the absence or presence of a coupling agent under coupling reaction, wherein the first reactive functional group is selected from the group consisting of $-\text{COCl}$, $-\text{COBr}$, $-\text{COOH}$, $-\text{NHR}_{\text{N2}}$, $-\text{NCO}$, $-\text{OH}$, $-\text{CHO}$, >C=O , >C=N-R_0 , or $-\text{N}^+\text{>C-R}_0$, wherein the second reactive functional group is selected from the group consisting of $-\text{COOH}$, $-\text{NHR}_{\text{N2}}$, >N- , >NH- , >NH- , $-\text{NCO}$, $-\text{OH}$, $-\text{SH}$, $-\text{CHO}$, >C=O , >C=N-R_0 , or $-\text{N}^+\text{>C-R}_0$, wherein R_0 is hydrogen or methyl and R_{N2} is hydrogen, a linear or branched $\text{C}_1\text{-C}_{15}$ alkyl, cyclohexyl, cyclopentyl, a substituted or unsubstituted phenyl, or a substituted- or unsubstituted-phenyl- $\text{C}_1\text{-C}_6$ alkyl.
59. The method of embodiment 58, wherein the reactive (meth)acrylamido or (meth)acryloxy monomer is selected from the group consisting of (meth)acryloyl halides ($\text{CH}_2=\text{CH}-\text{COX}$ or $\text{CH}_2=\text{CCH}_3-\text{COX}$, $\text{X}=\text{Cl}$ or Br), N-hydroxysuccinimide ester of (meth)acrylic acid, glycidyl (meth)acrylate, isocyanato- $\text{C}_2\text{-C}_6$ alkyl (meth)acrylate, amino- $\text{C}_2\text{-C}_6$ alkyl (meth)acrylamide, $\text{C}_1\text{-C}_6$ alkylamino- $\text{C}_2\text{-C}_6$ alkyl (meth)acrylamide, (meth)acrylic acid, $\text{C}_2\text{-C}_4$ alkylacrylic acid (e.g., ethylacrylic acid, propylacrylic acid, butylacrylic acid), N-2-acrylamidoglycolic acid, 3-(acryloyloxy)propanoic acid, $\text{C}_2\text{-C}_6$ hydroxylalkyl (meth)acrylate, $\text{C}_2\text{-C}_6$ hydroxyalkyl (meth)acrylamide, azlactone-containing vinylic monomers (e.g., 2-vinyl-4,4-dimethyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-1,3-oxazolin-5-one, 2-vinyl-4-methyl-4-ethyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-butyl-1,3-oxazolin-5-one, 2-vinyl-4,4-dibutyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-dodecyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-diphenyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-pentamethylene-1,3-oxazolin-5-one, 2-isopropenyl-4,4-tetramethylene-1,3-oxazolin-5-one, 2-vinyl-4,4-diethyl-1,3-oxazolin-5-one, 2-vinyl-4-methyl-4-nonyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-phenyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-benzyl-1,3-oxazolin-5-one, 2-vinyl-4,4-pentamethylene-1,3-oxazolin-5-one, and 2-vinyl-4,4-dimethyl-1,3-oxazolin-6-one, with 2-vinyl-4,4-dimethyl-1,3-oxazolin-5-one (VDMO) and 2-isopropenyl-4,4-dimethyl-1,3-oxazolin-5-one (IPDMO) as preferred azlactone-containing vinylic monomers), aziridinyl $\text{C}_1\text{-C}_{12}$ alkyl (meth)acrylate (e.g., 2-(1-aziridinyl) ethyl (meth)acrylate, 3-(1-aziridinyl) propyl

(meth)acrylate, 4-(1-aziridinyl) butyl (meth)acrylate, 6-(1-aziridinyl) hexyl (meth)acrylate, or 8-(1-aziridinyl) octyl (meth)acrylate), acrolein, methacrolein, crotonaldehyde, and combinations thereof.

60. The method of embodiment 58 or 59, wherein the reactive photochromic compound comprises 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-propyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxy-13-propyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-10,11-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-10,11-dimethoxy-13-(2-hydroxycarbonylethyl)carboxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-hydroxymethyl-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-(2-hydroxycarbonylethyl)carboxymethyl-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-hydroxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-phenyl-13-hydroxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-phenyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,7,10,11-tetramethyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-(4-(4,5-diphenyl-1H-imidazol-2-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6-methoxy-7-(3-hydroxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl)-carboxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7-dimethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11,13-trimethyl-13-(2-(2-hydroxyethoxy)-ethoxy)-indeno[2,1-

f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11,13-trimethyl-13-(2-(2-(2-(2-hydroxyethoxy)ethoxy)ethoxy)ethoxy)-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-diphenyl-13-hydroxy-13-(2-oxo-2-ethoxyethyl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-(2-oxo-2-ethoxyethyl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11-dimethyl-13-butyl-13-hydroxy-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13,13-diethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13,13-dipropyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13-carbomethoxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-diphenyl-6,7-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxy-ethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-diphenyl-6,7,10,11-tetramethoxy-13-ethyl-13-methyl-13-hydroxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 6,7-dimethoxy-2,2-diphenyl-13-hydroxy-13-butyl-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 6,7-dimethoxy-2,2-diphenyl-13-hydroxy-13-methyl-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 6,7-dimethoxy-2,2-diphenyl-13-hydroxy-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 3-(4-allyloxyphenyl)-3-(4-morpholinophenyl)-7-methoxy-11-phenyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(piperazin-1-yl)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(4-hydroxybenzamido)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-vinyl-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(carboxylic acid)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-methoxyphenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-methoxyphenyl)-6-methoxy-7-(4-(2-hydroxycarbonyl)ethyl)carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-morpholinophenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-morpholinophenyl)-6-methoxy-7-(4-(2-hydroxycarbonyl)ethyl)carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-hydroxyethoxyphenyl)-3-(4-methoxyphenyl)-11-(4-(N,N-dimethylamino)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,4-dimethoxyphenyl)-phenyl-6,11-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(3-methyl-4-methoxyphenyl)-13-hydroxy-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7,10,11-

tetramethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno [2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7-dimethoxy-13-hydroxy-13-methyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-13-oxo-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-phenyl-6-methoxy-7-morpholino-13-methyl-13-methyl-13-hydroxyethoxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-phenyl-6,11-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxy-ethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-(4-morpholinophenyl)-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b] pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-oxo-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyethoxyphenyl)-6-methoxy-7-morpholino-13,13-dimethyl-3H,13H-indeno-[2',3':3,4] naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonyl)carboxyethoxy-phenyl)-6-methoxy-7-morpholino-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxyethoxy)phenyl)-6-methoxy-7-piperidino-13,13-dimethyl-3H,13H-indene[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-(2-hydroxycarbonyl)carboxyethoxy)phenyl)-6-methoxy-7-piperidino-13,13-dimethyl-3H,13H-indene[2',3':3,4] naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyphenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyethoxy)phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonyl)carboxyethoxy)phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonyl)carboxy-phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxyethyl)piperazin-1-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-(2-(2-hydroxycarbonyl)carboxyethyl)piperazin-1-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-piperazinyl-13,13-dimethyl-3H,13H-indene[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(3-hydroxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(3-(2-hydroxycarbonyl)carboxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(4-

hydroxypipendin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl)-carboxypipendin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-methoxyphenyl-piperazin-1-yl)phenyl)-13,13-dimethyl-6-methoxy-7-hydroxy-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-methoxyphenyl-piperazin-1-yl)phenyl)-13,13-dimethyl-6-methoxy-7-(2-hydroxy-2-methyl-3-butyn-4-yl)-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-hydroxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-(2-hydroxycarbonyl-ethyl)carboxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3,4]-naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl)carboxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl)-carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-piperazinyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho [1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6,11-dimethyl-13-hydroxy-13-(1-oxo-methoxyprop-2-yl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-phenylpiperazino)-phenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-phenylpiperazino)phenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-piperazinylphenyl)-6,11-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-piperazinylphenyl)-6-methoxy-7-piperidinyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(3-methylpiperazin-1-yl)phenyl)-6-methoxy-7-(decahydroisoquinolin-2-yl)-11-*tert*-butyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-16-(ethoxycarnobyl)methyl-16-hydroxy-3,16-dihydrobenzofuro-[2',3':7,8] indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-16-(ethoxycarnobyl)-methyl-16-hydroxy-3,16-dihydrobenzofuro [2'',3'':6',7']indeno-[3',2':4,3]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-16-(ethoxycarnobyl)-methyl-16-hydroxy-3,16-dihydrobenzofuro[2'',3'':6',7']indeno[3',2':4,3]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-(ethoxycarbonyl)methyl-16-hydroxy-3,16-dihydro-benzofuro[2',3':7,8]indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16-ethyl-16H-benzofuro[2',3':3,4]naphtho [1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16H-benzofuro [2'',3'':6',7']indeno [3',2':4,3]naphtho-[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16-ethyl-16H-

benzofuro[2",3":6,7]-indeno[3',2':4,3]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,3-dihydrobenzofur-5-yl)-13-hydroxy-13-methyl-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,3-dihydrobenzofur-5-yl)-6,11-difluoro-13-hydroxy-13-(1-oxo-methoxyprop-2-yl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran, or a mixture thereof.


61. The method of embodiment 58 or 59, wherein the reactive photochromic compound is 2,2-di(4-fluorophenyl)-5-hydroxycarbonyl-6-phenyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methylphenyl)-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-hydroxy-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxyethoxycarbonyl-6-methyl-8-vinyl-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxyethoxycarbonyl-6-methyl-8-hydroxycarbonyl-2H-naphtho [1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-(2-hydroxyethoxy)ethoxy-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-phenyl-9-(2-hydroxyethoxy)-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxy-carbonyl-6-(4-(2-hydroxyethoxy)phenyl)-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-diphenylmethylol-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-diphenylmethylol-6-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-hydroxyethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-hydroxyethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-(2-hydroxyethoxy)ethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-(2-(2-hydroxyethoxy)ethoxy)ethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-methyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-phenyl-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-(3-aminophenyl)-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-2,5,7-trihydro-7-methylidene-5-oxo-furo-[3',4':3,4]naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-phenylthio-6-hydroxy-2H-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-13-hydroxy-13-methyl-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-9-methoxycarbonyl-8-(2-hydroxyethoxy)ethoxy-[3H]-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxycarbonyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxycarbonyl-8,9-dimethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-morpholinocarbonyl-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carbomethoxy-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-morpholinocarbonyl-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-methylol-6-(3-dimethylaminopropyl)methylamino-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-2,5,7-trihydro-

7-methyliden-5-oxofuro-[3',4':3,4]naphtho[1,2-b]pyran; 2,2-spiroadamantylene-5-phenylthio-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-spiro-admantylene-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 3,3-diphenyl-8-hydroxy-9-carbopropoxy-3H-naphtho[2,1-b]pyran; 2,2,5-triphenyl-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2,6-triphenyl-5-(2-(2-(2-hydroxyethoxy)ethoxy)-ethoxy)ethoxycarbonyl-[2H]-naphtho[1,2-b]pyran; 2,2,6-triphenyl-5-(2-(2-(2-oxiran-2-ylmethoxy)ethoxy)ethoxy)-ethoxycarbonyl-[2H]-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-(4-morpholinophenyl)-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-tert-butyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-(2-(2-hydroxyethoxy)ethoxy)-ethoxyphenyl)-2-phenyl-5-methoxycarbonyl-6-methyl-9-methoxy-[2H]-naphtho[1,2-b]pyran; 2-(4-(2-(2-hydroxyethoxy)ethoxy)phenyl)-2-phenyl-5-methoxycarbonyl-6-(2-(2-methylprop-2-enoxyl)ethoxy)-[2H]-naphtho[1,2-b]pyran; 3-(4-(2-(2-hydroxyethoxy)-ethoxy)ethoxyphenyl)-3-phenyl-9-methoxycarbonyl-8-methoxy-[3H]-naphtho[1,2-b]pyran; 2-(4-morpholinophenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(9-ethylcarbazol-2-yl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(9-phenylcarbazol-2-yl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-dimethylaminophenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 3-(2-fluorophenyl)-3-(4-methoxyphenyl)-8-hydroxy-9-carbopropoxy-3H-naphtho[2,1-b]pyran; 3-(2-fluorophenyl)-3-(4-methoxyphenyl)-8-hydroxy-9-carbomethoxy-3H-naphtho[2,1-b]pyran; 3-(2,4-dimethoxyphenyl)-3-(4-methoxyphenyl)-8-hydroxy-9-carbomethoxy-3H-naphtho[2,1-b]pyran; 3-(2,4,6-trifluorophenyl)-3-(2,4,6-trimethoxy-1-naphthyl)-8-acetyl-9-carboniloyl-3H-naphtho[2,1-b]pyran; 3-(4-methoxyphenyl)-3-(2-methyl-2,3-dihydrobenzofur-5-yl)-6-methoxy-12-hydroxymethyl-11-phenyl-3H-phenanthro[1,2-b]pyran; 5,5-bis(4-methoxyphenyl)-8-methylol-5H-fluorantheno[3,2-b]pyran; or a mixture thereof.


62. The method of embodiment 58 or 59, wherein the reactive photochromic compound is 1-hydroxyethyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-hydroxypropyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-aminoethyl-3,3-dimethyl-5-chlorospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-hydroxyethyl-3,3-dimethyl-8'-methoxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-(p-vinylphenyl)-3,3-dimethyl-5,6-dichlorospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-5'-hydroxymethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-aminospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-5-chloro-8'-hydroxyspiro[indoline-2,3'-[3H]-

naphtho[2,1-b][1,4]oxazine]; 1-benzyl-3,3-dimethyl-9'-vinylbenzoyloxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-benzyl-3,3-dimethyl-5'-hydroxymethylpiperidinospironaphthooxazine; 1,3,3-trimethyl-9'-hydroxyspiro[indoline-2,3'-[3H]-pyrido-[2,1-b][1,4]benzooxazine]; 5-hydroxy-6'-cyano-1,3,3-trimethyl-spiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-hydroxy-6'-phenylsulfonyl-1,3,3-trimethyl-spiro-[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5'-formyl-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3-dihydro-6'-piperazino-1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3-dihydro-6'-(4-hydroxyethyl)piperazino-1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3-dihydro-9'-hydroxy-1,3,3-trimethyl spiro 92H indole-2,3'-[3H]-naphtho[2,1-b][1,4] oxazine; 1,3,3,4,5-pentamethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine]; 1,3,3,5,6-pentamethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine]; 1-propyl-3,3,4,5-tetramethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine]; 1-propyl-3,3,5,6-tetramethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine]; 1-methoxyethyl-3,3-dimethyl-9'-allyloxycarbonyl-8'-chloroacetoxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine]; 1-allyl-3,3-spirocyclohexyl-9'-benzyloxycarbonyl-8'-chloroacetoxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine]; 5-amino-1,3,3-trimethyl-spiro[indoline-2,3'-[3H]-pyrido[3,4-f][1,4]benzooxazine]; 6-hydroxy-1',3',3',4',5'-pentamethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 6-hydroxy-1',3',3',5',6'-pentamethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 5,7-dimethoxy-1'-hydroxy-carbonylethyl-3',3'-dimethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 7-methoxy-1'-hydroxy-ethyl-3',3'-dimethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 9'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 5-chloro-9'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-5-methoxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-1,4,5-trimethylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-isopropylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-hexadecyl-spiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-octadecylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 1,1''-(1,5-pentanediy)bis[3,3-dimethyl]-9'-hydroxy-spiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1''-[1,4-phenylenebis(methylene)] bis[3,3-dimethyl]-5'-hydroxymethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1''-(1,4-butanediyl)bis[5,6-dichloro-3,3-dimethyl]-8'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-hydroxypiperidinospironaphthooxazine; 3-carboxyethyl-1,1-dimethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-naphtho[2,1-

- b][1,4]oxazine]; 1-carboxyethyl-3,3-dimethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1-dimethyl-3-hydroxyethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 3,3-dimethyl-1-hydroxyethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 3-carboxyethyl-1,1-dimethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 1-carboxyethyl-3,3-dimethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 1,1-dimethyl-3-hydroxyethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 3,3-dimethyl-1-hydroxyethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 5-amino-5'-(2-benzthiazolyl)-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-amino-5'-(5'-(2-hydroxyphenyl)-2-oxadiazolyl)-1-isopropyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-amino-5'-(5'-phenyl-2-oxadiazolyl)-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; or a mixture thereof.
63. The method of embodiment 58 or 59, wherein the reactive photochromic compound is 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxyethoxy-13-phenyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxyethoxy-13-phenyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-phenyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; or a mixture thereof.
64. The method of any one of embodiments 1 to 63, wherein said at least one first and second polymerizable materials independent of each other comprises at least one polymerizable UV/HEVL-absorbing compound.
65. The method of any one of embodiments 1 to 64, wherein the first polymerizable fluid composition further comprises at least one visible light free-radical photoinitiator, wherein the drop of the first polymerizable fluid composition is irradiated with a visible light for about 10 second or less before dispensing the second polymerizable fluid composition.
66. The method of embodiment 65, wherein said at least one visible light free radical photoinitiator comprises a benzoylphosphine initiator and/or an acylgermanium photoinitiator.
67. The method of embodiment 65, wherein said at least one first free radical photoinitiator



comprises an acylgermanium photoinitiator that is



68. The method of embodiment 66 or 67, wherein the visible light is a visible light in a region of from 420 nm to 500 nm.
69. The method of any one of embodiments 65 to 68, wherein the drop of the first polymerizable fluid composition is irradiated with a visible light for about 8 second or less.
70. The method of any one of embodiments 65 to 68, wherein the drop of the first polymerizable fluid composition is irradiated with a visible light for about 5 second or less.
71. A hydrogel contact lens obtained according to the method of any one of embodiments 1 to 70.

The previous disclosure will enable one having ordinary skill in the art to practice the invention. Various modifications, variations, and combinations can be made to the various embodiment described herein. In order to better enable the reader to understand specific embodiments and the advantages thereof, reference to the following examples is suggested. It is intended that the specification and examples be considered as exemplary.

Example 1

Oxygen Permeability Measurements

Unless specified, the oxygen transmissibility (Dk/t), the intrinsic (or edge-corrected) oxygen permeability (Dk_i or Dk_e) of a lens and a lens material are determined according to procedures described in ISO 18369-4.

Equilibrium Water Content

The equilibrium water content (EWC) of contact lenses are determined as follows.

Amount of water (expressed as percent by weight) present in a hydrated hydrogel contact lens, which is fully equilibrated in saline solution, is determined at room temperature. Quickly stack the lenses, and transfer the lens stack to the aluminum pan on the analytical balance after blotting lens in a cloth. The number of lenses for each sample pan is typically five (5). Record the pan plus hydrated weight of the lenses. Cover the pan with aluminum foil. Place pans in a laboratory oven at 100 ± 2 °C to dry for 16-18 hours. Remove pan plus lenses from the oven and cool in a desiccator for at least 30 minutes. Remove a single pan from the desiccator, and discard the aluminum foil. Weigh the pan plus dried lens sample on


an analytical balance. Repeat for all pans. The wet and dry weight of the lens samples can be calculated by subtracting the weight of the empty weigh pan.

Elastic Modulus

The elastic modulus of a contact lens is determined using a MTS insight instrument. The contact lens is first cut into a 3.12 mm wide strip using Precision Concept two stage cutter. Five thickness values are measured within 6.5mm gauge length. The strip is mounted on the instrument grips and submerged in PBS (phosphate buffered saline) with the temperature controlled at 21 ± 2 °C. Typically 5N Load cell is used for the test. Constant force and speed is applied to the sample until the sample breaks. Force and displacement data are collected by the TestWorks software. The elastic modulus value is calculated by the TestWorks software which is the slope or tangent of the stress vs. strain curve near zero elongation, in the elastic deformation region.

Chemicals

PrOH represent 1-propanol; TAA represents tert-amyl alcohol; EtOAc represents ethyl acetate; DMA represents N,N-dimethylacrylamide; MMA represents methyl methacrylate; EGMA represents ethylene glycol methyl ether methacrylate; TEGDMA represent triethyleneglycol dimethacrylate; D6 represents monobutyl-terminated monomethacryloxypropyl-terminated polydimethylsiloxane ($M_w \sim 750$ g/mol from Shin-Etsu); GA represents a hydrophilized polysiloxane vinylic crosslinker of formula (G) ($M_n \sim 6.8K$ g/mol, OH content ~ 1.2 meq/g from Shin-Etsu); "G4" macromer represents a di-methacryloyloxypropyl-terminated polysiloxane ($M_n \sim 13.5K$ g/mol, OH content ~ 1.8 meq/g) of formula (A) shown above; Vazo 64 represents 2,2'-dimethyl-2,2'-azodipropionitrile; Nobloc is 2-[3-(2H-Benzotriazol-2-yl)-4-hydroxyphenyl]ethyl methacrylate from Aldrich; Norbloc is 2-[2'-hydroxy-5'-(2-methacryloxyethyl)phenyl]-2H-benzotriazole from Aldrich; NPD-blue represent a polymerizable naphthopyran photochromic dye having a blue color in activated state (from Vivimed); NPD-green represents a polymerizable naphthopyran photochromic dye having a green color in activated state (from Vivimed); RB247 is Reactive Blue 247.



Example 2

Polymerizable Compositions

Two polymerizable compositions for forming silicone hydrogel materials are prepared

by blending all the required components to have the compositions shown in Tables 1 and 2.

Table 1

Component	Formulation A (weight unit parts)
TEGDMA	0.5
D6	31
GA	13
G4	135
DMA	17
MMA	9
EGMA	10.2
TAA	15
Vazo 64	1
NPD-blue	1.5
NPD-green	2.5
Norbloc	1.5
RB247	0.12

Table 2

Component	Formulation B (weight unit parts)
TEGDMA	2
D6	31
GA	20
DMA	17
MMA	9
EGMA	10.2
TAA	15
Vazo 64	0.5

Fabrication of SiHy contact lens with a central photochromic zone

Formulation 2A is purged with nitrogen at room temperature for 30 to 35 minutes. ~ 3 μ L of Formulation 2A is dosed to the geometrical center of the molding surface of a male (BC) mold half (made of polypropylene) of a plastic mold (power: -3.0) to form a drop in the geometrical center of the molding surface of the male mold half.

Formulation 2B is purged with nitrogen at room temperature for 30 to 35 minutes. ~60 μ L of N₂-purged Formulation 2B is added onto the molding surface of the female (FC) mold half and then the mold is closed with the male (BC) mold half having the drop adhered thereon to form a molding assembly comprising Formulation 2B and the drop of the Formulation 2A.

The molding assembly is thermally cured in an oven under the following curing profile: ramp from room temperature to 55°C at a ramp rate of about 7°C/minute; holding at 55°C for about 30 minutes; ramp from 55°C to 80°C at a ramp rate of about 7°C/minute; holding at 80°C for about 30 minutes; ramp from 80°C to 100°C at a ramp rate of about 7°C/minute; and holding at 100°C for about 30 minutes.

After de-molding, cast-molded SiHy contact lenses are extracted with PrOH for 180

minutes and then rinsed in PB (phosphate buffer containing about 0.077 wt.% $\text{NaH}_2\text{PO}_4 \cdot \text{H}_2\text{O}$ and about 0.31 wt.% $\text{Na}_2\text{HPO}_4 \cdot 2\text{H}_2\text{O}$) for 1 hour.

All the publications and patents which have been cited herein above are hereby incorporated by reference in their entireties.

What is claimed is:

1. A method for producing hydrogel contact lenses, comprising the steps of:
 - (1) obtain a first polymerizable fluid composition and a second polymerizable fluid composition, wherein the first polymerizable fluid composition comprises at least one first free-radical initiator, at least one first polymerizable material, and at least one photochromic compound, wherein said at least one first polymerizable material comprises at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 5000 Daltons or higher and is present in the first polymerizable composition in an amount of about 40% by weight or more, wherein the second polymerizable fluid composition comprises said at least one second free-radical initiator and at least one second polymerizable material and is free of any photochromic compound;
 - (2) obtaining a lens mold, wherein the lens mold comprises a male mold half having a first molding surface defining the posterior surface of a contact lens to be molded and a female mold half having a second molding surface defining the anterior surface of the contact lens to be molded, wherein the female and male mold halves are configured to receive each other such that a mold cavity is formed between the first and second molding surfaces when the mold is closed;
 - (3) applying a drop of the first polymerizable fluid composition onto the geometrical center of the first molding of the male mold half, wherein the drop has a volume of about 5 μ L or less;
 - (4) dispensing an amount of the second polymerizable fluid composition on the second molding surface of the female mold half;
 - (5) closing the female mold half with the male mold half having the drop adhered thereon to form a molding assembly comprising the second polymerizable composition and the drop of the first polymerizable composition within the mold cavity;
 - (6) curing the second polymerizable fluid composition and the drop of the first polymerizable composition to form an unprocessed silicone hydrogel contact lens having a central photochromic zone that has a diameter of about 13 mm or less, is concentric with the central axis of the unprocessed silicone hydrogel contact lens;
 - (7) separating the molding assembly into the male and female mold halves, with the unprocessed silicone hydrogel contact lens adhered onto a lens-adhered mold half which is one of the male and female mold halves;
 - (8) removing the unprocessed silicone hydrogel contact lens from the lens-adhered mold half; and

- (9) subjecting the unprocessed silicone hydrogel contact lens to post-molding processes including a hydration process and one or more other processes selected from the group consisting of extraction, surface treatment, packaging, sterilization, and combinations thereof.
2. The method of claim 1, wherein the step of (6) curing is carried out thermally, wherein said at least one first and second free-radical initiators comprise a thermal free-radical initiator.
 3. The method of claim 1, wherein the step of (6) curing is carried out actinically, wherein said at least one first and second free-radical initiators comprise a free-radical photoinitiator.
 4. The method of any one of claims 1 to 3, wherein the first polymerizable fluid composition further comprises at least one visible light free-radical photoinitiator, wherein the drop of the first polymerizable fluid composition is irradiated with a visible light for about 10 second or less before dispensing the second polymerizable fluid composition.
 5. The method of any one of claims 1 to 4, wherein said at least one first and second polymerizable materials independent of each other comprises: (a) at least one silicone-containing vinylic monomer, (b) at least one second polysiloxane vinylic crosslinker, at least one non-silicone vinylic crosslinker, or combinations thereof, (c) at least one hydrophilic vinylic monomer, and optionally (d) at least one component selected from the group consisting of a non-silicone hydrophobic vinylic monomer, a UV-absorbing vinylic monomer, and combinations thereof, wherein said at least one hydrophilic vinylic monomer comprises: (i) at least one hydrophilic (meth)acrylamido monomer having 3 to 8 carbon atoms; (ii) at least one hydrophilic (meth)acryloxy monomer; (iii) at least one hydrophilic N-vinyl amide monomer; or (iv) combinations thereof. wherein said at least one silicone-containing vinylic monomer comprises: (i) at least one silicone-containing vinylic monomer containing a tris(trialkylsiloxy)silyl group and one sole ethylenically-unsaturated group selected from the group consisting of a (meth)acryloyloxy group, a (meth)acryloylamino group, a vinyl carbonate group, and a vinylcarbamate group; (ii) at least one silicone-containing vinylic monomer containing a bis(trialkylsiloxy)-alkylsilyl group and one sole ethylenically-unsaturated group selected from the group consisting of a (meth)acryloyloxy group, a (meth)acryloylamino group, a vinyl carbonate group, and a vinylcarbamate group; (iii) at least silicone-containing vinylic monomer containing a) one sole ethylenically-unsaturated group selected from the group consisting of a (meth)acryloyloxy group, a (meth)acryloylamino group, a vinyl carbonate group, and a vinylcarbamate group and b) a polysiloxane chain

- having 2 to 30 siloxane units and terminated with an alkyl, hydroxyalkyl or methoxyalkyl group; or (iv) combinations thereof.
6. The method of claim 5, wherein the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 60% by weight relative to the total weight of all polymerizable materials present in the monomer mixture.
 7. The method of claim 5 or 6, wherein said at least one first and second polymerizable materials independent of each other comprise at least one second polysiloxane vinylic crosslinker.
 8. The method of any one of claims 1 to 7, wherein said at least one first and second polymerizable materials independent of each other comprises: at least one non-silicone vinylic crosslinker; at least one non-silicone hydrophobic vinylic monomer; at least one UV-absorbing vinylic monomer; or combinations thereof.
 9. The method of any one of claims 1 to 8, wherein said at least one photochromic compound comprises a naphthopyran, an indeno-fused naphthopyran (i.e., indeno-naphthopyran), a heterocyclic ring-fused naphthopyran, a benzopyran, a phenanthropyran, a quinopyran, a quinolinopyran, a fluoroanthropyran, an anthracene-fused pyran, a tetracene-fused pyran, a spiro(benzindoline) naphthopyran, a spiro(indoline)naphthopyran, a spiro(indoline)benzopyran, a spiro(indoline)quinopyran, a spiro(indoline)pyran, a naphthoxazine, a spirobenzopyran, a spirobenzothiopyran, a naphthacenedione, a benzoxazine, a spirooxazine, a naphthoxazine, a spiro(benzindoline)naphthoxazine, a spiro(indoline)naphthoxazine, a spiro(indoline)pyrido-benzoxazine, a spiro(indoline)benzoxazine, a spiro(benzindoline)benzoxazine, a spiro(benzindoline)pyridobenzoxazine, a spiro(indoline)fluoranthroxazine, a spiro(indoline)-quinoxazine, a spiropiperidine-naphthopyran, a piro(indoline)pyronobenzoxazinone, a benzospiropyran, a naphthospiropyran, a spirobenzoxazine-pyrrolopyridine, a spironaphthoxazine-pyrrolopyridine, a spiro-oxazepin-benzoxazine, a spiro-oxazepin-naphthoxazine, a spiro(indoline)benzothiazoloxazine, a spiro(indoline)benzopyrroloxazine, a spiro(indoline)quinazolinoxazine, a spiro(indoline)-anthracenobenzoxazine, a benzofurobenzopyran, a benzothienobenzopyran, a naphthofurobenzopyran, a benzopyrano-fused naphthopyran, a spiro(isoindoline)-naphthoxazine, a spiro(isoindoline)benzoxazine, or a mixture thereof.
 10. The method of any one of claims 1 to 9, wherein said at least one photochromic compound is polymerizable (i.e., comprising an ethylenically-unsaturated group).
 11. The method of claim 10, wherein said at least one photochromic compound is a coupling reaction product of a reactive (meth)acrylamido or (meth)acryloxy monomer having a first reactive functional group and a reactive photochromic compound have a

second reactive functional group in the absence or presence of a coupling agent under coupling reaction, wherein the first reactive functional group is selected from the group consisting of $-\text{COCl}$, $-\text{COBr}$, $-\text{COOH}$, $-\text{NHR}_{\text{N}2}$, $-\text{NCO}$, $-\text{OH}$, $-\text{CHO}$, $\text{---}\text{O}$, $\text{---}\text{N}^{\text{R}_0}$, or $-\text{N}^{\text{R}_0}$, wherein the second reactive functional group is selected from the group consisting of $-\text{COOH}$, $-\text{NHR}_{\text{N}2}$, $\text{---}\text{N}^{\text{R}_0}$, $\text{---}\text{NH}$, $\text{---}\text{NH}$, $\text{---}\text{NH}$, $-\text{NCO}$, $-\text{OH}$, $-\text{SH}$, $-\text{CHO}$, $\text{---}\text{O}$, $\text{---}\text{N}^{\text{R}_0}$, or $-\text{N}^{\text{R}_0}$, wherein R_0 is hydrogen or methyl and $\text{R}_{\text{N}2}$ is hydrogen, a linear or branched $\text{C}_1\text{--C}_{15}$ alkyl, cyclohexyl, cyclopentyl, a substituted or unsubstituted phenyl, or a substituted- or unsubstituted-phenyl- $\text{C}_1\text{--C}_6$ alkyl.

12. The method of claim 11, wherein the reactive (meth)acrylamido or (meth)acryloxy monomer is selected from the group consisting of (meth)acryloyl halides ($\text{CH}_2=\text{CH}-\text{COX}$ or $\text{CH}_2=\text{CCH}_3-\text{COX}$, $\text{X}=\text{Cl}$ or Br), N-hydroxysuccinimide ester of (meth)acrylic acid, glycidyl (meth)acrylate, isocyanato- $\text{C}_2\text{--C}_6$ alkyl (meth)acrylate, amino- $\text{C}_2\text{--C}_6$ alkyl (meth)acrylamide, $\text{C}_1\text{--C}_6$ alkylamino- $\text{C}_2\text{--C}_6$ alkyl (meth)acrylamide, (meth)acrylic acid, $\text{C}_2\text{--C}_4$ alkylacrylic acid (e.g., ethylacrylic acid, propylacrylic acid, butylacrylic acid), N-2-acrylamidoglycolic acid, 3-(acryloyloxy)propanoic acid, $\text{C}_2\text{--C}_6$ hydroxylalkyl (meth)acrylate, $\text{C}_2\text{--C}_6$ hydroxyalkyl (meth)acrylamide, azlactone-containing vinylic monomers (e.g., 2-vinyl-4,4-dimethyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-1,3-oxazolin-5-one, 2-vinyl-4-methyl-4-ethyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-butyl-1,3-oxazolin-5-one, 2-vinyl-4,4-dibutyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-dodecyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-diphenyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-pentamethylene-1,3-oxazolin-5-one, 2-isopropenyl-4,4-tetramethylene-1,3-oxazolin-5-one, 2-vinyl-4,4-diethyl-1,3-oxazolin-5-one, 2-vinyl-4-methyl-4-nonyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-phenyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-benzyl-1,3-oxazolin-5-one, 2-vinyl-4,4-pentamethylene-1,3-oxazolin-5-one, and 2-vinyl-4,4-dimethyl-1,3-oxazolin-6-one, with 2-vinyl-4,4-dimethyl-1,3-oxazolin-5-one (VDMO) and 2-isopropenyl-4,4-dimethyl-1,3-oxazolin-5-one (IPDMO) as preferred azlactone-containing vinylic monomers), aziridinyl $\text{C}_1\text{--C}_{12}$ alkyl (meth)acrylate (e.g., 2-(1-aziridinyl) ethyl (meth)acrylate, 3-(1-aziridinyl) propyl (meth)acrylate, 4-(1-aziridinyl) butyl (meth)acrylate, 6-(1-aziridinyl) hexyl (meth)acrylate, or 8-(1-aziridinyl) octyl (meth)acrylate), acrolein, methacrolein, crotonaldehyde, and combinations thereof.
13. The method of claim 11 or 12, wherein the reactive photochromic compound comprises 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonyl-ethyl)carboxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-

b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxy-13-phenyl-3H,13H-indeno [2',3':3,4] naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-propyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxy-13-propyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-10,11-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-10,11-dimethoxy-13-(2-hydroxycarbonylethyl)carboxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-hydroxymethyl-13-methyl-3H,13H-indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-(2-hydroxycarbonylethyl)carboxymethyl-13-methyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-hydroxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-phenyl-13-hydroxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-phenyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,7,10,11-tetramethyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-(4-(4,5-diphenyl-1H-imidazol-2-yl))phenyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6-methoxy-7-(3-hydroxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl)-carboxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7-dimethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11,13-trimethyl-13-(2-(2-hydroxyethoxy)-ethoxy)-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11,13-trimethyl-13-(2-(2-(2-hydroxyethoxy)ethoxy)ethoxy)-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-diphenyl-13-hydroxy-13-(2-oxo-2-ethoxyethyl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-(2-oxo-2-ethoxyethyl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11-dimethyl-13-butyl-13-hydroxy-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13,13-diethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-

methoxy-11-phenyl-13,13-dipropyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13-carbomethoxy-13-methyl-3H,13H-indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-diphenyl-6,7-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxy-ethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-diphenyl-6,7,10,11-tetramethoxy-13-ethyl-13-methyl-13-hydroxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho [1,2-b]pyran; 6,7-dimthoxy-2,2-diphenyl-13-hydroxy-13-butyl-2H,13H-indeno[1',2':4,3] naphtho[1,2-b]pyran; 6,7-dimthoxy-2,2-diphenyl-13-hydroxy-13-methyl-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 6,7-dimthoxy-2,2-diphenyl-13-hydroxy-13-methyl-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 3-(4-allyloxyphenyl)-3-(4-morpholinophenyl)-7-methoxy-11-phenyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(piperazin-1-yl)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(4-hydroxybenzamido)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-vinyl-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(carboxylic acid)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-methoxyphenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-methoxyphenyl)-6-methoxy-7-(4-(2-hydroxycarbonyl)ethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-morpholinophenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-morpholinophenyl)-6-methoxy-7-(4-(2-hydroxycarbonyl)ethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4] naphtho[1,2-b]pyran; 3-(4-hydroxyethoxyphenyl)-3-(4-methoxyphenyl)-11-(4-(N,N-dimethylamino)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,4-dimethoxyphenyl)-phenyl-6,11-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(3-methyl-4-methoxyphenyl)-13-hydroxy-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno [2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7-dimethoxy-13-hydroxy-13-methyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-13-oxo-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-phenyl-6-methoxy-7-

mprrhino-13-methyl-13-methyl-13-hydroxyethoxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-phenyl-6,11-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxy-ethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-(4-morpholinophenyl)-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b] pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-oxo-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyethoxyphenyl)-6-methoxy-7-morpholino-13,13-dimethyl-3H,13H-indeno[2',3':3,4] naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonyl)carboxyethoxy-phenyl)-6-methoxy-7-morpholino-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxyethoxy)phenyl)-6-methoxy-7-piperidino-13,13-dimethyl-3H,13H-indene[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-(2-hydroxycarbonyl)carboxyethoxy)phenyl)-6-methoxy-7-piperidino-13,13-dimethyl-3H,13H-indene[2',3':3,4] naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyphenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyethoxy)phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonyl)carboxyethoxy)phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonyl)carboxyphenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxyethyl)piperazin-1-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-(2-(2-hydroxycarbonyl)carboxyethyl)piperazin-1-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-piperazinyl-13,13-dimethyl-3H,13H-indene[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(3-hydroxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(3-(2-hydroxycarbonyl) carboxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(4-hydroxypipendin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(4-(2-hydroxycarbonyl)carboxypipendin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl-piperazin-1-yl)phenyl)-13,13-dimethyl-6-methoxy-7-hydroxy-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-methoxyphenyl-piperazin-1-yl)phenyl)-13,13-dimethyl-6-methoxy-7-(2-hydroxy-2-methyl-3-butyn-4-yl)-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-hydroxymethylene-

- piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-(2-hydroxycarbonyl-ethyl)carboxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3,4]-naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl)carboxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl)-carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-piperazinyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho [1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6,11-dimethyl-13-hydroxy-13-(1-oxo-methoxyprop-2-yl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-phenylpiperazino)-phenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-phenylpiperazino)phenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-piperazinylphenyl)-6,11-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-piperazinylphenyl)-6-methoxy-7-piperidinyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(3-methylpiperazin-1-yl)phenyl)-6-methoxy-7-(decahydroisoquinolin-2-yl)-11-*tert*-butyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-16-(ethoxycarbonyl)methyl-16-hydroxy-3,16-dihydrobenzofuro-[2',3':7,8] indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-16-(ethoxycarbonyl)-methyl-16-hydroxy-3,16-dihydrobenzofuro [2'',3'':6',7']indeno-[3',2':4,3]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-16-(ethoxycarbonyl)-methyl-16-hydroxy-3,16-dihydrobenzofuro[2'',3'':6',7']indeno[3',2':4,3]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-(ethoxycarbonyl)methyl-16-hydroxy-3,16-dihydro-benzofuro[2',3':7,8]indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16-ethyl-16H-benzofuro[2',3':7,8] indeno[2',3':3,4]naphtho [1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16H-benzofuro [2'',3'':6,7]indeno [3',2':4,3]naphtho-[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16-ethyl-16H-benzofuro[2'',3'':6,7]-indeno[3',2':4,3]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,3-dihydrobenzofur-5-yl)-13-hydroxy-13-methyl-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,3-dihydrobenzofur-5-yl)-6,11-difluoro-13-hydroxy-13-(1-oxo-methoxyprop-2-yl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran, or a mixture thereof.
14. The method of claim 11 or 12, wherein the reactive photochromic compound is 2,2-di(4-fluorophenyl)-5-hydroxycarbonyl-6-phenyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methylphenyl)-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-

methoxyphenyl)-5-methoxycarbonyl-6-hydroxy-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxyethoxycarbonyl-6-methyl-8-vinyl-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxyethoxycarbonyl-6-methyl-8-hydroxycarbonyl-2H-naphtho [1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-(2-hydroxyethoxy)ethoxy-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-phenyl-9-(2-hydroxyethoxy)-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxy-carbonyl-6-(4-(2-hydroxyethoxy)phenyl)-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-diphenylmethylol-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-diphenylmethylol-6-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-hydroxyethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-hydroxyethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-(2-hydroxyethoxy)ethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-(2-(2-hydroxyethoxy)ethoxy)ethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-methyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-phenyl-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-(3-aminophenyl)-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-2,5,7-trihydro-7-methylidene-5-oxo-furo-[3',4':3,4]naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-phenylthio-6-hydroxy-2H-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-13-hydroxy-13-methyl-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-9-methoxycarbonyl-8-(2-hydroxyethoxy)ethoxy-[3H]-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxycarbonyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxycarbonyl-8,9-dimethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-morpholinocarbonyl-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carbomethoxy-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-morpholinocarbonyl-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-methylol-6-(3-dimethylaminopropyl)methylamino-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-2,5,7-trihydro-7-methyliden-5-oxofuro-[3',4':3,4]naphtho[1,2-b]pyran; 2,2-spiroadamantylene-5-phenylthio-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl)-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-spiro-admantylene-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 3,3-diphenyl-8-hydroxy-9-carbopropoxy-3H-naphtho[2,1-b]pyran; 2,2,5-triphenyl-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2,6-triphenyl-5-(2-(2-(2-(2-hydroxyethoxy)ethoxy)-ethoxy)ethoxy)carbonyl-[2H]-naphtho[1,2-b]pyran; 2,2,6-triphenyl-5-(2-(2-(2-oxiran-2-ylmethoxy)ethoxy)ethoxy)-ethoxycarbonyl)-

[2H]-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-(4-morpholinophenyl)-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-tert-butyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-(2-(2-hydroxyethoxy)ethoxy)ethoxyphenyl)-2-phenyl-5-methoxycarbonyl-6-methyl-9-methoxy-[2H]-naphtho[1,2-b]pyran; 2-(4-(2-(2-hydroxyethoxy)ethoxy)phenyl)-2-phenyl-5-methoxycarbonyl-6-(2-(2-methylprop-2-enoxyloxy)ethoxy)-[2H]-naphtho[1,2-b]pyran; 3-(4-(2-(2-hydroxyethoxy)ethoxy)ethoxyphenyl)-3-phenyl-9-methoxycarbonyl-8-methoxy-[3H]-naphtho[1,2-b]pyran; 2-(4-morpholinophenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(9-ethylcarbazol-2-yl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(9-phenylcarbazol-2-yl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-dimethylaminophenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 3-(2-fluorophenyl)-3-(4-methoxyphenyl)-8-hydroxy-9-carbopropoxy-3H-naphtho[2,1-b]pyran; 3-(2-fluorophenyl)-3-(4-methoxyphenyl)-8-hydroxy-9-carbomethoxy-3H-naphtho[2,1-b]pyran; 3-(2,4-dimethoxyphenyl)-3-(4-methoxyphenyl)-8-hydroxy-9-carbomethoxy-3H-naphtho[2,1-b]pyran; 3-(2,4,6-trifluorophenyl)-3-(2,4,6-trimethoxy-1-naphthyl)-8-acetyl-9-carboniloyl-3H-naphtho[2,1-b]pyran; 3-(4-methoxyphenyl)-3-(2-methyl-2,3-dihydrobenzofur-5-yl)-6-methoxy-12-hydroxymethyl-11-phenyl-3H-phenanthro[1,2-b]pyran; 5,5-bis(4-methoxyphenyl)-8-methylol-5H-fluorantheno[3,2-b]pyran; or a mixture thereof.

15. The method of claim 11 or 12, wherein the reactive photochromic compound is 1-hydroxyethyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-hydroxypropyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-aminoethyl-3,3-dimethyl-5-chlorospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-hydroxyethyl-3,3-dimethyl-8'-methoxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-(p-vinylphenyl)-3,3-dimethyl-5,6-dichlorospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-5'-hydroxymethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-aminospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-5-chloro-8'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-benzyl-3,3-dimethyl-9'-vinylbenzoyloxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-benzyl-3,3-dimethyl-5'-hydroxymethylpiperidinospironaphthooxazine; 1,3,3-trimethyl-9'-hydroxyspiro[indoline-2,3'-[3H]-pyrido-[2,1-b][1,4]benzooxazine]; 5-hydroxy-6'-cyano-1,3,3-trimethyl-spiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-hydroxy-6'-phenylsulfonyl-1,3,3-trimethyl-spiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5'-formyl-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3-dihydro-6'-piperazino-

1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine; 1,3-dihydro-6'-(4-hydroxyethyl)piperazino-1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine; 1,3-dihydro-9'-hydroxy-1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4] oxazine; 1,3,3,4,5-pentamethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1,3,3,5,6-pentamethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-propyl-3,3,4,5-tetramethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-propyl-3,3,5,6-tetramethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-methoxyethyl-3,3-dimethyl-9'-allyloxycarbonyl-8'-chloroacetoxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-allyl-3,3-spirocyclohexyl-9'-benzyloxycarbonyl-8'-chloroacetoxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 5-amino-1,3,3-trimethyl-spiro[indoline-2,3'-[3H]-pyrido[3,4-f][1,4]benzoxazine; 6-hydroxy-1',3',3',4',5'-pentamethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 6-hydroxy-1',3',3',5',6'-pentamethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 5,7-dimethoxy-1'-hydroxy-carbonyl-ethyl-3',3'-dimethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 7-methoxy-1'-hydroxy-ethyl-3',3'-dimethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 9'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 5-chloro-9'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-5-methoxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-1,4,5-trimethylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-isopropylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-hexadecyl-spiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-octadecylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 1,1''-(1,5-pentanedyl)bis[3,3-dimethyl]-9'-hydroxy-spiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1''-[1,4-phenylenebis(methylene)] bis[3,3-dimethyl]-5'-hydroxymethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1''-(1,4-butanediyl)bis[5,6-dichloro-3,3-dimethyl]-8'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-hydroxypiperidinospironaphthooxazine; 3-carboxyethyl-1,1-dimethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-carboxyethyl-3,3-dimethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1-dimethyl-3-hydroxyethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 3,3-dimethyl-1-hydroxyethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 3-carboxyethyl-1,1-dimethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 1-carboxyethyl-3,3-dimethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 1,1-dimethyl-3-hydroxyethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-

- [3H]-pyrido[2,1-b][1,4]benzoxazine]; 3,3-dimethyl-1-hydroxyethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 5-amino-5'-(2-benzthiazolyl)-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-amino-5'-(5'-(2-hydroxyphenyl)-2-oxadiazolyl)-1-isopropyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-amino-5'-(5'-phenyl-2-oxadiazolyl)-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; or a mixture thereof.
16. The method of claim 11 or 12, wherein the reactive photochromic compound is 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; or a mixture thereof.
17. The method of any one of claims 1 to 16, wherein said at least one first and second polymerizable materials independent of each other comprises at least one polymerizable UV/HEVL-absorbing compound.
18. A hydrogel contact lens obtained according to the method of any one of claims 1 to 17.