

ABSTRACT

[PROBLEM TO BE SOLVED] To provide an organopolysiloxane paint composition capable of forming an antifouling coating film having an excellent long-term antifouling property.

5 [SOLUTION] A curable composition obtained by mixing:

(A) 100 parts by weight of a reaction curable silicone rubber with:

(B) 1 to 100 parts by weight of an organopolysiloxane mixture including a product obtained by an R^2OH elimination reaction

10 of:

(B1) an organopolysiloxane represented by:



wherein n is an integer of 2 or more and R^2 each is independently a monovalent hydrocarbon group, and

15 (B2) an organopolysiloxane having at least one structure represented by:



wherein R^3 is a divalent hydrocarbon group, in a molecule.