



159159

23 FEB 2000

METHOD FOR LAMINATING WOODY FIBERBOARD

FIELD OF THE INVENTION

The present invention relates to a method for laminating woody fiberboard for various kinds of usage.

BACKGROUND OF THE INVENTION

A woody fiberboard, a so called MDF board (Medium Density Fiberboard) is produced by molding into a plate form under the heat and pressure, fibers obtained by splitting wood chips into a cotton substance along with an adhesive. The MDF board is used for various materials for construction, furniture, washstands and kitchen units owing to its light weight, high strength and water resistance.

The MDF has remarkably excellent characteristics in that sapling and thinned wood can be utilized as a raw material and therefore, it is a new material attracting world wide attention in a view of the effective utilization of forest resources and the global environmental issues, such as the world wide shortage of forest resources.

Furthermore, the MDF board has the following excellent characteristics; a warp, twisting and cracking which are liable to occur in natural wood, can be prevented. It has feeling that is equivalent to natural wood. It has strength and toughness that are higher by 1.5 to 3 times than natural wood. It is stable against water and moisture. No unevenness is

formed on the surface during a long term use.

However, due to the production process thereof comprising pressing under the heat and pressure, there is a difference in material and specific gravity between the surface part and the central part of the article and has a problem, in that the smooth coating surface suffers immediately after coating a slight unevenness, from 3 to 6 months, because of the unevenness in degree of penetration of the coated material.

The MDF board also has a problem, in that swelling, warping and cracking at cutted ends occurs upon absorbing water.

Furthermore, the MDF board cannot be used where a certain strength is required and the thickness thereof is limited to about 40 mm at most, so that it can not be used for an article having a large thickness.

It is also impossible to produce articles having various sizes and shapes, such as an article having a curved surface and an article having a small thickness and a high strength.

SUMMARY OF THE INVENTION

The invention has been developed in order to solve the problems described above. An object of the invention is therefore to provide a method for laminating a woody fiberboard, in that woody fiberboards are laminated with increasing the strength thereof, the laminated woody fiberboard is processed by cutting into a prescribed shape and the strength of the

processed article is further increased to finish the product so as to obtain an article having various sizes and shapes.

A laminated body of a woody fiberboard having various sizes and shapes can be obtained by a method for laminating a woody fiberboard comprising the steps of:

molding wood chips using an adhesive as a binder, to produce a woody fiberboard having a prescribed thickness;

impregnating or coating a single board of the woody fiberboard with a polyurethane series primer, followed by drying;

laminating by adhering two or more of the dried woody fiberboards with an aqueous polymeric isocyanate series adhesive;

processing the laminated woody fiberboard by a cutting blade into a prescribed shape;

impregnating or coating the processed article with a polyurethane series primer, followed by drying; and

impregnating or coating the dried article with one or more of a urethane series resin, a melamine series resin, a polyester series resin and a lacquer.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a perspective view showing an embodiment where plural woody fiberboards are laminated.

Fig. 2 is a perspective view showing another embodiment where plural woody fiberboards are laminated.

Fig. 3 is a perspective view showing still another embodiment where plural woody fiberboards are laminated.

Fig. 4 is a perspective view showing a further embodiment where plural woody fiberboards are laminated.

Fig. 5 is a perspective view showing still further embodiment where plural woody fiberboards are laminated.

Fig. 6 is a perspective view showing an embodiment where an article obtained by laminating plural woody fiberboards is processed to produce a product.

PREFERRED EMBODIMENTS OF THE INVENTION

An embodiment of the method for laminating a woody fiberboard according to the invention will be described with reference to examples thereof.

As a material of the woody fiberboard of the invention, a woody fiberboard is used, which is obtained by molding into a plate form under the heat and pressure, fibers obtained by splitting wood chips into a cotton substance, with a urethane series or melamine series adhesive as a binder.

The woody fiberboard is of lightweight of a specific gravity of from 0.40 to 0.70, with an excellent strength in comparison to conventional particleboard and sheathing board and has a various kind of usage. For example, a fiberboard using conifer chips having a thickness of 3 mm has a specific gravity of 0.525, a density of 0.75 g/mm, a bending strength of 440 kg/mm, a peeling strength of 10.5 kg/mm, and water

absorption ratio of 47%. While the strength of the board is generally proportional to the specific gravity, the woody fiberboard used in the invention is lighter than the particle board, and has higher strength by 1.5 to 2.0 times and a higher impact strength by 2 to 3 times than those of particle board. Furthermore, the woody fiberboard has a stability against water and moisture, that is equivalent to plywood.

As the woody fiberboard, those having a thickness of about from 2.5 to 40 mm are suitably selected and used.

Both surfaces of the woody fiberboard having a prescribed thickness are impregnated or coated with a polyurethane series primer, to remove warp and distortion inherent in the board and simultaneously increase the strength thereof by 1.5 times or more.

After impregnating or coating the polyurethane series primer, the woody fiberboard is then placed in a drying chamber at a temperature of 25°C or more and a humidity of 60% or more to dry the woody fiberboard over 8 hours or more.

Examples of dried woody fiberboard that are laminated and adhered in all directions (in plural directions) are shown in Figs. 1 to 5. An aqueous polymeric isocyanate series adhesive is used as the adhesive for laminating. The number of laminated layers can be appropriately determined by considering the final product.

The adhesive, used for the woody fiberboard will be

described in more detail below:

100 units (weight ratio) of a modified vinyl resin as a base agent and 15 units of a polyisocyanate as a hardening agent are stirred and evenly mixed. The mixture can be used until 30 minutes after mixing at the temperature of 25 to 35 °C in the summer season and until 1 hour after mixing at a temperature of 5 to 25°C in the other seasons.

The strength of the woody fiberboard can be increased by 2 to 3 times according to the procedures described above.

After sufficiently adhering and jointing the woody fiberboards, the laminated woody fiberboard is processed by cutting into a prescribed shape depending on the usage by using processing means. Digging through processing and hollowing out processing can also be conducted.

The cutting process of the woody fiberboard is conducted by using a new ceramics bit tool, an industrial diamond bit tool, a superhard bit tool and a diamond cut chip saw. An automated computer controlled cutting process can be used.

The article obtained by processing the woody fiberboard depending on various kinds of usage is impregnated or coated with a polyurethane series primer, dried and hardened in a drying chamber over 8 hours and more. The drying chamber has a temperature of 25°C or more and a humidity of 60%.

After drying and hardening the woody fiberboard that has been processed into the prescribed shape, it is impregnated

or coated with a urethane series resin, a melamine series resin, a polyester series resin or a lacquer, to produce a laminated solid processed product.

Examples of the mode of laminating the woody fiberboard will be described below.

EXAMPLE 1

In the embodiment shown in Fig. 1, plurality of the woody fiberboards 1 is laminated in the horizontal direction.

EXAMPLE 2

In the embodiment shown in Fig. 2, an article obtained by laminating the woody fiberboards 1 in the horizontal direction and an article obtained by laminating them in the vertical direction are adhered on the side walls thereof.

EXAMPLE 3

In the embodiment shown in Fig. 3, plurality of articles obtained by laminating the woody fiberboards 1 in the horizontal direction and an article obtained by laminating them in the vertical direction are adhered into one body in the vertical direction. In this example, three layers are formed.

EXAMPLE 4

In the embodiment shown in Fig. 4, plurality of articles obtained by laminating the woody fiberboards 1 in the vertical direction are cutted into a triangular prism shape, and are adhered to each other to form a quadratic prism shape.

EXAMPLE 5

In the embodiment shown in Fig 5, plurality of articles obtained by laminating the woody fiberboards 1 in the horizontal direction and plurality of articles obtained by laminating them in the vertical direction are adhered into one body in the vertical direction to form five layers.

The laminate obtained by laminating the woody fiberboards 1 to form five layers is processed by cutting into the shape shown in Fig. 6 by a superhard bit tool or a diamond cut chip saw or the like.

In the invention, because the woody fiberboard used as a raw material comprises fibers obtained by splitting wood chips, sapling and thinned wood can be utilized to effectively utilize the forest resources.

In the invention, furthermore, a single board of a woody fiberboard is impregnated or coated with a polyurethane series material to increase the strength of the single board and then the woody fiberboard is laminated by using an isocyanate series adhesive to further increase the strength. The laminated fiberboard is further processed by cutting into a necessary shape. While the laminated fiberboard has certain hardness in this stage, the cutting procedure can be easily conducted to process into various sizes and shapes and thus it is excellent in processing property. Thereafter a further higher hardness (200 kg/cm²) can be obtained by impregnating or

coating with urethane series solvent. As a result, a product having an excellent strength in comparison to natural wood can be obtained.

Because the woody fiberboard comprises wood chips containing pores inside, it can be easily impregnated and penetrated with various solvents and the strength thereof can be uniform to completely prevent the formation of cracking, distortion, warp and worm-eaten parts, which frequently occur in natural wood.

Furthermore, because the woody fiberboards are laminated, a pattern like annual rings of a tree can be created in various forms depending on necessity, to obtain the beauty of natural wood. The feeling on touching of the laminated woody fiberboard is the same as that of natural wood.

Accordingly, various solid processed products, such as articles for handicapped persons, interior equipments, furniture and household goods, house related equipments, and construction finishing materials, can be produced. Furthermore, because the laminated woody fiberboard has excellent water resistance, it can be applied to various exterior materials for construction, civil engineering related materials, various exterior materials and interior sanitary and kitchen parts. Moreover, because the laminated woody fiberboard has a high strength, it can also be applied to various structural members for construction and civil

engineering construction and structural member of a large cross sectional area.

WHAT IS CLAIMED IS:

1. A method for laminating a woody fiberboard comprising the steps of:

molding wood chips using an adhesive as a binder to produce a woody fiberboard having a prescribed thickness;

impregnating or coating a single board of said woody fiberboard with a polyurethane series primer, followed by drying;

laminating by adhering two or more of said dried woody fiberboards with an aqueous polymeric isocyanate series adhesive;

processing said laminated woody fiberboard with a cutting blade into a prescribed shape;

impregnating or coating said processed article with a polyurethane series primer, followed by drying; and

impregnating or coating said dried article with one or more of a urethane series resin, a melamine series resin, a polyester series resin and a lacquer.