

Novel phosphonamidates – synthesis and flame retardant applications


Technical Field of the Invention

The present invention relates to novel phosphonamidate compounds and to their use as flame retardant substances.

Background of the Invention

These days polymers based on various organic monomers are present almost everywhere around us. They are equally used for exterior as well as interior purposes. For that reason it is very important to make most of these polymers flame retardant to minimize the risk of fires. In the past most common flame retardants were halogenated organic compounds which showed a very high efficiency in flame retardation of polymers. These halogenated compounds act by gas-phase mechanism, which means that in case of fire they decompose and easily release halogen-radicals. These halogen radicals act as a scavenger to trap reactive $H^{\bullet}$ - and $OH^{\bullet}$ -radicals so that there is no heat flow to sustain the flame. Nowadays some of these halogen based flame retardants have been banned because they are environmentally not very benign. Hence there is more than ever a need of novel flame retardants that are able to replace and act like halogenated ones.¹ DOPO (9,10-dihydro-9-oxa-phosphaphenanthrene-10-oxide)² and some derivatives thereof have drawn much attention in the last decade due to their flame-retardant properties.³ It is mainly accepted and investigated in detail that these compounds predominantly act by a gas phase-mechanism.⁴

Scheme 1: DOPO and its derivatives




During combustion they decompose and release low molecular weight phosphorus-containing fragments that are able to scavenge $H^{\bullet}$ - and $OH^{\bullet}$ -radicals.^{4a,5}

In the literature there are a lot of reports dealing with the synthesis and flame retardant application of alkyl DOPO-derivatives.^{3,6}

Apart from this, one can also find several reports dealing with the synthesis and application as flame retardant of alkoxy DOPO-derivatives. In contrast to the derivatives mentioned above one could find some publications dealing with amino DOPO-derivatives.^{7,8} To the best of our knowledge there are only few reports which describe the synthesis and characterization of amino-DOPO derivatives.^{7h-k} Again the synthesis proceeds via a two-step reaction sequence as mentioned before.⁸

Scheme 2: Preparation of amino-DOPO derivatives via a two-step reaction sequence⁸




Additionally one can also find a few amino-thio-DOPO derivatives in literature.⁹

Although phosphinate derivatives of DOPO are commonly known as flame retardants for various polymeric systems, the amino derivatives of DOPO are not well studied as flame retardants. It is known that organophosphorus compounds containing a P-N bond i.e. phosphoramidates exhibit superior flame retardant properties for example on cellulose.¹⁰ Hence it would be interesting to develop amino derivatives of DOPO and evaluate them, for their FR efficacy. There are a few patent documents mentioning flame retardant application of amino-DOPO derivatives on various polymeric resin compositions⁷. But the derivatives reported in these patent documents have not been characterized by appropriate analytical methods. Some alkylamino-DOPO derivatives have also been mentioned in EP 1889878 A1 as possible flame retardant structures. However, in said patent document there is no report on such structures

having been prepared nor is any method of their preparation elaborated.¹¹ Furthermore there are amino derivatives of DOPO which have been reported as component in organic light emitting diodes (OLEDs), batteries and azo-dyes.⁸


Scheme 3: Amino-DOPO derivatives previously described in the Literature



Summary of the Invention

According to one aspect of the invention, there is provided a group of novel phosphoramidate compounds, which are particularly contemplated for their flame retardant properties in combination with an improved thermal stability and concomitant processability at elevated temperatures such as in a thermoplastic process. The phosphoramidate compounds are selected from the group consisting of:

- AA-DOPO;
- BHEA-DOPO;
- PB-DOPO;
- PDAB-DOPO;
- a compound according to Formula (I)



R¹ = H, alkyl (C1-8), alkoxy (C1-8), amine (C1-8), OH, SR (R = H, alkyl), O-metal ^(I)

R² = H, alkyl (C1-8), alkoxy (C1-8), amine (C1-8), OH, SR (R = H, alkyl), O-metal


R³ = H, alkyl (C1-8), alkoxy (C1-8), amine (C1-8), OH, SR (R = H, alkyl), O-metal

Y = NH, N-DOPO moiety, O, S

X = NH, NR (R = alkyl)


n = 1-8

m = 1-8



particularly:

- TESPA-DOPO, or
- TMSPA-DOPO;
- a compound according to Formula (II)




X = O, NR (R = H, alkyl), S

Y = N-DOPO moiety, CH₂

Z = O, NR (R = H, alkyl), S

m = 0-8


n = 0-8



(II)

particularly:

- EAB-DOPO,
- DEA-DDOPO, or
- DEA-TDOPO;
- a compound according to formula (III)




Y=NR [R=H, alkyl, DOPO-moiety, any organophosphorus compound eg PO(OR)₂ (R=alkyl or aryl) or PO(OR¹)R² (R¹=alkyl or aryl, R²=alkyl or aryl), COR (R=O-alkyl, NH₂, NH-alkyl, N-(alkyl)₂, alkyl or aryl), carbonyl, SiR₃ (R=alkyl, alkoxy)]
n=0-100

(III)

and mixtures thereof,
particularly:

- EDAB-DOPO, or
- TDETA-DOPO,
- a compound according to formula (IV)



Y=NR [R=H, alkyl, DOPO-moiety, any organophosphorus compound eg PO(OR)₂ (R=alkyl or aryl) or PO(OR¹)R² (R¹=alkyl or aryl, R²=alkyl or aryl), COR (R=O-alkyl, NH₂, NH-alkyl, N-(alkyl)₂, alkyl or aryl), carbonyl, SiR₃ (R=alkyl, alkoxy)]
n=0-100

(IV)

and mixtures thereof,
particularly:

- TEPA-PDOPO.

The above mentioned acronyms shall have the meaning as unambiguously defined in the Examples given further below. Preferably, Y as referred to in formulae III and IV is NR wherein R=H, alkyl, DOPO-moiety, PO(OR)₂ (R=alkyl or aryl), PO(OR¹)R² (R¹=alkyl or aryl, R²=alkyl or aryl), COR (R=O-alkyl, NH₂, NH-alkyl, N-(alkyl)₂, alkyl or aryl), SiR₃ (R=alkyl, alkoxy). More preferably, for COR within the definition of Y, R = alkyl or aryl.

The compounds of Formula (I) represent a wide variety of functionalized silane or siloxane derivatives.

The compounds of Formula (II) represent a wide variety of "multi-DOPO derivatives", i.e. of compounds containing at least two DOPO entities.

The compounds of Formula (III) and Formula (IV) represent a further variety of "multi-DOPO derivatives" which are based on a polyethyleneamine backbone to which there are attached at least two DOPO entities. The backbone can comprise up to 100 amine units. The compounds of Formula III can be obtained by reacting a polyethyleneamine template with an excess of DOPO, which result in a mixture of poly-DOPO amino derivatives. Such a mixture can generally be considered as an oligomeric mixture that may not be subject to the REACH regulations.

It is envisaged that in certain situations AA-DOPO, BHEA-DOPO and /or PDAB-DOPO may desirably be excluded from the group of suitable phosphoramidate compounds. They may be excluded individually, or in any permutation.

According to another aspect of the invention, there is provided a method of improving flame resistance of a polymeric material, comprising the step of adding a first amount of a phosphoramidate according to the present invention, or of a mixture thereof, as a flame retardant substance to a second amount of the polymeric material.

According to a further aspect of the invention, there is provided a polymeric material with improved flame resistance, comprising a flexible polyurethane foam containing an amount of about 1% to about 30%, preferably about 3% to about 25%, particularly about 5%, by weight per 100 parts of polyol of a flame retardant additive selected from a phosphoramidate of the invention, preferably from the group consisting of

- EDAB-DOPO,
- TEPA-PDOPO,
- a compound of formula (IV) wherein $n=2-10$, preferably 3-10,
- BHEA-DOPO,
- DEA-DDOPO, And

- mixtures thereof.

According to a yet further aspect of the invention, there is provided a polymeric material with improved flame resistance, comprising a rigid polyurethane foam containing an amount of about 1% to about 30% by weight, preferably about 1% to about 25%, particularly about 3%, by weight per 100 parts of polyol of a flame retardant additive selected from a phosphonamidate of the invention, preferably the group consisting of

- EDAB-DOPO ,
- TEPA -PDOPO
- a compound of formula (IV) wherein $n=2-10$, preferably 3-10,
- BHEA-DOPO,
- DEA-DDOPO,
- mixtures thereof,

and optionally also comprising a synergist for example an efficient intumescent char former such as expandable graphite and /or an efficient carbonaceous char former such as pentaerythritol.

Further aspects of the invention provide methods of making phosphonamidate compounds using a single reaction step. Specifically there are provided methods of making a phosphonamidate comprising the steps: of dissolving DOPO and an amine in a solvent to form a mixture; optionally cooling the mixture to below about 20°C, 15°C, or 10°C; adding tetrachloromethane or trichloroisocyanuric acid to the mixture at a rate (i) such that the reaction temperature does not exceed about 30°C, or if the mixture was cooled, (ii) such that the reaction temperature does not exceed about 20°, 15°C or 10°C; allowing the mixture to return to about 25°C; and stirring the mixture. Preferably the solvent is dichloromethane, chloroform, dichloroethane, acetonitrile, THF, 1,4-dioxane or toluene.

Further the invention provides use of a phosphonamidate compound to improve flame resistance, in particular in polyurethane foams.

Advantageous embodiments are defined in the dependent claims.

Brief description of the drawings

The above mentioned and other features and objects of this invention and the manner of achieving them will become more apparent and this invention itself will be better understood by reference to the following description of various embodiments of this invention taken in conjunction with the accompanying drawings, wherein are shown:

- Figs. 1 to 10 total ion chromatograms for a selection of amino-DOPO derivatives showing, as a function of time in minutes: total ion chromatogram (top trace), ion signal of PO radical at $m/z = 47$ (middle trace) and ion signal of PO_2 radical at $m/z = 63$ (bottom trace); and
- Fig. 11 thermal gravimetric data for a selection of amino-DOPO derivatives showing percentage of residue as a function of temperature in °C.

Detailed description of the invention

Materials


All reagents and solvents were reagent grade or were purified by standard methods before use. 9,10-Dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) was purchased from Conier Chem&Pharma Co.,Ltd and used as received. The amines used were purchased from Aldrich and used as received. CCl_4 and Trichloroisocyanuric acid (TCCA) from Aldrich were used as chlorinating agents as received.

Syntheses

The amino-DOPO (phosphonamidates) were synthesized by two synthetic procedures as described hereinbelow.

General Procedure A for the preparation of amino-DOPO derivatives (phosphonamidates)


Scheme 4: General reaction scheme for the preparation of amino-DOPO derivatives via an Atherton-Todd-reaction



9,10-Dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) (108 g, 500 mmol), triethyl amine (79 ml, 566 mmol) and the appropriate amine (240-750 mmol) are dissolved in 400 ml of an appropriate solvent, for example dichloromethane, chloroform, dichloroethane, acetonitrile, THF, 1,4-dioxane or toluene, stirred and cooled to 0°C. After the solution has been cooled down, tetrachloro methane (59 ml, 600 mmol) is added dropwise at a rate that the reaction temperature does not exceed 10°C. After all tetrachloro methane has been added, the solution is allowed to warm up to room temperature and the stirring is continued until all the starting material has been consumed (observed with TLC). After complete conversion the triethylamine hydrochloride is filtered off and washed with excess of dichloromethane. The resulting clear solution is washed with water (100ml), dried over Na₂SO₄ and the solvent is evaporated in vacuum. If the resulting product does not exhibit enough analytical purity, it is recrystallized from an appropriate solvent.

General Procedure B for the preparation of amino-DOPO derivatives
(phosphoramidates):-

Scheme 5: General reaction scheme for the preparation of amino-DOPO using TCCA as chlorinating agent




TCCA- trichloroisocyanuric acid

9,10-Dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) (108 g, 500 mmol), triethyl amine (79 ml, 566 mmol) and the appropriate amine (240-750mmol) are dissolved in 400 ml of an appropriate solvent, for example dichloromethane, chloroform, dichloroethane acetonitrile, THF, 1,4-dioxane or toluene, stirred and cooled to 0°C. After the solution has been cooled down, a solution of TCCA (38,7 g, 166.7 mmol) in 200 ml acetonitrile is added dropwise at a rate that the reaction temperature does not exceed 10°C. After this solution has been added completely the solution is allowed to warm up to room temperature and stirring is continued until all the starting material has been consumed (TLC). After complete conversion the reaction mixture is filtered to remove of the triethylamine hydrochloride and cyanuric acid. The resulting clear solution is washed with water (100ml). The aqueous phase is extracted twice with 100ml dichloromethane. The combined organic phases are dried over Na₂SO₄ and the solvent is evaporated in vacuum. If the resulting product does not exhibit enough analytical purity, it is recrystallized from an appropriate solvent.

Analytical Data

Example1



6-(allylamino)-6H-dibenzo[c,e][1,2]
oxaphosphinine 6-oxide
(AA-DOPO)

Synthesis run with a ratio of DOPO to amine: 1:1

Solvent: CH₂Cl₂

Yield: 119.2g (440mmol, 88%)

m.p. 95°C

¹H-NMR (CDCl₃) δ (ppm): 7.88-7.99 (m, 3H), 7.92 (dd, *J* = 1.7, 7.9 Hz, 1H), 7.66 (tt, *J* = 1.3, 8.7, 1H), 7.48 (ddt, *J* = 1.0, 3.0, 7.5 Hz, 1H), 7.35 (m_c, 1H), 7.20-7.26 (m, 2H),

5.75-5.86 (m, 1H), 5.19 (dq, $J = 1.4, 17.1$ Hz, 1H), 5.06 (dq, $J = 1.4, 10.3$ Hz, 1H), 3.39-3.60 (m, 3H).


$^{13}\text{C-NMR}$ (CDCl_3) δ (ppm): 149.8, 138.9, 137.0, 132.7, 130.1, 130.0, 128.4, 128.1, 127.2, 124.8, 124.2, 123.5, 123.3, 121.9, 44.9.

$^{31}\text{P-NMR}$ (CDCl_3) δ (ppm): 15.9.

IR (Film) ν (cm^{-1}) = 3179 (m), 2855 (w), 1648 (w), 1592 (w), 1475 (m), 1428 (m), 1222 (s), 1198 (m), 1152 (m), 1142 (s), 1054 (w), 923 (m), 899 (w), 752 (s), 715 (s).

MS (ESI) m/z (%) 271 (14), 216 (55), 199 (18), 168 (54), 139 (27), 56 (100).

Example 2



6-((3-(triethoxysilyl)propyl)amino)-6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide (TESPA-DOPO)

One could imagine preparing DOPO-amino silane derivatives by choosing different kinds of functional silanes or siloxanes. Furthermore DOPO amino silane or siloxane derivatives can be further hydrolyzed and polymerized to form cross-linked or linear polymers as described for DOPO-phosphinates in literature.¹²

Synthesis run with a ratio of DOPO to amine: 1:1

Solvent: CH_2Cl_2

Yield: 7.57g (17.4mmol, 75%)

m.p.: 85°C


$^1\text{H-NMR}$ (CDCl_3) δ (ppm): 7.86-7.99 (m, 3H), 7.66 (tt, $J = 1.2, 8.8$, 1H), 7.48 (ddt, $J = 0.8, 3.1, 7.5$ Hz, 1H), 7.35 (m_c , 1H), 7.19-7.25 (m, 2H), 3.76 (q, $J = 6.9$ Hz, 6H), 3.41 (m_c , 1H), 2.87 (m_c , 2H), 1.59 (m_c , 2H), 1.17 (t, $J = 6.9$ Hz, 9H), 0.59 (m_c , 2H).

$^{13}\text{C-NMR}$ (CDCl_3) δ (ppm): 150.1, 137.2, 132.8, 130.3, 130.2, 128.2, 125.5, 125.0, 124.3, 123.8, 123.7, 122.2, 120.7, 58.5, 43.6, 25.1, 18.4, 7.5.

³¹P-NMR (CDCl₃) δ (ppm): 15.8.

IR (Film) ν (cm⁻¹) = 3148 (w), 2939 (w), 2895 (w), 2838 (w), 1597 (w), 1474 (m), 1430 (m), 1274 (w), 1225 (m), 1195 (s), 1149 (m), 1074 (s), 926 (m), 816 (m), 752 (s).

Example 3



6-((3-(trimethoxysilyl)propyl)amino)-
6*H*-dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
(TMSPA-DOPO)

Synthesis run with a ratio of DOPO to amine: 1:1

Solvent: CH₂Cl₂


Yield: 161g (370 mmol, 74%)

m.p.: 85°C

¹H-NMR (CDCl₃) δ (ppm): 7.86-7.99 (m, 3H), 7.66 (tt, *J* = 1.2, 8.8, 1H), 7.48 (ddt, *J* = 0.8, 3.1, 7.5 Hz, 1H), 7.35 (m_c, 1H), 7.19-7.25 (m, 2H), 3.55 (m_c, 1H), 3.49 (s, 9H), 2.87 (m_c, 2H), 1.58 (m_c, 2H), 0.59 (m_c, 2H).

³¹P-NMR (CDCl₃) δ (ppm): 15.8.

Example 4



6-(2-((6-oxido-6*H*-dibenzo[*c,e*][1,2]oxaphosphinin-6-yl)amino)
ethoxy)-6*H*-dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
(EAB-DOPO)

Synthesis run with a ratio of DOPO to amine: 2:1

Solvent: CH₂Cl₂

Yield: 98.2g (203mmol, 81%)

m.p. 121°C

¹H-NMR (CDCl₃) δ (ppm): 7.85-7.99 (m, 5H), 7.71-7.85 (m, 2H), 7.65 (m_c, 1H), 7.48-7.56 (m, 1H), 7.32-7.45 (m, 3H), 7.10-7.28 (m, 4H), 4.16 (m_c, 2H), 3.51 (m_c, 1H), 3.17 (m_c, 2H).


¹³C-NMR (CDCl₃) δ (ppm): 149.8, 149.7, 137.2, 137.1, 133.9, 133.1, 130.8, 130.5, 130.5, 130.4, 130.1, 128.6, 128.4, 125.5, 125.5, 125.1, 124.5, 124.3, 123.8, 122.6, 122.1, 120.7, 120.3, 120.2, 66.9, 41.4

³¹P-NMR (CDCl₃) δ (ppm): 15.5 (d, *J* = 3.5 Hz, 1P), 11.4.


IR (Film) ν (cm⁻¹) = 3215 (w), 2879 (w), 1597 (w), 1476 (m), 1430 (m), 1267 (m), 1230 (m), 1204 (s), 1151 (m), 1118 (s), 1029 (m), 989 (m), 911 (s), 749 (s).

MS (ESI) *m/z* (%) 489 (100).


Examples 5. 6. 7



6-(bis(2-hydroxyethyl)amino)-6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide (BHEA-DOPO)



6-((2-hydroxyethyl)(2-((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)oxy)ethyl)amino)-6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide (DEA-DDOPO)



6,6'-((((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)azanediyl)bis(ethane-2,1-diyl))bis(oxy))bis(6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide) (DEA-TDOPO)

Synthesis run with a ratio of DOPO to amine: 1:1 or 1:1.5


Solvent: CH₂Cl₂

Yield: 113.2g (355mmol, 71%)

HPLC-MS (ESI-MS): retention time BHEA-DOPO 15.2 min (319.9 m/z), DEA-DOPO 15.7 min (533.9 m/z); Flow 0.25 ml/min, solvent mixture 90:10 H₂O+0.1% formic acid: acetonitrile + 0.1% formic acid for 1 minute, then gradient to 0:100 within 10 minutes, then two more minutes 0:100, then gradient to 90:10 within two minutes, 5 minutes isocratic at 90:10. Column: Phenomenex® Gemini C18, 110A, 250mm*2mm*5µm.

Reaction of DOPO with diethanolamine (DEA) can result in three kinds of molecules i.e. BHEA-DOPO, DEA-DDOPO, DEA-TDOPO. In the synthesis described in our ex-

periment leads to compounds BHEA-DOPO and DEA-DDOPO in the ratio 1:3 respectively. One could imagine preparing DEA-TDOPO by varying the reaction conditions. It is also possible to prepare one the above mentioned compounds exclusively by optimizing the reaction conditions.



6,6'-(((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)azanediyl)bis(ethane-2,1-diyl))bis(oxy))bis(6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide)
(DEA-TDOPO)


Analytical data for DEA-TDOPO

¹H-NMR (CDCl₃) δ (ppm): 7.80-8.05 (m, 9H), 7.65-7.80 (m, 3H), 6.95-7.45 (m, 12H), 4.01-4.18 (m, 4H), 3.0-3.21 (m, 4H).

³¹P-NMR (Trifluoroethanol-d³) δ (ppm): 16.9, 10.7.

MS (ESI) *m/z* (%) 747 (100).

Example 8



6,6'-(piperazine-1,4-diyl)bis(6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide)
(PB-DOPO)

Synthesis run with a ratio of DOPO to amine: 2.5:1

Solvent: CHCl₃

Yield: 110.5g (212 mmol, 85%)

m.p. 320°C

¹H-NMR (Trifluoroethanol-d³) δ (ppm): 7.91 (m_c, 2H), 7.84 (m_c, 2H), 7.56-7.66 (m, 4H), 7.38 (m_c, 2H), 7.24 (m_c, 2H), 7.12 (m_c, 2H), 7.06 (m_c, 7.06), 2.99 (m_c, 8H).


¹³C-NMR (Trifluoroethanol-d³) δ (ppm): 151.2, 139.8, 136.0, 132.6, 131.2, 130.6, 127.0, 126.1, 123.5, 123.4, 121.9, 121.8, 45.7.

³¹P-NMR (Trifluoroethanol-d³) δ (ppm): 19.5.

IR (Film) ν (cm⁻¹) = 2856 (w), 1596 (w), 1476 (w), 1428 (w), 1369 (w), 1230 (s), 1205 (m), 1147 (m), 1114 (m), 969 (m), 901 (s), 747 (s), 707 (s).

MS (ESI) *m/z* (%) 514 (100).

Example 9



6,6'-(ethane-1,2-diylbis(azanediyl))bis(6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide)
(EDAB-DOPO)

~~Synthesis run with a ratio of DOPO to amine: 2.5:1~~

Solvent: CHCl₃

Yield: 102.5g (210mmol, 84%)

m.p. 267-270°C

¹H-NMR (Trifluoroethanol-d³) δ (ppm): 7.65-7.75 (m, 3H), 7.54-7.63 (m, 2H), 7.40-7.52 (m, 3H), 7.26-7.33 (m_c, 1H), 6.97-7.19 (m, 5H), 6.81 (dd, *J* = 1.1, 7.9 Hz, 1H), 7.59 (dd, *J* = 1.1, 8.0 Hz, 1H), 2.73-2.91 (m, 2H), 2.58-2.72 (m, 2H).


¹³C-NMR (Trifluoroethanol-d³) δ (ppm): 150.8, 150.5, 139.3, 139.1, 135.8, 135.7, 132.5, 132.4, 131.4, 131.3, 130.3, 130.2, 126.8, 126.7, 126.1, 125.8, 123.3, 123.2, 121.8, 121.5, 43.6, 43.4.

³¹P-NMR (Trifluoroethanol-d³) δ (ppm): 21.4, 20.7.

IR (Film) ν (cm^{-1}) = 3159 (m), 2877 (w), 1598 (w), 1476 (m), 1446 (m), 1196 (s), 1146 (m), 1116 (s), 922 (s), 747 (s), 711 (m).

MS (ESI) m/z (%) 488 (100).

Example 10



6,6'-(1,4-phenylenebis(azanediyl))bis(6*H*-dibenzo[*c,e*][1,2]
oxaphosphinine 6-oxide)
(PDAB-DOPO)

Synthesis run with a ratio of DOPO to amine: 2.5:1

Solvent: CHCl_3

Yield: 5.2g (9.7 mmol, 81%)

m.p. 295°C (decomp.)


$^1\text{H-NMR}$ (trifluoroethanol- d^3) δ (ppm): 7.75-7.90 (m, 4H), 7.51-7.65 (m, 4H), 7.27 (m_c , 2H), 7.21 (m_c , 2H), 7.11 (m_c , 2H), 7.01 (d, $J = 8.1$ Hz, 2H) 6.54 (s, 4H).

$^{31}\text{P-NMR}$ (CDCl_3) δ (ppm): 14.9.

IR (Film) ν (cm^{-1}) = 3153 (w), 3093 (w), 2944 (w), 1506 (m), 1477 (m), 1392 (w), 1286 (m), 1196 (s), 1116 (w), 974 (s), 911 (w), 747 (s).

MS (ESI) m/z (%) 536 (100).

Example 11



6-((3-((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)(2-((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)amino)ethyl)amino)propyl)amino)-6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide
TDETA-DOPO

Synthesis run with a ratio of DOPO to amine:3.5:1

Solvent: CHCl₃

Yield: 102.5g (210mmol, 84%)

m.p. 267-270°C


¹H-NMR (CDCl₃) δ (ppm): 7.65-7.95 (m, 9H), 7.40-7.63 (m, 3H), 6.82-7.35 (m, 12H), 3.99 (bs, 3H), 3.1-3.25 (m, 4H), 2.98-3.10 (m, 4H).

³¹P-NMR (Trifluoroethanol-d³) δ (ppm): 15.9, 17.8

MS (ESI) *m/z* (%) 745 (100).

Example 12

As an example for the preparation of multi-DOPO derivatives of tetraethylenepentamine, an amount of tetraethylenepentamine was reacted with an excess of DOPO. This reaction resulted in a mixture of poly-DOPO amino derivatives which were identified by HPLC-MS. HPLC-MS data of these mixtures indicates that tetraethylenepentamine had 3-5 DOPO attached to various amino groups. This mixture could be considered as an oligomeric mixture that does not have to pass the REACH regulations. Scheme shown below shows tetraethylenepentamine DOPO (TEPA-PDOPO) derivative where all amino groups have been reacted with DOPO.



6,6'-((((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)azanediyl)bis(ethane-2,1-diyl))bis((2-((6-oxido-6H-dibenzo[c,e][1,2]oxaphosphinin-6-yl)amino)ethyl)azanediyl))bis(6H-dibenzo[c,e][1,2]oxaphosphinine 6-oxide)-(TEPA-PDOPO)

HPLC-MS: $m/z = 1260$

Proof of gas phase action of amino-DOPO derivatives

DOPO and its phosphinate derivatives have been known to exhibit Gas phase action. There exist analytical data which clearly indicates the formation of PO^* radical which can quench the H^* and OH^* radicals formed during the thermal decomposition of polymers and prevent their oxidation.^{4a, 5} There exists no analytical data for the gas phase action of the amino -DOPO derivatives. Thus in this work elucidation of gas phase action of the amino derivatives of DOPO was carried out using direct insertion probe MS. The amino DOPO derivatives were heated from 50 °C to 450 °C at a rapid rate of 100 °C/ min in a quartz capillary in the ion source of MS and held for further 2mins and various mass fragments measured. The total ion chromatograph(TIC) was then scanned for PO^* (m/z 47) and PO_2 (m/z 63). Figs. 1 to 10 show the TIC chromatogram for each amino- DOPO derivatives.

The above figures clearly indicates the gas phase action of amino-DOPO derivatives as all of them exhibit PO^* (m/z 47) and PO_2 (m/z 63) release at elevated temperature. Furthermore it is also evident that the formation of these active species happens at different temperatures (indicated by time of formation) for different derivatives and thus could imply different application areas (i.e. different polymeric systems).

Thermal Stabilities of DOPO Derivatives

One of the important objectives of developing various amino derivatives of DOPO was to improve the thermal stability of DOPO itself. This will ensure their suitability to be used in thermoplastic polymers which require usually high processing temperatures (200-350 °C). The thermal decomposition studies of DOPO and DOPO derivatives are shown in Fig. 11.

Various transition temperatures and char content of amino derivatives of DOPO is further tabulated in Table 1.

Table 1: TGA data of Amino DOPO derivatives

Compounds	T _{d1} (°C)	T _{dMax} (°C)	% Char at 800 °C
DOPO	201	267	2
BHEA-DOPO:DEA-DDOPO (1:3)	284	361	8
EDAB-DOPO	355	415	7
PA-DOPO	235	292	2
AA-DOPO	247	295	3
PB-DOPO	387	433	5
BA-DOPO*	289	315/400/462	2
TESPA- DOPO*	234	135/287/437	28
EAB-DOPO	311	387	2
EA-DOPO*	241	293/375	2
TDETA-DOPO	294	385	2

T_{d1}: Temperature for 10% weight loss, T_{dMax}: Temperature for maximum decomposition rate, * Multiple decomposition stages, Bold data indicates main stage of decomposition.

It can be observed from the figure 11 and table 1 that DOPO starts to decompose earlier than 200 °C and thus not very suitable for melt processing of most organic polymers. Most of the amino DOPO derivatives are quite stable at this temperature and thus more suitable for melt processing at temperatures >200 °C. Furthermore some derivatives such as PB-DOPO and EDAB- DOPO have stabilities above 300 °C.

No previous studies on amino DOPO derivatives indicate their thermal stabilities. It can also be seen from the TGA data that TESPA-DOPO has a very interesting thermal behavior. It has relatively very high char content of (28%) at 800 °C and indicates

possible hybrid action i.e. combined gas phase and condensed phase action. This kind of hybrid flame retardant can find useful applications in special intumescent coatings.

Water Solubility of specific DOPO compounds

These DOPO-derivatives are very barely soluble in water as it is exemplarily shown for EDAB-DOPO and TEPA-PDOPO in table 2.

Table 2: Water solubility of EDAB-DOPO and TEPA-PDOPO

Flame retardant	Temperature	solubility FR in water mg/L	solubility FR in water mmol/L
EDAB-DOPO	25 °C	392.9	0.80
EDAB-DOPO	90 °C	500.8	1.03
TEPA-PDOPO	25 °C	15.4	0.01
TEPA-PDOPO	90 °C	818.1	0.65

From table 2 it can be seen that only very small amounts of EDAB-DOPO and TEPA-PDOPO dissolve in water even when the temperature is raised to 90°C.

This fact makes these compounds very useful for different flame retardant applications where one requirement is the solubility in any organic solvent and limited solubility in water.

Application and test procedures

The synthesized compounds were evaluated for flame retardant properties by incorporating them in flexible PU foams.

Methods for the manufacture of flexible polyurethane foams (flexible PU foams) are known in the art and are covered, for example, on pages 163 – 197 of the Plastics Manual, Volume 7, Polyurethanes, Becker/Braun, first edition (1985), published by Carl Hanser Verlag.

Conventionally, flexible PU foam may be made by reacting a polyol with a multifunctional isocyanate so that NCO and OH groups form urethane linkages by an addition reaction, and the polyurethane is foamed with carbon dioxide produced *in*

situ by reaction of isocyanate with water.

This conventional process may be carried out as a so-called 'one-shot' process whereby the polyol, isocyanate and water are mixed together so that the polyurethane is formed and foamed in the same step.

The flexible polyurethane foams were manufactured according to the recipe mentioned in Table 3 below.

The manufacture of the foams according to the formulations in Table 3 was done by handmix in the laboratory based on 200 gms polyol. The formulation of the components taking part in the reaction was identical in all cases except for the addition of Flame retardants where indicated.

Table 3: Flexible Polyurethane (PU) foam formulation

Flexible PU Foam	
Ingredients	pphp
All PO polyol	97
Compatibilizers	3.4
Tin(II)octanoate	0.25
Catalysts	0.5
Silicone Stabilizer	0.5
H ₂ O (total)	1.85
Toluene diisocyanate (TDI)	29.8
Flame Retardant (FR)	X

X=1-30%

Description of the ingredients :

With regard to the polyol this may be of any suitable kind. Typically polyether and polyester polyols are used in the production of PU foam and in accordance with

the present invention. In table 3 the polyol is a polyether polyol. Where a polyether polyol is used this is preferably wholly or predominantly propylene oxide (PO) derived, although ethylene oxide (EO) may also be used instead of, or additionally to PO. However it is also possible to use polyester polyol or mixtures of polyether and polyester polyol. Suitable polyols may have an OH functionality of 2 to 6, particularly 2 to 4 and may have a molecular weight (MW) in the range say 400-10,000.

It is well known in the art to use mixed polyols to vary the reactivity of the system or impart desired properties to the resulting PU foam and, with the present invention, whilst PO derived polyether polyol is generally preferred, other polyols and mixtures of polyols may be used as required.

Examples of the polyether polyols that can be used according to the invention are described, for example, on pages 44 - 54 and 75 – 78 of the Plastics Manual, Volume 7, Polyurethanes, Becker/Braun, 2nd edition, published by Carl Hanser Verlag.

Thus, for example, polyol may be as follows:

- I. derived from PO and propyleneglycol with viscosity (at 25°C) of 250-350 mPa.s, OH number 56 ± 3 .
- II. derived from EO and PO and trimethylolpropane with viscosity (at 25°C) 750-900 mPa.s, OH number 35 ± 2 .
- III. derived from PO and trimethylolpropane with viscosity 600-700, OH number 380 ± 25 .
- IV. derived from PO and glycerine with viscosity 450-550 and OH number 56 ± 3 .

All viscosity measurements (in mPa.s) are obtained using a Brookfield Viscometer. Unless otherwise stated viscosity is measured at 25EC. The OH number (hydroxyl number) is a conventional parameter which gives the concentration of NCO-reactive OH groups per unit weight in mg KOH/g.

$$\text{Hydroxyl number (OH)} = \frac{56.1 \times \text{functionality} \times 1,000}{\text{MW polyol}}$$

It is also possible to use those polyether polyols which already contain built-in catalysts, as for example described in WO 03/016373A1. It is likewise also possible to use mixtures of the aforementioned polyether polyols.

The invention can also be applied to OH terminated prepolymer foams, Natural oil based polyols (NOP's), mixtures and / or prepolymers thereof.

The polyol described in table 2 is a triol which is a propylene oxide adduct of glycerine and has a molecular weight of the order of 3,000. Commercial examples are Voranol® 3008 (Dow Chemical Company), or DESMOPHEN® 20WB56 (Bayer).

With regard to the multifunctional isocyanate this is preferably a diisocyanate, particularly TDI (toluene diisocyanate) as described in table 2. However other multifunctional isocyanates, preferably having a functionality of 2 to 5 may be used alone or in any suitable combination. Thus the multifunctional isocyanate may be any one or more of:

TDI (all isomer blends of toluene diisocyanate),

MDI (methylene diphenyl isocyanate),

Which may be pure or polymeric versions (so called aromatic isocyanates).

More particularly, the multifunctional isocyanate is a polyisocyanate containing two or more isocyanate groups and standard commercial di- and/or triisocyanates are typically used. Examples of suitable ones are aliphatic, cycloaliphatic, arylaliphatic and/or aromatic isocyanates, such as the commercially available mixtures of 2,4- and 2,6-isomers of diisocyanatotoluene (=tolylenediisocyanate TDI), which are marketed under the trade names Caradate® T80 (Shell) or Voranate® T80 and T65 (Dow Chemicals). 4,4'-diisocyanatodiphenylmethane (= 4,4'-methylenebis(phenylisocyanate); MDI) and mixtures of TDI and MDI can also be used. It is also possible, however to use isocyanate prepolymers based on TDI or MDI and polyols. Modified or mixed isocyanates (for example Desmodur® MT58 from Bayer) may also be used. Examples of aliphatic isocyanates are 1,6-hexamethylene diisocyanates or triisocyanates such as Desmodur® N100 or N3300 from Bayer. Isocyanate index can be used from very low (75 or less) to very high (125 or above) to suit required hardness or other properties of the foam.

Catalysts can be those well known in the PU foaming art, in particular an amine such as DMEA (dimethyl ethanolamine), DABCO® 33 LV (a tertiary amine from Air Products). Low emission / reactive amines can also be used as catalysts. Example are Tegomanin ZE -1 from Evonik or Niax EF 700 from Momentive or NE 400 from Air Products .

A metallo-organic compounds such as a tin catalyst e.g. KOSMOS 29 (stannous octoate) but other low emission catalyst such as Kosmos EF (Tin Ricinolate), zinc octoate or bismuth compounds be us can also be used.

Silicone stabilizers known in the art, for example silicone surfactant such as from the Tegostab® range from Evonik ie Tegostab B 8232 , BF 2370 ... or the Niaux ® range from Momentive ie L 670 , L 595..

Additional additives like Compatibilizers (ie Silbyk 9904 from Byk Chemie) , chain extending agents and/or cross-linking agents, such as diethanolamine, glycerine, sorbitol; as well as additional flame retardants; fillers can also be added to the formulation .. Those additives and others known in the art in relation to conventional foaming processes may be used in any combination.

Water can be used in any amount suitable to achieve desired density (typically 0.1 to 15 pphp , preferably 1 to 5 pphp) also in combination with liquid CO₂

For comparison of the efficiency of the synthesized amino- DOPO derivatives, Tris(2-chlorisopropyl)phosphate (TCPP) which is commonly used flame retardant for foams was taken as standard FR. It is common in PU foam industry to use haloalkyl derivatives as flame retardant additives. Recently use of some of these derivatives as flame retardants [TCEP (tris (2-chloroethyl phosphate)), TDCPP(tri (2,3-dichloropropyl) phosphate) and TCPP] have either been banned or being investigated for toxicity by environmental agencies.¹³

The resulting foams were dried and aged for 3 h at 80°C. The foams were then tested for their flammability according to Swiss flammability standard (BKZ). It's a vertical burning test for foamed materials with a specific sample size (length: 160 mm, width: 60 mm, thickness: 6 mm ± 10% tolerance). For each specimen flame test (BKZ) was performed in triplicate. If the results were not consistent, each specimen was tested 6 times. For the BKZ test an air dried specimen was placed in a vertical position and subjected to flame from the lower front edge by a standardized flame. The flame height of 20 mm was maintained and should burn constantly with sharp outlines. The burner position was adjusted 45° so that the flame hits the specimen vertically in the

middle of the lower front edge. The flame is brought in contact with the foam for 15 sec and should be placed such that the foam bottom is approximately 4 ± 1 mm inside the flame from the tip. The analysis of the burning test is then made according to the details given in Table 4.

Table 4: BKZ flammability test

Classification	Requirements
Degree of flammability (Class 3)	time 5 - 20 s
Degree of flammability (Class 4)	time, duration of burning > 20 s
Degree of flammability (Class 5)*	flame does not reach the top level of the sample holder (150 mm). duration $\leq$ 20 s

The BKZ-burning test was performed according to the procedure given above and the results are given in Table 5.

Table 5: Fire test on flexible PU foams-BKZ test

FR	Amount	Classification^b
DOPO	5%	Class 5
BHEA-DOPO:DEA-DDOPO (1:3)	5%	Class 5
EDAB-DOPO	5%	Class 5
AA-DOPO	5%	Class 5
PB-DOPO	5%	Class 5
TCPP	5%	Class 5
TDETA-DOPO	5%	Class 5
TEPA-PDOPO	5%	Class 5

a) Classification according to table 1. b) virgin foam does not self-extinguish

These foams were also evaluated for flame retardancy (UL-94 HB test) using standard ASTM D4986 or ISO/DIS 9772.3 . The data of such fire test is shown in Table 6 below:

Table 6: UL-94 HB test:

Samples	Burning Rate (mm/min)	Rating ^a
Blank	58	x
5% DOPO	48	HBF
5% AA-DOPO	47	HF-2
5% PB-DOPO	57	HBF
5% EDAB-DOPO	25	HF-1
5% DEA-DOPO: BHEA-DOPO(3:1)	52	HF-2
5% TDETA-DOPO	not determined	HF-1
5% TEPA-PDOPO	not determined	HF-1
5%TCPP	23	HBF

a) x = foam does not self extinguish; HBF = Doesn't have any specimens with a burning rate exceeding 40 mm per minute over a 100 mm span, or have each specimen cease to burn before flaming or glowing reaches the 125 mm gauge mark; HF-2 = foam self extinguishes within two seconds after the burner has been removed, foam is damaged < 60mm, after glow time is less than 30s, cotton indicator is allowed to be ignited by dripping, HF-1 = foam self extinguishes within two seconds after the burner has been removed, foam is damaged < 60mm, after glow time is less than 30s, cotton indicator is not allowed to be ignited by dripping

All amino-DOPO derivatives have similar or even better fire performance as compared to TCPP and hence can be used to replace TCPP as a halogen free FR system for flexible PU foams. It can be further observed from the Table 6 that amino derivatives of DOPO [AA-DOPO, EDAB-DOPO, DEA-DOPO: BHEA-DOPO (3:1)] have better flame retardancy effect as compared to unmodified DOPO. Without being bound by theory, it is contemplated that the enhanced flame retardancy effect of amino DOPO derivatives could be due to a P-N synergism effect.

Further tests were run to further investigate the effect of this new class of compounds.

Polyether foams / EDAB-DOPO

The foams were produced in a standard commercial flexible foam slab stock plant (Messrs. Hennecke, Germany) in a one-shot process. In this example

the basic materials (raw materials) were metered according to the formulation directly from storage vessels into a mixing chamber by means of pumps (e.g. piston or gear pumps), the mixing chamber being equipped with an agitator and a discharge pipe.

The metering and mixing of the raw materials was done in a manner known in the art. In this example the temperature of the raw materials was run at $25 \pm 3^{\circ}\text{C}$.

The polyol output overall was 30 kg/min. EDAB- DOPO was pre-dispersed in the polyol before running the formulation in the one shot process.

TABLE 7 : Evaluation of EDAB-DOPO in Polyether foams .

	1	2	3	4	5
.Ref.VA 1812	V06	V01	V02	V16	V14
Polyol OH 56 all PO	100	100	100	100	100
TDI 80/20	26.2	26.2	38.8	26.2	38.8
Water	1.6	1.6	2.8	1.6	2.8
Tegoamin ZE-1	0.5	0.35	0.35	0.5	0.5
Kosmos EF	0.5	0.5	0.5	0.9	0.9
Niax L 595	0.5	0.5	0.5	0.7	0.7
TCPP	0	5	5	0	0
EDAB-DOPO	0	0	0	5	5
Density (Kg/M3)	42.5	47.2	25.4?	46.0	30.0
CLD 40% (Kpa) DIN EN ISO 3381/1	3.1	3.5	3.0	2.5	2.6
Airflow (l/m2/s) DIN EN ISO 9237	7.9	57	500	161	414
BKZ Class (Vertical)	X burns	5	X burns	5	5
UL 94 HB test rating (Horizontal)	X burns	HF2	HF2	HF2	HF2

Discussion of the results of table 7 :

Columns 1 to 3 are not examples of the invention. 4 and 5 demonstrate the effect of EDAB - DOPO. One can see that at same water level (1.6 pphp) EDAB- DOPO has a positive effect on flammability (Comparison Columns 4 and 1) and works at least as well than TCPP (columns 4 and 2) . What is unexpected is that despite having isocyanate reactive groups (see structure in example 12 page 16) the resulting foam is more open airflow 161 versus 57 (l/m2/s) and needs more Kosmos EF indicated better processability (flexibility in production) .At lower density (2.8 pphp water) ED-AB-DOPO works better at least in vertical tests (Comparison columns 3 and 5) .

A proof of the efficiency of TEPA-PDOPO in polyether is given in table 8. Work was done in handmixes.

	1	2	3	4
OH terminated prepolymer OH 30 , all PO	100	100	100	100
TDI 80/20	31.9	31.9	31.9	31.9
Water	2.8	2.8	2.8	2.8
Tegoamin ZE-1	0.35	0.35	0.35	0.35
Kosmos EF	0.7	0.7	0.7	0.7
Tegostab B 8232	0.8	0.8	0.8	0.8
Exolit OP 560	0	10	0	0
TEPA-PDOPO	0	0	5	10
Density (Kg/M3)	38.5	Shrinks	40.6	42
CLD 40% (Kpa) DIN EN ISO 3381/1	7.3	No Foam	5.82	5.80
BKZ Class (Vertical)	X burns		X Burns	5
UL 94 HB test rating (Horizontal)	X burns		HF2	HF1

OH terminated prepolymers are described in patent WO 2005/108455 (Fritz Nauer Ag)

Exolit OP 560 is a leading reactive halogen free flame retardant from Clariant

One can clearly see the improvement of flammability versus the blank. Exolit OP 560 cannot be processed anymore at 10 pphp as it closes so much the foam that cells shrink. The addition of more TEPA-PDOPO improves flammability behavior in both horizontal and vertical tests.

Evaluation of EDAB-DOPO and TEPA –PDOPO in rigid formulations

Flame Retardancy of Polyurethane and Polyisocyanurate Foams:

The leading method for flame retarding rigid foam at present is to use additives, although reactive diols are occasionally employed where there is some special requirement. The well-established additives are still TCEP, i.e. tris(2-chloroethyl) phosphate, and TCPP, i.e. tris(1-chloro-2-propyl) phosphate. The recent need for higher percentages of these additives was

due to the use of HFCs or of hydrocarbon blowing agents in place of the phased out ozone-depleting chlorofluorocarbons.

The use of pentanes (cyclopentane , isopentane , n-pentane or mixture)for blowing of the foams in place of chlorofluorocarbon blowing, imposes a need for more flame retardants to counteract the flammability of the blowing agent.

Further it is well known that by raising the isocyanate index to get more isocyanurate structure,a lower level of flame retardant can be used to meet a standard.The higher the isocyanurate content,the greater the char yield on fire exposure and thus the more flame resistant,but also the more brittle(friable).

Non-ozone-depleting blowing agents containing fluorine ,i.e. HFCs , can allow for less flame retardant,especially in combination with a high isocyanurate content.

Although the chloroalkyl phosphates continue to dominate,there is an interest especially in Europe in non-halogenated flame retardants.

However,in case of fire,halogenated fire retarded polyurethanes evolve more toxic combustion products than the untreated polymer.

These are the reasons why current research focuses on the development of halogen-free and non-toxic fire retardants.

Classification and Testing of the Fire Performance of Building Materials and Components - the DIN 4102 Standard:

Compliance / conformity with building inspection regulations can be substantiated with the aid of the standards generally recognized as standard building practice.

The DIN 4102 Standard - Fire Performance of Building Materials and Components – defines in tangible terms the terminology of fire protection (combustible and non-combustible) employed in the rules and regulations covering building inspection and fire protection.

According to DIN 4102 - Part 1 building materials can be classified in class A (non-combustible) or class B (combustible).

Owing to their organic structures,plastics usually achieve only class B.

Acc. to DIN 4102 -1 combustible building materials can be classified in following categories:

1. B 1 = Low flammability (Brandschacht test)
2. B 2 = Moderately flammable (Small Burner test)
3. B 3 = Highly flammable

The test methods and requirements for combustible and (non-combustible building) materials are described in different sections of DIN 4102-1.

Class B2 Building Materials:

Building materials achieve class B2 if they satisfy the test requirements given in the following table

Specimens	4. Edge application of flame; five specimens 90mm x 190mm x original thickness (max. 80 mm), reference mark 150 mm from lower edge 5. Surface application of flame: five specimens 90 mm x 230 mm x original thickness (max. 80 mm), reference marks 40 mm and 150 mm from lower edge
Specimen position	6. Vertical
Ignition source	7. Small flame burner, inclined at 45°, flame height 20 mm
Flame application	8. 15s
Test duration	9. 20s
Continued:	10.
Conclusions	11. Passed if the tip of the flame does not reach the reference marks within 20s on any sample for: 12. If the filter paper under the sample ignites within 20 s after flaming, the material is judged to burn with flaming droplets.

Small Burner Test Equipment:

The Small Burner test equipment employed within this patent is in accordance to the requirements for the tests of the building materials class B2 specified in DIN 4102-1.

All flame tests done within this report are based on edge application of the impinging flame.

Dispersing EDAB-DOPO /TEPA-PDOPO:

EDAB-DOPO resp. TEPA-PDOPO were dispersed into the polyol-components by means of high speed dispersion in order to incorporate extremely fine solid particles into the fluids ,to produce colloidal suspensions.The preparations of the dispersions were carried out (prior to adding the respective blowing agents) at high peripheral velocities (formation of the doughnut-effect).

Equipment used:

IKA "Eurostar Power Control - Visc 6000" (speed range up to 6000 rpm) with dissolver disc IKA "R 1402 Dissolver".

For the dispersing of EDAB-DOPO resp. TEPA-PDOPO into the polyol component, high intensity ultrasonication could be an improved alternative to using a rotor-stator mixer.

Ultrasonic preparation of solids into liquids has been proven to be more effective than other high-shear mixing methods (14). At appropriate energy levels ultrasonication could achieve reduction in particle size of one to two magnitudes.

Efficiency of highly dispersed flame retardants of submicrometer particle size (0.1- to 1.0 μm) is discussed by Levchik (15)

Description of the chemicals

Petol PM 500 – 3F Mannich - Polyether Polyol ; OH-No. 480 – 520 ; $f = 3.0 - 3.5$;
visc. 5000 – 11000 mPa s (25 °C)

Rokopol RF- 551 Sorbitol-based Rigid Polyether Polyol ; OH-No. 400 – 440 ; f
= ca. 4.5 ; visc. 3000 – 5000 mPa s (25 °C)

Stepanpol PS-2352 Aromatic Rigid Polyester Polyol (o-Phthalate-
Diethyleneglycol based); OH-No. ca. 240 ; $f = 2.0$; visc. 3000 mPa s (25 °C)

Dabco DC 193 Rigid Foam Silicone Surfactant

Dabco TMR-2 Amine based, blocked trimerisation catalyst

Polycat 9 Tris-(dimethyl-aminopropyl)-amine ; blowing catalyst

4

Polycat 41 Triazine derivative ; trimerisation catalyst

Polycat 77 Pentamethyl dipropylene triamine ; blow/gel catalyst

Kitane 20 AS Emulsifier/compatiliser for pentane blown foams

Solkane 365mfc/227ea HFCs ; 365mfc : 227ea = 93 : 7 ; Bp. 30 °C ; classified as non
flammable

Pentane n – Pentane ; Bp. 36 °C

Desmodur 44 V 20 L PMDI ; $f = \text{ca. } 2.7$; visc. 160 - 240 mPa s (25°C)

Desmodur 44 V 40 L PMDI ; $f = \text{ca. } 2.9$; visc. 350 – 450 mPa s (25°C)

Test Results:

The B2-burner tests were carried out approx. one week after foaming.

1.Sandwich.Panel (SP):

All prepared sandwich panel specimens were of high macroscopic quality,i.e.very fine and regular cell structure. No shrink within shelf time of approx. four weeks after preparation.

No flame droplings occurred on fire exposure.

Formulations for discontinous Panel production (blowing agent HCF 365mfc/227ea) with TCPP as flame retardant were set up as bench mark.

A formulation containing 3.0 pbw of EDAB-DOPO blown with 365mfc /227ea (compare formulation SP-12 with 365mfc/227ea vs. formulation SP-10 with TCPP gave similar results reg.flame height and flame extinguishing demonstrating the efficiency of EDAB-DOPO in SP formulations .

Sandwich Panel (SP) - Solkane 365 mfc/227 ea

	SP-10	SP-12
Rokopol RF-551	10.0	10.0
Stepanpol PS 2352	40.0	40.0
TCPP	15.0	0.0
Dabco-TMR-2	2.5	2.5
Polycat 77	0.45	0.45
Polycat 41	0.15	0.15
Dabco DC 193	2.0	2.0
Kitane 20 AS	0.0	0.0
Water	0.50	0.5
EDAB - DOPO	0	3.0
Solkane 365 mfc/ 227 ea	10	10.0
Index	250	250
Desmodur 44 V 40 L (PMDI; f = ca.2.9)	101	101.0
Foam structure (very fine and regular= very good)	v.g.	v.g.
Flame height (cm)	13 - 14	16 - 17
Flame extinguishes after 15s Impinging plus x sec.	x = 0 - 1	x=0 - 1
Density (kg/cm ³)	39.2	41.2

HFC 365 mfc/227 ea was used for sandwich panels in case of discontinuous manufacturing; while pentane is standard for continuous production.

Further work indicate that EDAB-DOPO resp. TEPA-PDOPO could need the synergism of an efficient intumescent char former like expandable graphite in combination with an efficient carbonaceous char former like pentaerythritol to be efficient in pentane formulations .

From an individual point of conception the application of EDAB-DOPO resp. TEPA-PDOPO in combination with effective intumescent and carbonaceous char formers , like expandable graphite and pentaerythritol, have a pronounced effect on smoke reduction from sandwich panel burning (compared to the application of TCPP). Quantitative results conc. smoke density are to be obtained from Cone Calorimetry (CC).

2. Spray Foam (SPF):

All prepared spray foam specimens were of high macroscopic quality, i.e. very fine and regular cell structure. No shrink within shelf time of approx. four weeks after preparation.

No flame droplings occurred on fire exposure.

Formulations of Spray Foam (blowing agent HFC 365mfc/227ea) with TCPP as flame retardant were set up as bench mark.

Spray Foam(SPF) - Solkane 365 mfc / 227 ea

Product	SPF-11	SPF-17	SPF-18	SPF-19	SPF21
Petol PM 500-3F	43.0	43.0	43.0	43.0	43.0
Stepanpol PS 2352	31.0	31.0	31.0	31.0	31.0
TCPP	10.0	0	0	0	0
Dabco DC 193	3.0	3.0	3.0	3.0	3.0
Dabco TMR 2	2.00	2.0	2.0	2.0	2.0
Polycat 9	0.85	0.85	0.85	0.85	0.85
Polycat 41	0.15	0.15	0.15	0.15	0.15
Water	1.0	1.0	1.0	1.0	1.0
EDAB -DOPO	0	3.0	0	6.0	0
TEPA-PDOPO	0	0	3.0	0	0
Solkane 365 mfc/227 ea	10.0	10.0	10.0	10.0	10.0
Desmodur 44 V 20 L (PMDI; f = ca.2.7)	0	0	0	0	0
Desmodur 44 V 40 L (PMDI; f= ca.2.9)	150	150	150	150	150
Index	175	175	175	175	175

Foam structure very fine and regular = very good

	v.g. 12,5-	v.g.	v.g.	v.g.	v.g.
Flame height (cm)	13,5	14,5-15	15-16	14	>20
Flame extinguishes after 15s impinging plus x sec.	x = 1	x = 3	x = 4	x = 1	x = 9
Density (kg/m ³)	40	43.1	41.7	41.4	43.7

Reference formulation is SPF-11 (TCPP ; Index 175).It shows outstanding results.

Flame test results of SPF 11 are very good because of high TCPP content and/or higher PMDI-index ,which results in a higher PIR content in the foam (and thus higher char formation on fire exposure).

Acceptable results with EDAB–DOPO resp. TEPA-PDOPO were achieved with formulations SPF -17 to SPF- 19 (3.0 resp. 6.0 parts of EDAB-DOPO resp.TEPA-PDOPO .Compare results against the " blind "test SPF-21.

Remarkable and unexpected is the fact that doubling the amount of EDAB-DOPO resp. TEPA-PDOPO has no significant effect on flame height and extinguishing of the flame.


-
- ¹ Lu, S.-H., Hamerton, I. *Progress in Polymer Science* **2002** 27(8), 1661-1712.
- ² a) Lu, L. et al *U.S. Pat. Appl. Publ.* **2011**, 20110034717; b) Doering, M. et al. *Ger. Offen.* **2010** 102009035301; c) Buysch, H.-J. et al *Ger. Offen.* **1996**, 19505352; d) Saito T. *US Patent* **1972** 3702878
- ³ a) Shieh, J.-Y.; Wang, C.-S. *Polymer* **2001**, 42, 7617; b) Dittrich, U.; Just, B.; Doering, M.; Ciesielski, M. *US Patent Application Publication* **2005**, US 2005/0020739 A1; c) Wang, X.-j.; Wang, R.-m.; Yang, J.-H. *Reguxing Shuzhi* **2009**, 24, 27; d) Just, B.; Imeri, S.; Keller, H.; Storzer, U. *Eur. Pat. Appl.* **2009**, EP 2090618 A2 20090819; e) Tobisawa, A. *Jpn. Kokai Tokkyo Koho* **2002**, JP 2002161197 A 20020604; f) Just, B.; Dittrich, U.; Keller, H.; Döring, M.; Storzer, U.; Ciesielski, M. **2010**, US 2010280215 A1.
- ⁴ a) Koenig, A.; Kroke, E. *From Polymers for Advanced Technologies* **2011**, 22, 5; b) Zhao, X. *Huaxue Yanjiu Yu Yingyong* **2000**, 12, 648.
- ⁵ Schaefer, A., Seibold, S., Lohstroh, W., Walter, O., Döring, M. *Journal of Applied Polymer Science* **2007**, 105(2), 685–696.
- ⁶ a) Beletskaya, I.P.; Neganova, E.G.; Veits, Y.A. *Russian Journal of Organic Chemistry*, **2004**, 40, 1782; b) Sponton, M.; Lligadas, G.; Ronda, J.C.; Galia, M.; Cadiz, M. *Polymer Degradation and Stability* **2009**, 94, 1693.
- ⁷ a) Lindner, B.; Kammerer, F.; Kohl, C. *PCT Int. Appl.* **2011**, WO 2011000457A1 20110106
b) Saito, T.; Kim, S.H.; Kim, J.S.; Park, J.H. *Jpn. Kokai Tokkyo Koho* **2007**, JP 2007091606A 20070412; c) Yun, K.K.; Kim, Y.C.; Choi, T.K.; Park, I.S. *Repub. Korea* **1999**, KR 199102 B1 1999061; d) Wang, C.S.; Hsieh, C.Y.; Lin, C.Y. *Jpn. Kokai Tokkyo Koho* **2003**, JP 2003105058 A 2003040; e) Feng, L.; Tang, A.; Xu, Z.; Li, S. *Faming Zhuanli Shenqing Gongkai Shuomingshu* **2007** CN 100999145 A 20070718; f) Saito, T.; Kim, S.H.; Kim, J.S.; Park, J.H. *Jpn. Kokai Tokkyo Koho* **2006**, JP 2006328100 A 20061207. g) Kanno, T., Sugata, Y., Yanase, H., Shigehara, K., *PCT Int. Appl.* **2006** WO 2006126393 A1 20061130. h) Kerenyi, A.; Balassa, A.; Kortvelyesi, T.; Ludanyi, K.; Keglevich, G. *Transition Metal Chemistry* **2008**, 33, 459; i) Keglevich, G., Szelke, H., Kerenyi, A., Kudar, V., Hanusz, M., Simon, K., Imre, T., Ludanyi, K. *Tetrahedron Asymmetry* **2005** 16(24), 4015-4021; j) Ábrányi-Balogh, P.; Keglevich, G. *Synth. Comm.* **2011**, 41, 1421-1426; k) Ujj, V.; Czugler, M.; Schindler, J.; Fogassy, E.; Keglevich, G. *Magyar Kemiai Folyoirat, Kemiai Kozlemenyek* **2010**, 116, 31.
- ⁸ b) Jung, G. C.; Hyeon, N.; Park, I. G.; Yoo, J. H.; Hyun, A. R.; Jung, Y. H. *Repub. Korean Kongkae Taeho Kongbo* **2008**, KR 2008091036 A 20081009; a) Hinohara, A.; Hayashi, T.; Nogi, S.; Ikemoto, K.; Saito, T. *Jpn. Kokai Tokkyo Koho* **2009**, JP 2009266663 A 20091112; c) Uchida, O., Sato, K. *Jpn. Kokai Tokkyo Koho* **1998** JP 10203028 A 19980804.

-
- ⁹ a) Zich, T.; Artner, J.; Mehofer B.; Döring, M.; Ciesielski, M.; Zwick, G.; Rakotomalala, M. **2011**, *AT 508468 A1*; b) Rakotomalala, M; Wagner, S.; Zevaco, T.; Döring, M. *Heterocycles* **2011**, *83*, 743-753
- ¹⁰ a) Gaan, S., Rupper, P., Salimova, V. *POLYMER DEGRADATION AND STABILITY* **2009** *94*(7), 1125-1134; b) Deo, H. T.; Patel, N. K.; Patel, B. K. *J. of Engineered Fibers and Fabrics* **2008**, *3*(4), 23-38. c) Leu, T.-S.; Wang, C.-S. *J. of Applied Polymer Science* **2004**, *92*(1), 410-417. d) Nguyen, C.; Kim, J. *Polymer Degradation and Stability* **2008**, *93*, 1037-1043. e) Lewin, M. *J. of Fire Sciences* **1999**, *17*(1), 3-19.
- ¹¹ Toshiyuki, K.; Yoshinobu, S.; Hironori, Y.; Kiyotaka, S **2008**, *EP 1889878 A1*
- ¹² Wang, L., Wu, X., Wu, C., Yu, J., Wang, G., Jiang, P. *Journal of Applied Polymer Science* **2011**, *121*(1), 68-77.
- ¹³ a) Risk Assessment Report on Tris(2-Chlor-propyl) Phosphate (TCPP), *Scientific Committee on Health and Environmental Risks, Environmental Part* **2007**, *EINECS No. 237-158-7*.
b) Gupta, R. *Toxicology of Organophosphate and Carbamate compounds* **2006**, *ISBN: 978-0-12-088523-7*, Elsevier Inc. Burlington, Mass.
- ¹⁴ Stein, H.N.: *The Preparation of Dispersions in Liquids*, New York 1995, p.62 f.
- ¹⁵ Levchik, S.V. ; *Introduction to Flame Retardancy and Polymer Flammability* , in: Morgan, A.B. and Wilkie, C.A. (Eds.): *Flame Retardant Polymer Nanocomposites* , Hoboken/NJ 2007, p. 20 ff. (ibid. further references)

Claims

1. A phosphonamidate compound selected from the group consisting of:

- AA-DOPO;
- BHEA-DOPO;
- PB-DOPO;
- PDAB-DOPO;
- a compound according to Formula (I)



R¹= H, alkyl (C1-8), alkoxy (C1-8), amine (C1-8), OH, SR (R = H, alkyl), O-metal (I)

R²= H, alkyl (C1-8), alkoxy (C1-8), amine (C1-8), OH, SR (R = H, alkyl), O-metal


R³= H, alkyl (C1-8), alkoxy (C1-8), amine (C1-8), OH, SR (R = H, alkyl), O-metal

Y = NH, N-DOPO moiety, O, S

X = NH, NR (R = alkyl)


n = 1-8

m = 1-8



particularly:

- TESPA-DOPO, or
- TMSPA-DOPO;
- a compound according to Formula (II)




X = O, NR (R = H, alkyl), S

Y = N-DOPO moiety, CH₂

Z = O, NR (R = H, alkyl), S


m = 0-8

n = 0-8



particularly:

- EAB-DOPO,
 - DEA-DDOPO, or
 - DEA-TDOPO;
- a compound according to formula (III)




Y=NR [R=H, alkyl, DOPO-moiety, any organophosphorus compound eg $\text{PO}(\text{OR})_2$ (R=alkyl or aryl) or $\text{PO}(\text{OR}^1)\text{R}^2$ (R^1 =alkyl or aryl, R^2 =alkyl or aryl), COR (R=O-alkyl, NH_2 , NH-alkyl, N-(alkyl) $_2$, alkyl or aryl), carbonyl, SiR_3 (R=alkyl, alkoxy)]
 $n=0-100$

(III)

and mixtures thereof,
 particularly:

- EDAB-DOPO, or
 - TDETA-DOPO;
- a compound according to formula (IV)




Y=NR [R=H, alkyl, DOPO-moiety, any organophosphorus compound eg $\text{PO}(\text{OR})_2$ (R=alkyl or aryl) or $\text{PO}(\text{OR}^1)\text{R}^2$ (R^1 =alkyl or aryl, R^2 =alkyl or aryl), COR (R=O-alkyl, NH_2 , NH-alkyl, N-(alkyl) $_2$, alkyl or aryl), carbonyl, SiR_3 (R=alkyl, alkoxy)]
 $n=0-100$

(IV)


and mixtures thereof,
 particularly:

- TEPA-PDOPO;


wherein AA-DOPO, BHEA-DOPO, PB-DOPO, PDAB-DOPO, TESPA-DOPO, TMSPA-DOPO, EAB-DOPO, DEA-DDOPO, DEA-TDOPO, EDAB-DOPO, TDETA-DOPO and TEPA-PDOPO are defined as follows:




6-(allylamino)-6*H*-dibenzo[*c,e*][1,2]
oxaphosphinine 6-oxide
(AA-DOPO)




6,6'-(piperazine-1,4-diyl)bis(6*H*-
dibenzo[*c,e*][1,2]oxaphosphinine 6-
oxide)
(PB-DOPO)




6-(bis(2-hydroxyethyl)amino)-6*H*-
dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
(BHEA-DOPO)




6-((2-hydroxyethyl)(2-((6-oxido-6*H*-dibenzo[*c,e*]
[1,2]oxaphosphinin-6-yl)oxy)ethyl)amino)-6*H*-dibenzo[*c,e*]
[1,2]oxaphosphinine 6-oxide
(DEA-DDOPO)




6,6'-((((6-oxido-6*H*-dibenzo[*c,e*][1,2]oxaphosphinin-6-
yl)azanediyl)bis(ethane-2,1-diyl))bis(oxy))bis(6*H*-
dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide)
(DEA-TDOPO)




6,6'-(1,4-phenylenebis(azanediyl))bis(6*H*-dibenzo[*c,e*][1,2]
oxaphosphinine 6-oxide)
(PDAB-DOPO)




6-((3-(triethoxysilyl)propyl)amino)-6*H*-dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
(TESPA-DOPO)




6-((3-(trimethoxysilyl)propyl)amino)-
6*H*-dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
(TMSPA-DOPO)




6-(2-((6-oxido-6*H*-dibenzo[*c,e*][1,2]oxaphosphinin-6-yl)amino)
ethoxy)-6*H*-dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
(EAB-DOPO)



6,6'-(ethane-1,2-diylbis(azanediyl))bis(6*H*-
dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide)
(EDAB-DOPO)



6-((3-((6-oxido-6*H*-dibenzo[*c,e*][1,2]oxaphosphinin-6-yl)(2-((6-oxido-6*H*-
dibenzo[*c,e*][1,2]oxaphosphinin-6-yl)amino)ethyl)amino)propyl)amino)-6*H*-
dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide
TDETA-DOPO



6,6'-((((6-oxido-6*H*-dibenzo[*c,e*][1,2]oxaphosphinin-6-yl)azanediyl)bis(ethane-2,1-diyl))bis((2-((6-
oxido-6*H*-dibenzo[*c,e*][1,2]oxaphosphinin-6-yl)amino)ethyl)azanediyl))bis(6*H*-
dibenzo[*c,e*][1,2]oxaphosphinine 6-oxide)-(TEPA-PDOPO)

2. A phosphonamidate compound according to claim 1, wherein the compound is not AA-DOPO, BHEA-DOPO or PDAB-DOPO.
3. A phosphonamidate compound according to claim 1, wherein the compound is EDAB-DOPO, a compound of formula IV wherein $n=2-10$, or mixtures of compounds of formula IV wherein $n=2-10$.
4. A method of improving flame resistance of a polymeric material, comprising the step of adding a first amount of a phosphonamidate as defined in any of claims 1 -3, or of a mixture thereof, as a flame retardant substance to a second amount of said polymeric material.
5. The method according to claim 4, wherein said flame retardant substance is selected from the group consisting of:
 - AA-DOPO,
 - PB-DOPO,
 - EDAB-DOPO,
 - BHEA-DOPO,
 - DEA-DDOPO,and mixtures thereof.
6. The method according to claim 4, wherein said flame retardant substance is selected from the group consisting of:
 - AA-DOPO,
 - EDAB-DOPO,
 - a mixture of BHEA-DOPO, and
 - a mixture of DEA-TDOPO, BHEA-DOPO and DEA-DDOPO.
7. The method according to claim 4, wherein said flame retardant substance is BHEA-DOPO mixed with DEA-DDOPO in a molar ratio of about 1 : 3.
8. The method according to one of claims 4 to 7, wherein said flame retardant substance is admixed to a polyurethane foam formulation or added to a polyu-

urethane foam as a post treatment, preferably a flexible, semi-rigid or rigid polyurethane foam or foam formulation

9. The method according to one of claims 4 to 7, wherein said flame retardant substance is admixed to a flexible polyurethane foam formulation or added to a flexible polyurethane foam as a post treatment, wherein the flexible polyurethane foam or foam formulation is a polyether or polyester flexible polyurethane foam, or a combination thereof.
10. A polymeric material with improved flame resistance, comprising a flexible polyurethane foam containing an amount of about 1% to about 30% by weight, preferably about 3% to about 25%, particularly about 5%, by weight per 100 parts of polyol of a flame retardant additive selected from a phosphonamidate compound of claim 1, and is preferably selected from the group consisting of
 - EDAB-DOPO
 - TEPA-PDOPO
 - a compound of formula (IV) wherein $n=2-10$,
 - BHEA-DOPO,
 - DEA-DDOPO,
 - mixtures thereof.
11. A polymeric material with improved flame resistance, comprising a rigid polyurethane foam containing an amount of about 1% to about 30% by weight, preferably about 1% to about 25%, particularly about 3%, by weight per 100 parts of polyol of a flame retardant additive selected from a phosphonamidate compound of claim 1, and is preferably selected from the group consisting of
 - EDAB-DOPO,
 - TEPA-PDOPO,
 - a compound of formula (IV) wherein $n=2-10$,

- BHEA-DOPO,
- DEA-DDOPO,
- mixtures thereof,

and optionally also comprising a synergist for example an efficient intumescent char former such as expandable graphite and/or an efficient carbonaceous char former such as pentaerythritol.

12. A method of making a phosphonamidate according to claim 1, wherein this method comprises the steps of:
 - (a) dissolving DOPO and an amine in a solvent to form a mixture,
 - (b) optionally cooling the mixture to below about 10°C,
 - (c) adding tetrachloromethane to the mixture at a rate such that (i) the reaction temperature does not exceed about 30°C, or if the mixture was cooled, (ii) such that the reaction temperature does not exceed about 20°C,
 - (d) allowing the mixture to return to about 25°C, and stirring.
13. A method of making a phosphonamidate according to claim 1, wherein this method comprises the steps of:
 - (a) dissolving DOPO and an amine in a solvent to form a mixture,
 - (b) optionally cooling the mixture to below about 10°C,
 - (c) adding trichloroisocyanuric acid to the mixture at a rate such that (i) the reaction temperature does not exceed about 30°C, or if the mixture was cooled, (ii) such that the reaction temperature does not exceed about 20°C,
 - (d) allowing the mixture to return to about 25°C, and stirring.
14. Use of a phosphonamidate compound according to any of claims 1-3 to improve flame resistance.
15. Use of a phosphonamidate compound according to any of claims 1-3 to improve flame resistance in polyurethane foams.