

**Glass for Magnetic Recording Media Substrates,
Magnetic Recording Media Substrates,
Magnetic Recording Media and
Method for Preparation thereof**

[0001]

[Cross-references to related patent applications]

The present application claims priority under Japanese Patent Application 2008-72096, filed on March 19, 2008, and Japanese Patent Application 2008-170845, filed on June 30, 2008, the entire contents of which are hereby incorporated by reference.

[Prior Art]

[0002]

The present invention relates to a glass employed in the substrates of magnetic recording media such as hard disks, a magnetic recording medium substrate comprised of this glass, and a magnetic recording medium equipped with this substrate. The present invention further relates to a method for manufacturing the magnetic recording medium substrate, and a method for manufacturing the magnetic recording medium.

[Background Art]

[0003]

With developments in electronics technology, particularly information-related technology typified by computers, demand for information-recording media such as magnetic disks, optical disks, and magneto-optical disks has increased quickly. The main component elements of magnetic storage devices such as computers are a magnetic recording medium and a magnetic head for magnetic recording and reproduction. Flexible disks and hard disks are known as magnetic recording media. Among these, there exist substrate materials in the form of aluminum substrates, glass substrates, ceramic substrates, carbon substrates, and the like for hard disks (magnetic disks). In practical terms, aluminum substrates and glass substrates are primarily employed, depending on size and application. However, with the reduction in size of the hard disk drives employed in notebook computers and the increased density of magnetic recording, the requirements imposed on disk substrate surface flatness and thickness reduction have become quite stringent. Thus, aluminum substrates, which afford poor processability, strength, and rigidity, are inadequate.

Accordingly, glass substrates for magnetic disks affording high strength, high rigidity, high impact resistance, and high surface flatness have made an appearance.

[0004]

In recent years, vertical magnetic recording methods have been employed in an attempt to achieve higher recording densities in information-recording media (for example, high recording densities of 100 Gbit/inch² or greater). The use of vertical magnetic recording methods permits a marked increase in recording density. Additionally, achieving a high recording density requires greatly reducing the distance (referred to as the "flying height" in magnetic recording media) between the heads for reading and writing data (such as magnetic heads) and the medium surface, to 8 nm or less. However, when the substrate surface is not smooth, irregularities on the substrate surface are reflected on the medium surface, precluding a reduction in the distance between the heads and the recording medium, and hindering improvement in linear recording density. Thus, achieving high recording density through the use of a vertical magnetic recording method requires a glass substrate for use in an information-recording medium with a markedly better degree of flatness than in the past.

[0005]

Since adhesion of foreign matter to the glass substrate of an information-recording medium is unacceptable, adequate cleaning must be conducted. Cleaning agents such as acids and alkalis are employed in cleaning. However, when the chemical durability (acid and alkali resistance) of the glass constituting the substrate is inadequate, the manufacturing process ends up producing surface roughness, even when the substrate surface is finished for flatness. Even slight surface roughness makes it difficult to achieve a medium substrate with the level of flatness required by vertical recording methods. Thus, increasing the linear density of an information-recording medium requires a substrate material having good chemical durability.

[Patent Document 1] International Patent Application Publication No. 2007-142324 (WO 2007/142324) (the entire contents of which are hereby incorporated by reference).

[Disclosure of the Invention]

[Problem to Be Solved by the Invention]

[0006]

With the increasing recording density of magnetic recording media, a substrate glass having extremely few bubbles in addition to chemical durability is required. This goes beyond even the level of residual bubbles that is required of optical glass.

[0007]

When even extremely small bubbles remain in the glass, minute voids corresponding to bubbles appear in the substrate surface in the course of polishing the glass and shaping the substrate surface, forming localized pits and reducing the flatness of the substrate surface.

[0008]

In the glass disclosed in Patent Document 1, to increase chemical durability and achieve the properties required of a glass for use in a magnetic recording medium substrate, the content of SiO_2 and Al_2O_3 among the glass components is increased. To the extent that chemical durability does not decrease, Li_2O and Na_2O are incorporated, having the effect of maintaining melting properties, the coefficient of thermal expansion, and the like. However, in such glass, problems occur because, despite a lower glass melting temperature than in nonalkali glass, the melting temperature increases in alkali-containing glasses for magnetic recording medium substrates, making it difficult to effectively remove bubbles, due to the relation between the glass temperature and viscosity during the clarification step with Sb_2O_3 , which has conventionally been employed as a clarifying agent.

[0009]

The present invention, devised to solve such problems, has for its object to provide: a glass for a magnetic recording medium substrate permitting the realization of a magnetic recording medium substrate affording good chemical durability and having an extremely flat surface, a magnetic recording medium substrate comprised of this glass, a magnetic recording medium equipped with this substrate, and methods of manufacturing the same.

[0010]

[Means of Solving the Problem]

The present invention, which solves the above-stated problems, is as follows:

[1]

A glass for a magnetic recording medium substrate, comprised of an oxide glass, characterized:

by comprising, denoted as mass percentages:

Si 20 to 40 percent,
Al 0.1 to 10 percent,
Li 0.1 to 5 percent,
Na 0.1 to 10 percent,
K 0 to 5 percent
(where the total content of Li, Na, and K is 15 percent or less),
Sn 0.005 to 0.6 percent, and
Ce 0 to 1.2 percent;

in that the Sb content is 0 to 0.1 percent; and
by not comprising As or F.

[2]

The glass for a magnetic recording medium substrate according to [1], further characterized in that the ratio of the Ce content to the Sn content, Ce/Sn, falls within a range of 0 to 2.1.

[3]

The glass for a magnetic recording medium substrate according to [1], further characterized in that the ratio of the Ce content to the Sn content, Ce/Sn, falls within a range of 0.02 to 1.3.

[4]

The glass for a magnetic recording medium substrate according to any one of [1] to [3], further characterized by not comprising Sb.

[5]

The glass for a magnetic recording medium substrate according to any one of [1] to [4], comprising, denoted as mass percentages:

Mg 0 to 5 percent,
Ca 0 to 5 percent,
Sr 0 to 2 percent, and
Ba 0 to 2 percent.

[6]

The glass for a magnetic recording medium substrate according to any one of [1] to [5], further characterized by comprising 0.1 to 10 mass percent of Zr, Ti, La, Nb, Ta, and Hf in total.

[7]

The glass for a magnetic recording medium substrate according to any one of [1] to [6], characterized by a total content of Mg, Ca, Sr, and Ba of 0 to 10 percent.

[8]

The glass for a magnetic recording medium substrate according to any one of [1] to [7], characterized in that the total content of Si and Al is 30 mass percent or greater, and by having a viscous property whereby the viscosity at 1,400°C is 10^3 dPa·s or lower.

[9]

The glass for a magnetic recording medium substrate according to any one of [1] to [8], comprising, denoted as mass percentages:

Si 28 to 34 percent,

Al 6 to 10 percent

(where the total content of Si and Al is 37 percent or greater),

Li 0.1 to 3 percent,

Na 5 to 10 percent,

K 0.1 to 1 percent

(where the total content of Li, Na, and K is 7 to 13 percent),

Mg 0.1 to 2 percent,

Ca 0.1 to 2 percent,

Sr and Ba in total 0 to 1 percent,

Zr 1 to 5 percent,

B 0 to 1 percent, and

Zn 0 to 1 percent.

[10]

The glass for a magnetic recording medium substrate according to any one of [1] to [8], comprising, denoted as mass percentages:

Si 28 to 34 percent,

Al 6 to 10 percent

(where the total content of Si and Al is 37 percent or greater),

Li 1 to 5 percent,

Na 1 to 10 percent,

K 0.1 to 3 percent

(where the total content of Li, Na, and K is 5 to 11 percent),

Mg 0 to 2 percent,

Ca 0 to 2 percent,

Sr 0 to 1 percent,

Ba 0 to 1 percent,

Zr, Ti, La, Nb, Ta, and Hf in total 1 to 10 percent,

B 0 to 1 percent,
Zn 0 to 1 percent, and
P 0 to 1 percent.

[11]

A method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by:

preparing a glass starting material to which Sn, and optionally Ce, are added, comprising, denoted as mass percentages:

Si 20 to 40 percent,
Al 0.1 to 10 percent,
Li 0.1 to 5 percent,
Na 0.1 to 10 percent,
K 0 to 5 percent
(wherein the total content of Li, Na, and K is 15 percent or lower),
Sn 0.005 to 0.6 percent,
Ce 0 to 1.2 percent, and

so as to permit obtaining a glass comprising 0 to 0.1 percent of Sb and no As or F;

melting the glass starting material;
clarifying the resulting glass melt; and
then molding the resulting glass melt.

[12]

The method for manufacturing a glass for a magnetic recording medium substrate according to [11], further characterized by:

preparing a glass starting material comprising a ratio of Ce content to Sn content, Ce/Sn, falling within a range of 0.02 to 1.3;

maintaining the resulting glass melt at 1,400 to 1,600°C;

decreasing the temperature;

maintaining the temperature at 1,200 to 1,400°C; and

conducting molding.

[13]

The method for manufacturing a glass for a magnetic recording medium substrate according to [11] or [12], wherein the viscosity of the glass melt at 1,400°C is 10^3 dPa·s or lower.

[14]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [11] to [13], wherein the quantities of Sn and Ce added are established so as to achieve a density of residual bubbles in the glass of 60 bubbles/kg or lower.

[15]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, as converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);

in that, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide are added;

in that the content of Sb oxide is 0 to 0.1 mass percent; and

by not comprising As or F.

[16]

The glass for a magnetic recording medium substrate according to [15], further characterized in that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) as denoted by mass percentages falls within a range of 0 to 2.0.

[17]

The glass for a magnetic recording medium substrate according to [15], further characterized in that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) as denoted by mass percentages falls within a range of 0.02 to 1.2.

[18]

The glass for a magnetic recording medium substrate according to any one of [15] to [17], further characterized by not comprising Sb.

[19]

The glass for a magnetic recording medium substrate according to any one of [15] to [18], comprising, denoted as molar percentages:

MgO 0 to 10 percent,

CaO 0 to 10 percent,
SrO 0 to 5 percent, and
BaO 0 to 5 percent.

[20]

The glass for a magnetic recording medium substrate according to any one of [15] to [19], characterized by comprising 0.1 to 5 molar percent of ZrO_2 , TiO_2 , La_2O_3 , Nb_2O_5 , Ta_2O_5 , and HfO_2 in total.

[21]

The glass for a magnetic recording medium substrate according to any one of [15] to [20], characterized by comprising a total content of 0.1 to 10 molar percent of MgO, CaO, SrO, and BaO.

[22]

The glass for a magnetic recording medium substrate according to any one of [15] to [21], characterized in that the total content of SiO_2 and Al_2O_3 is 65 molar percent or greater, and by having a viscous property such that the viscosity at 1,400°C is 10^3 dPa·s or lower.

[23]

The glass for a magnetic recording medium substrate according to any one of [15] to [22], comprising, denoted as mass percentages:

SiO_2 66 to 70 percent,
 Al_2O_3 7 to 12 percent
(where the total content of SiO_2 and Al_2O_3 is 75 percent or greater),
 Li_2O 5 to 10 percent,
 Na_2O 8 to 13 percent,
 K_2O 0.1 to 2 percent
(wherein the total content of Li_2O , Na_2O , and K_2O is 15 to 22 percent),
MgO 0.1 to 5 percent,
CaO 0.1 to 5 percent,
SrO and BaO in total 0 to 1 percent,
 ZrO_2 0.1 to 2 percent,
 B_2O_3 0 to 1 percent, and
ZnO 0 to 1 percent.

[24]

The glass for a magnetic recording medium substrate according to any one of [15] to [22], comprising, denoted as mass percentages:

SiO_2 66 to 70 percent,

Al₂O₃ 5 to 12 percent,
Li₂O 5 to 20 percent,
Na₂O 1 to 13 percent,
K₂O 0.1 to 2 percent
(wherein the total content of Li₂O, Na₂O, and K₂O is 18 to 22 percent),
MgO and CaO in total 0 to 5 percent,
SrO and BaO in total 0 to 5 percent,
ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ in total 0.1 to 5 percent,
B₂O₃ 0 to 3 percent,
ZnO 0 to 1 percent, and
P₂O₅ 0 to 0.5 percent.

[25]

The glass for a magnetic recording medium substrate according to any one of [15] to [24], characterized by exhibiting an acid resistant property such that the etching rate when immersed in a 0.5 volume percent hydrogenfluosilicic acid aqueous solution maintained at 50°C is 3.0 nm/minute or less and an alkali resistant property such that the etching rate when immersed in a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C is 0.1 nm/minute or less.

[26]

A method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by:

preparing a glass starting material to which Sn, and optionally Ce, are added, comprising, as converted based on the oxides, denoted as molar percentages:

SiO₂ 60 to 75 percent,
Al₂O₃ 1 to 15 percent,
Li₂O 0.1 to 20 percent,
Na₂O 0.1 to 15 percent, and
K₂O 0 to 5 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);
so as to permit obtaining a glass comprising 0 to 0.1 percent of Sb, no As or F,
and, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide;

melting the glass starting material;
clarifying the resulting glass melt; and

molding the resulting glass melt.

[27]

The method for manufacturing a glass for a magnetic recording medium substrate according to [26], further comprising:

mixing the glass starting material so that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) denoted as a mass percentage falls within a range of 0.02 to 1.2,

melting the starting material,

maintaining the resulting glass melt at 1,400 to 1,600°C,

reducing the temperature,

maintaining the temperature at 1,200 to 1,400°C, and

molding the glass melt.

[28]

The method for manufacturing a glass for a magnetic recording medium substrate according to [26] or [27], wherein the viscosity of the glass melt at 1,400°C is 10^3 dPa·s or lower.

[29]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [26] to [28], wherein the quantities of Sn and Ce added are established to achieve a density of residual bubbles in the glass of 60 bubbles/kg or lower.

[30]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [11] to [14] and [26] to [29], wherein the glass melt is made to flow out to obtain glass melt gobs, and the glass gobs are press molded.

[31]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [11] to [14] and [26] to [29], wherein the glass melt is molded into a sheet of glass by the float method.

[32]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [11] to [14] and [26] to [29], wherein the glass melt is molded into a sheet of glass by overflow down draw molding.

[33]

The glass for a magnetic recording medium substrate according to any one of [1] to [10] and [15] to [25] that has been subjected to a chemical strengthening treatment.

[34]

A magnetic recording medium substrate comprised of the glass described in any one of [1] to [10], [15] to [25], and [33].

[35]

The magnetic recording medium substrate according to Claim 34, wherein roughness Ra of the main surface is less than 0.25 nm.

[36]

The magnetic recording medium substrate according to Claim 34 or [35], characterized by a bending strength of 10 kg or greater.

[37]

The magnetic recording medium substrate of any one of Claims 34 to [36], having a disklike shape and a thickness of 1 mm or less.

[38]

A method for manufacturing a magnetic recording medium substrate, comprising the steps of:

mirror-surface polishing the glass described in any one of [1] to [10], [15] to [25], and [33], and

following mirror-surface polishing, subjecting the glass to a cleaning step in which the glass is cleaned with an acid and cleaned with an alkali.

[39]

The method for manufacturing a magnetic recording medium substrate according to [38], further comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the cleaning step.

[40]

A method for manufacturing a magnetic recording medium substrate, comprising the steps of:

manufacturing a glass by the method described in any one of [11] to [14] and [26] to [32],

mirror-surface polishing the glass, and

following mirror surface polishing, subjecting the glass to a cleaning step in which the glass is cleaned with an acid and cleaned with an alkali.

[41]

The method for manufacturing a magnetic recording medium substrate of [40], additionally comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the cleaning step.

[42]

A magnetic recording medium having an information recording layer on the magnetic recording medium substrate described in any one of Claims 34 to [37].

[43]

The magnetic recording medium according to [42], suited to a vertical magnetic recording method.

[44]

A method for manufacturing a magnetic recording medium, comprising:
preparing a magnetic recording medium substrate by the method described in any one of [38] to [41] and
forming an information recording layer on the substrate.

[0000]

[45]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent,

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or less);

by comprising a 0.1 to 3.5 mass percent of total content of Sn oxide and Ce oxide, based on the total amount of the glass components;

in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 0.01 to 0.99;

in that the Sb oxide content is 0 to 0.1 percent; and

by comprising no As or F.

[46]

The glass for a magnetic recording medium substrate according to [45], further characterized in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 1/3 or greater.

[47]

The glass for a magnetic recording medium substrate according to [45], further characterized in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) falls within a range of 0.45 to 0.98.

[48]

The glass for a magnetic recording medium substrate according to any one of [45] to [47], further characterized by not containing Sb.

[49]

The glass for a magnetic recording medium substrate according to any one of [45] to [48], comprising, denoted as molar percentages:

MgO 0 to 10 percent,
CaO 0 to 10 percent,
SrO 0 to 5 percent,
BaO 0 to 5 percent,
B₂O₃ 0 to 3 percent,
P₂O₅ 0 to 1 percent, and
ZnO 0 to 3 percent.

[50]

The glass for a magnetic recording medium substrate according to any one of [45] to [49], further characterized by comprising a total content of ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ of 0.1 to 5 molar percent.

[51]

The glass for a magnetic recording medium substrate according to any one of [45] to [50], further characterized by comprising a total content of MgO, CaO, SrO, and BaO of 0.1 to 10 molar percent.

[52]

The glass for a magnetic recording medium substrate of any one of [45] to [51], further characterized in that the total content of SiO₂ and Al₂O₃ is 65 molar percent or greater and by having a viscous property such that the viscosity at 1,400°C is 10³ dPa·s or lower.

[53]

The glass for a magnetic recording medium substrate of any one of [45] to [52], comprising, denoted as mass percentages:

SiO₂ 66 to 70 percent,

Al₂O₃ 7 to 12 percent

(where the total content of SiO₂ and Al₂O₃ is 75 percent or greater),

Li₂O 5 to 10 percent,

Na₂O 8 to 13 percent,

K₂O 0.1 to 2 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 15 to 22 percent),

MgO 0.1 to 5 percent,

CaO 0.1 to 5 percent,

SrO and BaO in total 0 to 1 percent,

ZrO₂ 0.1 to 2 percent,

B₂O₃ 0 to 1 percent, and

ZnO 0 to 1 percent.

[54]

The glass for a magnetic recording medium substrate of any one of [45] to [52], comprising, denoted as mass percentages:

SiO₂ 66 to 70 percent,

Al₂O₃ 5 to 12 percent,

Li₂O 5 to 20 percent,

Na₂O 1 to 13 percent,

K₂O 0.1 to 2 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 18 to 22 percent),

MgO and CaO in total 0 to 5 percent,

SrO and BaO in total 0 to 5 percent,

ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ in total 0.1 to 5 percent,

B₂O₃ 0 to 3 percent,

ZnO 0 to 1 percent, and

P₂O₅ 0 to 0.5 percent.

[55]

The glass for a magnetic recording medium substrate according to any one of [45] to [54], characterized by exhibiting an acid resistant property such that the etching rate when immersed in a 0.5 volume percent hydrogenfluosillicic acid aqueous solution maintained at 50°C is 3.0 nm/minute or less and an alkali resistant property such that the etching rate when immersed in a 1 mass percent

potassium hydroxide aqueous solution maintained at 50°C is 0.1 nm/minute or less.

[56]

A method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by:

preparing a glass starting material to which Sn and Ce are added, comprising, as converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower); and, so as to permit obtaining a glass containing a total quantity of Sn oxide and Ce oxide of 0.1 to 3.5 mass percent based on the total amount of the glass components, wherein the ratio of the content of Sn oxide to the total content Sn oxide and Ce oxide (content of Sn oxide/(content of Sn oxide + content of Ce oxide)) is 0.01 to 0.99, having an Sb oxide content of 0 to 0.1 percent, and comprising no As or F;

melting the glass starting material;

clarifying the resulting glass melt; and

molding the resulting glass melt.

[57]

The method for manufacturing a glass for a magnetic recording medium substrate according to [56], wherein the glass melt obtained by preparing and melting the glass starting material is maintained at 1,400 to 1,600°C, the temperature is decreased, the glass melt is maintained at 1,200 to 1,400°C, and the glass melt is molded.

[58]

The method for manufacturing a glass for a magnetic recording medium substrate according to [56] or [57], wherein the viscosity of the glass melt at 1,400°C is 10³ dPa·s or lower.

[59]

The method for manufacturing a glass for a magnetic recording medium substrate of any one of [56] to [59], wherein the quantities of Sn and Ce added

are established so as to achieve a density of residual bubbles in the glass of 60 bubbles/kg or less.

[60]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [56] to [59], wherein the glass melt is made to flow out to obtain glass melt gobs and the glass gobs are press molded.

[61]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [56] to [59], wherein the glass melt is molded into a sheet of glass by the float method.

[62]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of [56] to [59], wherein the glass melt is molded into a sheet of glass by overflow down draw molding.

[63]

The glass for a magnetic recording medium substrate of any one of [45] to [55] that has been subjected to a chemical strengthening treatment.

[64]

A magnetic recording medium substrate being composed of the glass described in any one of [45] to [55] and [61].

[65]

The magnetic recording medium substrate according to [64], wherein roughness Ra of the main surface is less than 0.25 nm.

[66]

The magnetic recording medium substrate according to [64] or [65], further characterized by exhibiting a bending strength of 10 kg or greater.

[67]

The magnetic recording medium substrate described in any one of [64] to [66], having a disklike shape and a thickness of 1 mm or less.

[68]

A method for manufacturing a magnetic recording medium substrate, comprising:

a step of mirror-surface polishing the glass described in any one of [45] to [55] and [61]; and

following mirror-surface polishing, a cleaning step of cleaning with an acid and cleaning with an alkali.

[69]

A method for manufacturing the magnetic recording medium substrate according to [68], further comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the cleaning step.

[70]

A method for manufacturing a magnetic recording medium substrate, comprising:

a step of preparing a glass by the method described in any one of [56] to [62],

a step of mirror-surface polishing the glass, and

following mirror-surface polishing, a cleaning step of cleaning with an acid and cleaning with an alkali.

[71]

The method for manufacturing a magnetic recording medium substrate according to [70], further comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the washing step.

[72]

A magnetic recording medium comprising an information recording layer on the magnetic recording medium substrate described in any one of [64] to [67].

[73]

The magnetic recording medium according to [72], suited to a vertical recording method.

[74]

A method for manufacturing a magnetic recording medium, comprising:
preparing a magnetic recording medium substrate according to the method described in any one of [68] to [71]; and
forming an information recording layer on the substrate.

[75]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, denoted as mass percentages:

Si	20 to 40 percent,
Al	0.1 to 10 percent,
Li	0.1 to 5 percent,

Na 0.1 to 10 percent,
K 0 to 5 percent
(where the total content of Li, Na, and K is 15 percent or less),
Sn 0.005 to 0.6 percent, and
Ce 0 to 1.2 percent;

in that the Sb content is 0 to 0.1 percent;
by not comprising As or F; and
by having a $\lambda(\text{lambda})_{80}$ of 320 nm or greater.

[76]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, as converted based on the oxides, denoted as molar percentages:

SiO₂ 60 to 75 percent,
Al₂O₃ 1 to 15 percent,
Li₂O 0.1 to 20 percent,
Na₂O 0.1 to 15 percent, and
K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);
in that, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide are added;
in that the content of Sb oxide is 0 to 0.1 mass percent;
by not comprising As or F; and
by having a $\lambda(\text{lambda})_{80}$ of 320 nm or greater.

[77]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,
Al₂O₃ 1 to 15 percent,
Li₂O 0.1 to 20 percent,
Na₂O 0.1 to 15 percent, and
K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or less);

by comprising a 0.1 to 3.5 mass percent total content of Sn oxide and Ce oxide, based on the total amount of the glass components;
in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 0.01 to 0.99;
in that the Sb oxide content is 0 to 0.1 percent;
by comprising no As or F; and
by having a $\lambda(\lambda_{80})$ of 320 nm or greater.

[Advantages of the Invention]

[0012]

The present invention provides a glass for a magnetic recording medium substrate permitting the achievement of a magnetic recording medium substrate having good chemical durability and an extremely flat surface, a magnetic recording medium substrate comprised of this glass, a magnetic recording medium equipped with the substrate, and methods of manufacturing the same.

[Best Modes of Carrying Out the Invention]

[0013]

The glass for a magnetic recording medium substrate of the present invention is an amorphous glass and is comprised of two forms. In the first form (referred to as "glass I"), the proportions of the atoms constituting the glass are specified by mass ratio. In the second form (referred to as "glass II"), the contents of the various oxides, as converted based on the oxides, are specified. There is also a third form (referred to as "glass III") of the glass for a magnetic recording medium substrate of the present invention, an amorphous glass, in which the contents of the various oxides as converted based on the oxides, are specified.

[0014]

A far flatter substrate surface can be achieved with amorphous glass than with crystalline glass.

[0015]

[Glass I]

Glass I of the present invention is a glass for a magnetic recording medium substrate, comprised of an oxide glass, characterized:

by comprising, based on mass:

Si	20 to 40 percent,
Al	0.1 to 10 percent,

Li 0.1 to 5 percent,

Na 0.1 to 10 percent,

K 0 to 5 percent

(where the total content of Li, Na, and K is 15 percent or less),

Sn 0.005 to 0.6 percent, and

Ce 0 to 1.2 percent;

in that the Sb content is 0 to 0.1 percent; and

by not comprising As or F.

[0016]

In glass I, the contents and total contents of the various components are expressed as mass percentages, unless specifically stated otherwise.

[0017]

Si is a network-forming component of glass. It is an essential component that serves to enhance glass stability, chemical durability, and particularly, acid resistance; it also serves to lower thermal diffusion in the substrate; and increase the heating efficiency of the substrate by radiation. When the Si content is less than 20 percent, these functions are not adequately performed. When 40 percent is exceeded, unmelted material is produced in the glass, the viscosity of the glass during clarification becomes excessively high, and bubble elimination is inadequate. When a substrate is formed of glass containing unmelted material, protrusions due to unmelted material are formed on the surface of the substrate by polishing, precluding use as a magnetic recording medium substrate, for which an extremely high degree of surface flatness is required. In glass containing bubbles, when a portion of the bubbles are exposed on the substrate surface by grinding, they become pits, compromising flatness on the main surface of the substrate, thereby precluding its use as a magnetic recording medium substrate. Thus, the Si content is 20 to 40 percent, desirably falling within a range of 25 to 35 percent, and preferably falling within a range of 28 to 34 percent.

[0018]

Al contributes to the formation of the glass network, and serves to enhance glass stability and chemical durability. When the Al content is less than 0.1 percent, these functions cannot be adequately performed, and when 10 percent is exceeded, the meltability of the glass diminishes and unmelted material tends to be produced. Accordingly, the Al content is 0.1 to 10 percent, desirably falling within a range of 1 to 10 percent, preferably falling within a range

of 5 to 10 percent, more preferably falling within a range of 6 to 10 percent, and still more preferably, falling within a range of 7 to 10 percent.

[0019]

Both Si and Al are components that contribute to enhancing chemical durability. To further enhance chemical durability, it is desirable for the total content of Si and Al to be 30 percent or greater, preferably 32 percent or greater, more preferably 35 percent or greater, still more preferably 36 percent or greater, and yet more preferably, 37 percent or greater. Increasing the total content of Si and Al lowers the thermoconductivity of the glass, increasing the heating efficiency of the substrate during manufacturing of a magnetic recording medium.

[0020]

Li is an essential component that serves to strongly increase the meltability and moldability of the glass, even in alkalis. It is also desirable for imparting suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion. In chemically strengthened glass, it serves as a component that supports ion exchange during chemical strengthening. When the Li content is less than 0.1 percent, these functions cannot be adequately achieved. In particular, in glass I, in which relatively large quantities of Si and Al are incorporated to enhance chemical durability, an Li content of less than 0.1 percent results in an excessively high viscosity of the glass during clarification, precluding an adequate clarifying effect. When the Li content exceeds 5 percent, chemical durability, particularly acid resistance, diminishes. In addition, when the glass is formed into a substrate, the amount of alkali leaching out from the substrate surface increases. The precipitating alkali damages the information recording layer and the like. Accordingly, the Li content is 0.1 to 5 percent, desirably falling within a range of 1 to 5 percent, preferably a range of 1 to 4 percent, and still more preferably, a range of 1 to 3 percent.

[0021]

Na is an essential component that serves to enhance glass meltability and moldability, and is desirable for imparting suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion. In a chemically strengthened glass, it serves as a component that supports ion exchange during chemical strengthening. When the Na content is less than 0.1 percent, these functions cannot be adequately achieved. In particular, in glass I, in which relatively large quantities of Si and Al

are incorporated to enhance chemical durability, an Na content of less than 0.1 percent results in an excessively high viscosity of the glass during clarification, precluding an adequate clarifying effect. When the Na content exceeds 10 percent, chemical durability, particularly acid resistance, diminishes. In addition, when the glass is formed into a substrate, the amount of alkali leaching out from the substrate surface increases. The precipitating alkali damages the information recording layer and the like. Accordingly, the Na content is 0.1 to 10 percent, desirably falling within a range of 1 to 10 percent, preferably a range of 5 to 10 percent.

[0022]

Li and Na are essential components in glass I, producing effects by reducing and preventing the leaching out of alkalis from the glass surface due to the effect of alkali mixing.

[0023]

K is an optional component that serves to enhance glass meltability and moldability, and is desirable for imparting suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion. However, when the content of K exceeds 5 percent, chemical durability, particularly acid durability, diminishes. In addition, when the glass is formed into a substrate, the amount of alkali leaching out of the substrate surface increases, and the precipitating alkali damages the information recording layer and the like. Accordingly, the content of K is 0 to 5 percent, desirably falling within a range of 0 to 3 percent, and preferably falling within a range of 0.1 to 1 percent.

[0024]

In glass I, the total content of Li, Na, and K is limited to 15 percent or less to achieve good chemical durability. The total content of Li, Na, and K desirably falls within a range of 5 to 15 percent, preferably within a range of 5 to 13 percent, more preferably within a range of 5 to 12 percent, still more preferably within a range of 5 to 11 percent, and yet more preferably, within a range of 7 to 11 percent.

[0025]

In glass I, which contains relatively large quantities of Si and Al, the temperature of the glass during clarification is high, despite containing Li and Na. In such a glass, Sb has a poorer clarifying effect than Sn or Ce, described further below. In a glass to which Sn is added, the clarifying effect ends up deteriorating.

When the Sb content exceeds 0.1 percent, the coexistence of Sn causes the residual bubbles in the glass to increase sharply. Accordingly, the Sb content is limited to 0.1 percent or less in glass I. The Sb content desirably falls within a range of 0 to 0.08 percent, preferably within a range of 0 to 0.05 percent, still more preferably within a range of 0 to 0.02 percent, and yet more preferably, within a range of 0 to 0.01 percent. The addition of no Sb (glass containing no Sb) is particularly desirable. Not incorporating Sb (rendering the glass "Sb-free") reduces the density of residual bubbles in the glass to a range of from about one part in several to about one percent.

[0026]

Sb has a greater effect on the environment than Sn or Ce. Thus, reducing the Sb content, or using no Sb at all, reduces the effect on the environment.

[0027]

Although a powerful clarifying agent, As is desirably not incorporated (rendering the glass "As-free") because it is toxic. Further, although F exhibits a clarifying effect, it volatilizes during glass manufacturing, causing the properties and characteristics of the glass to fluctuate, and creating problems in terms of stable melting and molding. Further, volatilization causes the generation of heterogenous portions, called striae, in the glass. When striae are present in the glass and polishing is conducted, slight differences in the rates at which the glass is removed in striae portions and homogenous portions produce irregularities on the polished surface, which are undesirable in magnetic recording medium substrates for which a high degree of flatness is required. Accordingly, As and F are not incorporated into glass I.

[0028]

Glass I is prepared by the steps of melting a glass starting material, clarifying the glass melt obtained by melting the glass starting material, homogenizing the clarified glass melt, causing the homogenized glass melt to flow out, and molding it. In this process, the clarifying step is conducted at a relatively high temperature and the homogenizing step at a relatively low temperature. In the clarifying step, bubbles are actively produced in the glass, and clarification is promoted by incorporating minute bubbles contained in the glass to form large bubbles, which then tend to rise. Additionally, an effective method of eliminating bubbles is to incorporate as a glass component oxygen that is present as a gas within the glass in a state where the temperature of the glass is lowered as it flows out.

[0029]

Sn and Ce also have the effects of releasing and incorporating gases. Sn strongly serves to promote clarification by actively releasing oxygen primarily at high temperature (in a temperature range of about 1,400 to 1,600°C), while Ce strongly serves to incorporate oxygen at a low temperature state (a temperature range of about 1,200 to 1,400°C), fixing it as a glass component. By coexisting Sn and Ce, which exhibit good clarifying effects at different temperature ranges in this manner, it is possible to adequately eliminate bubbles even in glasses in which the incorporation of Sb, As, and F is limited.

[0030]

Sn is necessarily incorporated in a quantity of 0.005 percent or greater to achieve the above clarifying effect. However, when 0.6 percent is exceeded, metallic tin precipitates out into the glass. When the glass is polished to prepare a substrate, protrusions of metallic tin are produced on the substrate surface, and areas in which metallic tin drops out of the surface form pits, risking loss of the flatness of the substrate surface. Accordingly, the Sn content is 0.005 to 0.6 percent. From the above perspectives, the Sn content desirably falls within a range of 0.01 to 0.6 percent, preferably within a range of 0.06 to 0.6 percent, and more preferably, within a range of 0.1 to 0.6 percent.

[0031]

Ce is desirably incorporated to enhance the clarifying effect. However, when 1.2 percent is exceeded, it reacts strongly with the refractory material and platinum constituting the melt vessel, and with the metal mold used to mold the glass. This increases impurities, negatively affecting the surface state. Accordingly, the Ce content is 0 to 1.2 percent. From the above perspective, the Ce content desirably falls within a range of 0 to 0.7 percent.

[0032]

Sn and Ce serve to produce crystal nuclei when preparing crystalline glass. Since the glass in the present invention is employed in a substrate comprised of amorphous glass, it is desirable that no crystals precipitate during heating. Thus, the addition of excessive amounts of Sn and Ce is to be avoided.

[0033]

As set forth above, since Sn releases oxygen gas into the glass melt at high temperature, when a large quantity of Sn is employed, the quantity of Ce, which incorporates oxygen gas present in the melt at low temperature, is also

desirably increased. With this point in mind, preferred ranges of the Sn and Ce contents are given below.

[0034]

When the Sn content is 0.005 percent or greater but less than 0.1 percent, the Ce content is desirably kept to 0 to 0.4 percent, preferably 0.0001 to 0.2 percent, and more preferably, 0.001 to 0.12 percent.

[0035]

When the Sn content is 0.1 percent or greater but less than 0.14 percent, the Ce content is desirably kept to 0 to 0.4 percent, preferably 0.0005 to 0.4 percent, and more preferably, 0.003 to 0.14 percent.

[0036]

When the Sn content is 0.14 percent or greater but less than 0.28 percent, the Ce content is desirably kept to 0 to 0.4 percent, preferably 0.0005 to 0.4 percent, more preferably 0.001 to 0.36 percent, and still more preferably, 0.001 to 0.3 percent.

[0037]

When the Sn content is 0.28 percent or greater but less than 0.3 percent, the Ce content is desirably kept to 0 to 0.4 percent, preferably 0.0005 to 0.4 percent, more preferably 0.001 to 0.4 percent, and still more preferably, 0.006 to 0.4 percent.

[0038]

When the Sn content is 0.3 percent or greater but less than 0.35 percent, the Ce content is desirably kept to 0 to 0.4 percent, preferably 0.0004 to 0.6 percent, more preferably 0.0005 to 0.5 percent, and still more preferably, 0.006 to 0.4 percent.

[0039]

When the Sn content is 0.35 percent or greater but less than 0.43 percent, the Ce content is desirably kept to 0.0004 to 0.6 percent, preferably 0.0005 to 0.5 percent, and more preferably, 0.06 to 0.5 percent.

[0040]

When the Sn content is 0.43 percent or greater but less than 0.45 percent, the Ce content is desirably kept to 0.0004 to 0.6 percent, preferably 0.0005 to 0.5 percent.

[0041]

When the Sn content is 0.45 percent or greater but less than 0.5 percent, the Ce content is desirably kept to 0.0003 to 0.7 percent, preferably 0.005 to 0.6 percent, and more preferably, 0.006 to 0.5 percent.

[0042]

For bubbles 0.3 mm and smaller in size (the size of bubbles (voids) remaining in the solidified glass), Sn works strongly to eliminate both relatively large and extremely small bubbles. Ce can be optionally added. However, the clarifying effect can be increased by keeping the ratio (by mass) of the Ce content to the Sn content, Ce/Sn, to 2.1 or lower.

When Ce is added along with Sn, the density of large bubbles of about 50 micrometers to 0.3 mm can be reduced to about one in several tens of parts. To achieve such an effect, the lower limit of the ratio (by mass) of the Ce content to the Sn content, Ce/Sn, is desirably 0.005, preferably 0.01, more preferably 0.02, still more preferably 0.03, yet more preferably 0.05, yet still more preferably 0.1, and even more preferably, 0.5. The upper limit of the ratio (by mass) of the Ce content to the Sn content, Ce/Sn, is desirably 2.0, preferably 1.8, more preferably 1.6, still more preferably 1.5, yet more preferably 1.4, yet still more preferably 1.3, even more preferably 1.2, and particularly preferably, 1.1.

[0043]

From the above perspective, the total contents of Sn and Ce desirably falls within a range of 0.15 to 1.2 percent, preferably within a range of 0.15 to 0.8 percent.

[0044]

A desirable form of glass I comprises:

Mg 0 to 5 percent,

Ca 0 to 5 percent,

Sr 0 to 2 percent, and

Ba 0 to 2 percent.

[0045]

Mg serves to enhance glass meltability, moldability, and stability; heighten rigidity and hardness; and increase the coefficient of thermal expansion.

However, the incorporation of an excessive quantity reduces chemical durability. Thus, the Mg content is desirably 0 to 5 percent. The Mg content preferably falls within a range of 0 to 2 percent, more preferably, within a range of 0.1 to 2 percent.

[0046]

Ca specifically serves to enhance glass meltability, moldability, and stability; heighten rigidity and hardness; and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability. Thus, the Ca content is desirably 0 to 5 percent. The Ca content preferably falls within a range of 0 to 2 percent, more preferably, within a range of 0.1 to 2 percent.

[0047]

Sr also serves to enhance glass meltability, moldability, and stability, and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability and increases the specific gravity and cost of starting materials. Thus, the Sr content is desirably 0 to 2 percent. The Sr content preferably falls within a range of 0 to 1 percent, more preferably within a range of 0 to 0.5 percent, and still more preferably, is zero.

[0048]

Ba also serves to enhance glass meltability, moldability, and stability, and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability and increases the specific gravity and cost of starting materials. Thus, the Ba content is desirably 0 to 2 percent. The Ba content preferably falls within a range of 0 to 1 percent, more preferably within a range of 0 to 0.5 percent, and still more preferably, is zero.

[0049]

To achieve meltability, moldability, glass stability, thermal expansion characteristics, and chemical durability, the total content of Mg, Ca, Sr, and Ba is desirably 0 to 10 percent, preferably 0 to 5 percent, and more preferably, 0.1 to 2 percent.

[0050]

Since Mg and Ca are more desirable components than Sr and Ba among the alkaline earth metal components as set forth above, the total content of Mg and Ca is desirably 0 to 5 percent, preferably 0.1 to 5 percent. Further, the total content of Sr and Ba is desirably 0 to 2 percent, preferably 0 to 1 percent, and more preferably, zero.

[0051]

Zr, Ti, La, Nb, Ta, and Hf serve to enhance chemical durability, particularly alkali resistance. However, when employed in excessive quantity, they reduce meltability. Thus, the total content of Zr, Ti, La, Nb, Ta, and Hf is desirably 0 to 10 percent, preferably 0.1 to 10 percent, and more preferably, 1 to 5 percent.

[0052]

Of these, Zr does a particularly good job of enhancing chemical durability, particularly alkali resistance, while maintaining glass stability. It also serves to increase rigidity, toughness, and chemical strengthening efficiency. Accordingly, the Zr content is desirably 0 to 5 percent. The Zr content preferably falls within a range of 0.1 to 5 percent, more preferably a range of 1 to 2 percent.

[0053]

To increase chemical durability, particularly alkali resistance, and chemical strengthening efficiency without compromising meltability, the ratio of the Zr content to the total content of Zr, Ti, La, Nb, Ta, and Hf is desirably 0.1 to 1, preferably 0.5 to 1, and more preferably, 1.

[0054]

Sulfates can be added as clarifying agents to glass I in a range of 0 to 1 percent. However, they present a risk of unmelted material in the glass melt being scattered about by blowing, causing a sharp increase in foreign material in the glass. Thus, the incorporation of sulfates is undesirable.

[0055]

By contrast, Sn and Ce do not present the problem of scattering by blowing or increased foreign material, and have good effects in eliminating bubbles.

[0056]

Additional components that can be incorporated include B, which serves to reduce brittleness and enhance meltability. However, when introduced in excessive quantity, it diminishes chemical durability. The content thereof is thus desirably 0 to 2 percent, preferably 0 to 1 percent, and still more preferably, zero.

[0057]

Zn serves to enhance meltability and increase rigidity. However, the incorporation of an excessive quantity reduces chemical durability and causes the glass to become brittle. Accordingly, the content thereof is desirably 0 to 3 percent, preferably 0 to 1 percent, and still more preferably, zero.

[0058]

P can also be incorporated in small amounts without forfeiting the object of the invention. However, the incorporation of an excessive quantity reduces chemical durability. Thus, the content thereof is desirably 0 to 1 percent, preferably 0 to 0.5 percent, more preferably 0 to 0.2 percent, and still more preferably, zero.

[0059]

From the perspectives of enhancing meltability, moldability, and glass stability; increasing chemical durability, particularly alkali resistance; increasing heating efficiency during manufacturing of a magnetic recording medium; suppressing the leaching out of alkali from the glass surface due to the mixed alkali effect; and the like, a particularly desirable form of glass I comprises, denoted as mass percentages:

Si 28 to 34 percent,

Al 6 to 10 percent

(wherein the total content of Si and Al is 37 percent or greater),

Li 0.1 to 3 percent,

Na 5 to 10 percent,

K 0.1 to 1 percent

(where the total content of Li, Na, and K is 7 to 13 percent),

Mg 0.1 to 2 percent,

Ca 0.1 to 2 percent,

Sr and Ba in total 0 to 1 percent,

Zr 1 to 5 percent,

B 0 to 1 percent, and

Zn 0 to 1 percent

(referred to as glass I-1).

[0060]

A particularly desirable form of glass I-1 comprises:

Si 28 to 34 percent,

Al 6 to 10 percent

(wherein the total content of Si and Al is 37 percent or greater),

Li 1 to 3 percent,

Na 6 to 10 percent,

K 0.1 to 1 percent,

Mg 0.1 to 2 percent,

Ca 0.1 to 2 percent,

Sr and Ba in total 0 to 0.7 percent, and

Zr 1 to 3 percent.

This particularly desirable form affords the effects of a reduction in the specific gravity of the glass, further enhanced alkali resistance, and even better meltability.

From the perspectives of enhancing meltability, moldability, and glass stability; increasing chemical durability; and increasing heating efficiency during manufacturing of a magnetic recording medium, a desirable second form of glass I comprises, denoted as mass percentages:

Si 28 to 34 percent,
Al 6 to 10 percent
(wherein the total content of Si and Al is 37 percent or greater),
Li 1 to 5 percent,
Na 1 to 10 percent,
K 0.1 to 3 percent
(where the total content of Li, Na, and K is 5 to 11 percent),
Mg 0 to 2 percent,
Ca 0 to 2 percent,
Sr 0 to 1 percent,
Ba 0 to 1 percent,
Zr, Ti, La, Nb, Ta, and Hf in total 1 to 10 percent,
B 0 to 1 percent,
Zn 0 to 1 percent, and
P 0 to 1 percent

(referred to as glass I-2).

[0061]

A particularly desirable form of glass I-2 comprises:

Si 28 to 34 percent,
Al 6 to 10 percent
(wherein the total content of Si and Al is 37 percent or greater),
Li 1 to 5 percent,
Na 1 to 10 percent,
K 0.1 to 3 percent
(where the total content of Li, Na, and K is 5 to 11 percent),
Mg, Ca, Sr, and Ba in total 0 to 1 percent, and
Ti, La, and Nb in total 3 to 8 percent.

This particularly desirable form affords the effect of limiting the quantity of alkaline earth metal components. The incorporation of Ti, La, and Nb produces better chemical durability. To obtain even better chemical durability, a glass comprising 0.5 to 2 percent of Ti, 1 to 3 percent of La, and 0.5 to 2 percent of Nb is preferred.

[0062]

[Glass II]

Glass II will be described next.

Glass II is a glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, as converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);

in that, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide are added; in that the content of Sb oxide is 0 to 0.1 mass percent; and by not comprising As or F.

[0063]

Below, unless specifically indicated otherwise, the contents of Sn oxide, Ce oxide, and Sb oxide in glass II are given in the form of quantities added as mass percentages based on the total amount of the glass components which are glass components excluding Sn oxide, Ce oxide and Sb oxide. Other component contents and total contents are given as molar percentages.

[0064]

SiO₂, a glass network-forming component, is an essential component that serves to enhance glass stability, chemical durability, and particularly, acid resistance; lower thermal diffusion in the substrate; and increase the heating efficiency of the substrate by radiation. When the content of SiO₂ is less than 60 percent, these functions are not adequately performed. At greater than 75 percent, unmelted material is produced in the glass, the viscosity of the glass becomes excessively high during clarification, and bubble elimination becomes inadequate. When a substrate is formed of glass containing unmelted material, protrusions due to unmelted material are formed on the surface of the substrate by polishing, precluding use as a magnetic recording medium substrate for which an extremely high degree of surface flatness is required. In glass containing bubbles, when a portion of the bubbles are exposed on the substrate surface by

grinding, they become pits, compromising flatness on the main surface of the substrate, thereby precluding use as a magnetic recording medium substrate. Thus, the SiO_2 content is 60 to 75 percent, desirably falling within a range of 65 to 75 percent, preferably falling within a range of 66 to 75 percent, and more preferably, falling within a range of 66 to 70 percent.

[0065]

Al_2O_3 contributes to the formation of the glass network, and serves to enhance glass stability and chemical durability. When the Al_2O_3 content is less than 1 percent, these functions cannot be adequately performed, and when 15 percent is exceeded, the meltability of the glass diminishes and unmelted material tends to be produced. Accordingly, the Al_2O_3 content is 1 to 15 percent. The Al_2O_3 content desirably falls within a range of 5 to 13 percent, preferably within a range of 7 to 12 percent.

[0066]

To enhance chemical durability, it is desirable for the total content of SiO_2 and Al_2O_3 to be 65 percent or greater, preferably 70 percent or greater, more preferably 73 percent or greater, still more preferably 74 percent or greater, yet more preferably, 75 percent or greater, and even more preferably, 75.5 percent or greater. Increasing the total content of SiO_2 and Al_2O_3 lowers the thermoconductivity of the glass, increasing the heating efficiency of the substrate during manufacturing of a magnetic recording medium.

[0067]

Li_2O is an essential component that serves to strongly increase the meltability and moldability of the glass, even in alkalis. It is also desirable for imparting suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion. In chemically strengthened glass, it serves as a component that supports ion exchange during chemical strengthening. When the Li_2O content is less than 0.1 percent, these functions cannot be adequately achieved. In particular, in glass II, in which relatively large quantities of SiO_2 and Al_2O_3 are incorporated to enhance chemical durability, an Li_2O content of less than 0.1 percent results in an excessively high viscosity of the glass during clarification, precluding an adequate clarifying effect. Additionally, when the Li_2O content exceeds 20 percent, chemical durability, particularly acid resistance, diminishes. When the glass is formed into a substrate, the amount of alkali leaching out from the substrate surface increases. The precipitating alkali damages the information

recording layer and the like. Accordingly, the Li_2O content is 0.1 to 20 percent. The Li_2O content desirably falls within a range of 1 to 15 percent, preferably within a range of 5 to 10 percent.

[0068]

Na_2O is an essential component that serves to enhance glass meltability and moldability, and is desirable for imparting suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion. In a chemically strengthened glass, it serves as a component that supports ion exchange during chemical strengthening. When the Na_2O content is less than 0.1 percent, these functions cannot be adequately achieved. In particular, in glass II, in which relatively large quantities of SiO_2 and Al_2O_3 are incorporated to enhance chemical durability, an Na_2O content of less than 0.1 percent results in an excessively high viscosity of the glass during clarification, precluding an adequate clarifying effect. Additionally, when the Na_2O content exceeds 15 percent, chemical durability, particularly acid resistance, diminishes. When the glass is formed into a substrate, the amount of alkali leaching out from the substrate surface increases. The precipitating alkali damages the information recording layer and the like. Accordingly, the Na_2O content is 0.1 to 15 percent, desirably falling within a range of 1 to 15 percent, preferably a range of 8 to 13 percent.

[0069]

Li_2O and Na_2O are essential components in glass II, producing effects by reducing and preventing the leaching out of alkalis from the glass surface due to the effect of alkali mixing.

[0070]

K_2O is an optional component that serves to enhance glass meltability and moldability, and is desirable for imparting suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion. However, when the content of K_2O exceeds 5 percent, chemical durability, particularly acid durability, diminishes. When the glass is formed into a substrate, the amount of alkali leaching out of the substrate surface increases. The precipitating alkali damages the information recording layer and the like. Accordingly, the content of K_2O is 0 to 5 percent, desirably falling within a range of 0.1 to 2 percent, and preferably falling within a range of 0.1 to 1 percent.

[0071]

In glass II, the total content of Li_2O , Na_2O , and K_2O is limited to 25 percent or less to achieve good chemical durability. However, in addition to serving to enhance meltability and moldability as well as serving to impart suitable thermal expansion characteristics to a magnetic recording medium substrate by increasing the coefficient of thermal expansion, Li_2O , Na_2O , and K_2O also serve to lower the viscosity of the glass during clarification, promoting bubble elimination. When these factors are taken into account, the total content of Li_2O , Na_2O , and K_2O desirably falls within a range of 15 to 25 percent. The lower limit of the total content of Li_2O , Na_2O , and K_2O is preferably 18 percent, and the upper limit thereof is preferably 23 percent, more preferably 22 percent, still more preferably 21 percent, and yet still more preferably, 20 percent.

[0072]

In glass II, which contains relatively large quantities of SiO_2 and Al_2O_3 , the temperature of the glass during clarification is high, despite containing Li_2O and Na_2O . In such a glass, Sb oxide has a poorer clarifying effect than Sn oxide or Ce oxide, described further below. In a glass to which Sn oxide is added, the clarifying effect ends up is deteriorated by Sb oxide. When the Sb oxide content exceeds 0.1 percent, the coexistence of Sn oxide causes the residual bubbles in the glass to increase sharply. Accordingly, the Sb oxide content is limited to 0.1 percent or less in glass II. The Sb oxide content desirably falls within a range of 0 to 0.1 percent, preferably within a range of 0 to 0.05 percent, still more preferably within a range of 0 to 0.01 percent, and yet more preferably, within a range of 0 to 0.001 percent. The addition of no Sb oxide (glass containing no Sb) is particularly desirable. Not incorporating Sb (rendering the glass "Sb-free") reduces the density of residual bubbles in the glass to a range of from about one part in several to about one percent. Here, the term "Sb oxide" means oxides such as Sb_2O_3 and Sb_2O_5 that have melted into the glass, irrespective of the valence number of Sb.

[0073]

Sb oxide has a greater effect on the environment than Sn oxide or Ce oxide. Thus, reducing the Sb oxide content, or using no Sb at all, is desirable because it lessens the effect on the environment.

[0074]

Although As is a powerful clarifying agent, the glass is desirably rendered As-free due to the toxicity of this element. Further, although F exhibits a clarifying effect, it volatilizes during glass manufacturing, causing the properties and

characteristics of the glass to fluctuate, and creating problems in terms of stable melting and molding. Further, volatilization causes the generation of heterogeneous portions, called striae, in the glass. When striae are present in the glass and polishing is conducted, slight differences in the rates at which the glass is removed in striae portions and homogenous portions produce irregularities on the polished surface, which are undesirable in magnetic recording medium substrates for which a high degree of flatness is required. Accordingly, As and F are not incorporated into glass II.

[0075]

Glass II is prepared by the steps of melting a glass starting material, clarifying the glass melt that has been obtained by melting the glass starting material, homogenizing the clarified glass melt, causing the homogenized glass melt to flow out, and molding it. In this process, the clarifying step is conducted at a relatively high temperature and the homogenizing step at a relatively low temperature. In the clarifying step, bubbles are actively produced in the glass, and clarification is promoted by incorporating minute bubbles contained in the glass to form large bubbles, which then tend to rise. Additionally, an effective method of eliminating bubbles is to incorporate, as a glass component, oxygen that is present as a gas within the glass in a state where the temperature of the glass is lowered as it flows out.

[0076]

The clarification mechanisms of Sn and Ce are as set forth above. By coexisting Sn oxide and Ce oxide, it is possible to adequately eliminate bubbles even in glasses in which the incorporation of Sb, As, and F is limited.

[0077]

Sn oxide is necessarily incorporated in a quantity of 0.01 percent or greater to achieve the above clarifying effect. However, when 0.7 percent is exceeded, metallic tin precipitates out into the glass. When the glass is polished to prepare a substrate, protrusions of metallic tin are produced on the substrate surface, and areas in which metallic tin drops out of the surface form pits, risking loss of the flatness of the substrate surface. Accordingly, the Sn oxide content is 0.01 to 0.7 percent. From the above perspectives, the Sn content desirably falls within a range of 0.1 to 0.6 percent, preferably within a range of 0.15 to 0.5 percent. Here, the term "Sn oxide" means oxides such as SnO and SnO₂ that have melted into the glass, irrespective of the valence of Sn. The Sn oxide content is the total content of oxides such as SnO and SnO₂.

[0078]

Ce oxide is desirably incorporated to enhance the clarifying effect. However, when 1.4 percent is exceeded, it reacts strongly with the refractory material and platinum constituting the melting vessel, and reacts strongly with the metal mold used to mold the glass. This increases impurities, negatively affecting the surface state. Accordingly, the Ce oxide content is 0 to 1.4 percent. The Ce content desirably falls within a range of 0 to 0.7 percent, preferably within a range of 0.003 to 0.7 percent. Here, the term "Ce oxide" means oxides such as CeO_2 and Ce_2O_3 that have melted into the glass, irrespective of the valence of Ce. The Ce oxide content is the total content of oxides such as CeO_2 and Ce_2O_3 .

[0079]

Sn and Ce serve to produce crystal nuclei when preparing crystalline glass. Since the glass in the present invention is employed in a substrate comprised of amorphous glass, it is desirable that no crystals precipitate during heating. Thus, the addition of excessive amounts of Sn oxide and Ce oxide is to be avoided.

[0080]

As set forth above, since Sn oxide releases oxygen gas into the glass melt at high temperature, when a large quantity of Sn oxide is employed, the quantity of Ce oxide, which incorporates oxygen gas present in the melt at low temperature, is also desirably increased. With this point in mind, preferred ranges of the Sn oxide and Ce oxide contents are given below.

[0081]

When the Sn oxide content is 0.1 percent or greater but less than 0.15 percent, the Ce oxide content is desirably kept to 0 to 0.45 percent, preferably 0 or greater but less than 3 percent, more preferably 0.001 to 0.18 percent, still more preferably 0.001 to 0.15 percent, yet still more preferably 0.001 to 0.11 percent, and even more preferably, 0.003 to 0.1 percent.

[0082]

When the Sn oxide content is 0.15 percent or greater but less than 0.35 percent, the Ce oxide content is desirably kept to 0 to 0.45 percent, preferably 0.001 to 0.4 percent, and more preferably, 0.003 to 0.25 percent.

[0083]

When the Sn oxide content is 0.35 percent or greater but less than 0.45 percent, the Ce oxide content is desirably kept to 0 to 0.45 percent, preferably 0.001 to 0.4 percent, and more preferably 0.006 to 0.35 percent.

[0084]

When the Sn oxide content is 0.45 percent or greater but less than 0.5 percent, the Ce oxide content is desirably kept to 0.001 to 0.5 percent, preferably 0.008 to 0.5 percent, and more preferably, 0.06 to 0.5 percent.

[0085]

When the Sn oxide content is 0.5 percent or greater but less than 0.55 percent, the Ce oxide content is desirably kept to 0.001 to 0.5 percent, preferably 0.008 to 0.5 percent.

[0086]

When the Sn oxide content is 0.55 percent or greater but less than 0.6 percent, the Ce oxide content is desirably kept to 0.0005 to 0.6 percent, preferably 0.005 to 0.6 percent, and more preferably, 0.1 to 0.6 percent.

[0087]

For bubbles 0.3 mm and smaller in size (the size of bubbles (voids) remaining in the solidified glass), Sn oxide works strongly to eliminate both relatively large and extremely small bubbles. Ce oxide can be optionally added. However, the clarifying effect can be increased by keeping the ratio (by mass) of the Ce oxide content to the Sn oxide content, $\text{CeO}_2/\text{SnO}_2$, to 2.0 or lower.

[0088]

When Ce oxide is added along with Sn oxide, the density of large bubbles of about 50 micrometers to 0.3 mm can be reduced to about one in several tens of parts. To achieve such an effect, the lower limit of the ratio (by mass) of the Ce oxide content to the Sn oxide content, Ce/Sn , is desirably 0.01, preferably 0.02, more preferably 0.05, and still more preferably 0.1. The upper limit of the mass ratio of the Ce oxide content to the Sn oxide content, Ce/Sn , is desirably 1.8, preferably 1.6, more preferably 1.5, still more preferably 1.4, yet more preferably 1.3, yet still more preferably 1.2, and even more preferably, 1.1.

[0089]

A desirable form of glass II comprises:

MgO 0 to 10 percent,

CaO 0 to 10 percent,

SrO 0 to 5 percent, and

BaO 0 to 5 percent.

[0090]

MgO serves to enhance glass meltability, moldability, and glass stability; heighten rigidity and hardness; and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability.

Thus, the MgO content is desirably 0 to 10 percent. The MgO content preferably falls within a range of 0 to 5 percent, more preferably, within a range of 0.1 to 5 percent.

[0091]

CaO specifically serves to enhance glass meltability, moldability, and glass stability; heighten rigidity and hardness; and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability. Thus, the CaO content is desirably 0 to 10 percent. The Ca content preferably falls within a range of 0 to 5 percent, more preferably, within a range of 0.1 to 5 percent.

[0092]

SrO also serves to enhance glass meltability, moldability, and glass stability, and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability and increases the specific gravity and cost of starting materials. Thus, the SrO content is desirably 0 to 5 percent. The SrO content preferably falls within a range of 0 to 2 percent, more preferably within a range of 0 to 1 percent, and still more preferably, is zero.

[0093]

BaO also serves to enhance glass meltability, moldability, and glass stability, and increase the coefficient of thermal expansion. However, the incorporation of an excessive quantity reduces chemical durability and increases the specific gravity and cost of starting materials. Thus, the BaO content is desirably 0 to 5 percent. The Ba content preferably falls within a range of 0 to 2 percent, more preferably within a range of 0 to 1 percent, and still more preferably, is zero.

[0094]

To achieve meltability, moldability, glass stability, thermal expansion characteristics, and chemical durability, the total content of MgO, CaO, SrO, and BaO is desirably 0.1 to 10 percent, preferably 0.1 to 5 percent, and more preferably, 1 to 5 percent.

[0095]

Since MgO and CaO are more desirable components than SrO and BaO among the alkaline earth metal components as set forth above, the total content of MgO and CaO is desirably 0 to 5 percent, preferably 0.1 to 5 percent, and

more preferably, 1 to 5 percent. Further, the total content of SrO and BaO is desirably 0 to 5 percent, preferably 0 to 1 percent, and more preferably, zero.

[0096]

ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ serve to enhance chemical durability, particularly alkali resistance. However, when employed in excessive quantity, they reduce meltability. Thus, the total content of ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ is desirably 0 to 5 percent, preferably 0.1 to 5 percent, and more preferably, 0.1 to 3 percent.

[0097]

Of these, ZrO₂ does a particularly good job of enhancing chemical durability, particularly alkali resistance, while maintaining glass stability. It also serves to increase rigidity, toughness, and chemical strengthening efficiency. Accordingly, the ZrO₂ content is desirably 0.1 to 5 percent. The Zr content preferably falls within a range of 0.1 to 3 percent, more preferably within a range of 0.1 to 2 percent.

[0098]

To increase chemical durability, particularly alkali resistance, and chemical strengthening efficiency without compromising meltability, the ratio of the ZrO₂ content to the total content of ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ is desirably 0.1 to 1, preferably 0.3 to 1, more preferably 0.5 to 1, still more preferably 0.8 to 1, yet still more preferably 0.9 to 1, and particularly preferably, 1.

[0099]

Sulfates can be added as clarifying agents to glass II in a range of 0 to 1 percent. However, they present a risk of unmelted material in the glass melt being scattered about by blowing, causing a sharp increase in foreign material in the glass. Thus, no incorporation of sulfates is desirable.

[0100]

By contrast, Sn oxide and Ce oxide do not present the problem of scattering by blowing or increased foreign material, and have good effects in eliminating bubbles.

[0101]

Additional components that can be incorporated include B₂O₃, which serves to reduce brittleness and enhance meltability. However, when introduced in excessive quantity, it diminishes chemical durability. The content thereof is thus desirably 0 to 3 percent, preferably 0 to 1 percent, and still more preferably, zero.

[0102]

ZnO serves to enhance meltability and increase rigidity. However, the incorporation of an excessive quantity reduces chemical durability and causes the glass to become brittle. Accordingly, the content thereof is desirably 0 to 3 percent, preferably 0 to 1 percent, and still more preferably, zero.

[0103]

P₂O₅ can also be incorporated in small amounts without forfeiting the object of the invention. However, the incorporation of an excessive quantity reduces chemical durability. Thus, the content thereof is desirably 0 to 1 percent, preferably 0 to 0.5 percent, more preferably 0 to 0.3 percent, and still more preferably, zero.

[0104]

From the perspectives of enhancing meltability, moldability, and glass stability; increasing chemical durability, particularly alkali resistance; increasing heating efficiency during manufacturing of a magnetic recording medium; suppressing the leaching out of alkali from the glass surface due to the mixed alkali effect; and the like, a particularly desirable form of glass II comprises, denoted as mass percentages:

SiO₂ 66 to 70 percent,

Al₂O₃ 7 to 12 percent

(where the total content of SiO₂ and Al₂O₃ is 75 percent or greater),

Li₂O 5 to 10 percent,

Na₂O 8 to 13 percent,

K₂O 0.1 to 2 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 15 to 22 percent),

MgO 0.1 to 5 percent,

CaO 0.1 to 5 percent,

SrO and BaO in total 0 to 1 percent,

ZrO₂ 0.1 to 2 percent,

B₂O₃ 0 to 1 percent, and

ZnO 0 to 1 percent

(referred to as glass II-1).

[0105]

A particularly desirable form of glass II-1 comprises:

SiO₂ 66 to 70 percent,

Al₂O₃ 7 to 11 percent,

Li₂O 6 to 10 percent,
Na₂O 9 to 13 percent,
K₂O 0.1 to 1 percent
(wherein the total content of Li₂O, Na₂O, and K₂O is 16 to 22 percent),
MgO 0.1 to 2 percent,
CaO 0.5 to 4 percent,
SrO and BaO in total 0 to 0.5 percent, and
ZrO₂ 0.5 to 2 percent.

This particularly desirable form affords the effects of reducing the specific gravity of the glass, further enhancing alkali resistance, and further improving meltability.
[0106]

From the perspectives of enhancing meltability, moldability, and glass stability; increasing chemical durability; increasing heating efficiency during manufacturing of a magnetic recording medium; and the like, a desirable form of glass II comprises, denoted as mass percentages:

SiO₂ 66 to 70 percent,
Al₂O₃ 5 to 12 percent,
Li₂O 5 to 20 percent,
Na₂O 1 to 13 percent,
K₂O 0.1 to 2 percent
(wherein the total content of Li₂O, Na₂O, and K₂O is 18 to 22 percent),
MgO and CaO in total 0 to 5 percent,
SrO and BaO in total 0 to 5 percent,
ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ in total 0.1 to 5 percent,
B₂O₃ 0 to 3 percent,
ZnO 0 to 1 percent, and
P₂O₅ 0 to 0.5 percent

(referred to as glass II-2).

[0107]

A particularly desirable form of glass II-2 comprises:

SiO₂ 66 to 70 percent;
Al₂O₃ 5 to 11 percent
Li₂O 10 to 19 percent;
Na₂O 1 to 6 percent;
K₂O 0.1 to 2 percent,
MgO and CaO in total 0 to 2 percent;

SrO and BaO in total 0 to 2 percent; and

ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ in total 0.5 to 4 percent.

In this particularly desirable form, the quantity of alkaline earth metal components is suppressed and TiO₂, La₂O₃, and Nb₂O₅ are incorporated to achieve better chemical durability. To obtain better chemical durability, a glass containing 0.5 to 3 percent of TiO₂, 0.1 to 2 percent of La₂O₃, and 0.1 to 2 percent of Nb₂O₅ is preferred.

[0108]

[Common features of glasses I and II]

The common features of glasses I and II will be described below.

In the glasses of the present invention, Sn, or Sn and Ce, exhibit better clarifying effects than Sb. As set forth above, Sn primarily actively releases oxygen gas in high temperature states (a temperature range of about 1,400 to 1,600°C), thereby strongly promoting clarification. Ce strongly incorporates oxygen gas in low temperature states (a temperature range of about 1,200 to 1,400°C), fixing it as a glass component. The viscosity of the glass at 1,400°C, where the temperature range of the clarifying effect of Sn meets the temperature range of the clarifying effect of Ce, greatly affects clarification efficiency.

[0109]

To increase the chemical durability of both glass I and glass II, the quantities of the Si component and Al component are increased, and an alkali component is made an essential component. However, since the quantities thereof are limited as set forth above, the viscosity of the glass at 1,400°C exhibits an upward trend. When the viscosity of the glass in the clarification temperature range becomes excessively high, the rate at which bubbles rise in the glass decreases and bubble elimination deteriorates.

[0110]

To simultaneously achieve enhanced chemical durability and an improved clarifying effect in the present invention, the viscosity at 1,400°C is desirably made 10³ dPa·s or lower while employing a total content of Si and Al of 30 mass percent or higher in glass I, and the viscosity at 1,400°C is desirably made 10³ dPa·s or lower while employing a total content of SiO₂ and Al₂O₃ of 65 molar percent or greater in glass II.

[0111]

From the perspective of enhancing chemical durability, the range of the total content of Si and Al in glass I is desirably 32 mass percent or greater,

preferably 35 mass percent or greater, more preferably 36 mass percent or greater, and still more preferably, 37 mass percent or greater. The range of the total content of SiO_2 and Al_2O_3 in glass II is desirably 65 molar percent or greater, preferably 70 molar percent or greater, more preferably 73 molar percent or greater, still more preferably 74 molar percent or greater, yet still more preferably 75 molar percent or greater, and even more preferably, 75.5 molar percent or greater.

[0112]

To enhance the clarifying effect, the viscosity of both glass I and glass II is desirably $10^{2.7}$ dPa·s or lower at 1,400°C.

[0113]

In this manner, the density of residual bubbles contained in the glass per unit mass is kept to 60 bubbles/kg or lower, desirably 40 bubbles/kg or lower, preferably 20 bubbles/kg or lower, more preferably 10 bubbles/kg or lower, still more preferably 2 bubbles/kg or lower, and even more preferably, 0 bubbles/kg. This permits the highly efficient mass production of substrates suited to high recording density magnetic recording media.

[0114]

Halogens other than F, such as Cl, Br, and I, are desirably not added to glass I or glass II. These halogens also volatilize from the glass melt, producing striae, which are undesirable in the formation of a flat substrate surface.

[0115]

Since Pb, Cd, and the like negatively affect the environment, their incorporation is also desirably avoided.

[0116]

In both glasses I and II, the incorporation of Sn in the form of SnO_2 is desirable for effectively releasing oxygen gas at high temperature.

[0117]

Adding Sn and Ce as set forth above increases the Young's modulus of the glass. Increasing the Young's modulus affords good fluttering resistance during high-speed rotation of a magnetic recording medium equipped with a substrate made of glass I or glass II.

[0118]

Further, the addition of Sn and Ce as set forth above permits the stable production of thinner blanks in the course of press molding a glass melt into disk-

shaped substrate blanks, making it possible to reduce the sheet thickness tolerance of the glass blanks.

[0119]

Further, the addition of Ce makes it possible to use the emission of blue fluorescence when glass I or glass II is irradiated with light of short wavelength, such as UV light, to readily distinguish between substrates comprised of glass I or glass II and substrates made from glass to which no Ce has been added, which are identical in appearance and otherwise difficult to distinguish visually. That is, by irradiating these two types of substrates with UV light and checking for the presence of fluorescence, it is possible to distinguish between them without analyzing the composition of the glasses. As a result, in the course of producing magnetic recording media with substrates comprised of multiple types of glass, this test can be used to avoid problems caused by the mixing in of substrates comprised of heterogeneous glass.

[0120]

Further, by irradiating light of short wavelength, such as UV light, onto a substrate comprised of glass I or glass II to which Ce has been added to generate fluorescence, it is possible to check relatively easily for the presence of foreign matter on the substrate surface.

[0121]

The method for manufacturing the glass for a magnetic recording medium substrate of the present invention will be described next. The first form of the method for manufacturing a glass for a magnetic recording medium of the present invention (referred to as "glass manufacturing method I") is a method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by: mixing a glass starting material to which Sn, and optionally Ce, are added, comprising, denoted as mass percentages:

Si 20 to 40 percent;

Al 0.1 to 10 percent;

Li 0.1 to 5 percent;

Na 0.1 to 10 percent;

K 0 to 5 percent

(wherein the total content of Li, Na, and K is 15 percent or lower);

Sn 0.005 to 0.6 percent; and

Ce 0 to 1.2 percent;

so as to permit obtaining a glass with an Sb content of 0 to 0.1 percent and containing no As or F; melting the glass starting material; clarifying the glass melt obtained; and then molding the glass melt obtained. That is, glass manufacturing method I is a method for manufacturing glass I. The desirable composition range and characteristic ranges thereof are as set forth above.

[0122]

A desirable form of glass manufacturing method I is a method comprising mixing a glass starting material comprising a ratio of Ce content to Sn content, Ce/Sn, falling within a range of 0.02 to 1.3; maintaining the glass melt obtained at 1,400 to 1,600°C; decreasing the temperature; maintaining the temperature at 1,200 to 1,400°C; and conducting molding.

[0123]

Employing a ratio of Ce content to Sn content, Ce/Sn, of 0.02 to 1.3 and maintaining the glass melt at 1,400 to 1,600°C lowers the viscosity of the glass, creating a state in which bubbles in the glass readily rise. Further, the release of oxygen by Sn produces a clarification-enhancing effect. Subsequently lowering the temperature of the glass melt and maintaining it at 1,200 to 1,400°C makes it possible to markedly enhance the elimination of bubbles through the incorporation of oxygen by Ce.

[0124]

The second form of the method for manufacturing a glass for a magnetic recording medium substrate of the present invention (referred to as "glass manufacturing method II") is a method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by: mixing a glass starting material to which Sn, and optionally Ce, are added, comprising, as converted based on the oxides, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);

so as to permit obtaining a glass comprising 0 to 0.1 percent of Sb, no As or F, and, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide; melting the glass starting material; clarifying the glass melt obtained; and molding the glass melt

obtained. That is, glass manufacturing method II is a method for manufacturing glass II. The desirable composition range and characteristic ranges thereof are as set forth above.

[0125]

A desirable form of glass manufacturing method II is a method comprising mixing the glass starting material so that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) denoted as a mass percentage falls within a range of 0.02 to 1.2; melting the starting material; maintaining the glass melt obtained at 1,400 to 1,600°C; reducing the temperature; maintaining the temperature at 1,200 to 1,400°C; and molding the glass melt.

[0126]

Employing a ratio of Ce oxide content to Sn oxide content (Ce oxide/Sn oxide) of 0.02 to 1.2 and maintaining the glass melt at 1,400 to 1,600°C lowers the viscosity of the glass, creating a state in which bubbles in the glass readily rise. Further, the release of oxygen by Sn produces a clarification-enhancing effect. Subsequently lowering the temperature of the glass melt and maintaining it at 1,200 to 1,400°C makes it possible to markedly enhance the elimination of bubbles through the incorporation of oxygen by Ce.

[0127]

When both Sn and Ce are present in the glass melt in glass manufacturing methods I and II, the characteristic of the glass in the form of a viscosity at 1,400°C of 10^3 dPa·s or lower and the synergistic effect due to the presence of both Sn and Ce markedly enhance bubble elimination.

[0128]

Denoting the period of maintenance at 1,400 to 1,600°C as TH and the period of maintenance at 1,200 to 1,400°C as TL, it is desirable to keep TL/TH to 0.5 or less, preferably 0.2 or less. Increasing TH relative to TL in this manner facilitates the discharging of gases within the glass to the exterior. To promote the gas incorporating effect of Ce within the glass, TL/TH is desirably greater than 0.01, preferably greater than 0.02, more preferably greater than 0.03, and still more preferably, greater than 0.04.

[0129]

To increase the individual bubble eliminating effects of Sn and Ce, the temperature difference in the course of dropping the temperature from within the range of 1,400 to 1,600°C to within the range of 1,200 to 1,400°C is desirably 30°C or greater, preferably 50°C or greater, more preferably 80°C or greater, still

more preferably 100°C or greater, and even more preferably, 150°C or greater. The upper limit of the temperature difference is 400°C.

[0130]

In glass manufacturing methods I and II, the quantities of Sn and Ce added are desirably established to yield a density of residual bubbles within the glass of 100 bubbles/kg or lower. The quantities of Sn and Ce added are preferably established to yield a density of residual bubbles of 60 bubbles/kg or lower. The quantities of Sn and Ce added are more preferably established to yield a density of residual bubbles of 40 bubbles/kg or lower. The quantities of Sn and Ce added are still more preferably established to yield a density of residual bubbles of 20 bubbles/kg or lower. The quantities of Sn and Ce added are yet still more preferably established to yield a density of residual bubbles of 10 bubbles/kg or lower. The quantities of Sn and Ce added are even more preferably established to yield a density of residual bubbles of 2 bubbles/kg or lower. The quantities of Sn and Ce added are particularly preferably established to yield a density of residual bubbles of 0 bubbles/kg. Even when residual bubbles are present, the size of all of the bubbles can be kept to 0.3 mm or less. The above quantities of Sn and Ce added can be specified as the total quantity of Sn and Ce added, as a ratio of the quantities of Sn and Ce added, or the like.

[0131]

In glass manufacturing methods I and II, that is, in the methods for manufacturing glasses I and II, the glass starting materials are charged to a melting vat, heated and melted to obtain a glass melt. The glass melt is then sent to a clarifying vat. While the glass melt is in the clarifying vat, it is maintained in a higher temperature state than in the melting vat -- for example, within a temperature range of 1,400 to 1,600°C. The glass melt is then sent to an operating vat from the clarifying vat. In the operating vat, it is stirred by a stirring device. Once it has been homogenized, it is caused to flow out of a outflow pipe connected to the operating vat and then molded. The clarifying vat and operating vat are linked by means of a connecting apparatus, such as a pipe. While the glass melt is flowing through the connecting apparatus, the temperature decreases due to heat exchange with the connecting apparatus. The interior of the operating vat is maintained at 1,200 to 1,400°C. In such a process, the Sn discharges oxygen gas within the clarifying vat, promoting clarification. The Ce incorporates oxygen gas within the glass in the operating vat, fixing the oxygen in the glass composition and thereby promoting the bubble eliminating effect.

[0132]

The melting vat, in which the glass starting materials are heated and vitrified, and the clarifying vat, are comprised of a refractory material such as electrocasting bricks, sintered bricks, or the like. The operating vat and the connecting pipe linking the clarifying vat and the operating vat, and the outflow pipe, are desirably comprised of platinum or a platinum alloy (referred to as a "platinum-based material"). The molten material within the melting vat where the starting material is vitrified, and the glass melt within the clarifying vat reaching the maximum temperature in the glass manufacturing process, both exhibit highly corrosive properties. Although platinum-based materials exhibit good resistance to corrosion, they corrode when they come into contact with highly corrosive glass, mixing into the glass as a solid platinum material. Since the solid platinum material exhibits resistance to corrosion, platinum that has mixed into the glass as a solid material does not completely melt into the glass, but remains as foreign matter in the molded glass. However, refractory material that corrodes will mix into the glass, melting into the glass and tending not to remain as foreign matter. Accordingly, the melting vat and clarifying vat are desirably manufactured of a refractory material. When the operating vat is made of a refractory material, the surface of the refractory material melts into the glass melt, generating striae in the glass which was homogeneous, and rendering it heterogeneous. The temperature of the operating vat reaches up to 1,400°C, and the corrosiveness of the glass decreases. Thus, the operating vat, connecting pipe, and outflow pipe are desirably comprised of platinum-based material that tends not to melt into the glass. The stirring apparatus that stirs and homogenizes the glass melt in the operating vat is also desirably comprised of a platinum-based material.

[0133]

[Glass III]

Glass III will be described next.

Glass III is a glass for a magnetic recording medium substrate comprised of oxide glass, characterized by comprising, converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,
Al₂O₃ 1 to 15 percent,
Li₂O 0.1 to 20 percent,
Na₂O 0.1 to 15 percent,
K₂O 0 to 5 percent

(where the total content of Li_2O , Na_2O , and K_2O is 25 percent or less); by comprising a 0.1 to 3.5 mass percent total content, based on the total amount of the glass components, of Sn oxide and Ce oxide; in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 0.01 to 0.99; in that the Sb oxide content is 0 to 0.1 percent; and by comprising no As or F.

[0134]

Below, unless specifically indicated otherwise, the contents of Sn oxide, Ce oxide, and Sb oxide are given in the form of quantities added as mass percentages based on the total amount of the glass components. Additionally, component contents and total contents are given as molar percentages.

[0135]

The various contents of SiO_2 , Al_2O_3 , Li_2O , Na_2O , and K_2O , and the total contents of Na_2O , and K_2O in glass III are identical to those in glass II.

[0136]

In glass III, which comprises relatively large contents of SiO_2 and Al_2O_3 , the temperature of the glass during clarification is high despite containing Li_2O and Na_2O . In such a glass, Sb oxide has a poorer clarifying effect than Sn oxide or Ce oxide, described further below. In a glass to which Sn oxide is added, the clarifying effect ends up deteriorating with Sb oxide. When the Sb oxide content exceeds 0.1 percent, the coexistence of Sn oxide causes the residual bubbles in the glass to increase sharply. Accordingly, the Sb oxide content is limited to 0.1 percent or less in glass III. The Sb oxide content desirably falls within a range of 0 to 0.05 percent, preferably within a range of 0 to 0.01 percent, and still more preferably, within a range of 0 to 0.001 percent. The addition of no Sb oxide (glass containing no Sb) is particularly desirable. Not incorporating Sb (rendering the glass "Sb-free") reduces the density of residual bubbles in the glass to a range of from about one part in several to about one percent. Here, the term "Sb oxide" means oxides such as Sb_2O_3 and Sb_2O_5 that have melted into the glass, irrespective of the valence number of Sb.

[0137]

Sb oxide has a greater effect on the environment than Sn oxide or Ce oxide. Thus, reducing the Sb oxide content, or using no Sb at all, is desirable because it lessens the effect on the environment.

[0138]

Although As is a powerful clarifying agent, the glass is desirably rendered As-free due to the toxicity of this element. Further, although F exhibits a clarifying effect, it volatilizes during glass manufacturing, causing the properties and characteristics of the glass to fluctuate, and creating problems in terms of stable melting and molding. Further, volatilization causes the generation of heterogeneous portions, called striae, in the glass. When striae are present in the glass and polishing is conducted, slight differences in the rates at which the glass is removed in striae portions and homogenous portions produce irregularities on the polished surface, which are undesirable in magnetic recording medium substrates for which a high degree of flatness is required. Accordingly, As and F are not incorporated into glass III:

[0139]

Glass III is prepared by the steps of melting a glass starting material, clarifying the glass melt obtained by melting the glass starting material, homogenizing the clarified glass melt, causing the homogenized glass melt to flow out, and molding it. In this process, the clarifying step is conducted at a relatively high temperature and the homogenizing step at a relatively low temperature. In the clarifying step, bubbles are actively produced in the glass, and clarification is promoted by incorporating minute bubbles contained in the glass to form large bubbles, which then tend to rise. Additionally, an effective method of eliminating bubbles is to incorporate, as a glass component, oxygen that is present as a gas within the glass in a state where the temperature of the glass is lowered as it flows out.

[0140]

In glass III, the Sn oxide serves to promote clarification by releasing oxygen gas at high temperature, incorporating the small bubbles contained in the glass into large bubbles, which then tend to rise. Additionally, the Ce oxide serves to eliminate bubbles by incorporating as a glass component the oxygen that is present as a gas in the glass at low temperature. For bubbles 0.3 mm and smaller in size (the size of bubbles (voids) remaining in the solidified glass), Sn oxide works strongly to eliminate both relatively large and extremely small bubbles. When Ce oxide is added along with Sn oxide, the density of large bubbles of about 50 micrometers to 0.3 mm can be reduced to about one in several tens of parts. Employing Ce oxide in combination with Sn oxide in this manner enhances the clarifying effect of the glass over a broad temperature range, from a high temperature range to a low temperature range, permitting

adequate bubble elimination even in glasses in which the incorporation of Sb oxide, As, and F is limited.

[0141]

An adequate clarifying effect cannot be expected when the total content of Sn oxide and Ce oxide is less than 0.1 percent. When 3.5 percent is exceeded, the Sn oxide and Ce oxide do not melt entirely, running the risk of becoming foreign matter and contaminating the glass. When foreign matter appears in even trace quantities on the surface in the course of manufacturing a substrate, it forms protrusions, portions where foreign matter has dropped out become pits, the flatness of the substrate surface is lost, and the substrate can no longer be employed as a magnetic recording medium substrate. Sn and Ce serve to produce crystal nuclei when preparing crystalline glass. Since the glass in the present invention is employed in a substrate comprised of amorphous glass, it is desirable that no crystals precipitate during heating. The addition of excessive amounts of Sn and Ce tends to cause such crystals to precipitate. Thus, the addition of excessive amounts of Sn oxide and Ce oxide is to be avoided. For these reasons, in glass III, the total content of Sn oxide and Ce oxide is 0.1 to 3.5 percent. The total content of Sn oxide and Ce oxide desirably falls within a range of 0.1 to 2.5 percent, preferably within a range of 0.1 to 1.5 percent, and more preferably, within a range of 0.5 to 1.5 percent.

[0142]

In glass III, the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide ($\text{Sn oxide content} / (\text{Sn oxide content} + \text{Ce oxide content})$) falls within a range of 0.01 to 0.99.

[0143]

When this ratio drops below 0.01 or exceeds 0.99, the synergistic effect of the clarifying effect of Sn oxide at high temperature and the clarifying effect of Ce oxide at low temperature becomes difficult to achieve. When an unbalanced amount of either Sn oxide or Ce oxide is added, the oxide that has been incorporated in large quantity from among Sn oxide and Ce oxide tends not to melt entirely, and to produce unmelted material in the glass.

[0144]

For these reasons, the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide ($\text{Sn oxide content} / (\text{Sn oxide content} + \text{Ce oxide content})$) falls within a range of 0.01 to 0.99. This ratio desirably falls within a range of 0.02 and above, preferably a range of 1/3 and above, more preferably a range of

0.35 to 0.99, still more preferably a range of 0.45 to 0.99, yet still more preferably a range of 0.45 to 0.98, and even more preferably, a range of 0.45 to 0.85.

[0145]

The content of Sn oxide is desirably 0.1 percent or greater to achieve the above-described clarifying effect. However, when 3.5 percent is exceeded, it precipitates out of the glass as foreign matter. In the course of grinding the glass, protrusions of foreign matter form on the surface of the substrate, portions where foreign matter has dropped out of the surface become pits, and there is a risk of losing the flatness of the substrate surface. Accordingly, the content of Sn oxide is desirably 0.1 to 3.5 percent. From the above perspective, the Sn content preferably falls within a range of 0.1 to 2.5 percent, more preferably within a range of 0.1 to 1.5 percent, and still more preferably, a range of 0.5 to 1.0 percent. Here, the term "Sn oxide" means oxides such as SnO and SnO₂ that have melted into the glass, irrespective of the valence of Sn. The Sn oxide content is the total content of oxides such as SnO and SnO₂.

[0146]

Ce oxide is desirably incorporated to enhance the clarifying effect. However, when 3.5 percent is exceeded, it reacts strongly with the refractory material and platinum constituting the melt vessel, and reacts strongly with the metal mold used to mold the glass. This increases impurities, negatively affecting the surface state. Accordingly, the Ce oxide content is 0.1 to 3.5 percent. The Ce content desirably falls within a range of 0.5 to 2.5 percent, preferably within a range of 0.5 to 1.5 percent, and still more preferably, within a range of 0.5 to 1.0 percent. Here, the term "Ce oxide" means oxides such as CeO₂ and Ce₂O₃ that have melted into the glass, irrespective of the valence of Ce. The Ce oxide content is the total content of oxides such as CeO₂ and Ce₂O₃.

[0147]

Sn and Ce serve to produce crystal nuclei when preparing crystalline glass. Since the glass in the present invention is employed in a substrate comprised of amorphous glass, it is desirable that no crystals precipitate during heating. Thus, the addition of excessive amounts of Sn oxide and Ce oxide is to be avoided.

[0148]

As set forth above, the addition of Sn and Ce increases the Young's modulus of the glass. Increasing the Young's modulus affords good fluttering resistance during high-speed rotation of a magnetic recording medium equipped with a substrate made from glass III.

[0149]

Further, the addition of Sn and Ce as set forth above permits the stable production of thinner blanks in the course of press molding glass melt into disk-shaped substrate blanks, making it possible to reduce the sheet thickness tolerance of the glass blanks.

[0150]

Further, the addition of Ce makes it possible to use the emission of blue fluorescence when glass III is irradiated with light of short wavelength, such as UV light, to readily distinguish between substrates comprised of glass III and substrates made from glass to which no Ce has been added, which are identical in appearance and otherwise difficult to visually distinguish. That is, by irradiating these two types of substrates with UV light and checking for the presence of fluorescence, it is possible to distinguish between them without analyzing the composition of the glasses. As a result, in the course of producing magnetic recording media with substrates comprised of multiple types of glass, this test can be used to avoid problems caused by contamination of substrates comprised of heterogeneous glass.

[0151]

Further, by irradiating light of short wavelength, such as UV light, onto a substrate comprised of glass III, it is possible to check relatively easily for the presence of foreign matter on the substrate surface.

[0152]

A desirable form of glass III of the present invention comprises:

MgO 0 to 10 percent;

CaO 0 to 10 percent;

SrO 0 to 5 percent;

BaO 0 to 5 percent;

B₂O₃ 0 to 3 percent; and

P₂O₅ 0 to 1 percent.

[0153]

In the above desirable form of glass III, the various contents and total contents of MgO, CaO, SrO, BaO, B₂O₃, P₂O₅, and ZnO; the ratio of the ZrO₂ content to the total content of ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂; and the like are identical to those of the desirable form of glass II.

[0154]

Sulfates can be added as clarifying agents to glass III in a range of 0 to 1 percent. However, they present a risk of unmelted material in the glass melt being scattered about by blowing, causing a sharp increase in foreign material in the glass. Thus, no incorporation of sulfates is desirable.

[0155]

By contrast, Sn oxide and Ce oxide do not present the problem of scattering by blowing or increased foreign material, and have good effects in eliminating bubbles.

[0156]

As set forth above, Sn primarily actively releases oxygen gas in high temperature states (a temperature range of about 1,400 to 1,600°C), thereby strongly promoting clarification. Ce strongly incorporates oxygen gas in low temperature states (a temperature range of about 1,200 to 1,400°C), fixing it as a glass component. The viscosity of the glass at 1,400°C, where the temperature range of the clarifying effect of Sn meets the temperature range of the clarifying effect of Ce, greatly affects clarification efficiency.

[0157]

In glass III, to increase chemical durability, the quantity of the Si and Al components is increased and an alkali component is made an essential component. However, since the contents thereof are limited as set forth above, the viscosity of the glass at 1,400°C exhibits an upward trend. When the viscosity of the glass becomes excessively high in the clarification temperature range, the rate at which bubbles rise in the glass decreases, and bubble elimination deteriorates.

[0158]

In glass III, to simultaneously achieve enhanced chemical durability and an improved clarifying effect, the viscosity at 1,400°C is desirably kept to 10^3 dPa·s or lower while employing a total content of SiO_2 and Al_2O_3 of 65 molar percent.

[0159]

From the perspective of enhancing chemical durability, in glass III, the total content of SiO_2 and Al_2O_3 desirably ranges 65 molar percent or more, preferably 70 molar percent or more, more preferably 73 molar percent or more, still more preferably 74 molar percent or more, yet still more preferably 75 molar percent or more, and even more preferably 75.5 molar percent or more.

[0160]

To increase the clarifying effect, in glass III, the viscosity at 1,400°C is desirably kept to $10^{2.7}$ dPa·s or lower.

[0161]

In this manner, the density of residual bubbles contained in the glass per unit mass is kept to 60 bubbles/kg or lower, desirably 40 bubbles/kg or lower, preferably 20 bubbles/kg or lower, more preferably 10 bubbles/kg or lower, still more preferably 2 bubbles/kg or lower, and even more preferably, 0 bubbles/kg. This permits the highly efficient mass production of substrates suited to high recording density magnetic recording media.

[0162]

The method for manufacturing glass III, that is, a third form of the method for manufacturing a glass for a magnetic recording medium substrate of the present invention (referred to as "glass manufacturing method III") will be described next. Glass manufacturing method III is a method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by: mixing a glass starting material to which Sn and Ce, are added, comprising, as converted based on the oxides, denoted as molar percentages:

SiO₂ 60 to 75 percent;

Al₂O₃ 1 to 15 percent;

Li₂O 0.1 to 20 percent;

Na₂O 0.1 to 15 percent; and

K₂O 0 to 5 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower); so as to permit obtaining a glass containing a total quantity of Sn oxide and Ce oxide of 0.1 to 3.5 mass percent based on the total amount of the glass components, wherein the ratio of the content of Sn oxide to the total content Sn oxide and Ce oxide (content of Sn oxide/(content of Sn oxide + content of Ce oxide)) is 0.01 to 0.99, having an Sb oxide content of 0 to 0.1 percent, and comprising no As or F; melting the glass starting material; clarifying the glass melt obtained; and molding the glass melt obtained.

[0163]

A desirable form of glass manufacturing method III is a method of maintaining the glass melt at 1,400 to 1,600°C, decreasing the temperature, maintaining the glass melt at 1,200 to 1,400°C, and then conducting molding.

[0164]

Maintaining the glass melt at 1,400 to 1,600°C lowers the viscosity of the glass, creating a state where bubbles in the glass tend to rise, and produces a clarification-enhancing effect based on the release of oxygen by Sn.

Subsequently decreasing the temperature of the glass melt and maintaining it at 1,200 to 1,400°C markedly enhances bubble elimination by taking advantage of oxygen incorporation by Ce.

[0165]

In glass manufacturing method III, in which Sn and Ce are employed in combination in the glass melt, a glass characteristic in the form of a viscosity of 10^3 dPa·s at 1,400°C and a synergistic effect based on the presence of both Sn and Ce markedly enhance bubble elimination.

[0166]

Denoting the period of maintenance at 1,400 to 1,600°C as TH and the period of maintenance at 1,200 to 1,400°C as TL, it is desirable to keep TL/TH to 0.5 or less, preferably 0.2 or less. Increasing TH relative to TL in this manner facilitates the discharging of gases within the glass to the exterior. To promote the gas incorporating effect of Ce within the glass, TL/TH is desirably greater than 0.01, preferably greater than 0.02, more preferably greater than 0.03, and still more preferably, greater than 0.04.

[0167]

To increase the individual bubble eliminating effects of Sn and Ce, the temperature difference in the course of dropping the temperature from within the range of 1,400 to 1,600°C to within the range of 1,200 to 1,400°C is desirably 30°C or greater, preferably 50°C or greater, more preferably 80°C or greater, still more preferably 100°C or greater, and even more preferably, 150°C or greater. The upper limit of the temperature difference is 400°C.

[0168]

In glass manufacturing method III, the quantities of Sn and Ce added are desirably established to yield a density of residual bubbles within the glass of 60 bubbles/kg or lower. The density of residual bubbles in the glass can be further reduced by utilizing a characteristic of the glass in the form of its viscosity of 10^3 dPa·s or lower at 1,400°C. In glass manufacturing method III, the quantities of Sn and Ce added are desirably established to yield a density of residual bubbles of 40 bubbles/kg or lower. The quantities of Sn and Ce added are preferably established to yield a density of residual bubbles of 20 bubbles/kg or lower. The quantities of Sn and Ce added are more preferably established to yield a density

of residual bubbles of 10 bubbles/kg or lower. The quantities of Sn and Ce added are still more preferably established to yield a density of residual bubbles of 2 bubbles/kg or lower. The quantities of Sn and Ce added are particularly preferably established to yield a density of residual bubbles of 0 bubbles/kg. Even when residual bubbles are present, the size of all of the bubbles can be kept to 0.3 mm or less.

[0169]

In glass manufacturing method III, that is, the method for manufacturing glass III, as well, the melting vat, in which the glass starting materials are heated and vitrified, and the clarifying vat are comprised of a refractory material such as electrocasting bricks, sintered bricks, or the like. The operating vat and the connecting pipe linking the clarifying vat and the operating vat, and the outflow pipe, are desirably comprised of platinum or a platinum alloy (referred to as a "platinum-based material"). The molten material within the melting vat where the starting material is vitrified, and the glass melt within the clarifying vat reaching the maximum temperature in the glass manufacturing process, both exhibit highly corrosive properties. Although platinum-based materials exhibit good resistance to corrosion, they corrode when they come into contact with highly corrosive glass, mixing into the glass as a solid platinum material. Since the solid platinum material exhibits resistance to corrosion, platinum that has mixed into the glass as a solid material does not completely melt into the glass, but remains as foreign matter in the molded glass. However, the refractory material that corrodes will mix into the glass, melting into the glass and tending not to remain as foreign matter. Accordingly, the melting vat and clarifying vat are desirably manufactured of a refractory material. When the operating vat is made of a refractory material, the surface of the refractory material melts into the glass melt, generating striae in the glass which was homogenized, rendering it heterogeneous. The temperature of the operating vat reaches 1,400°C or lower, and the corrosiveness of the glass decreases. Thus, the operating vat, connecting pipe, and outflow pipe are desirably comprised of platinum-based material that tends not to melt into the glass. The stirring apparatus that stirs and homogenizes the glass melt in the operating vat is also desirably comprised of a platinum-based material.

[0170]

Halogens other than F, such as Cl, Br, and I, are desirably not added to glass III. These halogens also volatilize from the glass melt, producing striae, which are undesirable in the formation of a flat substrate surface.

[0171]

Since Pb, Cd, and the like negatively affect the environment, their incorporation is also desirably avoided in glass III.

[0172]

In glass III, the incorporation of Sn in the form of SnO_2 is desirable for effectively releasing oxygen gas at high temperature.

[0173]

From the perspectives of enhancing bubble elimination and inhibiting contamination by foreign matter, glass III for use in a magnetic recording medium substrate of the present invention is suited to production of quantities of glass melt of 10 liters or more, that is, production in which 10 liters or more of a glass melt is held in a heat resistant container. It is also suited to production of quantities of glass melt of 40 liters or more.

[0174]

[Acid resistance and alkali resistance]

Glasses I, II, and III desirably have an acid resistant property in the form of an etching rate of 3.0 nm/minute or less when immersed in a 0.5 volume percent hydrogenfluosilicic acid (H_2SiF) aqueous solution maintained at 50°C, and an alkali resistant property in the form of an etching rate of 0.1 nm/minute or less when immersed in a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C. Preferably, they possess both this acid resistant property and alkali resistant property.

[0175]

In manufacturing a magnetic recording medium substrate, organic material contaminating the surface of the glass is removed by an acid treatment, after which the adhesion of foreign matter is prevented by an alkali treatment to achieve an extremely clean substrate. A substrate comprised of a glass having the above-described acid resistance and alkali resistance can be maintained in a state of extremely high surface flatness despite the acid treatment and alkali treatment.

[0176]

The acid resistance of glasses I, II, and III is desirably an etching rate when immersed in a 0.5 volume percent hydrogenfluosilicic acid (H_2SiF) aqueous

solution maintained at 50°C of 2.5 nm/minute or less, preferably 2.0 nm/minute or less, and more preferably, 1.8 nm/minute or less. The alkali resistance is desirably an etching rate when immersed in a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C of 0.09 nm/minute or less, preferably 0.08 nm/minute or less.

[0177]

In the present invention, the etching rate is defined as the depth of the glass surface that is removed per unit time. For example, in the case of a glass substrate, it is the depth of the glass substrate removed per unit time. The method of measuring the etching rate is not specifically limited. The following method is an example. First, the glass is processed into a substrate shape (flat shape). To prepare a non-etched portion, part of the glass substrate is subjected to mask processing. The glass substrate in that state is then immersed in the above hydrogenfluosilicic acid aqueous solution or potassium hydroxide aqueous solution. After being immersed for a unit time, the glass substrate is pulled out of the aqueous solution and the amount of the difference (etching difference) between the masked portion and the portion without a mask is determined. In this manner, the amount of etching (etching rate) per unit time is obtained.

[0178]

Methods of manufacturing glasses I, II, and III will be described next. First, glass starting materials such as oxides, carbonates, nitrates, sulfates, and hydroxides, as well as clarifying agents such as SnO_2 and CeO_2 are weighed out and mixed to obtain a mixed starting material that will yield the desired composition. This starting material is heated in a refractory furnace and melted, clarified, and homogenized at a temperature of 1,400 to 1,600°C, for example. A homogenous glass melt free of bubbles and unmelted material is prepared in this manner, caused to flow out, and molded into a prescribed shape to obtain the above-described glass.

[0179]

[Chemically strengthened glass]

The glass for a magnetic recording medium substrate of the present invention is also suitable as a chemically strengthened glass. Glasses I, II, and III are chemically strengthened, for example, by immersing a piece of glass that has been processed into a disk shape in a molten alkali salt. Sodium nitrate molten salt, potassium nitrate molten salt, or a mixed molten salt of the two can be employed as the molten salt. The term "chemical strengthening treatment"

refers to bringing a glass substrate into contact with a chemical strengthening treatment solution (molten salt) to replace some of the ions in the glass substrate with larger ions that are contained in the chemical strengthening treatment solution to chemically strengthen the glass substrate. When the glass is immersed in molten salt, Li ions in the vicinity of the surface are replaced with Na ions and K ions in the molten salt, and Na ions in the vicinity of the glass surface are replaced with K ions in the molten salt, forming a compressive stress layer in the substrate surface. The temperature of the molten salt during chemical strengthening is higher than the strain point of the glass but lower than the glass transition temperature, and is desirably within a temperature range at which the molten salt does not thermally decompose. Since the molten salt is recycled, as the concentrations of the various alkali ions in the molten salt change, trace quantities of glass components other than Li and Na leach out. As a result, the processing conditions move outside the above-stated optimal ranges. This variation in chemical strengthening due to such changes over time in the molten salt can be reduced by adjusting the composition of the glass constituting the substrate as set forth above. It can also be reduced by setting the concentration of K ions in the molten salt high. The fact that chemical strengthening processing has been conducted can be confirmed by observation of a cross-section of the glass (a cut surface of the processed layer) by the Babinet method, by measuring the distribution in the depth direction of alkali ions (such as Li^+ , Na^+ , and K^+) from the glass surface; and the like.

[0180]

[The magnetic recording medium substrate]

The magnetic recording medium substrate of the present invention is comprised of above-described glass I, II, or III. In a glass substrate comprised of glass I, II, or III, the number of residual bubbles, from just one part in several tens to several percent that of conventional glasses, is extremely small. This permits a substrate with excellent surface flatness.

[0181]

When residual bubbles are present in a substrate, even without appearing on the substrate surface, they diminish the mechanical strength of the substrate. Since glass in which residual bubbles are absent, or are present in an extremely small number, is employed in the present invention, a substrate having good mechanical strength and good impact resistance is provided.

[0182]

Since the substrate is comprised of glass I, II, or III, all of which have good chemical durability, high surface flatness is maintained even after conducting cleaning to remove foreign matter.

[0183]

Since glass I, II, or III is employed, all of which have good chemical durability and exhibit little leaching out of alkali metal components, a substrate exhibiting little leaching out of alkalis due to chemical strengthening and good impact resistance is obtained based on the present invention.

[0184]

The bending strength is generally employed as an indicator of the impact resistance of the magnetic recording medium substrate. The present invention provides a glass substrate having a bending strength of, for example, 10 kg or greater, desirably 15 kg or greater, and preferably, 20 kg or greater. The bending strength is obtained as the value of the load at the point where the substrate is damaged when a steel ball is placed in a hole in the center of a substrate positioned on a holder as shown in Fig. 2, and the load is progressively increased by means of a load cell. Measurement can be conducted with a bending strength measuring and testing device (Shimadzu Autograph DDS-2000), for example.

[0185]

Magnetic recording media, known as magnetic disks, hard disks, and the like, are suited to the internal memory devices (fixed disks and the like) of desktop computers, server-use computers, notebook computers, mobile computers, and the like; the internal memory devices of portable recording and reproducing devices that record and reproduce images and/or sound; vehicle-mounted audio recording and reproducing devices; and the like.

[0186]

By way of example, the substrate of the present invention measures 1.5 mm or less, desirably 1.2 mm or less, and preferably 1 mm or less in thickness. The lower limit is desirably 0.3 mm. Such thin substrates tend to develop undulation due to chemical strengthening. However, the glass of the present invention is adjusted by balancing the various components to within a range in which undulation due to chemical strengthening tends not to develop. Thus, a thin substrate of good flatness is obtained even after chemical strengthening treatment. The substrate of the present invention may be disklike (disk-shaped), with a hole in the center portion (centerhole). The glass of the present invention reduces the variation in shape caused by the chemical strengthening treatment of

the substrate, permitting the mass production of disk-shaped substrates with a low centerhole inner diameter size tolerance.

[0187]

The present invention further relates to a method for manufacturing a glass substrate for use in an information-recording medium, comprising a step of mirror-surface polishing the glass substrate for a magnetic recording medium of the present invention, and a cleaning step, in which the glass is cleaned with an acid and cleaned with an alkali following mirror-surface polishing. This manufacturing method is a suitable method for manufacturing the substrate of the present invention. The specific form of this method will be described below.

[0188]

First, a glass melt is cast into a heat-resistant metal mold and molded into a cylindrical piece of glass. This is annealed, the lateral surfaces thereof are ground by centerless processing or the like, and the rod is sliced to prescribed thickness to produce thin, disk-shaped substrate blanks.

[0189]

Alternatively, an outflowing glass melt is severed to obtain a desired glass melt gob, which is then press molded in a pressing mold to manufacture a thin disk-shaped substrate blank. Those of Glasses I and II, to which Ce has been added, and glass III, afford the advantage of readily and thinly extending with uniform thickness when press molded. Accordingly, a thin substrate blank of low sheet thickness tolerance can be stably manufactured by press molding such glasses.

[0190]

A substrate blank can also be manufactured by molding a sheet by causing a glass melt to flow out into a float bath, annealing the glass, and cutting out disk-shaped substrate blanks. Instead of a float bath, the glass melt can be made to flow out onto a flat support, and a gas cushion can be formed between the support and the glass to mold the glass into a sheet. These methods are referred to as "float methods".

[0191]

Further, instead of the above press molding and float methods, a glass blank can be manufactured by causing a glass melt to overflow from two sides of a flume-shaped mold, fusing together the glass moving along the two sides beneath the mold, pulling the glass downward to mold it into sheet glass, annealing the glass, and cutting disk-shaped substrate blanks from the sheet

glass obtained. This sheet glass molding method is referred to as the "overflow down draw method" or "fusion method."

[0192]

A substrate blank produced as set forth above is drilled to provide a centerhole, the inner and outer circumferences thereof are processed, and lapping and polishing are conducted to finish a disk-shaped substrate. Subsequently, the substrate is cleaned with cleaning agents such as acids and alkalis, rinsed, dried, and subjected to the above-described chemical strengthening, as needed. A chemical strengthening treatment can also be conducted following the mirror-surface polishing step and before the cleaning step.

[0193]

The substrate is exposed to acids, alkalis, and water in this series of steps. However, the glass for an information-recording medium substrate of the present invention has good acid resistance, alkali resistance, and water resistance. Thus, the surface of the substrate does not roughen, and a substrate with a flat, smooth surface is obtained. How a substrate with increased smoothness without adhering matter is obtained will be described in detail below.

[0194]

As set forth above, a glass substrate for a magnetic recording medium (magnetic disk-use glass substrate) is subjected to lapping and polishing to form the surface shape of a substrate surface (main surface), which is a surface on which information is recorded. However, during polishing, for example, polishing abrasive and adhering matter are present on the main surface immediately following finishing (mirror-surface polishing). To remove these, it is necessary to clean the main surface after mirror-surface polishing. Further, for example, when conducting a chemical strengthening treatment following mirror-surface polishing, the chemical strengthening treatment ends up changing the surface shape of the main surface, or the strengthening salt adheres to the main surface, so cleaning must be conducted. Examples of this cleaning are washing with an acid and/or washing with an alkali. Both are often conducted. When the glass substrate for an information-recording medium has poor acid resistance and poor alkali resistance, the washing ends up roughening the substrate surface. When the cleaning agent is weakened to prevent roughening of the substrate surface by washing, the polishing abrasive, adhering material, strengthening salt or the like adhering to the substrate surface cannot be adequately removed. Accordingly, to

reduce adhering material containing polishing abrasive and to enhance the smoothness of the substrate surface, it is necessary for a glass substrate for an information-recording medium to possess adequate acid and alkali resistance.

[0195]

Recording densities have continued to climb in recent years. For example, high-density information-recording media with recording densities of 130 Gbit/inch² or higher, preferably 200 Gbit/inch², are in demand. Such high recording densities can be effectively achieved by reducing the amount of float of the recording and reproducing head relative to the information-recording medium. To this end, it is desirable to employ a highly smooth substrate in information-recording media. For example, to manufacture an information-recording medium with a recording density of 130 Gbit/inch², the surface roughness (Ra) of the main surface of the glass substrate of the information-recording medium is desirably 0.25 nm or lower, preferably 0.2 nm or lower, and more preferably, 0.15 nm or lower. Achieving this surface roughness makes it possible to achieve a high recording density because the amount of float of the recording and reproducing head relative to the information-recording medium is reduced. In the present invention, the term "main surface" means a surface on which an information recording layer is provided. Since these surfaces are the surfaces of greatest area of the information-recording medium, they are called "main surfaces." In a disk-shaped information-recording medium, they correspond to the round exterior surfaces of the disk (excluding the centerhole, when present).

[0196]

The polishing abrasive employed in the above mirror-surface polishing is not specifically limited other than that it be capable of imparting a roughness Ra of 0.25 nm or lower to the main surface of the glass substrate of an information-recording medium. However, silicon dioxide is preferred. It is also desirable to employ colloidal silica, in which the silicon dioxide is in the form of a colloid, to conduct acid polishing or alkali polishing to impart a surface shape to the glass substrate.

[0197]

In the above cleaning, acid cleaning is suitable from the perspective of removing organic matter adhering to the main substrate surface. Additionally, alkali cleaning is suitable from the perspective of removing inorganic matter (such as iron) adhering to the substrate surface. That is, acid cleaning and alkali cleaning are employed to remove different materials. In terms of manufacturing a

glass substrate for an information-recording medium, both are desirably employed in combination, preferably with an acid cleaning step and an alkali cleaning step being conducted successively. From the perspective of controlling the charge on the glass substrate after cleaning, it is desirable to conduct cleaning with an alkali after cleaning with an acid.

[0198]

Since the above glass substrate is highly resistant to acids and to alkalis, it permits the manufacturing of a glass substrate having a smooth surface with less adhered material.

[0199]

[The magnetic recording medium]

The present invention includes a magnetic recording medium having an information recording layer on the above magnetic recording medium substrate.

The present invention further relates to a method for manufacturing a magnetic recording medium, comprising manufacturing a glass substrate for a magnetic recording medium by the method for manufacturing a magnetic recording medium substrate of the present invention, and forming an information recording layer on the glass substrate.

[0200]

The glasses of the present invention as set forth above permit the manufacturing of substrates of high surface flatness, and of good shape stability following chemical strengthening treatment. Magnetic recording media comprising the above-described substrates are suited to high-density recording. Further, since a substrate of high heating efficiency can be obtained, it is possible to manufacture magnetic recording media with good production efficiency.

[0201]

As set forth above, the magnetic recording medium of the present invention is capable of catching up with high-density recording, and is particularly suitable to use as a magnetic recording medium in vertical magnetic recording methods. A magnetic recording medium suited to vertical magnetic recording methods makes it possible to provide a magnetic recording medium capable of catching up with even higher recording densities. That is, a magnetic recording medium suited to vertical magnetic recording methods can achieve even higher magnetic recording densities because it has a recording density (such as 1 Tbit/(2.5 cm)²) that is higher than the surface recording density (100 Gbit/(2.5

cm)² or higher) of magnetic recording media suited to conventional longitudinal magnetic recording methods.

[0202]

The magnetic recording medium of the present invention comprises an information recording layer on the above-described glass substrate. For example, it is possible to manufacture an information-recording medium such as a magnetic disk by successively providing an underlayer, magnetic layer, protective layer, and lubricating layer and the like on the above-described glass substrate.

[0203]

The information recording layer is not specifically limited other than that it be suitably selected for the type of medium. For example, it can be a Co-Cr-based (here, the term "based" means a material containing the denoted substance), Co-Cr-Pt-based, Co-Ni-Cr-based, Co-Ni-Pt-based, Co-Ni-Cr-Pt-based, or Co-Cr-Ta-based magnetic layer. An Ni layer, Ni-P layer, Cr layer, or the like can be employed as the underlayer. Specific examples of the material employed in the magnetic layer suited to high-density recording (information recording layer) are CoCrPt-based alloy materials, particularly CoCrPtB-based alloy materials. FePt-based alloy materials are also suitable. These magnetic layers are highly useful as magnetic materials, particularly in vertical magnetic recording systems. Films of CoCrPt-based alloy materials can be formed, or heat treated following film formation, at 300 to 500°C, and films of FePt-based alloy materials can be formed, or heat treated following film formation, at an elevated temperature of 500 to 600°C, to adjust the crystal orientation or crystalline structure and achieve a structure suited to high-density recording.

[0204]

A nonmagnetic and/or soft magnetic underlayer can be employed as the underlayer. A nonmagnetic underlayer is principally provided to reduce the size of the crystal grains of the magnetic layer, or to control the crystal orientation of the magnetic layer. A bcc-based crystalline underlayer, such as a Cr-based underlayer, has the effect of promoting an in-plane orientation, and is thus desirable in magnetic disks employed in in-plane (longitudinal) recording methods. An hcp-based crystalline underlayer, such as a Ti-based underlayer or Ru-based underlayer, has the effect of promoting a vertical orientation, and can thus be used in magnetic disks suited to vertical magnetic recording methods. An amorphous underlayer has the effect of reducing the size of the crystal grains in the magnetic layer.

[0205]

Soft magnetic underlayers are primarily employed in vertical magnetic recording disks. They have the effect of promoting magnetized pattern recording by magnetic heads on vertical magnetic recording layers (magnetic layers). To fully utilize the effects of a soft magnetic underlayer, a layer with a high saturation magnetic flux density and high magnetic transmittance is desirable. Desirable examples of such soft magnetic layer materials are Fe-based soft magnetic materials such as FeTa-based soft magnetic materials and FeTaC-based soft magnetic materials. CoZr-based soft magnetic materials and CoTaZr-based soft magnetic materials are also desirable.

[0206]

A carbon film or the like can be employed as the protective layer. A lubricant such as a perfluoropolyether-based lubricant can be employed to form the lubricating layer.

[0207]

One desirable form of a vertical magnetic recording disk is a magnetic disk comprised of the substrate of the present invention, upon which are successively formed films in the form of a soft magnetic underlayer, an amorphous nonmagnetic underlayer, a crystalline nonmagnetic underlayer, a vertical magnetic recording layer (magnetic layer), a protective layer, and a lubricating layer.

[0208]

In the case of a magnetic recording medium suited to vertical magnetic recording methods, desirable examples of the structure of the films formed on the substrate are, on a nonmagnetic material in the form of a glass substrate: a single-layer film formed of a vertical magnetic recording layer, a two-layer film comprising a successively layered soft magnetic layer and magnetic recording layer, and a three-layer film comprising a successively layered hard magnetic layer, soft magnetic layer, and magnetic recording layer. Of these, the two-layer film and three-layer film are desirable because they are better suited to high recording densities and stably maintaining the magnetic moment.

[0209]

The glass substrate for a magnetic recording medium of the present invention permits the suitable manufacturing of a magnetic disk for recording and reproduction at a surface information recording density of 200 Gbit/inch² or greater.

[0210]

An example of a magnetic disk corresponding to a surface information recording density of 200 Gbit/inch² or greater is a magnetic disk corresponding to a vertical magnetic recording method.

[0211]

When recording and reproducing information with a hard disk drive at a surface information recording density of 200 Gbit/inch² or greater, the flying height above the magnetic disk of the magnetic head that travels by floating opposite the main surface of the magnetic disk and records and reproduces signals is 8 nm or less. The main surfaces of a magnetic disk equipped to handle this are normally in a mirror-surface state. The main surfaces of the magnetic disk are normally required to have a surface roughness Ra of 0.25 nm or lower. Based on the glass substrate for a magnetic recording medium of the present invention, it is possible to suitably manufacture a magnetic disk corresponding to a magnetic head with a flying height of 8 nm or less.

[0212]

When recording and reproducing information at a surface information recording density of 200 Gbit/inch² or higher, a dynamically controlled flying height element called a "dynamic flying height" head ("DFH head" hereinafter) is sometimes employed as the recording and reproducing element on which the magnetic head is mounted.

[0213]

With a DFH head, the area around the element is heated to cause the magnetic head element to thermally expand, narrowing the gap between the magnetic head and the magnetic disk. Thus, the main surface of the magnetic disk must necessarily be a mirror surface with a surface roughness of 0.25 nm or less. Based on the glass substrate of an information-recording medium of the present invention, it is possible to suitably manufacture a magnetic disk for a DFH head.

[0214]

The glass substrate for a magnetic recording medium of the present invention is amorphous glass, and permits the generation of a mirror surface of suitable surface roughness.

[0215]

An implementing mode of a magnetic disk that is an information-recording medium employing the glass substrate for a magnetic recording medium of the present invention will be described below with reference to the drawings.

[0216]

Fig. 1 shows an example of the configuration of a magnetic disk 10 relating to an implementing mode of the present invention. In the present implementing mode of the present invention, magnetic disk 10 comprises a glass substrate 12, an adhesive layer 14, a soft magnetic layer 16, an underlayer 18, a size reduction enhancing layer 20, a magnetic recording layer 22, a protective layer 24, and a lubricating layer 26 in this order. Magnetic recording layer 22 functions as an information recording layer for recording and reproducing information.

[0217]

In magnetic disk 10, an amorphous seed layer may further be provided between soft magnetic layer 16 and underlayer 18. The term "seed layer" refers to a layer for enhancing the crystal orientation of underlayer 18. For example, when underlayer 18 is Ru, the seed layer is a layer for enhancing the C-axis orientation of the hcp crystalline structure.

[0218]

Glass substrate 12 is a glass substrate on which are formed the various layers of magnetic disk 10. The above-described glass substrate for a magnetic recording medium of the present invention can be employed as this glass substrate.

[0219]

The main surface of the glass substrate is desirably a mirror surface with a surface roughness Ra of 0.25 nm or less. A mirror surface with a surface roughness Rmax of 3 nm or less is desirable.

[0220]

Employing such a flat mirror surface makes it possible to achieve a constant separation distance between magnetic recording layer 22, which is a vertical magnetic recording layer, and soft magnetic layer 16. Thus, it is possible to form a suitable magnetic circuit between the head, magnetic recording layer 22, and soft magnetic layer 16.

[0221]

Adhesive layer 14 is a layer for enhancing adhesion between glass substrate 12 and soft magnetic layer 16. It is formed between glass substrate 12

and soft magnetic layer 16. Using adhesive layer 14 prevents separation of soft magnetic layer 16. By way of example, a Ti-containing material can be employed as the material of adhesive layer 14. In practical terms, the thickness of adhesive layer 14 is desirably 1 to 50 nm. The material of adhesive layer 14 is desirably an amorphous material.

[0222]

Soft magnetic layer 16 is a layer for adjusting the magnetic circuit of magnetic recording layer 22. Soft magnetic layer 16 is not specifically limited other than that it be formed of a magnetic material exhibiting soft magnetic characteristics. For example, it desirably exhibits a magnetic characteristic in the form of a coercivity (H_c) of 0.01 to 80 Oersteds, desirably 0.01 to 50 Oersteds. Further, it desirably exhibits a magnetic characteristic in the form of a saturation magnetic flux density (B_s) of 500 to 1,920 emu/cc. Examples of the material of soft magnetic layer 16 are Fe-based and Co-based materials. For examples, materials such as Fe-based soft magnetic materials such as FeTaC-based alloys, FeTaN-based alloys, FeNi-based alloys, FeCoB-based alloys, and FeCo-based alloys; Co-based soft magnetic materials such as CoTaZr-based alloys and CoNbZr-based alloys; and FeCo-based alloy soft magnetic materials can be employed. The material of soft magnetic layer 16 is suitably an amorphous material.

[0223]

The thickness of soft magnetic layer 16 is, for example, 30 to 1,000 nm, preferably 50 to 200 nm. At less than 30 nm, it is sometimes difficult to form a suitable magnetic circuit between the head, magnetic recording layer 22, and soft magnetic layer 16. At greater than 1,000 nm, the surface roughness sometimes increases. Further, at greater than 1,000 nm, film formation by sputtering is sometimes difficult.

[0224]

Underlayer 18 is a layer for controlling the crystal orientation of size reduction enhancing layer 20 and magnetic recording layer 22, and contains ruthenium (Ru), for example. In the present implementing mode of the invention, underlayer 18 is formed of multiple layers. In underlayer 18, a layer containing an interface with size reduction enhancing layer 20 is formed of Ru crystal grains.

[0225]

Size reduction enhancing layer 20 is a nonmagnetic layer having a granular structure. In the present implementing mode of the invention, size

reduction promoting layer 20 is comprised of a nonmagnetic CoCrSiO material having a granular structure.

Size reduction enhancing layer 20 has a granular structure comprised of an oxide grain boundary portion containing SiO and a metal particle portion containing CoCr separate from the grain boundary portion.

[0226]

Magnetic recording layer 22 comprises a ferromagnetic layer 32, a magnetic coupling control layer 34, and an energy exchange control layer 36 in this order on size reduction enhancing layer 20. Ferromagnetic layer 32 is a CoCrPtSiO layer with a granular structure, comprising magnetic crystal grains in the form of CoCrPt crystal grains.

Ferromagnetic layer 32 has a granular structure comprised of an oxide grain boundary portion containing SiO and a metal particle portion containing CoCrPt separate from the grain boundary portion.

[0227]

Magnetic coupling control layer 34 is a coupling control layer for controlling magnetic coupling between ferromagnetic layer 32 and energy exchange control layer 36. Magnetic coupling control layer 34 is comprised of, for example, a palladium (Pd) layer or a platinum (Pt) layer. The thickness of magnetic coupling control layer 34 is, for example, 2 nm or less, preferably 0.5 to 1.5 nm.

[0228]

Energy exchange control layer 36 is a magnetic layer (continuous layer) the easily magnetized axis of which is aligned in almost the same direction as ferromagnetic layer 32. By means of exchange coupling with ferromagnetic layer 32, energy exchange control layer 36 improves the magnetic recording characteristic of magnetic disk 10. Energy exchange control layer 36, for example, is comprised of multiple films in the form of alternating laminated films of cobalt (Co) or an alloy thereof and palladium (Pd) ([CoX/Pd]*n*), or alternating laminated films of cobalt (Co) or an alloy thereof and platinum (Pt) ([CoX/Pt]*n*). It is suitably 1 to 8 nm, preferably 3 to 6 nm in thickness.

[0229]

Protective layer 24 is a protective layer for protecting magnetic recording layer 22 from impact with the magnetic head. Lubricating layer 26 is a layer for increasing lubrication between the magnetic head and magnetic disk 10.

[0230]

A desirable method of manufacturing the various layers of magnetic disk 10 excluding lubricating layer 26 and protective layer 24 is film formation by sputtering. Formation by DC magnetron sputtering produces uniform films and is particularly desirable.

[0231]

As a desirable example, protective film 24 can be formed by CVD employing a hydrocarbon as the material gas. Lubricating film 26 can be formed by dipping.

[0232]

In the present mode, it is suitable to form an amorphous layer (such as adhesive layer 14) in contact with a mirror-surface amorphous glass substrate. Soft magnetic layer 16 is suitably employed as the amorphous material. Based on the present invention, it is possible to obtain a mirror-surface magnetic disk surface having a Ra of 0.25 nm or less, for example, reflecting the surface roughness of a glass substrate with a Ra of 0.25 nm or less.

[0233]

The dimensions of the magnetic recording medium substrate (for example, a magnetic disk substrate) or the magnetic recording medium (for example, a magnetic disk) of the present invention are not specifically limited. However, the medium and the substrate can be reduced in size to permit a high recording density. For example, a magnetic disk substrate or a magnetic disk with a nominal diameter of 2.5 inches, or even smaller (for example, 1 inch) is suitable.

[Embodiments]

[0234]

The present invention is described in greater detail below through embodiments. However, the present invention is not limited to the forms given in the embodiments.

[0235]

Embodiment A

(1) Melting of the glass

Starting materials such as oxides, carbonates, nitrates, and hydroxides, as well as clarifying agents such as SnO_2 and CeO_2 were weighed out and mixed to obtain mixed starting materials so as to obtain glasses with the compositions of No. 1-1 to No. 1-59, No. 2-1 to No. 2-59, No. 3-1 to No. 3-59, No. 4-1 to No. 4-59, No. 5-1 to No. 5-59, No. 6-1 to No. 6-59, No. 7-1 to No. 7-59, and No. 8-1 to No. 8-59 shown in Tables 1 to 8. The starting materials were charged to melting

vessels; heated, melted, clarified, and stirred for 6 hours over a range of 1,400 to 1,600°C to produce homogeneous glass melts containing neither bubbles nor unmelted material. After being maintained for 6 hours at a range of 1,400 to 1,600°C as stated above, the temperature of each glass melt was decreased (lowered), and the glass melt was maintained for 1 hour at a range of 1,200 to 1,400°C to markedly enhance the clarifying effect. In particular, glass melts in which Sn and Ce were both present were confirmed in the manner set forth above to exhibit extremely pronounced clarifying effects. In the glass compositions shown in Tables 1 to 8, the compositions denoted as molar percentages of oxides (with the exception that clarifying agents such as SnO₂ and CeO₂, denoted as mass percentages based on the total amount of the glass components, are added) serve as bases. Compositions in which the ratios of the atoms comprising the glass are denoted as mass percentages were obtained by conversion from the compositions serving as bases (denoted as molar percentages of oxides).

[0236]

The surface of each glass obtained was polished flat and smooth. The interior of the glass was magnified and observed (40 to 100-fold) from the polished surface with an optical microscope, and the number of residual bubbles was counted. The number of residual bubbles counted was divided by the mass of the glass corresponding to the magnified area observed to obtain the density of residual bubbles.

[0237]

Glasses with 0 to 2 residual bubbles/kg were ranked A. Glasses with 3 to 10 residual bubbles/kg were ranked B. Glasses with 11 to 20 residual bubbles/kg were ranked C. Glasses with 21 to 40 residual bubbles/kg were ranked D. Glasses with 41 to 60 residual bubbles/kg were ranked E. Glasses with 61 to 100 residual bubbles/kg were ranked F. Glasses with 101 or more residual bubbles/kg were ranked G. The corresponding rankings of the various glasses are given in Tables 1 to 8.

The size of the residual bubbles in each of the glasses shown in Tables 1 to 8 was 0.3 mm or less.

No crystals or unmelted starting materials were found in the glasses thus obtained.

[0238]

Based on the results given in Tables 1 to 8, the relation between the quantities of Sn and Ce added and the density of residual bubbles was determined. The quantities of Sn and Ce added were adjusted so that the density of residual bubbles was at or below a desired value, and glasses were produced. It is thus possible to suppress the density of residual bubbles to a desired level.

[0239]

Next, glasses were prepared by the same method as the above, with the exceptions that the temperature of glass melts that had been maintained for 15 hours at 1,400 to 1,600°C was lowered, the glass melts were maintained for 1 to 2 hours at 1,200 to 1,400°C, and molding was conducted. The density and size of the residual bubbles were examined, and the presence of crystals and unmelted starting materials was checked. This yielded the same results as above. When the period of maintenance at 1,400 to 1,600°C is denoted as TH and the period of maintenance at 1,200 to 1,400°C is denoted as TL, the ratio of TL/TH for all of the above-described methods is desirably 0.5 or lower, preferably 0.2 or lower. By increasing TH relative to TL, discharge of gas present within the glass to the exterior of the glass is facilitated. However, to enhance the incorporating effect of gas in the glass by Ce, TL/TH is desirably greater than 0.01, preferably greater than 0.02, more preferably greater than 0.03, and still more preferably, greater than 0.04.

[0240]

To enhance the bubble eliminating effects of Sn and Ce, the temperature difference in the course of decreasing the temperature from the 1,400 to 1,600°C range to the 1,200 to 1,400°C range is desirably 30°C or greater, preferably 50°C or greater, more preferably 80°C or greater, still more preferably 100°C or greater, and yet more preferably, 150°C or greater. The upper limit of the temperature difference is 400°C.

[0241]

The viscosity at 1,400°C of each of the glasses of Tables 1 to 8 was measured by the viscosity measuring method employing a coaxial double cylinder rotating viscometer of JIS Standard Z8803.

[0242]

The viscosity at 1,400°C of each of the glasses of No. 1-1 to No. 1-59 was 300 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 2-1 to No. 2-59 was 250 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 3-1 to No.

3-59 was 400 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 4-1 to No. 4-59 was 350 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 5-1 to No. 5-59 was 300 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 6-1 to No. 6-59 was 320 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 7-1 to No. 7-59 was 200 dPa·s. And the viscosity at 1,400°C of each of the glasses of No. 8-1 to No. 8-59 was 320 dPa·s.

[0243]

Further, each of the glasses to which Ce was added was processed into a flat sheet 1 mm in thickness with two optically polished surfaces. Light was directed vertically into the optically polished surfaces. The spectral transmittance was measured, and the wavelength $\lambda(\lambda_{80})$ at which the external transmittance become 80 percent (including the loss due to reflection at the glass surface) and the wavelength $\lambda(\lambda_5)$ at which it became 5 percent were measured. The following are measurement results for some of the glasses.

Glass No. 1-13 (0.1565 mass percent Sn, 0.1622 mass percent Ce, 0.2 mass percent SnO₂, 0.2 mass percent CeO₂) has a λ_{80} of 355 nm and a λ_5 of 327 nm.

Glass No. 1-28 (0.2344 mass percent Sn, 0.1620 mass percent Ce, 0.3 mass percent SnO₂, 0.2 mass percent CeO₂) has a λ_{80} of 355 nm and a λ_5 of 327 nm.

Glass No. 1-46 (0.3895 mass percent Sn, 0.2422 mass percent Ce, 0.5 mass percent SnO₂, 0.2 mass percent CeO₂) has a λ_{80} of 360 nm and a λ_5 of 335 nm.

[0244]

This shows that as the quantity of Ce added was increased, the absorption by the glass in the short wavelength range tended to increase. Along with this tendency, the fluorescent intensity of the glass when irradiated with UV light also increased. The addition of Ce is desirable in order to make it possible to distinguish glass based on the fluorescence emitted when irradiated with UV light and in order to generate adequately strong fluorescence to permit the detection of foreign matter on the glass surface. Accordingly, an examination of the relation between $\lambda(\lambda_{80})$, $\lambda(\lambda_5)$, and the fluorescent intensity suited to these applications revealed that a λ_{80} of 320 nm or greater provided adequate fluorescent intensity. On this basis, the quantity of Ce added is desirably determined to yield a λ_{80} of 320 nm or greater. The quantity of Ce added is preferably determined to yield a λ_{80} of 330 nm or greater. And the quantity of Ce added is more preferably determined to yield a λ_{80} of 350 nm or greater. Similarly, for λ_5 , the quantity of Ce added is desirably determined to yield a λ_5 of 300 nm or greater. The quantity of Ce added is preferably determined to yield a

λ_5 of 310 nm or greater. The quantity of Ce added is more preferably determined to yield a λ_5 of 320 nm or greater. And the quantity of Ce added is still more preferably determined to yield a λ_5 of 330 nm or greater.

[0245]

From the perspective of ready distinction and detection based on fluorescence, the quantity of CeO_2 added is desirably 0.1 mass percent or greater, preferably 0.2 mass percent or greater, and more preferably, 0.3 mass percent or greater. For distinction and detection by fluorescence, when λ_{80} or the quantity of CeO_2 added is outside the above-stated range, it is impossible to achieve an adequate fluorescent intensity. This renders distinction and detection difficult.

[0246]

The Young's modulus of each of the glasses of Nos. 1-1 to 1-59 is 81 GPa or higher; that of Nos. 5-1 to 5-59 is 84 GPa or higher; and that of Nos. 7-1 to 7-59 is 84 GPa or higher. In each of the above glasses, when neither Sn nor Ce was added, or when Sb was added without adding Sn and Ce, it is possible to obtain a glass with a higher Young's modulus than when Sn and Ce are added. For each of the glasses of Nos. 2-1 to 2-59, Nos. 3-1 to 3-59, Nos. 4-1 to 4-59, Nos. 6-1 to 6-59, and Nos. 8-1 to 8-59, as well, it is possible to increase the Young's modulus by adding Sn and Ce. Increasing the Young's modulus makes it possible to achieve good fluttering resistance during high-speed rotation in magnetic recording media equipped with substrates manufactured from these glasses.

[0247]

(2) Molding of the glass

Disk-shaped substrate blanks were fabricated from the above glasses by methods A to C below. Substrate blanks were fabricated by the three methods of A to C from the glasses of Nos. 1-1 to 1-59. For the other glasses, substrate blanks were fabricated by method A. For the glasses of Nos. 1-1 to 1-59, the results of residual bubbles and etching rates given in the tables are the results for the substrate blanks fabricated by method A. The same holds true for the results for the substrate blanks fabricated by methods B and C.

[0248]

(Method A)

The above-described glass melt that had been clarified and homogenized was made to flow at a constant rate out of a pipe and received in a lower mold for

press molding. The glass melt flowing out was cut with a cutting blade to obtain a glass melt gob of prescribed weight in the lower mold. The lower mold carrying the glass melt gob was immediately conveyed downward from the pipe. An upper mold facing the lower mold and a sleeve mold were employed to press mold the glass melt gob into a thin, disk shape 66 mm in diameter and 1.2 mm in thickness. The press-molded article was cooled to a temperature at which it did not deform, removed from the mold, and annealed to obtain a substrate blank. In the above molding, multiple lower molds were employed to successively mold the glass melt flowing out into disk-shaped substrate blanks. Since the glass contained prescribed quantities of Sn and Ce, particularly Ce, the glass extended more readily to a uniform thickness during press molding than glass that did not contain these additives. When glass blanks 1.2 mm or less in thickness were produced in quantity, it was possible to reduce the tolerance of the thickness of the glass blanks, permitting improved production efficiency in the glass blank processing step, described further below.

[0249]

(Method B)

The above-described glass melt that had been clarified and homogenized was continuously cast from above into the through-holes of a heat-resistant casting mold equipped with cylindrical through-holes, molded into a cylindrical shape, and removed from beneath the through-holes. The glass that was removed was annealed. A multiwire saw was then employed to slice the glass at regular intervals in a direction perpendicular to the cylindrical axis thereof to fabricate disk-shaped substrate blanks.

[0250]

(Method C)

The above-described glass melt was caused to flow out onto a float bath and molded into sheets (molded by the float method). After annealing, disk-shaped pieces of glass were cut from the sheet glass, yielding substrate blanks.

[0251]

(Method D)

The above-described glass melt was molded into glass sheets by the overflow down draw method (fusion method) and annealed. Disk-shaped pieces of glass were then cut from the sheet glass, yielding substrate blanks.

[0252]

(3) Substrate fabrication

A grindstone was used to form throughholes in the center of substrate blanks obtained by each of the above-described methods. Outer circumference grinding processing was conducted. The edge surfaces (inner circumference, outer circumference) were polished with brushes while rotating the disk-shaped pieces of glass to achieve a maximum surface roughness (R_{max}) of about 1.0 micrometer and an arithmetic average roughness (R_a) of about 0.3 micrometer. Next, abrasive particles with #1000-grit were employed to grind the glass substrate surfaces to a degree of flatness of 3 micrometers, an R_{max} of about 2 micrometers, and an R_a of about 0.2 micrometer on the main surface. Here, the term "degree of flatness" refers to the distance (difference in height) in a vertical direction (direction vertical to the surface) between the highest portion and the lowest portion of the substrate surface. This was measured with a flatness measuring device. R_{max} and R_a were measured for a 5 x 5 micrometer rectangular area with an atomic force microscope (AFM) (a Nanoscope made by Digital Instruments). Next, a preliminary polishing step was conducted with a polishing device capable of polishing both main surfaces of 100 to 200 glass substrates at once. A hard polisher was employed as the polishing pad. A polishing pad that had been preloaded with zirconium oxide and cerium oxide was employed as the polishing pad.

[0253]

The polishing solution in the preliminary polishing step was prepared by mixing cerium oxide abrasive grains with an average particle diameter of 1.1 micrometers in water. Polishing grains with a grain diameter exceeding 4 micrometers were eliminated in advance. Measurement of the polishing solution revealed that the largest polishing grains contained in the polishing solution were 3.5 micrometers, the average value was 1.1 micrometers, and the D50 value was 1.1 micrometers.

[0254]

Additionally, the load applied to the glass substrates was 80 to 100 g/cm². The thickness removed from the surface portion of the glass substrates was set to 20 to 40 micrometers.

[0255]

Next, a mirror-surface polishing step was conducted with a planetary gear-type polishing device capable of polishing both main surfaces of 100 to 200 glass substrates at once. A soft polisher was employed as the polishing pad.

[0256]

The polishing solution in the mirror-surface polishing step was prepared by adding sulfuric acid and tartaric acid to ultrapure water, and then further adding colloidal silica particles with a grain diameter of 40 nm. In this process, the sulfuric acid concentration in the polishing solution was adjusted to 0.15 mass percent, and the pH of the polishing solution to 2.0 or lower. The concentration of tartaric acid was adjusted to 0.8 mass percent, and the content of colloidal silica particles to 10 mass percent.

[0257]

In the course of mirror-surface polishing processing, the pH value of the polishing solution did not vary, and could be kept approximately constant. In the present embodiment, the polishing solution that was fed onto the surfaces of the glass substrates was recovered by means of a drain, cleaned by removing foreign material with a meshlike filter, and then reused by being fed back onto the glass substrate.

[0258]

The polishing rate in the mirror-surface polishing step was 0.25 micrometer/minute. This was found to be an advantageous polishing processing rate under the above-stated conditions. The polishing processing rate was calculated by dividing the amount of reduction (processing removed amount) in the thickness of the glass substrate required for finishing into a prescribed mirror surface by the time required for polishing processing.

[0259]

Next, the glass substrates were cleaned with an alkali by being immersed in a 3 to 5 mass percent concentration NaOH aqueous solution. This cleaning was conducted with the application of ultrasound. Cleaning was further conducted by successive immersion in cleaning vats of a neutral cleaning agent, pure water, pure water, isopropyl alcohol, isopropyl alcohol (steam drying). The surfaces of the substrates following cleaning were observed by AFM (Nanoscope, made by Digital Instruments) (a rectangular area 5 x 5 micrometers was measured), revealing that no colloidal silica polishing grains had adhered. Nor was any foreign matter in the form of stainless steel, iron, or the like discovered. Nor was any increase in the roughness of the substrate surfaces observed following cleaning.

[0260]

Portions of the glass substrates that had been fabricated were subjected to a masking treatment to protect the portions from etching. The glass substrates

in this state were immersed in a 0.5 volume percent hydrogenfluosilicic acid aqueous solution maintained at 50°C or a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C for a prescribed period. Subsequently, the glass substrates were withdrawn from the various aqueous solutions. The difference (etching difference) between the masked portions and the portions without masks was measured, and then divided by the immersion time to calculate the amount of etching (etching rate) per unit time. The acid etching rates and alkali etching rates obtained are given in the tables. Etching rates were measured for the glasses of Nos. 1-1 to 1-59, Nos. 2-1 to 2-59, and Nos. 7-1 to 7-59. Each of the glasses of Nos. 1-1 to 1-59 and Nos. 2-1 to 2-59 had an acid etching rate of 3.0 nm/minute or less and an alkali etching rate of 0.1 nm/minute or less. This indicates good acid resistance and alkali resistance. By contrast, although the various glasses of Nos. 7-1 to 7-59 had good alkali resistance, they exhibited poor acid resistance.

[0261]

In the same manner as the various glasses of Nos. 1-1 to 1-59 and Nos. 2-1 to 2-59, the various glasses of Nos. 3-1 to 3-59, Nos. 4-1 to 4-59, and Nos. 6-1 to 6-59 also exhibited acid etching rates of 3.0 nm/minute or less and alkali etching rates of 0.1 nm/minute or less, indicating good acid resistance and alkali resistance.

[0262]

Next, potassium nitrate (60 mass percent) and sodium nitrate (40 mass percent) were mixed and heated to 375°C to prepare a chemical strengthening salt. Glass substrates that had been cleaned and preheated to 300°C were immersed for 3 hours in this salt to conduct a chemical strengthening treatment. This treatment caused lithium ions and sodium ions on the surface of the glass substrates to be replaced with sodium ions and potassium ions; respectively, in the chemical strengthening salt, thereby chemically strengthening the glass substrates. The thickness of the compressive stress layer formed in the surfaces of the glass substrates was about 100 to 200 micrometers. Following chemical strengthening, the glass substrates were rapidly cooled by immersion in a vat of water at 20°C and maintained there for about 10 minutes.

[0263]

Next, the rapidly cooled glass substrates were immersed in sulfuric acid that had been heated to about 40°C, and cleaned while applying ultrasound. Subsequently, the glass substrates were cleaned with a 0.5 percent (volume

percent) hydrogenfluosilicic acid (H_2SiF) aqueous solution followed by a 1 mass percent potassium hydroxide aqueous solution. Through the above process, a magnetic disk glass substrate 12 was manufactured.

[0264]

The magnetic disk glass substrate was then examined. Atomic force microscopic (AFM) measurement (a 5 x 5 micrometer rectangular area was measured) of the surface roughness of the magnetic disk glass substrate revealed a maximum peak height (R_{max}) of 1.5 nm and an arithmetic average roughness (R_{a}) of 0.15 nm. The surface was in a clean mirror-surface state, free of the presence of foreign material hindering magnetic head flying, and free of foreign matter causing thermal asperity impediments. No increase in the roughness of the substrate surface was observed following cleaning. Next, the bending strength was measured. The bending strength was obtained as the value of the load when the glass substrate was damaged when a load was applied to the glass substrate as shown in Fig. 2 using a bending strength measuring and testing device (Shimadzu Autograph DDS-2000). The bending strength obtained, at 24.15 kg, was satisfactory.

[0265]

In the above description, acid cleaning and alkali cleaning were conducted after chemical strengthening, but it is also possible to conduct acid cleaning and alkali cleaning after the mirror-surface polishing step.

[0266]

For the various glasses shown in Tables 1 to 8, the substrates fabricated by adding Ce to the glass were irradiated with UV light. When observed in a darkroom, they were visually observed to emit blue fluorescence. This fluorescence could be used to determine whether or not foreign matter, such as residual abrasive or minute dust particles, had adhered to the substrate surface. The presence of blue fluorescence due to Ce could also be used to determine whether heterogeneous glass substrates in which no Ce had been added had been mixed in with the glass substrates to which Ce had been added.

[0267]

A magnetic disk 10 was fabricated using the glass substrate 12 that had been thus obtained, and tested in a hard disk drive. Fig. 1 shows a typical film configuration (cross-section) on substrate 12.

[0268]

First, a film-forming device in which a vacuum had been drawn was employed to successively form adhesive layer 14 and soft magnetic layer 16 in an argon atmosphere by DC magnetron sputtering.

[0269]

Adhesive layer 14 was formed as a 20 nm amorphous CrTi layer using a CrTi target. Soft magnetic layer 16 was formed as a 200 nm amorphous CoTaZr layer (Co: 88 atomic percent, Ta: 7 atomic percent, Zr: 5 atomic percent) using a CoTaZr target.

[0270]

Magnetic disk 10, on which films up to soft magnetic layer 16 had been formed, was removed from the film-forming device. The surface roughness thereof was measured as set forth above, revealing a smooth mirror surface with an Rmax of 2.1 nm and an Ra of 0.20 nm. Measurement of the magnetic characteristics with a vibrating sample magnetometer (VSM) revealed a coercivity (Hc) of 2 Oersteds and a saturation magnetic flux density of 810 emu/cc. This indicated suitable soft magnetic characteristics.

[0271]

Next, a single-wafer static opposed-type film-forming device was employed to successively form an underlayer 18, granular structure size reduction enhancing layer 20, granular structure ferromagnetic layer 32, magnetic coupling control layer 34, energy exchange control layer 36, and protective film 24 in an argon atmosphere. In the present embodiment, underlayer 18 had a two-layer structure comprised of a first layer and a second layer.

[0272]

In this process, a layer 10 nm in thickness of amorphous NiTa (Ni: 40 atomic percent, Ta: 10 atomic percent) was first formed on the disk substrate as the first layer of underlayer 18, followed by the formation of a Ru layer 10 to 15 nm in thickness as the second layer.

[0273]

Next, a nonmagnetic CoCr-SiO₂ target was employed to form size reduction enhancing layer 20 comprised of a 2 to 20 nm hcp crystalline structure. A CoCrPt-SiO₂ hard magnetic material target was then employed to form ferromagnetic layer 32 comprised of a 15 nm hcp crystalline structure. The composition of the target for fabricating ferromagnetic layer 32 was Co: 62 atomic percent; Cr: 10 atomic percent; Pt: 16 atomic percent, and SiO₂: 12 atomic

percent. A magnetic coupling control layer 34 in the form of a Pd layer was then formed, and an energy exchange control layer 36 in the form of a [CoB/Pd]_n layer was formed.

[0274]

CVD employing ethylene as the material gas was then used to form protective film 24 comprised of carbon hydride. The use of hydrogenated carbon increased film hardness, making it possible to protect magnetic recording layer 22 from impact with the magnetic heads.

[0275]

Subsequently, lubricating layer 26 comprised of perfluoropolyether (PFPE) was formed by dip coating. Lubricating layer 26 was 1 nm in thickness. A vertical magnetic recording medium in the form of magnetic disk 10 suited to vertical magnetic recording methods was obtained by the above manufacturing process. The roughness of the surface obtained was measured in the same manner as above, revealing a smooth mirror surface with an R_{max} of 2.2 nm and an Ra of 0.21 nm.

[0276]

Magnetic disk 10 that was obtained was loaded onto a 2.5-inch loading/unloading hard disk drive. The magnetic head mounted on the hard disk drive was a dynamic flying height (abbreviated as "DFH") magnetic head. The flying height of the magnetic head relative to the magnetic disk was 8 nm.

[0277]

A recording and reproducing test was conducted at a recording density of 200 Gbits/inch² in the recording and reproducing region of the main surface of the magnetic disk using this hard disk drive, revealing good recording and reproducing characteristics. During the test, no crash faults or thermal asperity faults were generated.

[0278]

Next, a load unload ("LUL" hereinafter) test was conducted with the hard disk drive.

[0279]

The LUL test is conducted with 2.5-inch hard disk drive rotating at 5,400 rpm and a magnetic head with a flying height of 8 nm. The above-described magnetic head was employed. The shield element was comprised of NiFe alloy. The magnetic disk was loaded on the magnetic disk device, LUL operations were

repeatedly conducted with the above magnetic head, and the LUL cycle durability was measured.

[0280]

Following the LUL durability test, the surface of the magnetic disk and the surface of the magnetic head are examined visually and by optical microscopy to check for abnormalities such as scratches and grime. In the LUL durability test, a durability of 400,000 or more LUL cycles without failure is required, with a durability of 600,000 cycles or more being particularly desirable. In the use environment in which a hard disk drive (HDD) is normally employed, it is reported to take about 10 years of use to exceed 600,000 LUL cycles.

[0281]

When the LUL test was implemented, magnetic disk 10 met the 600,000 cycle or more standard. Following the LUL test, magnetic disk 10 was removed and inspected, revealing no abnormalities such as scratches or grime. No was any precipitation of alkali metal components observed.

[0282]

(Comparative Example A)

Next, the 40 glasses of Comparative Examples 1-1 to 1-5, Comparative Examples 2-1 to 2-5, Comparative Examples 3-1 to 3-5, Comparative Examples 4-1 to 4-5, Comparative Examples 5-1 to 5-5, Comparative Examples 6-1 to 6-5, Comparative Examples 7-1 to 7-5, and Comparative Examples 8-1 to 8-5 shown in Tables 1 to 8 were fabricated.

[0283]

Only Sb was added as a clarifying agent in the glasses of Comparative Examples 1-1 to 1-8. Sn and an excess quantity of Sb were added as clarifying agents in the glasses of Comparative Examples 1-2 to 8-2. An excess quantity of Sn was added as clarifying agent in the glasses of Comparative Examples 1-3 to 8-3. An excess quantity of Ce was added as clarifying agent in the glasses of Comparative Examples 1-4 to 8-4. And excess quantities of Sn and Ce were added as clarifying agents in the glasses of Comparative Examples (Com.Ex.) 1-5 to 8-5.

[0284]

All of the glasses of the comparative examples had residual bubbles exceeding 100 bubbles/kg. Localized pitting attributed to residual bubbles was observed on the surface of glass substrates fabricated by the same methods as

in the embodiments using these glasses, and the impact resistance of the substrates was inferior to that of the embodiments.

[0285]

[Table 1]

Component		1-1	1-2	1-3	1-4	1-5	1-6	1-7	1-8	1-9	1-10	1-11	1-12	1-13
(mol%)	SiO2	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3
	Al2O3	9.2	9.2	9.2	9.2	9.2	9.2	9.2	9.2	9.2	9.2	9.2	9.2	9.2
	Li2O	8.1	8.1	8.1	8.1	8.1	8.1	8.1	8.1	8.1	8.1	8.1	8.1	8.1
	Na2O	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2
	K2O	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
	MgO	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	CaO	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO2	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	TiO2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La2O3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb2O5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta2O5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Sb2O3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO2	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	CeO2	0	0.001	0.005	0.01	0.05	0.1	0	0.001	0.005	0.01	0.05	0.1	0.2
	Sb2O3	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO2/SnO2	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000	1.0000
	SnO2+CeO2	0.1	0.101	0.105	0.11	0.15	0.2	0.2	0.201	0.205	0.21	0.25	0.3	0.4
(mol%)	Li2O+Na2O+K2O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9
	ZrO2+TiO2+La2O3+Nb2O5+Ta2O5+HfO2	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	SiO2+Al2O3	76.5	76.5	76.5	76.5	76.5	76.5	76.5	76.5	76.5	76.5	76.5	76.5	76.5
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A	A
Acid etching rate (nm./min)		1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Alkaline etching rate (nm./min)		0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07

[illegible]

[illegible]

[illegible]

Component(massa%)	1-1	1-2	1-3	1-4	1-5	1-6	1-7	1-8	1-9	1-10	1-11	1-12	1-13
Si	30.3840	30.3837	30.3825	30.3810	30.3689	30.3537	30.3538	30.3535	30.3523	30.3508	30.3229	30.3078	30.2776
Al	7.9806	7.9805	7.9802	7.9798	7.9766	7.9726	7.9726	7.9725	7.9722	7.9718	7.9763	7.9724	7.9644
Li	1.8075	1.8075	1.8074	1.8073	1.8066	1.8057	1.8057	1.8057	1.8056	1.8056	1.8066	1.8057	1.8039
Na	8.2781	8.2780	8.2777	8.2773	8.2740	8.2698	8.2699	8.2698	8.2695	8.2690	8.2737	8.2696	8.2614
K	0.3771	0.3771	0.3771	0.3771	0.3769	0.3767	0.3767	0.3767	0.3767	0.3767	0.3769	0.3787	0.3783
Mg	0.4298	0.4298	0.4297	0.4297	0.4296	0.4293	0.4293	0.4293	0.4293	0.4293	0.4295	0.4293	0.4289
Ca	1.1597	1.1596	1.1596	1.1595	1.1591	1.1585	1.1585	1.1585	1.1584	1.1584	1.1590	1.1585	1.1573
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4664	1.4664	1.4663	1.4663	1.4657	1.4650	1.4650	1.4649	1.4649	1.4648	1.4656	1.4649	1.4635
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0785	0.0786	0.0785	0.0785	0.0785	0.0784	0.1568	0.1568	0.1568	0.1568	0.1568	0.1567	0.1565
Ce	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1622
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.0383	48.0380	48.0369	48.0354	48.0235	48.0091	48.0117	48.0115	48.0102	48.0087	47.9921	47.9773	47.9480
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Li+Na+K	10.46	10.46	10.46	10.46	10.4575	10.4522	10.4523	10.4522	10.4518	10.4513	10.4572	10.4520	10.4416
Mg+Ca+Sr+Ba	1.5895	1.5894	1.5893	1.5892	1.5887	1.5878	1.5878	1.5878	1.5877	1.5877	1.5885	1.5878	1.5862
Zr+Ti+La+Nb+Ta+Hf	1.4664	1.4664	1.4663	1.4663	1.4657	1.4650	1.4650	1.4649	1.4649	1.4648	1.4656	1.4649	1.4635
Ca/Sn	0.000	0.010	0.052	0.103	0.517	1.036	0.000	0.005	0.026	0.052	0.259	0.518	1.036
Sn+Ce	0.079	0.079	0.083	0.087	0.119	0.160	0.157	0.158	0.161	0.165	0.197	0.238	0.319
Si+Al	38.3646	38.3642	38.3627	38.3608	38.3455	38.3263	38.3264	38.3260	38.3245	38.3226	38.2992	38.2802	38.2420
Rank on bubbles	D	C	B	B	B	B	D	B	A	A	A	A	A
Acid etching rate (nm/min)	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Alkaline etching rate (nm/min)	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07

Component(mass%)	1-14	1-15	1-16	1-17	1-18	1-19	1-20	1-21	1-22	1-23	1-24	1-25	1-26	1-27
Si	30.3229	30.3226	30.3214	30.3199	30.3078	30.2927	30.2626	30.2476	30.3078	30.3075	30.3063	30.3048	30.2927	30.2777
Al	7.9783	7.9783	7.9759	7.9755	7.9724	7.9684	7.9605	7.9565	7.9724	7.9723	7.9720	7.9716	7.9684	7.9644
Li	1.8066	1.8066	1.8065	1.8064	1.8057	1.8048	1.8030	1.8021	1.8057	1.8057	1.8056	1.8055	1.8048	1.8039
Na	8.2737	8.2737	8.2733	8.2729	8.2696	8.2655	8.2573	8.2532	8.2696	8.2695	8.2692	8.2688	8.2655	8.2614
K	0.3769	0.3769	0.3769	0.3769	0.3767	0.3765	0.3762	0.3760	0.3767	0.3767	0.3767	0.3767	0.3765	0.3763
Mg	0.4295	0.4295	0.4295	0.4295	0.4293	0.4291	0.4287	0.4285	0.4293	0.4293	0.4293	0.4293	0.4291	0.4289
Ca	1.1590	1.1590	1.1590	1.1589	1.1585	1.1579	1.1567	1.1562	1.1585	1.1585	1.1584	1.1583	1.1579	1.1573
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4656	1.4656	1.4656	1.4655	1.4649	1.4642	1.4627	1.4620	1.4649	1.4649	1.4648	1.4648	1.4642	1.4635
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.1960	0.1960	0.1960	0.1960	0.1959	0.1958	0.1955	0.1954	0.2351	0.2351	0.2351	0.2350	0.2349	0.2348
Ge	0.0000	0.0008	0.0041	0.0081	0.0406	0.0811	0.1621	0.2024	0.0000	0.0008	0.0041	0.0082	0.0406	0.0811
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.9933	47.9930	47.9918	47.9904	47.9786	47.9640	47.9347	47.9201	47.9800	47.9797	47.9785	47.9770	47.9654	47.9507
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Li+Na+K	10.4572	10.4572	10.4567	10.4562	10.4520	10.4468	10.4385	10.4313	10.4520	10.4519	10.4515	10.4510	10.4468	10.4416
Mg+Ca+Sr+Ba	1.5885	1.5885	1.5885	1.5884	1.5878	1.5870	1.5854	1.5847	1.5878	1.5878	1.5877	1.5876	1.5870	1.5862
Zr+Ti+La+Nb+Ta+Hf	1.4656	1.4656	1.4656	1.4655	1.4649	1.4642	1.4627	1.4620	1.4649	1.4649	1.4648	1.4648	1.4642	1.4635
Ce/Sn	0.000	0.004	0.021	0.041	0.207	0.414	0.829	1.036	0.000	0.003	0.017	0.035	0.173	0.345
Sn+Ge	0.196	0.197	0.200	0.204	0.237	0.277	0.358	0.398	0.235	0.236	0.239	0.243	0.276	0.316
Si+Al	38.2992	38.2989	38.2973	38.2954	38.2802	38.2611	38.2231	38.2041	38.2802	38.2798	38.2783	38.2764	38.2611	38.2421
Rank on bubbles	D	B	A	A	A	A	A	A	D	B	A	A	A	A
Acid etching rate (nm/min)	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Alkaline etching rate (nm/min)	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07

[0286]
[Table 2]

Component (mass%)	1-56	1-57	1-58	1-59	Com.Ex.1-1	Com.Ex.1-2	Com.Ex.1-3	Com.Ex.1-4	Com.Ex.1-5
Si	30.1124	30.0826	30.0372	30.0076	30.2480	30.2776	30.4099	30.4083	30.0671
Al	7.9328	7.9250	7.9248	7.9170	7.9566	7.9644	7.9873	7.9889	7.9327
Li	1.7967	1.7949	1.7949	1.7931	1.8021	1.8039	1.8091	1.8090	1.7967
Na	8.2286	8.2205	8.2202	8.2122	8.2533	8.2614	8.2851	8.2847	8.2284
K	0.3748	0.3745	0.3745	0.3741	0.3760	0.3763	0.3774	0.3774	0.3748
Mg	0.4272	0.4268	0.4268	0.4263	0.4285	0.4289	0.4301	0.4301	0.4272
Ca	1.1527	1.1516	1.1515	1.1504	1.1582	1.1573	1.1608	1.1606	1.1527
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4576	1.4562	1.4562	1.4547	1.4620	1.4635	1.4677	1.4676	1.4576
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4667	0.4661	0.4659	0.4653	0.0000	0.1957	0.0079	0.0079	0.7775
Ce	0.2418	0.3220	0.4023	0.4822	0.0000	0.0000	0.0041	0.0081	0.0000
Sb	0.0000	0.0000	0.0000	0.0000	0.4137	0.1250	0.0000	0.0000	0.0000
O	47.8087	47.7796	47.7457	47.7171	47.9036	47.9460	48.0609	48.0594	47.7853
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Li+Na+K	10.4001	10.3899	10.3898	10.3794	10.4314	10.4416	10.4716	10.4711	10.3999
Mg+Ca+Sr+Ba	1.5799	1.5784	1.5783	1.5767	1.5847	1.5862	1.5907	1.5907	1.5799
Zr+Ti+La+Nb+Ta+Hf	1.4576	1.4562	1.4562	1.4547	1.4620	1.4635	1.4677	1.4676	1.4576
Ce/Sn	0.518	0.691	0.863	1.036	—	0.000	0.519	—	0.000
Sn+Ce	0.709	0.788	0.868	0.948	0.000	0.196	0.012	0.016	0.778
Si+Al	38.0452	38.0078	37.9620	37.9246	38.2046	38.2420	38.3971	38.3952	37.9998
Rank on bubbles	B	B	B	B	G	G	G	G	G
Acid etching rate (nm/min)	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Alkaline etching rate (nm/min)	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07

[illegible]

[illegible]

Component	2-1	2-2	2-3	2-4	2-5	2-6	2-7	2-8	2-9	2-10	2-11	2-12	2-13
Si	30.0102	30.0089	30.0086	30.0089	29.9774	29.9607	29.9649	29.9645	29.9632	29.9615	29.9482	29.9317	29.8985
Al	8.0013	8.0012	8.0008	8.0004	8.0046	8.0001	8.0012	8.0011	8.0008	8.0003	7.9968	7.9924	7.9835
Li	1.8122	1.8122	1.8121	1.8120	1.8130	1.8120	1.8122	1.8122	1.8121	1.8120	1.8112	1.8102	1.8082
Na	8.2996	8.2995	8.2991	8.2987	8.3030	8.2984	8.2996	8.2995	8.2991	8.2986	8.2950	8.2904	8.2812
K	0.3781	0.3781	0.3781	0.3780	0.3782	0.3780	0.3781	0.3781	0.3781	0.3780	0.3779	0.3777	0.3772
Mg	0.5876	0.5876	0.5875	0.5875	0.5878	0.5875	0.5876	0.5876	0.5875	0.5875	0.5872	0.5869	0.5863
Ca	1.4856	1.4856	1.4855	1.4856	1.4862	1.4854	1.4856	1.4856	1.4855	1.4854	1.4848	1.4840	1.4823
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4702	1.4702	1.4701	1.4701	1.4708	1.4700	1.4702	1.4702	1.4701	1.4701	1.4694	1.4686	1.4670
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0765	0.0765	0.0765	0.0765	0.0766	0.0766	0.1531	0.1531	0.1530	0.1530	0.1530	0.1529	0.1527
Ce	0.0000	0.0009	0.0045	0.0090	0.0452	0.0803	0.0000	0.0009	0.0046	0.0090	0.0451	0.0902	0.1803
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.8787	47.8783	47.8772	47.8754	47.8572	47.8410	47.8475	47.8472	47.8460	47.8446	47.8314	47.8152	47.7828
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.4899	10.4898	10.4893	10.4887	10.4942	10.4884	10.4899	10.4898	10.4893	10.4886	10.4841	10.4783	10.4666
Mg+Ca+Sr+Ba	2.0732	2.0732	2.0730	2.0730	2.0740	2.0728	2.0732	2.0732	2.0730	2.0728	2.0720	2.0709	2.0686
Zr+Ti+La+Nb+Ta+Hf	1.4702	1.4702	1.4701	1.4701	1.4708	1.4700	1.4702	1.4702	1.4701	1.4701	1.4694	1.4686	1.4670
Ce/Sn	0.0000	0.0118	0.0588	0.1176	0.5901	1.1789	0.0000	0.0059	0.0301	0.0588	0.2948	0.5899	1.1807
Sn+Ce	0.0765	0.0774	0.0810	0.0855	0.1218	0.1669	0.1531	0.1540	0.1576	0.1620	0.1981	0.2431	0.3330

Component	2-56	2-57	2-58	2-59	Com.Ex.2-1	Com.Ex.2-2	Com.Ex.2-3	Com.Ex.2-4	Com.Ex.2-5
Si	29.7349	29.6908	29.6612	29.6286	29.8825	29.8082	30.0348	30.0332	29.7010
Al	7.9518	7.9521	7.9441	7.9354	7.9792	7.9861	8.0078	8.0074	7.9548
Li	1.8010	1.8011	1.7993	1.7973	1.8072	1.8098	1.8137	1.8136	1.8017
Na	8.2483	8.2486	8.2403	8.2313	8.2768	8.2839	8.3084	8.3059	8.2514
K	0.3757	0.3758	0.3754	0.3750	0.3770	0.3774	0.3784	0.3784	0.3759
Mg	0.5839	0.5840	0.5834	0.5827	0.5860	0.5865	0.5881	0.5880	0.5842
Ca	1.4764	1.4765	1.4750	1.4734	1.4815	1.4828	1.4868	1.4868	1.4770
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4611	1.4612	1.4597	1.4581	1.4662	1.4674	1.4714	1.4713	1.4617
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4753	0.4753	0.4749	0.4744	0.0000	0.1910	0.0077	0.0077	0.7608
Ge	0.2489	0.3228	0.4036	0.4926	0.0000	0.0000	0.0045	0.0090	0.0000
Sb	0.0000	0.0000	0.0000	0.0000	0.3914	0.1175	0.0000	0.0000	0.0000
O	47.8447	47.8120	47.5831	47.5512	47.7522	47.7804	47.8004	47.8987	47.6315
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.4250	10.4255	10.4150	10.4036	10.4610	10.4701	10.4985	10.4979	10.4290
Mg+Ca+Sr+Ba	2.0603	2.0605	2.0584	2.0561	2.0675	2.0693	2.0749	2.0748	2.0612
Zr+Ti+La+Nb+Ta+Hf	1.4611	1.4612	1.4597	1.4581	1.4662	1.4674	1.4714	1.4713	1.4617
Ce/Sn	0.5185	0.6787	0.8499	1.0384	--	0.0000	0.5844	--	0.0000
Sn+Ge	0.7222	0.7979	0.8785	0.9670	0.0000	0.1910	0.0122	0.0167	0.7608
Si+Al	37.6867	37.6429	37.6053	37.5640	37.8617	37.8943	38.0426	38.0406	37.6558
Rank on bubbles	B	B	B	B	G	G	G	G	G
Acid etching rate (nm/min)	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7
Alkaline etching rate (nm/min)	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07	0.07

[0287]

[Table 3]

Component		3-1	3-2	3-3	3-4	3-5	3-6	3-7	3-8	3-9	3-10	3-11	3-12	3-13
(mol%)	SiO ₂	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0
	Al ₂ O ₃	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
	Li ₂ O	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2
	Na ₂ O	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4
	K ₂ O	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass composition (mass%)	SnO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	CaO ₂	0	0.001	0.005	0.01	0.05	0.1	0	0.001	0.005	0.01	0.05	0.1	0.2
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000	1.0000
	SnO ₂ +CaO ₂	0.100	0.101	0.105	0.110	0.150	0.200	0.200	0.201	0.205	0.210	0.250	0.300	0.400
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	SiO ₂ +Al ₂ O ₃	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A	A

Component		3-14	3-15	3-16	3-17	3-18	3-19	3-20	3-21	3-22	3-23	3-24	3-25	3-26
(mol%)	SiO ₂	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0
	Al ₂ O ₃	8.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
	Li ₂ O	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2
	Na ₂ O	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4
	K ₂ O	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.3	0.3	0.3	0.3	0.3
	CeO ₂	0	0.001	0.005	0.01	0.05	0.1	0.2	0.25	0	0.001	0.005	0.01	0.05
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.0000	0.0040	0.0200	0.0400	0.2000	0.4000	0.8000	1.0000	0.0000	0.0033	0.0167	0.0333	0.1667
	SnO ₂ +CeO ₂	0.250	0.251	0.255	0.260	0.300	0.350	0.450	0.500	0.300	0.301	0.305	0.310	0.350
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	SiO ₂ +Al ₂ O ₃	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0
Rank on bubbles		D	B	A	A	A	A	A	A	D	B	A	A	A

Component		3-27	3-28	3-29	3-30	3-31	3-32	3-33	3-34	3-35	3-36	3-37	3-38	3-39
(mol%)	SiO ₂	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0
	Al ₂ O ₃	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
	Li ₂ O	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2
	Na ₂ O	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4
	K ₂ O	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.3	0.3	0.3	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.5
	GeO ₂	0.1	0.2	0.3	0	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0
	Sn ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	GeO ₂ /SnO ₂	0.3333	0.6667	1.0000	0.0000	0.0025	0.0125	0.0250	0.1250	0.2500	0.5000	0.7500	1.0000	0.0000
	SnO ₂ +GeO ₂	0.400	0.500	0.600	0.400	0.401	0.405	0.410	0.450	0.500	0.600	0.700	0.800	0.500
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	SiO ₂ +Al ₂ O ₃	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0
Rank on bubbles		A	A	A	D	B	B	A	A	A	A	A	A	E

Component		3-40	3-41	3-42	3-43	3-44	3-45	3-46	3-47	3-48	3-49	3-50	3-51	3-52
(mol%)	SiO ₂	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0
	Al ₂ O ₃	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
	Li ₂ O	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2
	Na ₂ O	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4
	K ₂ O	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.6	0.6	0.6	0.6
	CaO ₂	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0.5	0	0.001	0.005	0.01
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0020	0.0100	0.0200	0.1000	0.2000	0.4000	0.6000	0.8000	1.0000	0.0000	0.0017	0.0083	0.0167
	SnO ₂ +CaO ₂	0.501	0.505	0.510	0.550	0.600	0.700	0.800	0.900	1.000	0.600	0.601	0.605	0.610
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	SiO ₂ +Al ₂ O ₃	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0
Rank on bubbles		C	C	B	B	A	A	A	A	A	E	C	C	C

Component		3-53	3-54	3-55	3-56	3-57	3-58	3-59	Com.Ex.3-1	Com.Ex.3-2	Com.Ex.3-3	Com.Ex.3-4	Com.Ex.3-5
(mol%)	SiO ₂	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0	72.0
	Al ₂ O ₃	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
	Li ₂ O	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2
	Na ₂ O	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4
	K ₂ O	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0	0.25	1	0	1
	CeO ₂	0.05	0.1	0.2	0.3	0.4	0.5	0.6	0	0	0	1	1
	Sb ₂ O ₃	0	0	0	0	0	0	0	0.5	0.15	0	0	0
	CeO ₂ /SnO ₂	0.0833	0.1667	0.3333	0.5000	0.6667	0.8333	1.0000	-	0.0000	0.0000	-	1.0000
	SnO ₂ +CeO ₂	0.650	0.700	0.800	0.900	1.000	1.100	1.200	0.000	0.250	1.000	1.000	2.000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	SiO ₂ +Al ₂ O ₃	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0	78.0
Rank on bubbles		C	B	B	B	B	B	B	G	G	G	G	G

Component(mass%)	3-1	3-2	3-3	3-4	3-5	3-6	3-7	3-8	3-9	3-10	3-11	3-12	3-13
Si	33.2503	33.2500	33.2486	33.2470	33.2337	33.2171	33.2172	33.2169	33.2155	33.2139	33.2006	33.1707	33.1511
Al	5.3239	5.3238	5.3236	5.3234	5.3212	5.3188	5.3186	5.3185	5.3183	5.3181	5.3159	5.3185	5.3080
Li	1.8489	1.8489	1.8488	1.8487	1.8480	1.8471	1.8471	1.8471	1.8470	1.8469	1.8462	1.8471	1.8434
Na	7.8628	7.8627	7.8624	7.8620	7.8589	7.8550	7.8550	7.8549	7.8546	7.8542	7.8511	7.8549	7.8394
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	1.6475	1.6475	1.6474	1.6473	1.6467	1.6459	1.6459	1.6458	1.6458	1.6457	1.6450	1.6458	1.6426
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3500	1.3500	1.3499	1.3499	1.3493	1.3488	1.3487	1.3486	1.3486	1.3485	1.3480	1.3486	1.3460
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0786	0.0786	0.0786	0.0786	0.0785	0.0785	0.1569	0.1569	0.1569	0.1569	0.1568	0.1569	0.1565
Ce	0.0000	0.0008	0.0041	0.0081	0.0407	0.0813	0.0000	0.0008	0.0041	0.0081	0.0408	0.0813	0.1622
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.6380	48.6377	48.6366	48.6350	48.6230	48.6079	48.6106	48.6105	48.6082	48.6077	48.5957	48.5762	48.5508
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	99.9999	100.0000	100.0000
Li+Na+K	9.7117	9.7116	9.7112	9.7107	9.7089	9.7021	9.7021	9.7020	9.7016	9.7011	9.6973	9.7020	9.6828
Mg+Ca+Sr+Ba	1.6475	1.6475	1.6474	1.6473	1.6467	1.6459	1.6459	1.6458	1.6458	1.6457	1.6450	1.6458	1.6426
Zr+Ti+La+Nb+Ta+Hf	1.3500	1.3500	1.3499	1.3499	1.3493	1.3488	1.3487	1.3486	1.3486	1.3485	1.3480	1.3486	1.3460
Ce/Sn	0.0000	0.0102	0.0522	0.1031	0.5185	1.0357	0.0000	0.0051	0.0261	0.0516	0.2589	0.5182	1.0364
Sn+Ce	0.0786	0.0784	0.0827	0.0867	0.1192	0.1598	0.1569	0.1577	0.1610	0.1650	0.1974	0.2382	0.3187
Si+Al	38.5742	38.5738	38.5722	38.5704	38.5549	38.5357	38.5358	38.5354	38.5338	38.5320	38.5185	38.4892	38.4501
Rank on bubbles	D	C	B	B	B	B	D	B	A	A	A	A	A

Component(mass%)	3-14	3-15	3-16	3-17	3-18	3-19	3-20	3-21	3-22	3-23	3-24	3-25	3-26	3-27
Si	33.2007	33.2003	33.1990	33.1974	33.1707	33.1542	30.3850	30.3700	30.4303	30.4300	30.4288	30.4273	30.4152	30.4001
Al	5.3159	5.3159	5.3157	5.3154	5.3185	5.3159	8.1134	8.1094	8.1255	8.1254	8.1251	8.1247	8.1215	8.1175
Li	1.8462	1.8461	1.8461	1.8460	1.8471	1.8461	1.8376	1.8367	1.8404	1.8403	1.8403	1.8402	1.8394	1.8385
Na	7.8511	7.8510	7.8507	7.8503	7.8549	7.8510	8.4159	8.4118	8.4285	8.4284	8.4281	8.4276	8.4243	8.4201
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	1.6450	1.6450	1.6450	1.6449	1.6458	1.6450	1.5064	1.5057	1.5087	1.5087	1.5086	1.5085	1.5079	1.5072
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3480	1.3480	1.3479	1.3478	1.3486	1.3480	1.3417	1.3411	1.3437	1.3437	1.3437	1.3436	1.3431	1.3424
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.1960	0.1960	0.1960	0.1960	0.1961	0.1960	0.1950	0.1948	0.2344	0.2344	0.2344	0.2344	0.2343	0.2341
Ce	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1616	0.2019	0.0000	0.0008	0.0040	0.0081	0.0405	0.0809
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.5971	48.5969	48.5955	48.5941	48.5777	48.5626	48.0434	48.0286	48.0885	48.0883	48.0870	48.0856	48.0738	48.0592
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	9.6973	9.6971	9.6968	9.6963	9.7020	9.6971	10.2535	10.2485	10.2689	10.2687	10.2684	10.2678	10.2637	10.2586
Mg+Ca+Sr+Ba	1.6450	1.6450	1.6450	1.6449	1.6458	1.6450	1.5064	1.5057	1.5087	1.5087	1.5086	1.5085	1.5079	1.5072
Zr+Ti+La+Nb+Ta+Hf	1.3480	1.3480	1.3479	1.3478	1.3486	1.3480	1.3417	1.3411	1.3437	1.3437	1.3437	1.3436	1.3431	1.3424
Ce/Sn	0.0000	0.0041	0.0209	0.0413	0.2070	0.4143	0.8287	1.0364	0.0000	0.0034	0.0171	0.0346	0.1729	0.3456
Sn+Ce	0.1960	0.1968	0.2001	0.2041	0.2367	0.2772	0.3566	0.3967	0.2344	0.2352	0.2384	0.2425	0.2748	0.3150
Si+Al	38.5166	38.5162	38.5147	38.5128	38.4892	38.4701	38.4984	38.4794	38.5558	38.5554	38.5539	38.5520	38.5367	38.5176
Rank on bubbles	D	B	A	A	A	A	A	A	D	B	A	A	A	A

Component (mass%)	3-42	3-43	3-44	3-45	3-46	3-47	3-48	3-49	3-50	3-51	3-52	3-53	3-54	3-55
Si	30.3511	30.3391	30.3241	30.2941	30.2642	30.2344	30.1885	30.3241	30.3238	30.3228	30.3211	30.3092	30.2942	30.2643
Al	8.1166	8.1134	8.1094	8.1014	8.0934	8.0854	8.0854	8.1094	8.1093	8.1090	8.1086	8.1054	8.1014	8.0934
Li	1.8383	1.8376	1.8367	1.8349	1.8331	1.8313	1.8313	1.8367	1.8367	1.8366	1.8365	1.8358	1.8349	1.8331
Na	8.4192	8.4159	8.4117	8.4034	8.3951	8.3869	8.3888	8.4118	8.4117	8.4114	8.4109	8.4078	8.4035	8.3952
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	1.5070	1.5084	1.5057	1.5042	1.5027	1.5012	1.5012	1.5057	1.5057	1.5056	1.5056	1.5050	1.5042	1.5027
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3423	1.3417	1.3411	1.3398	1.3384	1.3371	1.3371	1.3411	1.3411	1.3410	1.3410	1.3404	1.3398	1.3384
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.3900	0.3898	0.3895	0.3890	0.3885	0.3879	0.3878	0.4674	0.4674	0.4674	0.4673	0.4671	0.4668	0.4661
Ce	0.0081	0.0404	0.0807	0.1612	0.2415	0.3216	0.4019	0.0000	0.0008	0.0040	0.0081	0.0403	0.0806	0.1610
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.0274	48.0157	48.0011	47.9720	47.9431	47.9142	47.8800	48.0038	48.0035	48.0024	48.0009	47.9892	47.9746	47.9458
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.2575	10.2535	10.2484	10.2383	10.2282	10.2182	10.2181	10.2485	10.2484	10.2480	10.2474	10.2434	10.2384	10.2283
Mg+Ca+Sr+Ba	1.5070	1.5084	1.5057	1.5042	1.5027	1.5012	1.5012	1.5057	1.5057	1.5056	1.5056	1.5050	1.5042	1.5027
Zr+Ti+La+Nb+Ta+Hf	1.3423	1.3417	1.3411	1.3398	1.3384	1.3371	1.3371	1.3411	1.3411	1.3410	1.3410	1.3404	1.3398	1.3384
Ce/Sn	0.0208	0.1036	0.2072	0.4144	0.6216	0.8291	1.0364	0.0000	0.0017	0.0086	0.0173	0.0863	0.1727	0.3454
Sn+Ce	0.3981	0.4302	0.4702	0.5502	0.6300	0.7095	0.7897	0.4674	0.4682	0.4714	0.4754	0.5074	0.5474	0.6271
Si+Al	38.4677	38.4525	38.4335	38.3955	38.3576	38.3198	38.2739	38.4935	38.4331	38.4316	38.4297	38.4146	38.3958	38.3577
Rank on bubbles	B	B	A	A	A	A	A	E	C	C	C	C	B	B

Component (mass%)	3-56	3-57	3-58	3-59	Com.Ex.3-1	Com.Ex.3-2	Com.Ex.3-3	Com.Ex.3-4	Com.Ex.3-5
Si	30.2345	30.1886	30.1589	30.1283	30.3700	30.4005	30.5326	30.5311	30.1890
Al	8.0854	8.0854	8.0775	8.0695	8.1094	8.1175	8.1405	8.1401	8.0855
Li	1.8313	1.8313	1.8295	1.8277	1.8367	1.8386	1.8438	1.8437	1.8313
Na	8.3869	8.3869	8.3786	8.3704	8.4118	8.4202	8.4440	8.4438	8.3870
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	1.5012	1.5012	1.4998	1.4983	1.5057	1.5072	1.5115	1.5114	1.5013
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3371	1.3371	1.3358	1.3345	1.3411	1.3424	1.3462	1.3462	1.3371
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4655	0.4654	0.4647	0.4641	0.0000	0.1952	0.0078	0.0078	0.7754
Ce	0.2412	0.3215	0.4013	0.4809	0.0000	0.0000	0.0041	0.0081	0.0000
Sb	0.0000	0.0000	0.0000	0.0000	0.4137	0.1234	0.0000	0.0000	0.0000
O	47.9189	47.8826	47.8539	47.8253	48.0116	48.0350	48.1695	48.1680	47.8934
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.2182	10.2182	10.2081	10.1981	10.2485	10.2588	10.2878	10.2873	10.2183
Mg+Ca+Sr+Ba	1.5012	1.5012	1.4998	1.4983	1.5057	1.5072	1.5115	1.5114	1.5013
Zr+Ti+La+Nb+Ta+Hf	1.3371	1.3371	1.3358	1.3345	1.3411	1.3424	1.3462	1.3462	1.3371
Ce/Sn	0.5182	0.6908	0.8636	1.0362	-	0.0000	0.5256	-	0.0000
Sn+Ce	0.7087	0.7869	0.8660	0.8450	0.0000	0.1952	0.0119	0.0159	0.7754
Si+Al	38.3189	38.2740	38.2364	38.1988	38.4794	38.5180	38.6731	38.6712	38.2745
Rank on bubbles	B	B	B	B	G	G	G	G	G

[0288]

[Table 4]

Component		4-1	4-2	4-3	4-4	4-5	4-6	4-7	4-8	4-9	4-10	4-11	4-12	4-13
(mol%)	SiO ₂	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0
	Al ₂ O ₃	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0
	Li ₂ O	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0
	Na ₂ O	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5
	K ₂ O	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	MgO	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	CaO	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	SrO	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	CeO ₂	0	0.001	0.005	0.01	0.05	0.1	0	0.001	0.005	0.01	0.05	0.1	0.2
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000	1.0000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	SiO ₂ +Al ₂ O ₃	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A	A

Component		4-14	4-15	4-16	4-17	4-18	4-19	4-20	4-21	4-22	4-23	4-24	4-25	4-26
(mol%)	SiO ₂	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0
	Al ₂ O ₃	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0
	Li ₂ O	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0
	Na ₂ O	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5
	K ₂ O	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	MgO	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	CaO	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	SrO	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.3	0.3	0.3	0.3	0.3
	GeO ₂	0	0.001	0.005	0.01	0.05	0.1	0.2	0.25	0	0.001	0.005	0.01	0.05
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	GeO ₂ /SnO ₂	0.0000	0.0040	0.0200	0.0400	0.2000	0.4000	0.8000	1.0000	0.0000	0.0033	0.0167	0.0333	0.1667
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	SiO ₂ +Al ₂ O ₃	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0
Rank on bubbles		D	B	A	A	A	A	A	A	D	B	A	A	A

Component		4-27	4-28	4-29	4-30	4-31	4-32	4-33	4-34	4-35	4-36	4-37	4-38	4-39
(mol%)	SiO ₂	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0
	Al ₂ O ₃	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0
	Li ₂ O	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0
	Na ₂ O	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5
	K ₂ O	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	MgO	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	CaO	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	SrO	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.3	0.3	0.3	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.5
	CeO ₂	0.1	0.2	0.3	0	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.3333	0.6667	1.0000	0.0000	0.0025	0.0125	0.0250	0.1250	0.2500	0.5000	0.7500	1.0000	0.0000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	SiO ₂ +Al ₂ O ₃	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0
Rank on bubbles		A	A	A	D	B	B	A	A	A	A	A	A	E

Component		4-40	4-41	4-42	4-43	4-44	4-45	4-46	4-47	4-48	4-49	4-50	4-51	4-52
(mol%)	SiO ₂	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0
	Al ₂ O ₃	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0
	Li ₂ O	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0
	Na ₂ O	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5
	K ₂ O	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	MgO	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	CaO	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	SrO	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.6	0.6	0.6	0.6
	CaO ₂	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0.5	0	0.001	0.005	0.01
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0020	0.0100	0.0200	0.1000	0.2000	0.4000	0.6000	0.8000	1.0000	0.0000	0.0017	0.0083	0.0167
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	SiO ₂ +Al ₂ O ₃	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0
Rank on bubbles		C	C	B	B	A	A	A	A	A	E	C	C	C

Component		4-53	4-54	4-55	4-56	4-57	4-58	4-59	Com.Ex.4-1	Com.Ex.4-2	Com.Ex.4-3	Com.Ex.4-4	Com.Ex.4-5
(mol%)	SiO ₂	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0	69.0
	Al ₂ O ₃	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0
	Li ₂ O	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0
	Na ₂ O	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5	11.5
	K ₂ O	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	MgO	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	CaO	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	SrO	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0	0.25	1	0	1
	CeO ₂	0.05	0.1	0.2	0.3	0.4	0.5	0.6	0	0	0	1	1
	Sb ₂ O ₃	0	0	0	0	0	0	0	0.5	0.15	0	0	0
	CeO ₂ /SnO ₂	0.0833	0.1667	0.3333	0.5000	0.6667	0.8333	1.0000	—	0.0000	0.0000	—	1.0000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4	3.4
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	SiO ₂ +Al ₂ O ₃	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0	76.0
Rank on bubbles		C	B	B	B	B	B	B	G	G	G	G	G

Component(mass%)	4-1	4-2	4-3	4-4	4-5	4-6	4-7	4-8	4-9	4-10	4-11	4-12	4-13
Si	31.4964	31.4961	31.4948	31.4933	31.4807	31.4501	31.4501	31.4498	31.4486	31.4470	31.4345	31.4188	31.3875
Al	6.1394	6.1393	6.1391	6.1388	6.1363	6.1392	6.1393	6.1392	6.1390	6.1386	6.1362	6.1331	6.1270
Li	1.8050	1.8050	1.8049	1.8048	1.8041	1.8049	1.8049	1.8049	1.8049	1.8048	1.8040	1.8031	1.8013
Na	8.5939	8.5939	8.5935	8.5931	8.5896	8.5937	8.5938	8.5937	8.5933	8.5929	8.5895	8.5852	8.5767
K	0.1271	0.1271	0.1271	0.1271	0.1270	0.1271	0.1271	0.1271	0.1271	0.1271	0.1270	0.1270	0.1268
Mg	0.3950	0.3950	0.3950	0.3950	0.3948	0.3950	0.3950	0.3950	0.3950	0.3950	0.3948	0.3946	0.3942
Ca	1.3028	1.3028	1.3027	1.3026	1.3021	1.3027	1.3027	1.3027	1.3027	1.3027	1.3026	1.3021	1.3001
Sr	0.5696	0.5696	0.5696	0.5696	0.5693	0.5696	0.5696	0.5696	0.5696	0.5696	0.5696	0.5691	0.5685
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3344	1.3344	1.3343	1.3343	1.3337	1.3344	1.3344	1.3343	1.3343	1.3342	1.3337	1.3330	1.3317
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.2901	0.2901	0.2901	0.2901	0.2900	0.2901	0.2901	0.2901	0.2901	0.2901	0.2899	0.2898	0.2895
Sn	0.0785	0.0785	0.0785	0.0785	0.0785	0.0785	0.1570	0.1570	0.1570	0.1569	0.1569	0.1568	0.1565
Ce	0.0000	0.0008	0.0041	0.0081	0.0407	0.0813	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1622
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.8678	47.8674	47.8663	47.8647	47.8532	47.8334	47.8360	47.8358	47.8343	47.8331	47.8215	47.8089	47.7780
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.5260	10.5280	10.5255	10.5250	10.5207	10.5257	10.5258	10.5257	10.5253	10.5248	10.5205	10.5153	10.5048
Mg+Ca+Sr+Ba	2.2674	2.2674	2.2673	2.2672	2.2662	2.2673	2.2673	2.2673	2.2673	2.2672	2.2662	2.2651	2.2628
Zr+Ti+La+Nb+Ta+Hf	1.6245	1.6245	1.6244	1.6244	1.6237	1.6245	1.6245	1.6244	1.6244	1.6243	1.6236	1.6228	1.6212
Ce/Sn	0.0000	0.0102	0.0522	0.1032	0.5185	1.0357	0.0000	0.0051	0.0261	0.0516	0.2588	0.5179	1.0364
Si+Al	37.6358	37.6354	37.6339	37.6321	37.6170	37.5893	37.5894	37.5880	37.5876	37.5856	37.5707	37.5519	37.5145
Rank on bubbles	D	C	B	B	B	B	D	B	A	A	A	A	A

Component(mass%)	4-14	4-15	4-16	4-17	4-18	4-19	4-20	4-21	4-22	4-23	4-24	4-25	4-26	4-27
Si	31.4345	31.4342	31.4329	31.4314	31.4188	31.4032	31.3720	31.3564	31.4189	31.4186	31.4173	31.4157	31.4032	31.3876
Al	6.1362	6.1361	6.1359	6.1356	6.1331	6.1301	6.1240	6.1210	6.1332	6.1331	6.1329	6.1325	6.1301	6.1271
Li	1.8040	1.8040	1.8040	1.8039	1.8031	1.8022	1.8005	1.7996	1.8031	1.8031	1.8031	1.8030	1.8023	1.8014
Na	8.5895	8.5894	8.5891	8.5886	8.5852	8.5809	8.5724	8.5681	8.5852	8.5851	8.5848	8.5844	8.5810	8.5787
K	0.1270	0.1270	0.1270	0.1270	0.1270	0.1269	0.1268	0.1267	0.1270	0.1270	0.1270	0.1270	0.1269	0.1268
Mg	0.3948	0.3948	0.3948	0.3948	0.3946	0.3944	0.3940	0.3938	0.3946	0.3946	0.3946	0.3946	0.3944	0.3942
Ca	1.3021	1.3021	1.3020	1.3020	1.3014	1.3008	1.2995	1.2989	1.3014	1.3014	1.3014	1.3013	1.3008	1.3001
Sr	0.5693	0.5693	0.5693	0.5693	0.5691	0.5688	0.5682	0.5679	0.5691	0.5690	0.5690	0.5690	0.5688	0.5685
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3337	1.3337	1.3336	1.3336	1.3330	1.3324	1.3310	1.3304	1.3330	1.3330	1.3330	1.3329	1.3324	1.3317
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.2899	0.2899	0.2899	0.2899	0.2898	0.2897	0.2894	0.2892	0.2898	0.2898	0.2898	0.2898	0.2897	0.2895
Sn	0.1961	0.1961	0.1961	0.1960	0.1959	0.1958	0.1955	0.1954	0.2351	0.2351	0.2351	0.2351	0.2350	0.2348
Ce	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1621	0.2025	0.0000	0.0008	0.0040	0.0081	0.0406	0.0811
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.8229	47.8228	47.8213	47.8198	47.8084	47.7936	47.7648	47.7501	47.8096	47.8094	47.8080	47.8066	47.7948	47.7805
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.5205	10.5204	10.5201	10.5195	10.5153	10.5100	10.4997	10.4944	10.5153	10.5152	10.5149	10.5144	10.5102	10.5049
Mg+Ca+Sr+Ba	2.2662	2.2662	2.2661	2.2661	2.2651	2.2640	2.2617	2.2606	2.2651	2.2650	2.2650	2.2649	2.2640	2.2628
Zr+Ti+La+Nb+Ta+Hf	1.6236	1.6236	1.6235	1.6235	1.6228	1.6221	1.6204	1.6196	1.6228	1.6228	1.6228	1.6227	1.6221	1.6212
Ce/Sn	0.0000	0.0041	0.0209	0.0413	0.2072	0.4147	0.8292	1.0383	0.0000	0.0034	0.0170	0.0345	0.1728	0.3454
Si+Al	37.5707	37.5703	37.5688	37.5670	37.5519	37.5333	37.4960	37.4774	37.5521	37.5517	37.5502	37.5482	37.5333	37.5147
Rank on bubbles	D	B	A	A	A	A	A	A	D	B	A	A	A	A

Component(mass%)	4-42	4-43	4-44	4-45	4-46	4-47	4-48	4-49	4-50	4-51	4-52	4-53	4-54	4-55
Si	31.3535	31.3260	31.3105	31.2795	31.2485	31.2177	31.1718	31.3106	31.3103	31.3090	31.3075	31.2951	31.2796	31.2486
Al	6.1204	6.1239	6.1209	6.1148	6.1088	6.1027	6.1026	6.1209	6.1208	6.1206	6.1203	6.1179	6.1148	6.1088
Li	1.7994	1.8004	1.7995	1.7978	1.7960	1.7942	1.7942	1.7995	1.7995	1.7995	1.7994	1.7987	1.7978	1.7960
Na	8.5674	8.5723	8.5680	8.5596	8.5511	8.5426	8.5425	8.5681	8.5680	8.5676	8.5672	8.5638	8.5596	8.5511
K	0.1267	0.1268	0.1267	0.1266	0.1265	0.1263	0.1263	0.1267	0.1267	0.1267	0.1267	0.1266	0.1266	0.1265
Mg	0.3938	0.3940	0.3938	0.3934	0.3931	0.3927	0.3927	0.3938	0.3938	0.3938	0.3938	0.3936	0.3934	0.3931
Ca	1.2987	1.2995	1.2988	1.2976	1.2963	1.2950	1.2950	1.2988	1.2988	1.2988	1.2987	1.2982	1.2976	1.2963
Sr	0.5679	0.5682	0.5679	0.5674	0.5668	0.5662	0.5662	0.5679	0.5679	0.5679	0.5679	0.5676	0.5674	0.5668
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3303	1.3310	1.3304	1.3290	1.3277	1.3264	1.3264	1.3304	1.3304	1.3303	1.3302	1.3297	1.3291	1.3277
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.2892	0.2894	0.2892	0.2889	0.2887	0.2884	0.2884	0.2892	0.2892	0.2892	0.2892	0.2891	0.2889	0.2887
Sn	0.3907	0.3910	0.3906	0.3900	0.3896	0.3891	0.3889	0.4687	0.4687	0.4687	0.4687	0.4684	0.4680	0.4675
Ce	0.0080	0.0405	0.0810	0.1617	0.2422	0.3225	0.4030	0.0000	0.0008	0.0040	0.0081	0.0404	0.0808	0.1615
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.7540	47.7370	47.7227	47.6937	47.6647	47.6362	47.6020	47.7254	47.7251	47.7239	47.7223	47.7109	47.6964	47.6674
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.4935	10.4995	10.4942	10.4840	10.4736	10.4631	10.4630	10.4943	10.4942	10.4938	10.4933	10.4891	10.4840	10.4736
Mg+Ca+Sr+Ba	2.2604	2.2617	2.2605	2.2584	2.2562	2.2539	2.2539	2.2605	2.2605	2.2605	2.2604	2.2594	2.2584	2.2562
Zr+Ti+La+Nb+Ta+Hf	1.6195	1.6204	1.6196	1.6179	1.6164	1.6148	1.6148	1.6196	1.6196	1.6195	1.6194	1.6188	1.6180	1.6164
Ce/Sn	0.0205	0.1036	0.2074	0.4146	0.6217	0.8288	1.0363	0.0000	0.0017	0.0085	0.0173	0.0863	0.1726	0.3455
Si+Al	37.4739	37.4499	37.4314	37.3943	37.3573	37.3204	37.2744	37.4315	37.4311	37.4296	37.4278	37.4130	37.3944	37.3574
Rank on bubbles	B	B	A	A	A	A	A	E	C	C	C	C	B	B

[0289]
[Table 5]

Component(mass%)	4-56	4-57	4-58	4-59	Com.Ex.4-1	Com.Ex.4-2	Com.Ex.4-3	Com.Ex.4-4	Com.Ex.4-5
Si	31.2178	31.1719	31.1412	31.1417	31.3567	31.3870	31.5231	31.5215	31.1723
Al	6.1028	6.1027	6.0966	6.0967	6.1210	6.1269	6.1446	6.1443	6.1027
Li	1.7942	1.7942	1.7924	1.7924	1.7996	1.8013	1.8065	1.8064	1.7942
Na	8.5427	8.5425	8.5341	8.4600	8.5682	8.5765	8.6012	8.6008	8.5426
K	0.1263	0.1263	0.1262	0.1262	0.1267	0.1268	0.1272	0.1272	0.1263
Mg	0.3927	0.3927	0.3923	0.3923	0.3938	0.3942	0.3954	0.3953	0.3927
Ca	1.2950	1.2950	1.2937	1.2937	1.2989	1.3001	1.3039	1.3038	1.2950
Sr	0.5662	0.5662	0.5657	0.5657	0.5679	0.5685	0.5701	0.5701	0.5662
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.3264	1.3264	1.3251	1.3251	1.3304	1.3317	1.3355	1.3355	1.3264
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.2884	0.2884	0.2881	0.2881	0.2892	0.2895	0.2903	0.2903	0.2884
Sn	0.4668	0.4667	0.4660	0.4659	0.0000	0.1957	0.0079	0.0079	0.7776
Ce	0.2419	0.3224	0.4024	0.4828	0.0000	0.0000	0.0041	0.0081	0.0000
Sb	0.0000	0.0000	0.0000	0.0000	0.4143	0.1264	0.0000	0.0000	0.0000
O	47.6388	47.6046	47.5762	47.5694	47.7333	47.7754	47.8902	47.8888	47.6156
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	10.4632	10.4630	10.4527	10.3786	10.4945	10.5046	10.5349	10.5344	10.4631
Mg+Ca+Sr+Ba	2.2539	2.2539	2.2517	2.2517	2.2606	2.2628	2.2694	2.2692	2.2539
Zr+Ti+La+Nb+Ta+Hf	1.6148	1.6148	1.6132	1.6132	1.6198	1.6212	1.6258	1.6258	1.6148
Ce/Sn	0.5182	0.6908	0.8635	1.0363	—	0.0000	0.5190	—	0.0000
Si+Al	37.3206	37.2746	37.2378	37.2384	37.4777	37.5139	37.6677	37.6658	37.2750
Rank on bubbles	B	B	B	B	G	G	G	G	G

Component		5-1	5-2	5-3	5-4	5-5	5-6	5-7	5-8	5-9	5-10	5-11	5-12	5-13
(mol%)	SiO ₂	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7
	B ₂ O ₃	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	Al ₂ O ₃	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7
	Li ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	Na ₂ O	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	TiO ₂	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
	La ₂ O ₃	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	CaO ₂	0	0.001	0.005	0.01	0.05	0.1	0	0.001	0.005	0.01	0.05	0.1	0.2
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000	1.0000
	SnO ₂ +CaO ₂	0.1000	0.1010	0.1050	0.1100	0.1500	0.2000	0.2000	0.2010	0.2050	0.2100	0.2500	0.3000	0.4000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	SiO ₂ +Al ₂ O ₃	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A	A

Component		5-14	5-15	5-16	5-17	5-18	5-19	5-20	5-21	5-22	5-23	5-24	5-25	5-26
(mol%)	SiO ₂	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7
	B ₂ O ₃	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	Al ₂ O ₃	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7
	Li ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	Na ₂ O	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	TiO ₂	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
	La ₂ O ₃	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.3	0.3	0.3	0.3	0.3
	CeO ₂	0	0.001	0.005	0.01	0.05	0.1	0.2	0.25	0	0.001	0.005	0.01	0.05
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.0000	0.0040	0.0200	0.0400	0.2000	0.4000	0.8000	1.0000	0.0000	0.0033	0.0167	0.0333	0.1667
	SnO ₂ +CeO ₂	0.2500	0.2510	0.2550	0.2600	0.3000	0.3500	0.4500	0.5000	0.3000	0.3010	0.3050	0.3100	0.3500
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	SiO ₂ +Al ₂ O ₃	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4
Rank on bubbles		D	B	A	A	A	A	A	A	D	B	A	A	A

Component		5-27	5-28	5-29	5-30	5-31	5-32	5-33	5-34	5-35	5-36	5-37	5-38	5-39
(mol%)	SiO ₂	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7
	B ₂ O ₃	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	Al ₂ O ₃	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7
	Li ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	Na ₂ O	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	TiO ₂	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
	La ₂ O ₃	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.3	0.3	0.3	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.5
	CeO ₂	0.1	0.2	0.3	0	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.3333	0.6667	1.0000	0.0000	0.0025	0.0125	0.0250	0.1250	0.2500	0.5000	0.7500	1.0000	0.0000
	SnO ₂ +CeO ₂	0.4000	0.5000	0.6000	0.4000	0.4010	0.4050	0.4100	0.4500	0.5000	0.6000	0.7000	0.8000	0.5000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	SiO ₂ +Al ₂ O ₃	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4
Rank on bubbles		A	A	A	D	B	B	A	A	A	A	A	A	E

Component		5-40	5-41	5-42	5-43	5-44	5-45	5-46	5-47	5-48	5-49	5-50	5-51	5-52
(mol%)	SiO ₂	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7
	B ₂ O ₃	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	Al ₂ O ₃	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7
	Li ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	Na ₂ O	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	TiO ₂	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
	La ₂ O ₃	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.6	0.6	0.6	0.6
	CaO ₂	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0.5	0	0.001	0.005	0.01
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0020	0.0100	0.0200	0.1000	0.2000	0.4000	0.6000	0.8000	1.0000	0.0000	0.0017	0.0083	0.0167
	SnO ₂ +CaO ₂	0.5010	0.5050	0.5100	0.5500	0.6000	0.7000	0.8000	0.9000	1.0000	0.6000	0.6010	0.6050	0.6100
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	SiO ₂ +Al ₂ O ₃	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4
Rank on bubbles		C	C	B	B	A	A	A	A	A	E	C	C	C

Component		5-53	5-54	5-55	5-56	5-57	5-58	5-59	Com.Ex.5-1	Com.Ex.5-2	Com.Ex.5-3	Com.Ex.5-4	Com.Ex.5-5
(mol%)	SiO ₂	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7	68.7
	B ₂ O ₃	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
	Al ₂ O ₃	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7	7.7
	Li ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	Na ₂ O	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5	3.5
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	TiO ₂	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
	La ₂ O ₃	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0	0.25	1	0	1
	CeO ₂	0.05	0.1	0.2	0.3	0.4	0.5	0.6	0	0	0	1	1
	Sb ₂ O ₃	0	0	0	0	0	0	0	0.5	0.15	0	0	0
	CeO ₂ /SnO ₂	0.0833	0.1667	0.3333	0.5000	0.6667	0.8333	1.0000	—	0.0000	0.0000	—	1.0000
	SnO ₂ +CeO ₂	0.6500	0.7000	0.8000	0.9000	1.0000	1.1000	1.2000	0.0000	0.2500	1.0000	1.0000	2.0000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	SiO ₂ +Al ₂ O ₃	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4	76.4
Rank on bubbles		C	B	B	B	B	B	B	G	G	G	G	G

Component(mass%)	5-1	5-2	5-3	5-4	5-5	5-6	5-7	5-8	5-9	5-10	5-11	5-12	5-13
Si	30.1647	30.1644	30.1632	30.1617	30.1501	30.1199	30.1200	30.1197	30.1185	30.1170	30.1054	30.0908	30.0618
B	0.6761	0.6761	0.6760	0.6760	0.6757	0.6760	0.6760	0.6760	0.6760	0.6760	0.6757	0.6754	0.6747
Al	6.4960	6.4960	6.4957	6.4954	6.4929	6.4958	6.4958	6.4958	6.4955	6.4952	6.4927	6.4896	6.4833
Li	3.0384	3.0383	3.0382	3.0381	3.0369	3.0383	3.0383	3.0383	3.0381	3.0380	3.0368	3.0353	3.0324
Na	2.5159	2.5159	2.5158	2.5156	2.5147	2.5158	2.5158	2.5158	2.5157	2.5156	2.5146	2.5134	2.5110
K	1.3447	1.3447	1.3447	1.3446	1.3441	1.3447	1.3447	1.3447	1.3446	1.3446	1.3441	1.3434	1.3421
Mg	0.3800	0.3800	0.3800	0.3799	0.3798	0.3800	0.3800	0.3800	0.3799	0.3799	0.3798	0.3796	0.3792
Ca	1.2531	1.2531	1.2531	1.2530	1.2525	1.2531	1.2531	1.2531	1.2530	1.2530	1.2525	1.2519	1.2507
Sr	0.5479	0.5479	0.5479	0.5479	0.5477	0.5479	0.5479	0.5479	0.5479	0.5479	0.5476	0.5474	0.5469
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4262	1.4261	1.4261	1.4260	1.4255	1.4261	1.4261	1.4261	1.4261	1.4260	1.4254	1.4247	1.4234
Ti	1.1228	1.1228	1.1228	1.1227	1.1223	1.1228	1.1228	1.1228	1.1227	1.1227	1.1222	1.1217	1.1206
La	2.1626	2.1625	2.1624	2.1623	2.1615	2.1625	2.1625	2.1625	2.1624	2.1623	2.1614	2.1604	2.1583
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0761	0.0761	0.0761	0.0761	0.0761	0.0761	0.1522	0.1522	0.1522	0.1522	0.1521	0.1520	0.1518
Ce	0.0000	0.0008	0.0039	0.0079	0.0394	0.0789	0.0000	0.0008	0.0039	0.0079	0.0394	0.0788	0.1573
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.7956	48.7953	48.7941	48.7927	48.7810	48.7621	48.7648	48.7645	48.7633	48.7619	48.7502	48.7356	48.7065
Total	100.0001	100.0000	100.0000	99.9999	100.0002	100.0000	100.0000	100.0002	99.9998	100.0002	99.9999	100.0000	100.0000
Li+Na+K	6.8980	6.8989	6.8987	6.8983	6.8957	6.8988	6.8988	6.8988	6.8984	6.8982	6.8955	6.8921	6.8855
Mg+Ca+Sr+Ba	2.1810	2.1810	2.1810	2.1808	2.1800	2.1810	2.1810	2.1810	2.1808	2.1808	2.1799	2.1789	2.1768
Zr+Ti+La+Nb+Ta+Hf	4.7116	4.7114	4.7113	4.7110	4.7093	4.7114	4.7114	4.7114	4.7112	4.7110	4.7090	4.7088	4.7023
Ce/Sn	0.0000	0.0105	0.0512	0.1038	0.5177	1.0368	0.0000	0.0053	0.0256	0.0519	0.2590	0.5184	1.0362
Sn+Ce	0.0761	0.0769	0.0800	0.0840	0.1155	0.1550	0.1522	0.1530	0.1561	0.1601	0.1915	0.2308	0.3091
Si+Al	36.6607	36.6604	36.6589	36.6571	36.6430	36.6157	36.6158	36.6155	36.6140	36.6122	36.5981	36.5804	36.5451
Rank on bubbles	D	C	B	B	B	B	D	B	A	A	A	A	A

Component(mass%)	5-14	5-15	5-16	5-17	5-18	5-19	5-20	5-21	5-22	5-23	5-24	5-25	5-26	5-27
Si	30.1054	30.1051	30.1040	30.1025	30.0909	30.0763	30.0473	30.0329	30.0909	30.0906	30.0895	30.0880	30.0764	30.0619
B	0.6757	0.6757	0.6757	0.6757	0.6754	0.6751	0.6744	0.6741	0.6754	0.6754	0.6754	0.6753	0.6751	0.6747
Al	6.4927	6.4926	6.4924	6.4921	6.4898	6.4884	6.4802	6.4771	6.4896	6.4895	6.4893	6.4890	6.4864	6.4833
Li	3.0368	3.0368	3.0367	3.0365	3.0353	3.0339	3.0310	3.0295	3.0354	3.0353	3.0352	3.0351	3.0339	3.0324
Na	2.5146	2.5146	2.5145	2.5144	2.5134	2.5122	2.5098	2.5086	2.5134	2.5134	2.5133	2.5132	2.5122	2.5110
K	1.3441	1.3440	1.3440	1.3439	1.3434	1.3428	1.3415	1.3408	1.3434	1.3434	1.3433	1.3433	1.3428	1.3421
Mg	0.3798	0.3798	0.3798	0.3797	0.3796	0.3794	0.3790	0.3789	0.3786	0.3786	0.3786	0.3786	0.3784	0.3782
Ca	1.2525	1.2525	1.2524	1.2524	1.2519	1.2513	1.2501	1.2495	1.2519	1.2519	1.2518	1.2518	1.2513	1.2507
Sr	0.5476	0.5476	0.5476	0.5476	0.5474	0.5471	0.5466	0.5463	0.5474	0.5474	0.5474	0.5473	0.5471	0.5469
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4254	1.4254	1.4254	1.4253	1.4247	1.4241	1.4227	1.4220	1.4247	1.4247	1.4247	1.4246	1.4241	1.4234
Ti	1.1222	1.1222	1.1222	1.1221	1.1217	1.1212	1.1201	1.1195	1.1217	1.1217	1.1216	1.1216	1.1212	1.1206
La	2.1615	2.1614	2.1613	2.1612	2.1604	2.1594	2.1573	2.1562	2.1604	2.1604	2.1603	2.1602	2.1594	2.1583
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.1901	0.1901	0.1901	0.1901	0.1900	0.1899	0.1896	0.1895	0.2280	0.2280	0.2280	0.2280	0.2278	0.2277
Ce	0.0000	0.0008	0.0039	0.0078	0.0394	0.0787	0.1572	0.1964	0.0000	0.0008	0.0039	0.0079	0.0393	0.0786
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.7515	48.7512	48.7500	48.7486	48.7369	48.7224	48.6833	48.6788	48.7382	48.7379	48.7368	48.7353	48.7237	48.7081
Total	99.9999	99.9998	100.0000	100.0000	100.0000	100.0002	100.0001	100.0001	100.0000	100.0000	100.0001	100.0002	100.0001	99.9999
Li+Na+K	6.8955	6.8954	6.8952	6.8948	6.8921	6.8889	6.8823	6.8788	6.8922	6.8921	6.8918	6.8916	6.8889	6.8855
Mg+Ca+Sr+Ba	2.1799	2.1799	2.1798	2.1797	2.1789	2.1778	2.1757	2.1747	2.1789	2.1789	2.1788	2.1787	2.1778	2.1768
Zr+Ti+La+Nb+Ta+Hf	4.7091	4.7090	4.7089	4.7088	4.7088	4.7047	4.7001	4.6977	4.7088	4.7088	4.7086	4.7084	4.7047	4.7023
Ce/Sn	0.0000	0.0042	0.0205	0.0416	0.2074	0.4144	0.8291	1.0364	0.0000	0.0035	0.0171	0.0346	0.1725	0.3452
Sn+Ca	0.1901	0.1909	0.1940	0.1980	0.2294	0.2686	0.3468	0.3859	0.2280	0.2288	0.2319	0.2359	0.2671	0.3063
Si+Al	36.5981	36.5977	36.5964	36.5948	36.5805	36.5627	36.5275	36.5100	36.5805	36.5801	36.5788	36.5770	36.5628	36.5452
Rank on bubbles	D	B	A	A	A	A	A	A	D	B	A	A	A	A

Component(mass%)	5-42	5-43	5-44	5-45	5-46	5-47	5-48	5-49	5-50	5-51	5-52	5-53	5-54	5-55
Si	30.0302	30.0030	29.9885	29.9597	29.9310	29.9023	29.8718	29.9886	29.9883	29.9872	29.9857	29.9742	29.9598	29.9310
B	0.6740	0.6744	0.6741	0.6734	0.6728	0.6721	0.6724	0.6741	0.6741	0.6740	0.6740	0.6738	0.6734	0.6728
Al	6.4765	6.4801	6.4769	6.4707	6.4645	6.4583	6.4612	6.4770	6.4769	6.4766	6.4763	6.4738	6.4707	6.4645
Li	3.0282	3.0309	3.0284	3.0266	3.0236	3.0207	3.0005	3.0294	3.0294	3.0293	3.0292	3.0280	3.0285	3.0236
Na	2.5083	2.5097	2.5085	2.5061	2.5037	2.5013	2.5024	2.5085	2.5085	2.5084	2.5083	2.5073	2.5061	2.5037
K	1.3407	1.3414	1.3408	1.3395	1.3382	1.3369	1.3375	1.3408	1.3408	1.3407	1.3407	1.3402	1.3395	1.3382
Mg	0.3788	0.3790	0.3789	0.3785	0.3781	0.3778	0.3779	0.3789	0.3789	0.3788	0.3788	0.3787	0.3785	0.3781
Ca	1.2494	1.2500	1.2494	1.2482	1.2471	1.2459	1.2464	1.2495	1.2494	1.2494	1.2493	1.2489	1.2483	1.2471
Sr	0.5463	0.5466	0.5463	0.5458	0.5453	0.5447	0.5450	0.5463	0.5463	0.5463	0.5463	0.5461	0.5458	0.5453
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4219	1.4227	1.4220	1.4206	1.4192	1.4179	1.4185	1.4220	1.4220	1.4219	1.4218	1.4213	1.4206	1.4192
Ti	1.1194	1.1200	1.1195	1.1184	1.1174	1.1163	1.1168	1.1195	1.1195	1.1195	1.1194	1.1190	1.1184	1.1174
La	2.1560	2.1572	2.1562	2.1541	2.1521	2.1500	2.1510	2.1562	2.1562	2.1561	2.1560	2.1552	2.1541	2.1521
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.3789	0.3791	0.3788	0.3783	0.3778	0.3773	0.3773	0.4546	0.4545	0.4545	0.4545	0.4543	0.4540	0.4534
Ce	0.0079	0.0393	0.0785	0.1568	0.2349	0.3128	0.3910	0.0000	0.0008	0.0039	0.0078	0.0392	0.0784	0.1566
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.6825	48.6666	48.6521	48.6232	48.5944	48.5657	48.5303	48.6547	48.6544	48.6533	48.6518	48.6403	48.6258	48.5970
Total	100.0000	100.0000	99.9999	99.9998	100.0001	100.0000	100.0000	100.0001	100.0000	99.9999	99.9999	100.0003	99.9999	100.0000
LH+Na+K	6.8782	6.8820	6.8787	6.8721	6.8655	6.8589	6.8404	6.8787	6.8787	6.8784	6.8782	6.8755	6.8721	6.8655
Mg+Ca+Sr+Ba	2.1745	2.1756	2.1746	2.1725	2.1705	2.1684	2.1693	2.1747	2.1746	2.1745	2.1744	2.1737	2.1726	2.1705
Zr+Ti+La+Nb+Ta+Hf	4.6973	4.6999	4.6977	4.6931	4.6887	4.6842	4.6883	4.6977	4.6977	4.6975	4.6972	4.6955	4.6931	4.6887
Ce/Sn	0.0208	0.1037	0.2072	0.4145	0.6218	0.8290	1.0363	0.0000	0.0018	0.0086	0.0172	0.0863	0.1727	0.3454
Sn+Ce	0.3868	0.4184	0.4573	0.5351	0.6127	0.6901	0.7683	0.4546	0.4553	0.4584	0.4623	0.4935	0.5324	0.6100
Si+Al	36.5067	36.4831	36.4654	36.4304	36.3955	36.3606	36.3330	36.4656	36.4652	36.4638	36.4620	36.4480	36.4305	36.3955
Rank on bubbles	B	B	A	A	A	A	A	E	C	C	C	C	B	B

[0290]
[Table 6]

Component(mass%)	5-56	5-57	5-58	5-59	Com.Ex.5-1	Com.Ex.5-2	Com.Ex.5-3	Com.Ex.5-4	Com.Ex.5-5
Si	29.9024	29.8719	29.8434	29.8149	30.0329	30.0616	30.1895	30.1880	29.8723
B	0.6721	0.6724	0.6718	0.6712	0.6741	0.6747	0.6766	0.6766	0.6724
Al	6.4583	6.4612	6.4550	6.4488	6.4771	6.4833	6.5014	6.5010	6.4613
Li	3.0207	3.0005	2.9976	2.9948	3.0295	3.0324	3.0409	3.0407	3.0005
Na	2.5013	2.5024	2.5000	2.4976	2.5086	2.5110	2.5180	2.5178	2.5024
K	1.3389	1.3375	1.3383	1.3350	1.3408	1.3421	1.3459	1.3458	1.3376
Mg	0.3778	0.3779	0.3776	0.3772	0.3789	0.3792	0.3803	0.3803	0.3779
Ca	1.2459	1.2464	1.2452	1.2440	1.2495	1.2507	1.2542	1.2541	1.2464
Sr	0.5447	0.5450	0.5445	0.5439	0.5463	0.5469	0.5484	0.5484	0.5450
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	1.4179	1.4185	1.4172	1.4168	1.4220	1.4234	1.4273	1.4273	1.4185
Ti	1.1163	1.1168	1.1157	1.1147	1.1195	1.1206	1.1237	1.1237	1.1168
La	2.1500	2.1510	2.1489	2.1468	2.1582	2.1583	2.1643	2.1642	2.1510
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4528	0.4528	0.4522	0.4516	0.0000	0.1898	0.0078	0.0076	0.7545
Ce	0.2346	0.3128	0.3905	0.4680	0.0000	0.0000	0.0039	0.0079	0.0000
Sb	0.0000	0.0000	0.0000	0.0000	0.4023	0.1216	0.0000	0.0000	0.0000
O	48.5883	48.5329	48.5043	48.4757	48.8623	48.7045	48.8181	48.8166	48.5433
Total	100.0000	100.0000	100.0002	100.0000	100.0000	100.0001	100.0001	100.0000	99.9999
Li+Na+K	6.8589	6.8404	6.8339	6.8274	6.8789	6.8855	6.9048	6.9043	6.8405
Mg+Ca+Sr+Ba	2.1884	2.1693	2.1673	2.1651	2.1747	2.1768	2.1829	2.1828	2.1693
Zr+Ti+La+Nb+Ta+Hf	4.6842	4.6863	4.6818	4.6773	4.6977	4.7023	4.7153	4.7152	4.6863
Ce/Sn	0.5181	0.6908	0.8636	1.0363	-	0.0000	0.5132	-	0.0000
Sn+Ce	0.6874	0.7656	0.8427	0.9196	0.0000	0.1898	0.0115	0.0155	0.7545
Si+Al	36.3607	36.3331	36.2984	36.2637	36.5100	36.5449	36.6909	36.6890	36.3336
Rank on bubbles	B	B	B	B	G	G	G	G	G

Component		6-1	6-2	6-3	6-4	6-5	6-6	6-7	6-8	6-9	6-10	6-11	6-12
(mol%)	SiO ₂	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6
	B ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	P ₂ O ₅	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	Li ₂ O	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3
	Na ₂ O	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	TiO ₂	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6
	La ₂ O ₃	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Nb ₂ O ₅	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.100	0.100	0.100	0.100	0.100	0.100	0.200	0.200	0.200	0.200	0.200	0.200
	CeO ₂	0.000	0.001	0.005	0.010	0.050	0.100	0.000	0.001	0.005	0.010	0.050	0.100
	Sb ₂ O ₃	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
	CeO ₂ /SnO ₂	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000
	SnO ₂ +CeO ₂	0.100	0.101	0.105	0.110	0.150	0.200	0.200	0.201	0.205	0.210	0.250	0.300
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8
	SiO ₂ +Al ₂ O ₃	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A

Component		6-25	6-26	6-27	6-28	6-29	6-30	6-31	6-32	6-33	6-34	6-35	6-36
(mol%)	SiO ₂	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6
	B ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	P ₂ O ₅	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	Li ₂ O	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3
	Na ₂ O	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	TiO ₂	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6
	La ₂ O ₃	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Nb ₂ O ₅	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.300	0.300	0.300	0.300	0.300	0.400	0.400	0.400	0.400	0.400	0.400	0.400
	CeO ₂	0.010	0.050	0.100	0.200	0.300	0.000	0.001	0.005	0.010	0.050	0.100	0.200
	Sb ₂ O ₃	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
	CeO ₂ /SnO ₂	0.0333	0.1667	0.3333	0.6667	1.0000	0.0000	0.0025	0.0125	0.0250	0.1250	0.2500	0.5000
	SnO ₂ +CeO ₂	0.310	0.350	0.400	0.500	0.600	0.400	0.401	0.405	0.410	0.450	0.500	0.600
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8
	SiO ₂ +Al ₂ O ₃	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4
Rank on bubbles		A	A	A	A	A	D	B	B	A	A	A	A

Component		6-37	6-38	6-39	6-40	6-41	6-42	6-43	6-44	6-45	6-46	6-47	6-48
(mol%)	SiO ₂	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6
	B ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	P ₂ O ₅	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	Li ₂ O	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3
	Na ₂ O	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	TiO ₂	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6
	La ₂ O ₃	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Nb ₂ O ₅	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.400	0.400	0.500	0.500	0.500	0.500	0.500	0.500	0.500	0.500	0.500	0.500
	CeO ₂	0.300	0.400	0.000	0.001	0.005	0.010	0.050	0.100	0.200	0.300	0.400	0.500
	Sb ₂ O ₃	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
	CaO ₂ /SnO ₂	0.7500	1.0000	0.0000	0.0020	0.0100	0.0200	0.1000	0.2000	0.4000	0.6000	0.8000	1.0000
	SnO ₂ +CeO ₂	0.700	0.800	0.500	0.501	0.505	0.510	0.550	0.600	0.700	0.800	0.900	1.000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8
	SiO ₂ +Al ₂ O ₃	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4
Rank on bubbles		A	A	E	C	C	B	B	A	A	A	A	A

Component		6-49	6-50	6-51	6-52	6-53	6-54	6-55	6-56	6-57	6-58	6-59	Com.Ex.6-1
(mol%)	SiO ₂	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6	68.6
	B ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	P ₂ O ₅	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	Li ₂ O	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3	15.3
	Na ₂ O	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	TiO ₂	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6
	La ₂ O ₃	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Nb ₂ O ₅	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.600	0.600	0.600	0.600	0.600	0.600	0.600	0.600	0.600	0.600	0.600	0.000
	CaO ₂	0.000	0.001	0.005	0.010	0.050	0.100	0.200	0.300	0.400	0.500	0.600	0.000
	Sb ₂ O ₃	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.500
	CaO ₂ /SnO ₂	0.0000	0.0017	0.0083	0.0167	0.0833	0.1667	0.3333	0.5000	0.6667	0.8333	1.0000	-
	SnO ₂ +CaO ₂	0.600	0.601	0.605	0.610	0.650	0.700	0.800	0.900	1.000	1.100	1.200	0.000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8
	SiO ₂ +Al ₂ O ₃	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4	77.4
Rank on bubbles		E	C	C	C	C	B	B	B	B	B	B	Q

Component		Com.Ex.6-2	Com.Ex.6-3	Com.Ex.6-4	Com.Ex.6-5
(mol%)	SiO ₂	88.6	88.6	88.6	88.6
	B ₂ O ₃	0.0	0.0	0.0	0.0
	Al ₂ O ₃	8.8	8.8	8.8	8.8
	P ₂ O ₅	0.2	0.2	0.2	0.2
	Li ₂ O	15.3	15.3	15.3	15.3
	Na ₂ O	3.2	3.2	3.2	3.2
	K ₂ O	1.1	1.1	1.1	1.1
	MgO	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0
	ZrO ₂	0.0	0.0	0.0	0.0
	TiO ₂	1.6	1.6	1.6	1.6
	La ₂ O ₃	0.8	0.8	0.8	0.8
	Nb ₂ O ₅	0.6	0.6	0.6	0.6
	Ta ₂ O ₅	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.250	1.000	0.000	1.000
	CeO ₂	0.000	0.000	1.000	1.000
	Sb ₂ O ₃	0.150	0.000	0.000	0.000
	CeO ₂ /SnO ₂	0.0000	0.0000	—	1.0000
	SnO ₂ +CeO ₂	0.250	1.000	1.000	2.000
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	19.6	19.6	19.6	19.6
	MgO+CaO+SrO+BaO	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.8	2.8	2.8	2.8
	SiO ₂ +Al ₂ O ₃	77.4	77.4	77.4	77.4
Rank on bubbles		G	G	G	G

Component(mass%)	6-1	6-2	6-3	6-4	6-5	6-6	6-7	6-8	6-9	6-10	6-11	6-12
Si	30.6067	30.6063	30.6051	30.6036	30.5914	30.5607	30.5608	30.5605	30.5582	30.5577	30.5455	30.5303
B	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Al	7.5438	7.5437	7.5434	7.5430	7.5400	7.5434	7.5435	7.5434	7.5431	7.5427	7.5397	7.5359
P	0.1968	0.1968	0.1968	0.1968	0.1967	0.1968	0.1968	0.1968	0.1968	0.1968	0.1967	0.1966
Li	3.3741	3.3740	3.3739	3.3737	3.3724	3.3739	3.3739	3.3739	3.3738	3.3736	3.3722	3.3706
Na	2.3374	2.3373	2.3372	2.3371	2.3362	2.3372	2.3373	2.3372	2.3371	2.3370	2.3361	2.3349
K	1.3664	1.3664	1.3664	1.3663	1.3658	1.3664	1.3664	1.3664	1.3663	1.3662	1.3657	1.3650
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ti	1.2170	1.2170	1.2169	1.2169	1.2164	1.2169	1.2169	1.2169	1.2169	1.2168	1.2163	1.2157
La	2.6369	2.6369	2.6368	2.6367	2.6356	2.6368	2.6368	2.6368	2.6367	2.6366	2.6355	2.6342
Nb	1.7711	1.7711	1.7710	1.7709	1.7702	1.7710	1.7710	1.7710	1.7709	1.7708	1.7701	1.7692
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0785	0.0785	0.0785	0.0785	0.0785	0.0785	0.1570	0.1570	0.1570	0.1569	0.1569	0.1568
Ce	0.0000	0.0008	0.0041	0.0081	0.0407	0.0813	0.0000	0.0008	0.0041	0.0081	0.0408	0.0812
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.8713	48.8712	48.8699	48.8684	48.8561	48.8371	48.8396	48.8393	48.8381	48.8368	48.8247	48.8096
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	7.0779	7.0777	7.0775	7.0771	7.0744	7.0775	7.0776	7.0775	7.0772	7.0768	7.0740	7.0705
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	5.8250	5.8250	5.8247	5.8245	5.8222	5.8247	5.8247	5.8247	5.8245	5.8242	5.8219	5.8191
Ce/Sn	0.0000	0.0102	0.0522	0.1032	0.5185	1.0357	0.0000	0.0051	0.0261	0.0516	0.2588	0.5179
Sn+Ce	0.0785	0.0793	0.0826	0.0865	0.1192	0.1598	0.1570	0.1578	0.1611	0.1650	0.1975	0.2380
SPAI	38.1505	38.1500	38.1485	38.1466	38.1314	38.1041	38.1043	38.1039	38.1023	38.1004	38.0852	38.0662
Rank on bubbles	D	C	B	B	B	B	D	B	A	A	A	A

Component(mass%)	6-13	6-14	6-15	6-16	6-17	6-18	6-19	6-20	6-21	6-22	6-23	6-24	6-25
Si	30.4999	30.5456	30.5453	30.5440	30.5425	30.5303	30.5151	30.4848	30.4697	30.5304	30.5301	30.5289	30.5273
B	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Al	7.5284	7.5397	7.5396	7.5393	7.5390	7.5360	7.5322	7.5247	7.5210	7.5360	7.5359	7.5356	7.5352
P	0.1964	0.1967	0.1967	0.1967	0.1967	0.1966	0.1965	0.1963	0.1962	0.1966	0.1966	0.1966	0.1966
Li	3.3672	3.3722	3.3722	3.3721	3.3719	3.3706	3.3689	3.3655	3.3639	3.3706	3.3705	3.3704	3.3702
Na	2.3326	2.3361	2.3361	2.3360	2.3359	2.3349	2.3338	2.3314	2.3303	2.3349	2.3349	2.3348	2.3347
K	1.3837	1.3857	1.3857	1.3856	1.3856	1.3850	1.3843	1.3830	1.3823	1.3850	1.3850	1.3850	1.3849
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ti	1.2145	1.2163	1.2163	1.2163	1.2162	1.2157	1.2151	1.2139	1.2133	1.2157	1.2157	1.2157	1.2156
La	2.6316	2.6355	2.6355	2.6354	2.6352	2.6342	2.6329	2.6303	2.6290	2.6342	2.6342	2.6341	2.6339
Nb	1.7675	1.7701	1.7701	1.7700	1.7699	1.7692	1.7684	1.7666	1.7657	1.7692	1.7692	1.7692	1.7691
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.1565	0.1961	0.1961	0.1961	0.1960	0.1859	0.1958	0.1955	0.1954	0.2351	0.2351	0.2351	0.2351
Ce	0.1622	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1621	0.2025	0.0000	0.0008	0.0041	0.0081
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.7795	48.8260	48.8256	48.8244	48.8230	48.8110	48.7958	48.7859	48.7507	48.8123	48.8120	48.8105	48.8093
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	7.0635	7.0740	7.0740	7.0737	7.0734	7.0705	7.0670	7.0599	7.0565	7.0705	7.0704	7.0702	7.0698
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	5.8136	5.8219	5.8219	5.8217	5.8213	5.8191	5.8164	5.8108	5.8080	5.8191	5.8191	5.8190	5.8186
Ce/Sn	1.0364	0.0000	0.0041	0.0209	0.0413	0.2072	0.4147	0.8292	1.0363	0.0000	0.0034	0.0174	0.0345
Sn+Ce	0.3187	0.1961	0.1969	0.2002	0.2041	0.2365	0.2770	0.3576	0.3979	0.2351	0.2359	0.2392	0.2432
Si+Al	38.0283	38.0853	38.0849	38.0833	38.0815	38.0663	38.0473	38.0095	37.9907	38.0684	38.0660	38.0645	38.0625
Rank on bubbles	A	D	B	A	A	A	A	A	A	D	B	A	A

Component(mass%)	6-26	6-27	6-28	6-29	6-30	6-31	6-32	6-33	6-34	6-35	6-36	6-37	6-38
Si	30.5152	30.5000	30.4697	30.4240	30.5001	30.4998	30.4988	30.4971	30.4849	30.4698	30.4241	30.3939	30.3839
B	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Al	7.5322	7.5285	7.5210	7.5207	7.5285	7.5284	7.5281	7.5277	7.5247	7.5210	7.5207	7.5132	7.5058
P	0.1965	0.1964	0.1962	0.1962	0.1964	0.1964	0.1964	0.1964	0.1963	0.1962	0.1962	0.1980	0.1958
Li	3.3689	3.3672	3.3639	3.3637	3.3672	3.3672	3.3671	3.3669	3.3655	3.3639	3.3637	3.3604	3.3570
Na	2.3338	2.3326	2.3303	2.3302	2.3326	2.3326	2.3325	2.3324	2.3315	2.3303	2.3302	2.3279	2.3256
K	1.3643	1.3637	1.3623	1.3623	1.3637	1.3637	1.3636	1.3635	1.3630	1.3623	1.3623	1.3609	1.3598
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ti	1.2151	1.2145	1.2133	1.2133	1.2145	1.2145	1.2145	1.2144	1.2139	1.2133	1.2133	1.2121	1.2109
La	2.6329	2.6316	2.6290	2.6288	2.6316	2.6316	2.6314	2.6313	2.6303	2.6290	2.6289	2.6283	2.6237
Nb	1.7684	1.7675	1.7657	1.7656	1.7675	1.7675	1.7674	1.7673	1.7666	1.7657	1.7657	1.7639	1.7622
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.2350	0.2348	0.2345	0.2344	0.3130	0.3130	0.3130	0.3130	0.3128	0.3126	0.3125	0.3121	0.3116
Ce	0.0406	0.0811	0.1620	0.2429	0.0000	0.0008	0.0041	0.0081	0.0405	0.0810	0.1619	0.2425	0.3229
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.7971	48.7821	48.7521	48.7178	48.7849	48.7845	48.7833	48.7819	48.7700	48.7549	48.7205	48.6908	48.6610
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	7.0670	7.0635	7.0565	7.0562	7.0635	7.0635	7.0632	7.0628	7.0600	7.0565	7.0562	7.0492	7.0422
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	5.6164	5.6136	5.6080	5.6078	5.6136	5.6136	5.6133	5.6130	5.6108	5.6080	5.6079	5.6023	5.5968
Ce/Sn	0.1728	0.3454	0.6908	1.0363	0.0000	0.0026	0.0131	0.0259	0.1295	0.2591	0.5181	0.7770	1.0363
Sn+Ce	0.2756	0.3159	0.3965	0.4773	0.3130	0.3138	0.3171	0.3211	0.3533	0.3936	0.4744	0.5546	0.6345
Si+Al	38.0474	38.0285	37.9907	37.9447	38.0286	38.0282	38.0267	38.0248	38.0096	37.9908	37.9448	37.9071	37.8697
Rank on bubbles	A	A	A	A	D	B	B	A	A	A	A	A	A

Component(mass%)	6-39	6-40	6-41	6-42	6-43	6-44	6-45	6-46	6-47	6-48	6-49	6-50	6-51
Si	30.4699	30.4696	30.4684	30.4669	30.4393	30.4242	30.3940	30.3639	30.3483	30.3028	30.4242	30.4239	30.4227
B	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Al	7.5210	7.5210	7.5207	7.5203	7.5245	7.5207	7.5133	7.5058	7.5020	7.5017	7.5207	7.5207	7.5204
P	0.1962	0.1962	0.1962	0.1962	0.1963	0.1962	0.1960	0.1958	0.1957	0.1957	0.1962	0.1962	0.1962
Li	3.3639	3.3639	3.3637	3.3636	3.3654	3.3637	3.3604	3.3571	3.3334	3.3333	3.3638	3.3637	3.3636
Na	2.3303	2.3303	2.3302	2.3301	2.3314	2.3302	2.3279	2.3256	2.3244	2.3243	2.3302	2.3302	2.3301
K	1.3623	1.3623	1.3623	1.3622	1.3629	1.3623	1.3609	1.3596	1.3589	1.3588	1.3623	1.3623	1.3622
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ti	1.2133	1.2133	1.2133	1.2132	1.2139	1.2133	1.2121	1.2109	1.2102	1.2102	1.2133	1.2133	1.2132
La	2.6290	2.6289	2.6288	2.6287	2.6302	2.6289	2.6263	2.6237	2.6223	2.6222	2.6289	2.6288	2.6287
Nb	1.7657	1.7657	1.7656	1.7656	1.7665	1.7657	1.7639	1.7622	1.7613	1.7612	1.7657	1.7656	1.7656
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.3908	0.3908	0.3907	0.3907	0.3909	0.3906	0.3901	0.3895	0.3892	0.3890	0.4687	0.4687	0.4687
Ce	0.0000	0.0008	0.0040	0.0080	0.0405	0.0809	0.1617	0.2422	0.3226	0.4031	0.0000	0.0008	0.0040
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.7576	48.7572	48.7561	48.7545	48.7382	48.7233	48.6934	48.6637	48.6317	48.5977	48.7260	48.7258	48.7246
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	7.0565	7.0565	7.0562	7.0559	7.0597	7.0562	7.0492	7.0423	7.0167	7.0164	7.0563	7.0562	7.0559
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	5.6080	5.6079	5.6077	5.6075	5.6106	5.6079	5.6023	5.5968	5.5938	5.5938	5.6079	5.6077	5.6075
Ce/Sn	0.0000	0.0020	0.0102	0.0205	0.1038	0.2071	0.4145	0.6218	0.8289	1.0362	0.0000	0.0017	0.0085
Sn+Ce	0.3908	0.3916	0.3947	0.3987	0.4314	0.4715	0.5518	0.6317	0.7118	0.7921	0.4687	0.4695	0.4727
Si+Al	37.9909	37.9906	37.9891	37.9872	37.9838	37.9449	37.9073	37.8697	37.8503	37.8045	37.9449	37.9446	37.9431
Rank on bubbles	E	C	C	B	B	A	A	A	A	A	E	C	C

Component(mass%)	6-52	6-53	6-54	6-55	6-56	6-57	6-58	6-59	Com.Ex.6-1	Com.Ex.6-2	Com.Ex.6-3	Com.Ex.6-4	Com.Ex.6-5
Si	30.4212	30.4092	30.3941	30.3840	30.3484	30.3029	30.2730	30.2432	30.4691	30.5004	30.5326	30.6311	30.3032
B	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Al	7.5200	7.5170	7.5133	7.5059	7.5020	7.5017	7.4943	7.4869	7.5208	7.5286	7.5502	7.5498	7.5018
P	0.1962	0.1961	0.1960	0.1958	0.1957	0.1957	0.1955	0.1953	0.1962	0.1964	0.1970	0.1970	0.1957
Li	3.3634	3.3621	3.3604	3.3571	3.3334	3.3333	3.3300	3.3268	3.3638	3.3673	3.3769	3.3768	3.3334
Na	2.3300	2.3291	2.3279	2.3256	2.3244	2.3243	2.3220	2.3197	2.3302	2.3326	2.3393	2.3392	2.3243
K	1.3621	1.3616	1.3609	1.3596	1.3589	1.3588	1.3575	1.3561	1.3623	1.3637	1.3676	1.3675	1.3588
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ti	1.2131	1.2127	1.2121	1.2109	1.2102	1.2102	1.2090	1.2078	1.2133	1.2145	1.2180	1.2180	1.2102
La	2.6286	2.6276	2.6263	2.6237	2.6223	2.6222	2.6196	2.6171	2.6289	2.6316	2.6392	2.6390	2.6223
Nb	1.7655	1.7648	1.7639	1.7622	1.7613	1.7612	1.7595	1.7577	1.7657	1.7675	1.7726	1.7725	1.7612
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4686	0.4684	0.4681	0.4674	0.4670	0.4668	0.4662	0.4656	0.0000	0.1957	0.0079	0.0079	0.7779
Ce	0.0081	0.0404	0.0808	0.1615	0.2420	0.3225	0.4026	0.4824	0.0000	0.0000	0.0041	0.0081	0.0000
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.4165	0.1235	0.0000	0.0000	0.0000
O	48.7232	48.7110	48.6962	48.6863	48.6344	48.6004	48.5708	48.5414	48.7332	48.7782	48.8946	48.8931	48.6112
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	7.0555	7.0528	7.0492	7.0423	7.0167	7.0164	7.0095	7.0026	7.0563	7.0636	7.0838	7.0835	7.0165
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	5.6072	5.6051	5.6023	5.5968	5.5938	5.5936	5.5881	5.5826	5.6079	5.6136	5.6298	5.6295	5.5937
Ce/Sn	0.0173	0.0863	0.1726	0.3455	0.5182	0.6909	0.8636	1.0361	-	0.0000	0.5190	-	0.0000
Sn+Ce	0.4767	0.5088	0.5489	0.6289	0.7090	0.7893	0.8688	0.9480	0.0000	0.1957	0.0120	0.0160	0.7779
Si+Al	37.9412	37.9262	37.9074	37.8699	37.8504	37.8046	37.7873	37.7301	37.9899	38.0290	38.1828	38.1809	37.8050
Rank on bubbles	C	C	B	B	B	B	B	B	G	G	G	G	G

[0291]

[Table 7]

Component		7-1	7-2	7-3	7-4	7-5	7-6	7-7	7-8	7-9	7-10	7-11	7-12	7-13
(mol%)	SiO ₂	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5
	Al ₂ O ₃	8.6	8.6	8.6	8.6	8.6	8.6	8.6	8.6	8.6	8.6	8.6	8.6	8.6
	Li ₂ O	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
	Na ₂ O	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4	10.4
	K ₂ O	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	MgO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	TiO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	La ₂ O ₃	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Based on glass components (mass%)	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
	SnO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	CaO ₂	0	0.001	0.005	0.01	0.05	0.1	0	0.001	0.005	0.01	0.05	0.1	0.2
	SS203	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000	1.0000
(mol%)	SnO ₂ +CaO ₂	0.1	0.101	0.105	0.11	0.15	0.2	0.2	0.201	0.205	0.21	0.25	0.3	0.4
	Li ₂ O+Na ₂ O+K ₂ O	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9
	MeO+CaO+SrO+BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
	SiO ₂ +Al ₂ O ₃	74.1	74.1	74.1	74.1	74.1	74.1	74.1	74.1	74.1	74.1	74.1	74.1	74.1
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A	A
Acid etching rate (nm/min)		3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9
Alkaline etching rate (nm/min)		0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01

[illegible]

[illegible]

[illegible]

Component(mass%)	7-1	7-2	7-3	7-4	7-5	7-6	7-7	7-8	7-9	7-10	7-11	7-12	7-13
Si	30.5534	30.5531	30.5519	30.5504	30.5382	30.5230	30.5231	30.5228	30.5215	30.5200	30.5078	30.4927	30.4449
Al	4.5232	4.5231	4.5229	4.5227	4.5209	4.5187	4.5187	4.5186	4.5184	4.5182	4.5164	4.5142	4.5145
Li	5.8179	5.8179	5.8176	5.8173	5.8150	5.8120	5.8120	5.8120	5.8118	5.8116	5.8092	5.8064	5.8068
Na	7.7080	7.7079	7.7076	7.7072	7.7041	7.7003	7.7003	7.7002	7.6999	7.6995	7.6985	7.6926	7.6932
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	2.2776	2.2776	2.2775	2.2774	2.2765	2.2754	2.2754	2.2754	2.2753	2.2751	2.2742	2.2731	2.2733
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0785	0.0785	0.0785	0.0785	0.0784	0.0784	0.1568	0.1568	0.1567	0.1567	0.1567	0.1565	0.1565
Ce	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.0000	0.0008	0.0041	0.0081	0.0406	0.0811	0.1622
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	49.0414	49.0411	49.0399	49.0384	49.0283	49.0110	49.0137	49.0134	49.0123	49.0108	48.9986	48.9834	48.9486
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	13.5259	13.5258	13.5252	13.5245	13.5191	13.5123	13.5123	13.5122	13.5117	13.5111	13.5057	13.4990	13.5000
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	2.2776	2.2776	2.2775	2.2774	2.2765	2.2754	2.2754	2.2754	2.2753	2.2751	2.2742	2.2731	2.2733
Ce/Sn	0.0000	0.0102	0.0522	0.1032	0.5179	1.0357	0.0000	0.0051	0.0262	0.0517	0.2591	0.5182	1.0364
Sn+Ce	0.0785	0.0793	0.0826	0.0866	0.1190	0.1596	0.1568	0.1576	0.1608	0.1648	0.1973	0.2376	0.3187</

Component(mass%)	7-42	7-43	7-44	7-45	7-46	7-47	7-48	7-49	7-50	7-51	7-52	7-53	7-54	7-55
Si	30.4281	30.4160	30.4009	30.3708	30.3408	30.2933	30.2634	30.4010	30.4007	30.3995	30.3980	30.3859	30.3708	30.3409
Al	4.5120	4.5102	4.5080	4.5035	4.4991	4.4894	4.4950	4.5080	4.5079	4.5078	4.5075	4.5058	4.5035	4.4991
Li	5.7789	5.7766	5.7737	5.7680	5.7623	5.7627	5.7571	5.7737	5.7737	5.7734	5.7732	5.7709	5.7680	5.7623
Na	7.6890	7.6859	7.6821	7.6745	7.6669	7.6675	7.6599	7.6821	7.6820	7.6817	7.6814	7.6783	7.6745	7.6669
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	2.2720	2.2711	2.2700	2.2677	2.2655	2.2657	2.2634	2.2700	2.2700	2.2699	2.2698	2.2689	2.2678	2.2655
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.3909	0.3907	0.3904	0.3899	0.3894	0.3893	0.3888	0.4685	0.4685	0.4684	0.4684	0.4682	0.4678	0.4672
Ce	0.0081	0.0405	0.0809	0.1616	0.2420	0.3227	0.4028	0.0000	0.0008	0.0040	0.0081	0.0404	0.0808	0.1614
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	48.9210	48.9090	48.8940	48.8640	48.8340	48.7994	48.7696	48.8967	48.8964	48.8953	48.8936	48.8816	48.8667	48.8367
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	13.4679	13.4625	13.4558	13.4425	13.4292	13.4302	13.4170	13.4558	13.4557	13.4551	13.4548	13.4492	13.4425	13.4292
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	2.2720	2.2711	2.2700	2.2677	2.2655	2.2657	2.2634	2.2700	2.2700	2.2699	2.2698	2.2689	2.2678	2.2655
Ca/Sn	0.0207	0.1037	0.2072	0.4145	0.6215	0.8289	1.0360	0.0000	0.0017	0.0085	0.0173	0.0863	0.1727	0.3455
Sn+Ce	0.3990	0.4312	0.4713	0.5515	0.6314	0.7120	0.7916	0.4685	0.4693	0.4724	0.4765	0.5086	0.5486	0.6286
Si+Al	34.9401	34.9262	34.9089	34.8743	34.8399	34.7827	34.7584	34.9090	34.9086	34.9073	34.9055	34.8917	34.8744	34.8400
Rank on bubbles	B	B	A	A	A	A	A	E	C	C	C	C	B	B
Acid etching rate (nm/min)	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9
Alkaline etching rate (nm/min)	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01

[0292]
[Table 8]

Component(mass%)	7-56	7-57	7-58	7-59	Com.Ex.7-1	Com.Ex.7-2	Com.Ex.7-3	Com.Ex.7-4	Com.Ex.7-5
Si	30.2934	30.2635	30.2337	30.2040	30.4319	30.4621	30.2829	30.2820	29.9892
Al	4.4994	4.4950	4.4906	4.4861	4.5052	4.5098	4.4831	4.4830	4.4513
Li	5.7628	5.7571	5.7514	5.7457	5.7948	5.8005	5.7664	5.7662	5.7011
Na	7.6675	7.6599	7.6524	7.6449	7.6773	7.6849	7.6397	7.6395	7.5855
K	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Mg	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr	2.2657	2.2634	2.2612	2.2590	2.2686	2.2708	2.2575	2.2574	2.2414
Ti	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
La	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Nb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4671	0.4665	0.4659	0.4653	0.0000	0.1955	0.7753	0.0000	0.7673
Ce	0.2420	0.3223	0.4023	0.4821	0.0000	0.0000	0.0000	0.8037	0.7951
Sb	0.0000	0.0000	0.0000	0.0000	0.4152	0.1256	0.0000	0.0000	0.0000
O	48.8021	48.7723	48.7425	48.7129	48.9070	48.9510	48.7951	48.7682	48.4891
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	13.4303	13.4170	13.4038	13.3906	13.4721	13.4854	13.4081	13.4057	13.2888
Mg+Ca+Sr+Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zr+Ti+La+Nb+Ta+Hf	2.2657	2.2634	2.2612	2.2590	2.2686	2.2708	2.2575	2.2574	2.2414
Ce/Sn	0.5181	0.6909	0.8635	1.0361	-	0.0000	0.0000	-	1.0362
Sn+Ce	0.7091	0.7888	0.8682	0.9474	0.0000	0.1955	0.7753	0.8037	1.5624
Si+Al	34.7928	34.7585	34.7243	34.8901	34.9371	34.9717	34.7680	34.7650	34.4205
Rank on bubbles	B	B	B	B	G	G	G	G	G
Acid etching rate (nm/min)	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9	3.9
Alkaline etching rate (nm/min)	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01

Component		8-1	8-2	8-3	8-4	8-5	8-6	8-7	8-8	8-9	8-10	8-11	8-12	8-13
(mol%)	SiO ₂	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8
	B ₂ O ₃	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	Li ₂ O	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
	Na ₂ O	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZnO	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3
	ZrO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	TiO ₂	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8
	La ₂ O ₃	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	Nb ₂ O ₅	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	CeO ₂	0	0.001	0.005	0.01	0.05	0.1	0	0.001	0.005	0.01	0.05	0.1	0.2
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.0000	0.0100	0.0500	0.1000	0.5000	1.0000	0.0000	0.0050	0.0250	0.0500	0.2500	0.5000	1.0000
	SnO ₂ +CeO ₂	0.1	0.101	0.105	0.11	0.15	0.2	0.2	0.201	0.205	0.21	0.25	0.3	0.4
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	MgO+CaO+SrO+BaO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SiO ₂ +Al ₂ O ₃	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6
Rank on bubbles		D	C	B	B	B	B	D	B	A	A	A	A	A

Component		8-14	8-15	8-16	8-17	8-18	8-19	8-20	8-21	8-22	8-23	8-24	8-25	8-26
(mol%)	SiO ₂	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8
	B ₂ O ₃	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	Li ₂ O	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
	Na ₂ O	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZnO	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3
	ZrO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	TiO ₂	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8
	La ₂ O ₃	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	Nb ₂ O ₅	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.3	0.3	0.3	0.3	0.3
	CeO ₂	0	0.001	0.005	0.01	0.05	0.1	0.2	0.25	0	0.001	0.005	0.01	0.05
	Sn ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.0000	0.0040	0.0200	0.0400	0.2000	0.4000	0.8000	1.0000	0.0000	0.0033	0.0167	0.0333	0.1667
	SnO ₂ +CeO ₂	0.25	0.251	0.255	0.26	0.3	0.35	0.45	0.5	0.3	0.301	0.305	0.31	0.35
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	MgO+CaO+SrO+BaO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SiO ₂ +Al ₂ O ₃	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6
Rank on bubbles		D	B	A	A	A	A	A	A	D	B	A	A	A

Component		8-27	8-28	8-29	8-30	8-31	8-32	8-33	8-34	8-35	8-36	8-37	8-38	8-39
(mol%)	SiO ₂	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8
	B ₂ O ₃	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	Li ₂ O	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
	Na ₂ O	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BeO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZnO	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3
	ZrO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	TiO ₂	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8
	La ₂ O ₃	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	Nb ₂ O ₅	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.3	0.3	0.3	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.5
	CeO ₂	0.1	0.2	0.3	0	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CeO ₂ /SnO ₂	0.3333	0.6667	1.0000	0.0000	0.0025	0.0125	0.0250	0.1250	0.2500	0.5000	0.7500	1.0000	0.0000
	SnO ₂ +CeO ₂	0.4	0.5	0.6	0.4	0.401	0.405	0.41	0.45	0.5	0.6	0.7	0.8	0.5
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	MgO+CaO+SrO+BaO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SiO ₂ +Al ₂ O ₃	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6
Rank on bubbles		A	A	A	D	B	B	A	A	A	A	A	A	E

Component		8-40	8-41	8-42	8-43	8-44	8-45	8-46	8-47	8-48	8-49	8-50	8-51	8-52
(mol%)	SiO ₂	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8
	B ₂ O ₃	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	Li ₂ O	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
	Na ₂ O	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZnO	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3
	ZrO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	TiO ₂	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8
	La ₂ O ₃	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	Nb ₂ O ₅	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.6	0.6	0.6	0.6
	CaO ₂	0.001	0.005	0.01	0.05	0.1	0.2	0.3	0.4	0.5	0	0.001	0.005	0.01
	Sb ₂ O ₃	0	0	0	0	0	0	0	0	0	0	0	0	0
	CaO ₂ /SnO ₂	0.0020	0.0100	0.0200	0.1000	0.2000	0.4000	0.6000	0.8000	1.0000	0.0000	0.0017	0.0083	0.0167
	SnO ₂ +CaO ₂	0.501	0.505	0.51	0.55	0.6	0.7	0.8	0.9	1	0.6	0.601	0.605	0.61
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	MgO+CaO+SrO+BaO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SiO ₂ +Al ₂ O ₃	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6
Rank on bubbles		C	C	B	B	A	A	A	A	A	E	C	C	C

Component		8-53	8-54	8-55	8-56	8-57	8-58	8-59	Com.Ex.8-1	Com.Ex.8-2	Com.Ex.8-3	Com.Ex.8-4	Com.Ex.8-5
(mol%)	SiO ₂	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8	64.8
	B ₂ O ₃	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
	Al ₂ O ₃	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
	Li ₂ O	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8	10.8
	Na ₂ O	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1
	K ₂ O	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	MgO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	CaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	SrO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	ZnO	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3
	ZrO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
	TiO ₂	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8
	La ₂ O ₃	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
	Nb ₂ O ₅	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
	Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	HfO ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Based on glass components (mass%)	SnO ₂	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0	0.25	1	0	1
	CeO ₂	0.05	0.1	0.2	0.3	0.4	0.5	0.6	0	0	0	1	1
	Sb ₂ O ₃	0	0	0	0	0	0	0	0.5	0.15	0	0	0
	CeO ₂ /SnO ₂	0.0833	0.1667	0.3333	0.5000	0.6667	0.8333	1.0000	-	0.0000	0.0000	-	1.0000
	SnO ₂ +CeO ₂	0.65	0.7	0.8	0.9	1	1.1	1.2	0	0.25	1	1	2
(mol%)	Li ₂ O+Na ₂ O+K ₂ O	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
	MgO+CaO+SrO+BaO	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
	ZrO ₂ +TiO ₂ +La ₂ O ₃ +Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
	SiO ₂ +Al ₂ O ₃	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6	73.6
Rank on bubbles		C	B	B	B	B	B	B	G	G	G	G	G

Component(mass%)	8-1	8-2	8-3	8-4	8-5	8-6	8-7	8-8	8-9	8-10	8-11	8-12	8-13
Si	28.7106	28.7103	28.7092	28.7077	28.6963	28.6648	28.6649	28.6646	28.6635	28.6621	28.6606	28.6363	28.6078
B	0.4434	0.4434	0.4434	0.4434	0.4432	0.4434	0.4434	0.4434	0.4434	0.4434	0.4432	0.4430	0.4425
Al	7.4914	7.4914	7.4911	7.4907	7.4877	7.4910	7.4911	7.4910	7.4907	7.4903	7.4873	7.4836	7.4762
Li	2.3652	2.3651	2.3650	2.3649	2.3640	2.3650	2.3650	2.3650	2.3649	2.3648	2.3639	2.3627	2.3603
Na	1.5232	1.5232	1.5232	1.5231	1.5225	1.5232	1.5232	1.5232	1.5231	1.5230	1.5224	1.5217	1.5201
K	1.3570	1.3569	1.3569	1.3568	1.3563	1.3569	1.3569	1.3569	1.3568	1.3568	1.3562	1.3555	1.3542
Mg	2.4156	2.4156	2.4155	2.4153	2.4144	2.4155	2.4155	2.4154	2.4153	2.4152	2.4143	2.4131	2.4107
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sc	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zn	2.3726	2.3726	2.3725	2.3724	2.3714	2.3725	2.3725	2.3725	2.3724	2.3722	2.3713	2.3701	2.3678
Zr	0.8635	0.8635	0.8634	0.8634	0.8630	0.8634	0.8634	0.8634	0.8634	0.8633	0.8630	0.8626	0.8617
Ti	0.6043	0.6043	0.6042	0.6042	0.6040	0.6042	0.6042	0.6042	0.6042	0.6042	0.6039	0.6036	0.6030
La	1.7457	1.7457	1.7457	1.7456	1.7449	1.7457	1.7457	1.7456	1.7456	1.7455	1.7448	1.7439	1.7422
Nb	2.0519	2.0519	2.0518	2.0517	2.0509	2.0518	2.0518	2.0518	2.0517	2.0516	2.0508	2.0498	2.0477
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.0785	0.0785	0.0785	0.0785	0.0785	0.0785	0.1570	0.1570	0.1570	0.1569	0.1569	0.1567	0.1565
Ce	0.0000	0.0008	0.0041	0.0081	0.0407	0.0813	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1622
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.9771	47.9768	47.9755	47.9742	47.9622	47.9428	47.9454	47.9452	47.9439	47.9426	47.9308	47.9162	47.8871
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	5.2454	5.2452	5.2451	5.2448	5.2428	5.2451	5.2451	5.2451	5.2448	5.2448	5.2425	5.2399	5.2348
Mg+Ca+Sr+Ba	2.4156	2.4156	2.4155	2.4153	2.4144	2.4155	2.4155	2.4154	2.4153	2.4152	2.4143	2.4131	2.4107
Zr+Ti+La+Nb+Ta+Hf	5.2654	5.2654	5.2651	5.2649	5.2628	5.2651	5.2651	5.2650	5.2649	5.2646	5.2625	5.2599	5.2546
Os/Sn	0.0000	0.0102	0.0522	0.1032	0.5185	1.0357	0.0000	0.0051	0.0281	0.0516	0.2588	0.5182	1.0364
Sn+Ce	0.0785	0.0793	0.0826	0.0866	0.1192	0.1598	0.1570	0.1678	0.1611	0.1650	0.1975	0.2379	0.3187
Si+Al	36.2020	36.2017	36.2003	36.1984	36.1840	36.1558	36.1560	36.1556	36.1542	36.1524	36.1379	36.1199	36.0840
Rank on bubbles	D	C	B	B	B	B	D	B	A	A	A	A	A

Component(mass%)	8-14	8-15	8-16	8-17	8-18	8-19	8-20	8-21	8-22	8-23	8-24	8-25	8-26	8-27
Si	28.6507	28.6504	28.6492	28.6478	28.6364	28.6221	28.5937	28.5795	28.6364	28.6361	28.6350	28.6336	28.6222	28.6079
B	0.4432	0.4432	0.4432	0.4431	0.4430	0.4427	0.4423	0.4421	0.4430	0.4430	0.4429	0.4429	0.4427	0.4425
Al	7.4873	7.4873	7.4870	7.4866	7.4836	7.4799	7.4724	7.4687	7.4836	7.4835	7.4832	7.4829	7.4799	7.4762
Li	2.3639	2.3638	2.3638	2.3636	2.3627	2.3615	2.3592	2.3580	2.3627	2.3627	2.3626	2.3625	2.3615	2.3603
Na	1.5224	1.5224	1.5223	1.5223	1.5217	1.5209	1.5194	1.5186	1.5217	1.5216	1.5216	1.5215	1.5209	1.5201
K	1.3582	1.3582	1.3581	1.3581	1.3555	1.3549	1.3535	1.3528	1.3555	1.3555	1.3555	1.3554	1.3549	1.3542
Mg	2.4143	2.4142	2.4141	2.4140	2.4131	2.4119	2.4095	2.4083	2.4131	2.4130	2.4129	2.4128	2.4119	2.4107
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zn	2.3713	2.3713	2.3712	2.3711	2.3701	2.3689	2.3666	2.3654	2.3701	2.3701	2.3700	2.3699	2.3689	2.3678
Zr	0.8630	0.8630	0.8630	0.8629	0.8626	0.8621	0.8613	0.8609	0.8626	0.8626	0.8625	0.8625	0.8621	0.8617
Ti	0.6039	0.6039	0.6039	0.6039	0.6036	0.6033	0.6027	0.6024	0.6036	0.6036	0.6036	0.6036	0.6033	0.6030
La	1.7448	1.7448	1.7447	1.7446	1.7439	1.7431	1.7413	1.7405	1.7439	1.7439	1.7438	1.7438	1.7431	1.7422
Nb	2.0508	2.0508	2.0507	2.0506	2.0498	2.0487	2.0467	2.0457	2.0498	2.0498	2.0497	2.0496	2.0488	2.0477
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.1961	0.1961	0.1961	0.1960	0.1959	0.1958	0.1955	0.1954	0.2351	0.2351	0.2351	0.2351	0.2348	0.2348
Ce	0.0000	0.0008	0.0041	0.0081	0.0406	0.0812	0.1621	0.2025	0.0000	0.0008	0.0041	0.0081	0.0406	0.0811
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.9321	47.9318	47.9306	47.9293	47.9175	47.9030	47.8738	47.8592	47.9189	47.9187	47.9175	47.9158	47.9043	47.8898
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	5.2425	5.2424	5.2422	5.2420	5.2399	5.2373	5.2321	5.2294	5.2399	5.2398	5.2397	5.2394	5.2373	5.2346
Mg+Ca+Sr+Ba	2.4143	2.4142	2.4141	2.4140	2.4131	2.4119	2.4095	2.4083	2.4131	2.4130	2.4129	2.4128	2.4119	2.4107
Zr+Ti+La+Nb+Ta+Hf	5.2625	5.2625	5.2623	5.2620	5.2599	5.2572	5.2520	5.2495	5.2599	5.2599	5.2596	5.2595	5.2573	5.2546
Ce/Sn	0.0000	0.0041	0.0209	0.0413	0.2072	0.4147	0.8292	1.0363	0.0000	0.0034	0.0174	0.0345	0.1728	0.3454
Sn+Ce	0.1961	0.1969	0.2002	0.2041	0.2365	0.2770	0.3576	0.3979	0.2351	0.2359	0.2392	0.2432	0.2755	0.3159
Si+Al	36.1380	36.1377	36.1362	36.1344	36.1200	36.1020	36.0661	36.0482	36.1200	36.1196	36.1182	36.1165	36.1021	36.0841
Rank on bubbles	D	B	A	A	A	A	A	A	D	B	A	A	A	A

Component(mass%)	8-42	8-43	8-44	8-45	8-46	8-47	8-48	8-49	8-50	8-51	8-52	8-53	8-54	8-55
Si	28.5768	28.5655	28.5341	28.5057	28.4777	28.4496	28.4042	28.5342	28.5339	28.5328	28.5314	28.5201	28.5059	28.4778
B	0.4420	0.4419	0.4421	0.4416	0.4412	0.4408	0.4407	0.4421	0.4421	0.4420	0.4420	0.4419	0.4416	0.4412
Al	7.4680	7.4651	7.4684	7.4610	7.4537	7.4463	7.4460	7.4685	7.4684	7.4681	7.4677	7.4648	7.4611	7.4537
Li	2.3578	2.3568	2.3579	2.3556	2.3532	2.3509	2.3508	2.3579	2.3579	2.3578	2.3577	2.3567	2.3556	2.3532
Na	1.5185	1.5179	1.5186	1.5171	1.5156	1.5141	1.5140	1.5188	1.5186	1.5185	1.5184	1.5178	1.5171	1.5156
K	1.3527	1.3522	1.3528	1.3515	1.3501	1.3488	1.3487	1.3528	1.3528	1.3527	1.3527	1.3521	1.3515	1.3501
Mg	2.4080	2.4071	2.4082	2.4058	2.4034	2.4010	2.4009	2.4082	2.4081	2.4081	2.4079	2.4070	2.4058	2.4034
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zn	2.3652	2.3643	2.3653	2.3630	2.3606	2.3583	2.3582	2.3653	2.3653	2.3652	2.3651	2.3642	2.3630	2.3606
Zr	0.8608	0.8604	0.8608	0.8600	0.8591	0.8583	0.8582	0.8608	0.8608	0.8608	0.8607	0.8604	0.8600	0.8591
Ti	0.6024	0.6021	0.6024	0.6018	0.6012	0.6008	0.6008	0.6024	0.6024	0.6024	0.6024	0.6021	0.6018	0.6012
La	1.7403	1.7396	1.7404	1.7387	1.7369	1.7352	1.7352	1.7404	1.7404	1.7403	1.7402	1.7395	1.7387	1.7370
Nb	2.0455	2.0447	2.0456	2.0436	2.0416	2.0395	2.0395	2.0456	2.0456	2.0455	2.0454	2.0446	2.0436	2.0416
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.3907	0.3905	0.3906	0.3901	0.3895	0.3890	0.3888	0.4687	0.4687	0.4686	0.4686	0.4684	0.4680	0.4674
Ce	0.0081	0.0405	0.0809	0.1617	0.2422	0.3225	0.4029	0.0000	0.0008	0.0040	0.0081	0.0404	0.0808	0.1614
Sb	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
O	47.8632	47.8514	47.8319	47.8028	47.7740	47.7451	47.7113	47.8345	47.8342	47.8332	47.8317	47.8200	47.8055	47.7767
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	5.2290	5.2269	5.2293	5.2242	5.2189	5.2138	5.2135	5.2293	5.2293	5.2290	5.2288	5.2266	5.2242	5.2189
Mg+Ca+Sr+Ba	2.4080	2.4071	2.4082	2.4058	2.4034	2.4010	2.4009	2.4082	2.4081	2.4081	2.4079	2.4070	2.4058	2.4034
Zr+Ti+La+Nb+Ta+Hf	5.2490	5.2468	5.2492	5.2441	5.2388	5.2336	5.2335	5.2492	5.2492	5.2490	5.2487	5.2466	5.2441	5.2389
Ce/Sn	0.0207	0.1037	0.2071	0.4145	0.6218	0.8290	1.0363	0.0000	0.0017	0.0085	0.0173	0.0863	0.1726	0.3453
Sn+Ce	0.3988	0.4310	0.4715	0.5518	0.6317	0.7115	0.7917	0.4687	0.4695	0.4726	0.4767	0.5088	0.5488	0.6288
Si+Al	36.0448	36.0306	36.0025	35.9687	35.9314	35.8959	35.8502	36.0027	36.0023	36.0009	35.9991	35.9849	35.9670	35.9315
Rank on bubbles	B	B	A	A	A	A	A	E	C	C	C	C	B	B

Component (mass%)	8-56	8-57	8-58	8-59	Com.Ex.8-1	Com.Ex.8-2	Com.Ex.8-3	Com.Ex.8-4	Dom.Ex.8-5
Si	28.4496	28.4043	28.3763	28.3617	28.5799	28.6086	28.4047	28.4211	28.1513
B	0.4408	0.4407	0.4403	0.4401	0.4421	0.4425	0.4407	0.4403	0.4382
Al	7.4463	7.4460	7.4387	7.4348	7.4689	7.4763	7.4461	7.4388	7.3185
U	2.3509	2.3508	2.3485	2.3256	2.3580	2.3604	2.3508	2.3486	2.3155
Na	1.5141	1.5140	1.5125	1.5117	1.5187	1.5202	1.5140	1.5125	1.5052
K	1.3488	1.3487	1.3474	1.3467	1.3529	1.3542	1.3487	1.3474	1.3409
Mg	2.4010	2.4009	2.3986	2.3973	2.4083	2.4107	2.4010	2.3986	2.3869
Ca	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sr	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Ba	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Zn	2.3583	2.3582	2.3559	2.3547	2.3655	2.3678	2.3582	2.3559	2.3445
Zr	0.8583	0.8582	0.8574	0.8569	0.8609	0.8617	0.8582	0.8574	0.8532
Ti	0.6006	0.6006	0.6000	0.5997	0.6024	0.6031	0.6006	0.6000	0.5971
La	1.7352	1.7352	1.7335	1.7326	1.7405	1.7422	1.7352	1.7335	1.7251
Nb	2.0396	2.0395	2.0375	2.0364	2.0457	2.0478	2.0395	2.0375	2.0278
Ta	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Hf	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
Sn	0.4668	0.4666	0.4660	0.4655	0.0000	0.1957	0.7775	0.0000	0.7700
Ce	0.2418	0.3223	0.4024	0.4824	0.0000	0.0000	0.0000	0.8053	0.7980
Sb	0.0000	0.0000	0.0000	0.0000	0.4138	0.1227	0.0000	0.0000	0.0000
O	47.7479	47.7140	47.6850	47.6539	47.8426	47.8861	47.7248	47.7031	47.4280
Total	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000	100.0000
Li+Na+K	5.2138	5.2135	5.2084	5.1840	5.2296	5.2348	5.2135	5.2085	5.1616
Mg+Ca+Sr+Ba	2.4010	2.4009	2.3986	2.3973	2.4083	2.4107	2.4010	2.3986	2.3869
Zr+Ti+Hf+Nb+Ta+Sn	5.2337	5.2335	5.2284	5.2256	5.2495	5.2548	5.2335	5.2284	5.2030
Ca/Sn	0.5180	0.6907	0.8635	1.0363	-	0.0000	0.0000	-	1.0364
Sr+Os	0.7086	0.7889	0.8684	0.9479	0.0000	0.1957	0.7775	0.8053	1.5680
Si+Al	35.8959	35.8503	35.8160	35.7965	36.0488	36.0949	35.8508	35.8599	35.4698
Rank on bubbles	B	B	B	B	G	G	G	G	G

[0293]

Embodiment B

(1) Melting of the glass

The basic composition indicated as No. 1 in Table 9 was employed in the glasses of Nos. 1-1 to Nos. 1-339. The basic composition indicated as No. 2 in Table 9 was employed in the glasses of Nos. 2-1 to 2-339. The basic composition indicated as No. 3 in Table 9 was employed in the glasses of Nos. 3-1 to 3-339. The basic composition indicated as No. 4 in Table 9 was employed in

the glasses of Nos. 4-1 to 4-339. The basic composition indicated as No. 5 in Table 9 was employed in the glasses of Nos. 5-1 to 5-339. The basic composition indicated as No. 6 in Table 9 was employed in the glasses of Nos. 6-1 to 6-339. The basic composition indicated as No. 7 in Table 9 was employed in the glasses of Nos. 7-1 to 7-339. For each of the glasses of Nos. 1 to 7, starting materials such as oxides, carbonates, nitrates, and hydroxides, as well as clarifying agents such as SnO_2 and CeO_2 , were weighed out and mixed to obtain mixed starting materials so as to obtain glasses comprising the quantities of SnO_2 and CeO_2 of Nos. 1 to 339, indicated in Table 10, that were added based on the total amount of the basic compositions of the glasses in Table 9. The starting materials were charged to a melting vessel; heated, melted, clarified, and stirred for 6 hours over a range of 1,400 to 1,600°C to produce homogeneous glass melts containing neither bubbles nor unmelted material. After being maintained for 6 hours at a range of 1,400 to 1,600°C as stated above, the temperature of each glass melt was decreased (lowered), and the glass melt was maintained for 1 hour at a range of 1,200 to 1,400°C to markedly enhance the clarifying effect. In particular, glass melts in which Sn and Ce were both present were found to exhibit highly pronounced clarifying effects.

[0294]

The number of glasses prepared in the present embodiment was $339 \times 7 = 2,373$. For example, glass No. 1-1 had the basic composition indicated by No. 1 in Table 9, with the components added based on the total amount of the basic composition indicated by No. 1 in Table 10. Glass No. 3-150 had the basic composition indicated by No. 3 in Table 9, with the components added based on the total amount of the basic composition indicated by No. 150 in Table 10. And glass No. 7-339 had the basic composition indicated by No. 7 in Table 9, with the components added based on the total amount of the basic composition indicated by No. 339 in Table 10.

[0295]

[Table 9]

No.	1	2	3	4	5	6	7
SiO_2	67.3	66.2	72.0	69.0	68.7	68.6	64.8
B_2O_3	—	—	—	—	2.0	—	1.3
Al_2O_3	9.2	9.3	6.0	7.0	7.7	8.8	8.8
P_2O_5	—	—	—	—	—	0.2	—
Li_2O	8.1	8.1	8.2	8.0	14.0	15.3	10.8
Na_2O	11.2	11.2	10.4	11.5	3.5	3.2	2.1

K ₂ O	0.3	0.4	0.0	0.1	1.1	1.1	1.1
MgO	1.1	1.5	0.0	1.0	0.0	0.0	6.3
CaO	1.8	2.3	2.5	2.0	0.0	0.0	0.0
SrO	0.0	0.0	0.0	0.4	0.0	0.0	0.0
BaO	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ZnO	—	—	—	—	—	—	2.3
ZrO ₂	1.0	1.0	0.9	0.9	1.0	0.0	0.6
TiO ₂	0.0	0.0	0.0	0.0	1.5	1.6	0.8
La ₂ O ₃	0.0	0.0	0.0	0.0	0.5	0.6	0.4
Nb ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.6	0.7
Ta ₂ O ₅	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HfO ₂	0.0	0.0	0.0	0.1	0.0	0.0	0.0
Total	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Li ₂ O+Na ₂ O+K ₂ O	19.6	19.7	18.6	19.6	18.6	19.6	14.0
MgO+CaO+SrO+BaO	2.9	3.8	2.5	3.4	0.0	0.0	6.3
ZrO ₂ +TiO ₂ +La ₂ O ₃ + Nb ₂ O ₅ +Ta ₂ O ₅ +HfO ₂	1.0	1.0	0.9	1.0	3.0	2.8	2.5
SiO ₂ +Al ₂ O ₃	76.5	75.5	78.0	76.0	76.4	77.4	73.6

[0296]

[Table 10]

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
1	0.01	0.09	0.00	0.10	0.10
2	0.03	0.07	0.00	0.10	0.30
3	0.05	0.05	0.00	0.10	0.50
4	0.07	0.03	0.00	0.10	0.70
5	0.09	0.01	0.00	0.10	0.90
6	0.01	0.29	0.00	0.30	0.03
7	0.03	0.27	0.00	0.30	0.10
8	0.05	0.25	0.00	0.30	0.17
9	0.07	0.23	0.00	0.30	0.23
10	0.1	0.2	0.00	0.30	0.33
11	0.15	0.15	0.00	0.30	0.50
12	0.2	0.1	0.00	0.30	0.67
13	0.23	0.07	0.00	0.30	0.77
14	0.25	0.05	0.00	0.30	0.83
15	0.27	0.03	0.00	0.30	0.90
16	0.29	0.01	0.00	0.30	0.97
17	0.01	0.49	0.00	0.50	0.02
18	0.05	0.45	0.00	0.50	0.10
19	0.1	0.4	0.00	0.50	0.20
20	0.15	0.35	0.00	0.50	0.30
21	0.2	0.3	0.00	0.50	0.40
22	0.25	0.25	0.00	0.50	0.50
23	0.3	0.2	0.00	0.50	0.60
24	0.35	0.15	0.00	0.50	0.70
25	0.4	0.1	0.00	0.50	0.80
26	0.45	0.05	0.00	0.50	0.90
27	0.49	0.01	0.00	0.50	0.98
28	0.02	0.78	0.00	0.80	0.03
29	0.05	0.75	0.00	0.80	0.06
30	0.1	0.7	0.00	0.80	0.13
31	0.15	0.65	0.00	0.80	0.19
32	0.2	0.6	0.00	0.80	0.25
33	0.25	0.55	0.00	0.80	0.31
34	0.3	0.5	0.00	0.80	0.38
35	0.35	0.45	0.00	0.80	0.44
36	0.4	0.4	0.00	0.80	0.50
37	0.45	0.35	0.00	0.80	0.56
38	0.5	0.3	0.00	0.80	0.63
39	0.55	0.25	0.00	0.80	0.69
40	0.6	0.2	0.00	0.80	0.75
41	0.65	0.15	0.00	0.80	0.81
42	0.7	0.1	0.00	0.80	0.88
43	0.75	0.05	0.00	0.80	0.94
44	0.79	0.01	0.00	0.80	0.99
45	0.02	0.98	0.00	1.00	0.02
46	0.05	0.95	0.00	1.00	0.05
47	0.1	0.9	0.00	1.00	0.10
48	0.15	0.85	0.00	1.00	0.15
49	0.2	0.8	0.00	1.00	0.20
50	0.3	0.7	0.00	1.00	0.30
51	0.4	0.6	0.00	1.00	0.40
52	0.5	0.5	0.00	1.00	0.50
53	0.6	0.4	0.00	1.00	0.60
54	0.7	0.3	0.00	1.00	0.70
55	0.8	0.2	0.00	1.00	0.80

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
56	0.85	0.15	0.00	1.00	0.85
57	0.9	0.1	0.00	1.00	0.90
58	0.95	0.05	0.00	1.00	0.95
59	0.98	0.02	0.00	1.00	0.98
60	0.03	1.17	0.00	1.20	0.03
61	0.05	1.15	0.00	1.20	0.04
62	0.08	1.12	0.00	1.20	0.07
63	0.1	1.1	0.00	1.20	0.08
64	0.12	1.08	0.00	1.20	0.10
65	0.15	1.05	0.00	1.20	0.13
66	0.2	1	0.00	1.20	0.17
67	0.3	0.9	0.00	1.20	0.25
68	0.4	0.8	0.00	1.20	0.33
69	0.5	0.7	0.00	1.20	0.42
70	0.6	0.6	0.00	1.20	0.50
71	0.7	0.5	0.00	1.20	0.58
72	0.8	0.4	0.00	1.20	0.67
73	0.9	0.3	0.00	1.20	0.75
74	1	0.2	0.00	1.20	0.83
75	1.1	0.1	0.00	1.20	0.92
76	1.15	0.05	0.00	1.20	0.96
77	1.18	0.02	0.00	1.20	0.98
78	0.03	1.47	0.00	1.50	0.02
79	0.05	1.45	0.00	1.50	0.03
80	0.07	1.43	0.00	1.50	0.05
81	0.1	1.4	0.00	1.50	0.07
82	0.2	1.3	0.00	1.50	0.13
83	0.3	1.2	0.00	1.50	0.20
84	0.4	1.1	0.00	1.50	0.27
85	0.5	1	0.00	1.50	0.33
86	0.6	0.9	0.00	1.50	0.40
87	0.7	0.8	0.00	1.50	0.47
88	0.75	0.75	0.00	1.50	0.50
89	0.8	0.7	0.00	1.50	0.53
90	0.9	0.6	0.00	1.50	0.60
91	1	0.5	0.00	1.50	0.67
92	1.1	0.4	0.00	1.50	0.73
93	1.2	0.3	0.00	1.50	0.80
94	1.3	0.2	0.00	1.50	0.87
95	1.4	0.1	0.00	1.50	0.93
96	1.43	0.07	0.00	1.50	0.95
97	1.45	0.05	0.00	1.50	0.97
98	1.47	0.03	0.00	1.50	0.98
99	1.48	0.02	0.00	1.50	0.99
100	0.02	1.68	0.00	1.70	0.01
101	0.05	1.65	0.00	1.70	0.03
102	0.07	1.63	0.00	1.70	0.04
103	0.1	1.6	0.00	1.70	0.06
104	0.2	1.5	0.00	1.70	0.12
105	0.3	1.4	0.00	1.70	0.18
106	0.4	1.3	0.00	1.70	0.24
107	0.5	1.2	0.00	1.70	0.29
108	0.6	1.1	0.00	1.70	0.35
109	0.7	1	0.00	1.70	0.41
110	0.8	0.9	0.00	1.70	0.47

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
111	0.9	0.8	0.00	1.70	0.53
112	0.85	0.85	0.00	1.70	0.50
113	0.9	0.8	0.00	1.70	0.53
114	1	0.7	0.00	1.70	0.59
115	1.1	0.6	0.00	1.70	0.65
116	1.2	0.5	0.00	1.70	0.71
117	1.3	0.4	0.00	1.70	0.76
118	1.4	0.3	0.00	1.70	0.82
119	1.5	0.2	0.00	1.70	0.88
120	1.6	0.1	0.00	1.70	0.94
121	1.65	0.05	0.00	1.70	0.97
122	1.68	0.02	0.00	1.70	0.99
123	0.02	1.98	0.00	2.00	0.01
124	0.05	1.95	0.00	2.00	0.03
125	0.07	1.93	0.00	2.00	0.04
126	0.1	1.9	0.00	2.00	0.05
127	0.2	1.8	0.00	2.00	0.10
128	0.3	1.7	0.00	2.00	0.15
129	0.4	1.6	0.00	2.00	0.20
130	0.5	1.5	0.00	2.00	0.25
131	0.6	1.4	0.00	2.00	0.30
132	0.7	1.3	0.00	2.00	0.35
133	0.8	1.2	0.00	2.00	0.40
134	0.9	1.1	0.00	2.00	0.45
135	1	1	0.00	2.00	0.50
136	1.1	0.9	0.00	2.00	0.55
137	1.2	0.8	0.00	2.00	0.60
138	1.3	0.7	0.00	2.00	0.65
139	1.4	0.6	0.00	2.00	0.70
140	1.5	0.5	0.00	2.00	0.75
141	1.6	0.4	0.00	2.00	0.80
142	1.7	0.3	0.00	2.00	0.85
143	1.8	0.2	0.00	2.00	0.90
144	1.9	0.1	0.00	2.00	0.95
145	1.95	0.05	0.00	2.00	0.98
146	1.97	0.03	0.00	2.00	0.99
147	1.98	0.02	0.00	2.00	0.99
148	0.05	2.25	0.00	2.30	0.02
149	0.1	2.2	0.00	2.30	0.04
150	0.2	2.1	0.00	2.30	0.09
151	0.3	2	0.00	2.30	0.13
152	0.4	1.9	0.00	2.30	0.17
153	0.5	1.8	0.00	2.30	0.22
154	0.6	1.7	0.00	2.30	0.26
155	0.7	1.6	0.00	2.30	0.30
156	0.8	1.5	0.00	2.30	0.35
157	0.9	1.4	0.00	2.30	0.39
158	1	1.3	0.00	2.30	0.43
159	1.1	1.2	0.00	2.30	0.48
160	1.2	1.1	0.00	2.30	0.52
161	1.3	1	0.00	2.30	0.57
162	1.4	0.9	0.00	2.30	0.61
163	1.5	0.8	0.00	2.30	0.65
164	1.6	0.7	0.00	2.30	0.70
165	1.7	0.6	0.00	2.30	0.74

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
166	1.8	0.5	0.00	2.30	0.78
167	1.9	0.4	0.00	2.30	0.83
168	2	0.3	0.00	2.30	0.87
169	2.1	0.2	0.00	2.30	0.91
170	2.2	0.1	0.00	2.30	0.96
171	2.25	0.05	0.00	2.30	0.98
172	2.27	0.03	0.00	2.30	0.99
173	0.05	2.45	0.00	2.50	0.02
174	0.07	2.43	0.00	2.50	0.03
175	0.1	2.4	0.00	2.50	0.04
176	0.2	2.3	0.00	2.50	0.08
177	0.3	2.2	0.00	2.50	0.12
178	0.4	2.1	0.00	2.50	0.16
179	0.5	2	0.00	2.50	0.20
180	0.6	1.9	0.00	2.50	0.24
181	0.7	1.8	0.00	2.50	0.28
182	0.8	1.7	0.00	2.50	0.32
183	0.9	1.6	0.00	2.50	0.36
184	1	1.5	0.00	2.50	0.40
185	1.1	1.4	0.00	2.50	0.44
186	1.2	1.3	0.00	2.50	0.48
187	1.3	1.2	0.00	2.50	0.52
188	1.4	1.1	0.00	2.50	0.56
189	1.5	1	0.00	2.50	0.60
190	1.6	0.9	0.00	2.50	0.64
191	1.7	0.8	0.00	2.50	0.68
192	1.8	0.7	0.00	2.50	0.72
193	1.9	0.6	0.00	2.50	0.76
194	2	0.5	0.00	2.50	0.80
195	2.1	0.4	0.00	2.50	0.84
196	2.2	0.3	0.00	2.50	0.88
197	2.3	0.2	0.00	2.50	0.92
198	2.4	0.1	0.00	2.50	0.96
199	2.45	0.05	0.00	2.50	0.98
200	2.47	0.03	0.00	2.50	0.99
201	2.48	0.02	0.00	2.50	0.99
202	0.06	2.64	0.00	2.70	0.02
203	0.08	2.62	0.00	2.70	0.03
204	0.1	2.6	0.00	2.70	0.04
205	0.2	2.5	0.00	2.70	0.07
206	0.3	2.4	0.00	2.70	0.11
207	0.4	2.3	0.00	2.70	0.15
208	0.5	2.2	0.00	2.70	0.19
209	0.6	2.1	0.00	2.70	0.22
210	0.7	2	0.00	2.70	0.26
211	0.8	1.9	0.00	2.70	0.30
212	0.9	1.8	0.00	2.70	0.33
213	1	1.7	0.00	2.70	0.37
214	1.1	1.6	0.00	2.70	0.41
215	1.2	1.5	0.00	2.70	0.44
216	1.3	1.4	0.00	2.70	0.48
217	1.35	1.35	0.00	2.70	0.50
218	1.4	1.3	0.00	2.70	0.52
219	1.5	1.2	0.00	2.70	0.56
220	1.6	1.1	0.00	2.70	0.59

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
221	1.7	1	0.00	2.70	0.63
222	1.8	0.9	0.00	2.70	0.67
223	1.9	0.8	0.00	2.70	0.70
224	2	0.7	0.00	2.70	0.74
225	2.1	0.6	0.00	2.70	0.78
226	2.2	0.5	0.00	2.70	0.81
227	2.3	0.4	0.00	2.70	0.85
228	2.4	0.3	0.00	2.70	0.89
229	2.5	0.2	0.00	2.70	0.93
230	2.6	0.1	0.00	2.70	0.96
231	2.65	0.05	0.00	2.70	0.98
232	2.67	0.03	0.00	2.70	0.99
233	0.06	2.94	0.00	3.00	0.02
234	0.08	2.92	0.00	3.00	0.03
235	0.1	2.9	0.00	3.00	0.03
236	0.2	2.8	0.00	3.00	0.07
237	0.3	2.7	0.00	3.00	0.10
238	0.4	2.6	0.00	3.00	0.13
239	0.5	2.5	0.00	3.00	0.17
240	0.6	2.4	0.00	3.00	0.20
241	0.7	2.3	0.00	3.00	0.23
242	0.8	2.2	0.00	3.00	0.27
243	0.9	2.1	0.00	3.00	0.30
244	1	2	0.00	3.00	0.33
245	1.1	1.9	0.00	3.00	0.37
246	1.2	1.8	0.00	3.00	0.40
247	1.3	1.7	0.00	3.00	0.43
248	1.4	1.6	0.00	3.00	0.47
249	1.5	1.5	0.00	3.00	0.50
250	1.6	1.4	0.00	3.00	0.53
251	1.7	1.3	0.00	3.00	0.57
252	1.8	1.2	0.00	3.00	0.60
253	1.9	1.1	0.00	3.00	0.63
254	2	1	0.00	3.00	0.67
255	2.1	0.9	0.00	3.00	0.70
256	2.2	0.8	0.00	3.00	0.73
257	2.3	0.7	0.00	3.00	0.77
258	2.4	0.6	0.00	3.00	0.80
259	2.5	0.5	0.00	3.00	0.83
260	2.6	0.4	0.00	3.00	0.87
261	2.7	0.3	0.00	3.00	0.90
262	2.8	0.2	0.00	3.00	0.93
263	2.9	0.1	0.00	3.00	0.97
264	2.95	0.05	0.00	3.00	0.98
265	2.97	0.03	0.00	3.00	0.99
266	0.07	3.13	0.00	3.20	0.02
267	0.1	3.1	0.00	3.20	0.03
268	0.2	3	0.00	3.20	0.06
269	0.3	2.9	0.00	3.20	0.09
270	0.4	2.8	0.00	3.20	0.13
271	0.5	2.7	0.00	3.20	0.16
272	0.6	2.6	0.00	3.20	0.19
273	0.7	2.5	0.00	3.20	0.22
274	0.8	2.4	0.00	3.20	0.25
275	0.9	2.3	0.00	3.20	0.28

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
276	1	2.2	0.00	3.20	0.31
277	1.1	2.1	0.00	3.20	0.34
278	1.2	2	0.00	3.20	0.38
279	1.3	1.9	0.00	3.20	0.41
280	1.4	1.8	0.00	3.20	0.44
281	1.5	1.7	0.00	3.20	0.47
282	1.6	1.6	0.00	3.20	0.50
283	1.7	1.5	0.00	3.20	0.53
284	1.8	1.4	0.00	3.20	0.56
285	1.9	1.3	0.00	3.20	0.59
286	2	1.2	0.00	3.20	0.63
287	2.1	1.1	0.00	3.20	0.66
288	2.2	1	0.00	3.20	0.69
289	2.3	0.9	0.00	3.20	0.72
290	2.4	0.8	0.00	3.20	0.75
291	2.5	0.7	0.00	3.20	0.78
292	2.6	0.6	0.00	3.20	0.81
293	2.7	0.5	0.00	3.20	0.84
294	2.8	0.4	0.00	3.20	0.88
295	2.9	0.3	0.00	3.20	0.91
296	3	0.2	0.00	3.20	0.94
297	3.1	0.1	0.00	3.20	0.97
298	3.15	0.05	0.00	3.20	0.98
299	3.16	0.04	0.00	3.20	0.99
300	0.07	3.43	0.00	3.50	0.02
301	0.09	3.41	0.00	3.50	0.03
302	0.1	3.4	0.00	3.50	0.03
303	0.2	3.3	0.00	3.50	0.06
304	0.3	3.2	0.00	3.50	0.09
305	0.4	3.1	0.00	3.50	0.11
306	0.5	3	0.00	3.50	0.14
307	0.6	2.9	0.00	3.50	0.17
308	0.7	2.8	0.00	3.50	0.20
309	0.8	2.7	0.00	3.50	0.23
310	0.9	2.6	0.00	3.50	0.26
311	1	2.5	0.00	3.50	0.29
312	1.1	2.4	0.00	3.50	0.31
313	1.2	2.3	0.00	3.50	0.34
314	1.3	2.2	0.00	3.50	0.37
315	1.4	2.1	0.00	3.50	0.40
316	1.5	2	0.00	3.50	0.43
317	1.6	1.9	0.00	3.50	0.46
318	1.7	1.8	0.00	3.50	0.49
319	1.75	1.75	0.00	3.50	0.50
320	1.8	1.7	0.00	3.50	0.51
321	1.9	1.6	0.00	3.50	0.54
322	2	1.5	0.00	3.50	0.57
323	2.1	1.4	0.00	3.50	0.60
324	2.2	1.3	0.00	3.50	0.63
325	2.3	1.2	0.00	3.50	0.66
326	2.4	1.1	0.00	3.50	0.69
327	2.5	1	0.00	3.50	0.71
328	2.6	0.9	0.00	3.50	0.74
329	2.7	0.8	0.00	3.50	0.77
330	2.8	0.7	0.00	3.50	0.80

No.	Added amount based on basic components (mass%)				SnO ₂ /(SnO ₂ +CeO ₂)
	SnO ₂	CeO ₂	Sb ₂ O ₃	SnO ₂ +CeO ₂	
331	2.9	0.6	0.00	3.50	0.83
332	3	0.5	0.00	3.50	0.86
333	3.1	0.4	0.00	3.50	0.89
334	3.2	0.3	0.00	3.50	0.91
335	3.3	0.2	0.00	3.50	0.94
336	3.4	0.1	0.00	3.50	0.97
337	3.43	0.07	0.00	3.50	0.98
338	3.45	0.05	0.00	3.50	0.99
339	3.46	0.04	0.00	3.50	0.99
Com.Ex.1	2.16	2.75	0	4.91	0.44
Com.Ex.2	2.21	2.8	0	5.01	0.44
Com.Ex.3	2.4	2.9	0	5.3	0.45
Com.Ex.4	2.39	3.05	0	5.44	0.44
Com.Ex.5	3.52	8.56	0	12.08	0.29
Com.Ex.6	0	0	0.50	0.00	-
Com.Ex.7	0.25	0	0.15	0.25	1.00
Com.Ex.8	1	0	0	1	1.00
Com.Ex.9	0	1	0	1	0.00

[0297]

[Table 11]

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
1-1	E	S	1.7	0.07
1-2	E	S	1.7	0.07
1-3	B	S	1.7	0.07
1-4	B	S	1.7	0.07
1-5	C	S	1.7	0.07
1-6	E	S	1.7	0.07
1-7	E	S	1.7	0.07
1-8	E	S	1.7	0.07
1-9	E	S	1.7	0.07
1-10	D	S	1.7	0.07
1-11	B	S	1.7	0.07
1-12	B	S	1.7	0.07
1-13	B	S	1.7	0.07
1-14	B	S	1.7	0.07
1-15	C	S	1.7	0.07
1-16	C	S	1.7	0.07
1-17	D	S	1.7	0.07
1-18	D	S	1.7	0.07
1-19	D	S	1.7	0.07
1-20	D	S	1.7	0.07
1-21	C	S	1.7	0.07
1-22	A	S	1.7	0.07
1-23	A	S	1.7	0.07
1-24	A	S	1.7	0.07
1-25	A	S	1.7	0.07
1-26	B	S	1.7	0.07
1-27	B	S	1.7	0.07
1-28	D	S	1.7	0.07
1-29	D	S	1.7	0.07
1-30	D	S	1.7	0.07
1-31	D	S	1.7	0.07
1-32	D	S	1.7	0.07
1-33	D	S	1.7	0.07
1-34	C	S	1.7	0.07
1-35	C	S	1.7	0.07
1-36	A	S	1.7	0.07
1-37	A	S	1.7	0.07
1-38	S	S	1.7	0.07
1-39	S	S	1.7	0.07
1-40	S	S	1.7	0.07
1-41	A	S	1.7	0.07
1-42	A	S	1.7	0.07
1-43	B	S	1.7	0.07
1-44	B	S	1.7	0.07
1-45	D	S	1.7	0.07
1-46	D	S	1.7	0.07
1-47	D	S	1.7	0.07
1-48	D	S	1.7	0.07
1-49	D	S	1.7	0.07
1-50	D	S	1.7	0.07
1-51	A	S	1.7	0.07
1-52	S	S	1.7	0.07
1-53	S	S	1.7	0.07
1-54	S	S	1.7	0.07
1-55	S	S	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
1-56	A	S	1.7	0.07
1-57	A	S	1.7	0.07
1-58	B	S	1.7	0.07
1-59	B	S	1.7	0.07
1-60	D	S	1.7	0.07
1-61	D	S	1.7	0.07
1-62	D	S	1.7	0.07
1-63	D	S	1.7	0.07
1-64	D	S	1.7	0.07
1-65	D	S	1.7	0.07
1-66	D	S	1.7	0.07
1-67	D	S	1.7	0.07
1-68	C	S	1.7	0.07
1-69	B	S	1.7	0.07
1-70	S	S	1.7	0.07
1-71	S	S	1.7	0.07
1-72	S	S	1.7	0.07
1-73	S	S	1.7	0.07
1-74	S	S	1.7	0.07
1-75	A	A	1.7	0.07
1-76	B	A	1.7	0.07
1-77	B	A	1.7	0.07
1-78	D	S	1.7	0.07
1-79	D	S	1.7	0.07
1-80	D	S	1.7	0.07
1-81	D	S	1.7	0.07
1-82	D	S	1.7	0.07
1-83	D	S	1.7	0.07
1-84	D	S	1.7	0.07
1-85	C	S	1.7	0.07
1-86	B	S	1.7	0.07
1-87	S	S	1.7	0.07
1-88	S	S	1.7	0.07
1-89	S	S	1.7	0.07
1-90	S	S	1.7	0.07
1-91	S	S	1.7	0.07
1-92	S	A	1.7	0.07
1-93	S	A	1.7	0.07
1-94	A	A	1.7	0.07
1-95	A	A	1.7	0.07
1-96	B	A	1.7	0.07
1-97	B	A	1.7	0.07
1-98	B	A	1.7	0.07
1-99	B	A	1.7	0.07
1-100	D	B	1.7	0.07
1-101	D	B	1.7	0.07
1-102	D	B	1.7	0.07
1-103	D	B	1.7	0.07
1-104	D	B	1.7	0.07
1-105	D	B	1.7	0.07
1-106	D	B	1.7	0.07
1-107	C	B	1.7	0.07
1-108	B	B	1.7	0.07
1-109	B	B	1.7	0.07
1-110	S	B	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
1-111	S	B	1.7	0.07
1-112	S	B	1.7	0.07
1-113	S	B	1.7	0.07
1-114	S	B	1.7	0.07
1-115	S	B	1.7	0.07
1-116	S	B	1.7	0.07
1-117	S	B	1.7	0.07
1-118	S	B	1.7	0.07
1-119	A	B	1.7	0.07
1-120	A	B	1.7	0.07
1-121	B	B	1.7	0.07
1-122	B	B	1.7	0.07
1-123	D	B	1.7	0.07
1-124	D	B	1.7	0.07
1-125	D	B	1.7	0.07
1-126	D	B	1.7	0.07
1-127	D	B	1.7	0.07
1-128	D	B	1.7	0.07
1-129	D	B	1.7	0.07
1-130	C	B	1.7	0.07
1-131	C	B	1.7	0.07
1-132	B	B	1.7	0.07
1-133	B	B	1.7	0.07
1-134	S	B	1.7	0.07
1-135	S	B	1.7	0.07
1-136	S	B	1.7	0.07
1-137	S	B	1.7	0.07
1-138	S	B	1.7	0.07
1-139	S	B	1.7	0.07
1-140	S	B	1.7	0.07
1-141	S	B	1.7	0.07
1-142	S	B	1.7	0.07
1-143	A	B	1.7	0.07
1-144	A	B	1.7	0.07
1-145	B	B	1.7	0.07
1-146	B	B	1.7	0.07
1-147	B	B	1.7	0.07
1-148	D	B	1.7	0.07
1-149	D	B	1.7	0.07
1-150	D	B	1.7	0.07
1-151	D	B	1.7	0.07
1-152	D	B	1.7	0.07
1-153	C	B	1.7	0.07
1-154	C	B	1.7	0.07
1-155	C	B	1.7	0.07
1-156	C	B	1.7	0.07
1-157	B	B	1.7	0.07
1-158	B	B	1.7	0.07
1-159	S	B	1.7	0.07
1-160	S	B	1.7	0.07
1-161	S	B	1.7	0.07
1-162	S	B	1.7	0.07
1-163	S	B	1.7	0.07
1-164	S	B	1.7	0.07
1-165	S	B	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
1-166	S	B	1.7	0.07
1-167	S	B	1.7	0.07
1-168	A	B	1.7	0.07
1-169	A	B	1.7	0.07
1-170	A	B	1.7	0.07
1-171	B	B	1.7	0.07
1-172	B	B	1.7	0.07
1-173	D	B	1.7	0.07
1-174	D	B	1.7	0.07
1-175	D	B	1.7	0.07
1-176	D	B	1.7	0.07
1-177	D	B	1.7	0.07
1-178	D	B	1.7	0.07
1-179	C	B	1.7	0.07
1-180	C	B	1.7	0.07
1-181	C	B	1.7	0.07
1-182	C	B	1.7	0.07
1-183	B	B	1.7	0.07
1-184	B	B	1.7	0.07
1-185	B	B	1.7	0.07
1-186	S	B	1.7	0.07
1-187	S	B	1.7	0.07
1-188	S	B	1.7	0.07
1-189	S	B	1.7	0.07
1-190	S	B	1.7	0.07
1-191	S	B	1.7	0.07
1-192	S	B	1.7	0.07
1-193	S	B	1.7	0.07
1-194	S	B	1.7	0.07
1-195	S	B	1.7	0.07
1-196	A	B	1.7	0.07
1-197	A	B	1.7	0.07
1-198	A	B	1.7	0.07
1-199	B	B	1.7	0.07
1-200	B	B	1.7	0.07
1-201	E	B	1.7	0.07
1-202	D	C	1.7	0.07
1-203	D	C	1.7	0.07
1-204	D	C	1.7	0.07
1-205	D	C	1.7	0.07
1-206	D	C	1.7	0.07
1-207	D	C	1.7	0.07
1-208	C	C	1.7	0.07
1-209	C	C	1.7	0.07
1-210	C	C	1.7	0.07
1-211	C	C	1.7	0.07
1-212	C	C	1.7	0.07
1-213	B	C	1.7	0.07
1-214	B	C	1.7	0.07
1-215	B	C	1.7	0.07
1-216	S	C	1.7	0.07
1-217	S	C	1.7	0.07
1-218	S	C	1.7	0.07
1-219	S	C	1.7	0.07
1-220	S	C	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm./min)	Alkaline etching rate (nm./min)
1-221	S	C	1.7	0.07
1-222	S	C	1.7	0.07
1-223	S	C	1.7	0.07
1-224	S	C	1.7	0.07
1-225	S	C	1.7	0.07
1-226	S	C	1.7	0.07
1-227	S	C	1.7	0.07
1-228	A	C	1.7	0.07
1-229	A	C	1.7	0.07
1-230	A	C	1.7	0.07
1-231	B	C	1.7	0.07
1-232	B	C	1.7	0.07
1-233	D	C	1.7	0.07
1-234	D	C	1.7	0.07
1-235	D	C	1.7	0.07
1-236	D	C	1.7	0.07
1-237	D	C	1.7	0.07
1-238	D	C	1.7	0.07
1-239	C	C	1.7	0.07
1-240	C	C	1.7	0.07
1-241	C	C	1.7	0.07
1-242	C	C	1.7	0.07
1-243	C	C	1.7	0.07
1-244	C	C	1.7	0.07
1-245	B	C	1.7	0.07
1-246	B	C	1.7	0.07
1-247	B	C	1.7	0.07
1-248	S	C	1.7	0.07
1-249	S	C	1.7	0.07
1-250	S	C	1.7	0.07
1-251	S	C	1.7	0.07
1-252	S	C	1.7	0.07
1-253	S	C	1.7	0.07
1-254	S	C	1.7	0.07
1-255	S	C	1.7	0.07
1-256	S	C	1.7	0.07
1-257	S	C	1.7	0.07
1-258	S	C	1.7	0.07
1-259	S	C	1.7	0.07
1-260	A	C	1.7	0.07
1-261	A	C	1.7	0.07
1-262	A	C	1.7	0.07
1-263	A	C	1.7	0.07
1-264	B	C	1.7	0.07
1-265	B	C	1.7	0.07
1-266	D	C	1.7	0.07
1-267	D	C	1.7	0.07
1-268	D	C	1.7	0.07
1-269	D	C	1.7	0.07
1-270	D	C	1.7	0.07
1-271	C	C	1.7	0.07
1-272	C	C	1.7	0.07
1-273	C	C	1.7	0.07
1-274	C	C	1.7	0.07
1-275	C	C	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
1-276	C	C	1.7	0.07
1-277	C	C	1.7	0.07
1-278	B	C	1.7	0.07
1-279	B	C	1.7	0.07
1-280	B	C	1.7	0.07
1-281	S	C	1.7	0.07
1-282	S	C	1.7	0.07
1-283	S	C	1.7	0.07
1-284	S	C	1.7	0.07
1-285	S	C	1.7	0.07
1-286	S	C	1.7	0.07
1-287	S	C	1.7	0.07
1-288	S	C	1.7	0.07
1-289	S	C	1.7	0.07
1-290	S	C	1.7	0.07
1-291	S	C	1.7	0.07
1-292	S	C	1.7	0.07
1-293	S	C	1.7	0.07
1-294	A	C	1.7	0.07
1-295	A	C	1.7	0.07
1-296	A	C	1.7	0.07
1-297	A	C	1.7	0.07
1-298	B	C	1.7	0.07
1-299	B	C	1.7	0.07
1-300	D	C	1.7	0.07
1-301	D	C	1.7	0.07
1-302	D	C	1.7	0.07
1-303	D	C	1.7	0.07
1-304	D	C	1.7	0.07
1-305	D	C	1.7	0.07
1-306	C	C	1.7	0.07
1-307	C	C	1.7	0.07
1-308	C	C	1.7	0.07
1-309	C	C	1.7	0.07
1-310	C	C	1.7	0.07
1-311	C	C	1.7	0.07
1-312	C	C	1.7	0.07
1-313	C	C	1.7	0.07
1-314	B	C	1.7	0.07
1-315	B	C	1.7	0.07
1-316	B	C	1.7	0.07
1-317	S	C	1.7	0.07
1-318	S	C	1.7	0.07
1-319	S	C	1.7	0.07
1-320	S	C	1.7	0.07
1-321	S	C	1.7	0.07
1-322	S	C	1.7	0.07
1-323	S	C	1.7	0.07
1-324	S	C	1.7	0.07
1-325	S	C	1.7	0.07
1-326	S	C	1.7	0.07
1-327	S	C	1.7	0.07
1-328	S	C	1.7	0.07
1-329	S	C	1.7	0.07
1-330	S	C	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
1-331	S	C	1.7	0.07
1-332	A	C	1.7	0.07
1-333	A	C	1.7	0.07
1-334	A	C	1.7	0.07
1-335	A	C	1.7	0.07
1-336	A	C	1.7	0.07
1-337	B	C	1.7	0.07
1-338	B	C	1.7	0.07
1-339	B	C	1.7	0.07
Com.Ex.1-1	C	D	1.7	0.07
Com.Ex.1-2	C	D	1.7	0.07
Com.Ex.1-3	B	D	1.7	0.07
Com.Ex.1-4	C	D	1.7	0.07
Com.Ex.1-5	E	D	1.7	0.07
Com.Ex.1-6	G	S	1.7	0.07
Com.Ex.1-7	G	S	1.7	0.07
Com.Ex.1-8	G	S	1.7	0.07
Com.Ex.1-9	G	S	1.7	0.07

[0298]

[Table 12]

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-1	E	S	1.7	0.07
2-2	E	S	1.7	0.07
2-3	B	S	1.7	0.07
2-4	B	S	1.7	0.07
2-5	C	S	1.7	0.07
2-6	E	S	1.7	0.07
2-7	E	S	1.7	0.07
2-8	E	S	1.7	0.07
2-9	E	S	1.7	0.07
2-10	D	S	1.7	0.07
2-11	B	S	1.7	0.07
2-12	B	S	1.7	0.07
2-13	B	S	1.7	0.07
2-14	B	S	1.7	0.07
2-15	C	S	1.7	0.07
2-16	C	S	1.7	0.07
2-17	D	S	1.7	0.07
2-18	D	S	1.7	0.07
2-19	D	S	1.7	0.07
2-20	D	S	1.7	0.07
2-21	C	S	1.7	0.07
2-22	A	S	1.7	0.07
2-23	A	S	1.7	0.07
2-24	A	S	1.7	0.07
2-25	A	S	1.7	0.07
2-26	B	S	1.7	0.07
2-27	B	S	1.7	0.07
2-28	D	S	1.7	0.07
2-29	D	S	1.7	0.07
2-30	D	S	1.7	0.07
2-31	D	S	1.7	0.07
2-32	D	S	1.7	0.07
2-33	D	S	1.7	0.07
2-34	C	S	1.7	0.07
2-35	C	S	1.7	0.07
2-36	A	S	1.7	0.07
2-37	A	S	1.7	0.07
2-38	S	S	1.7	0.07
2-39	S	S	1.7	0.07
2-40	S	S	1.7	0.07
2-41	A	S	1.7	0.07
2-42	A	S	1.7	0.07
2-43	B	S	1.7	0.07
2-44	B	S	1.7	0.07
2-45	D	S	1.7	0.07
2-46	D	S	1.7	0.07
2-47	D	S	1.7	0.07
2-48	D	S	1.7	0.07
2-49	D	S	1.7	0.07
2-50	D	S	1.7	0.07
2-51	A	S	1.7	0.07
2-52	S	S	1.7	0.07
2-53	S	S	1.7	0.07
2-54	S	S	1.7	0.07
2-55	S	S	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-56	A	S	1.7	0.07
2-57	A	S	1.7	0.07
2-58	B	S	1.7	0.07
2-59	B	S	1.7	0.07
2-60	D	S	1.7	0.07
2-61	D	S	1.7	0.07
2-62	D	S	1.7	0.07
2-63	D	S	1.7	0.07
2-64	D	S	1.7	0.07
2-65	D	S	1.7	0.07
2-66	D	S	1.7	0.07
2-67	D	S	1.7	0.07
2-68	C	S	1.7	0.07
2-69	B	S	1.7	0.07
2-70	S	S	1.7	0.07
2-71	S	S	1.7	0.07
2-72	S	S	1.7	0.07
2-73	S	S	1.7	0.07
2-74	S	S	1.7	0.07
2-75	A	A	1.7	0.07
2-76	B	A	1.7	0.07
2-77	B	A	1.7	0.07
2-78	D	S	1.7	0.07
2-79	D	S	1.7	0.07
2-80	D	S	1.7	0.07
2-81	D	S	1.7	0.07
2-82	D	S	1.7	0.07
2-83	D	S	1.7	0.07
2-84	D	S	1.7	0.07
2-85	C	S	1.7	0.07
2-86	B	S	1.7	0.07
2-87	S	S	1.7	0.07
2-88	S	S	1.7	0.07
2-89	S	S	1.7	0.07
2-90	S	S	1.7	0.07
2-91	S	S	1.7	0.07
2-92	S	A	1.7	0.07
2-93	S	A	1.7	0.07
2-94	A	A	1.7	0.07
2-95	A	A	1.7	0.07
2-96	B	A	1.7	0.07
2-97	B	A	1.7	0.07
2-98	B	A	1.7	0.07
2-99	B	A	1.7	0.07
2-100	D	B	1.7	0.07
2-101	D	B	1.7	0.07
2-102	D	B	1.7	0.07
2-103	D	B	1.7	0.07
2-104	D	B	1.7	0.07
2-105	D	B	1.7	0.07
2-106	D	B	1.7	0.07
2-107	C	B	1.7	0.07
2-108	B	B	1.7	0.07
2-109	B	B	1.7	0.07
2-110	S	B	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-111	S	B	1.7	0.07
2-112	S	B	1.7	0.07
2-113	S	B	1.7	0.07
2-114	S	B	1.7	0.07
2-115	S	B	1.7	0.07
2-116	S	B	1.7	0.07
2-117	S	B	1.7	0.07
2-118	S	B	1.7	0.07
2-119	A	B	1.7	0.07
2-120	A	B	1.7	0.07
2-121	B	B	1.7	0.07
2-122	B	B	1.7	0.07
2-123	D	B	1.7	0.07
2-124	D	B	1.7	0.07
2-125	D	B	1.7	0.07
2-126	D	B	1.7	0.07
2-127	D	B	1.7	0.07
2-128	D	B	1.7	0.07
2-129	D	B	1.7	0.07
2-130	C	B	1.7	0.07
2-131	C	B	1.7	0.07
2-132	B	B	1.7	0.07
2-133	B	B	1.7	0.07
2-134	S	B	1.7	0.07
2-135	S	B	1.7	0.07
2-136	S	B	1.7	0.07
2-137	S	B	1.7	0.07
2-138	S	B	1.7	0.07
2-139	S	B	1.7	0.07
2-140	S	B	1.7	0.07
2-141	S	B	1.7	0.07
2-142	S	B	1.7	0.07
2-143	A	B	1.7	0.07
2-144	A	B	1.7	0.07
2-145	B	B	1.7	0.07
2-146	B	B	1.7	0.07
2-147	B	B	1.7	0.07
2-148	D	B	1.7	0.07
2-149	D	B	1.7	0.07
2-150	D	B	1.7	0.07
2-151	D	B	1.7	0.07
2-152	D	B	1.7	0.07
2-153	C	B	1.7	0.07
2-154	C	B	1.7	0.07
2-155	C	B	1.7	0.07
2-156	C	B	1.7	0.07
2-157	B	B	1.7	0.07
2-158	B	B	1.7	0.07
2-159	S	B	1.7	0.07
2-160	S	B	1.7	0.07
2-161	S	B	1.7	0.07
2-162	S	B	1.7	0.07
2-163	S	B	1.7	0.07
2-164	S	B	1.7	0.07
2-165	S	B	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-166	S	B	1.7	0.07
2-167	S	B	1.7	0.07
2-168	A	B	1.7	0.07
2-169	A	B	1.7	0.07
2-170	A	B	1.7	0.07
2-171	B	B	1.7	0.07
2-172	B	B	1.7	0.07
2-173	D	B	1.7	0.07
2-174	D	B	1.7	0.07
2-175	D	B	1.7	0.07
2-176	D	B	1.7	0.07
2-177	D	B	1.7	0.07
2-178	D	B	1.7	0.07
2-179	C	B	1.7	0.07
2-180	C	B	1.7	0.07
2-181	C	B	1.7	0.07
2-182	C	B	1.7	0.07
2-183	B	B	1.7	0.07
2-184	B	B	1.7	0.07
2-185	B	B	1.7	0.07
2-186	S	B	1.7	0.07
2-187	S	B	1.7	0.07
2-188	S	B	1.7	0.07
2-189	S	B	1.7	0.07
2-190	S	B	1.7	0.07
2-191	S	B	1.7	0.07
2-192	S	B	1.7	0.07
2-193	S	B	1.7	0.07
2-194	S	B	1.7	0.07
2-195	S	B	1.7	0.07
2-196	A	B	1.7	0.07
2-197	A	B	1.7	0.07
2-198	A	B	1.7	0.07
2-199	B	B	1.7	0.07
2-200	B	B	1.7	0.07
2-201	E	B	1.7	0.07
2-202	D	C	1.7	0.07
2-203	D	C	1.7	0.07
2-204	D	C	1.7	0.07
2-205	D	C	1.7	0.07
2-206	D	C	1.7	0.07
2-207	D	C	1.7	0.07
2-208	C	C	1.7	0.07
2-209	C	C	1.7	0.07
2-210	C	C	1.7	0.07
2-211	C	C	1.7	0.07
2-212	C	C	1.7	0.07
2-213	B	C	1.7	0.07
2-214	B	C	1.7	0.07
2-215	B	C	1.7	0.07
2-216	S	C	1.7	0.07
2-217	S	C	1.7	0.07
2-218	S	C	1.7	0.07
2-219	S	C	1.7	0.07
2-220	S	C	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-221	S	C	1.7	0.07
2-222	S	C	1.7	0.07
2-223	S	C	1.7	0.07
2-224	S	C	1.7	0.07
2-225	S	C	1.7	0.07
2-226	S	C	1.7	0.07
2-227	S	C	1.7	0.07
2-228	A	C	1.7	0.07
2-229	A	C	1.7	0.07
2-230	A	C	1.7	0.07
2-231	B	C	1.7	0.07
2-232	B	C	1.7	0.07
2-233	D	C	1.7	0.07
2-234	D	C	1.7	0.07
2-235	D	C	1.7	0.07
2-236	D	C	1.7	0.07
2-237	D	C	1.7	0.07
2-238	D	C	1.7	0.07
2-239	C	C	1.7	0.07
2-240	C	C	1.7	0.07
2-241	C	C	1.7	0.07
2-242	C	C	1.7	0.07
2-243	C	C	1.7	0.07
2-244	C	C	1.7	0.07
2-245	B	C	1.7	0.07
2-246	B	C	1.7	0.07
2-247	B	C	1.7	0.07
2-248	S	C	1.7	0.07
2-249	S	C	1.7	0.07
2-250	S	C	1.7	0.07
2-251	S	C	1.7	0.07
2-252	S	C	1.7	0.07
2-253	S	C	1.7	0.07
2-254	S	C	1.7	0.07
2-255	S	C	1.7	0.07
2-256	S	C	1.7	0.07
2-257	S	C	1.7	0.07
2-258	S	C	1.7	0.07
2-259	S	C	1.7	0.07
2-260	A	C	1.7	0.07
2-261	A	C	1.7	0.07
2-262	A	C	1.7	0.07
2-263	A	C	1.7	0.07
2-264	B	C	1.7	0.07
2-265	B	C	1.7	0.07
2-266	D	C	1.7	0.07
2-267	D	C	1.7	0.07
2-268	D	C	1.7	0.07
2-269	D	C	1.7	0.07
2-270	D	C	1.7	0.07
2-271	C	C	1.7	0.07
2-272	C	C	1.7	0.07
2-273	C	C	1.7	0.07
2-274	C	C	1.7	0.07
2-275	C	C	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-276	C	C	1.7	0.07
2-277	C	C	1.7	0.07
2-278	B	C	1.7	0.07
2-279	B	C	1.7	0.07
2-280	B	C	1.7	0.07
2-281	S	C	1.7	0.07
2-282	S	C	1.7	0.07
2-283	S	C	1.7	0.07
2-284	S	C	1.7	0.07
2-285	S	C	1.7	0.07
2-286	S	C	1.7	0.07
2-287	S	C	1.7	0.07
2-288	S	C	1.7	0.07
2-289	S	C	1.7	0.07
2-290	S	C	1.7	0.07
2-291	S	C	1.7	0.07
2-292	S	C	1.7	0.07
2-293	S	C	1.7	0.07
2-294	A	C	1.7	0.07
2-295	A	C	1.7	0.07
2-296	A	C	1.7	0.07
2-297	A	C	1.7	0.07
2-298	B	C	1.7	0.07
2-299	B	C	1.7	0.07
2-300	D	C	1.7	0.07
2-301	D	C	1.7	0.07
2-302	D	C	1.7	0.07
2-303	D	C	1.7	0.07
2-304	D	C	1.7	0.07
2-305	D	C	1.7	0.07
2-306	C	C	1.7	0.07
2-307	C	C	1.7	0.07
2-308	C	C	1.7	0.07
2-309	C	C	1.7	0.07
2-310	C	C	1.7	0.07
2-311	C	C	1.7	0.07
2-312	C	C	1.7	0.07
2-313	C	C	1.7	0.07
2-314	B	C	1.7	0.07
2-315	B	C	1.7	0.07
2-316	B	C	1.7	0.07
2-317	S	C	1.7	0.07
2-318	S	C	1.7	0.07
2-319	S	C	1.7	0.07
2-320	S	C	1.7	0.07
2-321	S	C	1.7	0.07
2-322	S	C	1.7	0.07
2-323	S	C	1.7	0.07
2-324	S	C	1.7	0.07
2-325	S	C	1.7	0.07
2-326	S	C	1.7	0.07
2-327	S	C	1.7	0.07
2-328	S	C	1.7	0.07
2-329	S	C	1.7	0.07
2-330	S	C	1.7	0.07

No.	Bubbles rank	Unmelted rank	Acid etching rate (nm/min)	Alkaline etching rate (nm/min)
2-331	S	C	1.7	0.07
2-332	A	C	1.7	0.07
2-333	A	C	1.7	0.07
2-334	A	C	1.7	0.07
2-335	A	C	1.7	0.07
2-336	A	C	1.7	0.07
2-337	B	C	1.7	0.07
2-338	B	C	1.7	0.07
2-339	B	C	1.7	0.07
Com.Ex.2-1	C	D	1.7	0.07
Com.Ex.2-2	C	D	1.7	0.07
Com.Ex.2-3	B	D	1.7	0.07
Com.Ex.2-4	C	D	1.7	0.07
Com.Ex.2-5	E	D	1.7	0.07
Com.Ex.2-6	G	S	1.7	0.07
Com.Ex.2-7	G	S	1.7	0.07
Com.Ex.2-8	G	S	1.7	0.07
Com.Ex.2-9	G	S	1.7	0.07

[0299]

[Table 13]

No.	Bubbles rank	Unmelted rank
3-1	E	S
3-2	E	S
3-3	B	S
3-4	B	S
3-5	C	S
3-6	E	S
3-7	E	S
3-8	E	S
3-9	E	S
3-10	D	S
3-11	B	S
3-12	B	S
3-13	B	S
3-14	B	S
3-15	C	S
3-16	C	S
3-17	D	S
3-18	D	S
3-19	D	S
3-20	D	S
3-21	C	S
3-22	A	S
3-23	A	S
3-24	A	S
3-25	A	S
3-26	B	S
3-27	B	S
3-28	D	S
3-29	D	S
3-30	D	S
3-31	D	S
3-32	D	S
3-33	D	S
3-34	C	S
3-35	C	S
3-36	A	S
3-37	A	S
3-38	S	S
3-39	S	S
3-40	S	S
3-41	A	S
3-42	A	S
3-43	B	S
3-44	B	S
3-45	D	S
3-46	D	S
3-47	D	S
3-48	D	S
3-49	D	S
3-50	D	S
3-51	A	S
3-52	S	S
3-53	S	S
3-54	S	S
3-55	S	S
3-56	A	S
3-57	A	S
3-58	B	S
3-59	B	S
3-60	D	S

No.	Bubbles rank	Unmelted rank
3-61	D	S
3-62	D	S
3-63	D	S
3-64	D	S
3-65	D	S
3-66	D	S
3-67	D	S
3-68	C	S
3-69	B	S
3-70	S	S
3-71	S	S
3-72	S	S
3-73	S	S
3-74	S	S
3-75	A	A
3-76	B	A
3-77	B	A
3-78	D	S
3-79	D	S
3-80	D	S
3-81	D	S
3-82	D	S
3-83	D	S
3-84	D	S
3-85	C	S
3-86	B	S
3-87	S	S
3-88	S	S
3-89	S	S
3-90	S	S
3-91	S	S
3-92	S	A
3-93	S	A
3-94	A	A
3-95	A	A
3-96	B	A
3-97	B	A
3-98	B	A
3-99	B	A
3-100	D	B
3-101	D	B
3-102	D	B
3-103	D	B
3-104	D	B
3-105	D	B
3-106	D	B
3-107	C	B
3-108	B	B
3-109	B	B
3-110	S	B
3-111	S	B
3-112	S	B
3-113	S	B
3-114	S	B
3-115	S	B
3-116	S	B
3-117	S	B
3-118	S	B
3-119	A	B
3-120	A	B

No.	Bubbles rank	Unmelted rank
3-121	B	B
3-122	B	B
3-123	D	B
3-124	D	B
3-125	D	B
3-126	D	B
3-127	D	B
3-128	D	B
3-129	D	B
3-130	C	B
3-131	C	B
3-132	B	B
3-133	B	B
3-134	S	B
3-135	S	B
3-136	S	B
3-137	S	B
3-138	S	B
3-139	S	B
3-140	S	B
3-141	S	B
3-142	S	B
3-143	A	B
3-144	A	B
3-145	B	B
3-146	B	B
3-147	B	B
3-148	D	B
3-149	D	B
3-150	D	B
3-151	D	B
3-152	D	B
3-153	C	B
3-154	C	B
3-155	C	B
3-156	C	B
3-157	B	B
3-158	B	B
3-159	S	B
3-160	S	B
3-161	S	B
3-162	S	B
3-163	S	B
3-164	S	B
3-165	S	B
3-166	S	B
3-167	S	B
3-168	A	B
3-169	A	B
3-170	A	B
3-171	B	B
3-172	B	B
3-173	D	B
3-174	D	B
3-175	D	B
3-176	D	B
3-177	D	B
3-178	D	B
3-179	C	B
3-180	C	B

No.	Bubbles rank	Unmelted rank
3-181	C	B
3-182	C	B
3-183	B	B
3-184	B	B
3-185	B	B
3-186	S	B
3-187	S	B
3-188	S	B
3-189	S	B
3-190	S	B
3-191	S	B
3-192	S	B
3-193	S	B
3-194	S	B
3-195	S	B
3-196	A	B
3-197	A	B
3-198	A	B
3-199	B	B
3-200	B	B
3-201	E	B
3-202	D	C
3-203	D	C
3-204	D	C
3-205	D	C
3-206	D	C
3-207	D	C
3-208	C	C
3-209	C	C
3-210	C	C
3-211	C	C
3-212	C	C
3-213	B	C
3-214	B	C
3-215	B	C
3-216	S	C
3-217	S	C
3-218	S	C
3-219	S	C
3-220	S	C
3-221	S	C
3-222	S	C
3-223	S	C
3-224	S	C
3-225	S	C
3-226	S	C
3-227	S	C
3-228	A	C
3-229	A	C
3-230	A	C
3-231	B	C
3-232	B	C
3-233	D	C
3-234	D	C
3-235	D	C
3-236	D	C
3-237	D	C
3-238	D	C
3-239	C	C
3-240	C	C

No.	Bubbles rank	Unmelted rank
3-241	C	C
3-242	C	C
3-243	C	C
3-244	C	C
3-245	B	C
3-246	B	C
3-247	B	C
3-248	S	C
3-249	S	C
3-250	S	C
3-251	S	C
3-252	S	C
3-253	S	C
3-254	S	C
3-255	S	C
3-256	S	C
3-257	S	C
3-258	S	C
3-259	S	C
3-260	A	C
3-261	A	C
3-262	A	C
3-263	A	C
3-264	B	C
3-265	B	C
3-266	D	C
3-267	D	C
3-268	D	C
3-269	D	C
3-270	D	C
3-271	C	C
3-272	C	C
3-273	C	C
3-274	C	C
3-275	C	C
3-276	C	C
3-277	C	C
3-278	B	C
3-279	B	C
3-280	B	C
3-281	S	C
3-282	S	C
3-283	S	C
3-284	S	C
3-285	S	C
3-286	S	C
3-287	S	C
3-288	S	C
3-289	S	C
3-290	S	C
3-291	S	C
3-292	S	C
3-293	S	C
3-294	A	C
3-295	A	C

No.	Bubbles rank	Unmelted rank
3-296	A	C
3-297	A	C
3-298	B	C
3-299	B	C
3-300	D	C
3-301	D	C
3-302	D	C
3-303	D	C
3-304	D	C
3-305	D	C
3-306	C	C
3-307	C	C
3-308	C	C
3-309	C	C
3-310	C	C
3-311	C	C
3-312	C	C
3-313	C	C
3-314	B	C
3-315	B	C
3-316	B	C
3-317	S	C
3-318	S	C
3-319	S	C
3-320	S	C
3-321	S	C
3-322	S	C
3-323	S	C
3-324	S	C
3-325	S	C
3-326	S	C
3-327	S	C
3-328	S	C
3-329	S	C
3-330	S	C
3-331	S	C
3-332	A	C
3-333	A	C
3-334	A	C
3-335	A	C
3-336	A	C
3-337	B	C
3-338	B	C
3-339	B	C
Com.Ex.3-1	C	D
Com.Ex.3-2	C	D
Com.Ex.3-3	B	D
Com.Ex.3-4	C	D
Com.Ex.3-5	E	D
Com.Ex.3-6	G	S
Com.Ex.3-7	G	S
Com.Ex.3-8	G	S
Com.Ex.3-9	G	S

[0300]

[Table 14]

No.	Bubbles rank	Unmelted rank
4-1	E	S
4-2	E	S
4-3	B	S
4-4	B	S
4-5	C	S
4-6	E	S
4-7	E	S
4-8	E	S
4-9	E	S
4-10	D	S
4-11	B	S
4-12	B	S
4-13	B	S
4-14	B	S
4-15	C	S
4-16	C	S
4-17	D	S
4-18	D	S
4-19	D	S
4-20	D	S
4-21	C	S
4-22	A	S
4-23	A	S
4-24	A	S
4-25	A	S
4-26	B	S
4-27	B	S
4-28	D	S
4-29	D	S
4-30	D	S
4-31	D	S
4-32	D	S
4-33	D	S
4-34	C	S
4-35	C	S
4-36	A	S
4-37	A	S
4-38	S	S
4-39	S	S
4-40	S	S
4-41	A	S
4-42	A	S
4-43	B	S
4-44	B	S
4-45	D	S
4-46	D	S
4-47	D	S
4-48	D	S
4-49	D	S
4-50	D	S
4-51	A	S
4-52	S	S
4-53	S	S
4-54	S	S
4-55	S	S
4-56	A	S
4-57	A	S
4-58	B	S
4-59	B	S
4-60	D	S

No.	Bubbles rank	Unmelted rank
4-61	D	S
4-62	D	S
4-63	D	S
4-64	D	S
4-65	D	S
4-66	D	S
4-67	D	S
4-68	C	S
4-69	B	S
4-70	S	S
4-71	S	S
4-72	S	S
4-73	S	S
4-74	S	S
4-75	A	A
4-76	B	A
4-77	B	A
4-78	D	S
4-79	D	S
4-80	D	S
4-81	D	S
4-82	D	S
4-83	D	S
4-84	D	S
4-85	C	S
4-86	B	S
4-87	S	S
4-88	S	S
4-89	S	S
4-90	S	S
4-91	S	S
4-92	S	A
4-93	S	A
4-94	A	A
4-95	A	A
4-96	B	A
4-97	B	A
4-98	B	A
4-99	B	A
4-100	D	B
4-101	D	B
4-102	D	B
4-103	D	B
4-104	D	B
4-105	D	B
4-106	D	B
4-107	C	B
4-108	B	B
4-109	B	B
4-110	S	B
4-111	S	B
4-112	S	B
4-113	S	B
4-114	S	B
4-115	S	B
4-116	S	B
4-117	S	B
4-118	S	B
4-119	A	B
4-120	A	B

No.	Bubbles rank	Unmelted rank
4-121	B	B
4-122	B	B
4-123	D	B
4-124	D	B
4-125	D	B
4-126	D	B
4-127	D	B
4-128	D	B
4-129	D	B
4-130	C	B
4-131	C	B
4-132	B	B
4-133	B	B
4-134	S	B
4-135	S	B
4-136	S	B
4-137	S	B
4-138	S	B
4-139	S	B
4-140	S	B
4-141	S	B
4-142	S	B
4-143	A	B
4-144	A	B
4-145	B	B
4-146	B	B
4-147	B	B
4-148	D	B
4-149	D	B
4-150	D	B
4-151	D	B
4-152	D	B
4-153	C	B
4-154	C	B
4-155	C	B
4-156	C	B
4-157	B	B
4-158	B	B
4-159	S	B
4-160	S	B
4-161	S	B
4-162	S	B
4-163	S	B
4-164	S	B
4-165	S	B
4-166	S	B
4-167	S	B
4-168	A	B
4-169	A	B
4-170	A	B
4-171	B	B
4-172	B	B
4-173	D	B
4-174	D	B
4-175	D	B
4-176	D	B
4-177	D	B
4-178	D	B
4-179	C	B
4-180	C	B

No.	Bubbles rank	Unmelted rank
4-181	C	B
4-182	C	B
4-183	B	B
4-184	B	B
4-185	B	B
4-186	S	B
4-187	S	B
4-188	S	B
4-189	S	B
4-190	S	B
4-191	S	B
4-192	S	B
4-193	S	B
4-194	S	B
4-195	S	B
4-196	A	B
4-197	A	B
4-198	A	B
4-199	B	B
4-200	B	B
4-201	E	B
4-202	D	C
4-203	D	C
4-204	D	C
4-205	D	C
4-206	D	C
4-207	D	C
4-208	C	C
4-209	C	C
4-210	C	C
4-211	C	C
4-212	C	C
4-213	B	C
4-214	B	C
4-215	B	C
4-216	S	C
4-217	S	C
4-218	S	C
4-219	S	C
4-220	S	C
4-221	S	C
4-222	S	C
4-223	S	C
4-224	S	C
4-225	S	C
4-226	S	C
4-227	S	C
4-228	A	C
4-229	A	C
4-230	A	C
4-231	B	C
4-232	B	C
4-233	D	C
4-234	D	C
4-235	D	C
4-236	D	C
4-237	D	C
4-238	D	C
4-239	C	C
4-240	C	C

No.	Bubbles rank	Unmelted rank
4-241	C	C
4-242	C	C
4-243	C	C
4-244	C	C
4-245	B	C
4-246	B	C
4-247	B	C
4-248	S	C
4-249	S	C
4-250	S	C
4-251	S	C
4-252	S	C
4-253	S	C
4-254	S	C
4-255	S	C
4-256	S	C
4-257	S	C
4-258	S	C
4-259	S	C
4-260	A	C
4-261	A	C
4-262	A	C
4-263	A	C
4-264	B	C
4-265	B	C
4-266	D	C
4-267	D	C
4-268	D	C
4-269	D	C
4-270	D	C
4-271	C	C
4-272	C	C
4-273	C	C
4-274	C	C
4-275	C	C
4-276	C	C
4-277	C	C
4-278	B	C
4-279	B	C
4-280	B	C
4-281	S	C
4-282	S	C
4-283	S	C
4-284	S	C
4-285	S	C
4-286	S	C
4-287	S	C
4-288	S	C
4-289	S	C
4-290	S	C
4-291	S	C
4-292	S	C
4-293	S	C
4-294	A	C
4-295	A	C
4-296	A	C
4-297	A	C
4-298	B	C
4-299	B	C
4-300	D	C

No.	Bubbles rank	Unmelted rank
4-301	D	C
4-302	D	C
4-303	D	C
4-304	D	C
4-305	D	C
4-306	C	C
4-307	C	C
4-308	C	C
4-309	C	C
4-310	C	C
4-311	C	C
4-312	C	C
4-313	C	C
4-314	B	C
4-315	B	C
4-316	B	C
4-317	S	C
4-318	S	C
4-319	S	C
4-320	S	C
4-321	S	C
4-322	S	C
4-323	S	C
4-324	S	C
4-325	S	C
4-326	S	C
4-327	S	C
4-328	S	C
4-329	S	C
4-330	S	C
4-331	S	C
4-332	A	C
4-333	A	C
4-334	A	C
4-335	A	C
4-336	A	C
4-337	B	C
4-338	B	C
4-339	B	C
Com.Ex.4-1	C	D
Com.Ex.4-2	C	D
Com.Ex.4-3	B	D
Com.Ex.4-4	C	D
Com.Ex.4-5	E	D
Com.Ex.4-6	G	S
Com.Ex.4-7	G	S
Com.Ex.4-8	G	S
Com.Ex.4-9	G	S

[0301]

[Table 15]

No.	Bubbles rank	Unmelted rank
5-1	E	S
5-2	E	S
5-3	B	S
5-4	B	S
5-5	C	S
5-6	E	S
5-7	E	S
5-8	E	S
5-9	E	S
5-10	D	S
5-11	B	S
5-12	B	S
5-13	B	S
5-14	B	S
5-15	C	S
5-16	C	S
5-17	D	S
5-18	D	S
5-19	D	S
5-20	D	S
5-21	C	S
5-22	A	S
5-23	A	S
5-24	A	S
5-25	A	S
5-26	B	S
5-27	B	S
5-28	D	S
5-29	D	S
5-30	D	S
5-31	D	S
5-32	D	S
5-33	D	S
5-34	C	S
5-35	C	S
5-36	A	S
5-37	A	S
5-38	S	S
5-39	S	S
5-40	S	S
5-41	A	S
5-42	A	S
5-43	B	S
5-44	B	S
5-45	D	S
5-46	D	S
5-47	D	S
5-48	D	S
5-49	D	S
5-50	D	S
5-51	A	S
5-52	S	S
5-53	S	S
5-54	S	S
5-55	S	S
5-56	A	S
5-57	A	S
5-58	B	S
5-59	B	S
5-60	D	S

No.	Bubbles rank	Unmelted rank
5-61	D	S
5-62	D	S
5-63	D	S
5-64	D	S
5-65	D	S
5-66	D	S
5-67	D	S
5-68	C	S
5-69	B	S
5-70	S	S
5-71	S	S
5-72	S	S
5-73	S	S
5-74	S	S
5-75	A	A
5-76	B	A
5-77	B	A
5-78	D	S
5-79	D	S
5-80	D	S
5-81	D	S
5-82	D	S
5-83	D	S
5-84	D	S
5-85	C	S
5-86	B	S
5-87	S	S
5-88	S	S
5-89	S	S
5-90	S	S
5-91	S	S
5-92	S	A
5-93	S	A
5-94	A	A
5-95	A	A
5-96	B	A
5-97	B	A
5-98	B	A
5-99	B	A
5-100	D	B
5-101	D	B
5-102	D	B
5-103	D	B
5-104	D	B
5-105	D	B
5-106	D	B
5-107	C	B
5-108	B	B
5-109	B	B
5-110	S	B
5-111	S	B
5-112	S	B
5-113	S	B
5-114	S	B
5-115	S	B
5-116	S	B
5-117	S	B
5-118	S	B
5-119	A	B
5-120	A	B

No.	Bubbles rank	Unmelted rank
5-121	B	B
5-122	B	B
5-123	D	B
5-124	D	B
5-125	D	B
5-126	D	B
5-127	D	B
5-128	D	B
5-129	D	B
5-130	C	B
5-131	C	B
5-132	B	B
5-133	B	B
5-134	S	B
5-135	S	B
5-136	S	B
5-137	S	B
5-138	S	B
5-139	S	B
5-140	S	B
5-141	S	B
5-142	S	B
5-143	A	B
5-144	A	B
5-145	B	B
5-146	B	B
5-147	B	B
5-148	D	B
5-149	D	B
5-150	D	B
5-151	D	B
5-152	D	B
5-153	C	B
5-154	C	B
5-155	C	B
5-156	C	B
5-157	B	B
5-158	B	B
5-159	S	B
5-160	S	B
5-161	S	B
5-162	S	B
5-163	S	B
5-164	S	B
5-165	S	B
5-166	S	B
5-167	S	B
5-168	A	B
5-169	A	B
5-170	A	B
5-171	B	B
5-172	B	B
5-173	D	B
5-174	D	B
5-175	D	B
5-176	D	B
5-177	D	B
5-178	D	B
5-179	C	B
5-180	C	B

No.	Bubbles rank	Unmelted rank
5-181	C	B
5-182	C	B
5-183	B	B
5-184	B	B
5-185	B	B
5-186	S	B
5-187	S	B
5-188	S	B
5-189	S	B
5-190	S	B
5-191	S	B
5-192	S	B
5-193	S	B
5-194	S	B
5-195	S	B
5-196	A	B
5-197	A	B
5-198	A	B
5-199	B	B
5-200	B	B
5-201	E	B
5-202	D	C
5-203	D	C
5-204	D	C
5-205	D	C
5-206	D	C
5-207	D	C
5-208	C	C
5-209	C	C
5-210	C	C
5-211	C	C
5-212	C	C
5-213	B	C
5-214	B	C
5-215	B	C
5-216	S	C
5-217	S	C
5-218	S	C
5-219	S	C
5-220	S	C
5-221	S	C
5-222	S	C
5-223	S	C
5-224	S	C
5-225	S	C
5-226	S	C
5-227	S	C
5-228	A	C
5-229	A	C
5-230	A	C
5-231	B	C
5-232	B	C
5-233	D	C
5-234	D	C
5-235	D	C
5-236	D	C
5-237	D	C
5-238	D	C
5-239	C	C
5-240	C	C

No.	Bubbles rank	Unmelted rank
5-241	C	C
5-242	C	C
5-243	C	C
5-244	C	C
5-245	B	C
5-246	B	C
5-247	B	C
5-248	S	C
5-249	S	C
5-250	S	C
5-251	S	C
5-252	S	C
5-253	S	C
5-254	S	C
5-255	S	C
5-256	S	C
5-257	S	C
5-258	S	C
5-259	S	C
5-260	A	C
5-261	A	C
5-262	A	C
5-263	A	C
5-264	B	C
5-265	B	C
5-266	D	C
5-267	D	C
5-268	D	C
5-269	D	C
5-270	D	C
5-271	C	C
5-272	C	C
5-273	C	C
5-274	C	C
5-275	C	C
5-276	C	C
5-277	C	C
5-278	B	C
5-279	B	C
5-280	B	C
5-281	S	C
5-282	S	C
5-283	S	C
5-284	S	C
5-285	S	C
5-286	S	C
5-287	S	C
5-288	S	C
5-289	S	C
5-290	S	C
5-291	S	C
5-292	S	C
5-293	S	C
5-294	A	C
5-295	A	C
5-296	A	C
5-297	A	C
5-298	B	C
5-299	B	C
5-300	D	C

No.	Bubbles rank	Unmelted rank
5-301	D	C
5-302	D	C
5-303	D	C
5-304	D	C
5-305	D	C
5-306	C	C
5-307	C	C
5-308	C	C
5-309	C	C
5-310	C	C
5-311	C	C
5-312	C	C
5-313	C	C
5-314	B	C
5-315	B	C
5-316	B	C
5-317	S	C
5-318	S	C
5-319	S	C
5-320	S	C
5-321	S	C
5-322	S	C
5-323	S	C
5-324	S	C
5-325	S	C
5-326	S	C
5-327	S	C
5-328	S	C
5-329	S	C
5-330	S	C
5-331	S	C
5-332	A	C
5-333	A	C
5-334	A	C
5-335	A	C
5-336	A	C
5-337	B	C
5-338	B	C
5-339	B	C
Com.Ex.5-1	C	D
Com.Ex.5-2	C	D
Com.Ex.5-3	B	D
Com.Ex.5-4	C	D
Com.Ex.5-5	E	D
Com.Ex.5-6	G	S
Com.Ex.5-7	G	S
Com.Ex.5-8	G	S
Com.Ex.5-9	G	S

[0302]

[Table 16]

No.	Bubbles rank	Unmelted rank
6-1	E	S
6-2	E	S
6-3	B	S
6-4	B	S
6-5	C	S
6-6	E	S
6-7	E	S
6-8	E	S
6-9	E	S
6-10	D	S
6-11	B	S
6-12	B	S
6-13	B	S
6-14	B	S
6-15	C	S
6-16	C	S
6-17	D	S
6-18	D	S
6-19	D	S
6-20	D	S
6-21	C	S
6-22	A	S
6-23	A	S
6-24	A	S
6-25	A	S
6-26	B	S
6-27	B	S
6-28	D	S
6-29	D	S
6-30	D	S
6-31	D	S
6-32	D	S
6-33	D	S
6-34	C	S
6-35	C	S
6-36	A	S
6-37	A	S
6-38	S	S
6-39	S	S
6-40	S	S
6-41	A	S
6-42	A	S
6-43	B	S
6-44	B	S
6-45	D	S
6-46	D	S
6-47	D	S
6-48	D	S
6-49	D	S
6-50	D	S
6-51	A	S
6-52	S	S
6-53	S	S
6-54	S	S
6-55	S	S
6-56	A	S
6-57	A	S
6-58	B	S
6-59	B	S
6-60	D	S

No.	Bubbles rank	Unmelted rank
6-61	D	S
6-62	D	S
6-63	D	S
6-64	D	S
6-65	D	S
6-66	D	S
6-67	D	S
6-68	C	S
6-69	B	S
6-70	S	S
6-71	S	S
6-72	S	S
6-73	S	S
6-74	S	S
6-75	A	A
6-76	B	A
6-77	B	A
6-78	D	S
6-79	D	S
6-80	D	S
6-81	D	S
6-82	D	S
6-83	D	S
6-84	D	S
6-85	C	S
6-86	B	S
6-87	S	S
6-88	S	S
6-89	S	S
6-90	S	S
6-91	S	S
6-92	S	A
6-93	S	A
6-94	A	A
6-95	A	A
6-96	B	A
6-97	B	A
6-98	B	A
6-99	B	A
6-100	D	B
6-101	D	B
6-102	D	B
6-103	D	B
6-104	D	B
6-105	D	B
6-106	D	B
6-107	C	B
6-108	B	B
6-109	B	B
6-110	S	B
6-111	S	B
6-112	S	B
6-113	S	B
6-114	S	B
6-115	S	B
6-116	S	B
6-117	S	B
6-118	S	B
6-119	A	B
6-120	A	B

No.	Bubbles rank	Unmelted rank
6-121	B	B
6-122	B	B
6-123	D	B
6-124	D	B
6-125	D	B
6-126	D	B
6-127	D	B
6-128	D	B
6-129	D	B
6-130	C	B
6-131	C	B
6-132	B	B
6-133	B	B
6-134	S	B
6-135	S	B
6-136	S	B
6-137	S	B
6-138	S	B
6-139	S	B
6-140	S	B
6-141	S	B
6-142	S	B
6-143	A	B
6-144	A	B
6-145	B	B
6-146	B	B
6-147	B	B
6-148	D	B
6-149	D	B
6-150	D	B
6-151	D	B
6-152	D	B
6-153	C	B
6-154	C	B
6-155	C	B
6-156	C	B
6-157	B	B
6-158	B	B
6-159	S	B
6-160	S	B
6-161	S	B
6-162	S	B
6-163	S	B
6-164	S	B
6-165	S	B
6-166	S	B
6-167	S	B
6-168	A	B
6-169	A	B
6-170	A	B
6-171	B	B
6-172	B	B
6-173	D	B
6-174	D	B
6-175	D	B
6-176	D	B
6-177	D	B
6-178	D	B
6-179	C	B
6-180	C	B

No.	Bubbles rank	Unmelted rank
6-181	C	B
6-182	C	B
6-183	B	B
6-184	B	B
6-185	B	B
6-186	S	B
6-187	S	B
6-188	S	B
6-189	S	B
6-190	S	B
6-191	S	B
6-192	S	B
6-193	S	B
6-194	S	B
6-195	S	B
6-196	A	B
6-197	A	B
6-198	A	B
6-199	B	B
6-200	B	B
6-201	E	B
6-202	D	C
6-203	D	C
6-204	D	C
6-205	D	C
6-206	D	C
6-207	D	C
6-208	C	C
6-209	C	C
6-210	C	C
6-211	C	C
6-212	C	C
6-213	B	C
6-214	B	C
6-215	B	C
6-216	S	C
6-217	S	C
6-218	S	C
6-219	S	C
6-220	S	C
6-221	S	C
6-222	S	C
6-223	S	C
6-224	S	C
6-225	S	C
6-226	S	C
6-227	S	C
6-228	A	C
6-229	A	C
6-230	A	C
6-231	B	C
6-232	B	C
6-233	D	C
6-234	D	C
6-235	D	C
6-236	D	C
6-237	D	C
6-238	D	C
6-239	C	C
6-240	C	C

No.	Bubbles rank	Unmelted rank
6-241	C	C
6-242	C	C
6-243	C	C
6-244	C	C
6-245	B	C
6-246	B	C
6-247	B	C
6-248	S	C
6-249	S	C
6-250	S	C
6-251	S	C
6-252	S	C
6-253	S	C
6-254	S	C
6-255	S	C
6-256	S	C
6-257	S	C
6-258	S	C
6-259	S	C
6-260	A	C
6-261	A	C
6-262	A	C
6-263	A	C
6-264	B	C
6-265	B	C
6-266	D	C
6-267	D	C
6-268	D	C
6-269	D	C
6-270	D	C
6-271	C	C
6-272	C	C
6-273	C	C
6-274	C	C
6-275	C	C
6-276	C	C
6-277	C	C
6-278	B	C
6-279	B	C
6-280	B	C
6-281	S	C
6-282	S	C
6-283	S	C
6-284	S	C
6-285	S	C
6-286	S	C
6-287	S	C
6-288	S	C
6-289	S	C
6-290	S	C
6-291	S	C
6-292	S	C
6-293	S	C
6-294	A	C
6-295	A	C
6-296	A	C
6-297	A	C
6-298	B	C
6-299	B	C
6-300	D	C

No.	Bubbles rank	Unmelted rank
6-301	D	C
6-302	D	C
6-303	D	C
6-304	D	C
6-305	D	C
6-306	C	C
6-307	C	C
6-308	C	C
6-309	C	C
6-310	C	C
6-311	C	C
6-312	C	C
6-313	C	C
6-314	B	C
6-315	B	C
6-316	B	C
6-317	S	C
6-318	S	C
6-319	S	C
6-320	S	C
6-321	S	C
6-322	S	C
6-323	S	C
6-324	S	C
6-325	S	C
6-326	S	C
6-327	S	C
6-328	S	C
6-329	S	C
6-330	S	C
6-331	S	C
6-332	A	C
6-333	A	C
6-334	A	C
6-335	A	C
6-336	A	C
6-337	B	C
6-338	B	C
6-339	B	C
Com.Ex.6-1	C	D
Com.Ex.6-2	C	D
Com.Ex.6-3	B	D
Com.Ex.6-4	C	D
Com.Ex.6-5	E	D
Com.Ex.6-6	G	S
Com.Ex.6-7	G	S
Com.Ex.6-8	G	S
Com.Ex.6-9	G	S

[0303]

[Table 17]

No.	Bubbles rank	Unmelted rank
7-1	E	S
7-2	E	S
7-3	B	S
7-4	B	S
7-5	C	S
7-6	E	S
7-7	E	S
7-8	E	S
7-9	E	S
7-10	D	S
7-11	B	S
7-12	B	S
7-13	B	S
7-14	B	S
7-15	C	S
7-16	C	S
7-17	D	S
7-18	D	S
7-19	D	S
7-20	D	S
7-21	C	S
7-22	A	S
7-23	A	S
7-24	A	S
7-25	A	S
7-26	B	S
7-27	B	S
7-28	D	S
7-29	D	S
7-30	D	S
7-31	D	S
7-32	D	S
7-33	D	S
7-34	C	S
7-35	C	S
7-36	A	S
7-37	A	S
7-38	S	S
7-39	S	S
7-40	S	S
7-41	A	S
7-42	A	S
7-43	B	S
7-44	B	S
7-45	D	S
7-46	D	S
7-47	D	S
7-48	D	S
7-49	D	S
7-50	D	S
7-51	A	S
7-52	S	S
7-53	S	S
7-54	S	S
7-55	S	S
7-56	A	S
7-57	A	S
7-58	B	S
7-59	B	S
7-60	D	S

No.	Bubbles rank	Unmelted rank
7-61	D	S
7-62	D	S
7-63	D	S
7-64	D	S
7-65	D	S
7-66	D	S
7-67	D	S
7-68	C	S
7-69	B	S
7-70	S	S
7-71	S	S
7-72	S	S
7-73	S	S
7-74	S	S
7-75	A	A
7-76	B	A
7-77	B	A
7-78	D	S
7-79	D	S
7-80	D	S
7-81	D	S
7-82	D	S
7-83	D	S
7-84	D	S
7-85	C	S
7-86	B	S
7-87	S	S
7-88	S	S
7-89	S	S
7-90	S	S
7-91	S	S
7-92	S	A
7-93	S	A
7-94	A	A
7-95	A	A
7-96	B	A
7-97	B	A
7-98	B	A
7-99	B	A
7-100	D	B
7-101	D	B
7-102	D	B
7-103	D	B
7-104	D	B
7-105	D	B
7-106	D	B
7-107	C	B
7-108	B	B
7-109	B	B
7-110	S	B
7-111	S	B
7-112	S	B
7-113	S	B
7-114	S	B
7-115	S	B
7-116	S	B
7-117	S	B
7-118	S	B
7-119	A	B
7-120	A	B

No.	Bubbles rank	Unmelted rank
7-121	B	B
7-122	B	B
7-123	D	B
7-124	D	B
7-125	D	B
7-126	D	B
7-127	D	B
7-128	D	B
7-129	D	B
7-130	C	B
7-131	C	B
7-132	B	B
7-133	B	B
7-134	S	B
7-135	S	B
7-136	S	B
7-137	S	B
7-138	S	B
7-139	S	B
7-140	S	B
7-141	S	B
7-142	S	B
7-143	A	B
7-144	A	B
7-145	B	B
7-146	B	B
7-147	B	B
7-148	D	B
7-149	D	B
7-150	D	B
7-151	D	B
7-152	D	B
7-153	C	B
7-154	C	B
7-155	C	B
7-156	C	B
7-157	B	B
7-158	B	B
7-159	S	B
7-160	S	B
7-161	S	B
7-162	S	B
7-163	S	B
7-164	S	B
7-165	S	B
7-166	S	B
7-167	S	B
7-168	A	B
7-169	A	B
7-170	A	B
7-171	B	B
7-172	B	B
7-173	D	B
7-174	D	B
7-175	D	B
7-176	D	B
7-177	D	B
7-178	D	B
7-179	C	B
7-180	C	B

No.	Bubbles rank	Unmelted rank
7-181	C	B
7-182	C	B
7-183	B	B
7-184	B	B
7-185	B	B
7-186	S	B
7-187	S	B
7-188	S	B
7-189	S	B
7-190	S	B
7-191	S	B
7-192	S	B
7-193	S	B
7-194	S	B
7-195	S	B
7-196	A	B
7-197	A	B
7-198	A	B
7-199	B	B
7-200	B	B
7-201	E	B
7-202	D	C
7-203	D	C
7-204	D	C
7-205	D	C
7-206	D	C
7-207	D	C
7-208	C	C
7-209	C	C
7-210	C	C
7-211	C	C
7-212	C	C
7-213	B	C
7-214	B	C
7-215	B	C
7-216	S	C
7-217	S	C
7-218	S	C
7-219	S	C
7-220	S	C
7-221	S	C
7-222	S	C
7-223	S	C
7-224	S	C
7-225	S	C
7-226	S	C
7-227	S	C
7-228	A	C
7-229	A	C
7-230	A	C
7-231	B	C
7-232	B	C
7-233	D	C
7-234	D	C
7-235	D	C
7-236	D	C
7-237	D	C
7-238	D	C
7-239	C	C
7-240	C	C

No.	Bubbles rank	Unmelted rank
7-241	C	C
7-242	C	C
7-243	C	C
7-244	C	C
7-245	B	C
7-246	B	C
7-247	B	C
7-248	S	C
7-249	S	C
7-250	S	C
7-251	S	C
7-252	S	C
7-253	S	C
7-254	S	C
7-255	S	C
7-256	S	C
7-257	S	C
7-258	S	C
7-259	S	C
7-260	A	C
7-261	A	C
7-262	A	C
7-263	A	C
7-264	B	C
7-265	B	C
7-266	D	C
7-267	D	C
7-268	D	C
7-269	D	C
7-270	D	C
7-271	C	C
7-272	C	C
7-273	C	C
7-274	C	C
7-275	C	C
7-276	C	C
7-277	C	C
7-278	B	C
7-279	B	C
7-280	B	C
7-281	S	C
7-282	S	C
7-283	S	C
7-284	S	C
7-285	S	C
7-286	S	C
7-287	S	C
7-288	S	C
7-289	S	C
7-290	S	C
7-291	S	C
7-292	S	C
7-293	S	C
7-294	A	C
7-295	A	C
7-296	A	C
7-297	A	C
7-298	B	C
7-299	B	C
7-300	D	C

No.	Bubbles rank	Unmelted rank
7-301	D	C
7-302	D	C
7-303	D	C
7-304	D	C
7-305	D	C
7-306	C	C
7-307	C	C
7-308	C	C
7-309	C	C
7-310	C	C
7-311	C	C
7-312	C	C
7-313	C	C
7-314	B	C
7-315	B	C
7-316	B	C
7-317	S	C
7-318	S	C
7-319	S	C
7-320	S	C
7-321	S	C
7-322	S	C
7-323	S	C
7-324	S	C
7-325	S	C
7-326	S	C
7-327	S	C
7-328	S	C
7-329	S	C
7-330	S	C
7-331	S	C
7-332	A	C
7-333	A	C
7-334	A	C
7-335	A	C
7-336	A	C
7-337	B	C
7-338	B	C
7-339	B	C
Com.Ex.7-1	C	D
Com.Ex.7-2	C	D
Com.Ex.7-3	B	D
Com.Ex.7-4	C	D
Com.Ex.7-4	E	D
Com.Ex.7-5	G	S
Com.Ex.7-6	G	S
Com.Ex.7-7	G	S
Com.Ex.7-8	G	S

[0304]

The surface of each glass obtained was polished flat and smooth. The interior of the glass was magnified and observed (40 to 100-fold) from the polished surface with an optical microscope, and the number of residual bubbles was counted. The number of residual bubbles counted was divided by the mass of the glass corresponding to the magnified area observed to obtain the density of residual bubbles.

[0305]

Glasses with 0 residual bubbles/kg were ranked S. Glasses with 2 or fewer residual bubbles/kg were ranked A. Glasses with 3 to 10 residual bubbles/kg were ranked B. Glasses with 11 to 20 residual bubbles/kg were ranked C. Glasses with 21 to 40 residual bubbles/kg were ranked D. Glasses with 41 to 60 residual bubbles/kg were ranked E. And glasses with 61 or more residual bubbles/kg were ranked G. The corresponding rankings of the various glasses are given in Tables 11 to 17.

[0306]

Glasses containing neither unmelted nor foreign matter were ranked S. Glasses containing 2 pieces/kg or less of foreign matter, including unmelted material, were ranked A. Glasses containing 3-10 pieces/kg or more of foreign matter were ranked B. Glasses containing 11-20 pieces/kg or more of foreign matter were ranked C. And glasses containing 21 pieces/kg or more of foreign matter were ranked D. The corresponding ranks of the various glasses are given in Tables 11 to 17. Rank D indicated unsuitability as a glass material for an information-recording medium substrate.

[0307]

The size of the residual bubbles in each of the various glasses prepared from Nos. 1-1 to 7-339 shown in Tables 11 to 17 was 0.3 mm or less.

[0308]

No crystals or unmelted starting materials were found in the glasses thus obtained.

[0309]

Based on the results given in Table 9 and Tables 10 to 17, the relation between the quantities of Sn and Ce added and the density of residual bubbles was determined. The quantities of Sn and Ce added are adjusted so that the density of residual bubbles is at or below a desired value, and glasses are

produced. It is thus possible to suppress the density of residual bubbles to a desired level.

[0310]

Next, glasses were prepared by the same method as above, with the exceptions that the temperature of glass melts that had been maintained for 15 hours at 1,400 to 1,600°C was lowered, the glass melts were maintained for 1 to 2 hours at 1,200 to 1,400°C, and molding was conducted. The density and size of the residual bubbles were examined, and the presence of crystals and unmelted starting materials was checked. This yielded the same results as above. When the period of maintenance at 1,400 to 1,600°C is denoted as TH and the period of maintenance at 1,200 to 1,400°C is denoted as TL, the ratio of TL/TH for all of the above-described methods is desirably 0.5 or lower, preferably 0.2 or lower. By increasing TH relative to TL, discharge of gas in the glass to the exterior of the glass is facilitated. However, to enhance the incorporating effect of gas in the glass by Ce, TL/TH is desirably greater than 0.01, preferably greater than 0.02, more preferably greater than 0.03, and still more preferably, greater than 0.04.

[0311]

To enhance the bubble eliminating effects of Sn and Ce, the temperature difference in the course of decreasing the temperature from the 1,400 to 1,600°C range to the 1,200 to 1,400°C range is desirably 30°C or greater, preferably 50°C or greater, more preferably 80°C or greater, still more preferably 100°C or greater, and yet more preferably, 150°C or greater. The upper limit of the temperature difference is 400°C.

[0312]

The viscosity at 1,400°C of each of the glasses of Nos. 1-1 to 7-339 in Tables 11 to 17 was measured by the viscosity measuring method employing a coaxial double cylinder rotating viscometer of JIS Standard Z8803.

The viscosity at 1,400°C of each of the glasses of No. 1-1 to No. 1-339 in Tables 11 to 17 is 300 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 2-1 to No. 2-339 is 250 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 3-1 to No. 3-339 is 400 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 4-1 to No. 4-339 is 350 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 5-1 to No. 5-339 is 300 dPa·s. The viscosity at 1,400°C of each of the glasses of No. 6-1 to No. 6-339 is 320 dPa·s. And the viscosity at 1,400°C of each of the glasses of No. 7-1 to No. 7-339 is 320 dPa·s.

[0313]

Among the various glasses of Nos. 1-1 to 7-339 in Tables 11 to 17, the Young's modulus of the various glasses of Nos. 1-1 to 1-339 is 81 GPa or higher, and that of Nos. 5-1 to 5-339 is 84 GPa or higher. In each of the above glasses, when neither Sn nor Ce is added, or when Sb is added without adding Sn and Ce, it is possible to obtain a glass with a higher Young's modulus than when Sn and Ce were added. For each of the glasses of Nos. 2-1 to 2-339, Nos. 3-1 to 3-339, Nos. 4-1 to 4-339, Nos. 6-1 to 6-339, and Nos. 7-1 to 7-339, as well, it is possible to increase the Young's modulus by adding Sn and Ce. Increasing the Young's modulus makes it possible to achieve good fluttering resistance during high-speed rotation in magnetic recording media equipped with substrates manufactured from these glasses.

[0314]

When substrates fabricated using the various glasses shown in Tables 11 to 17 were irradiated with UV light and observed in a darkroom, they were visually observed to emit blue fluorescence. This fluorescence could be used to determine whether or not foreign matter, such as residual abrasive or minute dust particles, had adhered to the substrate surface. The presence of blue fluorescence due to Ce could also be used to determine whether heterogeneous glass substrates in which no Ce had been added had been mixed in with the glass substrates to which Ce had been added.

[0315]

Each of the glasses to which Ce was added was processed into a flat sheet 1 mm in thickness with two optically polished surfaces. Light was directed vertically into the optically polished surfaces. The spectral transmittance was measured, and the wavelength $\lambda(\lambda_{80})$ at which the external transmittance become 80 percent (including the loss due to reflection at the glass surface) and the wavelength $\lambda(\lambda_5)$ at which it became 5 percent were measured. The following are measurement results for some of the glasses. Glass No. 1-23 (quantity of SnO₂ added: 0.3 mass percent; quantity of CeO₂ added: 0.2 mass percent) had a λ_{80} of 354 nm and a λ_5 of 327 nm. Glass No. 1-38 (quantity of SnO₂ added: 0.5 mass percent; quantity of CeO₂ added: 0.3 mass percent) had a λ_{80} of 360 nm and a λ_5 of 335 nm. Glass No. 1-71 (quantity of SnO₂ added: 0.7 mass percent; quantity of CeO₂ added: 0.5 mass percent) had a λ_{80} of 366 nm and a λ_5 of 342 nm. This shows that as the quantity of Ce added was increased, the absorption by the glass in the short wavelength range tended to increase.

Along with this tendency, the fluorescent intensity of the glass when irradiated with UV light also increased. The addition of Ce is desirable to make it possible to distinguish between glasses based on the fluorescence emitted when irradiated with UV light and to generate adequately strong fluorescence to permit the detection of foreign matter on the glass surface. Accordingly, an examination of the relation between λ_{80} , λ_5 , and the fluorescent intensity suited to these applications revealed that a λ_{80} of 320 nm or greater provided adequate fluorescent intensity. On this basis, the quantity of Ce added is desirably determined to yield a λ_{80} of 320 nm or greater. The quantity of Ce added is preferably determined to yield a λ_{80} of 330 nm or greater. The quantity of Ce added is more preferably determined to yield a λ_{80} of 350 nm or greater. And the quantity of Ce added is still more preferably determined to yield a λ_{80} of 355 nm or greater. Similarly, for λ_5 , the quantity of Ce added is desirably determined to yield a λ_5 of 300 nm or greater. The quantity of Ce added is preferably determined to yield a λ_5 of 310 nm or greater. The quantity of Ce added is more preferably determined to yield a λ_5 of 320 nm or greater. And the quantity of Ce added is still more preferably determined to yield a λ_5 of 330 nm or greater.

[0316]

From the perspective of ready distinction and detection based on fluorescence, the quantity of CeO_2 added is desirably 0.1 mass percent or greater, preferably 0.2 mass percent or greater, and more preferably, 0.3 mass percent or greater. For distinction and detection by fluorescence, when λ_{80} or the quantity of CeO_2 added is outside the above-stated range, it is impossible to achieve an adequate fluorescent intensity. This renders distinction and detection difficult.

[0317]

(2) Molding of the glass

Disk-shaped substrate blanks were fabricated from the above glasses by methods A to C below. Substrate blanks were fabricated by the same three methods of A to D as in Embodiment A from the glasses of Nos. 1-1 to 1-339 and Nos. 2-1 to 2-339. For the other glasses, substrate blanks were fabricated by method A. For the glasses of Nos. 1-1 to 1-339 and Nos. 2-1 to 2-339, the results of residual bubbles and etching rates given in the tables are the results for the substrate blanks fabricated by method A. The same holds true for the results for the substrate blanks fabricated by methods B to D.

[0318]

(3) Substrate fabrication

Glass substrates were fabricated by the same method as in Embodiment A from substrate blanks obtained by the various above methods.

[0319]

Portions of the glass substrates that had been fabricated were subjected to a masking treatment to protect the portions from etching. The glass substrates in this state were immersed in a 0.5 volume percent hydrogenfluosilicic acid aqueous solution maintained at 50°C or a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C for a prescribed period. Subsequently, the glass substrates were withdrawn from the various aqueous solutions. The difference (etching difference) between the masked portions and the portions without masks was measured, and then divided by the immersion time to calculate the amount of etching (etching rate) per unit time. The acid etching rates and alkali etching rates obtained are given in the tables, respectively. Etching rates were measured for the glasses of Nos. 1-1 to 1-339 and Nos. 2-1 to 2-339. Each of the glasses of Nos. 1-1 to 1-339 and Nos. 2-1 to 2-339 had an acid etching rate of 3.0 nm/minute or less and an alkali etching rate of 0.1 nm/minute or less. This indicates good acid resistance and alkali resistance.

[0320]

In the same manner as the various glasses of Nos. 1-1 to 1-339 and Nos. 2-1 to 2-339, the various glasses of Nos. 3-1 to 3-339, Nos. 4-1 to 4-339, and Nos. 6-1 to 6-339 also exhibited acid etching rates of 3.0 nm/minute or less and alkali etching rates of 0.1 nm/minute or less, indicating good acid resistance and alkali resistance.

[0321]

Next, potassium nitrate (60 mass percent) and sodium nitrate (40 mass percent) were mixed and heated to 375°C to prepare a chemical strengthening salt. Glass substrates that had been cleaned and preheated to 300°C were immersed for 3 hours in this salt to conduct a chemical strengthening treatment. This treatment caused lithium ions and sodium ions on the surface of the glass substrates to be replaced with sodium ions and potassium ions, respectively, in the chemical strengthening salt, thereby chemically strengthening the glass substrates. The thickness of the compressive stress layer formed in the surfaces of the glass substrates was about 100 to 200 micrometers. Following chemical strengthening, the glass substrates were rapidly cooled by immersion in a vat of water at 20°C and maintained there for about 10 minutes.

[0322]

Next, the rapidly cooled glass substrates were immersed in sulfuric acid that had been heated to about 40°C and cleaned while applying ultrasound. Subsequently, the glass substrates were cleaned with a 0.5 percent (volume percent) hydrogenfluosilicic acid (H_2SiF_6) aqueous solution followed by a 1 mass percent potassium hydroxide aqueous solution. Through the process, a magnetic disk glass substrate 12 was manufactured.

[0323]

The magnetic disk glass substrate was then examined. Atomic force microscopic (AFM) measurement (a 5 x 5 micrometer rectangular area was measured) of the surface roughness of the magnetic disk glass substrate revealed a maximum peak height (R_{max}) of 1.5 nm and an arithmetic average roughness (R_{a}) of 0.15 nm. The surface was in a clean mirror-surface state, free of the presence of foreign material hindering magnetic head flying, and free of foreign matter causing thermal asperity impediments. No increase in the roughness of the substrate surface was observed following cleaning. Next, the bending strength was measured. The bending strength was obtained as the value of the load when the glass substrate was damaged when a load was applied to the glass substrate as shown in Fig. 2 using a bending strength measuring and testing device (Shimadzu Autograph DDS-2000). The bending strength obtained, at 24.15 kg, was satisfactory.

[0324]

In the above description, acid cleaning and alkali cleaning were conducted after chemical strengthening, but it is also possible to conduct acid cleaning and alkali cleaning after the mirror-surface polishing step.

[0325]

A magnetic disk 10 was fabricated using the glass substrate 12 that had been thus obtained, and tested in a hard disk drive. Fig. 1 shows a typical film configuration (cross-section) on substrate 12.

[0326]

First, a film-forming device in which a vacuum had been drawn was employed to successively form adhesive layer 14 and soft magnetic layer 16 in an argon atmosphere by DC magnetron sputtering.

[0327]

Adhesive layer 14 was formed as a 20 nm amorphous CrTi layer using a CrTi target. Soft magnetic layer 16 was formed as a 200 nm amorphous CoTaZr

layer (Co: 88 atomic percent, Ta: 7 atomic percent, Zr: 5 atomic percent) using a CoTaZr target.

[0328]

Magnetic disk 10, on which films up to soft magnetic layer 16 had been formed, was removed from the film-forming device. The surface roughness thereof was measured as set forth above, revealing a smooth mirror surface with an Rmax of 2.1 nm and an Ra of 0.20 nm. Measurement of the magnetic characteristics with a vibrating sample magnetometer (VSM) revealed a coercivity (Hc) of 2 Oersteds and a saturation magnetic flux density of 810 emu/cc. This indicated suitable soft magnetic characteristics.

[0329]

Next, a single-wafer static opposed-type film-forming device was employed to successively form an underlayer 18, granular structure size reduction enhancing layer 20, granular structure ferromagnetic layer 32, magnetic coupling control layer 34; energy exchange control layer 36, and protective film 24 in an argon atmosphere. In the present embodiment, underlayer 18 had a two-layer structure comprised of a first layer and a second layer.

[0330]

In this process, a layer 10 nm in thickness of amorphous NiTa (Ni: 40 atomic percent, Ta: 10 atomic percent) was first formed on the disk substrate as the first layer of underlayer 18, followed by the formation of a Ru layer 10 to 15 nm in thickness as the second layer.

[0331]

Next, a nonmagnetic CoCr-SiO₂ target was employed to form size reduction enhancing layer 20 comprised of a 2 to 20 nm hcp crystalline structure. A CoCrPt-SiO₂ hard magnetic material target was then employed to form ferromagnetic layer 32 comprised of a 15 nm hcp crystalline structure. The composition of the target for fabricating ferromagnetic layer 32 was Co: 62 atomic percent; Cr: 10 atomic percent; Pt: 16 atomic percent, and SiO₂: 12 atomic percent. A magnetic coupling control layer 34 in the form of a Pd layer was then formed, and an energy exchange control layer 36 in the form of [CoB/Pd]_n layers was formed.

[0332]

CVD employing ethylene as the material gas was then used to form protective film 24 comprised of carbon hydride. The use of carbon hydride

increased film hardness, making it possible to protect magnetic recording layer 22 from impact with the magnetic head.

[0333]

Subsequently, lubricating layer 26 comprised of perfluoropolyether (PFPE) was formed by dip coating. Lubricating layer 26 was 1 nm in thickness. A vertical magnetic recording medium in the form of magnetic disk 10 suited to vertical magnetic recording methods was obtained by the above manufacturing process. The roughness of the surface obtained was measured in the same manner as above, revealing a smooth mirror surface with an Rmax of 2.2 nm and an Ra of 0.21 nm.

[0334]

The magnetic disk 10 that had been obtained was loaded onto a 2.5-inch loading/unloading hard disk drive. The magnetic head mounted on the hard disk drive was a dynamic flying height (abbreviated as "DFH") magnetic head. The flying height of the magnetic head relative to the magnetic disk was 8 nm.

[0335]

A recording and reproducing test was conducted at a recording density of 200 Gbits/inch² in the recording and reproducing region of the main surface of the magnetic disk using this hard disk drive, revealing good recording and reproducing characteristics. During the test, no crash faults or thermal asperity faults were generated.

[0336]

Next, a load unload ("LUL" hereinafter) test was conducted with the hard disk drive.

[0337]

The LUL test was conducted with 2.5-inch hard disk drive rotating at 5,400 rpm and a magnetic head with a flying height of 8 nm. The above-described magnetic head was employed. The shield element was comprised of NiFe alloy. The magnetic disk was loaded on the magnetic disk device, LUL operations were repeatedly conducted with the above magnetic head, and the LUL cycle durability was measured.

[0338]

Following the LUL durability test, the surface of the magnetic disk and the surface of the magnetic head are examined visually and by optical microscopy to check for abnormalities such as scratches and grime. In the LUL durability test, a durability of 400,000 or more LUL cycles without failure is required, with a

durability of 600,000 cycles or more being particularly desirable. In the use environment in which a hard disk drive (HDD) is normally employed, it is reported to take about 10 years of use to exceed 600,000 LUL cycles.

[0339]

When the LUL test was implemented, magnetic disk 10 met the 600,000 cycle or more standard. Following the LUL test, magnetic disk 10 was removed and inspected, revealing no abnormalities such as scratches or grime. Any precipitation of alkali metal components was observed.

(Comparative Example B)

[0340]

Next, the 63 glasses of Comparative Examples 1-1 to 1-9, Comparative Examples 2-1 to 2-9, Comparative Examples 3-1 to 3-9, Comparative Examples 4-1 to 4-9, Comparative Examples 5-1 to 5-9, Comparative Examples 6-1 to 6-9, and Comparative Examples 7-1 to 7-9 shown in Tables 11 to 17 were fabricated. The glasses of the comparative examples were fabricated by the same procedure as in the embodiments.

[0341]

Excess quantities of Sn oxide and Ce oxide were added as clarifying agents to the glasses of Comparative Examples 1-1 to 7-1, Comparative Examples 1-2 to 7-2, and Comparative Examples 1-3 to 7-3 shown in Tables 11 to 17.

[0342]

Residual unmelted Sn oxide was observed in all of these glasses, rendering them unsuitable as glass substrate materials for information-recording media.

[0343]

Sb alone was added as clarifying agent to the glasses of Comparative Examples 1-6 to 7-6 shown in Tables 11 to 17. Sn and an excess quantity of Sb were added as clarifying agents to the glasses of Comparative Examples 1-7 to 8-7. An excess quantity of Sn was added as clarifying agent to the glasses of Comparative Examples 1-8 to 8-8. And an excess quantity of Ce was added as clarifying agent to the glasses of Comparative Examples 1-9 to 8-9 shown in Tables 11 to 17.

[0344]

The number of residual bubbles exceeded 100 bubbles/kg in all of these glasses. Localized pitting due to residual bubbles was also observed on the

surface of glass substrates fabricated by the same methods as in the embodiments using these glasses. The impact resistance of the substrates was also poorer than that of the embodiments.

[Brief Description of the Drawings]

[0345]

[Fig. 1] A drawing showing an example of the configuration of a magnetic disk relating to an implementing mode of the present invention.

[Fig. 2] A descriptive diagram of the method used to measure bending strength.

Claims

[1]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent,

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or less);

by comprising a 0.1 to 3.5 mass percent of total content of Sn oxide and Ce oxide, based on the total amount of the glass components;

in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 0.01 to 0.99;

in that the Sb oxide content is 0 to 0.1 percent; and

by comprising no As or F.

[2]

The glass for a magnetic recording medium substrate according to Claim 1, characterized in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 1/3 or greater.

[3]

The glass for a magnetic recording medium substrate according to Claim 1, characterized in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) falls within a range of 0.45 to 0.98.

[4]

The glass for a magnetic recording medium substrate according to any one of Claims 1 to 3, characterized by not containing Sb.

[5]

The glass for a magnetic recording medium substrate according to any one of Claims 1 to 4, comprising, denoted as molar percentages:

MgO 0 to 10 percent,
CaO 0 to 10 percent,
SrO 0 to 5 percent,
BaO 0 to 5 percent,
B₂O₃ 0 to 3 percent,
P₂O₅ 0 to 1 percent, and
ZnO 0 to 3 percent.

[6]

The glass for a magnetic recording medium substrate according to any one of Claims 1 to 5, characterized by comprising a total content of ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ of 0.1 to 5 molar percent.

[7]

The glass for a magnetic recording medium substrate according to any one of Claims 1 to 6, characterized by comprising a total content of MgO, CaO, SrO, and BaO of 0.1 to 10 molar percent.

[8]

The glass for a magnetic recording medium substrate of any one of Claims 1 to 7, characterized in that the total content of SiO₂ and Al₂O₃ is 65 molar percent or greater and by having a viscous property such that the viscosity at 1,400°C is 10³ dPa·s or lower.

[9]

The glass for a magnetic recording medium substrate of any one of Claims 1 to 8, comprising, denoted as mass percentages:

SiO₂ 66 to 70 percent,
Al₂O₃ 7 to 12 percent
(where the total content of SiO₂ and Al₂O₃ is 75 percent or greater),
Li₂O 5 to 10 percent,
Na₂O 8 to 13 percent,
K₂O 0.1 to 2 percent
(wherein the total content of Li₂O, Na₂O, and K₂O is 15 to 22 percent),
MgO 0.1 to 5 percent,
CaO 0.1 to 5 percent,

SrO and BaO in total 0 to 1 percent,
ZrO₂ 0.1 to 2 percent,
B₂O₃ 0 to 1 percent, and
ZnO 0 to 1 percent.

[10]

The glass for a magnetic recording medium substrate of any one of Claims 1 to 8, comprising, denoted as mass percentages:

SiO₂ 66 to 70 percent,
Al₂O₃ 5 to 12 percent,
Li₂O 5 to 20 percent,
Na₂O 1 to 13 percent,
K₂O 0.1 to 2 percent
(wherein the total content of Li₂O, Na₂O, and K₂O is 18 to 22 percent),
MgO and CaO in total 0 to 5 percent,
SrO and BaO in total 0 to 5 percent,
ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ in total 0.1 to 5 percent,
B₂O₃ 0 to 3 percent,
ZnO 0 to 1 percent, and
P₂O₅ 0 to 0.5 percent.

[11]

The glass for a magnetic recording medium substrate according to any one of Claims 1 to 10, characterized by exhibiting an acid resistant property such that the etching rate when immersed in a 0.5 volume percent hydrogenfluosilicic acid aqueous solution maintained at 50°C is 3.0 nm/minute or less and an alkali resistant property such that the etching rate when immersed in a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C is 0.1 nm/minute or less.

[12]

The glass for a magnetic recording medium substrate of any one of Claims 1 to 11 that has been subjected to a chemical strengthening treatment.

[13]

A magnetic recording medium substrate being composed of the glass described in any one of Claims 1 to 11 and 54.

[14]

The magnetic recording medium substrate according to Claim 13, wherein roughness Ra of the main surface is less than 0.25 nm.

[15]

The magnetic recording medium substrate according to Claim 13 or 14, characterized by exhibiting a bending strength of 10 kg or greater.

[16]

The magnetic recording medium substrate described in any one of Claims 13 to 15, having a disklike shape and a thickness of 1 mm or less.

[17]

A magnetic recording medium comprising an information recording layer on the magnetic recording medium substrate described in any one of Claims 13 to 16.

[18]

The magnetic recording medium according to Claim 17, suited to a vertical recording method.

[19]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, as converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);

in that, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide are added;

in that the content of Sb oxide is 0 to 0.1 mass percent; and

by not comprising As or F.

[20]

The glass for a magnetic recording medium substrate according to Claim 19, characterized in that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) as denoted by mass percentages falls within a range of 0 to 2.0.

[21]

The glass for a magnetic recording medium substrate according to Claim 19, characterized in that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) as denoted by mass percentages falls within a range of 0.02 to 1.2.

[22]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 21, characterized by not comprising Sb.

[23]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 22, comprising, denoted as molar percentages:

MgO 0 to 10 percent,

CaO 0 to 10 percent,

SrO 0 to 5 percent, and

BaO 0 to 5 percent.

[24]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 23, characterized by comprising 0.1 to 5 molar percent of ZrO_2 , TiO_2 , La_2O_3 , Nb_2O_5 , Ta_2O_5 , and HfO_2 in total.

[25]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 24, characterized by comprising a total content of 0.1 to 10 molar percent of MgO, CaO, SrO, and BaO.

[26]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 25, characterized in that the total content of SiO_2 and Al_2O_3 is 65 molar percent or greater, and by having a viscous property such that the viscosity at 1,400°C is 10^3 dPa·s or lower.

[27]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 26, comprising, denoted as mass percentages:

SiO₂ 66 to 70 percent,

Al₂O₃ 7 to 12 percent

(where the total content of SiO₂ and Al₂O₃ is 75 percent or greater),

Li₂O 5 to 10 percent,

Na₂O 8 to 13 percent,

K₂O 0.1 to 2 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 15 to 22 percent),

MgO 0.1 to 5 percent,

CaO 0.1 to 5 percent,

SrO and BaO in total 0 to 1 percent,

ZrO₂ 0.1 to 2 percent,

B₂O₃ 0 to 1 percent, and

ZnO 0 to 1 percent.

[28]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 26, comprising, denoted as mass percentages:

SiO₂ 66 to 70 percent,

Al₂O₃ 5 to 12 percent,

Li₂O 5 to 20 percent,

Na₂O 1 to 13 percent,

K₂O 0.1 to 2 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 18 to 22 percent),

MgO and CaO in total 0 to 5 percent,

SrO and BaO in total 0 to 5 percent,

ZrO₂, TiO₂, La₂O₃, Nb₂O₅, Ta₂O₅, and HfO₂ in total 0.1 to 5 percent,

B₂O₃ 0 to 3 percent,

ZnO 0 to 1 percent, and

P₂O₅ 0 to 0.5 percent.

[29]

The glass for a magnetic recording medium substrate according to any one of Claims 19 to 28, characterized by exhibiting an acid resistant property such that the etching rate when immersed in a 0.5 volume percent

hydrogenfluosilicic acid aqueous solution maintained at 50°C is 3.0 nm/minute or less and an alkali resistant property such that the etching rate when immersed in a 1 mass percent potassium hydroxide aqueous solution maintained at 50°C is 0.1 nm/minute or less.

[30]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, denoted as mass percentages:

Si 20 to 40 percent,

Al 0.1 to 10 percent,

Li 0.1 to 5 percent,

Na 0.1 to 10 percent,

K 0 to 5 percent

(where the total content of Li, Na, and K is 15 percent or less),

Sn 0.005 to 0.6 percent, and

Ce 0 to 1.2 percent;

in that the Sb content is 0 to 0.1 percent;

by not comprising As or F; and

by having a $\lambda(\text{lambda})_{80}$ of 320 nm or greater.

[31]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, as converted based on the oxides, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);

in that, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide are added;

in that the content of Sb oxide is 0 to 0.1 mass percent;

by not comprising As or F; and

by having a $\lambda(\text{lambda})_{80}$ of 320 nm or greater.

[32]

A glass for a magnetic recording medium substrate comprised of oxide glass, characterized:

by comprising, converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(where the total content of Li₂O, Na₂O, and K₂O is 25 percent or less);

by comprising a 0.1 to 3.5 mass percent of the total content of Sn oxide and Ce oxide, based on the total amount of the glass components;

in that the ratio of the Sn oxide content to the total content of Sn oxide and Ce oxide (Sn oxide content/(Sn oxide content + Ce oxide content)) is 0.01 to 0.99;

in that the Sb oxide content is 0 to 0.1 percent;

by comprising no As or F; and

by having a λ (*lambda*)₈₀ of 320 nm or greater.

[33]

A method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by:

preparing a glass starting material to which Sn, and optionally Ce, are added, comprising, denoted as mass percentages:

Si 20 to 40 percent,

Al 0.1 to 10 percent,

Li 0.1 to 5 percent,

Na 0.1 to 10 percent,

K 0 to 5 percent

(wherein the total content of Li, Na, and K is 15 percent or lower),

Sn 0.005 to 0.6 percent,

Ce 0 to 1.2 percent, and

so as to permit obtaining a glass comprising 0 to 0.1 percent of Sb and no As or F;

melting the glass starting material;

clarifying the resulting glass melt; and

then molding the resulting glass melt.

[34]

The method for manufacturing a glass for a magnetic recording medium substrate according to Claim 33, characterized by:

- preparing a glass starting material comprising a ratio of Ce content to Sn content, Ce/Sn, falling within a range of 0.02 to 1.3;
- maintaining the resulting glass melt at 1,400 to 1,600°C;
- decreasing the temperature;
- maintaining the temperature at 1,200 to 1,400°C; and
- conducting molding.

[35]

The method for manufacturing a glass for a magnetic recording medium substrate according to Claim 33 or 34, wherein the viscosity of the glass melt at 1,400°C is 10^3 dPa·s or lower.

[36]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 33 to 35, wherein the quantities of Sn and Ce added are established so as to achieve a density of residual bubbles in the glass of 100 bubbles/kg or lower.

[37]

A method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by:

preparing a glass starting material to which Sn, and optionally Ce, are added, comprising, as converted based on the oxides, denoted as molar percentages:

- SiO₂ 60 to 75 percent,

- Al₂O₃ 1 to 15 percent,

- Li₂O 0.1 to 20 percent,

- Na₂O 0.1 to 15 percent, and

- K₂O 0 to 5 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower);

so as to permit obtaining a glass comprising 0 to 0.1 percent of Sb, no As or F, and, based on the total amount of the glass components, 0.01 to 0.7 mass percent of Sn oxide and 0 to 1.4 mass percent of Ce oxide;

- melting the glass starting material;

- clarifying the resulting glass melt; and

- molding the resulting glass melt.

[38]

The method for manufacturing a glass for a magnetic recording medium substrate according to Claim 37, comprising:

mixing the glass starting material so that the ratio of the content of Ce oxide to the content of Sn oxide (Ce oxide/Sn oxide) denoted as a mass percentage falls within a range of 0.02 to 1.2,

melting the starting material,

maintaining the resulting glass melt at 1,400 to 1,600°C,

reducing the temperature,

maintaining the temperature at 1,200 to 1,400°C, and

molding the glass melt.

[39]

The method for manufacturing a glass for a magnetic recording medium substrate according to Claim 37 or 38, wherein the viscosity of the glass melt at 1,400°C is 10^3 dPa·s or lower.

[40]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claim 37 to 39, wherein the quantities of Sn and Ce added are established to achieve a density of residual bubbles in the glass of 100 bubbles/kg or lower.

[41]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 33 to 36 and 37 to 40, wherein the glass melt is made to flow out to obtain glass melt gobs, and the glass gobs are press molded.

[42]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 33 to 36 and 37 to 40, wherein the glass melt is molded into a sheet of glass by the float method.

[43]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 33 to 36 and 37 to 40, wherein the glass melt is molded into a sheet of glass by overflow down draw molding.

[44]

A method for manufacturing a magnetic recording medium substrate, comprising the steps of:

mirror-surface polishing the glass described in any one of Claims 19 to 29, and

following mirror-surface polishing, subjecting the glass to a cleaning step in which the glass is cleaned with an acid and cleaned with an alkali.

[45]

The method for manufacturing a magnetic recording medium substrate according to Claim 44, comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the cleaning step.

[46]

A method for manufacturing a magnetic recording medium, comprising: preparing a magnetic recording medium substrate by the method described in any one of Claims 44 to 45, 47 to 48, and forming an information recording layer on the substrate.

[47]

A method for manufacturing a magnetic recording medium substrate, comprising the steps of:

manufacturing a glass by the method described in any one of Claims 33 to 36 and 37 to 43,

mirror-surface polishing the glass, and

following mirror surface polishing, subjecting the glass to a cleaning step in which the glass is cleaned with an acid and cleaned with an alkali.

[48]

The method for manufacturing a magnetic recording medium substrate of Claim 47, comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the cleaning step.

[49]

A method for manufacturing a glass for a magnetic recording medium substrate comprised of an oxide glass, characterized by:

preparing a glass starting material to which Sn and Ce are added, comprising, as converted based on the oxide, denoted as molar percentages:

SiO₂ 60 to 75 percent,

Al₂O₃ 1 to 15 percent,

Li₂O 0.1 to 20 percent,

Na₂O 0.1 to 15 percent, and

K₂O 0 to 5 percent

(wherein the total content of Li₂O, Na₂O, and K₂O is 25 percent or lower); and, so as to permit obtaining a glass containing a total quantity of Sn oxide and Ce oxide of 0.1 to 3.5 mass percent based on the total amount of the glass components, wherein the ratio of the content of Sn oxide to the total content Sn oxide and Ce oxide (content of Sn oxide/(content of Sn oxide + content of Ce oxide)) is 0.01 to 0.99, having an Sb oxide content of 0 to 0.1 percent, and comprising no As or F;

melting the glass starting material;

clarifying the resulting glass melt; and

molding the resulting glass melt.

[50]

The method for manufacturing a glass for a magnetic recording medium substrate according to Claim 49, wherein the glass melt obtained by preparing and melting the glass starting material is maintained at 1,400 to 1,600°C, the temperature is decreased, the glass melt is maintained at 1,200 to 1,400°C, and the glass melt is molded.

[51]

The method for manufacturing a glass for a magnetic recording medium substrate according to Claim 49 or 50, wherein the viscosity of the glass melt at 1,400°C is 10³ dPa·s or lower.

[52]

The method for manufacturing a glass for a magnetic recording medium substrate of any one of Claims 49 to 52, wherein the quantities of Sn and Ce added are established so as to achieve a density of residual bubbles in the glass of 60 bubbles/kg or less.

[53]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 49 to 52, wherein the glass melt is made to flow out to obtain glass melt gobs and the glass gobs are press molded.

[54]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 49 to 52, wherein the glass melt is molded into a sheet of glass by the float method.

[55]

The method for manufacturing a glass for a magnetic recording medium substrate according to any one of Claims 49 to 52, wherein the glass melt is molded into a sheet of glass by overflow down draw molding.

[56]

A method for manufacturing a magnetic recording medium substrate, comprising:

a step of mirror-surface polishing the glass described in any one of Claims 1 to 11 and 54; and

following mirror-surface polishing, a cleaning step of cleaning with an acid and cleaning with an alkali.

[57]

A method for manufacturing the magnetic recording medium substrate according to Claim 56, comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the cleaning step.

[58]

A method for manufacturing a magnetic recording medium substrate, comprising:

a step of preparing a glass by the method described in any one of Claims 49 to 55,

a step of mirror-surface polishing the glass, and

following mirror-surface polishing, a cleaning step of cleaning with an acid and cleaning with an alkali.

[59]

The method for manufacturing a magnetic recording medium substrate according to Claim 58, comprising a step of subjecting the glass to a chemical strengthening treatment between the mirror-surface polishing step and the washing step.

[60]

A method for manufacturing a magnetic recording medium, comprising:
preparing a magnetic recording medium substrate according to the method described in any one of Claims 56 to 59; and
forming an information recording layer on the substrate.