CLAIMS

Claim 1. A polyvinyl acetal resin having a Z average molecular weight (Mz) of 800,000 or more and 2,300,000 or less and a molecular weight differential distribution value at Log M = 6.00 of 8.00 or more and 95.0 or less.

Claim 2. The polyvinyl acetal resin according to claim 1,

wherein a hydroxy group content relative to the Z average molecular weight (Hydroxy group content/Z average molecular weight) is 1.30×10^{-5} or more and 2.70×10^{-5} or less.

Claim 3. The polyvinyl acetal resin according to claim 1 or 2,

wherein the acetal group content is 50 to 83 mol%.

Claim 4. A resin composition for a ceramic green sheet, the resin composition comprising:

the polyvinyl acetal resin according to claim 1 or 2; and

a plasticizer.