



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 2/38, 220/12, C09D 157/00	A1	(11) International Publication Number: WO 99/46301 (43) International Publication Date: 16 September 1999 (16.09.99)
(21) International Application Number: PCT/GB99/00617 (22) International Filing Date: 11 March 1999 (11.03.99) (30) Priority Data: 9805141.0 12 March 1998 (12.03.98) GB 9817728.0 15 August 1998 (15.08.98) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chem- ical House, Millbank, London SW1P 3JF (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): CHISHOLM, Michael, Stephen [GB/GB]; 31 Sideling Tails, Yarm, Cleveland TS15 8HT (GB). SLARK, Andrew, Trevithick [GB/GB]; 2 Willow Road, Northallerton, North Yorkshire DL7 8RX (GB). SHERRINGTON, David [GB/GB]; 10 Hawthorn Avenue, Lenzie, Glasgow G66 4RA (GB). O'BRIEN, Niall [GB/GB]; 18 Tavistock Drive, Newlands, Glasgow G43 2SJ (GB). (74) Agents: GIBSON, Sara, Hillary, Margaret et al.; ICI Group Intellectual Property, Wilton, P.O. Box 90, Middlesbrough, Cleveland TS90 8JE (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: POLYMER COMPOSITION (57) Abstract A method of preparing a branched polymer comprising the steps of mixing together a monofunctional vinylic monomer with from 0.3 – 100 % w/w of a polyfunctional vinylic monomer and from 0.0001 – 50 % w/w of a chain transfer agent and thereafter reacting said mixture to form a polymer. The resulting soluble branched polymers are useful as components of surface coatings and inks or as moulding resins.		