

PROCESS COMPONENTS, CONTAINERS, AND PIPES
SUITABLE FOR CONTAINING AND TRANSPORTING
CRYOGENIC TEMPERATURE FLUIDS

5

FIELD OF THE INVENTION

This invention relates to process components, containers, and pipes suitable for containing and transporting cryogenic temperature fluids. More particularly, this invention relates to process components, containers, and pipes that are constructed
10 from an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).

BACKGROUND OF THE INVENTION

15 Various terms are defined in the following specification. For convenience, a Glossary of terms is provided herein, immediately preceding the claims.

Frequently in industry, there is a need for process components, containers, and pipes that have adequate toughness to process, contain, and transport fluids at cryogenic temperatures, i.e., at temperatures lower than about -40°C (-40°F), without failing.
20 This is especially true in the hydrocarbon and chemical processing industries. For example, cryogenic processes are used to achieve separation of components in hydrocarbon liquids and gases. Cryogenic processes are also used in the separation and storage of fluids such as oxygen and carbon dioxide.

Other cryogenic processes used in industry, for example, include low
25 temperature power generation cycles, refrigeration cycles, and liquefaction cycles. In low temperature power generation, the reverse Rankine cycle and its derivatives are typically used to generate power by recovering the cold energy available from an ultra-low temperature source. In the simplest form of the cycle, a suitable fluid, such as ethylene, is condensed at a low temperature, pumped to pressure, vaporized, and
30 expanded through a work-producing turbine coupled to a generator.

There are a wide variety of applications in which pumps are used to move cryogenic liquids in process and refrigeration systems where the temperature can be lower than about -73°C (-100°F). Additionally, when combustible fluids are relieved into a flare system during processing, the fluid pressure is reduced, e.g., across a pressure safety valve. This pressure drop results in a concomitant reduction in temperature of the fluid. If the pressure drop is large enough, the resulting fluid temperature can be sufficiently low that the toughness of carbon steels traditionally used in flare systems is not adequate. Typical carbon steel may fracture at cryogenic temperatures.

In many industrial applications, fluids are contained and transported at high pressures, i.e., as compressed gases. Typically, containers for storage and transportation of compressed gases are constructed from standard commercially available carbon steels, or from aluminum, to provide the toughness needed for fluid transportation containers that are frequently handled, and the walls of the containers must be made relatively thick to provide the strength needed to contain the highly-pressurized compressed gas. Specifically, pressurized gas cylinders are widely used to store and transport gases such as oxygen, nitrogen, acetylene, argon, helium, and carbon dioxide, to name a few. Alternatively, the temperature of the fluid can be lowered to produce a saturated liquid, and even subcooled if necessary, so the fluid can be contained and transported as a liquid. Fluids can be liquefied at combinations of pressures and temperatures corresponding to the bubble point conditions for the fluids. Depending on the properties of the fluid, it can be economically advantageous to contain and transport the fluid in a pressurized, cryogenic temperature condition if cost effective means for containing and transporting the pressurized, cryogenic temperature fluid are available. Several ways to transport a pressurized, cryogenic temperature fluid are possible, e.g., tanker truck, train tankcars, or marine transport. When pressurized cryogenic temperature fluids are to be used by local distributors in the pressurized, cryogenic temperature condition, in addition to the aforementioned storage and transportation containers, an alternative method of transportation is a flowline distribution system, i.e., pipes between a central storage area, where a large supply of the cryogenic temperature fluid is being produced and/or stockpiled, and local distributors or users. All of these methods of transportation require use of

storage containers and/or pipes constructed from a material that has adequate cryogenic temperature toughness to prevent failure and adequate strength to hold the high fluid pressures.

The Ductile to Brittle Transition Temperature (DBTT) delineates the two fracture regimes in structural steels. At temperatures below the DBTT, failure in the steel tends to occur by low energy cleavage (brittle) fracture, while at temperatures above the DBTT, failure in the steel tends to occur by high energy ductile fracture. Welded steels used in the construction of process components and containers for the aforementioned cryogenic temperature applications and for other load-bearing, cryogenic temperature service must have DBTTs well below the service temperature in both the base steel and the HAZ to avoid failure by low energy cleavage fracture.

Nickel-containing steels conventionally used for cryogenic temperature structural applications, e.g., steels with nickel contents of greater than about 3 wt%, have low DBTTs, but also have relatively low tensile strengths. Typically, commercially available 3.5 wt% Ni, 5.5 wt% Ni, and 9 wt% Ni steels have DBTTs of about -100°C (-150°F), -155°C (-250°F), and -175°C (-280°F), respectively, and tensile strengths of up to about 485 MPa (70 ksi), 620 MPa (90 ksi), and 830 MPa (120 ksi), respectively. In order to achieve these combinations of strength and toughness, these steels generally undergo costly processing, e.g., double annealing treatment. In the case of cryogenic temperature applications, industry currently uses these commercial nickel-containing steels because of their good toughness at low temperatures, but must design around their relatively low tensile strengths. The designs generally require excessive steel thicknesses for load-bearing, cryogenic temperature applications. Thus, use of these nickel-containing steels in load-bearing, cryogenic temperature applications tends to be expensive due to the high cost of the steel combined with the steel thicknesses required.

Although some commercially available carbon steels have DBTTs as low as about -46°C (-50°F), carbon steels that are commonly used in construction of commercially available process components and containers for hydrocarbon and chemical processes do not have adequate toughness for use in cryogenic temperature conditions. Materials with better cryogenic temperature toughness than carbon steel, e.g., the above-mentioned commercial nickel-containing steels (3 1/2 wt% Ni to 9 wt%

Ni), aluminum (Al-5083 or Al-5085), or stainless steel are traditionally used to construct commercially available process components and containers that are subject to cryogenic temperature conditions. Also, specialty materials such as titanium alloys and special epoxy-impregnated woven fiberglass composites are sometimes used. However, process components, containers, and/or pipes constructed from these materials often have increased wall thicknesses to provide the required strength. This adds weight to the components and containers which must be supported and/or transported, often at significant added cost to a project. Additionally, these materials tend to be more expensive than standard carbon steels. The added cost for support and transport of the thick-walled components and containers combined with the increased cost of the material for construction tends to decrease the economic attractiveness of projects.

A need exists for process components and containers suitable for economically containing and transporting cryogenic temperature fluids. A need also exists for pipes suitable for economically containing and transporting cryogenic temperature fluids. Consequently, the primary object of the present invention is to provide process components and containers suitable for economically containing and transporting cryogenic temperature fluids and to provide pipes suitable for economically containing and transporting cryogenic temperature fluids. Another object of the present invention is to provide such process components, containers, and pipes that are constructed from materials having both adequate strength and fracture toughness to contain pressurized cryogenic temperature fluids.

SUMMARY OF THE INVENTION

Consistent with the above-stated objects of the present invention, process components, containers, and pipes are provided for containing and transporting cryogenic temperature fluids. The process components, containers, and pipes of this invention are constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel, preferably containing less than about 7 wt% nickel, more preferably containing less than about 5 wt% nickel, and even more preferably containing less than about 3 wt% nickel. The steel has an ultra-high strength, e.g., tensile strength (as defined herein) greater than 830 MPa (120 ksi), and

a DBTT (as defined herein) lower than about -73°C (-100°F).

These new process components and containers can be advantageously used, for example, in cryogenic expander plants for natural gas liquids recovery, in liquefied natural gas ("LNG") treating and liquefaction processes, in the controlled freeze zone ("CFZ") process pioneered by Exxon Production Research Company, in
5 cryogenic refrigeration systems, in low temperature power generation systems, and in cryogenic processes related to the manufacture of ethylene and propylene. Use of these new process components, containers, and pipes advantageously reduces the risk of cold brittle fracture normally associated with conventional carbon steels in
10 cryogenic temperature service. Additionally, these process components and containers can increase the economic attractiveness of a project.

DESCRIPTION OF THE DRAWINGS

The advantages of the present invention will be better understood by referring to
15 the following detailed description and the attached drawings in which:

FIG. 1 is a typical process flow diagram illustrating how some of the process components of the present invention are used in a demethanizer gas plant;

FIG. 2 illustrates a fixed tubesheet, single pass heat exchanger according to the present invention;

20 FIG. 3 illustrates a kettle reboiler heat exchanger according to the present invention;

FIG. 4 illustrates an expander feed separator according to the present invention;

FIG. 5 illustrates a flare system according to the present invention;

FIG. 6 illustrates a flowline distribution network system according to the present
25 invention;

FIG. 7 illustrates a condenser system according to the present invention as used in a reverse Rankine cycle;

FIG. 8 illustrates a condenser according to the present invention as used in a cascade refrigeration cycle;

30 FIG. 9 illustrates a vaporizer according to the present invention as used in a cascade refrigeration cycle;

FIG. 10 illustrates a pump system according to the present invention;

FIG. 11 illustrates a process column system according to the present invention;

FIG. 12 illustrates another process column system according to the present invention;

FIG. 13A illustrates a plot of critical flaw depth, for a given flaw length, as a
5 function of CTOD fracture toughness and of residual stress; and

FIG. 13B illustrates the geometry (length and depth) of a flaw.

While the invention will be described in connection with its preferred
embodiments, it will be understood that the invention is not limited thereto. On the
contrary, the invention is intended to cover all alternatives, modifications, and
10 equivalents which may be included within the spirit and scope of the invention, as
defined by the appended claims.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to new process components, containers, and
15 pipes suitable for processing, containing and transporting cryogenic temperature
fluids; and, furthermore, to process components, containers, and pipes that are
constructed from materials comprising an ultra-high strength, low alloy steel
containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa
(120 ksi) and a DBTT lower than about -73°C (-100°F). Preferably, the ultra-high
20 strength, low alloy steel has excellent cryogenic temperature toughness in both the
base plate and in the heat affected zone (HAZ) when welded.

Process components, containers, and pipes suitable for processing and
containing cryogenic temperature fluids are provided, wherein the process
components, containers, and pipes are constructed from materials comprising an
25 ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a
tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C
(-100°F). Preferably the ultra-high strength, low alloy steel contains less than about 7
wt% nickel, and more preferably contains less than about 5 wt% nickel. Preferably
the ultra-high strength, low alloy steel has a tensile strength greater than about 860
30 MPa (125 ksi), and more preferably greater than about 900 MPa (130 ksi). Even
more preferably, the process components, containers, and pipes of this invention are
constructed from materials comprising an ultra-high strength, low alloy steel

containing less than about 3 wt% nickel and having a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).

Five co-pending U.S. provisional patent applications (the "PLNG Patent Applications"), each entitled "Improved System for Processing, Storing, and
5 Transporting Liquefied Natural Gas", describe containers and tanker ships for storage and marine transportation of pressurized liquefied natural gas (PLNG) at a pressure in the broad range of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature in the broad range of about -123°C (-190°F) to about -62°C (-80°F). The most recent of said PLNG Patent Applications has a priority date of 14 May 1998 and
10 is identified by the applicants as Docket No. 97006P4 and by the United States Patent and Trademark Office ("USPTO") as Application Number 60/085467. The first of said PLNG Patent Applications has a priority date of 20 June 1997 and is identified by the USPTO as Application Number 60/050280. The second of said PLNG Patent Applications has a priority date of 28 July 1997 and is identified by the USPTO as
15 Application Number 60/053966. The third of said PLNG Patent Applications has a priority date of 19 December 1997 and is identified by the USPTO as Application Number 60/068226. The fourth of said PLNG Patent Applications has a priority date of 30 March 1998 and is identified by the USPTO as Application Number 60/079904. Additionally, the PLNG Patent Applications describe systems and containers for
20 processing, storing, and transporting PLNG. Preferably, the PLNG fuel is stored at a pressure of about 1725 kPa (250 psia) to about 7590 kPa (1100 psia) and at a temperature of about -112°C (-170°F) to about -62°C (-80°F). More preferably, the PLNG fuel is stored at a pressure in the range of about 2415 kPa (350 psia) to about 4830 kPa (700 psia) and at a temperature in the range of about -101°C (-150°F) to
25 about -79°C (-110°F). Even more preferably, the lower ends of the pressure and temperature ranges for the PLNG fuel are about 2760 kPa (400 psia) and about -96°C (-140°F). Without hereby limiting this invention, the process components, containers, and pipes of this invention are preferably used for processing PLNG.

Steel for Construction of Process Components, Containers, and Pipes

Any ultra-high strength, low alloy steel containing less than 9 wt% nickel and having adequate toughness for containing cryogenic temperature fluids, such as PLNG, at operating conditions, according to known principles of fracture mechanics as described herein, may be used for constructing the process components, containers, and pipes of this invention. An example steel for use in the present invention, without thereby limiting the invention, is a weldable, ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and adequate toughness to prevent initiation of a fracture, i.e., a failure event, at cryogenic temperature operating conditions. Another example steel for use in the present invention, without thereby limiting the invention, is a weldable, ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength of at least about 1000 MPa (145 ksi) and adequate toughness to prevent initiation of a fracture, i.e., a failure event, at cryogenic temperature operating conditions. Preferably these example steels have DBTTs of lower than about -73°C (-100°F).

Recent advances in steel making technology have made possible the manufacture of new, ultra-high strength, low alloy steels with excellent cryogenic temperature toughness. For example, three U.S. patents issued to Koo et al., 5,531,842, 5,545,269, and 5,545,270, describe new steels and methods for processing these steels to produce steel plates with tensile strengths of about 830 MPa (120 ksi), 965 MPa (140 ksi), and higher. The steels and processing methods described therein have been improved and modified to provide combined steel chemistries and processing for manufacturing ultra-high strength, low alloy steels with excellent cryogenic temperature toughness in both the base steel and in the heat affected zone (HAZ) when welded. These ultra-high strength, low alloy steels also have improved toughness over standard commercially available ultra-high strength, low alloy steels. The improved steels are described in a co-pending U.S. provisional patent application entitled "ULTRA-HIGH STRENGTH STEELS WITH EXCELLENT CRYOGENIC TEMPERATURE TOUGHNESS", which has a priority date of 19 December 1997 and is identified by the United States Patent and Trademark Office ("USPTO") as Application Number 60/068194; in a co-pending U.S. provisional patent application

entitled "ULTRA-HIGH STRENGTH AUSAGED STEELS WITH EXCELLENT CRYOGENIC TEMPERATURE TOUGHNESS", which has a priority date of 19 December 1997 and is identified by the USPTO as Application Number 60/068252; and in a co-pending U.S. provisional patent application entitled "ULTRA-HIGH
5 STRENGTH DUAL PHASE STEELS WITH EXCELLENT CRYOGENIC TEMPERATURE TOUGHNESS", which has a priority date of 19 December 1997 and is identified by the USPTO as Application Number 60/068816. (collectively, the "Steel Patent Applications").

The new steels described in the Steel Patent Applications, and further
10 described in the examples below, are especially suitable for constructing the process components, containers, and pipes of this invention in that the steels have the following characteristics, preferably for steel plate thicknesses of about 2.5 cm (1 inch) and greater: (i) DBTT lower than about -73°C (-100°F), preferably lower than about -107°C (-160°F), in the base steel and in the weld HAZ; (ii) tensile strength
15 greater than 830 MPa (120 ksi), preferably greater than about 860 MPa (125 ksi), and more preferably greater than about 900 MPa (130 ksi); (iii) superior weldability; (iv) substantially uniform through-thickness microstructure and properties; and (v) improved toughness over standard, commercially available, ultra-high strength, low alloy steels. Even more preferably, these steels have a tensile strength of greater than
20 about 930 MPa (135 ksi), or greater than about 965 MPa (140 ksi), or greater than about 1000 MPa (145 ksi).

First Steel Example

25 As discussed above, a copending U.S. provisional patent application, having a priority date of 19 December 1997, entitled "Ultra-High Strength Steels With Excellent Cryogenic Temperature Toughness", and identified by the USPTO as Application No. 60/068194, provides a description of steels suitable for use in the present invention. A method is provided for preparing an ultra-high strength steel
30 plate having a microstructure comprising predominantly tempered fine-grained lath martensite, tempered fine-grained lower bainite, or mixtures thereof, wherein the method comprises the steps of (a) heating a steel slab to a reheating temperature

sufficiently high to (i) substantially homogenize the steel slab, (ii) dissolve substantially all carbides and carbonitrides of niobium and vanadium in the steel slab, and (iii) establish fine initial austenite grains in the steel slab; (b) reducing the steel slab to form steel plate in one or more hot rolling passes in a first temperature range in which austenite recrystallizes; (c) further reducing the steel plate in one or more hot rolling passes in a second temperature range below about the T_{nr} temperature and above about the Ar_3 transformation temperature; (d) quenching the steel plate at a cooling rate of about 10°C per second to about 40°C per second ($18^{\circ}\text{F}/\text{sec}$ - $72^{\circ}\text{F}/\text{sec}$) to a Quench Stop Temperature below about the M_s transformation temperature plus 200°C (360°F); (e) stopping the quenching; and (f) tempering the steel plate at a tempering temperature from about 400°C (752°F) up to about the Ac_1 transformation temperature, preferably up to, but not including, the Ac_1 transformation temperature, for a period of time sufficient to cause precipitation of hardening particles, i.e., one or more of ϵ -copper, Mo_2C , or the carbides and carbonitrides of niobium and vanadium. The period of time sufficient to cause precipitation of hardening particles depends primarily on the thickness of the steel plate, the chemistry of the steel plate, and the tempering temperature, and can be determined by one skilled in the art. (See Glossary for definitions of predominantly, of hardening particles, of T_{nr} temperature, of Ar_3 , M_s , and Ac_1 transformation temperatures, and of Mo_2C .)

To ensure ambient and cryogenic temperature toughness, steels according to this first steel example preferably have a microstructure comprised of predominantly tempered fine-grained lower bainite, tempered fine-grained lath martensite, or mixtures thereof. It is preferable to substantially minimize the formation of embrittling constituents such as upper bainite, twinned martensite and MA. As used in this first steel example, and in the claims, "predominantly" means at least about 50 volume percent. More preferably, the microstructure comprises at least about 60 volume percent to about 80 volume percent tempered fine-grained lower bainite, tempered fine-grained lath martensite, or mixtures thereof. Even more preferably, the microstructure comprises at least about 90 volume percent tempered fine-grained lower

bainite, tempered fine-grained lath martensite, or mixtures thereof. Most preferably, the microstructure comprises substantially 100% tempered fine-grained lath martensite.

A steel slab processed according to this first steel example is manufactured in a customary fashion and, in one embodiment, comprises iron and the following
5 alloying elements, preferably in the weight ranges indicated in the following Table I:

Table I

	Alloying Element	Range (wt%)
	carbon (C)	0.04 - 0.12, more preferably 0.04 - 0.07
10	manganese (Mn)	0.5 - 2.5, more preferably 1.0 - 1.8
	nickel (Ni)	1.0 - 3.0, more preferably 1.5 - 2.5
	copper (Cu)	0.1 - 1.5, more preferably 0.5 - 1.0
	molybdenum (Mo)	0.1 - 0.8, more preferably 0.2 - 0.5
	niobium (Nb)	0.02 - 0.1, more preferably 0.03 - 0.05
15	titanium (Ti)	0.008 - 0.03, more preferably 0.01 - 0.02
	aluminum (Al)	0.001 - 0.05, more preferably 0.005 - 0.03
	nitrogen (N)	0.002 - 0.005, more preferably 0.002 - 0.003

Vanadium (V) is sometimes added to the steel, preferably up to about 0.10
20 wt%, and more preferably about 0.02 wt% to about 0.05 wt%.

Chromium (Cr) is sometimes added to the steel, preferably up to about 1.0 wt%, and more preferably about 0.2 wt% to about 0.6 wt%.

Silicon (Si) is sometimes added to the steel, preferably up to about 0.5 wt%, more preferably about 0.01 wt% to about 0.5 wt%, and even more preferably about
25 0.05 wt% to about 0.1 wt%.

Boron (B) is sometimes added to the steel, preferably up to about 0.0020 wt%, and more preferably about 0.0006 wt% to about 0.0010 wt%.

The steel preferably contains at least about 1 wt% nickel. Nickel content of the steel can be increased above about 3 wt% if desired to enhance performance after
30 welding. Each 1 wt% addition of nickel is expected to lower the DBTT of the steel by about 10°C (18°F). Nickel content is preferably less than 9 wt%, more preferably less than about 6 wt%. Nickel content is preferably minimized in order to minimize cost

of the steel. If nickel content is increased above about 3 wt%, manganese content can be decreased below about 0.5 wt% down to 0.0 wt%. Therefore, in a broad sense, up to about 2.5 wt% manganese is preferred.

Additionally, residuals are preferably substantially minimized in the steel.

- 5 Phosphorous (P) content is preferably less than about 0.01 wt%. Sulfur (S) content is preferably less than about 0.004 wt%. Oxygen (O) content is preferably less than about 0.002 wt%.

In somewhat greater detail, a steel according to this first steel example is prepared by forming a slab of the desired composition as described herein; heating the
10 slab to a temperature of from about 955°C to about 1065°C (1750°F - 1950°F); hot rolling the slab to form steel plate in one or more passes providing about 30 percent to about 70 percent reduction in a first temperature range in which austenite recrystallizes, i.e., above about the T_{nr} temperature, and further hot rolling the steel plate in one or more passes providing about 40 percent to about 80 percent reduction
15 in a second temperature range below about the T_{nr} temperature and above about the A_{r3} transformation temperature. The hot rolled steel plate is then quenched at a cooling rate of about 10°C per second to about 40°C per second (18°F/sec - 72°F/sec) to a suitable QST (as defined in the Glossary) below about the M_s transformation temperature plus 200°C (360°F), at which time the quenching is terminated. In one
20 embodiment of this first steel example, the steel plate is then air cooled to ambient temperature. This processing is used to produce a microstructure preferably comprising predominantly fine-grained lath martensite, fine-grained lower bainite, or mixtures thereof, or, more preferably comprising substantially 100% fine-grained lath martensite.

- 25 The thus direct quenched martensite in steels according to this first steel example has ultra-high strength but its toughness can be improved by tempering at a suitable temperature from above about 400°C (752°F) up to about the A_{c1} transformation temperature. Tempering of steel within this temperature range also leads to reduction of the quenching stresses which in turn leads to enhanced
30 toughness. While tempering can enhance the toughness of the steel, it normally leads to substantial loss of strength. In the present invention, the usual strength loss from

tempering is offset by inducing precipitate dispersion hardening. Dispersion hardening from fine copper precipitates and mixed carbides and/or carbonitrides are utilized to optimize strength and toughness during the tempering of the martensitic structure. The unique chemistry of the steels of this first steel example allows for
5 tempering within the broad range of about 400°C to about 650°C (750°F - 1200°F) without any significant loss of the as-quenched strength. The steel plate is preferably tempered at a tempering temperature from above about 400°C (752°F) to below the Ac₁ transformation temperature for a period of time sufficient to cause precipitation of hardening particles (as defined herein). This processing facilitates transformation of
10 the microstructure of the steel plate to predominantly tempered fine-grained lath martensite, tempered fine-grained lower bainite, or mixtures thereof. Again, the period of time sufficient to cause precipitation of hardening particles depends primarily on the thickness of the steel plate, the chemistry of the steel plate, and the tempering temperature, and can be determined by one skilled in the art.

15

Second Steel Example

As discussed above, a copending U.S. provisional patent application, having a priority date of 19 December 1997, entitled "Ultra-High Strength Ausaged Steels
20 With Excellent Cryogenic Temperature Toughness", and identified by the USPTO as Application No. 60/068252, provides a description of other steels suitable for use in the present invention. A method is provided for preparing an ultra-high strength steel plate having a micro-laminate microstructure comprising about 2 vol% to about 10 vol% austenite film layers and about 90 vol% to about 98 vol% laths of
25 predominantly fine-grained martensite and fine-grained lower bainite, said method comprising the steps of: (a) heating a steel slab to a reheating temperature sufficiently high to (i) substantially homogenize the steel slab, (ii) dissolve substantially all carbides and carbonitrides of niobium and vanadium in the steel slab, and (iii) establish fine initial austenite grains in the steel slab; (b) reducing the steel
30 slab to form steel plate in one or more hot rolling passes in a first temperature range in which austenite recrystallizes; (c) further reducing the steel plate in one or more hot

rolling passes in a second temperature range below about the T_{nr} temperature and above about the Ar_3 transformation temperature; (d) quenching the steel plate at a cooling rate of about 10°C per second to about 40°C per second (18°F/sec - 72°F/sec) to a Quench Stop Temperature (QST) below about the M_s transformation temperature plus 100°C (180°F) and above about the M_s transformation temperature; and (e) stopping said quenching. In one embodiment, the method of this second steel example further comprises the step of allowing the steel plate to air cool to ambient temperature from the QST. In another embodiment, the method of this second steel example further comprises the step of holding the steel plate substantially isothermally at the QST for up to about 5 minutes prior to allowing the steel plate to air cool to ambient temperature. In yet another embodiment, the method of this second steel example further comprises the step of slow-cooling the steel plate from the QST at a rate lower than about 1.0°C per second (1.8°F/sec) for up to about 5 minutes prior to allowing the steel plate to air cool to ambient temperature. In yet another embodiment, the method of this invention further comprises the step of slow-cooling the steel plate from the QST at a rate lower than about 1.0°C per second (1.8°F/sec) for up to about 5 minutes prior to allowing the steel plate to air cool to ambient temperature. This processing facilitates transformation of the microstructure of the steel plate to about 2 vol% to about 10 vol% of austenite film layers and about 90 vol% to about 98 vol% laths of predominantly fine-grained martensite and fine-grained lower bainite. (See Glossary for definitions of T_{nr} temperature, and of Ar_3 and M_s transformation temperatures.)

To ensure ambient and cryogenic temperature toughness, the laths in the micro-laminate microstructure preferably comprise predominantly lower bainite or martensite. It is preferable to substantially minimize the formation of embrittling constituents such as upper bainite, twinned martensite and MA. As used in this second steel example, and in the claims, "predominantly" means at least about 50 volume percent. The remainder of the microstructure can comprise additional fine-grained lower bainite, additional fine-grained lath martensite, or ferrite. More preferably, the microstructure comprises at least about 60 volume percent to about 80

volume percent lower bainite or lath martensite. Even more preferably, the microstructure comprises at least about 90 volume percent lower bainite or lath martensite.

A steel slab processed according to this second steel example is manufactured in a customary fashion and, in one embodiment, comprises iron and the following alloying elements, preferably in the weight ranges indicated in the following Table II:

Table II

Alloying Element	Range (wt%)
carbon (C)	0.04 - 0.12, more preferably 0.04 - 0.07
manganese (Mn)	0.5 - 2.5, more preferably 1.0 - 1.8
nickel (Ni)	1.0 - 3.0, more preferably 1.5 - 2.5
copper (Cu)	0.1 - 1.0, more preferably 0.2 - 0.5
molybdenum (Mo)	0.1 - 0.8, more preferably 0.2 - 0.4
niobium (Nb)	0.02 - 0.1, more preferably 0.02 - 0.05
titanium (Ti)	0.008 - 0.03, more preferably 0.01 - 0.02
aluminum (Al)	0.001 - 0.05, more preferably 0.005 - 0.03
nitrogen (N)	0.002 - 0.005, more preferably 0.002 - 0.003

Chromium (Cr) is sometimes added to the steel, preferably up to about 1.0 wt%, and more preferably about 0.2 wt% to about 0.6 wt%.

Silicon (Si) is sometimes added to the steel, preferably up to about 0.5 wt%, more preferably about 0.01 wt% to about 0.5 wt%, and even more preferably about 0.05 wt% to about 0.1 wt%.

Boron (B) is sometimes added to the steel, preferably up to about 0.0020 wt%, and more preferably about 0.0006 wt% to about 0.0010 wt%.

The steel preferably contains at least about 1 wt% nickel. Nickel content of the steel can be increased above about 3 wt% if desired to enhance performance after welding. Each 1 wt% addition of nickel is expected to lower the DBTT of the steel by about 10°C (18°F). Nickel content is preferably less than 9 wt%, more preferably less than about 6 wt%. Nickel content is preferably minimized in order to minimize cost

of the steel. If nickel content is increased above about 3 wt%, manganese content can be decreased below about 0.5 wt% down to 0.0 wt%. Therefore, in a broad sense, up to about 2.5 wt% manganese is preferred.

Additionally, residuals are preferably substantially minimized in the steel.

- 5 Phosphorous (P) content is preferably less than about 0.01 wt%. Sulfur (S) content is preferably less than about 0.004 wt%. Oxygen (O) content is preferably less than about 0.002 wt%.

- In somewhat greater detail, a steel according to this second steel example is prepared by forming a slab of the desired composition as described herein; heating the
10 slab to a temperature of from about 955°C to about 1065°C (1750°F - 1950°F); hot rolling the slab to form steel plate in one or more passes providing about 30 percent to about 70 percent reduction in a first temperature range in which austenite recrystallizes, i.e., above about the T_{nr} temperature, and further hot rolling the steel plate in one or more passes providing about 40 percent to about 80 percent reduction
15 in a second temperature range below about the T_{nr} temperature and above about the A_{r3} transformation temperature. The hot rolled steel plate is then quenched at a cooling rate of about 10°C per second to about 40°C per second (18°F/sec - 72°F/sec) to a suitable QST below about the M_s transformation temperature plus 100°C (180°F) and above about the M_s transformation temperature, at which time the quenching is
20 terminated. In one embodiment of this second steel example, after quenching is terminated the steel plate is allowed to air cool to ambient temperature from the QST. In another embodiment of this second steel example, after quenching is terminated the steel plate is held substantially isothermally at the QST for a period of time, preferably up to about 5 minutes, and then air cooled to ambient temperature. In yet
25 another embodiment, the steel plate is slow-cooled at a rate slower than that of air cooling, i.e., at a rate lower than about 1°C per second (1.8°F/sec), preferably for up to about 5 minutes. In yet another embodiment, the steel plate is slow-cooled from the QST at a rate slower than that of air cooling, i.e., at a rate lower than about 1°C per second (1.8°F/sec), preferably for up to about 5 minutes. In at least one
30 embodiment of this second steel example, the M_s transformation temperature is about

350°C (662°F) and, therefore, the M_s transformation temperature plus 100°C (180°F) is about 450°C (842°F).

The steel plate may be held substantially isothermally at the QST by any suitable means, as are known to those skilled in the art, such as by placing a thermal
5 blanket over the steel plate. The steel plate may be slow-cooled after quenching is terminated by any suitable means, as are known to those skilled in the art, such as by placing an insulating blanket over the steel plate.

Third Steel Example

10

As discussed above, a copending U.S. provisional patent application, having a priority date of 19 December 1997, entitled "Ultra-High Strength Dual Phase Steels With Excellent Cryogenic Temperature Toughness", and identified by the USPTO as Application No. 60/068816, provides a description of other steels suitable for use in
15 the present invention. A method is provided for preparing an ultra-high strength, dual phase steel plate having a microstructure comprising about 10 vol% to about 40 vol% of a first phase of substantially 100 vol% (i.e., substantially pure or "essentially") ferrite and about 60 vol% to about 90 vol% of a second phase of predominantly fine-grained lath martensite, fine-grained lower bainite, or mixtures thereof, wherein the
20 method comprises the steps of (a) heating a steel slab to a reheating temperature sufficiently high to (i) substantially homogenize the steel slab, (ii) dissolve substantially all carbides and carbonitrides of niobium and vanadium in the steel slab, and (iii) establish fine initial austenite grains in the steel slab; (b) reducing the steel slab to form steel plate in one or more hot rolling passes in a first temperature range in
25 which austenite recrystallizes; (c) further reducing the steel plate in one or more hot rolling passes in a second temperature range below about the T_{nr} temperature and above about the Ar_3 transformation temperature; (d) further reducing said steel plate in one or more hot rolling passes in a third temperature range below about the Ar_3 transformation temperature and above about the Ar_1 transformation temperature (i.e., the intercritical temperature range); (e) quenching said steel plate at a cooling rate of
30 about 10°C per second to about 40°C per second (18°F/sec - 72°F/sec) to a Quench

Stop Temperature (QST) preferably below about the M_s transformation temperature plus 200°C (360°F); and (f) stopping said quenching. In another embodiment of this third steel example, the QST is preferably below about the M_s transformation temperature plus 100°C (180°F), and is more preferably below about 350°C (662°F).

- 5 In one embodiment of this third steel example, the steel plate is allowed to air cool to ambient temperature after step (f). This processing facilitates transformation of the microstructure of the steel plate to about 10 vol% to about 40 vol% of a first phase of ferrite and about 60 vol% to about 90 vol% of a second phase of predominantly fine-grained lath martensite, fine-grained lower bainite, or mixtures thereof. (See
- 10 Glossary for definitions of T_{nr} temperature, and of A_{r3} and A_{r1} transformation temperatures.)

- To ensure ambient and cryogenic temperature toughness, the microstructure of the second phase in steels of this third steel example comprises predominantly fine-grained lower bainite, fine-grained lath martensite, or mixtures thereof. It is
- 15 preferable to substantially minimize the formation of embrittling constituents such as upper bainite, twinned martensite and MA in the second phase. As used in this third steel example, and in the claims, "predominantly" means at least about 50 volume percent. The remainder of the second phase microstructure can comprise additional fine-grained lower bainite, additional fine-grained lath martensite, or ferrite. More
- 20 preferably, the microstructure of the second phase comprises at least about 60 volume percent to about 80 volume percent fine-grained lower bainite, fine-grained lath martensite, or mixtures thereof. Even more preferably, the microstructure of the second phase comprises at least about 90 volume percent fine-grained lower bainite, fine-grained lath martensite, or mixtures thereof.

- 25 A steel slab processed according to this third steel example is manufactured in a customary fashion and, in one embodiment, comprises iron and the following alloying elements, preferably in the weight ranges indicated in the following Table III:

Table III

	Alloying Element	Range (wt%)
5	carbon (C)	0.04 - 0.12, more preferably 0.04 - 0.07
	manganese (Mn)	0.5 - 2.5, more preferably 1.0 - 1.8
	nickel (Ni)	1.0 - 3.0, more preferably 1.5 - 2.5
	niobium (Nb)	0.02 - 0.1, more preferably 0.02 - 0.05
	titanium (Ti)	0.008 - 0.03, more preferably 0.01 - 0.02
10	aluminum (Al)	0.001 - 0.05, more preferably 0.005 - 0.03
	nitrogen (N)	0.002 - 0.005, more preferably 0.002 - 0.003

Chromium (Cr) is sometimes added to the steel, preferably up to about 1.0 wt%, and more preferably about 0.2 wt% to about 0.6 wt%.

15 Molybdenum (Mo) is sometimes added to the steel, preferably up to about 0.8 wt%, and more preferably about 0.1 wt% to about 0.3 wt%.

Silicon (Si) is sometimes added to the steel, preferably up to about 0.5 wt%, more preferably about 0.01 wt% to about 0.5 wt%, and even more preferably about 0.05 wt% to about 0.1 wt%.

20 Copper (Cu), preferably in the range of about 0.1 wt% to about 1.0 wt%, more preferably in the range of about 0.2 wt% to about 0.4 wt%, is sometimes added to the steel.

Boron (B) is sometimes added to the steel, preferably up to about 0.0020 wt%, and more preferably about 0.0006 wt% to about 0.0010 wt%.

25 The steel preferably contains at least about 1 wt% nickel. Nickel content of the steel can be increased above about 3 wt% if desired to enhance performance after welding. Each 1 wt% addition of nickel is expected to lower the DBTT of the steel by about 10°C (18°F). Nickel content is preferably less than 9 wt%, more preferably less than about 6 wt%. Nickel content is preferably minimized in order to minimize cost
30 of the steel. If nickel content is increased above about 3 wt%, manganese content can be decreased below about 0.5 wt% down to 0.0 wt%. Therefore, in a broad sense, up to about 2.5 wt% manganese is preferred.

Additionally, residuals are preferably substantially minimized in the steel. Phosphorous (P) content is preferably less than about 0.01 wt%. Sulfur (S) content is preferably less than about 0.004 wt%. Oxygen (O) content is preferably less than about 0.002 wt%.

5 In somewhat greater detail, a steel according to this third steel example is prepared by forming a slab of the desired composition as described herein; heating the slab to a temperature of from about 955°C to about 1065°C (1750°F - 1950°F); hot rolling the slab to form steel plate in one or more passes providing about 30 percent to about 70 percent reduction in a first temperature range in which austenite
10 recrystallizes, i.e., above about the T_{nr} temperature, further hot rolling the steel plate in one or more passes providing about 40 percent to about 80 percent reduction in a second temperature range below about the T_{nr} temperature and above about the Ar_3 transformation temperature, and finish rolling the steel plate in one or more passes to provide about 15 percent to about 50 percent reduction in the intercritical temperature
15 range below about the Ar_3 transformation temperature and above about the Ar_1 transformation temperature. The hot rolled steel plate is then quenched at a cooling rate of about 10°C per second to about 40°C per second (18°F/sec - 72°F/sec) to a suitable Quench Stop Temperature (QST) preferably below about the M_s transformation temperature plus 200°C (360°F), at which time the quenching is
20 terminated. In another embodiment of this invention, the QST is preferably below about the M_s transformation temperature plus 100°C (180°F), and is more preferably below about 350°C (662°F). In one embodiment of this third steel example, the steel plate is allowed to air cool to ambient temperature after quenching is terminated.

In the three example steels above, since Ni is an expensive alloying element,
25 the Ni content of the steel is preferably less than about 3.0 wt%, more preferably less than about 2.5 wt%, more preferably less than about 2.0 wt%, and even more preferably less than about 1.8 wt%, to substantially minimize cost of the steel.

Other suitable steels for use in connection with the present invention are described in other publications that describe ultra-high strength, low alloy steels
30 containing less than about 1 wt% nickel, having tensile strengths greater than 830

MPa (120 ksi), and having excellent low-temperature toughness. For example, such steels are described in a European Patent Application published February 5, 1997, and having International application number: PCT/JP96/00157, and International publication number WO 96/23909 (08.08.1996 Gazette 1996/36) (such steels
5 preferably having a copper content of 0.1 wt% to 1.2 wt%), and in a pending U.S. provisional patent application with a priority date of 28 July 1997, entitled "Ultra-High Strength, Weldable Steels with Excellent Ultra-Low Temperature Toughness", and identified by the USPTO as Application No. 60/053915.

For any of the above-referenced steels, as is understood by those skilled in the
10 art, as used herein "percent reduction in thickness" refers to percent reduction in the thickness of the steel slab or plate prior to the reduction referenced. For purposes of explanation only, without thereby limiting this invention, a steel slab of about 25.4 cm (10 inches) thickness may be reduced about 50% (a 50 percent reduction), in a first temperature range, to a thickness of about 12.7 cm (5 inches) then reduced about 80%
15 (an 80 percent reduction), in a second temperature range, to a thickness of about 2.5 cm (1 inch). Again, for purposes of explanation only, without thereby limiting this invention, a steel slab of about 25.4 cm (10 inches) may be reduced about 30% (a 30 percent reduction), in a first temperature range, to a thickness of about 17.8 cm (7 inches) then reduced about 80% (an 80 percent reduction), in a second temperature
20 range, to a thickness of about 3.6 cm (1.4 inch), and then reduced about 30% (a 30 percent reduction), in a third temperature range, to a thickness of about 2.5 cm (1 inch). As used herein, "slab" means a piece of steel having any dimensions.

For any of the above-referenced steels, as is understood by those skilled in the art, the steel slab is preferably reheated by a suitable means for raising the temperature of
25 substantially the entire slab, preferably the entire slab, to the desired reheating temperature, e.g., by placing the slab in a furnace for a period of time. The specific reheating temperature that should be used for any of the above-referenced steel compositions may be readily determined by a person skilled in the art, either by experiment or by calculation using suitable models. Additionally, the furnace
30 temperature and reheating time necessary to raise the temperature of substantially the entire slab, preferably the entire slab, to the desired reheating temperature may be readily determined by a person skilled in the art by reference to standard industry publications.

For any of the above-referenced steels, as is understood by those skilled in the art, the temperature that defines the boundary between the recrystallization range and non-recrystallization range, the T_{nr} temperature, depends on the chemistry of the steel, and more particularly, on the reheating temperature before rolling, the carbon concentration, the niobium concentration and the amount of reduction given in the rolling passes. Persons skilled in the art may determine this temperature for each steel composition either by experiment or by model calculation. Likewise, the A_{c1} , A_{r1} , A_{r3} , and M_s transformation temperatures referenced herein may be determined by persons skilled in the art for each steel composition either by experiment or by model calculation.

For any of the above-referenced steels, as is understood by those skilled in the art, except for the reheating temperature, which applies to substantially the entire slab, subsequent temperatures referenced in describing the processing methods of this invention are temperatures measured at the surface of the steel. The surface temperature of steel can be measured by use of an optical pyrometer, for example, or by any other device suitable for measuring the surface temperature of steel. The cooling rates referred to herein are those at the center, or substantially at the center, of the plate thickness; and the Quench Stop Temperature (QST) is the highest, or substantially the highest, temperature reached at the surface of the plate, after quenching is stopped, because of heat transmitted from the mid-thickness of the plate. For example, during processing of experimental heats of a steel composition according to this examples provided herein, a thermocouple is placed at the center, or substantially at the center, of the steel plate thickness for center temperature measurement, while the surface temperature is measured by use of an optical pyrometer. A correlation between center temperature and surface temperature is developed for use during subsequent processing of the same, or substantially the same, steel composition, such that center temperature may be determined via direct measurement of surface temperature. Also, the required temperature and flow rate of the quenching fluid to accomplish the desired accelerated cooling rate may be determined by one skilled in the art by reference to standard industry publications.

A person of skill in the art has the requisite knowledge and skill to use the information provided herein to produce ultra-high strength, low alloy steel plates

having suitable high strength and toughness for use in constructing the process components, containers, and pipes of the present invention. Other suitable steels may exist or be developed hereafter. All such steels are within the scope of the present invention.

5 A person of skill in the art has the requisite knowledge and skill to use the information provided herein to produce ultra-high strength, low alloy steel plates having modified thicknesses, compared to the thicknesses of the steel plates produced according to the examples provided herein, while still producing steel plates having suitable high strength and suitable cryogenic temperature toughness for use in the
10 present invention. For example, one skilled in the art may use the information provided herein to produce a steel plate with a thickness of about 2.54 cm (1 inch) and suitable high strength and suitable cryogenic temperature toughness for use in constructing the process components, containers, and pipes of the present invention. Other suitable steels may exist or be developed hereafter. All such steels are within
15 the scope of the present invention.

 When a dual phase steel is used in the construction of process components, containers, and pipes according to this invention, the dual phase steel is preferably processed in such a manner that the time period during which the steel is maintained in the intercritical temperature range for the purpose of creating the dual phase
20 structure occurs before the accelerated cooling or quenching step. Preferably the processing is such that the dual phase structure is formed during cooling of the steel between the A_{r3} transformation temperature to about the A_{r1} transformation temperature. An additional preference for steels used in the construction of process components, containers, and pipes according to this invention is that the steel has a
25 tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F) upon completion of the accelerated cooling or quenching step, i.e., without any additional processing that requires reheating of the steel such as tempering. More preferably the tensile strength of the steel upon completion of the quenching or cooling step is greater than about 860 MPa (125 ksi), and more preferably greater than
30 about 900 MPa (130 ksi). In some applications, a steel having a tensile strength of greater than about 930 MPa (135 ksi), or greater than about 965 MPa (140 ksi), or

greater than about 1000 MPa (145 ksi), upon completion of the quenching or cooling step is preferable.

Joining Methods for Construction of Process Components, Containers, and Pipes

5 In order to construct the process components, containers, and pipes of the present invention, a suitable method of joining the steel plates is required. Any joining method that will provide joints or seams with adequate strength and toughness for the present invention, as discussed above, is considered to be suitable. Preferably, a welding method suitable for providing adequate strength and fracture toughness to
10 contain the fluid being contained or transported is used to construct the process components, containers, and pipes of the present invention. Such a welding method preferably includes a suitable consumable wire, a suitable consumable gas, a suitable welding process, and a suitable welding procedure. For example, both gas metal arc welding (GMAW) and tungsten inert gas (TIG) welding, which are both well known
15 in the steel fabrication industry, can be used to join the steel plates, provided that a suitable consumable wire-gas combination is used.

 In a first example welding method, the gas metal arc welding (GMAW) process is used to produce a weld metal chemistry comprising iron and about 0.07 wt% carbon, about 2.05 wt% manganese, about 0.32 wt% silicon, about 2.20 wt%
20 nickel, about 0.45 wt% chromium, about 0.56 wt% molybdenum, less than about 110 ppm phosphorous, and less than about 50 ppm sulfur. The weld is made on a steel, such as any of the above-described steels, using an argon-based shielding gas with less than about 1 wt% oxygen. The welding heat input is in the range of about 0.3 kJ/mm to about 1.5 kJ/mm (7.6 kJ/inch to 38 kJ/inch). Welding by this method
25 provides a weldment (see Glossary) having a tensile strength greater than about 900 MPa (130 ksi), preferably greater than about 930 MPa (135 ksi), more preferably greater than about 965 MPa (140 ksi), and even more preferably at least about 1000 MPa (145 ksi). Further, welding by this method provides a weld metal with a DBTT below about -73°C (-100°F), preferably below about -96°C (-140°F), more preferably
30 below about -106°C (-160°F), and even more preferably below about -115°C (-175°F).

In another example welding method, the GMAW process is used to produce a weld metal chemistry comprising iron and about 0.10 wt% carbon (preferably less than about 0.10 wt% carbon, more preferably from about 0.07 to about 0.08 wt% carbon), about 1.60 wt% manganese, about 0.25 wt% silicon, about 1.87 wt% nickel, about 0.87 wt% chromium, about 0.51 wt% molybdenum, less than about 75 ppm phosphorous, and less than about 100 ppm sulfur. The welding heat input is in the range of about 0.3 kJ/mm to about 1.5 kJ/mm (7.6 kJ/inch to 38 kJ/inch) and a preheat of about 100°C (212°F) is used. The weld is made on a steel, such as any of the above-described steels, using an argon-based shielding gas with less than about 1 wt% oxygen. Welding by this method provides a weldment having a tensile strength greater than about 900 MPa (130 ksi), preferably greater than about 930 MPa (135 ksi), more preferably greater than about 965 MPa (140 ksi), and even more preferably at least about 1000 MPa (145 ksi). Further, welding by this method provides a weld metal with a DBTT below about -73°C (-100°F), preferably below about -96°C (-140°F), more preferably below about -106°C (-160°F), and even more preferably below about -115°C (-175°F).

In another example welding method, the tungsten inert gas welding (TIG) process is used to produce a weld metal chemistry containing iron and about 0.07 wt% carbon (preferably less than about 0.07 wt% carbon), about 1.80 wt% manganese, about 0.20 wt% silicon, about 4.00 wt% nickel, about 0.5 wt% chromium, about 0.40 wt% molybdenum, about 0.02 wt% copper, about 0.02 wt% aluminum, about 0.010 wt% titanium, about 0.015 wt% zirconium (Zr), less than about 50 ppm phosphorous, and less than about 30 ppm sulfur. The welding heat input is in the range of about 0.3 kJ/mm to about 1.5 kJ/mm (7.6 kJ/inch to 38 kJ/inch) and a preheat of about 100°C (212°F) is used. The weld is made on a steel, such as any of the above-described steels, using an argon-based shielding gas with less than about 1 wt% oxygen. Welding by this method provides a weldment having a tensile strength greater than about 900 MPa (130 ksi), preferably greater than about 930 MPa (135 ksi), more preferably greater than about 965 MPa (140 ksi), and even more preferably at least about 1000 MPa (145 ksi). Further, welding by this method provides a weld metal with a DBTT below about -73°C (-100°F), preferably below about -96°C

(-140°F), more preferably below about -106°C (-160°F), and even more preferably below about -115°C (-175°F).

Similar weld metal chemistries to those mentioned in the examples can be made using either the GMAW or the TIG welding processes. However, the TIG
5 welds are anticipated to have lower impurity content and a more highly refined microstructure than the GMAW welds, and thus improved low temperature toughness.

A person of skill in the art has the requisite knowledge and skill to use the information provided herein to weld ultra-high strength, low alloy steel plates to produce joints or seams having suitable high strength and fracture toughness for use
10 in constructing the process components, containers, and pipes of the present invention. Other suitable joining or welding methods may exist or be developed hereafter. All such joining or welding methods are within the scope of the present invention.

15 **Construction of Process Components, Containers, and Pipes**

Process components, containers, and pipes constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi) and DBTTs lower than about -73°C (-100°F) are provided. Preferably the ultra-high strength, low alloy steel
20 contains less than about 7 wt% nickel, and more preferably contains less than about 5 wt% nickel. Preferably the ultra-high strength, low alloy steel has a tensile strength greater than about 860 MPa (125 ksi), and more preferably greater than about 900 MPa (130 ksi). Even more preferably, the process components, containers, and pipes of this invention are constructed from materials comprising an ultra-high strength, low
25 alloy steel containing less than about 3 wt% nickel and having a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).

The process components, containers, and pipes of this invention are preferably constructed from discrete plates of ultra-high strength, low alloy steel with excellent cryogenic temperature toughness. The joints or seams of the components, containers,
30 and pipes preferably have about the same strength and toughness as the ultra-high strength, low alloy steel plates. In some cases, an undermatching of the strength on the order of about 5% to about 10% may be justified for locations of lower stress.

Joints or seams with the preferred properties can be made by any suitable joining technique. An exemplary joining technique is described herein, under the subheading "Joining Methods for Construction of Process Components, Containers, and Pipes".

As will be familiar to those skilled in the art, the Charpy V-notch (CVN) test
5 can be used for the purpose of fracture toughness assessment and fracture control in the design of process components, containers, and pipes for processing and transporting pressurized, cryogenic temperature fluids, particularly through use of the ductile-to-brittle transition temperature (DBTT). The DBTT delineates two fracture regimes in structural steels. At temperatures below the DBTT, failure in the Charpy
10 V-notch test tends to occur by low energy cleavage (brittle) fracture, while at temperatures above the DBTT, failure tends to occur by high energy ductile fracture. Containers that are constructed from welded steels for the load-bearing, cryogenic temperature service must have DBTTs, as determined by the Charpy V-notch test, well below the service temperature of the structure in order to avoid brittle failure.
15 Depending on the design, the service conditions, and/or the requirements of the applicable classification society, the required DBTT temperature shift may be from 5°C to 30°C (9°F to 54°F) below the service temperature.

As will be familiar to those skilled in the art, the operating conditions taken into consideration in the design of storage containers constructed from a welded steel
20 for transporting pressurized, cryogenic fluids, include among other things, the operating pressure and temperature, as well as additional stresses that are likely to be imposed on the steel and the weldments (see Glossary). Standard fracture mechanics measurements, such as (i) critical stress intensity factor (K_{IC}), which is a measurement of plane-strain fracture toughness, and (ii) crack tip opening displacement (CTOD),
25 which can be used to measure elastic-plastic fracture toughness, both of which are familiar to those skilled in the art, may be used to determine the fracture toughness of the steel and the weldments. Industry codes generally acceptable for steel structure design, for example, as presented in the BSI publication "Guidance on methods for assessing the acceptability of flaws in fusion welded structures", often referred to as
30 "PD 6493 : 1991", may be used to determine the maximum allowable flaw sizes for the containers based on the fracture toughness of the steel and weldment (including HAZ) and the imposed stresses on the container. A person skilled in the art can

develop a fracture control program to mitigate fracture initiation through (i) appropriate container design to minimize imposed stresses, (ii) appropriate manufacturing quality control to minimize defects, (iii) appropriate control of life cycle loads and pressures applied to the container, and (iv) an appropriate inspection
5 program to reliably detect flaws and defects in the container. A preferred design philosophy for the system of the present invention is "leak before failure", as is familiar to those skilled in the art. These considerations are generally referred to herein as "known principles of fracture mechanics."

The following is a non-limiting example of application of these known
10 principles of fracture mechanics in a procedure for calculating critical flaw depth for a given flaw length for use in a fracture control plan to prevent fracture initiation in a pressure vessel, such as a process container according to this invention.

FIG. 13B illustrates a flaw of flaw length 315 and flaw depth 310. PD6493 is used to calculate values for the critical flaw size plot 300 shown in FIG. 13A based on
15 the following design conditions for a pressure vessel, such as a container according to this invention:

	Vessel Diameter:	4.57 m (15 ft)
	Vessel Wall Thickness:	25.4 mm (1.00 in.)
20	Design Pressure:	3445 kPa (500 psi)
	Allowable Hoop Stress:	333 MPa (48.3 ksi).

For the purpose of this example, a surface flaw length of 100 mm (4 inches), e.g., an axial flaw located in a seam weld, is assumed. Referring now to FIG. 13A,
25 plot 300 shows the value for critical flaw depth as a function of CTOD fracture toughness and of residual stress, for residual stress levels of 15, 50 and 100 percent of yield stress. Residual stresses can be generated due to fabrication and welding; and PD6493 recommends the use of a residual stress value of 100 percent of yield stress in welds (including the weld HAZ) unless the welds are stress relieved using
30 techniques such as post weld heat treatment (PWHT) or mechanical stress relief.

Based on the CTOD fracture toughness of the steel at the minimum service temperature, the container fabrication can be adjusted to reduce the residual stresses

and an inspection program can be implemented (for both initial inspection and in-service inspection) to detect and measure flaws for comparison against critical flaw size. In this example, if the steel has a CTOD toughness of 0.025 mm at the minimum service temperature (as measured using laboratory specimens) and the residual stresses are reduced to 15 percent of the steel yield strength, then the value for critical flaw depth is approximately 4 mm (see point 320 on FIG. 13A). Following similar calculation procedures, as are well known to those skilled in the art, critical flaw depths can be determined for various flaw lengths as well as various flaw geometries. Using this information, a quality control program and inspection program (techniques, detectable flaw dimensions, frequency) can be developed to ensure that flaws are detected and remedied prior to reaching the critical flaw depth or prior to the application of the design loads. Based on published empirical correlations between CVN, K_{IC} and CTOD fracture toughness, the 0.025 mm CTOD toughness generally correlates to a CVN value of about 37 J. This example is not intended to limit this invention in any way.

For process components, containers, and pipes that require bending of the steel, e.g., into a cylindrical shape for a container or into a tubular shape for a pipe, the steel is preferably bent into the desired shape at ambient temperature in order to avoid detrimentally affecting the excellent cryogenic temperature toughness of the steel. If the steel must be heated to achieve the desired shape after bending, the steel is preferably heated to a temperature no higher than about 600°C (1112°F) in order to preserve the beneficial effects of the steel microstructure as described above.

Cryogenic Process Components

Process components constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi) and DBTTs lower than about -73°C (-100°F) are provided. Preferably the ultra-high strength, low alloy steel contains less than about 7 wt% nickel, and more preferably contains less than about 5 wt% nickel. Preferably the ultra-high strength, low alloy steel has a tensile strength greater than about 860 MPa (125 ksi), and more preferably greater than about 900 MPa (130 ksi). Even more preferably, the process components of this invention are constructed from

materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F). Such process components are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein.

In cryogenic temperature power generation cycles, the primary process components include, for example, condensers, pump systems, vaporizers, and evaporators. In refrigeration systems, liquefaction systems, and air separation plants, the primary process components include, for example, heat exchangers, process columns, separators, and expansion valves or turbines. Flare systems are frequently subjected to cryogenic temperatures, for example, when used in relief systems for ethylene or a natural gas in a low temperature separation process. FIG. 1 illustrates how some of these components are used in a demethanizer gas plant and is further discussed below. Without thereby limiting this invention, particular components, constructed according to the present invention, are described in greater detail below.

• Heat Exchangers

Heat exchangers, or heat exchanger systems, constructed according to this invention, are provided. Components of such heat exchanger systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Without thereby limiting this invention, the following examples illustrate various types of heat exchanger systems according to this invention.

For example, FIG. 2 illustrates a fixed tubesheet, single pass heat exchanger system 20 according to the present invention. In one embodiment, fixed tubesheet, single pass heat exchanger system 20 includes heat exchanger body 20a, channel covers 21a and 21b, a tubesheet 22 (the tubesheet 22 header is shown in FIG. 2), a vent 23, baffles 24, a drain 25, a tube inlet 26, a tube outlet 27, a shell inlet 28, and a shell outlet 29. Without thereby limiting this invention, the following example applications illustrate the advantageous utility of fixed tubesheet, single pass heat exchanger system 20 according to the present invention.

Fixed Tubesheet Example No. 1

In a first example application, fixed tubesheet, single pass heat exchanger system 20 is used as an inlet gas cross-exchanger in a cryogenic gas plant with demethanizer overheads on the shell side and inlet gas on the tubeside. The inlet gas enters fixed tubesheet, single pass heat exchanger system 20 through tube inlet 26 and exits through tube outlet 27, while the demethanizer overheads fluid enters through shell inlet 28 and exits through shell outlet 29.

Fixed Tubesheet Example No. 2

In a second example application, fixed tubesheet, single pass heat exchanger system 20 is used as a side reboiler on a cryogenic demethanizer with precooled feed on the tubeside and cryogenic column sidestream liquids boiling on the shell side to remove methane from the bottoms product. The precooled feed enters fixed tubesheet, single pass heat exchanger system 20 through tube inlet 26 and exits through tube outlet 27, while the cryogenic column sidestream liquids enter through shell inlet 28 and exit through shell outlet 29.

Fixed Tubesheet Example No. 3

In another example application, fixed tubesheet, single pass heat exchanger system 20 is used as a side reboiler on a Ryan Holmes product recovery column to remove methane and CO₂ from the bottoms product. A precooled feed enters fixed tubesheet, single pass heat exchanger system 20 through tube inlet 26 and exits through tube outlet 27, while cryogenic tower sidestream liquids enter through shell inlet 28 and exit through shell outlet 29.

Fixed Tubesheet Example No. 4

In another example application, fixed tubesheet, single pass heat exchanger system 20 is used as a side reboiler on a CFZ CO₂ removal column with a cryogenic liquid sidestream on the shell side and precooled feed gas on the tubeside to remove methane and other hydrocarbons from the CO₂-rich bottoms product. The precooled feed enters fixed tubesheet, single pass heat exchanger system 20 through tube inlet 26 and exits through tube outlet 27, while a cryogenic liquid sidestream enters through shell inlet 28 and exits through shell outlet 29.

In Fixed Tubesheet Example Nos. 1-4, heat exchanger body 20a, channel covers 21a and 21b, tubesheet 22, vent 23, and baffles 24 preferably are constructed

from steels containing less than about 3 wt% nickel and have adequate strength and fracture toughness to contain the cryogenic temperature fluid being processed, and more preferably are constructed from steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower
5 than about -73°C (-100°F). Furthermore, heat exchanger body 20a, channel covers 21a and 21b, tubesheet 22, vent 23, and baffles 24 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of fixed tubesheet, single pass heat exchanger system 20 may also be constructed from the ultra-high strength, low alloy steels with
10 excellent cryogenic temperature toughness described herein, or from other suitable materials.

FIG. 3 illustrates a kettle reboiler heat exchanger system 30 according to the present invention. In one embodiment, kettle reboiler heat exchanger system 30 includes a kettle reboiler body 31, a weir 32, a heat exchange tube 33, a tubeside inlet
15 34, a tubeside outlet 35, a kettle inlet 36, a kettle outlet 37, and a drain 38. Without thereby limiting this invention, the following example applications illustrate the advantageous utility of a kettle reboiler heat exchanger system 30 according to the present invention.

Kettle Reboiler Example No. 1

20 In a first example, kettle reboiler heat exchanger system 30 is used in a cryogenic gas liquids recovery plant with propane vaporizing at about -40°C (-40°F) on the kettle side and hydrocarbon gas on the tubeside. The hydrocarbon gas enters kettle reboiler heat exchanger system 30 through tubeside inlet 34 and exits through tubeside outlet 35, while the propane enters through kettle inlet 36 and exits through
25 kettle outlet 37.

Kettle Reboiler Example No. 2

In a second example, kettle reboiler heat exchanger system 30 is used in a refrigerated lean oil plant with propane vaporizing at about -40°C (-40°F) on the kettle side and lean oil on the tubeside. The lean oil enters kettle reboiler heat
30 exchanger system 30 through tube inlet 34 and exits through tube outlet 35, while the propane enters through kettle inlet 36 and exits through kettle outlet 37.

Kettle Reboiler Example No. 3

In another example, kettle reboiler heat exchanger system 30 is used in a Ryan Holmes product recovery column with propane vaporizing at about -40°C (-40°F) on the kettle side and product recovery column overhead gas on the tubeside to condense reflux for the tower. The product recovery column overhead gas enters kettle reboiler heat exchanger system 30 through tube inlet 34 and exits through tube outlet 35, while the propane enters through kettle inlet 36 and exits through kettle outlet 37.

Kettle Reboiler Example No. 4

In another example, kettle reboiler heat exchanger system 30 is used in Exxon's CFZ process with refrigerant vaporizing on the kettle side and CFZ tower overhead gas on the tube side to condense liquid methane for tower reflux and keep CO_2 out of the overhead methane product stream. The CFZ tower overhead gas enters kettle reboiler heat exchanger system 30 through tube inlet 34 and exits through tube outlet 35, while the refrigerant enters through kettle inlet 36 and exits through kettle outlet 37. The refrigerant preferably comprises propylene or ethylene, as well as a mixture of any or all of components of the group comprising methane, ethane, propane, butane, and pentane.

Kettle Reboiler Example No. 5

In another example, kettle reboiler heat exchanger system 30 is used as a bottoms reboiler on a cryogenic demethanizer with tower bottoms product on the kettle side and hot inlet gas or hot oil on the tube side to remove methane from the bottoms product. The hot inlet gas or hot oil enters kettle reboiler heat exchanger system 30 through tube inlet 34 and exits through tube outlet 35, while the tower bottoms product enters through kettle inlet 36 and exits through kettle outlet 37.

Kettle Reboiler Example No. 6

In another example, kettle reboiler heat exchanger system 30 is used as a bottoms reboiler on a Ryan Holmes product recovery column with bottoms products on the kettle side and hot feed gas or hot oil on the tube side to remove methane and CO_2 from the bottoms product. The hot feed gas or hot oil enters kettle reboiler heat exchanger system 30 through tube inlet 34 and exits through tube outlet 35, while the bottoms products enter through kettle inlet 36 and exit through kettle outlet 37.

Kettle Reboiler Example No. 7

In another example, kettle reboiler heat exchanger system 30 is used on a CFZ CO₂ removal tower with tower bottoms liquids on the kettle side and hot feed gas or hot oil on the tube side to remove methane and other hydrocarbons from the CO₂-rich liquid bottoms stream. The hot feed gas or hot oil enters kettle reboiler heat exchanger system 30 through tube inlet 34 and exits through tube outlet 35, while the tower bottoms liquids enter through kettle inlet 36 and exit through kettle outlet 37.

In Kettle Reboiler Example Nos. 1-7, kettle reboiler body 31, heat exchanger tube 33, weir 32, and port connections for tubeside inlet 34, tubeside outlet 35, kettle inlet 36, and kettle outlet 37 preferably are constructed from steels containing less than about 3 wt% nickel and have adequate strength and fracture toughness to contain the cryogenic fluid being processed, and more preferably are constructed from steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, kettle reboiler body 31, heat exchanger tube 33, weir 32, and port connections for tubeside inlet 34, tubeside outlet 35, kettle inlet 36, and kettle outlet 37 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of kettle reboiler heat exchanger system 30 may also be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

The design criteria and method of construction of heat exchanger systems according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

• Condensers

Condensers, or condenser systems, constructed according to this invention, are provided. More particularly, condenser systems, with at least one component constructed according to this invention, are provided. Components of such condenser systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Without thereby limiting

this invention, the following examples illustrate various types of condenser systems according to this invention.

Condenser Example No. 1

Referring to FIG. 1, a condenser according to this invention is used in a demethanizer gas plant 10 in which a feed gas stream is separated into a residue gas and a product stream using a demethanizer column 11. In this particular example, the overhead from demethanizer column 11, at a temperature of about -90°C (-130°F) is condensed into a reflux accumulator (separator) 15 using reflux condenser system 12. Reflux condenser system 12 exchanges heat with the gaseous discharge stream from expander 13. Reflux condenser system 12 is primarily a heat exchanger system, preferably of the types discussed above. In particular, reflux condenser system 12 may be a fixed tubesheet, single pass heat exchanger (e.g. fixed tubesheet, single pass heat exchanger 20, as illustrated by FIG. 2 and described above). Referring again to FIG. 2, the discharge stream from expander 13 enters fixed tubesheet, single pass heat exchanger system 20 through tube inlet 26 and exits through tube outlet 27 while the demethanizer overhead enters the shell inlet 28 and exits through shell outlet 29.

Condenser Example No. 2

Referring now to FIG. 7, a condenser system 70 according to this invention is used in a reverse Rankine cycle for generating power using the cold energy from a cold energy source such as pressurized liquefied natural gas (PLNG) (see Glossary) or conventional LNG (see Glossary). In this particular example, the power fluid is used in a closed thermodynamic cycle. The power fluid, in gaseous form, is expanded in turbine 72 and then fed as gas into condenser system 70. The power fluid exits condenser system 70 as a single phase liquid and is pumped by pump 74 and subsequently vaporized by vaporizer 76 before returning to the inlet of turbine 72. Condenser system 70 is primarily a heat exchanger system, preferably of the types discussed above. In particular, condenser system 70 may be a fixed tubesheet, single pass heat exchanger (e.g. fixed tubesheet, single pass heat exchanger 20, as illustrated by FIG. 2 and described above).

Referring again to FIG. 2, in Condenser Example Nos. 1 and 2, heat exchanger body 20a, channel covers 21a and 21b, tubesheet 22, vent 23, and baffles 24 preferably are constructed from ultra-high strength, low alloy steels containing less

than about 3 wt% nickel and have adequate strength and cryogenic temperature fracture toughness to contain the cryogenic fluid being processed, and more preferably are constructed from ultra-high strength, low alloy steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145
5 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, heat exchanger body 20a, channel covers 21a and 21b, tubesheet 22, vent 23, and baffles 24 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of condenser system 70 may also be constructed from the ultra-high strength, low alloy steels with excellent
10 cryogenic temperature toughness described herein, or from other suitable materials.

Condenser Example No. 3

Referring now to FIG. 8, a condenser according to this invention is used in a cascade refrigeration cycle 80 consisting of several staged compression cycles. The major items of equipment of cascade refrigeration cycle 80 include propane
15 compressor 81, propane condenser 82, ethylene compressor 83, ethylene condenser 84, methane compressor 85, methane condenser 86, methane evaporator 87, and expansion valves 88. Each stage operates at successively lower temperatures by the selection of a series of refrigerants with boiling points that span the temperature range required for the complete refrigeration cycle. In this example cascade cycle, the three
20 refrigerants, propane, ethylene, and methane, may be used in an LNG process with the typical temperatures indicated on FIG. 8. In this example, all parts of methane condenser 86 and of ethylene condenser 84 preferably are constructed from ultra-high strength, low alloy steels containing less than about 3 wt% nickel and have adequate strength and cryogenic temperature fracture toughness to contain the cryogenic fluid
25 being processed, and more preferably are constructed from ultra-high strength, low alloy steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, all parts of methane condenser 86 and of ethylene condenser 84 are preferably constructed from the ultra-high strength, low alloy steels with excellent
30 cryogenic temperature toughness described herein. Other components of cascade refrigeration cycle 80 may also be constructed from the ultra-high strength, low alloy

steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

The design criteria and method of construction of condenser systems according to this invention are familiar to those skilled in the art, especially in view of
5 the disclosure provided herein.

- Vaporizers/Evaporators

Vaporizers/evaporators, or vaporizer systems, constructed according to this invention, are provided. More particularly, vaporizer systems, with at least one
10 component constructed according to this invention, are provided. Components of such vaporizer systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Without thereby limiting this invention, the following examples illustrate various types of vaporizer systems according to this invention.

15 Vaporizer Example No. 1

In a first example, a vaporizer system according to this invention is used in a reverse Rankine cycle for generating power using the cold energy from a cold energy source such as pressurized LNG (as defined herein) or conventional LNG (as defined herein). In this particular example, a process stream of PLNG from a transportation
20 storage container is completely vaporized using the vaporizer. The heating medium may be power fluid used in a closed thermodynamic cycle, such as a reverse Rankine cycle, to generate power. Alternatively, the heating medium may consist of a single fluid used in an open loop to completely vaporize the PLNG, or several different fluids with successively higher freezing points used to vaporize and successively
25 warm the PLNG to ambient temperature. In all cases, the vaporizer serves the function of a heat exchanger, preferably of the types described in detail herein under the subheading "Heat Exchangers". The mode of application of the vaporizer and the composition and properties of the stream or streams processed determine the specific type of heat exchanger required. As an example, referring again to FIG. 2, where use
30 of fixed tubesheet, single pass heat exchanger system 20 is applicable, a process stream, such as PLNG, enters fixed tubesheet single pass heat exchanger system 20 through tube inlet 26 and exits through tube outlet 27, while the heating medium

enters through shell inlet 28 and exits through shell outlet 29. In this example, heat exchanger body 20a, channel covers 21a and 21b, tubesheet 22, vent 23, and baffles 24 preferably are constructed from steels containing less than about 3 wt% nickel and have adequate strength and fracture toughness to contain the cryogenic temperature fluid being processed, and more preferably are constructed from steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, heat exchanger body 20a, channel covers 21a and 21b, tubesheet 22, vent 23, and baffles 24 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of fixed tubesheet, single pass heat exchanger system 20 may also be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

Vaporizer Example No. 2

In another example, a vaporizer according to this invention is used in a cascade refrigeration cycle consisting of several staged compression cycles, as illustrated by FIG. 9. Referring to FIG. 9, each of the two staged compression cycles of cascade cycle 90 operates at successively lower temperatures by the selection of a series of refrigerants with boiling points that span the temperature range required for the complete refrigeration cycle. The major items of equipment in cascade cycle 90 include propane compressor 92, propane condenser 93, ethylene compressor 94, ethylene condenser 95, ethylene evaporator 96, and expansion valves 97. In this example, the two refrigerants propane and ethylene are used in a PLNG liquefaction process with the typical temperatures indicated. Ethylene evaporator 96 preferably is constructed from steels containing less than about 3 wt% nickel and has adequate strength and fracture toughness to contain the cryogenic temperature fluid being processed, and more preferably is constructed from steels containing less than about 3 wt% nickel and has a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F). Furthermore, ethylene evaporator 96 is preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of cascade cycle 90 may also be constructed from the ultra-high strength, low alloy steels with

excellent cryogenic temperature toughness described herein, or from other suitable materials.

The design criteria and method of construction of vaporizer systems according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

- Separators

Separators, or separator systems, (i) constructed from ultra-high strength, low alloy steels containing less than about 3 wt% nickel and (ii) having adequate strength and cryogenic temperature fracture toughness to contain cryogenic temperature fluids, are provided. More particularly, separator systems, with at least one component (i) constructed from an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and (ii) having a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F), are provided. Components of such separator systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Without thereby limiting this invention, the following example illustrates a separator system according to this invention.

FIG. 4 illustrates a separator system 40 according to the present invention. In one embodiment, separator system 40 includes vessel 41, inlet port 42, liquid outlet port 43, gas outlet 44, support skirt 45, liquid level controller 46, isolation baffle 47, mist extractor 48, and pressure relief valve 49. In one example application, without thereby limiting this invention, separator system 40 according to the present invention is advantageously utilized as an expander feed separator in a cryogenic gas plant to remove condensed liquids upstream of an expander. In this example, vessel 41, inlet port 42, liquid outlet port 43, support skirt 45, mist extractor supports 48, and isolation baffle 47 are preferably constructed from steels containing less than about 3 wt% nickel and have adequate strength and fracture toughness to contain the cryogenic temperature fluid being processed, and more preferably are constructed from steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, vessel 41, inlet port 42, liquid outlet port 43, support skirt 45, mist

extractor supports 48, and isolation baffle 47 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of separator system 40 may also be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

The design criteria and method of construction of separator systems according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

10 • Process Columns

Process columns, or process column systems, constructed according to this invention, are provided. Components of such process column systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Without thereby limiting this invention, the following examples illustrate various types of process column systems according to this invention.

Process Column Example No. 1

FIG. 11 illustrates a process column system according to the present invention. In this embodiment, demethanizer process column system 110 includes column 111, separator bell 112, first inlet 113, second inlet 114, liquid outlet 121, vapor outlet 115, reboiler 119, and packing 120. In one example application, without thereby limiting this invention, process column system 110 according to the present invention is advantageously utilized as a demethanizer in a cryogenic gas plant to separate methane from the other condensed hydrocarbons. In this example, column 111, separator bell 112, packing 120, and other internals commonly used in such a process column system 110 are preferably constructed from steels containing less than about 3 wt% nickel and have adequate strength and fracture toughness to contain the cryogenic temperature fluid being processed, and more preferably are constructed from steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, column 111, separator bell 112, packing 120, and other internals commonly used in such a process column system 110 are preferably constructed from

the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of process column system 110 may also be constructed from ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

5 Process Column Example No. 2

FIG. 12 illustrates a process column system 125 according to the present invention. In this example, process column system 125 is advantageously utilized as a CFZ tower in a CFZ process for separating CO₂ from methane. In this example, column 126, melting trays 127, and contacting trays 128 are preferably constructed
10 from steels containing less than about 3 wt% nickel and have adequate strength and fracture toughness to contain the cryogenic temperature fluid being processed, and more preferably are constructed from steels containing less than about 3 wt% nickel and have tensile strengths exceeding about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, column 126, melting trays 127, and
15 contacting trays 128 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of process column system 125 may also be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

20 The design criteria and method of construction of process columns according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

25 • Pump Components and Systems

Pumps, or pump systems, constructed according to this invention, are provided. Components of such pump systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Without thereby limiting this invention, the following example
30 illustrates a pump system according to this invention.

Referring now to FIG. 10, pump system 100 is constructed according to this invention. Pump system 100 is made from substantially cylindrical and plate

components. A cryogenic fluid enters cylindrical fluid inlet 101 from a pipe attached to inlet flange 102. The cryogenic fluid flows inside cylindrical casing 103 to pump inlet 104 and into multi-stage pump 105 where it undergoes an increase in pressure energy. Multi-stage pump 105 and drive shaft 106 are supported by a cylindrical bearing and pump support housing (not shown in FIG. 10). The cryogenic fluid leaves pump system 100 through fluid outlet 108 in a pipe attached to fluid exit flange 109. A driving means such as an electric motor (not shown in FIG. 10) is mounted on the drive mounting flange 210 and attached to pump system 100 through drive coupling 211. Drive mounting flange 210 is supported by cylindrical coupling housing 212. In this example, pump system 100 is mounted between pipe flanges (not shown in FIG. 10); but other mounting systems are also applicable, such as submerging pump system 100 in a tank or vessel such that the cryogenic liquid enters directly into fluid inlet 101 without the connecting pipe. Alternatively, pump system 100 is installed in another housing or "pump pot", where both fluid inlet 101 and fluid outlet 108 are connected to the pump pot, and pump system 100 is readily removable for maintenance or repair. In this example, pump casing 213, inlet flange 102, drive coupling housing 212, drive mounting flange 210, mounting flange 214, pump end plate 215, and pump and bearing support housing 217 are all preferably constructed from steels containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi) and DBTTs lower than about -73°C (-100°F), and more preferably are constructed from steels containing less than about 3 wt% nickel and having tensile strengths greater than about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, pump casing 213, inlet flange 102, drive coupling housing 212, drive mounting flange 210, mounting flange 214, pump end plate 215, and pump and bearing support housing 217 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of pump system 100 may also be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

The design criteria and method of construction of pump components and systems according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

- Flare Components and Systems

Flares, or flare systems, constructed according to this invention, are provided. Components of such flare systems are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described
5 herein. Without thereby limiting this invention, the following example illustrates a flare system according to this invention.

FIG. 5 illustrates a flare system 50 according to the present invention. In one embodiment, flare system 50 includes blowdown valves 56, piping, such as lateral
10 line 53, collection header line 52, and flare line 51, and also includes a flare scrubber 54, a flare stack or boom 55, a liquid drain line 57, a drain pump 58, a drain valve 59, and auxiliaries (not shown in FIG. 5) such as ignitors and purge gas. Flare system 50 typically handles combustible fluids that are at cryogenic temperatures due to process conditions or that cool to cryogenic temperatures upon relief to flare system 50, i.e.,
15 from a large pressure drop across relief valves or blowdown valves 56. Flare line 51, collection header line 52, lateral line 53, flare scrubber 54, and any additional associated piping or systems that would be exposed to the same cryogenic temperatures as flare system 50 are all preferably constructed from steels containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi)
20 and DBTTs lower than about -73°C (-100°F), and more preferably are constructed from steels containing less than about 3 wt% nickel and having tensile strengths greater than about 1000 MPa (145 ksi) and DBTTs lower than about -73°C (-100°F). Furthermore, flare line 51, collection header line 52, lateral line 53, flare scrubber 54, and any additional associated piping or systems that would be exposed to the same
25 cryogenic temperatures as flare system 50 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein. Other components of flare system 50 may also be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein, or from other suitable materials.

30 The design criteria and method of construction of flare components and systems according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

In addition to the other advantages of this invention, as discussed above, a flare system constructed according to this invention has good resistance to vibrations that can occur in flare systems when relieving rates are high.

5 Containers for Storage of Cryogenic Temperature Fluids

Containers constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi) and DBTTs lower than about -73°C (-100°F) are provided. Preferably the ultra-high strength, low alloy steel contains less than about 7 wt%
10 nickel, and more preferably contains less than about 5 wt% nickel. Preferably the ultra-high strength, low alloy steel has a tensile strength greater than about 860 MPa (125 ksi), and more preferably greater than about 900 MPa (130 ksi). Even more preferably, the containers of this invention are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and
15 having a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F). Such containers are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein.

In addition to the other advantages of this invention, as discussed above, i.e.,
20 less overall weight with concomitant savings in transport, handling, and substructure requirements, the excellent cryogenic temperature toughness of storage containers of this invention is especially advantageous for cylinders that are frequently handled and transported for refill, such as cylinders for storage of CO₂ used in the food and beverage industry. Industry plans have recently been announced to make bulk sales
25 of CO₂ at cold temperatures to avoid the high pressure of compressed gas. Storage containers and cylinders according to this invention can be advantageously used to store and transport liquefied CO₂ at optimized conditions.

The design criteria and method of construction of containers for storage of cryogenic temperature fluids according to this invention are familiar to those skilled
30 in the art, especially in view of the disclosure provided herein.

Pipes

Flowline distribution network systems, comprising pipes constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi) and DBTTs lower than about -73°C (-100°F) are provided. Preferably the ultra-high strength, low alloy steel contains less than about 7 wt% nickel, and more preferably contains less than about 5 wt% nickel. Preferably the ultra-high strength, low alloy steel has a tensile strength greater than about 860 MPa (125 ksi), and more preferably greater than about 900 MPa (130 ksi). Even more preferably, the flowline distribution network system pipes of this invention are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength exceeding about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F). Such pipes are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein.

FIG. 6 illustrates a flowline distribution network system 60 according to the present invention. In one embodiment, flowline distribution network system 60 includes piping, such as primary distribution pipes 61, secondary distribution pipes 62, and tertiary distribution pipes 63, and includes main storage containers 64, and end use storage containers 65. Main storage containers 64 and end use storage containers 65 are all designed for cryogenic service, i.e., appropriate insulation is provided. Any appropriate insulation type may be used, for example, without thereby limiting this invention, high-vacuum insulation, expanded foam, gas-filled powders and fibrous materials, evacuated powders, or multi-layer insulation. Selection of an appropriate insulation depends on performance requirements, as is familiar to those skilled in the art of cryogenic engineering. Main storage containers 64, piping, such as primary distribution pipes 61, secondary distribution pipes 62, and tertiary distribution pipes 63, and end use storage containers 65 are preferably constructed from steels containing less than 9 wt% nickel and having tensile strengths greater than 830 MPa (120 ksi) and DBTTs lower than about -73°C (-100°F), and more preferably are constructed from steels containing less than about 3 wt% nickel and having tensile strengths greater than about 1000 MPa (145 ksi) and DBTTs lower than about -73°C

(-100°F). Furthermore, main storage containers 64, piping, such as primary distribution pipes 61, secondary distribution pipes 62, and tertiary distribution pipes 63, and end use storage containers 65 are preferably constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described
5 herein. Other components of distribution network system 60 may be constructed from the ultra-high strength, low alloy steels with excellent cryogenic temperature toughness described herein or from other suitable materials.

The ability to distribute fluids that are to be used in the cryogenic temperature condition via a flowline distribution network system allows for smaller on-site storage
10 containers than would be necessary if the fluid had to be transported via tanker truck or railway. The primary advantage is a reduction in required storage due to the fact that there is continual feed, rather than periodic delivery, of the pressurized, cryogenic temperature fluid.

The design criteria and method of construction of pipes for flowline
15 distribution network systems for cryogenic temperature fluids according to this invention are familiar to those skilled in the art, especially in view of the disclosure provided herein.

The process components, containers, and pipes of this invention are advantageously used for containing and transporting pressurized, cryogenic
20 temperature fluids or cryogenic temperature fluids at atmospheric pressure. Additionally, the process components, containers, and pipes of this invention are advantageously used for containing and transporting pressurized, non-cryogenic temperature fluids.

While the foregoing invention has been described in terms of one or more
25 preferred embodiments, it should be understood that other modifications may be made without departing from the scope of the invention, which is set forth in the following claims.

Glossary of terms:

	Ac ₁ transformation temperature:	the temperature at which austenite begins to form during heating;
5	Ac ₃ transformation temperature:	the temperature at which transformation of ferrite to austenite is completed during heating;
10	Ar ₁ transformation temperature:	the temperature at which transformation of austenite to ferrite or to ferrite plus cementite is completed during cooling;
15	Ar ₃ transformation temperature:	the temperature at which austenite begins to transform to ferrite during cooling;
	CFZ:	controlled freeze zone;
20	conventional LNG:	liquefied natural gas at about atmospheric pressure and about -162°C (-260°F);
	cooling rate:	cooling rate at the center, or substantially at the center, of the plate thickness;
25	cryogenic temperature:	any temperature lower than about -40°C (-40°F);
	CTOD:	crack tip opening displacement;

	DBTT (Ductile to Brittle Transition Temperature):	delineates the two fracture regimes in structural steels; at temperatures below the DBTT, failure tends to occur by low energy cleavage (brittle) fracture, while at temperatures above the DBTT, failure tends to occur by high energy ductile fracture;
5		
10	essentially:	substantially 100 vol%;
	GMAW:	gas metal arc welding;
	hardening particles	one or more of ϵ -copper, Mo_2C , or the carbides and carbonitrides of niobium and vanadium;
15		
	HAZ:	heat affected zone;
	intercritical temperature range:	from about the Ac_1 transformation temperature to about the Ac_3 transformation temperature on heating, and from about the Ar_3 transformation temperature to about the Ar_1 transformation temperature on cooling;
20		
25	K_{IC} :	critical stress intensity factor;
	kJ:	kilojoule;
	low alloy steel:	a steel containing iron and less than about 10 wt% total alloy additives;
30		
	MA:	martensite-austenite;

	maximum allowable flaw size:	critical flaw length and depth;
	Mo ₂ C:	a form of molybdenum carbide;
5	M _s transformation temperature:	the temperature at which transformation of austenite to martensite starts during cooling;
	pressurized liquefied natural	
10	gas (PLNG):	liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F);
15	ppm:	parts-per-million;
	predominantly:	at least about 50 volume percent;
20	quenching:	accelerated cooling by any means whereby a fluid selected for its tendency to increase the cooling rate of the steel is utilized, as opposed to air cooling;
25	Quench Stop Temperature (QST):	the highest, or substantially the highest, temperature reached at the surface of the plate, after quenching is stopped, because of heat transmitted from the mid-thickness of the plate;
30	QST:	Quench Stop Temperature;

	slab:	a piece of steel having any dimensions;
5	tensile strength:	in tensile testing, the ratio of maximum load to original cross-sectional area;
	TIG welding:	tungsten inert gas welding;
10	T_{nr} temperature:	the temperature below which austenite does not recrystallize;
	USPTO:	United States Patent and Trademark Office; and
15	weldment:	a welded joint, including: (i) the weld metal, (ii) the heat-affected zone (HAZ), and (iii) the base metal in the "near vicinity" of the HAZ. The portion of the base metal that is considered within the "near vicinity" of the HAZ, and therefore, a part of the weldment, varies
20		depending on factors known to those skilled in the art, for example, without limitation, the width of the weldment, the size of the item that was welded, the number of weldments required to fabricate the item, and the distance between
25		weldments.

We Claim:

1. A heat exchanger system suitable for containing a pressurized, cryogenic temperature fluid, said heat exchanger system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).
2. The heat exchanger system of claim 1 comprising a heat exchanger body, first and second channel covers, a tubesheet, a vent, and a plurality of baffles.
3. The heat exchanger system of claim 2, wherein said heat exchanger body, said first and second channel covers, said tubesheet, said vent, and said plurality of baffles are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength greater than about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).
4. The heat exchanger system of claim 1, wherein said pressurized, cryogenic temperature fluid is pressurized liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F).
5. A heat exchanger system suitable for containing pressurized liquefied natural gas at a pressure of about 1725 kPa (250 psia) to about 4830 kPa (700 psia) and at a temperature of about -112°C (-170°F) to about -79°C (-110°F), wherein said heat exchanger system (i) is constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and (ii) has adequate strength and fracture toughness to contain said pressurized liquefied natural gas.


This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



6. A condenser system suitable for containing a pressurized, cryogenic temperature fluid, said condenser system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).
7. A vaporizer system suitable for containing a pressurized, cryogenic temperature fluid, said vaporizer system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).
8. A separator system suitable for containing a pressurized, cryogenic temperature fluid, said separator system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).
9. The separator system of claim 8 comprising a vessel, an inlet port, a liquid outlet port, a support skirt, a plurality of mist extractor supports, and at least one isolation baffle.
10. The separator system of claim 9, wherein said vessel, said inlet port, said liquid outlet port, said support skirt, said plurality of mist extractor supports, and said at least one isolation baffle, are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength greater than about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).


This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



11. The separator system of claim 8, wherein said pressurized, cryogenic temperature fluid is pressurized liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F).
- 5
12. A process column system suitable for containing a pressurized, cryogenic temperature fluid, said process column system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120
- 10 ksi) and a DBTT lower than about -73°C (-100°F).
13. The process column system of claim 12 comprising a column, a separator bell, and packing.
- 15
14. The process column system of claim 13, wherein said column, said separator bell, and said packing, are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength greater than about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).
- 20
15. The process column system of claim 12, wherein said pressurized, cryogenic temperature fluid is pressurized liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F).
- 25
16. A pump system suitable for pumping a pressurized, cryogenic temperature fluid, said pump system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower
- 30 than about -73°C (-100°F).

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



17. The pump system of claim 16 comprising a pump casing, an inlet flange, a drive coupling housing, a drive mounting flange, a mounting flange, a pump end plate, and a pump and bearing support housing.
- 5 18. The pump system of claim 17, wherein said pump casing, said inlet flange, said drive coupling housing, said drive mounting flange, said mounting flange, said pump end plate, and said pump and bearing support housing, are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength greater than about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).
- 10
19. The pump system of claim 16, wherein said pressurized, cryogenic temperature fluid is pressurized liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F).
- 15
20. A pump system suitable for pumping pressurized liquefied natural gas at a pressure of about 1725 kPa (250 psia) to about 4830 kPa (700 psia) and at a temperature of about -112°C (-170°F) to about -79°C (-110°F), wherein said pump system (i) is constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and (ii) has adequate strength and fracture toughness to contain said pressurized liquefied natural gas.
- 20
- 25 21. A flare system suitable for containing a pressurized, cryogenic temperature fluid, said flare system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).
- 30
22. The flare system of claim 21 comprising a flare line, a collection header line, a lateral line, and a flare scrubber.

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



23. The flare system of claim 22, wherein said flare line, said collection header line, said lateral line, and said flare scrubber, are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength greater than about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).
24. The flare system of claim 21, wherein said pressurized, cryogenic temperature fluid is pressurized liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F).
25. A flare system suitable for containing pressurized liquefied natural gas at a pressure of about 1725 kPa (250 psia) to about 4830 kPa (700 psia) and at a temperature of about -112°C (-170°F) to about -79°C (-110°F), wherein said flare system (i) is constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and (ii) has adequate strength and fracture toughness to contain said pressurized liquefied natural gas.
26. A flowline distribution network system for distributing a pressurized, cryogenic temperature fluid, said flowline distribution network system being constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and having a tensile strength greater than 830 MPa (120 ksi) and a DBTT lower than about -73°C (-100°F).
27. The flowline distribution network system of claim 26 comprising at least one main storage container, at least one primary distribution pipe, and at least one end use storage container.

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



28. The flowline distribution network system of claim 27, wherein said at least one main storage container, at least one primary distribution pipe, and at least one end use storage container, are constructed from materials comprising an ultra-high strength, low alloy steel containing less than about 3 wt% nickel and having a tensile strength greater than about 1000 MPa (145 ksi) and a DBTT lower than about -73°C (-100°F).
29. The flowline distribution network system of claim 26, wherein said pressurized, cryogenic temperature fluid is pressurized liquefied natural gas at a pressure of about 1035 kPa (150 psia) to about 7590 kPa (1100 psia) and at a temperature of about -123°C (-190°F) to about -62°C (-80°F).
30. A flowline distribution network system suitable for containing pressurized liquefied natural gas at a pressure of about 1725 kPa (250 psia) to about 4830 kPa (700 psia) and at a temperature of about -112°C (-170°F) to about -79°C (-110°F), wherein said flowline distribution network system (i) is constructed from materials comprising an ultra-high strength, low alloy steel containing less than 9 wt% nickel and (ii) has adequate strength and fracture toughness to contain said pressurized liquefied natural gas.

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED