

**Catalyst for the synthesis of methyl mercaptan and process for
producing methyl mercaptan from synthesis gas and hydrogen
sulphide**

5 The work that led to this invention received financing from the European Union as part of the 7th Framework Programme (FP7/2007-2013) under project number No. 241718 EUROBIOREF.

10 The present invention relates to a specific molybdenum- and potassium-based catalyst that is useful for producing methyl mercaptan from synthesis gas and hydrogen sulfide, and to its preparation process.

 The invention also relates to a process for producing methyl mercaptan that uses this catalyst.

15 The invention lastly relates to the use of hydroxyapatite as a support for a catalyst for producing methyl mercaptan.


 Methyl mercaptan has great industrial interest, particularly as a raw material for synthesizing methionine, an essential amino acid that is in widespread use in animal food. Methyl mercaptan is also a raw material for many other molecules, in particular dimethyldisulfide (DMDS), a sulfidation additive for hydrotreating catalysts in
20 petroleum fractions, among other applications.

 Methyl mercaptan is commonly produced in large tonnages industrially from methanol and hydrogen sulfide. It may prove economically interesting to want to produce methyl mercaptan directly
25 from carbon monoxide, hydrogen and hydrogen sulfide according to the following reaction scheme:




 The main by-product from this synthesis is carbon dioxide. Carbonyl sulfide (COS) is considered to be the reaction intermediate,
30 which leads to methyl mercaptan after hydrogenation according to the following reaction schemes:






The carbon dioxide comes from two side reactions:



5 These two side reactions, which consume the main raw material: carbon monoxide, and the reaction intermediate: carbonyl sulfide, are due to the inescapable presence of water, coproduced during methyl mercaptan synthesis. The carbon dioxide can optionally be recycled to produce methyl mercaptan as well according to the
10 following scheme:



 But this reaction is known to be slower than that from carbon monoxide. Therefore there is incentive to make carbon dioxide production as low as possible at the outlet of the methyl mercaptan
15 reactor.

 From document WO2005/040082 several catalysts are known for the synthesis of methyl mercaptan from synthesis gas and hydrogen sulfide.

 In particular, this document discloses the use of a catalyst
20 comprising a Mo-O-K based active component, an active promoter and optionally a support. The catalysts exemplified have different chemical natures, such as $\text{K}_2\text{MoO}_4/\text{Fe}_2\text{O}_3/\text{NiO}$ or $\text{K}_2\text{MoO}_4/\text{CoO}/\text{CeO}_2/\text{SiO}_2$, each supported on silica. This leads to a CO_2/MeSH selectivity ratio of 0.88 at 333°C.

25 A family of catalysts composed of a porous support onto which a metal has been deposited electrolytically is also known from document US2010/0286448. K_2MoO_4 and another metal oxide as promoter were then impregnated onto this support. Example 15 of this document describes the preparation of $\text{K}_2\text{MoO}_4/\text{NiO}/\text{CoSiO}_2$. The
30 CO_2/MeSH selectivity ratio with this complex catalyst is 0.65.

 Lastly, US document 2010/0094059 describes supported K_2MoO_4 based catalysts, where the porous support used alone or in mixtures is chosen from SiO_2 , Al_2O_3 , TiO_2 , $\text{Al}_2\text{O}_3/\text{SiO}_2$, ZrO_2 , zeolites or carbon-containing materials. Tellurium oxide (TeO_2) is used as

promoter. The CO₂/MeSH selectivity ratios are comprised between 0.60 and 0.77 measured at 300°C.

5 From the teaching of these documents it has been observed that combining catalysts with specific structures, promoters and supports, each being carefully selected, means that interesting selectivity ratios can be achieved.

10 There is a current need for a catalyst that is simply synthesized and leads to very good selectivity. This technical problem has been resolved by a molybdenum- and potassium- based catalyst supported by hydroxyapatite.

Summary

15 In one aspect of the present disclosure, there is provided a catalyst comprising a molybdenum- and potassium-based active component, chosen from compounds based on Mo-S-K, compounds based on Mo-O-K, and their mixtures, and a hydroxyapatite-based support.

20 In another aspect of the present disclosure, there is provided a preparation process for the catalyst as defined herein, characterized in that it comprises the following steps:

- preparing the precursor for the active phase
 - preparing the support, and
 - dry impregnating the support with the active phase
- 25 precursor.

In a further aspect of the present disclosure, there is provided a production process for methyl mercaptan in a catalytic process by reacting carbon oxide, sulfur and/or hydrogen sulfide and hydrogen, comprising the use of a catalyst as defined herein.

30

Description

5 It has been observed that the catalyst according to the invention is easier to prepare, given that the presence of a promoter is not indispensable. It is less costly than those disclosed in the previously cited documents. And lastly, it leads to very good CO₂/MeSH selectivities.

The invention also relates to the preparation process for this catalyst.

10 The invention also relates to a process for producing methyl mercaptan from synthesis gas and hydrogen sulfide using the catalyst according to the invention.

The invention also relates to the use of the catalyst as defined above for the synthesis of methyl mercaptan from synthesis gas and hydrogen sulfide.

15 Lastly the invention relates to the use of hydroxyapatite as support for preparing a catalyst for producing methyl mercaptan, and in particular in a catalytic process by reacting carbon oxide, sulfur and/or hydrogen sulfide and hydrogen.

20 Other characteristics, features, subjects and benefits of the present invention will emerge even more clearly on reading the description and the examples that follow.

25 Any range of values denoted by the expression "between a and b" represents the values ranging from more than a to less than b (i.e. limits a and b excluded), while any range of values denoted by the expression

“from a to b” means the values ranging from a to b (i.e. including the limits a and b).

Catalyst

The present invention relates to a catalyst.

5 This catalyst comprises a molybdenum- and potassium-based active component and a hydroxyapatite-based support.

Active component

10 The active component present in the catalyst according to the invention comprises molybdenum and potassium within a single component.

Preferably, the molybdenum- and potassium-based active component is chosen from compounds based on Mo-S-K, compounds based on Mo-O-K, and their mixtures.

15 The Mo-S-K based active component may be obtained by deposit and calcination of K_2MoS_4 or $(NH_4)_2 MoS_4$ precursors with impregnated K_2CO_3 added separately to the support.

The Mo-O-K based active component may be obtained by deposit and calcination of K_2MoO_4 or $(NH_4)_2 MoO_4$ precursors with impregnated K_2CO_3 added separately to the support.

20 it is also possible to use ammonium heptamolybdate $(NH_4)_6Mo_7O_{24}.4H_2O$ as reagent, in the presence of a potassium salt such as for instance potassium nitrate KNO_3 , potassium carbonate K_2CO_3 or potassium hydroxide KOH .



25 These compounds are precursors of Mo-S-K and Mo-O-K based active phases respectively. The active phases are obtained after *in situ* precursor pretreatment, with for example a procedure consisting in a first step of drying in nitrogen at 250°C, followed by sulfidation with hydrogen sulfide at the same temperature for 1 hour, then a step of reduction/sulfidation with H_2/H_2S at 350°C for 1 hour.

Support

30 The catalyst support according to the invention is hydroxyapatite having formula $Ca_{10}(PO_4)_6(OH)_2$, advantageously a stoichiometric hydroxyapatite.

Preferably, hydroxyapatite that is useful according to the present invention has a Ca/P molar ratio ranging from 1.5 to 2.1, and more preferably 1.67, corresponding to the expected value for stoichiometric hydroxyapatite.

5 Preferably, the weight ratio of the catalyst according to the invention is:



10 The catalytic activity may be improved by using a support material having a specific area greater than 25 m²/g.

Preferably, the hydroxyapatite supports according to the invention have a specific area of at least 40 m²/g, more specifically the specific area ranges from 40 m²/g to 300 m²/g and a Ca/P molar ratio of 1.67.

15 The structure of the support may be three dimensional, spherical, cylindrical, ring-shaped, star-shaped, granulates or any other three dimensional shape, or in the form of a powder, which can be pressed, extruded, granulated or in a three dimensional shape.

20 Preferably, the catalyst particles have uniform particle size distribution with diameter from 0.1 mm to 20.0 mm measured by sieve analysis.

Promoter

25 Preferably, the catalyst according to the invention consists in a molybdenum- and potassium-based active component and a hydroxyapatite-based support.

However, it is possible to envisage the presence of a promoter known to the person skilled in the art, such as tellurium oxide, nickel oxide or iron oxide.

Catalyst preparation process

30 The invention also relates to the preparation process for the catalyst according to the invention. This process comprises the following successive steps:

- preparing the precursor for the active phase
- preparing the support, and

- dry impregnating the support with the active phase precursor.

Preparing the precursor for the active phase

1/Mo-O-K

5 1. The K_2MoO_4 salt is a commercial salt. To prepare the Mo-O-K based-catalyst, a fixed quantity of K_2MoO_4 is dissolved in a volume of water to obtain a solution with desired concentration, such as for example a concentration ranging from 0.5-1.0 g/mL.

10 2. It is also possible to begin with separated molybdenum and potassium salts, i.e. that are not part of the same compound. For this synthesis, a molybdenum-based solution is prepared by adding ammonium heptamolybdate in water to obtain a MoO_3 concentration ranging from 22 to 33% by weight.

15 In parallel, a potassium-based solution is prepared by adding potassium nitrate in water to obtain a K_2O concentration ranging from 31 to 43 % by weight.

2/Mo-S-K

The K_2MoS_4 synthesis is generally done in two steps.

20 The first step involves preparing ammonium tetrathiomolybdate (ATTM); the second step is the synthesis of potassium tetrathiomolybdate (K_2MoS_4) from the salt prepared in the first step.

25 To prepare ATTM, hydrogen sulfide is left to bubble continuously in a 25% aqueous ammonia solution, in which ammonium heptamolybdate (HMA) has been dissolved. The solution temperature increases, indicating an exothermic reaction. The hydrogen sulfide bubbling is stopped when the temperature falls (generally after one hour).

The solution then contains red crystals with green reflections, which correspond to ammonium tetrathiomolybdate.

30 The second step consists in an ion exchange between ammonium ions in the ammonium tetrathiomolybdate salt obtained and potassium ions, which come from a potassium hydroxide solution. The salts obtained are then stored under vacuum. A quantity of potassium tetrathiomolybdate is dissolved in water.

The potassium salt useful in the catalyst according to the present invention may come from the following compounds: potassium acetate (KAc), potassium oxalate ($K_2C_2O_4$), potassium hydroxide (KOH), potassium carbonate (K_2CO_3), potassium nitrate (KNO_3), and potassium bicarbonate ($KHCO_3$).

Support preparation

The catalyst support, constituted of hydroxyapatite, is prepared by a coprecipitation method. An aqueous solution of calcium nitrate $Ca(NO_3)_2$ was added dropwise to an ammonium hydrogenphosphate $(NH_4)H_2PO_4$ solution with stirring. The temperature is held at $100^\circ C$ and the pH is held at 10 with addition of an ammonia solution (25%).

The resulting white precipitate is filtered, washed, dried at $80^\circ C$ overnight and calcinated at $400^\circ C$. The hydroxyapatite $Ca_{10}(PO_4)_6(OH)_2$ was obtained with a Ca/P molar ratio of 1.67 corresponding to the expected value for a stoichiometric hydroxyapatite.

Dry impregnating the support with the active phase precursor

1/Mo-O-K

The dry impregnation method is used to prepare the catalyst. The K_2MoO_4 solution is impregnated in one step on the support. When the solutions containing potassium and molybdenum are distinct, the impregnation is done in 2 steps.

2/Mo-S-K

A potassium tetrathiomolybdate solution is then impregnated onto hydroxyapatite. The molybdate content in the catalyst depends on the K_2MoS_4 or K_2MoO_4 solubility and the support's porous volume.

The K_2MoS_4 solubility is between 0.25 g/mL and 0.50 g/mL (0.35 g/mL) and the K_2MoO_4 solubility is between 0.50 g/mL and 1.50 g/mL (0.90 g/mL). The support's porous volume is between 0.8 mL/g and 2.2 mL/g.

Consequently, the volume of solution used is calculated to obtain the desired weight ratio, and preferably the weight ratio as defined above.

After impregnation, the solid undergoes a maturation step for 2 hours, then oven drying at 80 °C for 24 hours, and calcination under gas flow (typically air) at 490 °C for 4 hours. If a second impregnation step is necessary, the solid undergoes the maturation, drying and calcination steps again.

Production process for methyl mercaptan

The invention relates to a production process for methyl mercaptan in a catalytic process by reacting carbon oxide, sulfur and/or hydrogen sulfide and hydrogen, comprising the use of a catalyst as defined above.

The CO or CO₂/H₂S/H₂ molar ratios range from 1/1/0 to 1/8/8, or when sulfur is used to replace hydrogen sulfide, the molar ratios of CO or CO₂/H₂S/H₂/S reagents range from 1/1/0/1 to 1/8/8/8.

Preferably, the CO or CO₂/H₂S/H₂ molar ratios range from 1/2/1 to 1/4/4, when sulfur is used to replace hydrogen sulfide, the molar ratios of CO or CO₂/H₂S/H₂/S reagents from 1/2/2/1 to 1/4/4/4.

These molar ratios take CO₂ into account. Therefore, they consider both reaction scheme (1) and reaction scheme (6).

Preferably, the reaction may occur in fixed tubular, multitubular, catalytic wall micro-channel or fluid bed reactors.

The invention also relates to the use of the catalyst as defined above for the production of methyl mercaptan from synthesis gas and hydrogen sulfide.

Lastly the invention relates to the use of hydroxyapatite as support for preparing a catalyst for producing methyl mercaptan, and in particular in a catalytic process by reacting carbon oxide, sulfur and/or hydrogen sulfide and hydrogen.

The present invention will now be described in the examples below, these examples being given only for illustration, and are of course not limiting.

EXAMPLES

Example 1

The catalyst according to the invention is prepared according to the dry impregnation method, as defined above.

The resulting catalyst has the following characteristics:

Catalyst (% by weight)	Chemical composition			
	Mo	K	S	N
K ₂ MoS ₄ /Hap	9.9	8.1	13.3	<0.10

Table 1: Elemental analysis of the catalyst

Example 2: The catalyst used is K₂MoO₄ on hydroxyapatite

Example 3: The catalyst tested is K₂MoO₄ on SiO₂

Example 4: The catalyst tested is K₂MoS₄ on Al₂O₃

Example 5: The catalyst tested is K₂MoO₄ on Al₂O₃.

Evaluating the catalysts

The catalysts are evaluated in a reaction to produce methyl mercaptan in a fixed-bed reactor in the following conditions:

Temperature: 280°C,

Pressure: 10 bars,

Composition of CO/H₂/H₂S=1/2/1 feed gas (v/v),

GHSV (Gas Hourly Space Velocity)= 1333 h⁻¹

The reagents and products were analyzed in-line by gas chromatography.

Before the test, the catalysts were activated *in situ* with a first procedure consisting in a first step of drying in nitrogen at 250°C, followed by sulfidation with hydrogen sulfide at the same temperature

for 1 hour, then a step of reduction/sulfidation with H_2/H_2S at $350^\circ C$ for 1 hour.

The results are in table 2 below.

5

Examples	Catalyst	Molar selectivities (%)			CO_2/CH_3SH ratio
		CH_3SH	COS	CO_2	
1 (inv)	K_2MoS_4/Hap	44.1	23.3	32.6	0.74
2 (inv)	K_2MoO_4/Hap	43.3	23.6	31.9	0.74
3 (comp)	K_2MoO_4/SiO_2	48.8	5.3	45.3	0.93
4 (comp)	K_2MoS_4/Al_2O_3	45.0	7.3	46.6	1.04
5 (comp)	K_2MoO_4/Al_2O_3	47.0	3.4	49.6	1.06

TABLE 2: Results of catalytic tests

The results presented in table 2 show that the catalysts according to the invention (examples 1 and 2) give much lower CO_2 (undesired product) selectivities than catalysts on the supports in the prior art (silica: example 3 or alumina: examples 4 and 5).

10

The selectivities are compared using carbon monoxide isoconversion, where this conversion is expressed by m^2 of specific air in the catalyst.

15

By comparing the results obtained with catalysts 1 and 4, we observe a 30% improvement in ratio, and this improvement is linked to choosing hydroxyapatite as support.

The same observation is seen when comparing example 2 according to the invention and examples 3 and 5.

20

We observe increased methyl mercaptan selectivity compared to the carbon dioxide produced according to a side reaction.

It should be noted that this selectivity is obtained without aid from the promoter such as tellurium oxide, nickel oxide or iron oxide as described in the prior art.

CLAIMS

1. A catalyst comprising a molybdenum- and potassium-based active component, chosen from compounds based on Mo-S-K, compounds based on Mo-O-K, and their mixtures, and a hydroxyapatite-based support.

2. The catalyst as claimed in claim 1, characterized in that the catalyst support is hydroxyapatite having stoichiometric formula $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$.

3. The catalyst as claimed in claim 1 or 2, characterized in that the precursor for the Mo-S-K based active component has structure K_2MoS_4 .

4. The catalyst as claimed in claim 3, characterized in that the weight ratio for the catalyst according to the invention is

$$\text{K}_2\text{MoS}_4/\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2 = 31.3/100$$

5. The catalyst as claimed in claim 1 or 2, characterized in that the precursor for the Mo-O-K based active component has structure K_2MoO_4 .

6. The catalyst as claimed in claim 5, characterized in that the weight ratio for the catalyst according to the invention is:

$$\text{K}_2\text{MoO}_4/\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2 = 50.7/100$$

7. A preparation process for the catalyst as defined in any of claims 1 to 6, characterized in that it comprises the following steps:

- preparing the precursor for the active phase
- preparing the support, and
- dry impregnating the support with the active phase precursor.

8. A production process for methyl mercaptan in a catalytic process by reacting carbon oxide, sulfur and/or hydrogen sulfide and hydrogen, comprising the use of a catalyst as defined in any of claims 1 to 6.