## Description

The present invention relates generally to thermal ink jet printhead construction and concerns to a process for fabricating a thin film resistor printhead structure as well as a thin film resistor printhead and interconnect structure produced thereby in accordance with the precharacterizing parts of the independent claims 1 and 4.

Such a process and a thin film resistor printhead are known by US-A-4 463 359.

### Background Art

In the manufacture of thin film resistor (TFR) type of thermal ink jet printheads, it is a common practice to photolithographically define the individual heater resistors on a TFR substrate by creating a pattern in an overlying conducting trace layer. This layer is deposited in a predetermined pattern on the resistive heater material using known deposition techniques. The resistive heater layer material may, for example, be tantalum-aluminum, TaAl. The conductive trace pattern is most typically aluminium, although it could also be gold or other conductive material compatible with the other materials in the materials set for the printhead. After the conductive trace material or pattern is completed, it is then usually covered with an inert barrier layer such as a composite layer of silicon nitride and silicon carbide in order to protect the underlying layers from cavitation wear and ink corrosion.

In order to make electrical contact between this conductive trace material and external pulse drive circuitry for the printhead, the prior art approach according to US-A-4463359 involved etching a relatively large opening or via in the silicon nitride/silicon carbide composite barrier layer and then forming a relatively large contact pad in this opening to thus make contact with the underlying aluminum trace conductor material. Then, wire bonding or pressure contact connections could be made to this relatively large contact pad to provide an electrical current path into the aluminum trace material and to the ink jet heater resistors.

The above prior art structure is possessed with several disadvantages associated with the relatively large opening or via in the insulating barrier layer and directly over the aluminum conductive trace layer. The first of these disadvantages resides in the fact that the large via in the silicon nitride/silicon carbide composite layer exposes a relatively large sidewall area of these materials. This large area sidewall exposure means increasing the area in which pinholes or cracks might possibly occur and thus produce electrical shorts in the barrier layer. As a result of the dissimilarity of the silicon nitride and silicon carbide layers and the differences in their etch rates, there is produced a "diving board" geometry at the edge of these two dissimiliar insulating materials at the via opening. This stepped geometry, when coupled with the large area deposited contact pad in the via, increases the probability of material defects in this region which are capable of reducing wafer processing yields.

Another disadvantage of the above prior art electrical interconnect approach involves exposing a relatively large area of the aluminum trace material in order to provide the desired wide area contact pad thereover. The exposure of such a large area of aluminum trace material in the manufacturing process increases the possibility of forming aluminum oxide, $Al_2O_3$, on the conductive trace material and thus rendering it insulating or partially insulating instead of fully conducting.

Another disadvantage of using the above prior art approach resides in the increased probability of undercutting the silicon nitride and silicon carbide layers during the etching of the via therein. Again, such increased probability is caused by the exposure of the relatively wide area sidewall of the silicon nitride/silicon carbide barrier defining the via.

Another disadvantage of using the prior art approach described above relates to the formation of a non-flat dish-shaped contact pad directly over the aluminum trace material. This geometry and structure increases the likelihood of scratching the edge of the printhead structure immediately adjacent the conducting trace material, and such scratching in turn increases the likelihood of producing electrical shorts down through the printhead structure to the aluminum conductive trace material. In addition, the dish shape or non-planar contour of the contact pad makes it difficult to make certain types of electrical connections to the printhead structure, e.g. spring biased pressure connections from a lead frame-type of flexible circuit.

A further disadvantage of using the above prior approach relates to the sensitivity of chipping and cracking at the edges of the multiple layers of materials over which the dish-shaped contact is placed. This chipping and cracking will cause corrosion of these materials at their outer edges, but this does not occur in devices manufactured by the present invention where the lead-in contacts have been removed from pressure contact at the edges of these interior layered materials.

### Disclosure of Invention

The general purpose of this invention is to provide a new and improved integrated circuit in-

terconnect structure for providing drive current to thermal ink jet printhead heater resistors and a high yield process for fabricating same. This interconnect structure is uniquely adapted and constructed for making good electrical connections to spring biased pressure contacts, such as individual fingers or leads on a lead frame type of flexible or "flex" circuit.

The above object is solved by the features characterized in the independent claims 1 and 4.

Claims 2 and 3 depending on claim 1 characterize advantageous developments of the process defined in claim 1. Claims 5 and 6 depending on claim 4 characterize advantageous developments of the thin film resistor print head and interconnect structure defined in claim 4.

The interconnect metal in this latter area provides a relatively large and flat electrical contact area for spring biased contacts. Thereby the electrical connection to the conductive trace pattern is only through the relatively small via in the barrier layer where the area of edge exposure in the barrier layer and the area of conductive trace material exposure is maintained at a minimum.

The above and other advantages, novel features and alternative methods of construction of this invention will become better understood in the following description of the accompanying drawings.

## Brief Description of Drawings

Figures 1 through 7 illustrate, in schematic cross section, a series of thin film resistor process steps utilized in fabricating a printhead interconnect structure according to the invention.

Figure 8 is an alternative embodiment of the invention wherein the barrier layers have been laterally reduced to expose an edge portion of the underlying aluminum trace material for subsequent metal overlay thereon.

## Best Mode For Carrying Out The Invention

Referring now to Figure 1, a substrate starting material 10 such as silicon is treated using either thermal oxidation or vapor deposition techniques to form a thin layer 12 of silicon dioxide thereon. The combination of the silicon substrate 10 and the layer 12 of silicon dioxide will be referred to herein as the "insulating substrate" upon which a subsequent layer 14 of resisitive heater material is deposited. Preferably, the layer 14 will be tantalum aluminum, TaAl, which is a well known resistive heater material in the art of thermal ink jet printhead construction. Next, a thin layer 16 of aluminum is deposited atop the tantalum aluminum layer 14 to complete the structure of Figure 1.

In the particular materials set described above for a preferred embodiment of the invention, the silicon-silicon dioxide combination 10, 12 was approximately 600 microns in thickness; the tantalum aluminum layer 14 was approximately 1000 angstroms in thickness; and the aluminum conductive trace material 16 was approximately 5000 angstroms in thickness. The resistor and conductor materials were magetron sputter deposited. This materials set is generally well known in the art and is described, for example, in the Hewlett-Packard Journal, Vol. 36, No. 5, May, 1985, incorporated herein by reference.

Referring now to Figure 2, the structure shown therein was appropriately masked and etched with a suitable etchant in order to define the composite island 18 of tantalum aluminum 14 and aluminum 16 on the right hand side of the insulating substrate. As will become better appreciated below, the island 18 is formed on only a portion of the insulating substrate 10 and 12, leaving an area of the left hand side of the substrate available for making good electrical contacts of the type to be described. Next, as shown in Figure 3, a pattern is etched in the aluminum layer 16 to form the opening 20 which defines the lateral extent of a resistive heater element 22 which is current driven by the conductive trace aluminum layer 16.

Next, as shown in Figure 4, a composite layer barrier material is deposited over the upper surface of the structure in this figure and includes a first layer 24 of silicon nitride which is covered by a second layer of highly inert silicon carbide. This composite layer (24, 26) barrier material provides both good adherance to the underlying materials and good insulation and protection against cavation wear and ink corrosion which the underlying layers beneath these materials 24 and 26 would otherwise receive during an ink jet printing operation.

Next, as shown Figure 5, a relatively small via 28 is dry etched in the composite silicon nitride/silicon carbide barrier layer using freon gas to thereby leave a small area 30 in the aluminum conductive trace material exposed for further electrical contact. Such contact is made as shown in Figure 6 when a conductive lead-in or overlay pattern of conductors 32 and 34 are magnetron sputter deposited on the surface of Figure 5 and extend from into electrical contact with a relatively small area 30 of conductor trace material and then out onto the left hand side of the structure in Figure 5 and atop the previously deposited barrier layer material. The combined thickness of the gold and tantalum layers is approximately 2 microns.

This conductive lead-in composite structure includes a first layer 32 of tantalum and a second layer 34 of gold successively deposited in the geometrical configuration shown using conventional

masking and metal evaporation techniques. Thus, the area 36 on the upper surface of the gold layer 34 in Figure 6 extends over a relatively wide and flat area of the integrated structure and is located away from the aluminium conductive trace pattern previously described. This construction therefore enables a finger or spring lead contact member 38, which may be part of a larger lead frame member (not shown), to be brought into good firm pressure contact with the surface area 36 of the gold layer 34 and without causing any detrimental effect on the aluminum conductive trace pattern. This larger lead frame member is described in more detail in copending application of Janet E. Mebane et al Serial No. (ID 186201) and assigned to the present assignee.

Finally, and of course prior to the application of the spring biased contact 38, a surface pattern of polymer material 40 is formed in the geometry own in Figure 7 to a thickness of approximately 50 microns. This polymer material provides a protective layer or shield over the contact via 30 and over the electrical contact layers 32 and 34 extending down into contact therewith.

It will be understood that, for sake of brevity, only a single heater resistor and conductive trace connection therefor has been shown. However, in actual practice the printhead will have many of these heater resistors which will usually be symmetrically spaced in a rectangular pattern on one area of the insulating substrate.

Various modifications may be made in the above described embodiment without departing from the scope of this invention. For example, in Figure 4, it may be preferable in certain applications to deposit layers 24 and 26 on only a predetermined area of the underlying aluminum trace material 20. Then, the tantalum and gold layers 32 d 34 would be deposited over an area of edge exposed aluminum trace material and down and out over the now-exposed silicon dioxide layer 12 on the left hand side of the device structure. Thus, in this modified embodiment as shown in Figure 8, the tantalum-gold composite layer 32', 34' on the now-exposed left hand SiO2 layer 12 will serve as the electrical contact area for receiving the above spring biased leads or the like. The $Si_3N_4$/Si C composite layer 24', 26' is masked and etched so as to leave a small edge portion of the aluminium trace material 16' exposed to receive the tantalum layer 32' thereon as shown in Figure 8. And, as in Figure 7, there is a relatively wide area on the surface of the gold film 34' for recieving the spring biased lead contact 38'.

## Industrial Applicability

The present invention is used in the fabrication of printheads for thermal ink jet printers which serve as standard peripheral equipment for a variety of computers and the like.

## Claims

1. A process for fabricating a thin film resistor printhead structure which includes:
   a. forming a resistive layer on an insulating substrate and a conductive trace pattern laterally coextensive therewith and having an opening therein defining a resistive heater element, and
   b. forming an insulating barrier layer atop said conductive trace pattern and exposing a predetermined area of said conductive trace pattern, characterized by
   c. forming a metal overlay pattern extending from said conductive trace pattern and down over and on an adjacent area of said insulating substrate under which no conductive trace pattern appears, whereby the metal over said adjacent area of said insulating substrate provides a relatively large and flat electrical contact area remote from said conductive trace pattern for spring biased contacts and the like.

2. The process defined in claim 1 wherein a small via is etched in the barrier layer for receiving said metal overlay pattern in electrical contact with said conductive trace pattern.

3. The process defined in claim 1 which includes forming said insulating barrier layer of smaller lateral dimension than said conductive trace pattern to thereby leave an edge of said conductive trace pattern exposed to receive said metal overlay pattern in electrical contact therewith.

4. A thin film resistor printhead and interconnect structure including, in combination:
   a. a resistive layer and a conductive trace pattern formed laterally coextensive on a predetermined area of an insulating substrate, and said conductive trace pattern having an opening therein defining a resistive heater element, and
   b. an insulating barrier layer formed atop said conductive trace material and exposing a predetermined area of said conductive trace pattern, characterized by
   c. a metal overlay pattern extending from said conductive trace pattern and down over and on an adjacent area of said insulating substrate under which no conductive trace

masking and metal evaporation techniques. Thus, the area 36 on the upper surface of the gold layer 34 in Figure 6 extends over a relatively wide and flat area of the integrated structure and is located away from the aluminium conductive trace pattern previously described. This construction therefore enables a finger or spring lead contact member 38, which may be part of a larger lead frame member (not shown), to be brought into good firm pressure contact with the surface area 36 of the gold layer 34 and without causing any detrimental effect on the aluminum conductive trace pattern. This larger lead frame member is described in more detail in copending application of Janet E. Mebane et al Serial No. (ID 186201) and assigned to the present assignee.

Finally, and of course prior to the application of the spring biased contact 38, a surface pattern of polymer material 40 is formed in the geometry own in Figure 7 to a thickness of approximately 50 microns. This polymer material provides a protective layer or shield over the contact via 30 and over the electrical contact layers 32 and 34 extending down into contact therewith.

It will be understood that, for sake of brevity, only a single heater resistor and conductive trace connection therefor has been shown. However, in actual practice the printhead will have many of these heater resistors which will usually be symmetrically spaced in a rectangular pattern on one area of the insulating substrate.

Various modifications may be made in the above described embodiment without departing from the scope of this invention. For example, in Figure 4, it may be preferable in certain applications to deposit layers 24 and 26 on only a predetermined area of the underlying aluminum trace material 20. Then, the tantalum and gold layers 32 d 34 would be deposited over an area of edge exposed aluminum trace material and down and out over the now-exposed silicon dioxide layer 12 on the left hand side of the device structure. Thus, in this modified embodiment as shown in Figure 8, the tantalum-gold composite layer 32', 34' on the now-exposed left hand SiO2 layer 12 will serve as the electrical contact area for receiving the above spring biased leads or the like. The $Si_3N_4$/Si C composite layer 24', 26' is masked and etched so as to leave a small edge portion of the aluminium trace material 16' exposed to receive the tantalum layer 32' thereon as shown in Figure 8. And, as in Figure 7, there is a relatively wide area on the surface of the gold film 34' for recieving the spring biased lead contact 38'.

## Industrial Applicability

The present invention is used in the fabrication of printheads for thermal ink jet printers which serve as standard peripheral equipment for a variety of computers and the like.

## Claims

1. A process for fabricating a thin film resistor printhead structure which includes:
   a. forming a resistive layer on an insulating substrate and a conductive trace pattern laterally coextensive therewith and having an opening therein defining a resistive heater element, and
   b. forming an insulating barrier layer atop said conductive trace pattern and exposing a predetermined area of said conductive trace pattern, characterized by
   c. forming a metal overlay pattern extending from said conductive trace pattern and down over and on an adjacent area of said insulating substrate under which no conductive trace pattern appears, whereby the metal over said adjacent area of said insulating substrate provides a relatively large and flat electrical contact area remote from said conductive trace pattern for spring biased contacts and the like.

2. The process defined in claim 1 wherein a small via is etched in the barrier layer for receiving said metal overlay pattern in electrical contact with said conductive trace pattern.

3. The process defined in claim 1 which includes forming said insulating barrier layer of smaller lateral dimension than said conductive trace pattern to thereby leave an edge of said conductive trace pattern exposed to receive said metal overlay pattern in electrical contact therewith.

4. A thin film resistor printhead and interconnect structure including, in combination:
   a. a resistive layer and a conductive trace pattern formed laterally coextensive on a predetermined area of an insulating substrate, and said conductive trace pattern having an opening therein defining a resistive heater element, and
   b. an insulating barrier layer formed atop said conductive trace material and exposing a predetermined area of said conductive trace pattern, characterized by
   c. a metal overlay pattern extending from said conductive trace pattern and down over and on an adjacent area of said insulating substrate under which no conductive trace

* C L M S *

pattern appears, whereby the metal over said adjacent area of said insulating substrate provides a relatively large and flat electrical contact area for receiving spring biased contacts and the like.

5. The structure defined in claim 4 wherein a small via is made in said insulating barrier layer to expose said conductive trace pattern for connection to said metal overlay pattern.

6. The structure defined in claim 4 wherein said insulating barrier layer is formed of smaller lateral dimension than said conductive trace pattern to thereby leave an edge area of said conductive trace pattern exposed to receive said metal overlay pattern in electrical contact therewith.

**Patentansprüche**

1. Verfahren zur Herstellung eines Dünnfilmwiderstands-Druckkopfs, das aufweist:
   a) Ausbildung einer Widerstandsschicht auf einem isolierenden Substrat sowie eines leitenden Linienmusters mit einer seitlichen Ausdehnung wie die der Widerstandsschicht, wobei in dem leitenden Linienmuster eine ein Widerstandsheizelement bildende Öffnung ausgebildet ist, und
   b) Ausbildung einer isolierenden Sperrschicht über dem leitenden Linienmuster und Freilegen eines vorgegebenen Bereichs des leitenden Linienmusters,
   gekennzeichnet durch
   c) Ausbilden eines metallischen Überzugsmusters, das sich von dem leitenden Linienmuster nach unten über und auf einen angrenzenden Bereich des isolierenden Substrats unter dem kein leitendes Linienmuster vorhanden ist, erstreckt, wodurch das Metall über dem angrenzenden Bereich des isolierenden Substrats eine verhältnismäßig große und flache elektrische Kontaktzone abgesetzt vom leitenden Linienmuster für federbelastete Kontakte und dergleichen bildet.

2. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß ein kleiner Durchbruch in die Sperrschicht geätzt wird, in dessen Innerem das metallische Überzugsmuster in elektrischem Kontakt mit dem leitenden Linienmuster steht.

3. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß es die Ausbildung einer isolierenden Sperrschicht enthält, deren Seitenabmessung geringer ist als die des leitenden Linienmusters, um dadurch eine Kante des leitenden Linienmusters freizulassen, um einen elektrischen Kontakt mit dem metallischen Überzugsmuster herzustellen.

4. Dünnfilmwiderstands-Druckkopf und Verbindungsstruktur, die in Kombination aufweisen:
   a) eine Widerstandsschicht und ein leitendes Linienmuster, die mit derselben seitlichen Ausdehnung auf einem vorgegebenen Bereich eines isolierenden Substrats ausgebildet sind, wobei das leitende Linienmuster eine Öffnung hat, die ein Widerstandsheitselement definiert, und
   b) eine isolierende Sperrschicht, die das leitende Linienmuster überdeckt und einen vorgegebenen Bereich des leitenden Linienmusters freiläßt, gekennzeichnet durch
   c) eine metallische Überzugsschicht, die sich von dem leitenden Linienmuster nach unten über und auf einem angrenzenden Bereich des isolierenden Substrats erstreckt, unter dem kein leitendes Linienmuster vorhanden ist, wodurch das Metall über dem angrenzenden Bereich des isolierenden Substrats eine verhältnismäßig große und flache elektrische Kontaktzone zur Aufnahme federbelasteter Kontakte und dergleichen bildet.

5. Dünnfilmwiderstands-Druckkopf nach Anspruch 4, dadurch gekennzeichnet, daß die isolierende Sperrschicht einen kleinen Durchbruch aufweist, welcher das leitende Linienmuster für die Verbindung mit dem metallischen Überzugsmuster freilegt.

6. Dünnfilmwiderstands-Druckkopf nach Anspruch 4, dadurch gekennzeichnet, daß die isolierende Sperrschicht eine geringere Seitenabmessung als das leitende Linienmuster aufweist, wodurch ein Kantenbereich des leitenden Linienmusters frei bleibt, um elektrischen Kontakt mit dem metallischen Überzugsmuster herzustellen.

**Revendications**

1. Un procédé de fabrication d'une structure de tête d'imprimante de résistances en pellicule mince qui comprend les étapes consistant à :
   a. former sur un substrat isolant une couche résistante et une configuration de trace conductrice, dont les limites latérales prolongent celles de cette couche et dans laquelle est ménagée une ouverture qui définit un élément chauffant résistant, et
   b. former une couche de barrière isolante

* C L M S *

au-dessus de ladite configuration de trace conductrice et exposer une surface prédéterminée de ladite configuration de trace conductrice, caractérisé par

c. la formation d'une couche métallique de revêtement qui s'étend à partir de ladite configuration de trace conductrice et se prolonge, vers le bas en revêtant le flanc de celle-ci, puis en venant recouvrir une surface adjacente dudit substrat isolant au-dessous de laquelle il ne se trouve aucune configuration de trace conductrice, grâce à quoi le métal situé au-dessus de ladite zone adjacente dudit substrat isolant constitue, à distance de ladite configuration de trace conductrice, une surface de contact électrique relativement grande et plate prévue pour des contacts sollicités élastiquement et similaires.

2. Le procédé selon la revendication 1 dans lequel un petit trou métallisé est gravé dans la couche de barrière pour recevoir ladite configuration métallique de revêtement en contact électrique avec ladite configuration de trace conductrice.

3. Le procédé selon la revendication 1 qui comprend l'étape consistant à former ladite couche de barrière isolante d'une dimension latérale plus petite que ladite configuration de trace conductrice pour laisser ainsi exposé un bord de ladite configuration de trace conductrice afin de recevoir ladite configuration métallique de revêtement en contact électrique avec celle-ci.

4. Une structure de tête d'impression et d'interconnexion de résistances en pellicule mince comprenant, en combinaison :

a. sur une zone prédéterminée d'un substrat isolant: une couche résistante et une configuration de trace conductrice dont les limites latérales prolongent celles de cette couche, une ouverture qui définit un élément chauffant résistant étant ménagée dans ladite configuration de trace conductrice, et

b. une couche de barrière isolante formée au-dessus de ladite matière de trace conductrice exposant une zone prédéterminée de ladite configuration de trace conductrice, caractérisée en ce que :

c. une configuration métallique de revêtement qui s'étend à partir de ladite configuration de trace conductrice et se prolonge, vers le bas en revêtant le flanc de celle-ci, puis en venant recouvrir une surface adjacente dudit substrat isolant au-dessous de laquelle il ne se trouve aucune configuration de trace conductrice, grâce à quoi le métal situé au-dessus de ladite zone adjacente dudit substrat isolant constitue une surface de contact électrique relativement grande et plate prévue pour des contacts sollicités élastiquement et similaires.

5. La structure selon la revendication 4 dans laquelle un petit trou métallisé est ménagé dans ladite couche de barrière isolante afin d'exposer ladite configuration de trace conductrice en vue d'une connexion avec ladite configuration métallique de revêtement.

6. La structure selon la revendication 4 dans laquelle ladite couche de barrière isolante est formée d'une dimension latérale plus petite que ladite configuration de trace conductrice pour laisser ainsi exposée une zone de bord de ladite configuration de trace conductrice afin de recevoir ladite configuration métallique de revêtement en contact électrique avec elle.