

Abstract

FILM

There is provided a film wherein, an outer layer includes a polypropylene resin, an intermediate layer includes a polypropylene resin and a hydrogenated block copolymer (a), and an inner layer includes a polypropylene resin,

the hydrogenated block copolymer (a) includes

a polymer block mainly comprising a conjugated diene compound (C),

a polymer block mainly comprising a conjugated diene compound (B), and

a polymer block mainly comprising a vinyl aromatic compound (S),

a content of the polymer block (C) is 1 to 30% by mass, a content of the polymer block (B) is 69 to 98% by mass, and a content of the polymer block (S) is 1 to 20% by mass in the hydrogenated block copolymer (a),

the polymer block (C) has a vinyl bond content before hydrogenation of 1 to 25 mol%, the polymer block (B) has a vinyl bond content before hydrogenation of 60 to 100 mol%, and the hydrogenated block copolymer (a) has a degree of hydrogenation of 80 mol% or more. The film has excellent transparency and flexibility and an excellent balance between the properties.