
CLAIMS

What is claimed is

1. A polymerization process comprising contacting a cyclic olefin monomer and optional comonomer selected from C_2 to C_{20} alpha olefins with a catalyst system comprising activator and catalyst compound represented by the Formula (**I**):



(**I**)

wherein:

M is a group 3, 4, 5, or 6 transition metal or a Lanthanide;

E and E' are each independently O, S, or NR^9 where R^9 is independently hydrogen, a C_1-C_{40} hydrocarbyl, a C_1-C_{40} substituted hydrocarbyl or a heteroatom-containing group;

Q is group 14, 15, or 16 atom that forms a dative bond to metal M;

$A^1QA^{1'}$ are part of a heterocyclic Lewis base containing 4 to 40 non-hydrogen atoms that links A^2 to $A^{2'}$ via a 3-atom bridge with Q being the central atom of the 3-atom bridge, A^1 and $A^{1'}$ are independently C, N, or C(R^{22}), where R^{22} is selected from hydrogen, C_1-C_{20} hydrocarbyl, C_1-C_{20} substituted hydrocarbyl;

A^3----A^2 is a divalent group containing 2 to 40 non-hydrogen atoms that links A^1 to the E-bonded aryl group via a 2-atom bridge;

$A^{2'}$---$A^{3'}$ is a divalent group containing 2 to 40 non-hydrogen atoms that links $A^{1'}$ to the E'-bonded aryl group via a 2-atom bridge;

L is a Lewis base;

X is an anionic ligand;

n is 1, 2 or 3;

m is 0, 1, or 2;

n+m is not greater than 4;

each of R^1, R^2, R^3, R^4, $R^{1'}$, $R^{2'}$, $R^{3'}$, and $R^{4'}$ is independently hydrogen, a C_1-C_{40} hydrocarbyl, a C_1-C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group,

and one or more of R^1 and R^2, R^2 and R^3, R^3 and R^4, $R^{1'}$ and $R^{2'}$, $R^{2'}$ and $R^{3'}$, $R^{3'}$ and $R^{4'}$ may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl


rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings;

any two L groups may be joined together to form a bidentate Lewis base;

an X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group.

2. The process of claim 1 where the catalyst compound represented by the Formula (**II**):



(**II**)

wherein:

M is a group 3, 4, 5, or 6 transition metal or a Lanthanide;

E and E' are each independently O, S, or NR^9, where R^9 is independently hydrogen, a C_1-C_{40} hydrocarbyl, a C_1-C_{40} substituted hydrocarbyl, or a heteroatom-containing group;

each L is independently a Lewis base;

each X is independently an anionic ligand;

n is 1, 2 or 3;

m is 0, 1, or 2;

n+m is not greater than 4;

each of R^1, R^2, R^3, R^4, $R^{1'}$, $R^{2'}$, $R^{3'}$, and $R^{4'}$ is independently hydrogen, C_1-C_{40} hydrocarbyl, C_1-C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R^1 and R^2, R^2 and R^3, R^3 and R^4, $R^{1'}$ and $R^{2'}$, $R^{2'}$ and $R^{3'}$, $R^{3'}$ and $R^{4'}$ may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings; any two L groups may be joined together to form a bidentate Lewis base;

an X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group;

each of R^5, R^6, R^7, R^8, $R^{5'}$, $R^{6'}$, $R^{7'}$, $R^{8'}$, R^{10}, R^{11}, and R^{12} is independently hydrogen, a C_1-C_{40} hydrocarbyl, a C_1-C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing

group, or one or more of R^5 and R^6, R^6 and R^7, R^7 and R^8, $R^{5'}$ and $R^{6'}$, $R^{6'}$ and $R^{7'}$, $R^{7'}$ and $R^{8'}$, R^{10} and R^{11}, or R^{11} and R^{12} may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings.

3. The process of claim 1 or 2 wherein the M is Hf, Zr or Ti, wherein E and E' are each O, wherein R^1 and $R^{1'}$ is independently a C_4-C_{40} tertiary, cyclic tertiary, or polycyclic tertiary hydrocarbyl group.


4. The process any of claims 1 to 3 wherein each X is, independently, selected from the group consisting of substituted or unsubstituted hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halides, and a combination thereof, (two X's may form a part of a fused ring or a ring system), and wherein each L is, independently, selected from the group consisting of: ethers, thioethers, amines, phosphines, ethyl ether, tetrahydrofuran, dimethylsulfide, triethylamine, pyridine, alkenes, alkynes, allenes, and carbenes and combinations thereof, optionally two or more L's may form a part of a fused ring or a ring system).

5. The process of claim 1, wherein M is Zr or Hf, Q is nitrogen, both A^1 and $A^{1'}$ are carbon, both E and E' are oxygen, and both R^1 and $R^{1'}$ are C_4-C_{20} cyclic tertiary alkyls, adamantan-1-yl or substituted adamantan-1-yl.

6. The process of claim 1, wherein M is Zr or Hf, Q is nitrogen, both A^1 and $A^{1'}$ are carbon, both E and E' are oxygen, and X is methyl or chloro, and n is 2 or wherein Q is nitrogen, A^1 and $A^{1'}$ are both carbon, both R^1 and $R^{1'}$ are hydrogen, both E and E' are NR^9, where R^9 is selected from a C_1-C_{40} hydrocarbyl, a C_1-C_{40} substituted hydrocarbyl, or a heteroatom-containing group.


7. The process of claim 1, wherein Q is carbon, A^1 and $A^{1'}$ are both nitrogen, and both E and E' are oxygen or wherein Q is carbon, A^1 is nitrogen, $A^{1'}$ is $C(R^{22})$, and both E and E' are oxygen, where R^{22} is selected from hydrogen, C_1-C_{20} hydrocarbyl, C_1-C_{20} substituted hydrocarbyl.

8. The process of claim 1, wherein the heterocyclic Lewis base is selected from the groups represented by the following formulas:




where each R^{23} is independently selected from hydrogen, C_1-C_{20} alkyls, and C_1-C_{20} substituted alkyls.


9. The process of claim 1 wherein the catalyst compound is represented by one or more of the following formulas:




Complex 1




Complex 2




Complex 3




Complex 4




Complex 5




Complex 6




Complex 7




Complex 8




Complex 9




Complex 10




Complex 11




Complex 12




Complex 13




Complex 14




Complex 15




Complex 16




Complex 17




Complex 18




Complex 19




Complex 20




Complex 21




Complex 22




Complex 23




Complex 24




Complex 25




Complex 26




Complex 27




Complex 29




Complex 30




Complex 31




Complex 32




Complex 33




Complex 34




Complex 35




Complex 36




Complex 37




Complex 38




Complex 39




Complex 40




Complex 41




Complex 42




Complex 43




Complex 44




Complex 45




Complex 46




Complex 47




Complex 48




Complex 49




Complex 50




Complex 51




Complex 52




Complex 53




Complex 54




Complex 56




Complex 57




Complex 58




Complex 59




Complex 60




Complex 62




Complex 63



Complex 64






Complex 65











Complex 66

5

10. The process of claim 1 wherein the catalyst compound is one or more of










 Complex 1	 Complex 2	 Complex 3



















 Complex 4	 Complex 5	 Complex 6
 Complex 33	 Complex 48	 Complex 49
 Complex 65	 Complex 66	

11. The process of any of claims 1 to 10, wherein the activator is represented by the formula:

$$(Z)_d^+ (A^{d-})$$

wherein A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3 and $(Z)_d^+$ is represented by one or more of:

10		**11**		**12**	
13		**14**		**15**	
16		**17**		**18**	

19		**20**		**21**	
22		**23**		**24**	
25		**26**		**27**	
29		**28**		**30**	
31		**32**		**33**	
34		**35**		**36**	

12. The process of any of claims 1 to 3, further comprising recovering a polymer, wherein the polymer comprises at least 0.1 mol% cyclic olefin.

13. The process of any of claims 1 to 3, further comprising recovering a polymer, wherein the polymer comprises at least 1 mol% cyclic olefin and at least 20 mol% ethylene or at least 20 mol% propylene.

14. A polymer produced by the process of any of claims 1 to 3 comprising one or more cyclic olefin monomers selected from substituted or unsubstituted cyclopentene and substituted or unsubstituted 2-norbornene.