

COMPOSITIONS AND METHODS FOR REMOVING ORGANIC SUBSTANCES

Cross-Reference to Related Applications

- 5 This application claims priority to U.S. Provisional Application Serial No. 61/164,195 filed March 27, 2009 the disclosure of which is incorporated herein by reference in its entirety.

Field of the Invention

- 10 The present invention relates generally to the removal of organic substances from a substrate. In particular, the present invention relates to a universal method with a range of compositions, which applies to the removal of both amorphous and thermoset polymers from electronic devices such as semiconductor wafers and flat panel displays (FPD), and other microelectronic substrates.

15

Background

- Various polymers are used in the manufacture of electronic devices, to include photoresists and organic-based dielectrics. Photoresists, for example, are used throughout semiconductor device fabrication in photolithographic operations. The resist is exposed to actinic radiation through a photomask. Where a positive-acting resist is used, exposure causes a chemical reaction within the material resulting in a solubility increase in aqueous alkali, allowing it to be dissolved and rinsed away with developer. In the case of a negative-acting material, crosslinking of the polymer occurs in the exposed regions while leaving unexposed regions unchanged. The unexposed regions are subject to dissolution and rinsing by a suitable developer chemistry. Following development, a resist mask is left behind. The design and geometry of the resist mask is dependent upon the positive or negative tone of the resist; positive tone resist will match the design of the photomask, while a negative tone resist will provide a pattern that is opposite the photomask design. The use of photoresists requires several cleaning steps with a final clean of the mask before the next circuit design process step is implemented.
- 20
- 25
- 30

Organic-based dielectrics represent engineering polymers used to offer insulative properties to the microelectronic circuit. Examples of these chemistries include polyimide (PI) and poly-(p-phenylene-2, 6-benzobisoxazole) (PBO) as manufactured by Hitachi-DuPont Microsystems. Another popular organic insulator for electronic applications is bisbenzocyclobutene (BCB), manufactured by the USA-based, Dow Chemical Company. These polymers are applied to the substrate in a similar fashion as photoresists using conventional spin, spray, or they may be slit-coated as is common practice in manufacturing FPDs. For these application reasons, organic-based dielectrics may often be referred to as spin-on dielectrics. Once the polymer is applied, they may undergo a patterning process, but ultimately all of these systems lead to a final-stage cure, which permanently fixes the material in place by undergoing chemical and physical property changes. The final material exhibits both electrical and physical properties desirable for performance of the electric circuit. Once these organic-based dielectrics are fully cured, they are considered to be permanent, whereby, the need for rework would either require the use of aggressive materials such as strong acids or bases that likely would attack the substrate or adjacent metals or more practically, the rework condition would be considered as not commercially available.

Positive photoresists are commonly based upon resins of the novolac or polyhydroxystyrene (Phost) varieties chosen for high-resolution device processing in front-end semiconductor and flat panel display manufacturing. Positive-tone systems represent the largest volume portion of photoresists produced globally and there are many suppliers. Example suppliers of these systems for both semiconductor and FPD include the USA-based AZ Electronic Materials, the USA-based Rohm and Haas Corporation, and the Japanese company, Tokyo Ohka Kogyo Co Ltd. In positive photoresist applications, a substrate is etched by plasma processes, which use gases of inert and chemical varieties to produce both ionized and reactive species that travel through the mask and etch down into the substrate. During etching, ionized and reactive species combine with atoms of the substrate, form a by-product, and that by-product is vented away via the reduced pressure of the plasma system. These same gaseous species also impact the photoresist mask, baking it into place and also ejecting carbon-containing by-products into the plasma. Photoresist by-products mix

with other species in the plasma and are continually directed down towards the substrate. These materials condense to form a residue along the sidewalls of the etched features, producing a desirable condition, otherwise referred to as anisotropic etching whereby species are highly controlled and directed into the substrate with little or no lateral loss. Upon completion, it is desired to remove this etch residue along with the resist mask, as they can have deleterious effects on subsequent processes and lead to reduced device performance or device failure. Such residues and their associated resist masks, however, can be difficult to remove, normally involving the use of formulated stripper chemistries.

Negative photoresists are commonly chosen for more rigorous process conditions whereby more aggressive chemical or thermal exposure processes may be used. These negative photoresists include isoprene (rubber), acrylic, and epoxy-based resins. Cyclized isoprene (rubber) photoresists are chosen for their high chemical resistance. Examples of these photoresists may be obtained from Fujifilm Electronic Materials, Ltd. under the trade name *SC-Resist* or *HNR-Resist*. Negative-tone isoprene resin resists are common in aluminum processing where a brief chemical etch is used to remove metal surrounding the masked feature. Negative-tone acrylic photoresists are commonly chosen for wafer-level-packaging bump formation. Suppliers include the USA-based Printed Circuits Division of E. I. duPont de Nemours and Company under the trade name *Riston*, and the Japan's JSR Corporation for dry-film and spin-on (wet) negative acrylics, respectively. Dry-film and spin-on acrylics offer an ability to deposit thick layers from 25 to 120 microns (μm), used to pattern the corresponding solder bumps. Once the pattern is formed, metal deposition occurs by electroplating or screen-printing, a process that exposes the resist to heated acid or baking in excess of 250°C , respectively. Another popular negative resist, an epoxy system under the trade name of SU-8 TM, originally developed by International Business Machines (IBM) and now sold by the USA company, MicroChem Corporation, and Gersteltec Engineering Solutions, a Swiss-based company. The SU-8 TM is commonly chosen for thick patterns that may exceed 300 microns (μm), with a high-aspect ratio (i.e. height vs width), and with the pattern definition to exhibit extremely straight sidewalls. Because of the extremely unique characteristics of the SU-8 TM epoxy resin, photoresists of this variety are chosen to manufacture large

devices, and most commonly include microelectromechanical systems (MEMS). The varieties of negative-tone photoresists are significantly different from positive, their cleaning (removal) practice is even more rigorous. In fact, it is commonly understood that SU-8™ photoresist is considered to be a permanent system, removed only with
5 more complex, time, and costly practices.

As with any process involving photolithography, it is desirable to completely remove the photoresist from the substrate in order to proceed successfully to the next process. Incomplete stripping of the photoresist can result in irregularities during the next etching or deposition step, which may cause quality and yield problems. For
10 example, during solder bumping, resist contamination can prevent metal solder from wetting to a metal pad during the board assembly reflow processes, resulting in yield loss in a finished assembly. The same photoresist contamination is manifested as organic contamination in front end of line device patterning and results in the exact same non-wetting problems in an etch or deposition process. Such irregularities, no
15 matter how small, continue to magnify the problem throughout manufacturing until during final device assembly and testing, the condition leads to poor mechanical and electrical contacts, which produce high resistance and heat, or worse, catastrophic electrical shorting.

Throughout each of these chemical processes, one can appreciate maximum
20 selectivity in cleanliness and high throughput must be met without failure. Any problems associated with a lack of performance, presence of residue, or worse, a rise in process complexity, all will result in reduced yield and increased cost.

It is generally understood that the chemistry of positive tone resists are typically hydrophilic (polar) and amorphous (i.e. non thermoset and cross-linked), and
25 it is for these reasons that these systems are believed to be easier to clean (remove) using conventional solvents and/or chemical strippers. The resins for positive-tone chemistries are based upon either novolac (cresol, phenol-formaldehyde) or polyhydroxystyrene (Phost), with occasional options of styrenated copolymer and/or acrylic/PMMA (polymethylmethacrylate). These chemistries offer good adhesion and
30 fixing to a wide variety of surfaces while the hydroxyl groups present in the various forms of novolac (i.e. cresol, bis-phenol, etc.) provide intermolecular hydrogen bonding which aids in aqueous solubility. This condition combines during the

photoconversion of the initiator diazonaphthoquinone (DNQ) in novolac systems, while in Phost systems, the acid catalyzed de-protection of the ester forms the more soluble alcohol. When used during normal operating conditions up to and including 100 degrees C, these systems remain soluble in polar solvents while their UV-
5 exposure will produce counterparts that are soluble in aqueous-base.

As indicated here, the positive-tone resists are used as primary imaging masks for plasma-based etching. During this process, species in the plasma produce etch residue while exposing the mask to temperatures exceeding 150 degrees C. It is well known that etch residue (e.g. side wall polymer) is comprised of by-products of the
10 plasma with organic constituents of photoresist. The chemistry of the residue may comprise constituents of the substrate, metal topography, and plasma gases, to include silicon, gallium, arsenic, boron, phosphate, titanium, tantalum, tungsten, copper, nickel, aluminum, chromium, fluorine, chlorine, as well as carbon containing compounds. In novolac systems which contain hydroxyl constituents, these elevated
15 temperature exposure conditions will facilitate further reactions to form insoluble species. Such reactivity of hydroxyl groups with halides and active metals, especially in the heated and acidic conditions of a plasma, to produce alkyl halides, esters, and, in some cases, high molecular weight polymers is known (*Morrison, R.T. and Boyd, R.N., Organic Chemistry, 3rd Ed., Allyn & Bacon, Inc., Boston MA, Ch.16 (1973)*).
20 Conventional cleaning of etch residue and overexposed photoresist masks resulting from the effects of hot plasma etching require the use of chemical strippers processed at elevated temperatures for extended periods of time dependent upon the process and tool.

Typical measurement used to predict stripping challenges of bulk resins
25 includes thermal analysis determination of glass transition (T_g). Relatively unchanged T_g values are observed in positive-tone photoresists and similar amorphous systems (Fedynyshyn, T. et al., *Proc. SPIE 6519*, 65197-1 (2007)). Detectable increases of T_g in photoresists have been observed to be a function of the evaporative loss in solvent, which in turn, will depend upon the thickness of the
30 photoresist coating. Most notable are observed increases in T_g with radiation and thermal exposure with polymer crosslinking (J. D. D'Amour et al., *Proc. SPIE 5039*, 966 (2003)). Such crosslinking of high temperature exposed novolac resins and

negative-tone systems is consistent with the presence of higher molecular weight species as detectable by increased values of Tg.

Cleaning (removal) of photoresist etch residue and the mask use complex chemical strippers composed of organic solvents, amines, water, reducing agents, 5 chelating agents, corrosion inhibitors, and surfactants. The reducing agent, hydroxylamine, has been cited extensively in the literature as a basic material which facilitates dissolution of photoresist and its residue while offering protection of underlying aluminum metal features. Common practice in using stripper chemistries involves delivery of large volumes of stripper to the substrate to be cleaned at a 10 specific temperature for a given period of time.

As the industry continues to replace aluminum with copper to capture improved performance in their devices, the stripper chemistries must also be adjusted. Hydroxylamine may be acceptable for cleaning of aluminum devices; however, it is too aggressive for copper. Device architecture using copper and low-K (dielectric 15 constant, K), e.g. Cu/Low-K, require fluorinated-based chemistries to remove silicon-laden etch residue. Amines and ammonia compounds are known to be complexing agents for Cu and are observed to etch (attack) copper metal. Additionally, fluorinated and glycol-based stripper chemistries are considered toxic and exhibit elevated viscosities.

20 Negative photoresists used in forming wafer bumping metallization masks generally include acrylic, styrenic, maleic anhydride or related monomers and copolymers. Such materials are used to produce photosensitive thick films. These photoresists are commonly referred to as "acrylic" polymer systems due to the pendant groups on the main polymer chains, which include vinyl groups common to 25 acrylics. In general, the dry-film form of acrylic photoresists is chosen where exposure to rigorous process conditions is required. As a result of this exposure, the cleaning of dry-film masks and residues presents a stripper challenge. When a dry-film system is removed, the material is typically not dissolved. Rather, many chemical strippers interact with the material to cause lifting or peeling from the 30 substrate, resulting in the generation of suspended insoluble flakes and particles. Such insoluble materials can lead to filter fouling and performance degradation in the processing tool. This can create a significant loss in productivity as a result of process

tool downtime for maintenance. In addition, the failure to filter off or rinse away particles may result in the formation of residue on the final product and contribute to yield loss.

Resist stripping compositions that include aromatic quaternary ammonium hydroxide such as benzyltrimethylammonium hydroxide (BTMAH), a solvent such as an alkylsulfoxide, a glycol and a corrosion inhibitor and non-ionic surfactant do not completely remove many dry-film resists from a wafer surface. Similarly, compositions which use pyrrolidone-based solvents such as N-methylpyrrolidone (NMP) exhibit the same drawback in that they cannot achieve complete removal of many dry-film resists. In general, compositions which include a quaternary ammonium hydroxide as tetramethylammonium hydroxide (TMAH) in NMP do not completely dissolve many dry-film resist. As discussed above, incomplete dissolution produces particles that can become a source of contamination resulting in yield loss.

Similar experience is noted for negative-tone photoresist of the rubber-based resin variety. Stripper chemistries used to clean residue and masks resulting from rubber photoresists include a hydrocarbon solvent and an acid, commonly a sulfonic acid. High acidity is required for performance and emulsification of hydrolyzed rubber components. Representative inhibitors include mercaptobenzotriazole (MBT) and related triazoles to prohibit attack upon adjacent metallic features. A common inhibitor for these chemistries includes catachol, a toxic and carcinogenic material. Further, rinse steps for hydrocarbon strippers of this variety must use isopropanol (IPA) or related neutral and compatible solvents. This rinse practice, albeit a cost increase, will reduce the effects of metal attack to adjacent metals due to a pH-drop during water mixing with constituents of the stripper. Due to compatibility issues, wastes from the use of hydrocarbon-based strippers must be segregated from normal organic streams in a microelectronic fab.

While it is important to give attention to the challenges of polymer and residue removal from the standpoint of the stripper chemistry, equal diligence is necessary towards the design of the process and proper performance of the tool. It is generally understood that the primary purpose of the cleaning tool is to provide control in the process. Variability between part batches is reduced by the operation of the tool. Barring any mixing or chemical adjustments made by the unit, the variables available

to the tool for control include temperature, agitation, and time. With an ever-present intensive pressure to increase throughput in a manufacturing line, a constant emphasis is to decrease the process time. Again, without a change in chemistry, this leaves as the only option to increase temperature and agitation, with the expectation that

5 polymer dissolution rates will increase resulting in shorter process time. However, other reactions which are contradictory to the objectives of the process, such as corrosion rate, will also increase with increase in temperature and agitation. Additionally, and most important, there is continued loading of the stripper chemistry with the organic substance, causing a reduction in bath life and accelerates the

10 observation of residue or other phenomena that indicate a drop in performance.

On the temperature continuum, bath life may be facilitated by increasing temperature or agitation. Where agitation must be controlled to protect substrate features, bath life conditions may be increased through increased polymer dissolution with increasing temperature. There is a fundamental safety limit as communicated by

15 industry guidelines (SEMI S3-91, *Safety Guidelines for Heated Chemical Baths*). In accordance with SEMI, liquid over temperature shall be controlled at not more than 10 degrees C above the normal operating temperature of the liquid, where the typical operating temperature does not exceed the flashpoint of the liquid. Many companies will set policy which is more restrictive such as operating at 10 degrees C below the

20 flashpoint and setting the over temperature to be the flashpoint. These criteria and others may best be observed in the processing of flat panel displays (FPDs).

Resist stripping at a FPD manufacturing plant occurs on large substrates traveling on a conveyor from one chamber to another. The resist is stripped from the panel by a stripper delivered by a sprayer that floods the entire glass surface, traveling

25 to a rinse stage where distilled, deionized, or demineralized water or an alternative solvent is sprayed onto the surface, and the process is completed with a drying step that includes a hot air knife. Stripping is supported by at least two product tanks which are separate and distinct and arranged in-line with the flow direction of the parts. Substrates entering the tool will be first "washed" by the chemistry in the first

30 tank. The stripper is sprayed onto the substrate surface, and upon reacting with the resist and flowing off of the substrate, it is collected and returned to the tank where it is subsequently heated and filtered such that any suspended and undissolved materials

are removed from the bulk chemistry. The filtered and heated stripper is then cycled back to the spray chamber where it is delivered to the substrate in a continuous manner that optimizes the resist stripping process.

As the part travels on the conveyor from the first chamber supported by tank #1 to the next chamber supported by tank #2, there is a fundamental purity change in the stripper. Although the conditions of operation for tank #2 may be the same as that for tank #1, the amount of resist present is lower than that for tank #1. Typical processing times are defined for chamber #1 to offer a dwell time of the chemistry in contact with the resist which optimizes resist stripping and maximum removal. Over time, tank #1 will reach a maximum loading capacity for dissolved resist and a decision to replace the contents will be necessary. When this occurs, the contents of tank #1 will be sent to waste and replaced by the contents of tank #2. The contents of tank #2 will be replaced with fresh stripper (i.e. pure stripper). In this manner, the system is said to operate in a counter-current fashion. Namely, the process flow of parts is "counter" or opposite to the flow direction of the chemistry. By using this practice, tanks #1 & #2 become the dirty and clean tanks, respectively. In other words, the unwanted resist is concentrated in the front of the line while the cleanest chemistries remain near the end whereby after this point, the product substrate is rinsed and dried.

The configuration given here for the FPD example is consistent with most, if not all, in-line bench style tools and with many batch style-processing tools. In a bench tool, parts move from one station to another while the tanks are at fixed locations. In a batch style tool, the parts may rotate but remain at a fixed location, while the chemistry is being delivered by spraying. There will be two tanks, the tool will pump from one or the other and carry-out counter-current cleaning designs by the use of "dirty" and "clean" tanks.

There is an equal, yet unsatisfied, need to achieve selectivity during processing with these formulated strippers. Namely, as the use of more aggressive chemistries is put into practice to achieve a desired cleaning performance in ever reducing time, this practice must be met without damage to sensitive metals and the underlying substrate. This is especially challenging as many of the acids or alkalis of choice will rapidly "spike" the pH of the system, once they are mixed with water

during the rinse step, causing galvanic corrosion to substrate metals. During the rinse stage on a FPD line, water is sprayed on the heated glass surface that contains residual stripper. No surfactants are used in a FPD line, in fear that a foam condition will occur and ultimately cause catastrophic failing of filters, pumping of dry air bubbles, and worse, contaminating the fab by overflowing stripper which may trigger electrical shorting and lead to a fire. Since no surfactants are used, there is irregular diffusion due to rising surface tension from the organic stripper to the aqueous condition. Irregular mixing and spreading cause momentary dead spots on the panel, which contribute to accelerated corrosion. The corrosive byproduct and foaming condition may be avoided through rinsing with neutral solvents such as isopropanol (IPA). Although this practice is accepted by several FPD manufacturers, it is both expensive and a flammability hazard.

There is a need, accordingly, for improved stripping compositions which will remove the processed resist in a rapid manner while maintaining safety towards the underlying metallurgy during rinsing with distilled, deionized, or demineralized water, and preventing corroding, gouging, dissolving, dulling, or otherwise marring the surfaces throughout the entire process. Further, growing initiatives exist within the industry to move towards being "green." A green process and the associated chemistries are those which will reduce or eliminate the use and generation of hazardous substances. According to the *American Chemical Society's Green Chemistry Institute*, there are twelve (12) principles which help to define a green chemistry.

This review of polymeric substances in microelectronic fabrication presents serious and compelling challenges in the industry. Where organic dielectrics are used, there is a continuing need for processes and compositions which may be used to effectively re-work a cured polymer by dissolving and cleaning the unwanted material from the underlying substrate. In cases of positive photoresists, there is a similar and continuing need for processes and compositions to effectively remove polymer from a substrate without deleterious effects to adjacent metal features. Finally, in the case of negative-tone photoresists, the same need exists for processes and compositions to effectively remove polymer from a substrate without deleterious effects to adjacent metal features. Although all of these materials are organic in origin, their chemistry is

different and presents unique challenges that must be overcome in order to effect the desired cleaning result.

While there is a desire to address the removal needs of organic substances with unique compositions, there also, is a challenge to design a process that is supported by a tool which will enable rapid processing of parts, rinsing with water, without deleterious effects to the substrate. There is a continuing emphasis for the microelectronics industry to be green through improving the safety of operations, reducing the use of chemistry, and reducing the generation of hazardous waste. Taking these challenges together, there is a pressing need to provide a consistent and universal process, which uses compositions of matter that vary depending upon the performance needs of the unique polymer or residue to be removed, which provides high performance, high throughput, a green process, all at a reduced cost of ownership.

15 Summary of the Invention

An embodiment according to the present invention concerns a composition for cleaning organic resin from inorganic substrates comprising:

a solvent or mixture of solvents; and

a metal sulfonate salt of isophthalic acid, a metal sulfonate salt of a isophthalic acid diester, or a combination thereof where the sulfonate group is attached to the aromatic nucleus and the metal is selected from lithium, sodium, or potassium and mixtures thereof at a weight % of greater than 0.5%;

wherein the solvent is selected from the group consisting of ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, diethylene glycol ethyl ether, diethylene glycol methyl ether, diethylene glycol butyl ether, diethylene glycol propyl ether, ethylene glycol propyl ether, ethylene glycol butyl ether and mixtures thereof.

Another embodiment concerns a composition for removing organic resin from inorganic substrates comprising:

an organic solvent or mixture of solvents at a weight % of from about 0.5% to about 99.0%, and

a metal sulfonate salt of isophthalic acid, a metal sulfonate salt of a isophthalic acid diester, or a combination thereof where the sulfonate group is attached to the

aromatic nucleus and the metal is selected from lithium, sodium, or potassium and mixtures thereof at a weight % of greater than 0.5%; and

at least one additive which enhances cleaning performance at a weight % of from about 0.01% to about 99.0%,

5 wherein the solvent is selected from the group consisting of ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, diethylene glycol ethyl ether, diethylene glycol methyl ether, diethylene glycol butyl ether, diethylene glycol propyl ether, ethylene glycol propyl ether, ethylene glycol butyl ether and mixtures thereof.

Yet another embodiment concerns a method for removing organic resin from
10 inorganic substrates comprising:

- i) coating said organic resin with a stripping composition,
- ii) heating the substrate to a temperature and for a time sufficient to achieve dissolution of the organic resin, and
- 15 iii) rinsing the substrate with a volume of a rinsing agent sufficient to remove the composition and the organic resin,

wherein said coating results in a layer of stripping composition on the substrate that is about 1000 microns or less.

Another embodiment concerns a method for removing organic resin from an inorganic substrate comprising,

- 20 (i) coating said organic resin with a stripping composition,
- (ii) heating the substrate to a temperature and for a time sufficient to achieve dissolution of the organic resin, and
- (iii) rinsing the substrate with a volume of a rinsing agent sufficient to remove the composition and the organic resin;

25 wherein said coating comprises spray coating, spin coating or slit coating.

Detailed Description of the Invention

The present invention provides stripping compositions and methods, which quickly and effectively remove polymeric organic substances from inorganic
30 substrates, from metallic, non-metallic and metallized non-metallic substrates. In an embodiment, the stripping composition comprises a water-soluble monomer and various additives, which effectively remove organic substances and their residues of

thermoplastic or thermoset nature that comprise the basis for fabricating microcircuits in electronic manufacturing. The method defines a practice of coating the composition onto the substrate, heating the substrate to a specific temperature for a given time sufficient to achieve dissolution of the organic substance, and finishing
5 with removal of the by-product by rinsing with a rinsing agent, such as water. The composition and method work together to provide performance and other desired goals in manufacturing not normally seen in conventional stripper processes. Although the organic substances to be removed may be cured to a hard and chemically resistant framework when exposed to the customer's process, the invention
10 is found to maintain acceptable performance.

The compositions and methods have particular applicability to semiconductor wafer fabrication, for example, in the removal of organic films and residues from semiconductor wafers. Such organic substances are present, for example, on post-etched wafers during front-end processing or in back-end wafer-level-packaging
15 during a wafer bumping process. The compositions and methods are particularly suitable for the removal from wafers of hard-to-remove materials such as full-cure polyimide and dry-film photoresist residues.

While the present invention provides stripping compositions and methods which can effectively remove polymeric organic substances from a substrate, it is also
20 adapted for removing photoresists that include positive-tone of both novolac (i.e. cresol formaldehyde) and polyhydroxy styrene (Phost), negative-tone varieties to include acrylics, isoprene (i.e. rubber), and epoxy (i.e. SU-8TM), as well as dielectrics to include polyimide, polybenzoxazole (PBO), and bisbenzocyclobutene (BCB). The stripping compositions and methods can also remove other photoresists, for example
25 multi-layer photoresists and chemically amplified photoresists. These organic substances are employed in the fabrication of substrates, for example, the electronic devices on substrates such as wafers or flat panel displays, which may include various layers and structures such as metal, semiconductor, and the associated organic materials. Typical substrate materials include, for example, semiconductor materials
30 such as silicon, gallium arsenide and indium phosphide and sapphire, as well as glass and ceramic.

Whenever the term "water-dissipatable" or "water-dispersible" is used in this description, it will be understood to refer to the activity of a water or aqueous solution on the monomer (Component B). The term is specifically intended to cover those situations wherein a water or aqueous solution dissolves and/or disperses the monomer material therein and/or therethrough.

The terms "stripping", "removing", and "cleaning" are used interchangeably throughout this specification. Likewise, the terms "stripper", "remover", and "cleaning composition" are used interchangeably. The term "coating" is defined as a method for applying a film to a substrate such as spray coating, puddle coating, slit coating or immersing. The terms "film" or "coating" are used interchangeably. The indefinite articles "a" and "an" are intended to include both the singular and the plural. All ranges are inclusive and combinable in any order except where it is clear that such numerical ranges are constrained to add up to 100%. The term "wt%" means weight percent based on the total weight of the components of the stripping composition, unless otherwise indicated.

A process according to the present invention can involve submerging the inorganic substrate in a bath of the composition according to the present invention or preferably by applying the composition as a coating to the inorganic substrate. Once the substrate is submerged in the composition or the composition is applied and covers, or coats, the entire area, heating of the substrate begins. A rapid rate of heating occurs until the desired temperature is reached and is held for a desired period of time. Alternatively, the bath into which the substrate is submerged could be maintained at the desired temperature. Rinsing with a rinsing agent occurs and is followed by a drying step. The total method of practice involves three (3) distinct steps, namely, the coating, heating, and rinsing. As used herein, the term "rinsing agent" includes any solvent which removes the composition and material to be stripped. Examples of rinsing agents include water, acetone, isopropyl alcohol and mixtures thereof.

An embodiment of the invention concerns a method whereby a composition according to the present invention or other stripping composition is applied as a liquid coating in direct contact with the substance to be removed. The method includes heating anywhere from approximately 25°C to about 400°C or from about 100°C to

about 250°C. Variability in temperature will depend upon the nature and thickness of the organic substance. The heating step process time can be from about 5 seconds to about 10 minutes, from about 10 seconds to about 8 minutes, or even from about 30 seconds to about 4 minutes. Moreover, the entire process time can vary anywhere
 5 from less than 15 seconds to 180 seconds, in some cases, from 5 minutes to 10 minutes. The variability in time is dependent upon the material to be removed, its thickness, and exposure condition. For example, for a Phost or Novolac resin, the heating step could be from about 15 seconds to about 1 minute. However, for other, more highly cured resins, the heating step can last from about 2 to 4 minutes or even
 10 longer. Once the diffusion of the organic substance is complete, rinsing with a rinsing agent such as distilled, deionized, or demineralized water may be performed.

Rinsing is facilitated by the presence of the water-soluble monomer in the composition. This monomer performs as a carrier system for the organic substance to be removed from the inorganic substrate. The rinsing agent used for rinsing can be at
 15 a temperature of about 5°C to about 100°C. However, rinsing can also occur at room temperature and performs two objectives, to remove the dissolved organic substance, and to reduce the temperature of the substrate such that next stage processing may proceed.

Compositions of matter used in this invention include a major component to
 20 be a solvent system of the varieties which include one or more esters selected from the group consisting of structures (I) $R-CO_2R_1$, glycol ether esters of structures (II) $R_2-CO_2C_2H_4(OC_2H_4)_n-OR_3$, (III) $R_4-CO_2C_3H_6(OC_3H_6)_n-OR_5$ and (IV) $R_6OCO_2R_7$, alcohols selected from structures (V) R_8OH , (VI) $R_9OC_2H_4(OC_2H_4)_nOH$, (VII) $R_{10}OC_3H_6(OC_3H_6)_nOH$, (VIII) $R_{11}(OC_2H_4)_nOH$, and (IX) $R_{12}(OC_3H_6)_nOH$, ketones
 25 selected from structures (X) $R_{13}COR_{14}$, sulfoxides selected from structure (XI) $R_{15}SOR_{16}$, and amides such as N,N-dimethyl formamide, N,N-dimethyl acetamide, and N-methyl pyrrolidone, wherein R, R_1 , R_2 , R_3 , R_4 , R_5 , R_6 , R_7 , R_8 , R_9 , R_{10} , R_{11} , R_{12} , R_{13} , R_{14} , R_{15} , and R_{16} are independently selected from hydrogen or $C_1 - C_{14}$ - alkyl groups and n represents a repeating unit ranging from 1 to 10. Further, suitable
 30 solvents include, but are not limited to ketones such as cyclohexanone, 2-heptanone, methyl propyl ketone, and methyl amyl ketone, esters such as isopropyl acetate, ethyl acetate, butyl acetate, ethyl propionate, methyl propionate, gamma- butyrolactone

(BLO), ethyl 2-hydroxypropionate (ethyl lactate (EL)), ethyl 2-hydroxy-2-methyl propionate, ethyl hydroxyacetate, ethyl 2-hydroxy-3-methyl butanoate, methyl 3-methoxypropionate, ethyl 3-methoxy propionate, ethyl 3-ethoxypropionate, methyl 3-ethoxy propionate, methyl pyruvate, and ethyl pyruvate, ethers and glycol ethers such as diisopropyl ether, ethyleneglycol monomethyl ether, ethyleneglycol monoethyl ether, and propylene glycol monomethyl ether (PGME), glycol ether esters such as ethyleneglycol monoethyl ether acetate, propyleneglycol methyl ether acetate (PGMEA), and propyleneglycol propyl ether acetate, aromatic solvents such as methylbenzene, dimethylbenzene, anisole, and nitrobenzene, amide solvents such as N,N-dimethylacetamide (DMAC), N,N-dimethylformamide, and N-methylformanilide, and pyrrolidones such as N-methylpyrrolidone (NMP), N-ethylpyrrolidone (NEP), dimethylpiperidone, 2-pyrrole, N-hydroxyethyl-2-pyrrolidone (HEP), N-cyclohexyl-2-pyrrolidone (CHP), and sulfur containing solvents such as dimethyl sulfoxide, dimethyl sulfone and tetramethylene sulfone.

Although these organic solvents may be used either individually or in combination (i.e., as mixtures with others), the preferred solvent system should contain diethylene glycol (DEG, Eastman Chemical Company), diethylene glycol monomethyl ether (DM Solvent, Eastman Chemical Company), diethylene glycol monoethyl ether (DE Solvent, Eastman Chemical Company), or diethylene glycol monopropyl ether (DP Solvent, Eastman Chemical Company), diethylene glycol monobutyl ether (DB Solvent, Eastman Chemical Company) or mixtures thereof.

An embodiment of the composition includes one or more solvents at about 0.5 weight percent to about 99.5 weight percent. In one embodiment, the solvent is present in the solvent composition at a weight % of from about 40% to about 97% or at a weight % of from about 60% to about 90 %.

In an embodiment, the composition also contains a monomer, which exhibits the property of water solubility, water dispersibility, or water dissipatability present at about 0.5 to about 99.5 weight percent and derived from, but not limited to, is selected from multifunctional sulfomonomers containing at least one metal sulfonate group attached to an aromatic nucleus that are water soluble or water dispersible or water dissipatable determined to be at or greater than 0.5 weight % concentration (i.e. monomer in water) and the metal of the sulfonate group is Na, Li, K, and mixtures

thereof. The composition includes of one or more of these said monomers at about 0.5 weight percent to about 99.5 weight percent. In one embodiment, the monomer is present in the composition at a weight % of from about 2 to about 59 or at a weight % of from about 5 to about 35.

5 Examples of water soluble monomers are selected from metal sulfonate salts of isophthalic acid, metal sulfonate salts of a isophthalic acid diester, or a combination thereof where the sulfonate group is attached to the aromatic nucleus and the metal is selected from lithium, sodium, or potassium and mixtures thereof. In general, suitable monomers are 5-sodiosulfoisophthalic acid and salts and esters of the same,
10 in particular, the diethylene glycol diester of 5-sodiosulfoisophthalic acid.

 Additives to the composition may comprise about 100 parts-per-million (ppm) to about 99 weight percent of an alkali or acid of organic or inorganic origin to include ammonium hydroxide, quaternary hydroxides such as tetramethyl ammonium hydroxide (TMAH), tetraethyl ammonium hydroxide (TEAH), and benzyltrimethyl
15 ammonium hydroxide (BTMAH), amines such as triethylene tetramine, alkanolamines which include monoethanolamine, monoisopropanolamine, diglycolamine, elemental hydroxides, or alkoxides such as potassium tertiary butyl hydroxide (KTB), alkyl-sulfonic acids such as methanesulfonic (MSA), toluenesulfonic (TSA), and dodecylbenzene sulfonic acid (DDBSA), formic acid,
20 fatty acids, sulfuric acid, nitric acid, or phosphoric acids; an inhibitor defined as a protecting agent for substrate composition which may include chelating, complexing, or reducing agents, comprising one or more of the known varieties, including benzylic hydroxides such as catechol, triazoles, imidazoles, borates, phosphates, and alkyl or elemental silicates, ethylenediaminetetraacetic acid, diethylenetriaminepentaacetic
25 acid, nitrilotriacetic acid, and 2,4-pentanedione, reducing sugars, hydroquinones, glyoxal, salicylaldehyde, acids such as citric and ascorbic acid, hydroxylamines, or vanillin; and a surfactant consisting of one or more of the known varieties, including nonionic nonyl-phenols and nonyl-ethoxylates, anionic forms that include alkyl-sulfonates, phosphate esters, and succinates, and fluorinated systems. The additive
30 can be present in an amount of from about 0.1 weight percent to about 95 weight percent, about 1.0 weight percent to about 50 weight percent, or about 5.0 weight percent to about 35 percent.

The composition may also include an inhibitor which acts as a protecting agent for the substrate composition. The inhibitors include chelating, complexing, or reducing agents, comprising one or more of the known varieties, including benzylic hydroxides such as catechol, triazoles, imidazoles, borates, phosphates, and alkyl or
5 elemental silicates, ethylenediaminetetraacetic acid, diethylenetriaminepentaacetic acid, nitrilotriacetic acid, and 2,4-pentanedione, reducing sugars, hydroquinones, glyoxal, salicylaldehyde, fatty acids such as citric and ascorbic acid, hydroxylamines, or vanillin.

The compositions according to the present invention may also include a
10 surfactant including one or more of the known varieties, including nonionic nonyl-phenols and nonyl-ethoxylates, anionic forms that include alkyl-sulfonates, phosphate esters, and succinates, and fluorinated systems.

Contact is made to the substrate by the composition via bath submersion or using a coating practice. In microelectronic manufacturing, spin coating is the
15 method of choice used to apply coatings to a substrate. However, other methods exist to include spray-spin coating and slit coating for large substrates as in FPD manufacturing. In all cases, the objective is to apply the composition in a manner to achieve complete coverage. Normally, most coating applications are concerned with a high degree of uniformity. In this invention method, a thickness shall be
20 established, typically on the order of a maximum value of 1000 microns ($1\text{ }\mu\text{m} = 1 \times 10^{-6}\text{ m}$), but some cases where the organic substance is very thin, the composition thickness may be smaller. In one embodiment of the present invention, the coating can be up to about 800 microns thick, between about 200 to about 600 microns thick, or from about 300 to about 400 microns thick.

25 Common practice for spin-coating the composition for this invention is to dispense the material at the center of a substrate, and operate the equipment at a low rate of circular motion speed (i.e. less than 100 revolutions per min, rpm). Liquid delivery may be done by a static method, whereby the fluid will "puddle" onto the surface. A dynamic method may also be used where the material is dispensed when
30 the substrate is already in motion. During the early stages for a new process set-up, the exact conditions of rpm and time may need to be established in such a manner to ensure complete coverage of the substrate with minimal or no waste. There is no need

to be concerned with edge bead formation as this condition will be irrelevant to the process objective.

The manipulation of spin-speed is a common focus of many apparatus used in the microelectronics industry. Substrate rotation will have a direct affect on these properties and produce different coating results. At low spin-speeds, fluid mobility will be low with minor material loss, however, irregularities in substrate coverage may also occur. Alternatively, high spin-speeds will result in high mobility and high material loss. Although spin-coating is a standard practice in the industry, experience shows that thick coatings of acceptable thickness uniformity may be achieved with a spray-coating practice. Once the coating is completed, heat activation of the process may immediately proceed.

Heat application may be conducted through several paths. For manual operations, a simple hot-plate may be used. This requires the substrate to be moved from one location to another. In situations where automation is of interest, the wafer may remain stationary while heat is applied using a base-chuck or an overhead IR convection source. Exact ergonomics and logistic concerns with respect to controls and throughput can be readily determined by those skilled in the art of tool design. Once the proper heating regime is followed, the composition and organic resin may be removed by rinsing with a rinsing agent either in an agitated batch or by direct spray contact.

The stripping compositions of the invention function by maintaining a solvency environment when used on amorphous organic substances such as positive-tone photoresists of the Phost or novolac varieties. In such cases and when exposure conditions include moderate temperatures up to 150 degrees C, a composition which contains the minimum constituents, including the solvent system and water soluble monomer, is coated and processed at the conditions of the invention method. When heated to a sufficient temperature, rapid dissolution occurs and diffusion of the photoresist into the composition proceeds rapidly to completion. Additives such as an alkali agent, inhibitor, and surfactant may be used to facilitate good results with highly baked (i.e. >150 degrees C) photoresists. Advantages in using additives contained within the stripping composition may include improved dissolution rates

due to saponifying cross linked photoresist while the inhibitors protect exposed metal during the stripping and rinsing steps.

Organic alkanolamine compounds are preferred for alkaline saponifying and emulsification of the positive-tone photoresists, to include one or more low molecular weight candidates, for example, monoethanolamine (MEA), N-(2-aminoethyl) ethanolamine (AEEA), monoisopropanolamine (MIPA), or diglycolamine (DGA), and combinations thereof. In cases where a negative-tone acrylic photoresist or a cured thermoset polyimide are the candidates to be removed, the composition will require a strong alkali, namely, a quaternary hydroxide, metal hydroxide, or alkoxide.

Similar to the review given here for removing coatings and residues compositions also apply for removal of negative isoprene (rubber) resist and negative-epoxy (SU-8TM) photoresist. As we have determined for the positive photoresist and negative acrylic and polyimide, the choice in composition is dependent upon the material to remove. For negative-isoprene, the chemistry is hydrophobic (non-polar) and the cross linked rubber system does not respond to alkalis, only acids. Rubber photoresists require aromatic solvents and hydrophobic acids, such as dodecylbenzene sulfonic acid. For negative epoxy photoresist, the chemistry is hydrophilic (polar) and like the rubber photoresists, these systems also do not respond to alkalis. The preferred system is one which incorporates hydrophilic acids such as methanesulfonic acid (MSA) or sulfuric acid. These systems all contain the water soluble monomer, to facilitate proper rinsing following dissolution of the photoresist.

EXAMPLES

The invention is further illustrated, without limitation, by the following examples. All percentages given are by weight unless otherwise specified. In these examples, the measurement of performance and selectivity of the invention is conducted using practices readily accepted by the industry. In such cases, measurement is made by optical microscope and where necessary, the use of etch rate determinations by high sensitivity gravimetric reviews on metallic substrates, and where necessary, more detailed studies were conducted using scanning electron microscopy (SEM). In the following examples, silicon wafers were used as the inorganic substrate upon which the organic substance is applied and cured. The

following items in Table 1 represent the organic substances to be removed, their preparation methods, and the sources from which they were procured.

Table 1: List of Organic Resins Used to Demonstrate the Invention.

Example #	Material	Form	Type	Description/Manufacturer
1	Phost	Solid resin worked up as liquid	Amorphous, positive	Equal quantities as 1:1 w/wwt% PB5 and PB5W resin (Hydrite Chemical Co., Brookfield WI), dissolved in PGMEA* as 20wt% solids
2	Novolac	Solid resin worked up as liquid	Amorphous, positive	Equal quantities as 1:1 w/wwt% <i>Rezicure</i> 5200 and 3100 (SI Group, Schenectady, NY), dissolved in PGMEA* as 20wt% solids
3	Acrylic	Dry-film	Thermoset, negative	Shipley GA-series (GA-20) removed and applied direct, (Rhom & Haas, Inc. Marlborough, MA)
4	Polyimide	Liquid	Thermoset, Non-photoactive	PI-2611 (HD Microsystems, Parlin, NJ)
5	Isoprene	Liquid	Thermoset, negative	SC-Resist (Fujifilm Electronic Materials, North Kingston, RI)

5 *PGMEA: propylene glycol monomethyl ether acetate

Where applicable, the organic substance is applied in the manner of a coating utilizing a Brewer Science, Inc. CB-100 coater and following standard protocol for applying the liquid form of the polymer material to the inorganic substrate. Once the material is coated, it is sent to a soft bake step for a short 60sec hot plate bake at 100
 10 degrees C. For negative Acrylic resist, the material is exposed to ultraviolet light of a broad-band type emitting at 365nm and of a high exposure dose of 0.12W/cm²-sec, for an excessive period of 30min. Following exposure, the wafer was post-exposure baked at a predetermined hard bake temperature and time depending on the resist. Once the wafer samples have been prepared, they are staged for experimentation. The
 15 experiments in Examples 2-5 are all conducted identical to each other using the same wafers and handling practices. Each wafer is staged in the work station where the invention will be demonstrated. Compositions of the invention are prepared ahead of time and also set aside. The invention method is tested by applying the composition of interest to a portion of the wafer surface. The wafer is then immediately
 20 transferred to a hot plate which has been preset at the desired processing temperature.

Once the wafer is set onto the hot plate, a digital timer is started. Once the pre-established time has expired, the wafer is removed and immediately rinsed with distilled, deionized, or demineralized water from a wash bottle. The rinsed wafer is observed and set aside to dry. Additional observations are taken and the results are recorded.

In all cases, introduction of the monomer was obtained by the addition of a premade stock solution. These stock solutions were comprised of a hydrophilic solvent (Component A) and a water soluble or water dispersible or water dissipatable monomer (Component B). The monomers chosen were selected from various multifunctional sulfomonomers containing at least one metal sulfonate group attached to an aromatic nucleus that are water soluble or water dispersible or water dissipatable determined to be at or greater than 0.5 weight % concentration (i.e. monomer in water). Such monomers are well known to those skilled in the art and include such monomers as the lithium and sodium salts of diethylene glycol diesters of 5-sulfoisophthalic acid, ethylene glycol diesters of 5-sulfoisophthalic acid, alkyl diesters of 5-sulfoisophthalic acid, aryl diesters of 5-sulfoisophthalic acid, and 5-sulfoisophthalic acid. Other monomers include salts of phenolsulfonates, alkoxybenzenesulfonates, and aryloxybenzenesulfonates. The solvents chosen were ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, diethylene glycol methyl ether (*Eastman* DM Solvent), diethylene glycol ethyl ether (*Eastman* DE Solvent), diethylene glycol propyl ether (*Eastman* DP Solvent), diethylene glycol butyl ether (*Eastman* DB Solvent), ethylene glycol propyl ether (*Eastman* EP Solvent), and ethylene glycol butyl ether (*Eastman* EB Solvent). In a screening study, solutions were attempted for each of the monomer and solvent pairings at 10, 20, and 30 wt% solids. These stock solutions were prepared by adding the solvent to a round-bottomed flask with an agitator, condenser, and nitrogen source connected. The appropriate amount of the monomer was then added, and the mixture was heated with agitation until the solution was obtained.

The tables include description of the cleaning composition by weight % of the components and the cleaning conditions employed to test effectiveness of the cleaning process. The term "Clean" means complete removal of photoresist resin by visual inspection, "Not Clean" means partial removal of photoresist resin by visual

inspection, and "No Change" means no indication that photoresist resin was attacked under process conditions by visual inspection. Solutions of the sodium salt of the diethylene glycol diester of 5-sulfoisophthalic acid (I) in diethylene glycol (DEG) are used to illustrate the invention in the following examples. Example 3 illustrates the use of other 5-sulfoisophthalic monomers.

Example 1

Table 2 contains the results from a cleaning study conducted for Novolac resin coated as described in Table 1. Resin was cured for 15 minutes at 200 degrees C. Process temperatures for the cleaning stage were 100 degrees C, 150 degrees C, and 200 degrees C.

Table 2

Solution (wt%)			Process Conditions			
I	DEG	DE Solvent	150°C for 60s	150°C for 90s	200°C for 30s	200°C for 60s
29.64%	70.36%	0.00%	Not Clean	Clean	Not Clean	Clean
15.96%	84.04%	0.00%	Not Clean	Clean	Not Clean	Not Clean
25.08%	74.92%	0.00%	Clean	Clean	Clean	Clean
15.96%	38.04%	46.00%	Not Clean	Clean	Not Clean	Not Clean
25.08%	59.92%	15.00%	Not Clean	Clean	Not Clean	Not Clean

I - Sodium salt of the diethylene glycol diester of 5-sulfoisophthalic acid

DEG - Diethylene glycol

DE Solvent - Diethylene glycol ethyl ether

Example 2

Table 3 contains the results from a cleaning study conducted for Phost resin coated as described in Table 1. Resin was cured for 15 minutes at 200 degrees C. All cleaning compositions are comprised of 6 wt% sulfopolyester, 24 wt% DE Solvent, with the remaining 70 wt% being comprised of two additives as noted in Table 4. Process temperatures for the cleaning stage were 100 degrees C, 150 degrees C, and 200 degrees C.

Table 3

Solution (wt%)			Process Conditions		
I	DEG	DE Solvent	100°C for 30s	100°C for 60s	150°C for 60s
29.64%	70.36%	0.00%	Clean	Clean	Clean
15.96%	84.04%	0.00%	Clean	Clean	Clean
25.08%	74.92%	0.00%	Clean	Clean	Clean
15.96%	38.04%	46.00%	Clean	Clean	Clean
25.08%	59.92%	15.00%	Clean	Clean	Clean

I - Sodium salt of the diethylene glycol diester of 5-sulfoisophthalic acid

DEG – Diethylene glycol

DE Solvent – Diethylene glycol ethyl ether

Examples 1 and 2 demonstrate the general utility of invention in cleaning cured novolac and polyhydroxystyrene resins from silica wafers. In the case of polyhydroxystyrene resin (Example 2), all cleaning compositions were effective in removing cured resin using cleaning conditions of 100-150°C from 30 to 60 seconds. For novolac resins (Example 1), cleaning required process temperatures greater than 100°C to achieve satisfactory removal of resin although some removal is noted under all reported conditions. In both examples, it was found resins could be removed by compositions containing DE solvent. Addition of such solvent could benefit the management of viscosity as needed to utilize the invention in various coating process steps.

Example 3

Table 4 contains the results from a cleaning study conducted to test compositions containing 20 weight percent 5-sodiosulfoisophthalic acid (SSIPPA), 5-lithiosulfoisophthalic acid (LiSIPA), the ethylene glycol diester of 5-sodiosulfoisophthalic acid (EGSIPA diester), and the diethylene glycol ethyl ether diester of 5-sodiosulfoisophthalic acid (DESIPA diester) as cleaning compositions to remove novolac and polyhydroxystyrene resins. Resins were cured for 15 minutes at 200 degrees C. Process temperatures for the cleaning stage were 100 degrees C for 60 seconds.

Table 4

Monomer	Wt% Monomer	Solvent	Novolac	Phost
SSIPA	20	Diethylene glycol	No Change	No Change
LiSIPA	20	Diethylene glycol	Not Clean	Clean
EGSIPA diester	20	ethylene glycol	No Change	Clean
DESIPA diester	20	Diethylene glycol ethyl ether	Not Clean	Clean

The data in Table 4 indicates compositions of ethylene glycol, diethylene glycol and diethylene glycol ethers containing lower molecular weight monomeric salts of 5-sulfosulfonic acid and related esters perform well as cleaning compositions to Phost resin, but little success cleaning novolac resin.

Example 4

Table 5 contains the results from a cleaning study conducted for polyimide resin coated as described in Table 1. Resin was cured for 15 minutes at 150 degrees C. Process temperatures for the cleaning stage were 100 degrees C, 150 degrees C, and 200 degrees C at various durations of time. Results are tabulated below.

Table 5

Solution (wt%)						Process Conditions		
I	DEG	DE Solvent	2-Pyrolle	MEA	KTB	150°C for 90s	200°C for 30s	200°C for 60s
8.89%	21.11%	0.00%	28.00%	35.00%	7.00%	No Change	Not Clean	Not Clean
4.79%	25.21%	0.00%	28.00%	35.00%	7.00%	No Change	Not Clean	Clean
7.52%	22.48%	0.00%	28.00%	35.00%	7.00%	No Change	Clean	Not Clean
4.79%	11.41%	13.80%	28.00%	35.00%	7.00%	No Change	Not Clean	Not Clean
7.52%	17.98%	4.50%	28.00%	35.00%	7.00%	No Change	No Change	Not Clean

- I – Sodium salt of the diethylene glycol diester of 5-sulfoisophthalic acid
 15 DEG – Diethylene glycol
 DE Solvent – Diethylene glycol ethyl ether
 MEA – monoethanolamine
 KTB – potassium tert-butoxide

Example 4 suggests that cured polyimide resin is more difficult to clean than either Phost or novolac resin. Only the use of highly basic materials such as 2-pyrrolle, MEA and KTB in the additive component produced desirable results on low temperature cleaned wafers. No evidence of attack is noted unless the temperature of the cleaning process is elevated to 200°C.

Example 5

Table 6 contains the results from a cleaning study conducted for acrylic resin coated as described in Table 1. Resin was cured for 15 minutes at 150 degrees C. Process temperatures for the cleaning stage were 100 degrees C, 150 degrees C, and 200 degrees C. Results are tabulated below.

Table 6

Solution (wt%)						Process Conditions		
I	DEG	DE Solvent	2-Pyrrolle	MEA	KTb	150°C for 90s	200°C for 30s	200°C for 60s
8.89%	21.11%	0.00%	28.00%	35.00%	7.00%	No Change	Not Clean	Not Clean
4.79%	25.21%	0.00%	28.00%	35.00%	7.00%	No Change	Not Clean	Clean
7.52%	22.48%	0.00%	28.00%	35.00%	7.00%	No Change	Clean	Not Clean
4.79%	11.41%	13.80%	28.00%	35.00%	7.00%	No Change	Not Clean	Not Clean
7.52%	17.98%	4.50%	28.00%	35.00%	7.00%	No Change	No Change	Not Clean

I - Sodium salt of the diethylene glycol diester of 5-sulfoisophthalic acid

15 DEG - Diethylene glycol

DE Solvent - Diethylene glycol ethyl ether

MEA - monoethanolamine

KTb - potassium tert-butoxide

20 Example 5 suggests that cured acrylic resin is more difficult to clean than either Phost or novolac resin but requires conditions similar to polyimide resin for satisfactory removal of resin.

Example 6

25 Table 7 contains the results from a cleaning study conducted for Isoprene resin coated as described in Table 1. Wafers were cured for 15 minutes at 150 degrees C.

Process temperatures for the cleaning stage were 100 degrees C, 150 degrees C, and 200 degrees C.

Table 7

5

Solution (wt%)				Process Conditions			
Solids	DEG	Aromatic-100	DDBSA	100°C for 60s	100°C for 90s	150°C for 60s	150°C for 90s
2.74%	3.27%	56.40%	37.60%	Some Clean	Clean	Clean	Clean
6.84%	8.17%	51.00%	34.00%	Some Clean	Clean	Clean	Clean
9.12%	10.89%	48.00%	32.00%	Some Clean	Clean	Clean	Clean

I - Sodium salt of the diethylene glycol diester of 5-sulfoisophthalic acid

DEG - Diethylene glycol

DE Solvent - Diethylene glycol ethyl ether

- 10 The cleaning compositions presented in Example 6 were designed to be specifically hydrophobic (hydrocarbon) in order to allow penetration of the cleaning composition into the resin. The compositions shown here represent key conditions that are necessary to affect proper performance.

15 Example 7

To further illustrate the method of the invention, wafers having a cured photoresist layer as described above were coated with formulations described in art as useful for removing photoresist by a typical bath or soaking dissolution process.

- 20 Formulations were prepared according to Table 8 and applied to isoprene coated wafer pieces cured 15 minutes at 150°C per Table 1. The wafer pieces were immediately heated to the target temperature for 60 seconds, and rinsed with water. The effectiveness of photoresist removal was judged by visual inspection.

Table 8: Cleaning Results for Isoprene Resin

Additive A	Additive B	Additive A:B wt% Concentrations	95°C	125°C	150°C
¹ Aromatic 100 Fluid	² DDBSA	50:50	Partial Clean	Not Clean	Partial Clean
¹ Aromatic 150 Fluid	² DDBSA	50:50	Partial Clean	Partial Clean	Partial Clean
¹ Aromatic 200 Fluid	² DDBSA	50:50	Clean	Partial Clean	Partial Clean

¹Aromatic 100 Fluid, Aromatic 150 Fluid and Aromatic 200 Fluid from ExxonMobil Chemical

²DDBSA – dodecylbenzenesulfonic acid

5

Example 8

Formulations were prepared according to Table 9 and applied to acrylic coated wafer pieces cured 15 minutes at 150°C per Table 1. The wafer pieces were immediately heated to the target temperature for 60 seconds, and rinsed with water.

10 The effectiveness of photoresist removal was judged by visual inspection.

Table 9: Cleaning Results for Acrylic Resin

Additive A (%)	Additive B (%)	Additive C (%)	Additive D (%)	95°C	125°C	150°C
¹ DGA (60)	² HA(40)	-	-	Partial Clean	Partial Clean	Clean
³ MEA (60)	HA (40)	-	-	Clean	No Clean	No Clean
⁴ AEEA (60)	HA (30)	Water (10)	-	Partial Clean	Partial Clean	Partial Clean
AEEA(35)	MEA(25)	HA(30)	Water (10)	Partial Clean	Partial Clean	Partial Clean
DGA (40)	⁵ NMP(20)	HA(40)	-	Clean	Partial Clean	Partial Clean
MEA (40)	NMP(20)	HA(40)	-	Partial Clean	Partial Clean	Partial Clean
AEEA(40)	NMP(20)	HA(30)	Water (10)	Clean	Partial Clean	No Clean
AEEA(25)	MEA(15)	NMP(20)	HA(40)	No Clean	No Clean	No Clean
DGA (40)	⁶ DMAC(20)	HA(40)	-	Clean	Clean	Clean
MEA (40)	DMAC(20)	HA(40)	-	Clean	Partial Clean	Clean
AEEA(40)	DMAC(20)	HA(30)	Water (10)	Partial Clean	No Clean	No Clean
AEEA(25)	MEA(15)	DMAC(20)	HA(40)	Clean	No Clean	No Clean
⁷ DMSO(70)	HA(30)	-	-	Clean	Partial Clean	Partial Clean
DMSO(86)	⁸ DEGEE(6)	AEEA	⁹ TMAH	Clean	Clean	Partial Clean
DMSO(88)	MEA(6)	TMAH(6)		Partial Clean	Partial Clean	Partial Clean

¹DGA – diglycolamine²HA – 50% hydroxylamine in water³MEA – monoethanolamine5 ⁴AEEA - N-(2-aminoethyl)ethanolamine⁵NMP - N-methyl 2-pyrrolidinone⁶DMAC – N,N-dimethyl acetamide⁷DMSO – dimethylsulfoxide⁸DEGEE – Diethylene glycol ethyl ether10 ⁹TMAH – tetramethylammonium hydroxide

The data contained in Tables 8 and 9 indicate many different formulations may be used to effect photoresist removal according to the method of the invention. It should be noted that high temperatures will cause the formation of a water insoluble haze or crust in some cases. This can be mitigated by temperature optimization.

- 5 The invention has been described in detail with particular reference to preferred embodiments thereof, but it will be understood that variations and modifications can be effected within the spirit and scope of the invention.

Claims:

1. A composition for cleaning organic resin from inorganic substrates comprising:
 - a solvent or mixture of solvents; and
 - at least one monomer comprising a metal sulfonate salt of isophthalic acid, a metal sulfonate salt of a isophthalic acid diester, or a combination thereof where the sulfonate group is attached to the aromatic nucleus and the metal is selected from lithium, sodium, or potassium and mixtures thereof at a weight % of greater than 0.5%,
 - wherein the solvent is selected from the group consisting of ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, diethylene glycol ethyl ether, diethylene glycol methyl ether, diethylene glycol butyl ether, diethylene glycol propyl ether, ethylene glycol propyl ether, ethylene glycol butyl ether and mixtures thereof.
2. The composition according to claim 1, wherein the solvent is at a weight % of from 40% to 97%.
3. The composition according to claim 2, wherein the solvent is at a weight % of from 60% to 90%.
4. A method for removing organic resin from an inorganic substrate comprising,
 - (i) coating said organic resin with a stripping composition of claim 1,
 - (ii) heating the substrate to a temperature and for a time sufficient to achieve dissolution of the organic resin, and
 - (iii) rinsing the substrate with a volume of a rinsing agent sufficient to remove the composition and the organic resin;wherein said coating results in a layer of stripping composition on the substrate that is 1000 microns or less.

5. The method according to claim 4, wherein the stripping composition comprises:
 - a. an organic solvent or mixture of organic solvents at a weight % of from 0.5% to 99.0%, and
 - b. the monomer is at a weight % of from 0.5% to 99.0%,
6. The method according to claim 5, wherein the composition further comprises at least one additive which enhances cleaning performance at a weight % of from 0.01% to 99.0%;
7. The method according to Claim 6, wherein the solvent is at a weight % of from 40% to 97%, the monomer is at a weight % of from 2% to 59%, and the additive is at a weight % of from 1% to 50%.
8. The method according to claim 4, wherein the monomer is the diethylene glycol diester of 5-sodiosulfoisophthalic acid .
9. The method according to Claim 6, wherein the additive is selected from the group consisting of an ammonium hydroxide, a quaternary ammonium hydroxide, an amine, an alkanolamine, an elemental hydroxide, an elemental alkoxide, and mixtures thereof.

10. The method according to Claim 9, wherein the additive is selected from the group consisting of tetramethylammonium hydroxide, N-(2-aminoethyl)ethanolamine, tetraethylammonium hydroxide, benzyltrimethylammonium hydroxide, triethylene tetramine, monoethanolamine, monoisopropanolamine, diglycolamine, 1,2-diaminoethane, 1,3-diaminomethylbenzene, 1,3-diaminomethylcyclohexane, potassium tertiary butyl hydroxide, and mixtures thereof.
11. The method according to Claim 6, wherein the additive is methanesulfonic acid, p-toluenesulfonic acid, dodecylbenzene sulfonic acid, formic acid, sulfuric acid, nitric acid, phosphoric acid or a mixture thereof.
12. The method according to Claim 4, further comprising an inhibitor, a surfactant or both.
13. The method according to claim 4, wherein the substrate is heated to a temperature of between 25° C to 400° C.
14. The method according to claim 4, wherein the temperature of the rinsing agent is between 5° C and 100° C.
15. The method according to claim 4, wherein the organic resin comprises a positive-tone photoresist, a negative-tone photoresist, a multi-layer photoresist, or a chemically amplified photoresist.
16. The method according to claim 4, wherein the inorganic substrate comprises a semiconductive wafer, a flat panel display, or a printed circuit board.

17. The method according to claim 4, wherein said coating comprises spray coating, spin coating or slit coating.
18. The method according to claim 4, wherein the rinsing agent is water, acetone, isopropyl alcohol or mixtures thereof.