

LOW OPTICAL LOSS ELECTRODE STRUCTURES FOR LEDS

TECHNICAL FIELD

[0001] Embodiments of the present invention relate generally to light emitting diodes (LEDs). Embodiments of the present invention relate more particularly to electrode structures that mitigate optical losses and thus tend to enhance the brightness and/or the efficiency of LEDs.

BACKGROUND

[0002] Light emitting diodes (LEDs) for use as indicators are well known. LEDs have been used extensively for this purpose in consumer electronics. For example, red LEDs are commonly used to indicate that power has been applied to such devices as radios, televisions, video recorders (VCRs), and the like.

[0003] Although such contemporary LEDs have proven generally suitable for their intended purposes, they possess inherent deficiencies that detract from their overall effectiveness and desirability. For example, the light output of such contemporary LEDs is not as great as is sometimes desired. This limits the ability of contemporary LEDs to function in some applications, such as providing general illumination, e.g., ambient lighting. Even high power contemporary LEDs do not provide sufficient illumination for such purposes.

[0004] At least a part of this problem of insufficient brightness is due to inefficiency of contemporary LEDs. Efficiency of LEDs is a measure of the amount of light provided as compared to the electrical power consumed. Contemporary LEDs are not as efficient as they can be because some of the light generated thereby is lost due to internal absorption. Such internal absorption limits the amount of light that can be extracted from an LED and thus undesirably reduces the efficiency thereof.

[0005] Thus, although contemporary LEDs have proven generally suitable for their intended purposes, they possess inherent deficiencies which detract from their overall effectiveness and desirability. As such, it is desirable to provide LEDs that have enhanced brightness and/or efficiency.

BRIEF SUMMARY

[0006a] According to a first aspect, there is provided a reflective electrode structure comprising: an electrode; a semiconductor material configured to emit light about a central wavelength λ ; a dielectric material formed upon the semiconductor material; at least one DBR pair formed upon the dielectric material; and wherein a portion of the electrode is formed over both the dielectric material and the DBR pair(s) and another portion of the electrode is in ohmic contact with the semiconductor material.

[0006b] According to a second aspect, there is provided a reflective electrode structure comprising: a metal electrode; a GaN semiconductor material configured to emit light about a central wavelength λ ; silicon dioxide dielectric material formed upon the GaN material, the dielectric material having a thickness of approximately 1.75λ ; at least one DBR pair formed upon the silicon dioxide material; and wherein a portion of the electrode is formed over both the dielectric material and the DBR pair(s) and another portion of the electrode is in ohmic contact with the semiconductor material.

[0006c] According to a third aspect, there is provided a method for making an electrode structure, the method comprising: providing a semiconductor material that is configured to emit light about a central wavelength λ ; forming a dielectric material formed upon the semiconductor material; forming at least one DBR pair formed upon the dielectric material; forming a portion of an electrode over both the dielectric material and the DBR pair(s); and forming another portion of the electrode in ohmic contact with the semiconductor material.

[0006d] According to a fourth aspect, there is provided a method comprising: forming a portion of an electrode over both a dielectric material and at least one DBR pair; and forming another portion of the electrode in ohmic contact with a semiconductor material.

[0006e] According to a fifth aspect, there is provided a device comprising: means for emitting light; means for providing current flow to the means for emitting light; means for providing electrical insulation formed upon the means for emitting light; at least one DBR pair formed upon the means for providing electrical insulation; and wherein a portion of the means for providing current flow is formed over both the means for providing electrical insulation and the DBR pair(s) and another portion of the means for providing current flow is in ohmic contact with the means for emitting light.

[0006f] According to a sixth aspect, there is provided an electrode structure for an LED, the electrode structure comprising: a semiconductor material having an n-portion and a p-portion; a metal n-electrode in electrical communication with the n-portion; a metal p-electrode in electrical communication with the p-portion; an optically transmissive dielectric material formed to at least one of the n-electrode and the p-electrode so as to enhance reflection of light, the dielectric material having a thickness of approximately 1.75λ ; and wherein the semiconductor material, the n-electrode and the p-electrode cooperate to define a lateral LED structure.

[0006g] According to a seventh aspect, there is provided an electrode structure for a semiconductor LED, the electrode structure comprising: an electrode; and an optically transmissive dielectric material having an index of refraction greater than or equal to one and less than that of a semiconductor upon which the dielectric material is formed, the dielectric material being formed to the electrode so as to enhance reflection of light.

[0006h] According to an eighth aspect, there is provided an electrode structure for a semiconductor LED, the electrode structure comprising: a electrode; and an optically transmissive dielectric material having a thickness greater than $1/2 \lambda$, the dielectric material being formed to the electrode so as to enhance reflection of light.

[0006i] According to a ninth aspect, there is provided an electrode structure for a semiconductor LED, the electrode structure comprising: an electrode; and an optically transmissive dielectric material formed to the electrode and being porous enough to reduce the dielectric material's effective index of refraction such that total internal reflection occurs within the semiconductor material.

[0006j] According to a tenth aspect, there is provided an electrode structure for an LED, the electrode structure comprising: a semiconductor material having a cutout formed therein; an electrically insulating dielectric material; a metal electrode; wherein a portion of the electrode is formed outside of the cutout and a portion of the electrode is formed inside of the cutout; wherein the portion of the electrode outside the cutout is electrically isolated from the semiconductor material by the dielectric material; and wherein the portion of the electrode inside the cutout is in electrical contact with the semi conducting material.

[0006k] Systems and methods are disclosed herein to provide brighter and/or more efficient LEDs. For example, in accordance with an embodiment of the present invention, an LED can comprise a reflective electrode structure comprising a metal electrode.

[0007] More particularly, the electrode can be formed upon a semiconductor material that emits light having a central wavelength λ . This light is emitted in all directions. A comparatively thick, optically transmissive dielectric material can be formed upon the semiconductor material. A portion of the electrode can be formed over the comparatively thick dielectric material. Another portion of the same electrode can be in electric contact with the semiconductor material. The electrode cooperates with the thick dielectric to enhance reflection such that light emitted in the direction of the electrode is reflected back into the semiconductor material and thus has another opportunity to be extracted from the LED.

[0008] The term wavelength (λ), as used herein, refers to the wavelength of light inside of the material that the light is traveling within. Thus, if light within a semiconductor material is being referred to, for example, then the wavelength of this light is its wavelength within the semiconductor material.

[0009] The thick dielectric thickness can be greater than $\frac{1}{2} \lambda$, where λ is the Wavelength of light inside of the thick dielectric material. The thick dielectric material can have an index of refraction that is lower than that of the semiconductor material and that is greater than or equal 1.0. The light emitting semiconductor material can comprise AlGaAs, AlInGaP, AlInGaN, and/or GaAsP, for example. Other materials can similarly be suitable.

[0010] The optically transmissive thick dielectric layer can be a comparatively thick layer of material such as silicon dioxide, silicon monoxide, MgF_2 and siloxane polymers, and/or air, for example. Other materials can similarly be suitable.

[0011] There can be an ohmic contact layer between the metal electrode and the semiconductor. The ohmic contact layer can comprise indium tin oxide (ITO), nickel oxide, and/or RuO_2 , for example. Other materials can similarly be suitable. The ohmic contact layer can be part of the semiconductor device comprising of a heavily doped layer.

[0012] There can be a current spreading layer between the metal electrode and the semiconductor. The current spreading layer is composed of indium tin oxide, nickel oxide, RuO_2 , for example. Other materials can similarly be suitable.

[0013] A series of one or more pairs of DBR dielectric layers can be formed between the thick dielectric layer and the metal electrode such that each DBR dielectric layer of this pair can be optically transmissive, of different indices of refraction from each other, and/or odd multiples of about $\frac{1}{4} \lambda$ thick.

[0014] Each layer of the pairs of DBR dielectric material can comprise titanium dioxide TiO_2 , Ti_3O_5 , Ti_2O_3 , TiO , ZrO_2 , $\text{TiO}_2\text{ZrO}_2\text{Nb}_2\text{O}_5$, CeO_2 , ZnS , Al_2O_3 , SiN niobium pentoxide (Nb_2O_5), tantalum pentoxide (Ta_2O_5), siloxane polymers SiO , SiO_2 , and/or MgF_2 , for example. Other materials can similarly be suitable.

[0015] The metal electrode can be comprise one or more metal layers, wherein each metal layer can be selected from a group consisting of Al, Ag, Rh, Pd, Cu, Au, Cr, Ti, Pt nickel/gold alloys, chrome/gold alloys, silver/aluminum mixtures and combinations thereof. Other materials can similarly be suitable.

[0016] The LED can have either a vertical or lateral structure. A portion of the metal electrode can form an area for wire bonding. A portion of the metal electrode can make an electrical contact to the semiconductor material at the edges of the thick dielectric material. A portion of the metal electrode makes an

electrical contact to the semiconductor material through openings in the thick dielectric material.

[0017] According to one embodiment of the present invention, a reflective electrode structure for an LED comprises a metal electrode. A GaN material emits light about some central wavelength λ . A comparatively thick silicon dioxide material can be formed upon the GaN material. A portion of the electrode can be formed over the thick dielectric material. Another portion of the same electrode can be in ohmic contact with a semiconductor material. The thick dielectric can have a thickness greater than $1/2 \lambda$. Both the dielectric material and the metal electrode can make physical contact to the semiconductor via an ITO layer or other materials than can be similarly suitable.

[0018] According to one embodiment of the present invention, a reflective electrode structure comprises a metal electrode and a GaN material emits light about some central wavelength λ . A thick silicon dioxide material can be formed upon the GaN material. A series of at least one DBR pair can be formed upon the thick silicon dioxide material.

[0019] A portion of the electrode can be formed over both the thick dielectric material and the DBR pairs. Another portion of the same electrode can be in ohmic contact with the semiconductor material. The thick dielectric thickness can be greater than $1/2 \lambda$.

[0020] Each layer of the DBR pairs can be optically transmissive, of different indices of refraction with respect to one another, and can be odd multiples of about $1/4 \lambda$ in thickness. Both the thick dielectric and the metal electrode can make physical contact to the semiconductor via an ITO layer.

[0021] Thus, according to one or more embodiments of the present invention a brighter and/or more efficient LED can be provided. Increasing the brightness and/or efficiency of LED enhances their utility by making them more suitable for a wider range of uses, including general illumination.

[0022] This invention will be more fully understood in conjunction with the following detailed description taken together with the following drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0023] Figure 1 is a schematic diagram showing the concept of critical angle;

[0024] Figure 2 is a semi-schematic perspective view of a contemporary lateral LED structure;

[0025] Figure 3 is a semi-schematic perspective view of a contemporary vertical LED structure;

[0026] Figure 4A is a semi-schematic diagram showing light reflection at a contemporary GaN/Cr/Au interface;

[0027] Figure 4B is a chart showing reflectivity at the GaN/Cr/Au interface of Figure 4A for different angles of incidence;

[0028] Figure 5A is a semi-schematic diagram showing a contemporary electrode structure having an ohmic contact layer;

[0029] Figure 5B is a semi-schematic diagram showing a contemporary electrode structure having an ohmic contact/current spreading layer;

[0030] Figure 6A is a semi-schematic top view of a portion of a contemporary LED die showing a circular contact that can also function as a bond pad;

[0031] Figure 6B is a semi-schematic top view of a portion of a contemporary LED dice showing a cross shaped contact with a circular bond pad;

[0032] Figure 6C is a semi-schematic top view of a portion of a contemporary LED dice showing exemplary contact geometry that is suitable for

use with larger LEDs and having a circular contact that can also function as a bonding pad;

[0033] Figure 7A is a semi-schematic side view of a contemporary low aspect ratio electrode structure;

[0034] Figure 7B is a semi-schematic side view of a high aspect ratio electrode structure;

[0035] Figure 8A is a semi-schematic diagram showing light reflection at a contemporary Ag interface;

[0036] Figure 8B is a chart showing reflectivity at the Ag interface of Figure 8A for different angles of incidence;

[0037] Figure 9A is a semi-schematic diagram showing light reflection at a contemporary GaN/SiO₂/Ag interface of a vertical structure LED;

[0038] Figure 9B is a chart showing reflectivity at the GaN/SiO₂/Ag interface of Figure 9A for different angles of incidence;

[0039] Figure 10A is a semi-schematic diagram showing light reflection at a contemporary GaN/air interface;

[0040] Figure 10B is a chart showing reflectivity at the GaN/air interface of Figure 10A for different angles of incidence;

[0041] Figure 11A is a semi-schematic diagram showing light reflection at a GaN/SiO₂ interface, wherein the thick dielectric is thick according to an embodiment of the present invention;

[0042] Figure 11B is a chart showing reflectivity at the GaN/SiO₂ interface of Figure 11A for different angles of incidence;

[0043] Figure 12A is a semi-schematic diagram showing light reflection at a GaN/SiO₂/Al interface according to an embodiment of the present invention;

[0044] Figure 12B is a chart showing reflectivity at the GaN/SiO₂/Al interface of Figure 12A for different angles of incidence wherein thicknesses of the SiO₂ layer are less than or equal to $\frac{1}{4}$ the wavelength of incident light according to an embodiment of the present invention;

[0045] Figure 12C is a chart showing reflectivity at the GaN/SiO₂/Al interface of Figure 12A for different angles of incidence wherein thicknesses of the SiO₂ layer are greater than $\frac{1}{4}$ the wavelength of incident light according to an embodiment of the present invention;

[0046] Figure 13A is a semi-schematic diagram showing light reflection at a distributed Bragg reflector (DBR) comprised of alternating layers of SiO₂ and TiO₂ according to an embodiment of the present invention;

[0047] Figure 13B is a chart showing reflectivity at the DBR layers of Figure 13A for different angles of incidence according to an embodiment of the present invention;

[0048] Figure 14 is a chart showing reflectivity of several materials for different angles of incidence according to an embodiment of the present invention;

[0049] Figure 15A is a semi-schematic diagram showing a first exemplary embodiment of a suspended electrode according to the present invention;

[0050] Figure 15B is a semi-schematic diagram showing a second exemplary embodiment of a suspended electrode according to the present invention;

[0051] Figure 15C is a semi-schematic diagram showing a third exemplary embodiment of a suspended electrode according to the present invention;

[0052] Figure 15D is a semi-schematic diagram showing a fourth exemplary embodiment of a suspended electrode according to the present invention;

[0053] Figure 15E is a semi-schematic diagram showing a fifth exemplary embodiment of a suspended electrode according to the present invention;

[0054] Figure 15F is a semi-schematic diagram showing a sixth exemplary embodiment of a suspended electrode according to the present invention;

[0055] Figure 16A is a semi-schematic diagram showing a first exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention;

[0056] Figure 16B is a semi-schematic diagram showing a second exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention;

[0057] Figure 16C is a semi-schematic diagram showing a third exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention;

[0058] Figure 16D is a semi-schematic diagram showing a fourth exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention;

[0059] Figure 16E is a semi-schematic diagram showing a fifth exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention;

[0060] Figure 16F is a semi-schematic diagram showing a sixth exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention;

[0061] Figure 17A is cross-section view of a contemporary lateral structure LED;

[0062] Figures 17B-17D are semi-schematic perspective views showing some steps in the process for fabricating the LED of Figure 17A;

[0063] Figure 18A is cross-section view of a lateral structure LED according to an embodiment of the present invention;

[0064] Figures 18B-18E are semi-schematic perspective views showing some steps in the process for fabricating the LED of Figure 18A;

[0065] Figure 19A is cross-section view of a lateral structure LED according to an embodiment of the present invention;

[0066] Figures 19B-19E are semi-schematic perspective views showing some steps in the process for fabricating the LED of Figure 19A;

[0067] Figure 20A is a semi-schematic perspective view showing another embodiment of suspended structure according to an embodiment of the present invention;

[0068] Figure 20B is a semi-schematic perspective view showing another embodiment of suspended structure according to an embodiment of the present invention;

[0069] Figure 21A is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0070] Figure 21B is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0071] Figure 22A is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0072] Figure 22B is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0073] Figure 22C is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0074] Figure 23A is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0075] Figure 23B is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED;

[0076] Figure 23C is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED; and

[0077] Figure 24 is a semi-schematic diagram showing an exemplary embodiment of the present invention in an elongated LED.

[0078] Embodiments of the present invention and their advantages are best understood by referring to the detailed description that follows. It should be appreciated that like reference numerals are used to identify like elements illustrated in one or more of the figures.

DETAILED DESCRIPTION

[0079] Light emitting devices (LEDs) emit light in response to excitation by an electrical current. One typical LED has a heterostructure grown on a substrate by metal-organic vapor phase epitaxy or a similar technique. An LED heterostructure includes n-type and p-type semiconductor layers that sandwich a light producing layer, i.e., an active region. Exemplary active areas may be quantum wells surrounded by barrier layers. Typically, electrical contacts are attached to the n-type and p-type semiconductor layers. When a forward bias is applied across the electrical contacts electrons and holes flow from n-type and p-type layers to produce light in the active region. Light is produced according to well known principles when these electrons and holes recombine with each other in the active region.

[0080] The efficiency with which a LED converts electricity to light is determined by the product of the internal quantum efficiency, the light-extraction efficiency, and losses due to electrical resistance. The internal quantum efficiency is determined by the quality of the semiconductor layers and the energy band structure of the device. Both of these are determined during deposition of the semiconductor layers.

[0081] The light extraction efficiency is the ratio of the light that leaves the LED chip to the light that is generated within the active layers. The light extraction efficiency is determined by the geometry of the LED, self-absorption of light in semiconductor layers, light absorption by electrical contacts, and light absorption by materials in contact with the LED that are used to mount a device in a package.

[0082] Semiconductor layers tend to have relatively high indices of refraction. Consequently, most of the light that is generated in the active region of an LED is internally-reflected by surfaces of a chip many times before it escapes. To achieve high light-extraction efficiency it is important to minimize absorption of light by the semiconductor layers and by electrical connections to the chip. When these layers are made to have very low optical absorption, by being transparent or highly reflective, the overall light extraction in an LED is improved substantially.

[0083] Referring now to Figure 1, light inside of a high index of refraction medium 11 is incident at interface to a lower index of refraction medium 12. The light can be incident at different angles. When light from a high index of refraction medium 11 encounters the interface to a lower index of refraction medium 12 the light can either be transmitted into the lower index of refraction medium 12 or be reflected back into the higher index of refraction medium 11.

[0084] According to Snell's law, a portion of the light traveling from a material having an index of refraction n_1 into a material having a lower index of refraction n_2 at an angle less than the critical angle Θ_c will pass into the lower index of refraction material. This is indicated by the arrow on the left that continues from the material having the lower index of refraction n_1 into the material having the higher index of refraction n_2 .

[0085] Conversely, according to Snell's law, all of the light traveling from a material having a higher index of refraction n_1 toward a material having a lower index of refraction n_2 at an angle greater than the critical angle Θ_c will be reflected back into the higher index of refraction material. This mechanism is known as total internal reflection (TIR) and is indicated by the arrow on the right that does not

continue from the material having the higher index of refraction n_1 into the material having the lower index of refraction but the arrow rather extends back through the material having the higher index of refraction.

[0086] Light within a material having a higher index of refraction than exists outside of the material (such as light within a semiconductor material where air or an encapsulating epoxy is the outside material) which is incident upon the interface surface at angles greater than Θ_c will experience total internal reflection. Typical semiconductor materials have a high index of refraction compared to ambient air (which has an index of refraction of 1.0), or encapsulating epoxy (which can have an index of refraction of approximately 1.5).

[0087] In an LED, this light is reflected back into the LED chip where further absorption can undesirably occur from other materials. This undesirable absorption reduces the efficiency of the LED by reducing the amount of light that the LED provides.

[0088] For conventional LEDs, the vast majority of light generated within the structure suffers total internal reflection before escaping from a semiconductor chip. In the case of conventional Gallium Nitride (GaN) based LEDs on sapphire substrates, about 70% of emitted light can be trapped between the sapphire substrate and the outer surface of the GaN. This light is repeatedly reflected due to total internal reflection, thus suffering multiple absorptions by the metal electrodes and the other materials. It is thus desirable to create structures that tend to minimize this absorption.

[0089] As used herein, the term electrode can refer to a conductor (such as a metal conductor) that supplies current to a semiconductor material of an LED. Thus, an electrode can be in electrical contact with the semiconductor material. However, not all portions of an electrode are necessarily in contact with the semiconductor material. Indeed, according to one or more embodiments of the present invention, a portion of an electrode is in electrical contact with the

semiconductor material and another portion of an electrode is not in electrical contact with the semiconductor.

[0090] Referring now to Figure 2, a contemporary lateral structure LED is shown. Regions on the surface of a p-layer 21 and an n- layer 22 of an LED 20 can be metallized so as to form electrodes 23 and 24. p-n junction or active region 26 is between p-layer 21 and an n- layer 22. Electrodes 23 and 24 provide a means to provide electrical power to LED 20. For device structures where the semiconductor is supported by an optically transparent, electrically non-conductive substrate 23, comprised of a material such as sapphire, the electrical contact to p-layer 21 and n-layer 22 must be made from the top surface.

[0091] In the configuration shown in Figure 2, p-layer 21 is already exposed at top surface and electrical contact can be readily made therewith. However n-layer 22 is buried beneath both p-layer 21 and active region 26. To make electrical contact to n-layer 22, a cutout area 28 is formed by removing a portion of p-layer 21 and active layer 26 (the removed portion is indicated by the dashed lines) so as to expose n-layer 24 therebeneath. After the creation of cutout area 28, the n-layer electrical contact or electrode 24 can be formed.

[0092] Such device structures as that shown in Figure 2 result in the current flowing generally in the lateral direction. This is why they are referred to as lateral structures. One disadvantage of such lateral structures is that a portion of the active light producing region must be removed to produce the cutout structure 28 so the n-electrode 24 can be formed. Of course, this reduces the active region area and consequently reduces the ability of LED 20 to produce light.

[0093] Referring now to Figure 3, an LED 30 can alternatively comprise structures where the semiconductor (comprised of a p-layer 31 and an n-layer 32 that cooperate to define an active region 36) is supported by an electrically conductive substrate 37. Substrate 37 can be formed of an optically transparent conductive material such as silicon carbide or can be formed of an optically non-transparent, electrically conductive substrate such as copper or molybdenum.

Such LEDs can be configured to have either the n-layer, or p-layer in contact with the substrate.

[0094] In such LEDs, electrically conductive substrate 37 serves as one electrode while the other electrode 33 can be readily formed on the top surface, e.g. p-layer 31. Since the contacts or electrodes are on opposing surfaces of LED 30, current flow is in a generally vertical direction. Such devices are thus referred to as vertical structures.

[0095] Regardless of whether the metal electrodes are for vertical or lateral LED structures, they must satisfy similar requirements. These requirements include good adhesion, the ability to make ohmic contact to the semiconductor, good electrical conductivity, and good reliability. Often, these requirements are satisfied by using two or more layers. For example a first layer of metal such as chromium or titanium can provide good adhesion and ohmic contact. A second layer of metal such as silver or gold can provide good electrical conductivity.

[0096] Although chromium has good adhesion and gold is a good electrical conductor. Neither material has good optical reflectivity in the visible region. The optical reflectivity and the corresponding optical absorption can be calculated from the refractive indices of these structures and their corresponding thicknesses.

[0097] Where a material thickness has not been given herein, the thickness can be assumed to be great enough such that optical interference effects are not an issue. For example, such reflectivity calculations typically assume the incident and exit medium to be semi-infinite. In cases of metal reflector layers where their thickness have not been specified, they are assumed to be thick enough, typically a few thousand nanometers, so that an insignificant amount of light reaches the other surface of the metal. The refractive index values of Table 1 are used to calculate all reflectivity curves in this disclosure.

[0098]

Dielectric Material	Abbreviation	Wavelength	Refractive Index	Refractive Index
---------------------	--------------	------------	------------------	------------------

		(nm)	(Real)	(Imaginary)
Aluminum	Al	450	0.49	-4.7
Titanium Dioxide	TiO ₂	450	2.57	-0.0011
Silicon Dioxide	SiO ₂	450	1.465	0
Air	Air	450	1	0
Gold	Au	450	1.4	-1.88
Chromium	Cr	450	2.32	-3.14
Indium Tin Oxide	ITO	450	2.116	-0.0047
Titanium	Ti	450	2.27	-3.04
Silver *	Ag	450	0.132	-2.72
Gallium Nitride	GaN	450	2.45	
Nano Porous Silicon Dioxide	SiO ₂ _Nano	633	1.1	0
Titanium Dioxide	TiO ₂	633	2.67	0
Gallium Phosphide	GaP	633	3.31	0
Silicon Dioxide	SiO ₂	633	1.456	0

Table 1

[0099] The thickness of materials as referenced in this disclosure can be in absolute units, T_{ABS} , such as microns (μm) or nanometers (nm). Alternatively, the thickness of material can be given relative to the number of wavelengths in the medium, T_{1Rel} . When given as the number of wavelengths (λ), the parameter specifically refers to the wavelength of light within the material itself. This can be converted to the absolute thickness by multiplying by the index of refraction of the material (N) as indicated by Equation 1 below. For example a $\frac{1}{4} \lambda$ of SiO₂ at 450 nm would be 76.8 nm ($0.25 \cdot 450 / 1.465$).

[00100]
$$T_{\text{ABS}} = (T_{\lambda, \text{Rel}} / N) \cdot \lambda \quad (\text{Equation 1})$$

[00101] The optically reflectivity curve as a function of incident angle has two components, i.e., P-polarized light and S-polarized light. P-polarized light experiences Brewster's angles and has a lower overall reflectivity than S-polarized light.

[00102] Referring now to Figure 4A, a diagram of a contemporary semiconductor and electrode structure showing the reflectivity of an electrode 44 for light originating within the semiconductor 41 is provided. The electrode utilizes a typical chromium 42 and gold 43 electrode configuration and is formed upon a GaN semiconductor 41. For a reflection at an incident angle of 45 degrees, an average of only 25% of the P-polarized and S-polarized light is reflected while, 75% of the light is absorbed. Thus, this contemporary configuration is undesirably highly absorbing.

[00103] Although Figure 4A shows a gold/chromium metal electrode structure formed upon GaN, other metals and semiconductor materials can alternatively be utilized.

[00104] Referring now to Figure 4B, a chart shows reflectivity at the GaN/Cr/Au interface of the device of Figure 4A for different angles of incidence.

[00105] Referring now to Figure 5A, a more generic contemporary contact structure is shown. According to this more generic contact structure, there may be an ohmic contact and/or current spreading layer 52 between a metal contact 53 and a semiconductor material 51. The metal contact 53 may have multiple layers for purposes for adhesion, diffusion barrier, solder, electrical conductivity, and ohmic contact. The layers can be fabricated from various metals and combinations of metals, including nickel, platinum, titanium, silver, aluminum, gold, tin, lead, and chromium. The semiconductor material 51 can be from the material systems such as AlGaAs, AlInGaP, AlInGaN, and GaAsP. The ohmic contact layer can be part of the metal electrode layers such as nickel oxide.

[00106] Referring now to Figure 5B, an electrically conductive metal oxide such as indium tin oxide or nickel oxide can be deposited on entire surface of semiconductor 55 to define an ohmic contact/current spreading layer 56 upon which metal electrode 57 can be formed. In such a case, layer 56 serves both as an ohmic contact and current spreading layer. There can be a layer that allows for ohmic contact on the very top of the LED semiconductor material, such as a heavily doped region.

[00107] Regardless of the exact metal electrode configuration, semiconductor material or LED structure, contemporary metal electrodes undesirably absorb some light. In addition, metal contacts are not transparent, they block the available surface area where light can escape. Thus, such contemporary electrodes have a double effect. They not only directly absorb a portion of the incident light, but the remaining reflected light is directed back into the device where it suffers further absorption by other materials. The total amount of absorption is highly dependent on the exact configuration of the electrode and tends to scale proportionally to the size of the electrode contact area.

[00108] Referring now to Figures 6A-6C, the principle of current spreading so as to mitigate the problem of current crowding is discussed. The p-layer and n-layer of contemporary LEDs are thin and have relatively low electrical conductivity. By themselves, these layers do not evenly distribute current to all regions of the p-n junction, i.e., the active region. For larger areas where portions of the active region are far away from the electrode, there will be less current flow in these distant areas than in areas close to the metal contact. This results in uneven current distribution and consequent uneven light emission. To reduce current crowding, the geometry of the metal electrodes is extended over the semiconductor surface. These extensions however lead to additional undesirable light absorption.

[00109] With particular reference to Figure 6A, a circular contact or electrode 62 can be formed upon a semiconductor 61 and can serve as a wire bond pad. With particular reference to Figure 6B, a cross shaped contact 63 can be

combined with electrode 62 to enhance current spreading. With particular reference to Figure 6C, various other geometrical structures 63 can similarly be combined with electrode 62 to facilitate current spreading, especially on larger LED dies.

[00110] Typically, wire bonds are used as a means to provide electric power the LED. However the wire bond pad areas must be some minimum size of about $100\mu\text{m}$ by $100\mu\text{m}$. Since the size of each wire bond pad is fixed regardless of device size, the absorbing and opaque wire bond areas can be a significant portion of the overall surface area and for some LED devices.

[00111] One method for reducing the undesirable absorption of light by an electrode is to minimize the contact area or the width of the electrode. If electrical connection to the LED semiconductor material is the only consideration, then the contact width can be quite narrow, such as on the order of a few microns. However, an important consideration is the undesirable increase of electrical resistivity caused by decreasing the cross sectional area. In high power applications, the electrode may carry an amp or more of current. This requires the cross sectional area, width (W) x thickness (T) to be of some minimum value to minimize electrical resistance. Thus, the contact area or width of the electrode cannot merely be reduced without otherwise compensating for the increase in resistivity of the electrode.

[00112] Referring now to Figure 7A, a typical dimension for a gold electrode is $W=20\mu\text{m}$ and $T=2\mu\text{m}$ for a total cross sectional area of $40\mu\text{m}^2$. Theoretically, one could keep a constant cross sectional area and therefore a constant electrical resistance by proportionally increasing thickness while decreasing the width as discussed with reference to Figure 7B below.

[00113] Referring now to Figure 7B, according to one embodiment of the present invention the aspect ratio of electrode 77 can be increased. That is, the height of electrode 77 can be increase as compared to the width thereof. For example, the height can be increase so as to provide a thickness greater than 2.5

μm. In this manner, the area of electrode 74 that is in contact with semiconductor 75 (and is thus available for light absorption) is reduced and light absorption is consequently similarly reduced. Increasing the height of electrode 77 desirably maintains its conductivity. The contact area has been decreased and the thickness of the electrode has been increased so as to maintain desired conductivity. However manufacturing cost and practical process considerations typically limit electrode thickness to 2.5 μm or below. Thus the electrode contact area and its associated absorption become much greater than would be necessary if the electrode was used for only electrical contact to the semiconductor material.

[00114] Another method for reducing electrode absorption is to increase the reflectivity of the electrode. Several prior art approaches have been used to create reflective electrodes for LEDs. The simplest is to use a metal that has a high reflectivity. These include Al, Ag, Re and others known to one familiar with the art.

[00115] The chosen metal needs to not only have a high reflectance, but must also make an acceptably low resistance ohmic contact to the semiconductor material. In the case of p-type AlInGaN, only Ag combines low electrical resistance with high reflectivity.

[00116] Referring now to Figure 8A, an electrode structure comprised of Ag is shown. That is, an Ag electrode 82 is formed upon a semiconductor substrate 81. Unfortunately, Ag presents a reliability concern because it is subject to tarnish and it is subject to electromigration during device operation. Also, the contact resistance of Ag-based contacts sometimes increases with time during device operation.

[00117] Referring now to Figure 8B, the reflectance of the Ag electrode of Figure 8A for different angles of incidence is shown. Even with a highly reflective metal electrode, silver, the absorption per reflection near normal incidence is about 10%. It would be desirable to further decrease absorption to well below 10%.

[00118] Referring now to Figure 9A, it is known to use a $1/4 \lambda$ layer of dielectric 103, i.e., SiO₂, to enhance reflectivity in a vertical structure LED. The

dielectric 103 is formed between a GaN semiconductor 104 and an Ag metal layer 102, both of which are formed upon a conductive holder 101. However, as discussed below, the use of a $1/4 \lambda$ of dielectric does not substantially enhance reflectivity.

[00119] Referring now to Figure 9B, it can be seen that the use of the $1/4 \lambda$ layer of dielectric does provide enhanced reflectance for the S polarized light incident thereon, as indicated by curve 153. However, the P polarized light incident upon this dielectric layer has a deep dip in the reflectance curve around 47° , as indicated by curve 152. This dip substantially reduces the overall reflectivity, as indicated by the curve 151 for the average of the S polarized and the P polarized light. Therefore, the use of a $1/4 \lambda$ layer of dielectric is not a suitable solution to the problem of light absorption by an LED electrode.

[00120] According to one embodiment of the present invention, a reflective electrode structure minimizes contact area between the electrode and the LED semiconductor material. A comparatively thick dielectric material is disposed between a conductive electrode and the semiconductor material so as to electrically isolate portions of the electrode while allowing for other portions to make electrical contact. The dielectric material can be of a lower index of refraction than the semiconductor and can be thick enough such that total internal reflection occurs for incident angles greater than the critical angle Θ_c , as discussed below.

[00121] Total internal reflection for dielectric materials provides the desirable capability for approximately 100% reflectivity. Total internal reflection occurs beyond the critical angle, Θ_c . In the case of a GaN to air interface, the critical angle is approximately 24° . In the case of a GaN to SiO_2 interface, the critical angle is approximately 37° .

[00122] Referring now to Figure 10A, a semi-schematic diagram shows light reflection at a GaN/air. A ray of light is shown being reflected from the interface

back into the GaN semiconductor material 121 because the angle of incidence is greater than the critical angle Θ_c .

[00123] Referring now to Figure 10B, a chart shows reflectivity at the GaN/air interface of Figure 10A for different angles of incidence.

[00124] Referring now to Figure 11A, a semi-schematic diagram shows light reflection at a GaN/SiO₂ interface according to an embodiment of the present invention. A ray of light is shown being reflected from the interface of the GaN semiconductor material 131 and the SiO₂ layer 132 back into the GaN semiconductor material 131 because the angle of incidence is greater than the critical angle Θ_c .

[00125] Referring now to Figure 11B, a chart shows reflectivity at the GaN/SiO₂ interface of Figure 11A for different angles of incidence according to an embodiment of the present invention.

[00126] Referring now to Figure 12A, is a semi-schematic diagram show light reflection at a GaN/ SiO₂/Al interface according to an embodiment of the present invention. A portion of electrode 173 is suspended over GaN substrate 171 and has a thick dielectric SiO₂ layer 172 formed therebetween. Another portion of electrode 173 is formed directly upon GaN substrate 171.

[00127] Referring now to Figure 12B, is a chart showing the P-polarization reflectivity at the GaN/SiO₂/Al interface of Figure 12A for different angles of incidence wherein thicknesses of the SiO₂ layer are less than or equal to $1\frac{3}{4} \lambda$ according to an embodiment of the present invention. At a $1/16 \lambda$ of SiO₂ there is no total internal reflection effect and the reflectivity is marginally worse than without the SiO₂ layer. At a $1/4 \lambda$ of SiO₂ there is still no TIR effect and the reflectivity is dramatically worse. At $1/2 \lambda$ of SiO₂ total internal reflection does occur for large incident angles but a tremendous dip in reflectivity occurs at approximately 38°. At $1\frac{3}{4} \lambda$, total internal reflection occurs for the high angles of incidence and no noticeable dip in reflectivity. Since TIR begins at $1/2 \lambda$ of SiO₂, the term "thick" dielectric will refer to all dielectrics thicker or equal to $1/2 \lambda$.

[00128] Referring now to Figure 12C, is a chart showing reflectivity at the GaN/SiO₂/Al interface of Figure 12A for different angles of incidence wherein thicknesses of the SiO₂ layer are greater than $1\frac{3}{4}$ the wavelength of incident light according to an embodiment of the present invention.

[00129] Once the dielectric layer is greater than this minimum thickness for total internal reflection, its exact thickness is not as critical as in conventional optical coatings based on interference. This allows for greater latitude in the manufacturing process. This is illustrated in Figure 12C, which shows the reflectivity curves of for a thick dielectric at two different thicknesses, one at 1.75λ , and the other at 1.85λ . The total internal reflection angle does not change.

[00130] Referring now to Figure 13A, a semi-schematic diagram shows light reflection at a distributed Bragg reflector (DBR) comprised of alternating layers of SiO₂ 182 and TiO₂ 183 on top of the thick dielectric SiO₂ base layer 185 according to an embodiment of the present invention. An electrode 184 makes electrical contact to semiconductor material 181 and is the final layer onto top of the DBR stack. Thick dielectric layer 185 is formed between the DBR stack and semiconductor material 181.

[00131] The thick dielectric creates an effective reflector at high angles. However, it does not substantially enhance the reflectivity below the critical angle. It is possible to add a distributed Bragg reflector (DBR) to reflect the light at these lower angles. DBRs are typically fabricated using a series of alternating high index/low index dielectric materials. As shown in Figure 13A, a series of 2 pairs of $\frac{1}{4} \lambda$ SiO₂ and $\frac{1}{4} \lambda$ TiO₂ over a thick layer of $1\frac{3}{4} \lambda$ SiO₂ enhances the reflectivity at lower angles. DBRs use optical interference to affect reflectivity, as result their thickness is more critical than the thickness of the underlying thick SiO₂ layer.

[00132] Table 2 below provides further information regarding the electrode materials utilized according to one or more embodiments of the present invention. The reference wavelength for the coating thickness is 0.4500 microns. The phase

and retardance values are in degrees. The coating has six layers. The incident media is GaN. The wavelength of the light used is 0.4500 microns.

[00133]

Material	Thickness
Al ₁	1.000000
SiO ₂	0.250000
TiO ₂	0.250000
SiO ₂	0.250000
TiO ₂	0.250000
SiO ₂	0.750000

Table 2

[00134] Referring now to Figure 13B, is a chart showing reflectivity at the DBR layers of Figure 13A for different angles of incidence according to an embodiment of the present invention compared to a design with only thick dielectric compared to a design with no thick dielectric and no DBR.

[00135] Referring now to Figure 14, is a chart showing reflectivity of several materials for different angles of incidence according to an embodiment of the present invention as compared to prior art. A Au metal layer with a Cr under layer has the worst reflectance as indicated by the lowest curve 1951. Al is substantially better as indicated by curve 1952. Ag is even better as indicated by curve 1953. An Ag metal layer with a thick SiO₂ dielectric under layer has generally better reflectance than Ag, although curve 1954 dips below curve 1953 in some places. An Ag metal layer with 2 pairs of DBR followed by with a thick SiO₂ has the best reflectance, as indicated by curve 1955.

[00136] Referring now to Figure 15A, a semi-schematic diagram shows a first exemplary embodiment of a suspended electrode according to the present invention. Electrode 142a is suspended above a GaN substrate 141 such that a thick air gap 143a is formed therebetween. Electrode 142a is supported on both sides thereof.

[00137] Referring now to Figure 15B, a semi-schematic diagram shows a second exemplary embodiment of a suspended electrode according to the present invention. Electrode 142b is suspended above the GaN substrate 141 such that a plurality of air gaps 143b are formed therebetween. Electrode 142a is supported on both sides and in the middle thereof.

[00138] Referring now to Figure 15C, a semi-schematic diagram shows a third exemplary embodiment of a suspended electrode according to the present invention. Electrode 142c is suspended above the GaN substrate 141 such that a thick air gap 143c is formed therebetween. Electrode 142c is supported only on one side thereof.

[00139] Referring now to Figure 15D, a semi-schematic diagram shows a fourth exemplary embodiment of a suspended electrode according to the present invention. Electrode 142d is suspended above the GaN substrate 141 and a thick SiO₂ layer 143d is formed therebetween. Electrode 142d is supported on both sides thereof.

[00140] Referring now to Figure 15E, a semi-schematic diagram shows a fifth exemplary embodiment of a suspended electrode according to the present invention. Electrode 142e is suspended above the GaN substrate 141 and a plurality of sections of a thick SiO₂ layer 143e are formed therebetween. Electrode 142e is supported on both sides and in the middle thereof.

[00141] Referring now to Figure 15F, a semi-schematic diagram shows a sixth exemplary embodiment of a suspended electrode according to the present invention. Electrode 142f is suspended above the GaN substrate 141 such that a

thick SiO₂ layer 143f is formed therebetween. Electrode 142f is supported only on one side thereof.

[00142] Referring now to Figure 16A, a semi-schematic diagram shows a first exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention. The structure of the electrode of Figure 16A is similar to that of Figure 15A, except for the addition of indium tin oxide (ITO) layer 144.

[00143] Referring now to Figure 16B, a semi-schematic diagram shows a second exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention. The structure of the electrode of Figure 16B is similar to that of Figure 16B, except for the addition of indium tin oxide (ITO) layer 144.

[00144] Referring now to Figure 16C, a semi-schematic diagram shows a third exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention. The structure of the electrode of Figure 16C is similar to that of Figure 15C, except for the addition of indium tin oxide (ITO) layer 144.

[00145] Referring now to Figure 16D, a semi-schematic diagram shows a fourth exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention. The structure of the electrode of Figure 16D is similar to that of Figure 15D, except for the addition of indium tin oxide (ITO) layer 144.

[00146] Referring now to Figure 16E, a semi-schematic diagram shows a fifth exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention. The structure of the electrode of Figure 16E is similar to that of Figure 15E, except for the addition of indium tin oxide (ITO) layer 144.

[00147] Referring now to Figure 16F, a semi-schematic diagram shows a sixth exemplary embodiment of a suspended electrode with an ohmic contact layer according to the present invention. The structure of the electrode of Figure 15F is similar to that of Figure 14F, except for the addition of indium tin oxide (ITO) layer 144.

[00148] Referring now to Figures 17A-17D, an exemplary, contemporary, lateral LED structure and the process for forming it are shown.

[00149] [With particular reference to Figure 17A, a pair of wire bond pads 1091 and 1092 facilitate the application of current to a semiconductor 1093. Semiconductor 1093 is formed upon a substrate 1096. Semiconductor 1093 comprises an p-layer 1097 and a n-layer 1098 (n-layer 1098 and p-layer 1097 are generally interchangeable for the purposes of this discussion) The current causes active region 1094 to produce light according to well known principles.

[00150] With particular reference to Figure 17B, the fabrication of the LED of Figure 9A comprises forming a semiconductor layer 1093 upon a substrate 1096. Semiconductor layer 1093 comprises an n-layer 1098 and a p-layer 1097 (as shown in Figure 17A).

[00151] With particular reference to Figure 17C, a portion of p-layer 1097 is removed, such as by etching. A sufficient amount of p-layer 1097 is removed so as to expose a portion of n-layer 1098 therebeneath. Removal of the portion of p-layer 1097 defines a cutout portion 1099. The formation of cut out 1099 leaves n-layer 1098 exposed.

[00152] With particular reference to Figure 17D, wire bond pad 1091 is formed upon p-layer 1097 and wire bond pad 1092 is formed upon n-layer 1098. wire bond pads 1091 and 1092 cover a comparatively large portion of the surface area of semiconductor 1093. For example, the electrode wire bond pads of a contemporary LED can be 100 μm x 100 μm . They thus absorb an undesirably large amount of the light produced by active region 1094. Further, the comparatively large cut out area 1099 that is required for wire bond pads 1092

undesirably reduces the size of active area 1094 and thus further reduces the amount of light produced by such contemporary LEDs. Since the size of each electrode is fixed regardless of device size, the undesirable light absorption can be a significant portion of the overall surface area, particularly for smaller LEDs.

[00153] It is worthwhile to appreciate that that the formation of such an electrode structure that is partially within and partially outside of a cutout offers substantial advantage, even if the electrode is not reflective. For example, the electrode structure described in connection with Figures 18A-18B below provides adequate bonding area while minimizing the size of the cutout such that less active area is removed and more light can be produced.

[00154] Referring now to Figures 18A-18E, an exemplary lateral LED structure and the process for forming it according to an embodiment of the present invention are shown. A thick dielectric layer 1101 and 1102 is formed beneath wire bond pads 1091a and 1092a, respectively. Thick dielectric layers 1101 and 1102 enhance the reflectivity of wire bond pads 1091a and 1092a such that undesirable light absorption thereby is substantially decreased. A portion of each wire bond pad 1091a and 1092a remains in contact with semiconductor 1093 so as to facilitate current flow therethrough.

[00155] As used herein, a thick dielectric layer is a layer having sufficient thickness such that effects of interference are not substantial. Moreover, as used herein a thick dielectric layer can have a thickness of greater than $\frac{1}{4} \lambda$. For example, a thick dielectric layer can have a thickness equal or great then $\frac{1}{2} \lambda$, approximately 1.5λ , approximately 1.75λ , or greater than 1.75λ .

[00156] With particular reference to Figures 18B and 18C, semiconductor 1093 is formed upon substrate 1096 and cutout 1099 is formed in semiconductor 1093 as in Figures 17B and 17C.

[00157] With particular reference to Figure 18D, thick dielectric layers 1101 and 1102 are formed upon p-layer 1097 and n-layer 1098, respectively. Thick dielectric layers 1101 and 1102 can be formed according to well known principles.

[00158] With particular reference to Figure 18E, wire bond pad 1091a is formed so as to at least partially cover thick dielectric layer 1101 and wire bond pad 1092a is formed so as to at least partially cover thick dielectric layer 1102. As mentioned above, a portion of wire bond pads 1091a and 1092a contacts semiconductor 1093 therebeneath.

[00159] Referring now to Figure 19A-19E an exemplary lateral LED structure and the process for forming it according to an embodiment of the present invention are shown.

[00160] With particular reference to Figures 19A A thick dielectric layer 1101 and 1102a is formed beneath wire bond pads 1091a and 1092b, respectively. Thick dielectric layers 1101 and 1102a enhance the reflectivity wire bond pads 1091a and 1092b such that undesirable light absorption thereby is substantially decreased. A portion of each wire bond pad 1091a and 1092b remains in contact with semiconductor 1093 so as to facilitate current flow.

[00161] With particular reference to Figures 19B and 19C, semiconductor 1093 is formed upon substrate 1096 and cutout 1099a is formed in semiconductor 1093 as in Figures 17B and 17C. However, in this embodiment cutout 1099a is formed in an L-shaped configuration so as to mitigate the amount of surface area thereof. In this manner, less of the active area is sacrificed in the formation of cutout 1099a and the brightness of the LED is consequently enhanced.

[00162] With particular reference to Figure 19D, a thick dielectric layer 1101 is formed upon the p-layer 1097. Another thick dielectric layer 1102a is formed partially on the p-layer 1097 and partially on the n-layer 1098. Thick dielectric layers 1101 and 1102a can again be formed according to well known principles. In this instance thick dielectric layer 1102a is formed downwardly, along the side of p-layer 1097 and active layer 1094 so as to electrically insulate wire bond pad 1092b therefrom. That is, thick dielectric layer 1102a is formed upon both p-layer 1097 and n-layer 1098, as well as the interface therebetween, i.e., active layer 1094. Thick dielectric layer 1102a stair steps downwardly from n-layer 1097 to n-layer

1098. This configuration of thick dielectric layer 1102a is best seen in the cross section of Figure 19A.

[00163] With particular reference to Figure 19E, wire bond pad 1091a is formed so as to at least partially cover thick dielectric layer 1101 and wire bond pad 1092b is formed so as to at least partially cover thick dielectric layer 1102a. As mentioned above, a portion of wire bond pad 1091a contacts p-layer 1097 and a portion of wire bond pad 1092b contacts n-layer 1098. In this instance, wire bond pad 1092b is formed downwardly, insulated by and covering thick dielectric layer 1102a and electrically contacting n-layer 1098. The configuration of wire bond pad 1092b is best seen in Figure 19A.

[00164] In this embodiment, thick dielectric layers 1101 and 1102a substantially mitigate light absorption by wire bond pads 1091a and 1092b so as to enhance the brightness of the LED. The reduced size of cutout 1099a provides a larger active area 1094, so as to further enhance the brightness of the LED.

[00165] According to the present invention, a thick dielectric can be formed between at least a portion of each bond pad and/or electrode and the semiconductor material. The thick dielectric material enhances reflectivity such that undesirable light absorption by the bond pad and/or electrode is substantially mitigated.

[00166] Referring now to Figure 20A, a semi-schematic perspective view shows one embodiment of a suspended electrode structure according to an embodiment of the present invention. A metal electrode 162 is formed upon a semiconductor 161. A thick dielectric 163 is formed between metal electrode 162 and semiconductor 161. A portion of electrode 162 is formed over thick dielectric 163 and a portion of electrode 162 contacts semiconductor 161 such that electrode 162 is in electrical contact with semiconductor 161.

[00167] Referring now to Figure 20B, a semi-schematic perspective view shows another configuration of a suspended electrode structure according to an embodiment of the present invention. This structure is generally similar to that of

Figure 20A except that thick dielectric 163 is broken up such that portions of electrode 162 contact semiconductor in different places than in Figure 20A. As shown in Figure 20B, multiple contacts of electrode 162 to semiconductor 161 are provided. As those skilled in the art will appreciate, various configurations of electrode 162 and thick dielectric 163, with electrode 162 contacting semiconductor 161 in various different places, are possible.

[00168] Figures 21A–24 show exemplary electrode structures that utilize thick dielectrics according to one or more embodiments of the present invention. For example, one or more layers of insulating dielectric can be formed under the bond pads. Some advantages of such construction include: the mitigation of current crowding, thus facilitating a simplified design; the minimization of light absorption because the dielectric layer(s) under the electrode can form a mirror; more efficient use of the emission area that is achieved by reducing the cutout area; a more easily scalable design for a large range of die sizes; comparatively low forward voltage; and more even current spreading.

[00169] The exemplary embodiments of Figures 21A–24 are implementations of an elongated chip. Such elongated chips can provide enhanced brightness with better efficiency.

[00170] Referring now to Figure 21A, an electrode design for an elongated chip is shown. Thick dielectric layers 1002 and 1003 can be formed under each of the bond pads 1006 (the p-bond pad, for example) and 1007 (the n-bond pad, for example). N-bond pad 1007 and n-electrode extension 1001 are formed upon an etched away portion of semiconductor material 1008 or cutout 1004.

[00171] The thick dielectric layers 1002 and 1003 insulate the bond pads 1006 and 1007 from semiconductor material 1008 so as to mitigate current crowding. This results in an improved geometry for more even current flow. Hot spots that cause uneven brightness and can result in damage to the LED are substantially mitigated.

[00172] Such thick dielectric layers are not formed under conductive extensions 1001 and 1005 that define n-wiring and p-wiring respectively. Extensions 1001 and 1005 thus more evenly distribute current throughout semiconductor 1008. That is, the distance between the electrodes that provide current to the LED tends to be more equal according to one aspect of the present invention.

[00173] It is worthwhile to appreciate that total internal reflection (TIR) provides a substantial advantage in enhancing light extraction for one or more embodiments of the present invention. The use of a DBR structure is optional and can be used, according to at least one embodiment of the present invention, to further enhance light extraction.

[00174] The use of TIR and/or DBR structures as described above can substantially mitigate undesirable absorption of light under bond pads 1006 and 1007. Such insulators (as well as insulating layers 1002 and 1003) can be formed beneath bond pads 1006 and 1007 and not beneath extensions 1001 and 1005, so that current flow through semiconductor (and consequently the active region thereof) is more evenly distributed.

[00175] Bond pads 1006 and 1007, as shown in Figures 21A and 21B, are not located exactly at the end of the wire traces or extensions 1001 and 1005. This is to show that bond pads 1006 and 1007 can be placed at any arbitrary location along the trace. Thus, bond pads 1006 and 1007 can be placed at the end, near the end, and/or in the middle of extensions 1001 and 1005. Any desired location of bond pads 1006 and 1007 can be used.

[00176] Referring now to Figure 21B, a potential improvement with respect to the configuration of Figure 21A is shown. The area of cutout 1104 is reduced by putting the n-bond pad above the p-surface and separated from the p-surface by the thick dielectric. That is, at least a portion of the n-bond pad is not in cutout 1104 and cutout 1104 can thus be much smaller than in Figure 21A. This thick dielectric must also cover the edges of the cutout to ensure isolation of the n-bond

pad from the p-Layer. That is, the area of the cutout is reduced such that the size of the active area is increased. The larger emission area facilitated by using a smaller cutout 1004 can enable a greater power output.

[00177] In some applications, the distance between the p and n electrodes may be too great, thus resulting in an undesirably high forward voltage. In such cases, the use of multiple electrodes may be beneficial. Figures 22A-23C show various exemplary implementations of three electrode designs that can mitigate such undesirability high forward voltages.

[00178] Referring now to Figures 22A-22C, the n-bond pad is shown split into two electrically isolated pads 1217 and 1218. In principle, they can be touching (and thus in electrical contact with one another) and thus effectively form a single pad. There can be two separate wire bonds, one to each of pads 1217 and 1218. However if a gap 1220 between pad 1217 and 1218 is small enough, then a single bond pad can be used to electrically connect bond pads 1217 and 1218 together. In this manner, any desired number of such electrodes can be used.

[00179] With particular reference to Figure 22A, two n-bond pads 1217 and 1218 and a single p-bond pad 1219 can be used. Two thick dielectric layers 1204 and 1283 can be formed between each bond pad 1219 and the semiconductor material 1280 disposed therebeneath. Similarly, a thick dielectric layer 1202 can be formed between bond pads 1217 and 1218 and the semiconductor material 1201 of cutout 1281. As mentioned above, such construction results in more even current distribution. This is particularly true for larger and/or higher current LEDs.

[00180] With particular reference to Figure 22B, the area of cutout 1201 is reduced with respect to that shown in Figure 22A in a manner analogous to that of Figure 21B. Again, two thick dielectric layers 1204 and 1283 can be formed between each bond pad 1219 and the semiconductor material 1280 disposed therebeneath. Similarly, a thick dielectric layer 1202 can be formed between bond pads 1217 and 1218 and the semiconductor material 1201 of cutout 1281.

[00181] With particular reference to Figure 22C, p-wiring extension 1203 extends beneath n-bond pad thick dielectric 1202 such that a distal end 1230 of p-wiring extension extends to the right of thick dielectric 1202. Again, two thick dielectric layers 1204 and 1283 can be formed between each bond pad 1219 and the semiconductor material 1280 disposed therebeneath. Similarly, a thick dielectric layer 1202 can be formed between bond pads 1217 and 1218 and the semiconductor material 1201 of cutout 1281.

[00182] With particular reference to Figure 23A-23C, the p-layer and the n-layer are reversed in position (with a consequent reversal in the respective bond pads, insulators, etc) to show that the construction of Figures 22A-22C is suitable with either type of device. Thus, n-bond 1507 and thick n-bond pad dielectric 1503 are formed on cutout 1504 and p-bond pads 1511 and 1512 and thick p-bond pad dielectric 1501 are not formed on cutout 1504 (which is the opposite of the construction shown in Figures 22A-22C). Thus, the electrodes are reversed with respect to those shown in Figures 22A-22C.

[00183] With particular reference to Figure 24, a two electrode LED that facilitates more uniform current distribution is shown. An n-bond pad 2403 and a p-bond pad 2404 are formed upon a semiconductor material 2401. n-bond pad 2403 has a thick dielectric layer 2406 formed between itself and semiconductor material 2401. Similarly, p-bond pad 2404 has a thick dielectric layer 2407 formed between itself and semiconductor material 2401.

[00184] A cutout 2402 facilitates contact of n-bond pad 2403 to the n-layer of semiconductor 2401. A portion of n-bond pad 2403 can be formed outside of cutout 2402 (and thus upon the p-layer of semiconductor material 2401) and a portion of n-bond pad 2403 can be formed within cutout 2402 (to provide electrical contact with the n-layer). Similarly, a portion of thick dielectric layer 2406 can be formed outside of cutout 2402 (and thus upon the p-layer of semiconductor material 2401) and a portion of thick dielectric layer 2406 can be formed within cutout 2402.

[00185] n-bond pad 2403 and thick dielectric layer 2406 thus extend down the side of cutout 2402 from the n-layer to the p-layer of semiconductor material 2401, in a fashion similar to that of Figure 21B. Such construction tends to minimize the size of cutout 2402 and thus tends to enhance the brightness and efficiency of the LED, as discussed above.

[00186] p-wiring or extension 2407 extends from p-pad 2404 so as to more uniformly distribute current through the active region of semiconductor 2401. A portion of p-pad 2404 and all of extension 2407 can be formed directly upon semiconductor material 2401 (without a thick dielectric layer therebetween).

[00187] Although in Figures 15-24 only a single thick dielectric layer is shown, a series of one or more DBR pairs can be deposited between the thick dielectric and the electrode. Similarly, although Figures 15-24 show the electrode in direct contact with the semiconductor material, the contact can be via an ohmic contact layer or current spreading layer.

[00188] According to one or more embodiments of the present invention, the thick dielectric can be non-perforated. That is, the dielectric can be continuous in cross-section. It can be formed such that it does not have any holes or perforations that would cause the thick dielectric to appear to be discontinuous in cross-section.

[00189] The dielectric material can be porous. Thus, thick dielectric materials which may otherwise be too dense (and thus have too high of an index of refraction) can be used by effectively reducing the density (and the effective index of refraction, as well) by making the dielectric material porous or non continuous.

[00190] In view of the foregoing, one or more embodiments of the present invention provide a brighter and/or more efficient LED. Increasing the brightness of an LED enhances its utility by making it better suited for use in a wide of applications. For example, brighter LEDs can be suitable for general illumination applications. Further, more efficient LEDs are desirable because they tend to

reduce the cost of use (such as by reducing the amount of electricity required in order to provide a desire amount of light.

[00191] Embodiments described above illustrate, but do not limit, the invention. It should also be understood that numerous modifications and variations are possible in accordance with the principles of the present invention. Accordingly, the scope of the invention is defined only by the following claims.

CLAIMS:

1. A reflective electrode structure comprising:
an electrode;
a semiconductor material configured to emit light about a central wavelength λ ;
a dielectric material formed upon the semiconductor material;
at least one DBR pair formed upon the dielectric material; and
wherein a portion of the electrode is formed over both the dielectric material and the DBR pair(s) and another portion of the electrode is in ohmic contact with the semiconductor material.
2. The reflective electrode structure as recited in claim 1, wherein the electrode comprises a metal electrode.
3. The reflective electrode structure as recited in claim 1 or 2, wherein the semiconductor material comprises GaN.
4. The reflective electrode structure as recited in any one of the preceding claims, wherein the dielectric material comprises at least one material selected from the group consisting of:
silicon dioxide;
silicon monoxide;
MgF₂; and
siloxane polymers.
5. The reflective electrode structure as recited in any one of the preceding claims, wherein the dielectric material comprises silicon dioxide.

6. The reflective electrode structure as recited in any one of the preceding claims, wherein the dielectric material has a thickness of approximately 1.75λ .

7. A reflective electrode structure comprising:
a metal electrode;
a GaN semiconductor material configured to emit light about a central wavelength λ ;
silicon dioxide dielectric material formed upon the GaN material, the dielectric material having a thickness of approximately 1.75λ ;
at least one DBR pair formed upon the silicon dioxide material; and
wherein a portion of the electrode is formed over both the dielectric material and the DBR pair(s) and another portion of the electrode is in ohmic contact with the semiconductor material.

8. The reflective electrode structure as recited in claim 7, wherein each layer of the DBR pair(s) is optically transmissive and has a different index of refraction with respect to each other layer.

9. The reflective electrode structure as recited in claim 7 or 8, wherein each layer of the DBR pair(s) has a thickness that is a multiple of approximately $\frac{1}{4} \lambda$.

10. The reflective electrode structure as recited in any one of claims 7 to 9, wherein the dielectric and the electrode make physical contact to the semiconductor via an ITO layer.

11. A method for making an electrode structure, the method comprising:
providing a semiconductor material that is configured to emit light about a central wavelength λ ;

forming a dielectric material formed upon the semiconductor material;
forming at least one DBR pair formed upon the dielectric material;
forming a portion of an electrode over both the dielectric material and the DBR pair(s); and

forming another portion of the electrode in ohmic contact with the semiconductor material.

12. The method as recited in claim 11, wherein the electrode comprises a metal electrode.

13. The method as recited in claim 11 or 12, wherein the semiconductor material comprises GaN.

14. The method as recited in any one of claims 11 to 13, wherein the dielectric material comprises silicon dioxide.

15. The method as recited in any one of claims 11 to 14, wherein the dielectric material comprises at least one material selected from the group consisting of:

silicon dioxide;

silicon monoxide;

MgF₂; and

siloxane polymers.

16. The method as recited in any one of claims 11 to 15, wherein the dielectric material has a thickness of approximately 1.75 λ .

17. A method comprising:

forming a portion of an electrode over both a dielectric material and at least one DBR pair; and

forming another portion of the electrode in ohmic contact with a semiconductor material.

18. The method as recited in claim 17, wherein each layer of the DBR pair is optically transmissive and has a different index of refraction with respect to each other layer.

19. The method as recited in claim 17 or 18, wherein each layer of the DBR pair has a thickness that is a multiple of approximately $\frac{1}{4} \lambda$.

20. The method as recited in any one of claims 17 to 19, wherein the dielectric and the electrode make physical contact to the semiconductor via an ITO layer.

21. A device comprising:
means for emitting light;
means for providing current flow to the means for emitting light;
means for providing electrical insulation formed upon the means for emitting light;
at least one DBR pair formed upon the means for providing electrical insulation;
and

wherein a portion of the means for providing current flow is formed over both the means for providing electrical insulation and the DBR pair(s) and another portion of the means for providing current flow is in ohmic contact with the means for emitting light.

22. An electrode structure for an LED, the electrode structure comprising:
a semiconductor material having an n-portion and a p-portion;
a metal n-electrode in electrical communication with the n-portion;
a metal p-electrode in electrical communication with the p-portion;
an optically transmissive dielectric material formed to at least one of the n-electrode and the p-electrode so as to enhance reflection of light, the dielectric material having a thickness of approximately 1.75λ ; and
wherein the semiconductor material, the n-electrode and the p-electrode cooperate to define a lateral LED structure.

23. An electrode structure for a semiconductor LED, the electrode structure comprising:
an electrode; and
an optically transmissive dielectric material having an index of refraction greater than or equal to one and less than that of a semiconductor upon which the dielectric material is formed, the dielectric material being formed to the electrode so as to enhance reflection of light.

24. An electrode structure for a semiconductor LED, the electrode structure comprising:
a electrode; and
an optically transmissive dielectric material having a thickness greater than $1/2 \lambda$, the dielectric material being formed to the electrode so as to enhance reflection of light.

25. An electrode structure for a semiconductor LED, the electrode structure comprising:
an electrode; and
an optically transmissive dielectric material formed to the electrode and being porous enough to reduce the dielectric material's effective index of refraction such that total internal reflection occurs within the semiconductor material.

26. An electrode structure for an LED, the electrode structure comprising:
a semiconductor material having a cutout formed therein;
an electrically insulating dielectric material;
a metal electrode;
wherein a portion of the electrode is formed outside of the cutout and a portion of the electrode is formed inside of the cutout;
wherein the portion of the electrode outside the cutout is electrically isolated from the semiconductor material by the dielectric material; and
wherein the portion of the electrode inside the cutout is in electrical contact with the semi conducting material.