

ZONE-DELINEATED PYROLYSIS APPARATUS FOR CONVERSION OF POLYMER WASTE

BACKGROUND OF THE INVENTION

5 The present invention relates to an apparatus for the conversion of polymer waste, whether in solid and/or liquid form, herein interchangeably described as hydrocarbonaceous material, polymer waste and/or polymeric material, to condensable, non-condensable and solid hydrocarbon products. Condensable hydrocarbon products include synthetic petroleum and a variety of its fractions including but not limited to light sweet crude oil, fuel additives, base oil, 10 slack wax, paraffin wax, microcrystalline wax and condensate dominated by aromatic petroleum hydrocarbons. The non-condensable hydrocarbon product is a gas. The solid hydrocarbon product is a finely divided carbon char. In particular, the present invention is a continuous, zone-delineated pyrolysis apparatus, having capability to simultaneously produce multiple products, one of which, a hard wax, is produced from the apparatus at temperatures lower than typical 15 pyrolysis conversion temperatures.

 Converting waste polymers to obtain useful end products via pyrolysis has been a goal sought by many, for many years. Prior art involving pyrolytic decomposition of polymers largely relies on batch, semi-batch or serial batch processes limited in commercially viable application by their operating complexity and inability to continuously process mixed, poorly sorted and/or 20 contaminated polymer waste without fouling. Many claim that serial batch processes comprised of a series of batch reactors progressively operated in a set sequence are “continuous” merely because some product is constantly being discharged from one or more exit ports connected to the batch reactors by a manifold or other suitable exit configuration. Polymer conversion processes include the primary processes of chemical depolymerization, gasification with partial 25 oxidation, and thermal cracking, including pyrolysis, either with or without catalytic cracking and reforming, as well as the secondary process of hydrogenation. Chemical depolymerization has mainly been limited to decomposition of polyesters e.g. PET, and polyurethanes, with secondary application to polyamides, polycarbonates and polyacetals. This method is generally restricted to decomposition of condensation polymers, targeting monomer yield.

30 Gasification and partial oxidation of waste polymers typically targets production of mixtures of carbon monoxide and hydrogen generally known as syngas. Although partial

oxidation can be a more efficient process than steam methane reformation in terms of reactor size and process rate, partial oxidation produces a lower comparative hydrogen yield. Little, if any, condensable hydrocarbons are produced.

Thermal cracking processes employ thermal decomposition resulting in complex mixtures. Reaction temperature, coupled with molecular retention times within respective desired temperature ranges, is the most significant reaction variable, influencing both polymer conversion and molecular distribution of conversion products. Accordingly, efficient control of reaction temperature and residence times is paramount in importance to maximize yield of the desired product mix. Batch, semi-batch and serial batch processes experience difficulty in efficiently achieving and maintaining control of reaction temperatures and residence times due to problems resulting from, among other things, inefficient heat transfer through the waste polymer as this polymer appears to exhibit poor thermal conductivity. Unlike continuous processes, which achieve a dynamic process equilibrium thereby maintaining control of reaction temperatures and residence times, batch, semi-batch and serial batch processes are continually in a state of disequilibrium, posing chronic control challenges with every process cycle and acute problems of reactor fouling. Other variables, including catalysts, are optimizers; although catalytic cracking and reforming offers advantages of polymer breakdown at lower temperatures and higher rate with added control on product quality, catalytic cracking poses challenges including process complexity, deposition of residues hindering activity, poisoning of catalysts, high capital and operating cost of catalyst reactors, and cost of disposal of spent catalyst.

Hydrogenation is a basic step in petroleum refining and petrochemical production that has been applied to secondary processing of oil resulting from thermal cracking processes. This secondary method, often coupled with distillation, is employed in the production of petroleum-based fuels and process cuts where hydrogen saturation of olefins and removal of heteroatoms is required. Hydrogenation is capital intensive, and can have high operating cost attributed to high pressure operation, cost of hydrogen, cost of removing waste heat, and other factors. The term "heteroatom" is understood to mean any atom that is not carbon or hydrogen, and has been applied to indicate that non-carbon atoms have replaced carbon in the backbone of the molecular structure or replaced hydrogen or alkyl groups bonded to the backbone of the molecular structure. Typical heteroatoms are nitrogen, oxygen, sulfur, phosphorus, chlorine, bromine,

fluorine and iodine. Hydrogenation is a secondary process deployed in petroleum refining and petrochemical production.

Prior art systems and processes have not achieved wide acceptance or success involving pyrolytic decomposition of polymers and this has been attributed to high operating costs, inability to consistently process contaminated waste streams and waste streams of varying composition, the prohibitively high cost or lack of market availability of uncontaminated raw material streams, inability to reliably and efficiently control temperature and pressure process conditions, inability to consistently supply adequate quantities of in-specification raw material to plants requiring high volumes of material to sustain operations, inability to control system fouling by char, terephthalic acid, benzoic acid, minerals, metals and the like, attempts to produce fuel having comparatively narrow ranges of market-driven specifications from widely varying raw material compositions, inability to control heteroatom content of product oil thus limiting market acceptance of the products, inability to consistently and effectively manage safety issues attributed to worker exposure to hazardous vapors and solids in every batch reactor cycle, and generation of hazardous waste including but not limited to char, waste water and off-specification hydrocarbonaceous liquids.

More specifically, prior art involving batch or semi-batch processes must overcome challenges of thermal inefficiency to promote conversion. Given that polymer waste has poor thermal conductivity, most batch reactor systems rely on some configuration of mixing elements within the reactor or complex arrays of raw material-containing cartridges placed into the batch reactor or concentric tubular devices containing raw material subjected to thermal energy or tubular heat transfer geometries deployed within the body of the batch reactor and the like, with the intent to increase raw material surface area, thereby increasing surface exposure to thermal energy which is otherwise poorly conveyed through material having poor thermal conductivity. The large number of batch reactor configurations that have sought patent protection is consistent with a broad-spectrum series of attempts to solve the heat transfer and process control challenges inherent to batch reactor systems. Complex mechanical and/or geometric solutions to the limitations are inherent to batch reactors.

Additionally, most if not all batch reactors, whether singly or in series, must be charged with hydrocarbonaceous raw materials, purged of atmospheric air containing oxygen, heated to the desired temperature when product vapors are extracted, then cooled to a temperature below

flash point of the residual solids to facilitate their removal. The repeated thermal cycles experienced by these systems have poor thermal efficiency resulting in overconsumption of energy to complete the polymer conversion.

In an embodiment of the batch process, U.S. Pat. No. 8,192,587 to Garrison et al provides limited means of process control. In a batch reactor, all of the chemistries in the batch reactor described by Garrison are decomposed at successive times in the same three-dimensional space. Without the addition of the complex geometric means in Garrison to increase surface area available for heat transfer in a batch reactor by circulating heat transfer fluid through a sealed heating system, temperature control over the internal cross section of the reactor is poor because of poor thermal conductivity and varying material densities in the raw material charge. Such material densities change as conversions occur and mass is removed from the reactor via discharge of vapor. Moreover, poor thermal conductivity of polymer raw materials in a batch reactor, such as in Garrison, even with internal heat transfer fluids deployed results in varying degrees of raw material thermal transfer capacity across the complex cross section of the batch reactor. Additional complexity arises from change in thermal conductivity of the raw material as its composition changes as it decomposes. Further inefficiency in a batch reactor system such as in Garrison results from deposition of heavy oligomer, polynuclear aromatic hydrocarbons, asphaltines and/or char upon the surface of the internal heat transfer system and upon the surface of the reactor body itself, thereby offering an incomplete thermal conductivity solution to promotion of efficient heat transfer. As waste polymer decomposes in place in an unstirred reactor as described by Garrison, deposition of char on the internal surface of the reactor for much of the reactor cycle promotes formation and adsorption of aromatic and polynuclear aromatic hydrocarbons onto the surface of the char. Unless those aromatic and polynuclear aromatic hydrocarbons are removed from the char or unless this adsorption is prevented, disposal of the char created by the batch process can be rendered prohibitively expensive if it is characterized as a hazardous waste. As with all batch reactors, at the end of each process cycle, the char must be removed.

U.S. Pat. Nos. 5,389,961 5,740,384 to Cha et al describe a continuous, two-step thermal process for co-recycling scrap tires and oils. This prior art processes scrap tire with relatively large amounts of used motor oil, cylinder oil, vacuum tower bottoms and the like Cha describes a dual-reactor system operated in series whereby a transfer point between the two reactors is

required to discharge un-reacted material from the first inclined reactor to the second horizontal reactor. This transfer point results in operational challenges as a result of fouling. Cha describes a cross-sectional shape of the dual-reactor system which provides for an open headspace through which un-reacted tire components, including steel fibers, could move, said open headspace posing a challenge to efficient transport of raw material up the incline of the first reactor. Cha describes operating the inclined reactor at increasing temperature, and operating the horizontal a higher temperature to drive off volatile hydrocarbons from the char.

U.S. Pat. No. 5,836,524 to Wang describes a process that processes solid polymer waste and used lubricating oils or recycled heavy oil in a single continuous step at relatively low temperatures. This prior art employs a continuous process inclined screw having no means for control in rate of temperature ramp and control of residence time. Wang recognizes that process yield is a function of temperature.

U. S. Pat. No. 6,172,275 to Tadauchi et al describes a pyrolysis method and apparatus for decomposing waste plastic which may contain organic chlorine. Tadauchi teaches the use of heating zones for decomposition of plasticizers and for dechlorination of halogenated polymer including polyvinyl chloride (PVC), by which the plasticizers can be decomposed to oil and hydrochloric acid, which can evolve from PVC. Both the oil and the hydrochloric acid are separately recovered. Tadauchi further describes condensation and isolation of wax from lighter molecules which may contain organic chlorine compounds, and further pyrolyzing of that wax fraction to light oil. Tadauchi teaches plasticizer decomposition and hydrochloric acid evolution, noting only that additional decomposition occurs at temperatures at or above 450°C (842°F) to produce a pyrolysis product, which can be light oil dominated by 4-15 carbon atoms. Tadauchi teaches that the material remaining after decomposition of plasticizers and recovery of hydrochloric acid are subjected to a pyrolysis process generally exceeding 450°C (842°F). Tadauchi describes a vacuum to remove hydrochloric acid from the plastic and increasing reactor pressure coincident with pyrolysis to shift molecular distribution toward lighter molecules having 4-15 carbon numbers.

U. S. Pat. No. 7,344,622 to Grispin describes what is called a continuous process wherein control upon the composition of liquids resulting from the thermal decomposition of polymer waste is achieved by maintaining a slow heating rate in the substantial absence of oxygen, creating a char bed having a thermal gradient. Grispin suggests that the nature of the char bed,

reactor size, the amount of raw material charge, heating rate and the substantial exclusion of oxygen are simultaneously related to the composition of the product. The process described by Grispin operates by achieving a controlled single heat ramp for an optimal time period in a reactor targeting a relationship between reactor volume and reactor charge, to impact the composition of the oil formed thereby. Grispin's teaching is for a process for the production of aromatic fractions having 6-12 carbon numbers.

U. S. Pat. No. 7,893,307 to Smith describes a process whereby "hydrocarbon-formable materials, such as plastics and other waste or other recycled materials" are melted in a "viscous shear apparatus" such as an extruder and introduced into a device described as a "ribbonchannel" reactor wherein a cylindrical ribbon of melted plastic having a thin cross-sectional area is advanced and wherein pyrolytic decomposition of the plastic occurs. The intent of this design is to maximize surface area available to heating by exposing the thin body of melted material to a skin temperature far above that which is necessary to promote polymer decomposition, thus imparting a high thermal gradient to the material in the reactor. The temperature of melt exiting the viscous shear apparatus and entering the ribbonchannel reactor is claimed to range from about 238⁰C (460⁰F) to about 315⁰C (600⁰F). In the Smith process, effective dechlorination, if any, occurs between about 300⁰C (572⁰F) to about 365⁰C (690⁰F). Smith further discloses that residual material is discharged from the ribbonchannel reactor in a temperature range from about 524⁰C (975⁰F) to about 538⁰C (1000⁰F). To achieve decomposition in the ribbonchannel reactor, the skin temperature / heating element temperature of the ribbon channel reactor ranges from about 760⁰C (1400⁰F) to about 1315⁰C (2400⁰F) in an effort to efficiently heat the thin cross section of material filling the ribbon channel by maintaining a high temperature differential between the reactor skin and internal reactor temperature. This heating results in internal ribbonchannel reactor temperatures increasing from 338⁰C (640⁰F) – 368⁰C (694⁰F) up to 393⁰C (740⁰F) - 524⁰C (975⁰F) where pyrolytic decomposition is achieved, optionally in the presence of a melt-phase catalyst. Char material, dirt, and small pieces of metal are discharged at the end of the process about 524⁰C (975⁰F) to about 538⁰C (1000⁰F). Smith's teaching is to a process throughput of 3,000 to 10,000 pounds per hour, and focuses on the geometry of the ribbonchannel reactor to optimize rapid heat transfer. The extruder and ribbonchannel reactor cannot accept particles larger than the clearance between the extruder screw and barrel, or the effective distance between the inner diameter of the outer heated cylinder and the outer diameter

of the inner heated cylinder, whichever is smaller. In the exemplary case of rubber, Smith articulated far smaller particle sizes including crumb. Smith focuses only on providing a solution to effective heat transfer.

5 SUMMARY OF THE INVENTION

An apparatus and method of operation for continuous pyrolysis of hydrocarbonaceous materials to produce useful vapor and solid products comprising a generally cylindrical, linear reactor having a screw means for transporting hydrocarbonaceous materials through said reactor, means for feeding and heating said hydrocarbonaceous materials whereby they are processed and
10 pyrolyzed to produce vapor and solid products, wherein said screw means extends substantially the length of said reactor; means for removing vapor products from said processed hydrocarbonaceous materials, means for removing solid products, means whereby said hydrocarbonaceous material is maintained within a zone for a range of defined residence times, means for rotating said screw, which has a plurality of flight configurations for compressing, and
15 for melting said hydrocarbonaceous materials to convert them from a solid to a liquid, for mixing, destabilizing and dehalogenating said hydrocarbonaceous materials, for pyrolyzing said hydrocarbonaceous materials, for devolatilizing the pyrolyzed hydrocarbonaceous materials, and for discharging solid products.

20 BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing and other features and advantages of the present invention will become apparent to those skilled in the art to which the present invention relates upon reading the following description with reference to the accompanying drawings, in which:

25 FIG 1 is a schematic side view of a zone-delineated thermal reactor in accordance with the present invention.

FIG 2 is a schematic side view of a step-down condenser array and its deployment downstream of a zone-delineated thermal reactor in accordance with the present
30 invention.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is a zone-delineated continuous pyrolysis apparatus for conversion of hydrocarbonaceous material. It is a generally cylindrical, linear, heated, continuous reactor having an auger or screw in the center of the reactor, along its axis, with capability to simultaneously discharge end products both before and after an integral series of step-down condensers. It operates in a continuous manner. Moreover, it is a modular and scalable pyrolysis apparatus capable of converting polymer waste and low-value or contaminated polymers to synthetic petroleum and a variety of its fractions, including but not limited to, light sweet crude oil, fuel additives, base oil, slack wax, paraffin wax, microcrystalline wax and condensate dominated by aromatic petroleum hydrocarbons. The non-condensable hydrocarbon product is a gas. The solid hydrocarbon product is a finely divided carbon char which may or may not contain non-polymer solids if such non-polymer solids are present in the raw material prior to its decomposition. The reactor has a central rotating shaft with sections having varying auger or screw configurations to mix and/or advance the polymer to be converted.

The present invention has the flexibility to allow, and capacity to produce and separately discharge, a primary microcrystalline or paraffin wax product having, collectively, 30-70 carbon atoms via direct discharge from the apparatus, in a preferred embodiment, at the end of the fourth of seven continuously operated, series-oriented process zones, hereinafter referred to as Zones. Specifically, this occurs after the Mixing, Molecular Destabilization and Heteroatom Scavenging Zone, within a temperature range of 300°C to 338°C (572°F to 690°F), a temperature threshold not previously identified from which consistent yield of microcrystalline or paraffin wax product could be achieved. Further, in a preferred embodiment, it allows additional and simultaneous capacity to produce one or more additional, lighter fractions collectively having 4-30 carbon numbers recovered from separate discharge ports located in the fifth and sixth continuously operated, series-oriented process Zones, namely, the Pyrolysis Zone and the Char and Residual Solids Devolatilization Zone, respectively, via subsequent recovery of pyrolysis vapor in a series of step-down condensers, with optional demisters in plurality with respective condensers when very highly efficient separation is required, operating at progressively colder operating temperature ranges. The apparatus requires no deployment of catalyst reactors and/or reflux reactors and/or fractionation columns, although the modularity and scalability of the apparatus which is the subject of this invention provides opportunity for optional deployment of those

additional devices in examples when, for example, production of only light oil, diesel additive or gasoline additive is required.

Raw material feed to the apparatus can be a combination of mixed and/or varying solids with mixed and/or varying proportions of petroleum-based liquids, if any. Zone-delineated process control provides for efficient conversion of widely variable raw material streams, highly contaminated raw material streams, and raw material streams having inconsistent compositions over time. Clean, uncontaminated raw material feed streams are not required. Even contamination of the polymer waste by pesticides, herbicides, petroleum products, pharmaceuticals and the like is well tolerated. Certain characteristic and listed hazardous wastes can constitute or be included as a component of the hydrocarbonaceous raw material if the apparatus is operated pursuant to an EPA Permit to Operate a Hazardous Waste Storage, Treatment, and Disposal Facility.

The present invention includes a Zone-delineated, continuous pyrolysis apparatus **10** for conversion of hydrocarbonaceous material, one embodiment of which is illustrated in FIG 1. It is a continuous, modular and scalable apparatus for manufacturing condensable hydrocarbon products. These hydrocarbon products include synthetic petroleum and a variety of its fractions including but not limited to light sweet crude oil, fuel additives, base oil, slack wax, paraffin wax, microcrystalline wax and condensate dominated by aromatic petroleum hydrocarbons. The non-condensable hydrocarbon product is a gas. The solid hydrocarbon product is a finely divided carbon char plus recyclable metals and/or aggregates. This solid hydrocarbon product will also be described herein as “solid residue” or “solid products.”

It is a generally cylindrical, linear, heated reactor **10** having an auger or screw **11** in the center of the reactor **10**, along its axis. It operates in a continuous manner. Moreover, it is a modular and scalable pyrolysis apparatus capable of converting polymer waste and low-value or contaminated polymers, collectively, **100**, to liquid and/or condensable hydrocarbon products including synthetic petroleum and a variety of its fractions including but not limited to light sweet crude oil, fuel additives, base oil, slack wax, paraffin wax, microcrystalline wax and condensate dominated by aromatic petroleum hydrocarbons. Many of the waxes discussed herein exit the reactor in a liquid phase, but tend to cool to a solid or slow-flowing liquid once collected. For this reason and for purposes of consistency and for purposes of this invention, wax

and waxes, regardless of where they are recovered in the process, will be treated as solids, solid products, and/or solid residue(s), unless specifically indicated otherwise.

This reactor **10** has a central rotating shaft **11** with sections, also hereinafter referred to as Zones, having varying auger or screw configurations. An optimum product mix is achieved by determining and establishing a variety of progressive temperature zones to affect optimal temperature ramps, and by varying screw configurations along the length of the reactor to control residence time within each respective temperature zone. This creates a plurality of temperature ramps and retention times (soaks) resulting in the apparatus of the present invention, which operates as a continuous process, having the thermal efficiency advantage of Zone-delineated conversion. The feed to the apparatus can be a combination of mixed and/or varying solids with mixed and/or varying petroleum-based liquids, collectively the “hydrocarbonaceous material” **100**. As used herein “petroleum-based liquids” and “hydrocarbon liquids” will be used interchangeably and is meant to include used oil, waste oil, gasoil, refinery bottoms, cylinder oil, and the like. The process control provides for efficient conversion of widely variable raw material streams, highly contaminated raw material streams, and raw material streams having inconsistent compositions over time.

The apparatus of the present invention accepts shredded polymer waste **100**, which may or may not be contaminated by non-polymer fractions. For this purpose, in addition to thermoplastic and thermoset plastics (“plastic”), “polymer waste” can include elastomers (or “waste elastomers”) such as scrap tires, rubber residue, rubber belting, EPDM rubber sheet, membrane or extrudate, and the like. This polymer waste is continuously fed to a Zone-delineated thermal reactor **10**. Petroleum based liquid in any proportion and/or mineral-based additives and/or melt-phase catalyst can also be added if desired to the reactor at the beginning of the zonal sequence **101** (Zone 1), and are mixed with the polymer waste in the reactor. As the raw material charge is advanced along the length of the reactor, phase change occurs as it is progressively compressed or otherwise experiences reduction in volume in Zone 2 **201** to expel entrained atmospheric air and heated via a temperature ramp or gradient until entrained moisture in the polymer waste boils, resulting in steam formation, and subsequent melting in Zone 3 **301**. The melt is then heated in another thermal ramp and advanced through a mixing, molecular destabilization and heteroatom scavenging zone (Zone 4) **401** of controlled maximum temperature in the reactor. Mixing of the melt in this zone (Zone 4) **401** over a controlled

residence time and temperature results in molecular destabilization, decomposition of cellulose to char and additional steam, decomposition of a number of plasticizers and organic additives to vapor recoverable as condensable petroleum product, near complete scavenging of sulfur, near complete reduction of the organic halogens chlorine and bromine, partial reduction of the organic halogen fluorine, and near complete reduction of terephthalic acid to benzoic acid and benzoic acid to benzene. Hard wax product can be discharged from Zone 4 **401** at its termination and transition to Zone 5 **501**. Remaining melt which has not been discharged directly from the thermal reactor at the termination of Zone 4 **401** to recover hard wax is subsequently advanced through another thermal ramp to a zone (Zone 5) **501** in which the majority of pyrolysis occurs. This pyrolysis occurs over a residence time optimized per category of raw material to be decomposed. Advancing the remaining mass through a Zone 5 **501** environment of controlled maximum temperature and adequate residence time results in pyrolysis products of optimum yield and composition. As the remaining mass exits the pyrolysis zone **501**, it experiences yet another thermal ramp at the introduction to Zone 6 **601**, thereby promoting devolatilization of the char and coking of residual aromatic hydrocarbons and polynuclear aromatic hydrocarbons over adequate residence time. Accordingly, after the residual solid moves from Zone 6 **601** to Zone 7 **701**, it is continuously discharged from Zone 7 **700** as dry and friable, finely divided, residual solid material, which is not saturated with adsorbed aromatic and polynuclear aromatic hydrocarbons. These remaining solids are continuously removed from the apparatus as char which may contain entrained metals (precious and/or nonprecious), glass, stones and the like if these contaminants are present in the raw material feed. Stated another way, "char" is carbon residue and residual solids other than carbon remaining from the decomposition of hydrocarbonaceous material.

Hydrocarbonaceous materials are introduced as a blend of raw material **100** into a primary, thermal, anaerobic, inclined, Zone-delineated screw reactor **10**. The reactor has a cross section and magnitude of incline, if any, **20**, or optional decline, if any, **20**, as selected to promote transport, mixing and reaction of differing raw hydrocarbonaceous materials as well as to discharge paraffin or microcrystalline wax from discharge port **420** at the termination of Zone 4 **401** and/or condensable hydrocarbons from discharge ports **520** and **530** located in Zone 5 **501**, and residual solid char from exit **700** in Zone 7 **701**. The varying screw configurations are coupled with a plurality of temperature zones. As this is a single piece of equipment, operated in

a continuous process, there may not necessarily be clear demarcations between Zones, such that one Zone might incidentally transition or overlap with the succeeding Zone.

The Zones are generally defined and/or delineated by the geometry of the internal screw or auger in plurality with its external reactor to establish desired respective Zonal residence times coupled with the respective operating temperature maintained in that Zone for each desired rate of process throughput. Design of a cylindrical, continuous process Zone-delineated thermal reactor is conducted to allow for construction of that reactor having adequate but not unnecessary length at its respective diameter to promote adequate heat transfer to the hydrocarbonaceous material over the appropriate residence time in each Zone, thereby accomplishing the desired chemical reactions over required residence times to desired magnitudes of completion for the desired overall rate of process throughput. Preferably, continuous reactor components are designed in context of an interactive thermal and kinetic model incorporating variables including, among other things, reactor orientation, reactor length, reactor diameter, materials of reactor construction, screw design, hydrocarbonaceous material throughput rate, density and thermal conductivity, kinetic viscosity, Zonal retention time, inter-Zonal temperature ramp, etc. That model must have the capacity to forecast the outcome of operating the present invention to decompose any raw material composition which may be encountered with a desired or tolerable outcome. In the absence of such a model, an optimal geometry may or may not be derived from trial and error which can, especially in this context, have undesired or even catastrophic results.

The geometry of a screw conveyor typically is determined by the ratio of flight outside diameter to spacing between flights (blades). This ratio will be referred to as “pitch” or “pitch ratio” herein. The typical ratio of flight outside diameter to blade spacing is 1:1, or a pitch ratio of 1, where the spacing to outside diameter is equal. This will be a standard pitch, with lesser spacings being, for example, a shorter pitch or pitch ratio greater than 1:1, or a half pitch or pitch ratio of 2:1 resulting in longer residence time, or a quarter pitch or pitch ratio of 4:1 resulting in an even longer residence time, or greater spacings being a long pitch or pitch ratio of less than 1:1 resulting in a shorter residence time. The embodiment of the present invention illustrated in FIG 1 also includes a mixing section coincident with Zone 4 **401**, in which a ribbon mixer **410** having open segments with flighting designed to promote mixing, rather than transport, is deployed between adjacent screw conveyor segments **310** and **510**. Accordingly, Zone 1 **101**, Zone 2 **201** and Zone 3 **301**, collectively, of the present invention serve as a screw reactor, Zone

4 **401** serves as a plug reactor, and Zone 5 **501**, Zone 6 **601** and Zones 7 **701**, collectively, serve as a screw reactor. The diameter of the apparatus is constant; the ratio within the screw conveyor sections can change because the blades are more closely spaced or more widely spaced.

5 Other embodiments of the present invention having process zones beginning with raw material introduction into the system (Zone 1 **101**), then proceeding with volume reduction and/or compression (Zone 2 **201**), the proceeding with raw material phase change to melt (Zone 3 **301**), then proceeding with decomposition of certain plasticizers and additives as well as evolution of hydrochloric acid, among other things, concurrent and/or subsequent molecular destabilization (Zone 4 **401**), then proceeding with pyrolytic decomposition (Zone 5 **501**), then
10 proceeding with char devolatilization and/or coking (Zone 6 **601**), and ending with discharge of solid product (Zone 7 **701**) can be deployed in any configuration over a wide variety of scalabilities to accommodate all economically viable throughput solutions. The system embodied by the present invention is modular, scalable and versatile, being adaptable to applications having varied raw material compositions and desired throughput rates. Examples of the present
15 invention's versatility include application of a Zone-delineated process to any system configuration. Note that while some but not all of the preferred embodiments of this invention are described in the following detailed descriptions of the invention, a variety of modifications and changes within the spirit of the invention will become evident to persons skilled in the art from disclosures made in the preceding and following detailed descriptions. Accordingly, the
20 preceding and following descriptions are not limitative of the present invention.

It should be noted that in this application, the terms "reactor", "retort" and "apparatus" are frequently used interchangeably. In all cases, unless noted otherwise, these terms refer to the present invention.

25 This reactor **10** features a generally cylindrical, linear reactor having a long central rotating shaft **11**, running the length of the apparatus, comprising sections having varying auger or screw configurations. The precise means of rotating the shaft **11** is not critical, and can include any means known in the industry. The varying screw configurations coincide with and delineate a plurality of temperature zones.

30 The incline **20** can be between about 1° and about 20° off of horizontal **30**, with the preferred incline being about +2° to about +6°. The reactor **10** can also be oriented or pitched in the opposite direction, or at a decline between about 1° and about 20° off of horizontal **30**, with

the preferred decline being about -2° to about -6° for declining orientation. This gives a possible range of between about -20° to about $+20^{\circ}$ with respect to the horizon **30**.

The preferred embodiment of incline is deployed when raw material compositions, which, upon heating, result in throughput viscosities which can be transported through an inclined screw reactor. Vapors evolving from decomposition of the raw material move downstream and up-slope through progressively hotter zones until reaching discharge ports **520** and **530** under the relative vacuum of the integral condenser train, one embodiment of which is illustrated in FIG 2. In inclined deployment, zone-delineated heat control is readily maintained in the solid and melt phases while this denser material makes continuous contact with the heated skin of the cylindrical reactor and/or an optional heated internal screw deployed when external heating alone cannot overcome the poor thermal conductivity of the hydrocarbonaceous material. In inclined deployment, melt level **50** is maintained at a vertical elevation dictated, in dynamic equilibrium, by the rate of mass loss in Pyrolysis Zone **5** **501** versus rate of feed introduction in Zone **1** **101**. In any inclined orientation, the thermal reactor operates as a screw reactor in Zones **1** through **3** and Zones **5** through **7**, and as a stirred plug reactor in Zone **4** **401**.

The opposite orientation of decline is deployed when raw material compositions, which, upon heating, result in throughput viscosities which are difficult to transport through in an inclined screw reactor. In this declined deployment, zone-delineated heat control can be maintained in the vapor phase in open headspace as vapor evolving from the raw material moves downstream and down-slope through progressively hotter zones until reaching discharge ports **520** and **530** under the relative vacuum of the integral condenser train. To further promote and accelerate this vapor movement, and to minimize the tendency for excessive heat to rise in the open headspace of a reactor in declining orientation, thereby potentially over-cracking vapor-phase molecules, a portion of the non-condensable gas discharged from the final condenser can be optionally re-injected into the reactor at injection port **400** and/or steam withdrawn from vent **200** can be optionally re-injected into the reactor at injection port **400**. The preferred temperature of injected non-condensable gas and/or steam, if any, is slightly below the operating temperature of the point of injection. The injection temperature is high enough to prevent any condensation, thereby keeping the injected vapor in the vapor phase, but low enough to consume heat energy from the head space, thereby mitigating any condition of excessive cracking of vapor-phase molecules. Although vapor phase heat regulation is important in all phases in any orientation,

consideration of heat regulation in the vapor phase becomes especially critical in the declining orientation because melt level will, as the result of flow of melt in response to the force of gravity, be a long, declining surface above which head space open to vapor flow will be present over a much greater length of reactor **10** and a much broader range of temperatures in reactor **10** than in the opposing inclined orientation. In declined deployment, Zone-delineated heat control can also be maintained in the denser solid and melt phases as they make continuous contact with the heated skin of the cylindrical reactor and/or an optional heated internal screw deployed when external heating alone cannot overcome the poor thermal conductivity of the hydrocarbonaceous material. In the declined orientation, although the thermal reactor operates as a screw reactor in Zones 1 through 3 and Zones 5 through 7, and as a stirred plug reactor in Zone 4, solid and melt phase material retention time in Zone 4 is likely to be reduced by its tendency to flow downhill in response to the force of gravity, necessitating increase in the length of Zone 4 for the declined orientation to maintain adequate residence time for molecular destabilization and heteroatom scavenging reactions to occur to the desired degree of completion.

In either the inclining or declining embodiment, proper placement of discharge ports **520** and **530** provides for optimum recovery of vapor-phase hydrocarbon molecules without over-cracking and resultant excess non-condensable gas and char production. Given that discharge ports **520** and **530** are in plurality with condensers **80**, and that operation of condensers results in relative vacuum consistent with removal of vapor-phase molecules from the vapor stream, it is important to recognize and use this resource of relative vacuum to the benefit of the process. Accordingly, the preferred embodiment is placement of discharge port **520** in Zone 5 **501** immediately above melt level **50** in the inclined deployment of reactor **10**; there is no adjustment to this preferred embodiment in the declined deployment of reactor **10**. Placement of discharge port **520** as described allows for removal of evolved vapor before that vapor would otherwise experience the higher temperature environment of Zone 6 **601** in which gas-prone cracking and coking occur. Likewise, placement of discharge port **530** at the transition between Zone 5 **501** and Zone 6 **601** promotes immediate quenching of vapor evolving from Zone 6 **601**, such vapor containing residual aromatic hydrocarbons that, if not quenched as they enter discharge port **530**, would otherwise be coked to char and methane if they were to remain in Zone 6 **601** and Zone 7 **701**.

The temperature of the apparatus is varied along its length from Zone to Zone, depending on the desired functionality, and is controlled via external heating means (not shown). Optionally, the internal screw can also be heated when external heating alone cannot overcome the poor thermal conductivity of the hydrocarbonaceous material. The heating means is not critical, and can include electric heating elements, radiant heating, direct fired heating thereby consuming the gaseous product produced by the present invention, thermal jacketing, using heat transfer medium known to the industry, including but not limited to, Dowtherm®, molten lead, molten salt, molten sodium, and the like.

Although modest temperature variation over operating periods is well tolerated by the reactor **10**, for purposes of efficiency and to maintain the plurality between Zone temperature and residence time, it is desirable to maintain dynamic equilibrium in reactor **10**. Dynamic equilibrium is achieved by maintaining a constant raw material throughput rate and constant reactor temperatures in each Zone once these temperatures have been achieved when operations ensue. The slower the raw material throughput, the longer the residence time. Although the dynamic equilibrium has been interrupted, less heat may be required to successfully drive the desired chemical reactions over a longer residence time so long as operations continue within rate-determining limits. In contrast, the faster the raw material throughput, the shorter the residence time. Although the dynamic equilibrium has been interrupted, more heat may be required to successfully drive the chemical reactions over a shorter residence time so long as operations continue within rate-determining limits. In both cases, if rate-determining limits are exceeded by variations in temperature and/or residence time, the desired reactions will not be experienced, and undesirable reactions may result. Accordingly, if the dynamic equilibrium is not maintained, operations in disequilibrium pose risk to efficient system operation and consistency in product quality.

Although it is critical to maintain the plurality between Zone temperature and residence time, limits exist as to functional ability to maintain this plurality if the dynamic equilibrium is interrupted. These limits stem from, among other things, reactor design capacity, fixed thermal conductivity of the hydrocarbonaceous material and reaction kinetics. For example, an excessive feed rate beyond that contemplated in reactor design is likely to result in residence times being insufficient to facilitate heat transfer to the hydrocarbonaceous material. Those reduced residence times may be insufficient for the desired reactions to achieve the desired level of completion

even if adequate heat could be transferred to the hydrocarbonaceous raw material. In another example, in an attempt to compensate for faster raw material throughput, one might increase the temperature of the heating system. Although limited benefit is achieved by this action, the temperature differential between heated surfaces and the hydrocarbonaceous material can become so extreme as to prematurely promote reactions which ideally should occur in a successive Zone, thereby losing Zone definition in the reactor **10**. Risks created by overheating to compensate for excessive throughput include creation of excessive reactor pressure / unsafe operation conditions, as well as overproduction of gas and char at the expense of solid wax and/or condensable hydrocarbon yield. In another example, a feed rate far below reactor **10** capacity or chronic interruptions to feed can result in excessive residence times. Denser components of the hydrocarbonaceous material can, in an inclined reactor orientation, settle to the bottom of the melt column, displace materials of lower density and collect at the bottom of the melt column, promoting reactor **10** fouling requiring unscheduled production shut-down to correct the problem. Similarly, in the declining orientation, denser components of the hydrocarbonaceous material can settle to the bottom of the reactor and collect behind each flighting blade, similarly fouling the reactor **10**, although in many more places along the length of the reactor.

The reactor **10** is comprised of a series of distinct, throughput process Zones through which the raw material blend is continually heated and advanced. There are seven of these throughput process Zones: the Raw Material Feed Zone **101**, the Compression Zone **201**, the Melt Zone **301**, the Mixing, Molecular Destabilization and Heteroatom Scavenging Zone **401**, the Pyrolysis Zone **501**, the Devolatilization Zone **601**, and the Char Discharge Zone **701**.

Zone 1: Raw Material Feed Zone. This zone **101** is operated at ambient temperature and pressure for a residence time of less than one minute. In the embodiment of the present invention shown in FIG 1, raw materials are introduced to the apparatus at the entrance **100**. The exact means of introducing feed materials is not critical, and may be of any method known in the industry so long as the feed method selected is sufficiently robust and effective thereby avoiding failure to feed shredded and often highly compressible raw materials, and isolate undesirably large and bulky non-polymeric solid contaminants that will foul the reactor feed entrance **100** or the reactor **10** itself. The pitch ratio of the screw **110** in this zone is between 1.0 and 1.5. The

purpose of this zone is to accept material into the apparatus **10** and move the material into the next zone.

The present apparatus **10** allows for the purposeful combination of mixed and/or varying solids with any quantity, including zero, of mixed and/or varying petroleum-based liquids. It provides for efficient conversion of widely variable raw material streams, highly contaminated raw material streams, and raw material streams having inconsistent compositions over time. Additionally, hydrocarbonaceous materials can be fed at entrance **100** to the reactor **10** with finely divided, mineral-based additives selected from one or more melt-phase heteroatom scavengers in forms including but not limited to oxides, hydroxides and/or carbides of the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals and/or metalloids. Optionally, for example, when only light oil, diesel additive or gasoline additive is desired, feed materials can additionally include addition of one or more melt-phase catalysts in forms including but not limited to oxides, hydroxides and/or carbides of the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals, metalloids, non-metals and/or naturally-occurring & synthetic silicate minerals.

Addition of mineral-based additives and/or melt-phase catalysts at entrance **100** is optional, depending upon factors including but not limited to composition of the raw hydrocarbonaceous materials, desired product mix, e.g. ratio of produced oil to produced gas, ratio of produced wax to oil and desired molecular composition of condensable hydrocarbon products. For example, when addition of heteroatom scavengers is desired, the weight percentage of heteroatom scavenger of the total hydrocarbonaceous material added to the reactor, such percentage ranging from 0% to 20% or more, is determined by fate of the scavenger in the reactor. Thorough dispersion of mineral-based additives and/or melt-phase catalysts is critical to efficient use of these mineral-based additives and/or melt-phase catalysts and to prevent reactor fouling, especially in Zones 1 through 4 resulting from the presence of excessive finely divided mineral-based additives and/or melt-phase catalysts. Some but not all of the heteroatom scavenger will be available to participate in the desired reactions if dispersion of the scavenger in the hydrocarbonaceous material is not be complete. Moreover, some of the heteroatom scavenger may aggregate in the hydrocarbonaceous material prior to or after introduction of the hydrocarbonaceous material to the reactor, thereby reducing its availability to participate in the desired reactions. If only one primary reaction involving heteroatom scavenger is anticipated, the

optimal weight percentage of heteroatom scavenger added to the total hydrocarbonaceous raw material feed may be the sum of the amount of heteroatom scavenger stoichiometrically required to complete all desired dehalogenation and desulfurization reactions plus the amount of heteroatom scavenger not available to the desired reactions due to, for example, incomplete dispersion of heteroatom scavenger in the system. If more than one primary reaction involving heteroatom scavenger is anticipated, such scavenger can be consumed by competing reactions. As one of many possible examples, if the hydrocarbonaceous material includes polyvinyl chloride (PVC) and/or polyvinylidene chloride (PVDC) in the presence of polyesters of terephthalic acid (PET), competing reactions may include conversion of hydrochloric acid evolving from PVC and PVDC to calcium chloride salt and water, as well as promoting conversion of the sublimates terephthalic acid and benzoic acid evolving from the decomposition of PET to benzene. Accordingly, the amount of heteroatom scavenger added to the hydrocarbonaceous material must be sufficient to allow for all desired competing reactions to achieve completion. Similarly, the number of polymer species and their relative concentrations in the raw hydrocarbonaceous material will impact polymer decomposition rates. For example, citing simple first order kinetics, rate limited on a single species, the addition of more of that species can promote acceleration of the decomposition rate. Determination of optimum weight percentages, if any, of heteroatom scavengers to the raw hydrocarbonaceous material must be made with thorough knowledge of the composition of the hydrocarbonaceous material, as well as any anticipated variance of that same material over time. Similarly, polymer decomposition rates can change via catalyst addition to the hydrocarbonaceous material whereby energy barriers are lowered, resulting in interactions to accelerate some, but not all, decomposition reactions. The selection and quantity of catalyst, if any, added to the hydrocarbonaceous material is also a function of the composition of the hydrocarbonaceous material.

Zone 2: Raw Material Volume Reduction / Compression Zone. This zone **201** is operated to reduce the volume of the hydrocarbonaceous material, expel atmospheric air from the hydrocarbonaceous material at a temperature below the flash point of the hydrocarbonaceous material, and to generate and expel steam as moisture in the hydrocarbonaceous material boils. Zone 2 **201** is operated with an internal temperature, as opposed to skin temperature, not less than ambient temperature and not more than 220°F, more or less, at ambient pressure or, optionally, for example when water vapor must be minimized in the reactor **10**, under a vacuum

200 less than 0.1 atm, more or less, for a residence time of less than three minutes, more or less. In the embodiment of the present invention shown in FIG 1, the pitch ratio of the screw 210 in this zone is between 1.5 and 2.0. The volume of the hydrocarbonaceous material is reduced, and feed materials are compressed by the rotating screw 210, which forces air and moisture, as steam, out of the system under optional vacuum 200. Raw material moisture reduction is accomplished thereby to a moisture content ranging from less than 1% moisture by weight up to 15% moisture by weight, more or less. In the preferred embodiment, moisture is reduced to about 10% by weight. Expelled air and moisture can be routed to a carbon bed; the moisture condensed and disposed of as waste water. The remaining air can, for example to promote odor control, optionally be directed to the air intake of a direct-fired reactor heating system or the air intake of a generator set ("genset", not shown) comprising a diesel generator fueled by the non-condensable gas product discharged from gas discharge port 830 (shown in FIG 2) plus a dynamo. A genset is used to generate electricity, which can be used utilized by the apparatus and/or distributed to other parts of the facility. Possible uses for a genset include but are not limited to heating the reactor 10 and powering the motor that rotates the shaft 11.

Zone 3: Raw Material Melt Zone. This zone 301 is operated with an internal reactor temperature range between 220°F and 572°F, more or less, at *in situ* derived reactor pressure for a residence time of not less than 15 minutes and not more than 45 minutes, more or less. For example, if the hydrocarbonaceous material is composed of polyisobutylene, some or all of the polyisobutylene will enter Zone 3 as a melt, depending upon the isomers of polyisobutylene constituting the material. In another example, if the hydrocarbonaceous material is composed of low density polyethylene, the minimum Zone 3 operating temperature is 220°F or more, in an operating temperature adequate to accomplish melting of all constituents have a melting point at or below 220°F, more or less. In yet another example, if the hydrocarbonaceous material is composed of polystyrene, the minimum Zone 3 operating temperature is 464°F or more, in an operating temperature adequate to accomplish melting of all constituents have a melting point at or below 464°F, more or less. In the embodiment of the present invention shown in FIG 1, the screw 310 has a pitch ratio between 2.0 to 5.0, with a preferred pitch of 2.5. If organic halogens are present in the melt, operation of the present invention will result in generation of a relatively modest yield of halogen acids in the temperature range of not less than 305°F. Additional hydrochloric acid may evolve in Zone 3 301 as the Zone 3 operating temperature approaches

572°F. In that event, salts resulting from the reaction of heteroatom scavenger and halogen acids will begin to form, acting with remaining halogen acids as melt-phase cracking catalysts generated *in situ* by operation of the present invention.

Zone 4: Mixing, Destabilization and Heteroatom Scavenging Zone. This zone **401** is operated with an internal reactor temperature range of not less than 572°F and not more than 690°F, more or less, and *in situ* derived reactor pressure for a residence time of not less than 30 minutes and not more than 120 minutes, more or less. The purpose of this section of the apparatus is to thoroughly mix the melt for a prolonged period, destabilize molecules comprising the melt, scavenge sulfur (desulfurize), and convert organic halogens to solid salts (i.e. dehalogenate). In a preferred embodiment, there is no helical screw in this zone; instead the shaft **11** drives a ribbon mixer **410**. Other embodiments (not shown) could employ other mixing means such paddle mixers, cut and folded auger mixers, and the like. The reactor **10** operates as a plug reactor in Zone 4.

Polymer cracking in the raw materials is promoted by multiple-stage generation of hydrochloric acid, hydrobromic acid and/or hydrofluoric acid, as such acids are commonly identified as cracking catalysts. Concurrently and subsequently, reaction of these halogen acids with heteroatom scavenger results in conversion of organic halogens in the hydrocarbonaceous material to salts which are also identified as cracking catalysts. Accordingly, in addition to Zone 4 **401** generation of hydrocarbon vapors as a result of decomposition of certain polymer plasticizers and additives in Zone 4, operation of Zone 4 also results in production of hydrocarbon vapors at temperatures well below those predicted by standard thermal and kinetic models. Upon condensation, such hydrocarbon vapors produced in Zone 4 **401** result in not less than 2% nor more than 22%, more or less, of the total condensable product yield of the present invention. The efficacy of heteroatom scavenging and rate of production of product oil resulting from operation of Zone 4 **401** are controlled by factors including but not limited to ramp rate to achieve Zone 4 operating temperature, residence time in Zone 4, and interplay of the geometry of Zone 4 vs. raw material throughput rate and composition. Zone 4 geometry is a function of factors including reactor **10** length, reactor diameter, screw design and, to a far lesser degree, total mass loss from Zone 4 melt. Heteroatoms removed from the hydrocarbonaceous melt via reactions in Zone 4 accumulate largely as salts in the char material, which is removed at a later stage, described below.

In addition to the products of pyrolysis recovered from subsequent segments of the present invention, microcrystalline and/or paraffin wax product can be directly discharged from takeoff port **420** located at the transition from Zone 4 **401** to Zone 5 **501**. While mixed melt within the first half of Zone 4 maintains characteristics of melted plastic when discharged and examined upon freezing, as the material progressively advances within the last half of Zone 4 toward the transition of Zone 4 **401** to Zone 5 **501**, the material begins to experience cracking that is dominated by homologous cracking, gradually losing viscosity and, upon freezing, becoming more friable, eventually taking on the characteristics of hard wax when held at adequate residence time in the temperature range of 352⁰C (670⁰F) to 365⁰C (690⁰F). Given that relatively little char has formed prior to pyrolysis in Zone 5, wax discharged from takeoff port **420** is contaminated only by dissolved lower molecular weight hydrocarbon molecules which have not evolved from the wax as vapor, non-hydrocarbonaceous components of the raw material introduced into the reactor, and reaction byproducts, if any, of heteroatom scavengers, if any were introduced. The reactor can be operated with or without wax take-off. If the wax is not removed, it remains in the reactor in a liquid state, due to the temperature, and is further processed as an intermediate product in the liquid melt. If it is removed and recovered, it will cool to a solid state at room temperature. As such, wax is to be considered a solid product.

Certain non-polymeric materials in the hydrocarbonaceous material will participate in and/or promote reactions resulting in changes in end-product molecular composition. For example, the presence of paper as a contaminant of the raw hydrocarbonaceous material introduced into the reactor **10** may cause a proportional increase in concentration of aromatic and polynuclear aromatic hydrocarbons at the expense of paraffin and/or isoparaffin in the wax recovered from takeoff port **420** shown on FIG 1 as well as in the condensable hydrocarbon vapors condensed and recovered from takeoff ports **831** and/or **833** and/or **835** shown on FIG 2. If the primary products desired include an aromatic cut, the presence of paper in the raw material can offer an advantage. In another example, laminate food-packing wastes including aluminum foils as components of the laminate can be present in municipal waste plastics. After the polymer layers melt, the aluminum foil is released. The metallic surface of the aluminum promotes rapid depolymerization on its surface, resulting in increased yield of the wax fraction.

Wax discharge from takeoff port **420** results in a higher total process yield of condensable petroleum hydrocarbons than operation of the present invention with no wax

discharge from takeoff port 420. When condensable hydrocarbons are removed as wax from takeoff port 420, those removed molecules do not experience pyrolysis in Zones 5 501, and 6 601, and the proportional yield of gas and char is lower. In general, the relatively limited amount of char suspended in wax discharged from takeoff port 420 is composed largely of carbon
5 resulting from the decomposition of cellulose included as a contaminant to the raw material feed, non-polymeric matter included as a contaminant to the raw material feed, reacted and un-reacted heteroatom scavenger, if heteroatom scavenger is added, melt-phase catalyst created *in situ*, and any melt-phase catalyst added to the raw material feed.

Wax resulting from decomposition of mixed polymers and recovered from takeoff port
10 420 exhibits many characteristics of microcrystalline wax in contrast to paraffin wax, including ratio of unbranched to branched alkanes, darker color, higher melting point, hardness and adhesive characteristics. In general, if takeoff port 420 is located closer to or within the transition between Zone 4 401 and Zone 5 501, properties of the wax appear more like paraffin wax, although the content of suspended char is higher.

15 Successful recovery of microcrystalline and or paraffin wax product from takeoff port 420 is accomplished at inclined reactor orientation when the level of melt boundary 50, also described as the level of melted and destabilized hydrocarbonaceous material entering Zone 5 501 from Zone 4 401, is maintained by feeding the raw hydrocarbonaceous material to reactor 10 at an adequate rate to maintain the level of melt boundary 50. Unsuccessful recovery of
20 microcrystalline and or paraffin wax product from takeoff port 420 results from allowing melt boundary 50 to fall below takeoff port 420 due to mass loss via vapor evolution and vapor discharge. If the feed rate is fast enough, melt boundary 50 will be maintained above discharge port 420. If the feed is too slow, melt boundary 50 will fall below discharge port 420. If the feed rate is too fast, the melt boundary 50 will be high enough to discharge "wax" from discharge port
25 420, but melt boundary 50 would rise to cover vapor discharge ports 520 and, in an extreme event, also cover discharge port 530, thereby preventing open vapor flow through the ports and creating undesirable high pressure conditions. In such a case, raw material feeding to the reactor at an excessive throughput rate could result in a condition where the hydrocarbonaceous material has inadequate residence time to pyrolyze in succeeding Zone 5 501. Accordingly, raw material
30 feeding to the reactor at an excessive rate could also result in fouling of subsequent Zones 6 601 and 7 701 with un-reacted hydrocarbonaceous material. As a safety measure and to prevent an

unanticipated acute or even catastrophic reactor failure, standard pop-off valves (not shown) are positioned on reactor **10** at positions including the transition between Zone 4 **401** and Zone 5 **501**, as well as in Zone 6 **601**.

Successful recovery of microcrystalline and or paraffin wax product from takeoff port **420** is accomplished at declined reactor orientation with lower risk of covering vapor discharge ports **520** and **530** thus lower risk of creating undesirable high pressure conditions.

Zone 5: Pyrolysis Zone. This Zone **501** is operated with an internal reactor temperature range appropriate to the blend of raw material introduced into the primary thermal reactor, commonly between 365°C (690°F) and 393°C (740°F), more or less, at the lower end of the temperature range, and 454°C-488°C (850°F-910°F), more or less, at the upper end of the temperature range, and at *in situ* derived reactor pressure, generally not more than 5.0 psig, more or less, for a residence time of not less than 30 minutes and not more than 90 minutes, more or less. In the embodiment of the present invention shown in FIG 1, the screw **510** has a pitch ratio between 2.0 to 5.0, with a preferred pitch ratio of 2.5 to 3.0. The lack of oxygen, coupled with high temperature over the required residence time, results in various pyrolysis reactions taking place governed by high-order reaction kinetics, breaking down the polymeric material into volatile vapors and char material. The vapor stream is composed primarily of vapor, but may contain aerosol liquids and condensable molecules. This vapor stream is subject to further downstream treatment (described below), wherein condensable and non-condensable vapors are separated. The condensable vapors form liquids, including oil, light sweet crude oil, fuel additives, and base oil. A fraction can form solid products, in the form of slack wax. The non-condensable vapors or gases are recovered and can be optionally passed to a genset (described above) to produce electric power or can be circulated prior to use elsewhere as the vapor blanket over liquid product (discussed in more detail below).

The ultimate yields of condensable hydrocarbons, as well as relative material balance of oil, gas, char and inorganic residue, are controlled by several factors. These factors include, but are not limited to, operating temperature, interplay of the geometry of Zone 5 **501** versus raw material throughput rate, residence time required for pyrolysis reactions to go to completion, desired magnitude of reaction completions, raw material composition, and recovery, if any, of wax product from takeoff port **420**. Zone 5 geometry is a function of factors including but not limited to reactor length, reactor diameter, screw/mixer design, and forecasted rate of mass loss

via vapor evolution and emission from Zone 5 melt, such mass loss being a key input from an interactive thermal and kinetic model into design of Zone 5 geometry. The process comprising the present invention is characterized by the virtual absence of oxygen and organic halogens in Pyrolysis Zone 5 **501** coupled with the presence of *in situ* derived catalysts, including salts.

5 Operation of Zone 5 **501** results in significant loss of mass of the hydrocarbonaceous material as pyrolysis proceeds on the continuously advancing hydrocarbonaceous material, and vapor is expelled from the reactor. Accordingly, when reactor **10** is in an inclined orientation, at the transition from the termination of Zone 4 **401** to the beginning of Zone 5 **501** the internal volume of the inclined reactor in Zone 5 is saturated with molten hydrocarbonaceous material.

10 However, as the material is advanced along the length of Zone 5, the internal volume of reactor in Zone 5 is no longer saturated with molten hydrocarbonaceous material, resulting in the melt boundary **50**. This creates head space and relative volumetric increase in head space over the molten and pyrolyzing hydrocarbonaceous material as the material is advanced toward Zone 6

15 **601**. The surface of the melt boundary **50** of the pyrolyzing hydrocarbonaceous material is a boiling and dynamic transitional interface of vapor above incompletely pyrolyzed hydrocarbonaceous material. This surface **50** continually rises and falls as it boils under conditions of the dynamic equilibrium until the hydrocarbonaceous material is effectively pyrolyzed, leaving only the solid char material and any incompletely pyrolyzed hydrocarbonaceous material to be advanced into Zone 6 **601** for devolatilization and coking.

20 Accompanying and correlative change in viscosity of the hydrocarbonaceous material is experienced in the reactor as pyrolysis proceeds to completion.

 Optionally, for example, in cases where accelerated evacuation of product vapor from the reactor **10** is desired, and depending upon the product mix desired, a non-condensable carrier gas can be introduced into the coldest portion of Zone 5 **501** at purge gas port **500**. Such non-

25 condensable carrier gas is comprised of nitrogen and/or a recycled non-condensable gas fraction resulting from operation of the present invention and/or methane from natural gas. Use of a recycled gas and/or methane as an alternative to nitrogen for carrier gas has a benefit of increased BTU content of produced process gas in the absence of dilution by nitrogen, as well as decreased operating expenses by eliminating the need to purchase or generate nitrogen. This

30 aspect of the present invention can, depending upon raw material composition and range of operating conditions, also result in the unanticipated benefit of increase in oil yield,

unanticipated albeit modest benefit of slight increase in hydrogen concentration of the reactor atmosphere in the pyrolysis environment, and an unanticipated increase in the hydrogen concentration of resulting process gas.

Zone 6: Char and Residual Solids Devolatilization Zone. Zone 6 **601** serves to drive volatile hydrocarbons from the char as well as to convert any remaining oligomer and semi-volatile aromatic hydrocarbons to coke. Zone 6 is operated with an internal reactor temperature not less than the maximum pyrolysis temperature appropriate to the blend of raw material introduced into the thermal reactor, commonly between 454°C (850°F) and 488°C (910°F), more or less, and not greater than 982°C (1800°F), more or less, commonly and preferably between 593°C (1100°F) and 649°C (1200°F), more or less, and at *in situ* derived reactor pressure, generally not more than 5.0 psig, more or less. Zone 6 **601** is operated at an *in situ* derived reactor pressure, generally not more than 0.8 psig, more or less, and a residence time of not less than 15 minutes and not more than 60 minutes, more or less. In the embodiment of the present invention shown in FIG 1, the screw **610** has a pitch ratio between 2.0 to 5.0, with a preferred pitch ratio of 2.5 to 3.0. Vapor resulting from reactions occurring in Zones 5 **501** and 6 **601** is discharged to outlets **520** and **530** positioned in Zone 5 **501** and Zone 6 **601**. The outlets can be a single outlet **520**, or a plurality of outlets, including back-up or auxiliary outlets **530**.

A scrubber (not shown) can be used to recover any residual halogens not captured in Zone 4 **401** prior to discharge to step-down condensers **80**. This heteroatom scrubber is operated in a temperature range appropriate to recovery of halogens in each unique raw material blend, but not at an excessive temperature to promote cracking, for example between 338°C (640°F) and 365°C (690°F), more or less.

Vapor resulting from operation of Zone 6 **601** can be optionally routed to catalyst reactors and/or reflux reactors and/or fractionation columns (collectively, not shown) for further processing prior to discharge to step-down condensers **80**. Vapor emanating from Zones 5 **501**, 6 **601** and/or 7 **701** of the primary thermal reactor **10** and/or the scrubber can be routed to one or more secondary catalyst reactors and/or reflux reactors and/or fractionation columns (collectively, not shown). These reactors and/or columns are designed to optimize molecular size and molecular species distribution in the condensable product as may be desired.

In addition, the purpose of Zone 6 **601** includes completion of molecular cracking to the desired end point, also targeting decomposition of some but not all silanes and siloxanes.

Notably, of the hydrocarbonaceous material including polyfluoroethylene (PTFE), chloromethylaromatic silanes (a component of flexible, multi-layer circuit boards) or other halogenated species for which kinetic models describe dehalogenation at temperatures exceeding 454°C (850°F), capture of said halogens must be accomplished at a scrubber (not shown) located
5 downstream from reactor **10** and upstream of the condenser array **80**.

Optionally, if olefin content of the condensable products is problematic, an anti-oxidant/stabilizer/inhibitor (hereinafter referred to as “inhibitor”) can be injected downstream from discharge from reactor **10** and downstream from a point of vapor discharge from any catalyst reactors and/or reflux reactors and/or fractionation columns where temperature
10 mitigation is sufficient. The inhibitor may be comprised of 4-tert-butylcatechol, other alkyl catechols, 2,6-dinitro-p-cresol (DNPC), cuts of whole or topped asphaltic crude oil, phenylenediamine and/or commercially available materials in the category of oxy-compound inhibitors. The inhibitors are introduced to inhibit broad spectrum, downstream oxidative reactions involving metastable molecular species as well as additive polymerization which would
15 otherwise occur. The refluxed product stream at a temperature of about 280°F can be injected with inhibitor at a rate of about 0.00001 to 0.05 mole percent to condenser **801** if condenser **801** is operated at a maximum temperature below about 280°F or injected to condenser **803** if condenser **801** is operated at a maximum temperature above about 280°F.

Product vapor is discharged from discharge ports **520** and **530** or, if deployed,
20 downstream catalyst reactors and/or reflux reactors and/or fractionation columns and/or scrubbers to step-down condensers **80** in series, for example to condensers **801**, **803** and **805** shown on FIG 2, optionally supplemented by demisters **811**, **813** and **815** between condensers for those required applications where more efficient separation than condensers alone can achieve. A final demister system (not shown) can be deployed at the termination of the
25 condensation train when it is necessary to very efficiently remove residual aromatic hydrocarbons from the non-condensable gas product. Each condenser in the series is operated within a predetermined temperature range specified to isolate molecules within desired dew point ranges, resulting in condensable products having respective API gravities and pour points and/or melting points. In Fig. 2, the first condenser **801** in the series **80** operates at the highest
30 temperature range, and the final condenser **805** in the series operates at the coldest temperature range. Optional multiple demisters **811**, **813** and **815** are operated at temperatures corresponding

to the minimum operating temperatures of their respective condensers. The condensers and, where deployed, the demisters are fitted with collection vessels **821**, **823** and **825**, also known as knockouts, which provide for oil accumulation / takeoff, and oil-water separation as may be required for each petroleum cut that is to be recovered.

5 Condensable product cuts are recovered from each condenser and its dedicated demister to respective knockouts **821**, **823** and **825** that provide for density separation of *in situ* derived water and oil. Multiple condensers deployed in series **80** constitute a series of step-down condensers, also known as a condenser train. As an example, if the step-down condenser train is constructed in a fashion adequate to recover at least 4 cuts, four step-down condensers are
10 installed in series. Slack wax can be recovered from the first step-down condenser and its respective demister if operated between 300°F and 360°F, more or less, or, alternatively, slack wax and base oil can be recovered from the first step-down condenser and its respective demister is operated between 130°F and 300°F, more or less. Light sweet crude oil, sometimes described as diesel additive, can be recovered from the second step-down condenser and its respective
15 demister if operated between 90°F and 130°F, more or less. The majority of water can be recovered coincident with recovery of C₄-C₈ hydrocarbons, sometimes described as condensate or gasoline additive, from the third step-down condenser and its respective demister if operated between 60°F and 90°F, more or less. A light aromatic cut, as well as the principal balance of water, is recovered from the fourth and final step-down condenser and its respective demister if
20 operated between 35°F and 60°F more or less.

Liquid product can be routed to remote day tanks **831**, **833** and **835** as depicted in FIG 2 and subsequent product sale. Product tanks containing liquids having higher pour points or wax products that must be transported in the molten state are heated to a point minimally above
25 respective product pour points and/or melting points to provide for product transfer without distilling the products in their respective day tanks. The preferred embodiment is to maintain an anaerobic, non-condensable vapor blanket over liquid products to minimize product degradation via oxidation and retard the formation of tar and varnish resulting from additive polymerization that may occur, attributed to the presence of olefins, especially if inhibitor (as described above) is not added to the product. The vapor blanket can be comprised of non-condensable product gas
30 produced by the apparatus and discharged from gas discharge port **830**. Tank vapor inlets and vents can be pressure regulated and can be integral to the non-condensable gas discharge port

830 of the present invention. Heavy cuts recovered from the first condenser **801** can be recycled back into the process as described above if recovery and sale of heavy cuts is not desired.

Residual, non-condensable gas is recovered from non-condensable gas discharge port **830** and can be optionally passed to a genset (described above) to produce electric power. As previously noted, possible uses for this electric power include but are not limited to heating the reactor **10** and powering the motor that rotates the shaft **11**. Alternatively, the recovered non-condensable gas can be circulated prior to use elsewhere as the vapor blanket over liquid product in the liquid product tanks, consumed as fuel for direct-fired heating of the reactor apparatus, consumed as fuel for other purposes, or flared.

An optional genset, deployed when electric power generation is advantageous such as in remote locations or if the price of electricity is prohibitive, can take in make-up air from the compression zone **201** and/or areas where odor control is desired, e.g. post-consumer plastic raw material inventory storage, product driers and the like. Exhaust from the genset is routed to an air pollution control system.

In situ derived water, recovered from moisture entering the primary thermal reactor with the raw hydrocarbonaceous material and created by chemical reactions in the primary thermal reactor and elsewhere, can be separately recovered from the bottom of the knockouts **821**, **823** and **825** as depicted in FIG 2, passed over a carbon bed to adsorb dissolved aromatic hydrocarbon compounds, and subsequently vaporized to steam using waste heat from the genset, if deployed, from direct-fired heating of the reactor, and/or from elsewhere. Optionally, some portion of this steam can be returned to the process at injection port **400** located either in Zone 3 (as depicted in FIG 1) or in Zone 4, or alternatively injected in Zone 5 purge gas port **500** to promote the water-gas shift reaction. Alternatively, it can be routed to the air pollution control system as steam.

Zone 7: Char and Solids Discharge Zone. This zone **701** is operated with an internal reactor temperature range of not less than the maximum temperature of the preceding Zone 6 **601** and not greater than 1,800°F, more or less, at the start of the discharge zone to ambient temperature at the conclusion of discharge. It is operated at *in situ* derived reactor pressure, generally less than the system pressure experienced in Zone 6 **601** and not more than 1.0 psig, more or less, experienced in Zone 7 and downstream from vapor takeoff ports **520** and **530** which operate at relative vacuum due to their respective discharge to condensers **80**. The

residence time in the char discharge zone is not less than 15 minutes and not more than 30 minutes. Solid char is removed from the system, and inert contaminants including but not limited to glass, stones, metal and the like are sequestered from the reactor thereby with the char. In the embodiment of the present invention shown in FIG 1, the screw **710** has a pitch ratio between 2.0 to 5.0, with a preferred pitch ratio of 3.0 to 3.5. Solids from Zone 7 **701** are discharged via char exit **700**. Solids can be discharged to a sealed, cooled continuous process solids takeoff system (not shown) which can be a part of Zone 7 **701**. At its hot end, the char is purged with methane from natural gas. The system is designed to collect and/or separate and cool the solids, prevent re-adsorption of aromatic hydrocarbons and polynuclear aromatic hydrocarbons onto the char via ethane purge, and convert vapor entrained in the solids stream from a hot, anaerobic atmosphere dominated by methane purge gas in Zone 7 **701** downstream from char exit **700** to atmospheric air at a temperature below the flash point of the solids at the termination of Zone 7 **701**. This is done in such a manner so as to prevent spontaneous combustion and mitigate a dust explosion hazard. Given the very high insulating capacity of char, adequate residence time to allow cooling is critical to avoid spontaneous combustion.

The ability of the present invention to prevent the re-adsorption of aromatic hydrocarbons and polynuclear aromatic hydrocarbons onto the char in Zone 7 **701** is an important improvement over prior char recovery attempts. Pyrolysis char is notoriously known as being “sticky” given the presence of adsorbed tar composed of aromatic and polynuclear aromatic hydrocarbons. This problem is solved by the ability of the present invention to prevent re-adsorption of aromatic hydrocarbons and polynuclear aromatic hydrocarbons onto the char by hot methane purge prior to final cooling as it is discharged. As a result, given the absence of nearly all aromatic and polynuclear aromatic hydrocarbons, if the char must be disposed of as a waste, char discharged from Zone 7 **701** of the present invention does not exhibit the D018, D023, D024, D025, D026 or D036 toxicity characteristics of hazardous waste as described in 40 CFR Part 261.20. Given the great difference in disposal cost between non-hazardous solid waste and hazardous waste, this improvement of the present invention provides a means to dispose, if necessary, char as non-hazardous solid waste in contrast to hazardous waste as identified by the hazardous waste codes previously identified.

Fouling is a common problem and can occur at various points in the apparatus. Such points include discharge nozzles exiting the primary thermal reactor. This fouling is a result of

deposition of char, varnish, tar, terephthalic acid, benzoic acid, mineral salts and the like. These deposits can be removed and/or prevented from accumulating in various ways. One method is by operation of one or more mechanical rapper systems which are installed in the interior of the nozzles or other ports. One preferred embodiment of a rapper system is described in U.S. Patent
5 Application 13/735677, "Anti-Fouling Apparatus for Cleaning Deposits in Pipes and Pipe Joints" filed January 7, 2013. That rapper apparatus is designed to abrade the interior of surfaces prone to fouling while allowing bypass of vapor so as not to create unwanted pressure drops and pressure fluctuations, and are operated via scheduled manual use or via electronic control. The resulting vapor is passed through a filter element comprised of ceramic, glass fibers, and/or an
10 electrostatic device to mitigate passage of suspended particles to successive segments of the system. This reduces downstream system fouling, undesirable downstream chemical reactions, including catalysis, promoted by the presence of particles of char and/or salts and oxides and entrained/suspended particulate matter otherwise contributing to total metals concentration in the condensable products.

15 Although the invention has been described in detail with reference to particular examples and embodiments, the examples and embodiments contained herein are merely illustrative and are not an exhaustive list. Variations and modifications of the present invention will readily occur to those skilled in the art. The present invention includes all such modifications and equivalents. The claims alone are intended to set forth the limits of the present invention.

CLAIMS

What is claimed is:

1. An apparatus for pyrolyzing hydrocarbonaceous materials to produce useful vapor products and solid products comprising:

5 a generally cylindrical, linear reactor having a screw means for transporting said hydrocarbonaceous materials through said reactor,

means for feeding hydrocarbonaceous materials to said reactor,

means for heating said hydrocarbonaceous materials whereby they are processed and pyrolyzed to produce vapor products and solid products,

10 wherein said screw means extends substantially the length of said linear reactor;

wherein said screw means has zones for advancing and mixing hydrocarbonaceous material in the reactor,

means for removing vapor products from said processed hydrocarbonaceous materials in said reactor,

15 means for removing solid products from said reactor,

wherein said reactor has zones that are maintained in the apparatus within defined ranges of temperature,

means whereby said hydrocarbonaceous material is maintained within a zone for a range of defined residence times,

20 wherein said zones collectively comprise the complete environments required for pyrolysis,

means for rotating said screw,

25 wherein said screw means has a plurality of flight configurations for compressing said hydrocarbonaceous materials, for melting said hydrocarbonaceous materials to convert said hydrocarbonaceous materials from a solid to a liquid state, for mixing, destabilizing, desulfurizing, and dehalogenating said hydrocarbonaceous materials, for pyrolyzing said hydrocarbonaceous materials, for devolatilizing the pyrolyzed hydrocarbonaceous materials, and for discharging solid products from said hydrocarbonaceous materials.

2. The apparatus of claim 1 wherein the means for removing moisture from said hydrocarbonaceous material includes means for compressing and heating said hydrocarbonaceous materials to remove air and moisture from said hydrocarbonaceous materials.
- 5 3. The apparatus of claim 1 wherein the flight configurations of said screw incorporates a ribbon mixer.
4. The apparatus of claim 1 wherein said reactor is oriented with respect to the horizon at an angle between about -20° to about $+20^{\circ}$, preferably in an incline between about $+2^{\circ}$ to about
10 $+6^{\circ}$.
5. The apparatus of claim 1 wherein said reactor is oriented with respect to the horizon at an angle between about -20° to about $+20^{\circ}$, preferably in a decline between about -2° to about -6° .
- 15 6. The apparatus of claim 1 further comprising a series of step-down condensers for condensing and recovering liquid products from said vapor products.
7. The apparatus of claim 1 further including a wax collection takeoff port located between the mixing, molecular destabilization and heteroatom scavenging zone and the succeeding
20 pyrolysis zone.
8. The apparatus of claim 1 wherein the sequence for mixing, destabilizing, desulfurizing, and dehalogenating said hydrocarbonaceous materials has a screw flight configuration of a
25 ribbon mixer.
9. The apparatus of claim 1 further including a means for removing and collecting solid products wherein said solid products are char.
10. A pyrolysis process for conversion of hydrocarbonaceous material to produce useful
30 vapor products and solid products comprising:

providing a generally cylindrical, linear reactor having a screw means for transporting said hydrocarbonaceous materials through said reactor, having means for heating said hydrocarbonaceous materials whereby they are processed and pyrolyzed to produce vapor products and solid products, zones that are maintained in the apparatus within defined ranges of temperature and defined residence times,

compressing said hydrocarbonaceous material to remove entrained air and moisture from said hydrocarbonaceous material,

melting said hydrocarbonaceous material,

mixing said melted hydrocarbonaceous material to form a melted mixture whereby said melted mixture is subject to molecular destabilization, dehalogenation, desulfurization, and heteroatom scavenging,

subjecting said melted hydrocarbonaceous material to pyrolysis to convert said hydrocarbonaceous material to vapor products and solid products, and

recovering said vapor products and said solid products.

11. The process of claim 10 wherein said hydrocarbonaceous material is fed to said reactor with finely divided, mineral-based additives selected from one or more melt-phase heteroatom scavengers selected from the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals and metalloids, and mixtures thereof.

12. The process of claim 10 wherein said hydrocarbonaceous material is fed to said reactor with finely divided, mineral-based additives selected from (i) one or more melt-phase heteroatom scavengers selected from the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals and metalloids, and mixtures thereof; and, (ii) one or more melt-phase catalysts selected from the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals, metalloids, non-metals and silicate minerals, and mixtures thereof.

13. The process of claim 10 wherein the residence time in the compression zone is less than about one minute.

14. The process of claim 10 wherein the moisture is removed to about 10% moisture by weight.

15. The process of claim 10 wherein said hydrocarbonaceous materials are maintained in a melt zone at a temperature of about 220°F to 572°F to melt said hydrocarbonaceous materials.

16. The process of claim 10 wherein the residence time in the melt zone is about 15 minutes to 45 minutes.

17. The process of claim 10 wherein said hydrocarbonaceous materials are mixed, destabilized, desulfurized, and dehalogenated at a temperature in the range of about 572°F to 690°F.

18. The process of claim 10 wherein the residence time in the mixing, molecular destabilization and heteroatom scavenging zone is about 30 minutes to 120 minutes.

19. The process of claim 10 wherein the residence time in the feed zone is less than about one minute.

20. The process of claim 10 wherein the recovered solid products include microcrystalline wax and paraffin wax and mixtures thereof.

21. The process of claim 10 wherein the residence time in the pyrolysis zone is about 30 minutes to 90 minutes.

22. The process of claim 10 wherein said solid products are devolatilized at a temperature in the range of about 850°F to 1,800°F.

23. The process of claim 10 wherein the residence time in the devolatilization zone is about 15 minutes to 60 minutes.

24. The process of claim 10 wherein the residence time in the char discharge zone is about 15 minutes to 30 minutes.

25. The process of claim 10 wherein said hydrocarbonaceous materials are selected from the group consisting of plastic, thermoplastic polymer, thermoset polymer, hydrocarbon liquids, used oil, waste oil, gasoil, refinery bottoms, cylinder oil, waste elastomer, scrap tire, rubber residue, rubber belting, EPDM rubber sheet, membrane, and extrudate, and mixtures thereof.

26. The process of claim 10 further comprising condensing said vapor products to recover liquid products.

27. A process for conversion of hydrocarbonaceous material to produce useful wax products comprising:

providing a generally cylindrical, linear reactor having a screw means for transporting said hydrocarbonaceous materials through said reactor, having means for heating said hydrocarbonaceous materials whereby they are melted and processed to produce vapor products and solid products, wherein said solid products comprise one or more wax products, zones that are maintained in the apparatus within defined ranges of temperature and defined residence times,

feeding a mixture of hydrocarbonaceous material and heteroatom scavenging composition to said reactor,

compressing said hydrocarbonaceous material to remove entrained air and moisture from said hydrocarbonaceous material,

melting said hydrocarbonaceous material,

mixing said melted hydrocarbonaceous material to form a melted mixture whereby said melted mixture is subject to molecular destabilization, dehalogenation, and heteroatom scavenging,

recovering said wax products.

28. The process of claim 27 wherein said hydrocarbonaceous material is fed to said reactor with finely divided, mineral-based additives selected from (i) one or more melt-phase heteroatom

scavengers selected from the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals and metalloids, and mixtures thereof; and, (ii) one or more melt-phase catalysts selected from the group consisting of alkali metals, alkaline earth metals, transition metals, post-transition metals, metalloids, non-metals and silicate minerals, and mixtures thereof.

10

15

20

25

30