

ABSTRACT

An acrylic rubber contains 5 to 75 wt% of a methacrylate ester monomeric unit; and 0.5 to 5
5 wt% of a crosslinkable monomeric unit, wherein the methacrylate ester monomeric unit is at least one species selected from among a methacrylate alkoxyalkyl ester monomeric unit, a methacrylate polyalkylene glycol ester monomeric unit, and a
10 methacrylate alkoxy polyalkylene glycol ester monomeric unit.