

☐ Description : paged to paged
☒ Claim(s) : paged 15 to paged 18
☐ Drawing(s) : paged to paged
☒ Abstract : paged 19 to paged

LEAD-FREE BULLET

This invention relates generally to projectiles and more particularly to a projectile which is lead free.

5 Lead projectiles and lead shots which are expended in indoor ranges are said by some medical experts to pose a significant health hazard. Ingestion by birds, particularly water fowl, has been said to pose a problem in the wild. In indoor shooting ranges, lead vapors due to vaporized lead
10 from lead bullets is of concern. Disposal of the lead-contaminated sand used in sand traps in conjunction with the backstops in indoor ranges is also expensive, since lead is a hazardous material. Reclamation of the lead from the sand is an
15 operation which is not economically feasible for most target ranges.

Accordingly, various attempts have been made to produce effective lead-free bullets.

20 Density differences between bullets of the same size, fired using the same power charges result in differences in long range trajectory and differences in firearm recoil. Such differences are undesirable as the shooter needs to have a trajectory consistent with that of a lead bullet so the shooter knows
25 where to aim and a recoil consistent with that of shooting a lead bullet so the "feel" of shooting is the same as that of shooting a lead bullet. If these differences in trajectory and recoil are large enough, experience gained on the practice range will
30 degrade, rather than improve, accuracy when firing a lead bullet in the field.

Various approaches have also been used to produce shot pellets that are non toxic. U.S. Patent Nos. 4,027,594 and 4,428,295 assigned to the
35 applicant disclose such non-toxic shot. Both of these patents disclose pellets made of metal powders

wherein one of the powders is lead. U.S. Patent Nos. 2,995,090 and 3,193,003 disclose gallery bullets made of iron powder, a small amount of lead powder, and a thermoset resin. Both of these
5 bullets are said to disintegrate upon target impact. The main drawback of these bullets is their density, which is significantly less than that of a lead bullet. Although, these are not entirely lead free, the composition of the shot or bullets is designed
10 to reduce the effects of the lead. U.S. Patent No. 4,881,465 discloses a shot pellet made of lead and ferro-tungsten, which is also not lead free. U.S. Patent Nos. 4,850,278 and 4,939,996 disclose a projectile made of ceramic zirconium which also has
15 a reduced density compared to lead. U.S. Patent No. 4,005,660 discloses another approach, namely a polyethylene matrix which is filled with a metal powder such as bismuth, tantalum, nickel, and copper. Yet another known approach is a frangible
20 projectile made of a polymeric material which is filled with metal or metal oxide. U.S. Patent No. 4,949,644 discloses a non toxic shot which is made of of bismuth or a bismuth alloy. However, bismuth is in such short supply that it is of limited
25 utility for projectiles. U.S. Patent No. 5,088,415 discloses a plastic covered lead shot. However, as with other examples discussed above, this shot material still contains lead, which upon backstop impact, will be exposed to the environment. Plated
30 lead bullets and plastic-coated lead bullets are also in use, but they have the same drawback that upon target impact the lead is exposed and this creates spent bullet disposal difficulties.

None of the prior bullets noted above has
35 proved commercially viable, either due to cost, density differences, difficulty of mass production

and the like. Accordingly, a new approach is needed to obtain a projectile for target shooting ranges or for hunting use which is completely devoid of lead and performs ballistically similarly to lead.

5 The invention described in detail below is basically a lead-free bullet which comprises a solid body comprising a sintered composite having one or more, high-density constituent powder materials selected from the group consisting of tungsten
10 carbide, tungsten, ferro-tungsten and carballoy, and a second, lower-density constituent consisting essentially either of a metallic matrix material selected from the group of consisting of tin, zinc, iron and copper, or a plastic matrix material
15 selected from the group consisting of phenolics, epoxies, dialylphthalates, acrylics, polystyrenes, polyethylene, or polyurethanes. In addition, the composite of either type may contain a filler metal such as iron powder or zinc powder. The bullet of
20 the invention comprises a solid body having a density of at least about 9 grams per cubic centimeter (80 percent that of pure lead), and a yield strength in compression greater than about 31 MPa (4500 p.s.i.).

25 Other constituents could also be added in small amounts for special purposes such as enhancing frangibility. For example, carbon could be added if iron is used as one of the composite components to result in a brittle or frangible microstructure
30 after suitable heat treatment processes. Lubricants and/or solvents could also be added to the metal matrix components to enhance powder flow properties, compaction properties, ease die release etc.

35 The invention stems from the understanding that ferrotungsten and the other high-density, tungsten-containing materials listed are not only

economically feasible for bullets, but that they can, by an especially thorough metallurgical and ballistic analysis, be alloyed in proper amounts under proper conditions to become useful as lead free bullets.

The invention further stems from the realization that ballistic performance can best be measured by actual shooting experiences since the extremes of acceleration, pressure, temperature, frictional forces, centrifugal acceleration and deceleration forces, impact forces both axially and laterally, and performance against barriers typical of bullet stops in current usage impose an extremely complex set of requirements on a bullet that make accurate theoretical prediction virtually impossible.

The invention will be better understood by referring to the attached drawing, in which:

FIG. 1 is a bar graph of densities of powder composites;

FIG. 2 is a bar graph of maximum engineering stress attained with the powder composites;

FIG. 3 is a bar graph of the total energy absorbed by the sample during deformation to 20% strain or fracture;

FIG. 4 is a bar graph showing the maximum stress at 20% deformation (or maximum) of 5 conventional bullets; and

FIG. 5 is a bar graph showing the total energy absorbed in 20% deformation or fracture of the five conventional bullets of Figure 4.

There are at least six (6) requirements for a successful lead-free bullet. First, the bullet must closely approximate the recoil of a lead bullet when fired so that the shooter feels as though he is firing a standard lead bullet. Second, the bullet

must closely approximate the trajectory, i.e. exterior ballistics, of a lead bullet of the same caliber and weight so that the practice shooting is directly relevant to shooting in the field with an actual lead bullet. Third, the bullet must not penetrate or damage the normal steel plate backstop on the target range and must not ricochet significantly. Fourth, the bullet must remain intact during its travel through the gun barrel and while in flight. Fifth, the bullet must not damage the gun barrel. Sixth, the cost of the bullet must be reasonably comparable to other alternatives.

In order to meet the first two requirements, the lead-free bullet must have approximately the same density as lead. This means that the bullet must have an overall density of about 11.3 grams per cubic centimeter.

The third requirement above, that of not penetrating or damaging the normal steel backstops at target shooting ranges, dictates that the bullet must either (1) deform at stresses lower than those which would be sufficient to penetrate or severely damage the backstop, or (2) fracture into small pieces at low stresses or (3) both deform and fracture at low stress.

As an example, a typical 158 grain lead (10.3 gm 0.0226 lb.) .38 special bullet has a muzzle kinetic energy from a 10.2 cm (4 inch) barrel of 272 joules (200 foot pounds) and a density of 11.35 gm/cm³ (0.41 pounds per cubic inch). This corresponds to an energy density of 296 joules/cm³ (43,600 inch-pounds per cubic inch). The deformable lead-free bullet in accordance with the invention must absorb enough of this energy per unit volume as strain energy (elastic plus plastic) without imposing on the backstop stresses higher than the

yield strength of mild steel, about 310 MPa (about 45,000 psi), in order for the bullet to stop without penetrating or severely damaging the target backstop. In the case of a frangible bullet or a
5 deformable frangible bullet respectively, the fracture stress of the bullet must be below the stresses experienced by the bullet upon impact with the target backstop and below the yield strength of mild steel.

10 The requirements that the bullet remain intact as it passes through the barrel and that the bullet not cause excessive barrel erosion, are more difficult to quantify. Actual shooting tests are normally required to determine this quality.
15 However, it is clear that the bullet of the invention must be coated with metal or plastic or jacketed in a conventional manner to protect the barrel.

The cost of ferrotungsten is generally
20 reasonable in comparison to other high-density alternatives, as are the costs of each of the alternatives noted in the claims below.

The metal-matrix bullets in accordance with the preferred embodiments of the present invention would
25 be fabricated by powder metallurgical techniques.

For the more frangible materials, the powders of the individual constituents would be blended, compacted under pressure to near net shape, and sintered in that shape. If the bullets are jacketed,
30 compacting could be done in the jacket and sintered therein. Alternatively, the bullets could be compacted and sintered before being inserted into the jackets. If the bullets are coated, they would be coated after compacting and sintering. The
35 proportions of the several powders would be those required by the rule of mixtures to provide a final

density about equal to that of lead. In this formulation, the inability to eliminate all porosity must be taken into account and compensated for by an appropriate increase in the proportion of the denser constituent, tungsten, ferro-tungsten, carballoy, or tungsten carbide or mixtures thereof. The optimum mixture is determined by the tradeoff between raw material cost and bullet performance.

For the more ductile matrix materials such as the metals mentioned above, the bullets may be made by the above process or alternatively, compacted into rod or billet shapes using conventional pressing or isostatic pressing techniques. After sintering, the rod or billet could then be extruded into wire for fabrication into bullets by forging using punches and dies as is done with conventional lead bullets. Alternatively, if the materials are too brittle for such fabrication, conventional fabrication processes could be used to finish the bullet.

The metal matrix bullets could be given an optional embrittling treatment to enhance frangibility after final shape forming. For example, an iron matrix bullet having a carbon addition could be embrittled by suitable heat treatment.

A tin matrix bullet could be embrittled by cooling it into and holding it within a temperature range in which partial transformation to alpha tin occurs. This method can provide precise control of the degree of frangibility.

A third example of embrittlement would be the use of select impurity additions such as bismuth to a copper matrix composite. After fabrication, the bullet could be heated to a temperature range in

which the impurity collects preferentially at the copper grain boundaries, thereby embrittling them.

In addition, even without embrittling additives, frangibility can be controlled by
5 suitably varying the sintering time and/or sintering temperature.

In the case of the thermoplastic or thermosetting plastic matrix materials, the powders are to be blended as described above using the same
10 considerations as to mass and density and the mixture then directly formed into the final part by any of the conventional processes used in the field of polymer technology such as injection molding, transfer molding, etc.

15 In the case of jacketed plastic-matrix bullets, compacting under heat can be done with the composite powder inside the jacket. Alternatively, the powders can be compacted using pressure and heat to form pellets for use in such processes.

20 Finally, in order to protect the gun barrel from damage during firing, the bullet must be jacketed or coated with a soft metallic coating or plastic coating. The coatings for the metal-matrix bullets would preferably be tin, zinc, copper, brass
25 or plastic. In the case of plastic matrix bullets, plastic coatings would be preferred and it would be most desirable if the plastic matrix and coating could be of the same material. In both cases, plastic coatings could be applied by dipping,
30 spraying, fluidized bed or other conventional plastic coating processes. The metallic coatings could be applied by electroplating, hot dipping or other conventional coating processes.

EXAMPLES

A. Plastic Matrix

Frangible plastic matrix composite bullets were made of tungsten powder with an average particle size of 6 microns. Iron powder was added to the tungsten powder at levels of 0, 15, and 30 percent by weight. After blending with one of two polymer powders, phenyl formaldehyde (Lucite) or polymethylmethacrylate (Bakelite) which acted as the matrix, the mixtures were hot compacted at a temperature within the range of from about 149°C to about 177°C (300°F - 350°F) and a pressure of about 241 MPa - 276 MPa (35 - 40 ksi) into 3.18 cm (1.25 inch) diameter cylinders which were then cut into rectangular parallelepipeds for compression testing and drop weight testing. In all, six (6) samples were made as shown in Table I below:

TABLE I

<u>SAMPLE #</u>	<u>COMPOSITION</u>
1	Lucite - Tungsten
2	Lucite - 85% Tungsten - 15% Iron
3	Lucite - 70% Tungsten - 30% Iron
4	Bakelite - Tungsten
5	Bakelite - 85% Tungsten - 15% Iron
6	Bakelite - 70% Tungsten - 30% Iron

The bullet materials so formed were very frangible in the compression test. Their behavior in the drop weight test was similarly highly frangible. The densities relative to that of lead for these samples are as shown in Table II below:

TABLE II

<u>SAMPLE</u>	<u>DENSITY</u>	<u>STRESS</u>	<u>ENERGY</u> <u>ABSORBED</u>
1	81%	29.6MPa (4.3ksi)	0.34J/cm ³ (49in-lb/in ³)
2	78%	23.4MPa (3.4ksi)	0.28J/cm ³ (40 in-lb/in ³)
3	75%	18.6MPa (2.7ksi)	0.15J/cm ³ (21 in-lb/in ³)
4	84%	32.4MPa (4.7ksi)	0.28J/cm ³ (40 in-lb/in ³)
5	80%	9.65MPa (1.4ksi)	0.069J/cm ³ (10 in-lb/in ³)
6	1.9%	13.1MPa (1.9ksi)	0.062J/cm ³ (9 in-lb/in ³)

The maximum stress in the compression test and the energy absorbed in the compression test for these materials is also recorded in Table II. The maximum stress before fracture was below 34.5 MPa (5 ksi) which is well within the desired range to avoid backstop damage.

Metal Matrix Composites

Figure 1 shows the densities attained with metal matrix composites made of tungsten powder, tungsten carbide powder or ferro-tungsten powder blended with powder of either tin, bismuth, zinc, iron (with 3% carbon), aluminum, or copper. The

proportions were such that they would have the density of lead if there was no porosity after sintering. The powders were cold compacted into half-inch diameter cylinders using pressures of 690 MPa (100 ksi). They were then sintered for two hours at appropriate temperatures, having been sealed in stainless steel bags. The sintering temperatures were (in degrees Celsius) 180, 251, 350, 900, 565, 900 respectively.

Figure 2 shows the maximum axial internal stresses attained in the compression test. Figure 3 shows the energies absorbed up to 20 percent total strain (except for the copper tungsten compact which reached such high internal stresses that the test was stopped before 20 percent strain was achieved). All of the materials exhibited some plastic deformation. The energy adsorptions in the compression test indicate the relative ductilities, with the more energy absorbing materials being the most ductile.

Even the most ductile samples such as the tin and bismuth matrix composites showed some fracturing during the compression test due to barreling and secondary tensile stresses which result from this. In the drop weight test using either 326 Joules (240 foot pounds) or 163 Joules (120 foot pounds), the behavior was similar to but an exaggeration of that observed in the compression test.

Control Examples

Figure 4 shows, for comparison, a lead slug, two standard 38 caliber bullets, and two commercial plastic matrix composite bullets tested in compression. Figure 4 shows that maximum stresses of the lead slug and lead bullets were significantly

less than those of the plastic bullets. However, all were of the same order as those attained by the metal matrix samples in the iron free plastic matrix samples. Figure 5 shows the energy absorption for these materials. Values are generally less than that of the metal matrix samples shown in Figure 3 and much higher than that of the frangible plastic matrix samples.

All of these materials deformed significantly in the 326 Joules (240 ft.-lb.) drop weight test. The lead samples did not fracture, whereas the plastic matrix bullets did.

Jacketed Composite Bullets

As another example, 38 caliber metal-matrix bullets and plastic-matrix bullets with the compositions listed in Table III were fabricated inside standard brass jackets (deep-drawn cups) which had a wall thickness varying from 0.25 mm (0.010 inch) to 0.64 mm (0.025 inch). The plastic-matrix ("Lucite" or "Bakelite" listed as code 1 and code 2 in the Table) samples were compacted at the temperature described in the first example. The metal-matrix samples (Codes 3-11) were compacted at room temperature and sintered as described above while they were encased in the jackets.

TABLE III

Bullets Used in Trial
(all jacketed except #4)

5	Code	Matrix	Ferrotungsten in core wt. %	Density with jacket), % vs. Pb	Average	
					Weight, Grams	(Grains)
	1	Lucite	97.5	87.6	8.55	(132)
	2	Bakelite	98.4	91.6	9.14	(141)
	3	Fe + 0.5% C	79.6	84.6	9.27	(143)
10	4	Bi	0	83.6	10.37	(160)
	5	Fe + 0.4% C	89.6	86.6	9.27	(143)
	6	Bi	0	79.8	9.08	(140)
	7	Bi	41.4	88.3	9.98	(154)
	8	Zn	85.0	85.0	9.27	(143)
15	10	Sn	71.5	90.0	9.27	(143)
	11	Cu	72.0	80.4	8.10	(125)

These bullets were fired into a box of sawdust using a +P load of powder, exposing them to pressures in excess of 138 MPa (20,000 pounds per square inch) while in the barrel. Examination and weighing of the samples before and after firing revealed that the iron-matrix, copper-matrix and zinc-matrix bullets lost no weight and no material from the end of the composite core that had been exposed to the hot gases in the barrel.

5

10 Microstructural examination revealed that only the pure bismuth bullet had internal cracks after being fired.

These bullets were also fired at a standard steel plate backstop 5.1 mm (0.2 inch) thick, hardness of Brinell 327 at an incidence angle of 45 degrees and a distance typical of indoor pistol ranges. None of the bullets damaged the backstop or ricocheted.

15

While the invention has been described above and below with references to preferred embodiments and specific examples, it is apparent that many changes, modifications and variations in the materials, arrangements of parts and steps can be made without departing from the inventive concept disclosed herein. Accordingly, the spirit and broad scope of the appended claims is intended to embrace all such changes, modifications and variations that may occur to one of skill in the art upon a reading of the disclosure.

20

25



WHAT IS CLAIMED IS:

1. A lead free composite bullet characterized
by a compacted composite of one or more high-density
constituents selected from the group consisting
5 essentially of tungsten, tungsten carbide, and
ferro-tungsten and a second constituent selected
from the group consisting essentially of tin, zinc,
aluminum, iron, copper, and bismuth.

2. A lead free composite bullet characterized
10 by a composite having one or more constituents
selected from the group consisting essentially of
tungsten, tungsten carbide, ferro-tungsten, and
carballoy and a second constituent selected from the
group consisting essentially of thermosetting and
15 thermoplastics polymers.

3. The bullet according to claim 2
characterized in that said second constituent is
selected from the group consisting essentially of
phenolics, epoxies, dialylphthalates, acrylics,
20 polystyrenes, polyethylenes and polyurethanes.

This Sheet Has Been Replaced





4. A method of manufacturing a lead-free bullet, characterized by the steps of:

- 5 a) blending one or more dense metal powders with a second less dense metal matrix powder, the first dense powders selected from the group consisting essentially of tungsten, tungsten carbide, and ferro-tungsten and the second powder selected from the group consisting essentially of tin, zinc, aluminum, iron, copper, and bismuth, increasing the percentage by weight of the dense powder to compensate for any porosity;
- 10 b) compacting the blended powders to near net shape and
- 15 c) sintering the powders in that shape.

5. The method of Claim 4 characterized by the further step of putting a quantity of the blended powders into a bullet jacket prior to sintering and then inserting the sintered core into a jacket.

20 6. The method of claim 4 characterized by the further step of coating the sintered powder shape with a plastic coating at least 0.10 mm (0.004 inch) in thickness to prevent subsequent barrel erosion.

25 7. A lead free composite bullet characterized by a compacted composite of one or more first constituents selected from the group consisting essentially oftungsten, tungsten carbide, and ferro-tungsten and a plastic binder material and a plastic coating of the same material as the binder;

30 and

a plastic coating different from the binder material.

This Sheet Has Been Replaced





8. A method of making a lead free bullet, characterized by the steps of:

- 5 a) blending tungsten and iron powders, as the heavy constituent with a polymer powder selected from the group consisting essentially of phenyl formaldehyde and polymethylmethacrylate as the matrix,
- 10 b) hot compacting the blended powders at a temperature within the range of from about 149°C to about 177°C (300°F - 350°F) and a pressure within the range of about 241 MPa to about 276 MPa (35 ksi - 40 ksi) into suitable projectile shapes.

9. The method of claim 8 characterized in that
15 the iron powder was preblended with the tungsten powder prior to blending them with the polymer powder.


10. The method of claim 9 characterized in that the iron powder comprises up to 30% by weight
20 of the tungsten-iron preblend.

11. The method of claim 8 characterized by the further step of coating the bullet with a plastic coating at least 0.10 mm (0.004 inch) thick.

12. The method of claim 8 characterized by the
25 further step of introducing a quantity of the blended powders into a metal bullet jacket prior to compacting the powders.

13. The method of claim 8 characterized by the further step of placing the compacted powders into a
30 bullet jacket at least 0.10 mm (0.004 inch) thick.





14. The method of claim 8 characterized in
that the percentage (of total metallic constituent)
of tungsten powder is 100 and the percentage of iron
powder is zero and the polymeric powder is phenyl
5 formaldehyde.

15. The method of claim 8 characterized in
that the percentage of iron powder is zero and the
polymeric powder is polymethylmethacrylate.

16. The method of claim 8 characterized in
10 that the density of the portion of the bullet other
than the jacket, if any, is more than about 9 grams
per cubic centimeter (i.e. greater than about 80% of
the density of lead).

17. The method of claim 8 characterized in
15 that the powders are compacted to a sufficient
extent to achieve a compression strength of 9.65 MPa
(1400 psi) and an energy absorption in compression
test of at least 0.062 Joules/cm³ (9 inch-pounds per
in³) and a yield strength in compression of at least
20 about 31 MPa (4500 psi).

This Sheet Has Been Replaced

