



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : D21C 9/00, D21H 11/20	A1	(11) International Publication Number: WO 98/56981 (43) International Publication Date: 17 December 1998 (17.12.98)
(21) International Application Number: PCT/US98/11943 (22) International Filing Date: June 1998 (09.06.98) (30) Priority Data: 60/049,457 12 June 1997 (12.06.97) US 09/087,037 29 May 1998 (29.05.98) US (71) Applicant: THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors: SEGER, Geoffrey, Eugene; 3584 Centurion Drive, Cincinnati, OH 45211 (US). MACKKEY, Larry, Neil; 5856 Crestview Avenue, Fairfield, OH 45014 (US). TROKHAN, Paul, Dennis; 1356 Warvel Road, Hamilton, OH 45013 (US). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE(SG), SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> This Sheet Has Been Replaced 
(54) Title: MODIFIED CELLULOSIC FIBERS AND FIBROUS WEBS CONTAINING THESE FIBERS		
(57) Abstract Disclosed are modified cellulosic fibers having a dry zero span tensile index that is substantially less than the dry zero span tensile index of the corresponding unmodified cellulosic fibers. Fibers having reduced dry zero span tensile may provide fibrous structures having improved hand feel compared with fibers prepared from unmodified fibers. In particular, such modified fibers provide fibrous structures with improved flexibility, which is perceived as improved softness. The reduced dry zero span tensile is preferably achieved by reacting the fibers with one or more cellulase enzymes and one or more debonders. The invention also relates to a fibrous structure having a density of not more than about 0.4 g/cc, wherein the fibrous structure comprises modified cellulosic fibers having a dry zero span tensile index that is at least about 15 % less than the dry zero span tensile index of the corresponding unmodified cellulosic fibers; and wherein the fibrous structure has a bending modulus per unit dry tensile that is at least about 30 % less than the bending modulus per unit dry tensile of a fibrous structure prepared from corresponding unmodified fibers.		