

SYSTEMS AND METHODS FOR PRE-STRESSING BLADES

FIELD

[0001] The present disclosure relates generally to systems and methods for pre-stressing components of a gas turbine engine.

BACKGROUND

[0002] Gas turbine engine components are susceptible to damage due to foreign objects and fatigue caused by prolonged operational use, which can lead to cracks and other forms of wear. Such damage can limit the component's operational life and increase its maintenance time and cost. While increasing a component's thickness or peening its surface to harden it are successful methodologies used in the art to increase its operational life, there continues to be a need for improved systems and methodologies which increase the component's operational life while minimizing cost, manufacturing time, and any adverse effects on aerodynamic performance.

SUMMARY

[0003] Disclosed and claimed herein are systems and methods for pre-stressing components for a gas turbine engine. In one embodiment, a method for pre-stressing a component for a gas turbine engine includes rotating the component relative to an axis and controlling rotational speed of the component to generate residual stress in the component.

[0004] In one embodiment, the component includes a blade element.

[0005] In one embodiment, the blade element is at least one of a fan blade, a compressor blade, a solid blade, a hollow blade and a shrouded blade.

[0006] In one embodiment, the axis is perpendicular to a central axis of the blade element.

[0007] In one embodiment, controlling rotational speed includes rotating the blade element to exceed a maximum operating speed of the blade element to 109.5% of the maximum operating speed.

[0008] In one embodiment, controlling rotational speed includes controlling rotation of the blade element to exceed a maximum operation speed of the blade element for a predetermined time period.

[0009] In one embodiment, the component includes a plurality of blade elements.

[0010] In one embodiment, the component includes a plurality of fan blade units.

[0011] In one embodiment, the residual stress includes residual compressive stress in one or more regions of the component.

[0012] Another embodiment is directed to a system for pre-stressing blade elements for a gas turbine engine including a rotation unit configured to rotate a blade element relative to an axis, and a control unit configured to control rotation speed of the blade element to generate residual stress in the blade element.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] The features, objects, and advantages of the present disclosure will become more apparent from the detailed description set forth below when taken in conjunction with the drawings in which like reference characters identify correspondingly throughout and wherein:

[0014] FIG. 1 depicts a system diagram according to one or more embodiments;

[0015] FIG. 2 depicts a graphical representation of residual stress regions in a gas turbine engine component according to one or more embodiments;

[0016] FIG. 3 depicts a process for pre-stressing blade elements according to one or more embodiments;

[0017] FIG. 4 depicts a graphical representation of operating zones for a component with respect to vibratory and steady stress on the component according to one or more embodiments; and

[0018] FIG. 5 depicts a system diagram according to one or more embodiments.

DETAILED DESCRIPTION OF THE EXEMPLARY EMBODIMENTS

Overview and Terminology

[0019] As used herein, the term ‘blade element’ refers to one or more fan blades, compressor blades, or other rotational blade elements which are solid, hollow, or shrouded.

[0020] As used herein, the term ‘maximum operating speed’ refers to a maximum rotational speed at which a blade element is designed to safely operate. This speed may be above speeds at which the blade actually operates in various applications. It is estimated or determined based on modeling or testing, and accounts for rotation speeds required during a blade’s life in an engine. Gas turbine engines can employ high and low speed rotors where components, such as blades, are optimized structurally for their respective rotor. In addition, regulatory agencies (e.g., Federal Aviation Administration) may require blades to survive a worst case speed, or redline speed, such that the blades may be continuously operated up to the redline speed. The maximum operating speed may correlate to a redline speed for which a blade element is rated.

[0021] As used herein, the term ‘pre-stressing’ refers to applying loads to or stressing a structure before the structure is used or operated in its intended application.

[0022] As used herein, the terms “a” or “an” shall mean one or more than one. The term “plurality” shall mean two or more than two. The term “another” is defined as a second or more. The terms “including” and/or “having” are open ended (e.g., comprising). The term “or” as used herein is to be interpreted as inclusive or meaning any one or any combination. Therefore, “A, B or C” means “any of the following: A; B; C; A and B; A and C; B and C; A, B and C”. An exception to this definition will occur only when a combination of elements, functions, steps or acts are in some way inherently mutually exclusive.

[0023] Reference throughout this document to “one embodiment,” “certain embodiments,” “an embodiment,” or similar term means that a particular feature, structure, or characteristic described in connection with the embodiment is included in at least one embodiment. Thus, the appearances of such phrases in various places throughout this specification are not necessarily all referring to the same embodiment. Furthermore, the particular features, structures, or characteristics may be combined in any suitable manner on one or more embodiments without limitation.

[0024] Referring now to FIGS. 1 and 2, a system **100** includes one or more blade elements **105_{1-n}** mechanically coupled to a rotation unit **106** and a shaft **110**, and operatively associated with a controller **115** configured to rotate blade elements **105_{1-n}** relative to axis **120** in a direction **125** to generate residual stress therein. As shown in FIG. 2, an exemplary blade element **200**, which can include shrouds **206**, includes a general region **205** having a high stress area **210**, and a general region **215** having high stress areas **220**, **225**. These high stress areas (**210**, **220**, **225**) are portions of blade element **200** which encounter particularly high stress during operation in an engine, and thus are exemplary regions which may be targeted for pre-stressing in order to increase durability and longevity of blade element **210**.

[0025] Referring to FIG. 3, a method **300** pre-stresses blade elements **105_{1-n}** using exemplary system **100**. At block **305**, controller **115** initiates rotation of blade elements **105_{1-n}** on shaft **110** about axis **120**. At block **310**, controller **115** increases rotational speed of blade elements **105_{1-n}** beyond a maximum operating speed of the blade elements. For example, if blade elements are designed for rotation speeds within the range of 3,000 rpm or 12,000 rpm during operation in an engine, then controller **115** may be configured to increase their rotational speed about axis **120** to a rotational speed that is 109.5% of the maximum operating speed to generate a 20% increase in stress at block **310**. Controller **115** may be configured to increase the rotational speed up to 120%, such as an increase of 118.3% to generate a 40% increase in steady stress. Such rotational overspeeding pre-stresses the blade elements **105_{1-n}** and generates residual stress in at least high stress areas (**210**, **220**, **225**) thereof. The residual stress from process **300** can include tensile and/or compressive stress which remains in the material of the blade element **200**. The residual stress results from stresses induced within the blade element **200** above its yield stress (e.g., at or above the minimum level of stress required to structurally change the blade element **200**) during controlled rotational overspeeding thereof.

[0026] It will be appreciated that such structural changes of blade elements **105_{1-n}** caused by rotating the blade elements at speeds above their yield stress include permanent deformations in one or more areas (e.g., areas **210**, **220**, **225**). It will also be appreciated that inducing residual stress in a blade element can be beneficial by increasing the blade element's durability or operational life to, for example, one or more years more than conventional blades. The maximum rotational speed utilized at block **310** can be controlled up to the ductile limit of the blade elements **105_{1-n}**.

[0027] Referring to FIG. 4, chart **400** depicts a graphical representation of operating zones for a blade element relative to vibratory and steady stress limits, such as maximum vibratory stress **410**, maximum steady stress **415**, allowable operating zone **420** and dangerous operating zone **425**. In addition, chart **400** is an exemplary representation of a Goodman diagram for a blade element (e.g., blade elements **105_{1-n}**), or blade units. Maximum vibratory stress **410** refers to the endurance limit or endurance strength of a blade element. Maximum steady stress **415** refers to the yield strength or ultimate strength of a material. Maximum vibratory stress **410** and maximum steady stress **415** can be determined by modeling and/or test data to account for one or more of temperature, pressure, material of the blade and blade type, where line **405** represents the boundary between allowable operating zone **420** and dangerous operating zone **425**. Line **405**, which may be a curve, is relative to vibratory stress (e.g., vibrating part of load due to engine imbalance, air smoothness, etc.) and steady stress (e.g., stress due to centrifugal loads during rotation, air loads, etc.).

[0028] Pre-stressing may include rotation of a blade element above a maximum operating speed for the blade element (e.g., outside of allowable operating zone **420**), wherein rotationally induced steady stress is increased. Triangle **430** represents an exemplary region (e.g., regions **210**, **220** and **225**) of a blade element prior to pre-stressing. Residual compressive stress induced in the region or blade element during pre-stressing can shift triangle **430** into allowable operating zone **420** which is represented by triangle **435**. The shift in diagram **400** from triangle **430** to triangle **435** represents a horizontal shift and induced generation of residual compressive stress. This horizontal shift can indicate that durability of a blade element is improved with respect to steady state stress. It may be appreciated that different portions of a blade element may fall into different areas of allowable operating zones. According to one embodiment, pre-stressing can allow for conversion of blade regions into allowable operating zone **420** and/or allow for regions within allowable operating zone **420** to shift further away from line **405**, or within operating zone **420**, as a result of pre-stressing.

[0029] Referring to FIG. 5, a system **500** includes a plurality of blade units **505_{1-n}** (e.g., a plurality of sets of blade elements) mounted to rotation unit **506** and shaft **510**. System **500** may be configured to rotate blade units **505_{1-n}** based on control output from controller **515**. In certain embodiments, system **500** may include an overspeed rig for rotating the blade units **505_{1-n}** as shown by direction **525** relative to axis **520**, which is perpendicular to a central axis of blade

units **505_{1-n}**. System **500** can rotate multiple blades and blade units to pre-stress multiple blade units as described above at the same time.

[0030] It will be appreciated that the above described systems and methods may utilize different rotation speeds and time periods depending on the specific application. For example, in accordance with certain embodiments, the maximum rotational speed utilized at block **310** is 109.5 % of the blade element's maximum operating speed, which generates a 20% increase in stress. In other embodiments, the maximum rotational speed utilized at block **310** is 120% of the blade element's maximum operating speed. In yet other embodiments, the maximum rotational speed utilized at block **310** is between 100%-120% of the blade element's maximum operating speed.

[0031] In accordance with certain embodiments, the temperature and pressure of the atmosphere in which pre-stressing will take place can be measured to determine the rotation speeds and time periods used. By way of example, pre-stressing blade elements in a spin pit having a lower pressure and/or modified temperature can affect the required speed and time period needed to accomplish a given level of pre-stressing on the blade elements. Blade elements may be pre-stressed in a vacuum or a partial vacuum such that a reduction in air at the pre-stressing location requires less air to circulate/pump, which in turn provides less stress on the rotational unit. System **100** and/or process **300** may be configured to reduce the pressure to a pure vacuum or very low pressure during pre-stressing of blade elements **105_{1-n}**, such that less energy is required to rotate the blade elements.

[0032] In accordance with certain embodiments, the rotational speed of the blade elements at block **310** may exceed their maximum operating speed for a predetermined time period within the range of, for example, 1-30 seconds. The predetermined rotational time period at overspeed depends on the material and/or ductility of the blade elements. By way of example, titanium blade elements may be rotated with controlled overspeed for 1 second to establish residual stress. In certain embodiments, overspeeding may be performed for 0.25 seconds to 30 seconds. Other time periods can alternatively or additionally be utilized.

[0033] Pre-stressing the blade elements as described herein can cause twisting thereof such that residual compressive stress generated therein counteracts one or more operational forces during use in an engine, whereby such over twisting corrects for twisting during engine use. It will be

appreciated that the characteristics of a blade at sea level or at low temperatures may vary greatly relative to the characteristics of the blade at flight altitude and while at operating temperatures.

[0034] Although the systems and methods of the present disclosure are described as being used with one or more blade elements, it will be appreciated that the principles described herein can apply to other components, such vane elements, non-gas turbine engine components, and rotating elements in general.

[0035] While this disclosure has been particularly shown and described with references to exemplary embodiments thereof, it will be understood by those skilled in the art that various changes in form and details may be made therein without departing from the scope of the claimed embodiments.

CLAIMS

What is claimed is:

1. A method for pre-stressing a component for a gas turbine engine, the method comprising:

rotating the component relative to an axis; and

controlling rotational speed of the component to generate residual stress in the component.
2. The method of claim 1, wherein the component includes a blade element.
3. The method of claim 2, wherein the blade element is at least one of a fan blade, a compressor blade, a solid blade, a hollow blade and a shrouded blade.
4. The method of claim 2, wherein the axis is perpendicular to a central axis of the blade element.
5. The method of claim 2, wherein controlling rotational speed includes rotating the blade element to exceed a maximum operating speed of the blade element to 109.5% of the maximum operating speed.
6. The method of claim 2, wherein controlling rotational speed includes controlling rotation of the blade element to exceed a maximum operation speed of the blade element for a predetermined time period.
7. The method of claim 2, wherein the component includes a plurality of blade elements.

8. The method of claim 1, wherein the component includes a plurality of fan blade units.

9. The method of claim 1, wherein the residual stress includes residual compressive stress in one or more regions of the component.

10. A system for pre-stressing blade elements for a gas turbine engine, the system comprising:

a rotation unit configured to rotate a blade element relative to an axis; and

a control unit configured to control rotation speed of the blade element to generate residual stress in the blade element.

11. The system of claim 10, wherein the blade element is at least one of a fan blade, a compressor blade, a solid blade, a hollow blade and a shrouded blade.

12. The system of claim 10, wherein the axis is perpendicular to a central axis of the blade element.

13. The system of claim 10, wherein controlling rotational speed includes rotating the blade element to exceed a maximum operating speed of the blade element to 109.5% of the maximum operating speed.

14. The system of claim 10, wherein controlling rotation speed includes controlling rotation of the blade element to exceed a maximum operational speed for a predetermined time period.

15. The system of claim 10, wherein the blade element is a plurality of blade elements mounted to the rotation unit.

16. The system of claim 10, wherein of the blade element is a plurality of fan blade units.

17. The system of claim 10, wherein the residual stress includes residual compressive stress in one or more regions of the blade element.