

DESCRIPTION

ETHYLENE-VINYL ALCOHOL COPOLYMER COMPOSITION, AND MULTILAYER
STRUCTURE

5

TECHNICAL FIELD

[0001] The present disclosure relates to an ethylene-vinyl
alcohol copolymer composition containing an ethylene-vinyl
alcohol copolymer (hereinafter sometimes referred to simply
10 as "EVOH resin") as a main component and to a multilayer
structure produced by using the same. More specifically, the
present disclosure relates to an EVOH resin composition having
a UV absorbing ability and to a multilayer structure having
at least one layer containing the EVOH resin composition.

15

BACKGROUND ART

[0002] EVOH resin is excellent in transparency, gas barrier
property (e.g., oxygen barrier property), perfume retaining
property, solvent resistance, oil resistance, mechanical
20 strength, and the like, and is widely used for various packaging
materials such as a food packaging material, a pharmaceutical
product packaging material, an industrial chemical packaging
material, and an agricultural chemical packaging material.

[0003] However, foods and pharmaceutical products are liable
25 to be degraded or deteriorated by ultraviolet radiation.

Therefore, packaging materials for packaging the foods and the pharmaceutical products are required to have a UV absorbing ability.

A typical method for imparting such a packaging
5 material with a UV absorbing property is to include a UV
absorber in a resin to be used for the packaging material. For
example, a multilayer structure is proposed, which includes
a polyolefin layer and an EVOH resin layer and has a UV
transmittance reduced by including a UV absorber in a material
10 for one of the layers or in materials for the respective layers
(see, for example, PTL 1).

RELATED ART DOCUMENT

PATENT DOCUMENT

15 [0004] PTL 1: JP-A-2008-230112

SUMMARY OF INVENTION

[0005] However, the UV absorber is generally a low- molecular
weight compound. Therefore, when the UV absorber is contained
20 in the multilayer structure, the UV absorber is problematically
liable to migrate to a surface of the multilayer structure
through the resin, thereby being brought into contact with an
article packaged with the multilayer structure or making the
surface of the multilayer structure sticky.

25 Further, it is necessary to include a large amount

of the UV absorber with the resin to impart the multilayer structure with a sufficient UV absorbing ability. As a result, the properties of the resin are liable to be deteriorated.

[0006] The present disclosure provides EVOH resin composition imparted with an excellent UV absorbing property without containing a known UV absorber, and a multilayer structure.

[0007] In view of the foregoing, the inventors conducted intensive studies and, as a result, found that an EVOH resin composition containing an iron compound in a proportion of 0.01 to 100 ppm on a metal basis based on the weight of the EVOH resin composition has a satisfactory UV absorbing ability, and attained the present disclosure.

According to a first inventive aspect, there is provided an EVOH resin composition containing: an EVOH resin; and an iron compound; wherein the iron compound is present in a proportion of 0.01 to 100 ppm on a metal basis based on the weight of the EVOH resin composition.

According to a second inventive aspect, there is provided a multilayer structure that includes at least one layer containing the EVOH resin composition described above.

[0008] The inventive EVOH resin composition is imparted with a satisfactory UV absorbing ability without including a UV absorber that is liable to migrate to the surface and impair the properties of the resin. Therefore, the inventive EVOH

resin composition is advantageously used for a packaging material for packaging an article that is liable to be degraded or deteriorated by ultraviolet radiation.

[0009] The multilayer structure including at least one layer
5 containing the inventive EVOH resin composition has a satisfactory UV absorbing ability and, therefore, is particularly useful for a food packaging material.

DESCRIPTION OF EMBODIMENTS

10 [0010] The present disclosure will hereinafter be described in detail by way of preferred embodiments thereof. However, it should be understood that these preferred embodiments are illustrative of the disclosure but not limitative of the disclosure.

15 [0011] In the present disclosure, an EVOH resin composition contains an EVOH resin as a main component and 0.01 to 100 ppm of an iron compound on a metal basis based on the weight of the EVOH resin composition. The inventive EVOH resin composition contains the EVOH resin as a base resin. That is,
20 the EVOH resin is typically present in a proportion of not less than 90 wt.%, preferably not less than 95 wt.%, more preferably not less than 97 wt.%, in the EVOH resin composition.

These components will hereinafter be described in detail.

25 [0012] [EVOH resin]

The EVOH resin to be used in the present disclosure is generally a water-insoluble thermoplastic resin prepared by saponifying an ethylene-vinyl ester copolymer, which is a copolymer of ethylene and a vinyl ester monomer. Vinyl acetate
5 is typically used as the vinyl ester monomer for economy.

Known polymerization methods such as a solution polymerization method, a suspension polymerization method, and an emulsion polymerization method may be used for the polymerization. A solution polymerization method using
10 methanol as a solvent is generally used. The resulting ethylene-vinyl ester copolymer may be saponified by a known method.

The EVOH resin thus prepared mainly contains an ethylene structural unit and a vinyl alcohol structural unit,
15 and further contains a very small amount of a vinyl ester structural unit that remains unsaponified.

[0013] A typical example of the vinyl ester monomer is vinyl acetate, which is readily commercially available and ensures a higher impurity treatment efficiency in the production
20 process. Other examples of the vinyl ester monomer include aliphatic vinyl esters such as vinyl formate, vinyl propionate, vinyl valerate, vinyl butyrate, vinyl isobutyrate, vinyl pivalate, vinyl caprate, vinyl laurate, vinyl stearate, and vinyl versatate, and aromatic vinyl esters such as vinyl
25 benzoate. The aliphatic vinyl esters typically have 3 to 20

carbon atoms, preferably 4 to 10 carbon atoms, particularly preferably 4 to 7 carbon atoms. These vinyl esters may be used alone or, as required, a plurality of vinyl esters may be selected from these vinyl esters to be used in combination.

5 [0014] The EVOH resin typically has an ethylene structural unit content of 20 to 60 mol %, preferably 25 to 50 mol %, particularly preferably 25 to 35 mol %, which may be controlled by adjusting the pressure of ethylene in the copolymerization of the vinyl ester monomer and ethylene. If the ethylene
10 structural unit content is too low, the EVOH resin tends to be poorer in high-humidity gas barrier property and melt formability. If the ethylene structural unit content is excessively high, on the other hand, the EVOH resin tends to be poorer in gas barrier property.

15 The ethylene content may be measured in conformity with ISO14663.

[0015] The EVOH resin typically has a vinyl ester saponification degree of 90 to 100 mol %, preferably 95 to 100 mol %, particularly preferably 99 to 100 mol %, which may be
20 controlled by adjusting the amount of a saponification catalyst (typically, an alkaline catalyst such as sodium hydroxide), the temperature and the period for the saponification of the ethylene-vinyl ester copolymer. If the saponification degree is too low, the EVOH resin tends to be poorer in gas barrier
25 property, heat stability, moisture resistance and the like.

The saponification degree of the EVOH resin may be measured in conformity with JIS K6726 (by using a solution prepared by homogenously dissolving the EVOH resin in a water/methanol solvent).

5 [0016] The EVOH resin typically has a melt flow rate (MFR) of 0.5 to 100 g/10 minutes, preferably 1 to 50 g/10 minutes, particularly preferably 3 to 35 g/10 minutes (as measured at 210°C with a load of 2160 g). If the MFR is excessively great, the EVOH resin tends to be unstable in a film forming process.
10 If the MFR is too small, the EVOH resin tends to have an excessively high viscosity, resulting in difficulty in melt extrusion.

The MFR is an index of the polymerization degree of the EVOH resin, and may be controlled by adjusting the amount of a polymerization initiator and the amount of a solvent in
15 of a polymerization initiator and the amount of a solvent in the copolymerization of ethylene and the vinyl ester monomer.

[0017] The EVOH resin to be used in the present disclosure may further contain a structural unit derived from any of the following comonomers in a proportion that does not impair the
20 effects of the present disclosure (e.g., in a proportion of not greater than 10 mol %).

The comonomers include: olefins such as propylene, 1-butene and isobutene, hydroxyl-containing α -olefins such as 3-buten-1-ol, 3-butene-1,2-diol, 4-penten-1-ol, and
25 5-hexene-1,2-diol, and esterification products, acylation

products, and other derivatives of these olefins; hydroxyalkyl vinylidenes such as 2-methylenepropene-1,3-diol and 3-methylenepentane-1,5-diol; hydroxyalkyl vinylidene diacetates such as 1,3-diacetoxy-2-methylenepropene, 5 1,3-dipropionyloxy-2-methylenepropene, and 1,3-dibutyroyloxy-2-methylenepropene; unsaturated acids such as acrylic acid, methacrylic acid, crotonic acid, (anhydrous) phthalic acid, (anhydrous) maleic acid, and (anhydrous) itaconic acid, and salts and C1 to C18 monoalkyl and dialkyl 10 esters of these unsaturated acids; acrylamide compounds such as acrylamide, C1 to C18 N-alkylacrylamides, N,N-dimethylacrylamide, 2-acrylamidopropanesulfonic acid, and salts thereof, and acrylamidopropyldimethylamine and acid salts and quaternary salts thereof; methacrylamide compounds 15 such as methacrylamide, C1 to C18 N-alkylmethacrylamides, N,N-dimethylmethacrylamide, 2-methacrylamidopropanesulfonic acid, and salts thereof, and methacrylamidopropyldimethylamine and acid salts and quaternary salts thereof; N-vinylamides such as 20 N-vinylpyrrolidone, N-vinylformamide, and N-vinylacetamide; cyanated vinyl compounds such as acrylonitrile and methacrylonitrile; vinyl ethers such as C1 to C18 alkyl vinyl ethers, hydroxyalkyl vinyl ethers, and alkoxyalkyl vinyl ethers; halogenated vinyl compounds such as vinyl chloride, 25 vinylidene chloride, vinyl fluoride, vinylidene fluoride, and

vinyl bromide; vinylsilanes such as trimethoxyvinylsilane;
halogenated allyl compounds such as allyl acetate and allyl
chloride; allyl alcohol compounds such as allyl alcohol and
dimethoxyallyl alcohol; and
5 trimethyl-(3-acrylamido-3-dimethylpropyl)-ammonium chloride
and acrylamido-2-methylpropanesulfonic acid, which may be
used alone or in combination.

[0018] A post-modified EVOH resin such as an urethanized,
acetalized, cyanoethylated or oxyalkylenated EVOH resin may
10 be used as the EVOH resin.

[0019] Particularly, the EVOH resin prepared by the
copolymerization with any of the hydroxyl-containing
 α -olefins is preferred for excellent secondary formability.
An EVOH resin having a 1,2-diol structure at its side chain
15 is particularly preferred.

[0020] The EVOH resin to be used in the present disclosure
may be a mixture of different EVOH resins. These EVOH resins
may have different saponification degrees and different
polymerization degrees, and contain different comonomer
20 components.

[0021] [EVOH Resin Composition (Pellets)]

It is a feature of the present disclosure that the
EVOH resin composition contains the iron compound in a
proportion of 0.01 to 100 ppm on a metal basis based on the
25 weight of the EVOH resin composition. The proportion of the

iron compound is particularly preferably 1 to 80 ppm, further preferably 3 to 70 ppm, especially preferably 10 to 50 ppm.

If the proportion of the iron compound is too small, the EVOH resin composition tends to have an insufficient UV
5 absorbing ability. If the proportion of the iron compound is excessively large, a product formed from the EVOH resin composition is liable to be colored.

[0022] The proportion of the iron compound may be determined by treating the EVOH resin composition containing the EVOH
10 resin and the iron compound with an acid such as dilute sulfuric acid or hydrochloric acid, adding pure water to the resulting solution to a predetermined volume to prepare a sample solution and analyzing the sample solution by the atomic absorption spectrometry.

15 [0023] Examples of the iron compound include ferric oxide, ferrosferric oxide, ferrous chloride, ferric chloride, ferrous hydroxide, ferric hydroxide, ferrous oxide, iron sulfate, and iron phosphate, which may be each present in the form of an iron salt, in an ionized form or in the form of a
20 complex coordinated with the resin or other ligands in the EVOH resin composition.

[0024] In the present disclosure, exemplary methods for producing the inventive EVOH resin composition in pellet form include: (i) a method including the steps of adding the iron
25 compound to a homogeneous solution (water/alcohol solution or

the like) of the EVOH resin, extruding the resulting solution into a strand form in a coagulation liquid, cutting the resulting strands into pellets and drying the pellets in a process for producing the EVOH resin; (ii) a method including
5 the steps of keeping pellets of the EVOH resin in contact with an aqueous solution of the iron compound to introduce the iron compound into the pellets of the EVOH resin, and drying the resulting pellets; (iii) a method including the steps of dry-blending pellets of the EVOH resin and the iron compound,
10 and melt-kneading the resulting mixture; and (iv) a method including the steps of adding a predetermined amount of the iron compound to a melt of the EVOH resin, and melt-kneading the resulting mixture.

Particularly, the method (ii) is preferred because
15 the EVOH resin composition produced by the method (ii) ensures more remarkable effects of the present disclosure without the need for an additional production step.

[0025] The EVOH resin composition pellets to be produced by the method (i) and the EVOH resin pellets to be used in the
20 methods (ii) and (iii) may each have, for example, a spherical shape, a cylindrical shape, a cubic shape, an elongated cubic shape or the like. The pellets typically each have a spherical shape (rugby ball shape) or a cylindrical shape. The spherical pellets typically each have a diameter of 1 to 6 mm and a height
25 of 1 to 6 mm, preferably a diameter of 2 to 5 mm and a height

of 2 to 5 mm, and the cylindrical pellets typically each have a bottom face diameter of 1 to 6 mm and a length of 1 to 6 mm, preferably a bottom face diameter of 2 to 5 mm and a length of 2 to 5 mm, for easy handling of the pellets for use as a forming material.

[0026] The iron compound to be used in the methods (i), (iii) and (iv) is preferably a water-soluble iron compound. Examples of the water-soluble iron compound include iron salts (inorganic acid salts and the like) such as ferric oxide, ferrosoferric oxide, ferrous chloride, ferric chloride, ferrous hydroxide, ferric hydroxide, ferrous oxide, iron sulfate, iron sulfide, iron nitrate, and iron phosphate, which may be each present in the form of a salt, in an ionized form or in the form of a complex coordinated with the resin or other ligands in the EVOH resin as described above.

[0027] Usable as the aqueous solution of the iron compound in the method (ii) are an aqueous solution of any of the aforementioned iron compounds, and an aqueous solution that contains iron ions leached out of a steel material immersed in water containing chemical agents. In this case, the proportion (on a metal basis) of the iron compound in the EVOH resin composition may be controlled by adjusting the concentration of the iron compound in the aqueous solution in which the EVOH resin pellets are immersed, the immersion temperature, the immersion period and/or the like. The

immersion period is typically 0.5 to 48 hours, preferably 1 to 36 hours, and the immersion temperature is typically 10°C to 40°C, preferably 20°C to 35°C.

The EVOH resin composition pellets are separated from the aqueous solution by a known method, and dried by a known drying method. Various drying methods are usable for the drying, and examples of the drying methods include a stationary drying method and a fluidized drying method, which may be used alone or in combination.

[0028] The inventive EVOH resin composition pellets typically have a water content of 0.01 to 0.5 wt.%, preferably 0.05 to 0.35 wt.%, particularly preferably 0.1 to 0.3 wt.%.

[0029] In the present disclosure, the water content of the EVOH resin composition pellets is measured and calculated in the following manner.

The weight (W_1) of the EVOH resin composition pellets is measured by an electronic balance, and the EVOH resin composition pellets are dried at 150°C for 5 hours in a hot air dryer and cooled for 30 minutes in a desiccator. Then, the weight (W_2) of the resulting pellets is measured. The water content of the EVOH resin composition pellets is calculated from the following expression:

$$\text{Water content (wt.\%)} = [(W_1 - W_2)/W_1] \times 100$$

[0030] In the aforementioned manner, the inventive EVOH resin composition pellets are produced.

[0031] The EVOH resin composition pellets thus produced may be subjected to a melt-forming process as they are, but a lubricant is preferably applied to surfaces of the pellets in order to ensure stable feeding of the pellets in the melt-forming process. Examples of the lubricant include higher fatty acids (e.g., lauric acid, myristic acid, palmitic acid, stearic acid, behenic acid, oleic acid, and the like), higher fatty acid esters (e.g., methyl esters, isopropyl esters, butyl esters, octyl esters, and the like of the higher fatty acids), higher fatty acid amides (saturated fatty acid amides such as stearamides and behenamides, unsaturated fatty acid amides such as oleamides and erucamides, and bis-fatty acid amides such as ethylene bisstearamide, ethylene bisoleamide, ethylene biserucamide, and ethylene bislauramide), low-molecular weight polyolefins (e.g., low-molecular weight polyethylenes and low-molecular weight polypropylenes having a molecular weight of about 500 to about 10,000, and acid modification products of these low-molecular weight polyolefins), higher alcohols, ester oligomers, and fluorinated ethylene resins. The higher fatty acids, and the esters and the amides of the higher fatty acids are preferred, and the higher fatty acid amides are further preferred. The proportion of the lubricant is typically not greater than 5 wt.%, preferably not greater than 1 wt.%, of the EVOH resin composition.

[0032] The inventive EVOH resin composition may further contain additives that are generally added to EVOH resin, as long as the effects of the present disclosure are not impaired.

[0033] [Multilayer Structure]

5 The inventive multilayer structure includes at least one layer containing the inventive EVOH resin composition. The layer containing the inventive EVOH resin composition (hereinafter referred to simply as "EVOH resin composition layer") is laminated with other base material mainly containing
10 a thermoplastic resin other than the inventive EVOH resin composition (the resin used as the base material being hereinafter sometimes referred to simply as "base resin"), whereby the resulting multilayer structure is imparted with additional strength. Further, the EVOH resin composition
15 layer is protected from an influence of water or the like, and is imparted with other functions.

[0034] Examples of the base resin include: (unmodified) polyolefin resins including polyethylene resins such as linear low-density polyethylenes, low-density polyethylenes,
20 very-low-density polyethylenes, medium-density polyethylenes, high-density polyethylenes, ethylene-propylene (block and random) copolymers, and ethylene- α -olefin (C4 to C20 α -olefin) copolymers, polypropylene resins such as polypropylenes and propylene- α -olefin (C4 to C20 α -olefin) copolymers,
25 polybutenes, polypentenes, and polycycloolefin resins

(polymers having a cycloolefin structure at a main chain and/or a side chain); polyolefin resins in a broader sense including modified olefin resins such as unsaturated carboxyl-modified polyolefin resins obtained by graft-modifying any of the
5 aforementioned polyolefin resins with an unsaturated carboxylic acid or an unsaturated carboxylate; ionomers, ethylene-vinyl acetate copolymers, ethylene-acrylic acid copolymers, ethylene-acrylate copolymers, polyester resins, polyamide resins (including polyamide copolymers), polyvinyl
10 chlorides, polyvinylidene chlorides, acryl resins, polystyrene resins, vinyl ester resins, polyester elastomers, polyurethane elastomers, polystyrene elastomers, halogenated polyolefins such as chlorinated polyethylenes and chlorinated polypropylenes, and aromatic and aliphatic polyketones.

15 [0035] Of these resins, polyamide resins, polyolefin resins, polyester resins, and polystyrene resins, which are hydrophobic resins, are preferred. Further, polyolefin resins such as polyethylene resins, polypropylene resins and polycycloolefin resins, and unsaturated carboxyl-modified
20 polyolefin resins obtained by modifying these polyolefin resins are more preferred, and polycycloolefin resins are particularly preferred as the hydrophobic resins.

[0036] Where layers a (a1, a2, ...) of the inventive EVOH resin composition and layers b (b1, b2, ...) of the base resin
25 are stacked to form the multilayer structure, possible

combinations of the layers a and the layers b include a/b, b/a/b, a/b/a, a1/a2/b, a/b1/b2, b2/b1/a/b1/b2, b2/b1/a/b1/a/b1/b2, and the like. Where the multilayer structure is configured to include recycle layers R obtained by recycling cutoff pieces and defective products occurring during the production of the multilayer structure and melt-forming the recycled material (a mixture including the inventive EVOH resin composition and the thermoplastic resin other than the inventive EVOH resin composition), possible combinations of the layers a, the layers b, and the layers R include b/R/a, b/R/a/b, b/R/a/R/b, b/a/R/a/b, b/R/a/R/a/R/b, and the like. The total number of the layers of the multilayer structure is typically 2 to 15, preferably 3 to 10.

In the aforementioned layered configuration, an adhesive resin layer containing an adhesive resin may be provided between the respective layers as required.

[0037] Known adhesive resins are usable as the adhesive resin. The adhesive resin is properly selected according to the type of the thermoplastic resin to be used for the base resin layer b. Typical examples of the adhesive resin include carboxyl-containing modified polyolefin polymers prepared by chemically bonding an unsaturated carboxylic acid or its anhydride to a polyolefin resin by an addition reaction, a graft reaction, or the like. Examples of the carboxyl-containing modified polyolefin polymers include polyethylenes

graft-modified with maleic anhydride, polypropylenes
graft-modified with maleic anhydride, ethylene-propylene
(block and random) copolymers graft-modified with maleic
anhydride, ethylene-ethyl acrylate copolymers graft-modified
5 with maleic anhydride, ethylene-vinyl acetate copolymers
graft-modified with maleic anhydride, polycycloolefin resins
modified with maleic anhydride, and polyolefin resins
graft-modified with maleic anhydride, which may be used alone
or in combination as a mixture.

10 [0038] Where the adhesive resin layer is provided between
the layer of the inventive EVOH resin composition and the base
resin layer in the multilayer structure, the adhesive resin
layer is present on at least one of opposite sides of the EVOH
resin composition layer and, therefore, the adhesive resin is
15 preferably hydrophobic.

[0039] The base resin and the adhesive resin may contain a
plasticizer, a filler, a clay (montmorillonite or the like),
a colorant, an antioxidant, an antistatic agent, a lubricant,
a nucleating agent, an antiblocking agent, a wax, and the like
20 in amounts that do not impair the effects of the present
disclosure (e.g., in amounts of not greater than 30 wt.%,
preferably not greater than 10 wt.%).

[0040] A conventional stacking method may be employed for
stacking the layer of the inventive EVOH resin composition and
25 the layer of the base resin (optionally with the adhesive resin

layer provided between the layers). Examples of the stacking method include: a method in which a film or a sheet of the inventive EVOH resin composition is laminated with the base resin by melt extrusion; a method in which the base resin layer
5 is laminated with the inventive EVOH resin composition by melt extrusion; a method in which the EVOH resin composition and the base resin are coextruded; a method in which the layer of the EVOH resin composition and the layer of the base resin are bonded together by dry laminating with the use of a known
10 adhesive agent such as of an organic titanium compound, an isocyanate compound, a polyester compound, or a polyurethane compound; and a method in which a solution of the EVOH resin composition is applied on the base resin layer and a solvent is removed from the applied solution. Of these methods, the
15 coextrusion method is preferred in consideration of costs and environmental concerns.

[0041] The multilayer structure described above may be further subjected to a (heat) stretching process as required. The stretching process may be a uniaxial stretching process
20 or a biaxial stretching process. The biaxial stretching process may be a simultaneous stretching process or a sequential stretching process. A roll stretching method, a tenter stretching method, a tubular stretching method, a stretch blowing method, or a vacuum pressure forming method
25 having a higher stretch ratio may be employed for the stretching

process. A temperature for the stretching is typically selected from a range of 40°C to 170°C, preferably about 60°C to about 160°C, around the melting point of the multilayer structure. If the stretching temperature is too low, poorer
5 stretchability will result. If the stretching temperature is excessively high, it will be difficult to ensure stable stretching.

[0042] The resulting multilayer structure may be further subjected to a heat-setting process to ensure dimensional
10 stability after the stretching. The heat-setting process may be performed in a known manner. For example, the stretched multilayer structure (stretched film) is typically heat-treated at 80°C to 180°C, preferably 100°C to 165°C, for about 2 to about 600 seconds, while under tension.

15 Where the stretched multilayer film produced by using the inventive EVOH resin composition is used as a shrinkable film, for example, the stretched film may be cold-set so as to be imparted with a heat-shrinkable property by applying cold air over the stretched film without performing the above
20 heat-setting process.

[0043] In some case, a cup-shaped or tray-shaped multilayer container may be produced from the inventive multilayer structure. For the production of the multilayer container, an ordinary drawing process is employed. Specific examples
25 of the drawing process include a vacuum forming method, a

pressure forming method, a vacuum pressure forming method, and a plug-assisted vacuum pressure forming method. Where a tube-shaped or bottle-shaped multilayer container (having a laminate structure) is produced from a multilayer parison (a hollow tubular preform to be blown), a blow molding process is employed. Specific examples of the blow molding process include an extrusion blow molding method (a twin head type, a mold shift type, a parison shift type, a rotary type, an accumulator type, a horizontal parison type, and the like), a cold parison blow molding method, an injection blow molding method and a biaxial stretching blow molding method (an extrusion type cold parison biaxial stretching blow molding method, an injection type cold parison biaxial stretching blow molding method, an injection inline type biaxial stretching blow molding method and the like). As required, the resulting multilayer structure may be subjected to a heating process, a cooling process, a rolling process, a printing process, a dry laminating process, a solution or melt coating process, a bag forming process, a deep drawing process, a box forming process, a tube forming process, a splitting process, or the like.

[0044] The thickness of the multilayer structure (or the stretched multilayer structure) and the thicknesses of the EVOH resin composition layer, the base resin layer, and the adhesive resin layer of the multilayer structure are properly determined

according to the layered configuration, the type of the base resin, the type of the adhesive resin, the purpose, the package shape, the required physical properties, and the like of the multilayer structure. The thickness of the multilayer
5 structure (or the stretched multilayer structure) is typically 10 to 5000 μm , preferably 30 to 3000 μm , particularly preferably 50 to 2000 μm . The thickness of the EVOH resin composition layer is typically 1 to 500 μm , preferably 3 to 300 μm , particularly preferably 5 to 200 μm . The thickness of the base
10 resin layer is typically 5 to 30000 μm , preferably 10 to 20000 μm , particularly preferably 20 to 10000 μm . The thickness of the adhesive resin layer is typically 0.5 to 250 μm , preferably 1 to 150 μm , particularly preferably 3 to 100 μm .

[0045] The thickness ratio between the EVOH resin
15 composition layer and the base resin layer of the multilayer structure (EVOH resin composition layer/base resin layer) (if these layers each include a plurality of layers, the thickness ratio between the thickest one of the EVOH resin composition layers and the thickest one of the base resin layers) is
20 typically 1/99 to 50/50, preferably 5/95 to 45/55, particularly preferably 10/90 to 40/60. The thickness ratio between the EVOH resin composition layer and the adhesive resin layer of the multilayer structure (EVOH resin composition layer/adhesive resin layer) (if these layers each include a
25 plurality of layers, the thickness ratio between the thickest

one of the EVOH resin composition layers and the thickest one of the adhesive resin layers) is typically 10/90 to 99/1, preferably 20/80 to 95/5, particularly preferably 50/50 to 90/10.

5 [0046] Bags, cups, trays, tubes, bottles and other containers and lids produced from the film, the sheet or the stretched film formed in the aforementioned manner are useful as packaging material containers for general foods, condiments such as mayonnaise and dressing, fermented foods such as miso,
10 fat and oil such as salad oil, beverages, cosmetics, and pharmaceutical products.

In particular, the layer of the inventive EVOH resin composition has a satisfactory UV absorbing ability and, therefore, is particularly useful as a food packaging material,
15 particularly, for packaging raw meat, ham, sausage, and other meat products, which are liable to be discolored due to ultraviolet radiation.

EXAMPLES

20 [0047] The present disclosure will hereinafter be described more specifically by way of examples thereof. However, it should be understood that the present disclosure be not limited to the examples within the scope of the present disclosure.

In the following examples, "parts" means "parts by
25 weight" unless otherwise specified.

[0048] <Example 1>

An iron strip (an SS400 plate available from Daido Die & Mold Steel Solutions Co., Ltd. and having a size of 60 mm × 60 mm × 990 mm) was kept in contact with an aqueous solution of additives (an aqueous solution containing 206 ppm of acetic acid, 206 ppm of sodium dihydrogen phosphate, 28 ppm of calcium phosphate, 280 ppm of sodium acetate and 117 ppm of boric acid) for 24 hours, whereby an aqueous solution containing iron compound in a proportion of 30 ppm on a metal basis was prepared.

Then, water containing pellets of an EVOH resin having an ethylene structural unit content of 44 mol %, a saponification degree of 99.6 mol % and an MFR of 12 g/10 minutes (as measured at 210°C with a load of 2160 g) were brought into contact with (immersed in) the aqueous solution containing the additives and the iron compound, whereby the additives and the iron compound were introduced into the EVOH resin pellets. Thereafter, the resulting pellets were dried at 118°C for 14 hours. Thus, pellets of an EVOH resin composition were produced.

[0049] After 10 ml of dilute sulfuric acid was added to 1 g of the EVOH resin composition pellets thus produced, the resulting mixture was heated at 250°C on a hot plate for 1 hour. Then, the mixture was further heated on an electric stove for 2 hours, and then heated at 700°C in an electric furnace for 4 hours. After the resulting sample was transferred from the

electric furnace to the electric stove, 2 ml of hydrochloric acid and 3 to 4 ml of distilled water were added to the sample and boiled. The resulting sample was put in a measuring flask and diluted with distilled water. Then, a sample solution thus
5 prepared was analyzed by an atomic spectrophotometer (Z-2300 available from Hitachi, Ltd.) and the proportion of the iron compound (on a metal basis) based on the weight of the EVOH resin composition pellets was determined.

[0050] By using the EVOH resin composition pellets thus
10 produced, a water/isopropanol (4/6) solution containing the EVOH resin composition at a concentration of 5 wt.% was prepared. Then, the UV transmittance of the solution thus prepared was measured at a wavelength of 300 nm by UV-VIS SPECTROPHOTOMETER UV-2600 (available from Shimadzu Corporation).

15 The results are shown in Table 1.

[0051] <Example 2>

Pellets of an EVOH resin composition were produced in substantially the same manner as in Example 1, except that the iron strip was kept in contact with the aqueous solution
20 of the additives for 3 hours and the iron compound was contained in a proportion of 6 ppm on a metal basis in the aqueous solution to be used for the immersion of the EVOH resin pellets.

The proportion of the iron compound (on a metal basis) based on the weight of the EVOH resin composition pellets was
25 determined. Further, a water/isopropanol solution

containing the EV0H resin composition at a concentration of 5 wt.% was prepared by using the EV0H resin composition pellets, and the UV transmittance of the aqueous solution was measured in the same manner as in Example 1.

5 The results are shown in Table 1.

[0052] <Comparative Example 1>

Pellets of an EVOH resin composition were produced in substantially the same manner as in Example 1, except that the aqueous solution of the additives was not kept in contact with the iron strip and, therefore, the iron compound was not contained in the aqueous solution to be used for the immersion of the EVOH resin pellets. Then, a water/isopropanol solution of the EVOH resin composition was prepared by using the EVOH resin composition pellets, and the UV transmittance of the solution was measured in the same manner as in Example 1.

The results are shown in Table 1.

[0053] Table 1

	Example 1	Example 2	Comparative Example 1
Proportion (ppm) of iron compound (on metal basis) based on weight of EVOH resin composition pellets	40	5	0
UV transmittance (%)	68.4	88.9	91.2

[0054] The above results indicate that the pellets of the
20 EVOH resin compositions of Examples 1 and 2 each containing
the iron compound in a specific proportion were satisfactory

in UV absorbing ability with a lower UV transmittance as compared with the EVOH resin composition pellets of Comparative Example 1 not containing the iron compound.

[0055] While specific forms of the embodiments of the present disclosure have been shown in the aforementioned inventive examples, the inventive examples are merely illustrative of the disclosure but not limitative of the disclosure. It is contemplated that various modifications apparent to those skilled in the art could be made within the scope of the disclosure.

[0056] The inventive EVOH resin composition is imparted with a satisfactory UV absorbing ability without including a UV absorber. Therefore, the inventive EVOH resin composition is advantageously used for packaging materials for packaging foods and chemicals.

CLAIMS:

1. An ethylene-vinyl alcohol copolymer composition comprising:

an ethylene-vinyl alcohol copolymer; and

an iron compound;

wherein the iron compound is present in a proportion of 0.01 to 100 ppm on a metal basis based on weight of the ethylene-vinyl alcohol copolymer composition.

2. A multilayer structure comprising at least one layer comprising an ethylene-vinyl alcohol copolymer composition according to claim 1.