

ABSTRACT

The present invention provides a microcrystalline glass product. The microcrystalline glass product includes the following components in percentage by weight: SiO₂: 45-70%;
5 Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃: greater than 0 but less than or equal to 8%. Through reasonable component design, the microcrystalline glass and the microcrystalline glass product obtained in the present invention have excellent mechanical and optical properties and are suitable for electronic devices or display devices.