

5 A treatment method for silicon-containing wastewater and the
utilization method thereof, and a method for preparing a molecular
sieve and the system thereof

10 **Technical field**

The present invention relates to a field of wastewater treatment, in particular to
a treatment of wastewater produced from the preparation of a molecular sieve or
catalyst. Specifically, the present invention relates to a method for treating the
15 silicon-containing wastewater produced from the preparation of a molecular sieve
or catalyst and a comprehensive utilization method. The present invention
further relates a method for preparing a molecular sieve, and the present
invention also relates to a preparation system of a molecular sieve.

20 **Background of the technology**

Molecular sieves are widely used as catalytic materials, adsorption and
separation materials and ion exchange materials for their structural
characteristics of high specific surface area, good thermal stability, good
25 water stability and uniform pore size, and in the field of petrochemical
industry molecular sieves find wide uses. In general, it is necessary to wash
crystallization products to remove the silicate/aluminosilicate salts remained
on the internal and external surfaces thereof after the crystallization process
is completed. Silicon-containing wastewater is thus produced. In addition,
30 artificially synthesized molecular sieves generally need to be converted into
hydrogen or multivalent metal ionic molecular sieves through an ion

exchange, so that they can be used as active components of an acid catalyst. Wastewater containing salt, silicon/silicon-aluminum materials can also be produced. Such wastewater cannot be discharged directly due to the high amount of suspended matters.

5

The following process is adopted by Jiang Feihua (Study on Silicon-Containing Wastewater Recycling Process of NaY Molecular Sieve, *Guangzhou Chemical Industry*, 41(21):131-132, 2013) for treating the wastewater produced from the preparation of NaY molecular sieve:

10

the crystallization mother liquid and the primary filtrate having a high content of SiO_2 and Na_2O are firstly subjected to a sedimentation separation; then the supernatant is neutralized with aluminum sulfate to form a colloid, i.e., aluminosilica colloid which is used for synthesizing the NaY molecular sieve.

15 At the same time, the bottom concentrated liquor produced from the sedimentation is delivered into the secondary phase of a belt filter for filtration in order to further recover the molecular sieve;

the secondary filtrate having a relatively low SiO_2 content cannot be directly recycled for the preparation of aluminosilica colloids due to the low SiO_2 concentration. Therefore, a sedimentation tank is used for a cascade sedimentation. When the suspended matters are reduced to a certain level, the supernatant is recycled to the crystallizing tank as the water for crystallization termination, cooling and alkalinity reduction in the crystallization tank in replace of fresh chemical water. The thick liquid at the bottom of the sedimentation tank together the thick liquid at the tank bottom for the sedimentation of the primary filtrate are delivered to the secondary phase of a belt filter and recycled to achieve the recycling of SiO_2 filtrate which has a low concentration.

30

Although the method saves chemical water and decreases the discharging of

sewage with an improved utilization of silicon to some extent, the method does not recover the silicon in the secondary filtrate. But the secondary filtrate is used as the water for crystallization termination, cooling and alkalinity reduction in the crystallization tank after the sedimentation and the separation of the suspended matters, as still results in wasting of the silicon resource.

For the recovery of silicon in the wastewater containing SiO_2 from the preparation of molecular sieves, the existing methods usually employs a neutralization of aluminum to a colloid together with the use of a flocculant for facilitating the filtration.

For example, CN103359848A discloses a method for the treatment of silicon-containing washing wastewater from the preparation of a Na molecular sieve, comprising the following steps:

- (1) the silica-containing washing wastewater of the Na molecular sieve is neutralized with an acidified aluminum salt solution until the pH is 6-10 and a alumina-silica gel is formed;
- (2) a flocculant or a flocculant and a filter aid are added into the above gel for flocculation and sedimentation;
- (3) the gel obtained in step (2) is filtered and washed. The filtration residue is recycled while the filtrate is discharged directly.

In another example, CN1453220A discloses a recycling method of the washing water of a Y molecular sieve. The method comprises the following steps:

- (1) cationic polyacrylamide or anionic polyacrylamide in an amount of 5-20ppm, preferably 8-15ppm is added into the washing water for the molecular sieve exchange and stirred for at least 2 minutes; then the polymerized AlCl_3 in an amount of 1-10ppm, preferably 2-8ppm is added. Keep stirring until a clear liquid and a solid precipitate are formed;

(2) a depth filter or other common filters in the art are used for separating the above clear liquid and the solid precipitate. The selected depth filter is filled with quartz sand and/or slag having a particle size of 0.7-2.0mm, preferably 0.8-1.5mm and a bed height of 300-1000mm, preferably 400-900mm as fillers. A clear liquid having a turbidity of 10-20 can be obtained after the clear liquid and the solid precipitate from step (1) are filtered by a depth filter;

(3) the clear liquid from step (2) passes through a cation exchange column filled with a cation exchange resin. The Na^+ in the clear liquid exchanges with the H^+ on the ion exchange resin so that the content of Na^+ in the clear liquid is reduced to 0.1-0.6 wt.%;

(4) the clear liquid from step (3) is formulated into a molecular sieve exchange solution for recycling.

However, as a flocculant is a must in the recovery of silicon element in the washing wastewater containing silicon in the above method, the recovered silicon also contains the flocculant. Therefore, the recycled silicon may have an adverse effect on the quality of the molecular sieve when being reused in the preparation of the molecular sieve. Moreover, the practical operation shows that the recovery rate of silicon in the above method still needs to be further improved. Furthermore, the above methods only realize a partial reuse of the silicon-containing washing wastewater, and a certain amount of effluent is still produced.

Contents of the invention

The object of the present invention is to overcome the deficiencies of the existing recovery and recycling of the wastewater from the preparation of a molecular sieve, and provide a treatment method for silicon-containing wastewater. By the treatment method, a higher silicon recovery rate and a higher wastewater utilization rate can be reached in the treatment of the

wastewater produced from the preparation process of a molecular sieve, particularly the crystallization wastewater, the washing wastewater and/or the ion exchange wastewater with a relatively high silicon content.

5 According to the first aspect of the present invention, the invention provides a treatment method for silicon-containing wastewater, wherein the silicon-containing wastewater comes from the preparation of a molecular sieve or a catalyst, comprising the following steps:

10 Step (1): the silicon-containing wastewater is contacted with at least one acid or at least one alkali, so that at least a part of the silicon elements in the silicon-containing wastewater form a colloid, and a mixture containing a colloid is obtained;

15 Steps (2): the mixture containing a colloid as obtained in step (1) is subjected to a solid-liquid separation to produce a silicon-containing solid phase and a first liquid phase;

Step (3): the pH value of the first liquid phase is regulated to 8 or more, and
20 CO_3^{2-} and/or Ca^{2+} are introduced into the first liquid phase so that at least a part of the metal elements in the first liquid phase form a precipitate;

Steps (4): the mixture as obtained by step (3) is subjected to a solid-liquid separation to produce a solid phase and a second liquid phase;

25

Step (5): at least a part of the second liquid phase is subjected to an electrodialysis treatment to produce an acid liquor and /or alkali liquor.

According to the second aspect of the invention, the present invention
30 provides a method for the utilization of silicon-containing wastewater, wherein the silicon-containing wastewater comes from the preparation of a

molecular sieve or a catalyst. The method comprises the treatment of the silicon-containing wastewater by using the method according to the first aspect of the present invention.

- 5 In the above, the silicon-containing solid phase as obtained in step (2) is recycled as the raw material for a molecular sieve synthesis;

at least a part of the second liquid phase as obtained in step (4) is recycled as the washing water for the washing process of the molecular sieve;

10

the acid liquor as obtained in step (5) is recycled as the ion exchange liquid in the ion exchange process of the molecular sieve; the alkali liquor as obtained in step (5) is recycled as the alkali source in the molecular sieve synthesis.

- 15 Preferably, step (5) further produces desalted water which is recycled as the washing water in the synthesis of the molecular sieve and/or the washing process of the molecular sieve.

According to the third aspect of the invention, the present invention provides
20 a method for the preparation of a molecular sieve, comprising a synthesis step, a crystallization step, a separation step, a washing step, a wastewater recovery and recycling step, and an optional ion exchange step.

In the synthesis step, a silicon source and an alkali source as well as an
25 optional aluminum source and an optional titanium source are contacted in water for reaction;

in the crystallization step, the mixture as obtained from the synthesis step is crystallized;

30

in the separation step, the mixture obtained from the crystallization step is

subjected to a solid-liquid separation to produce a solid phase and a liquid phase;

5 in the washing step, the solid phase as obtained from the separation step is washed with washing water to obtain a molecular sieve and washing wastewater;

10 in the ion exchange process, the molecular sieve is contacted with an ion exchange liquid for carrying out ion exchange and thereafter the solid-liquid separation is carried out to produce an ion exchanged molecular sieve and an ion exchange waste liquid;

15 in the wastewater recovery and recycling step, wastewater is collected and treated by using the method according to the first aspect of the invention. The wastewater is the liquid phase in the separation step, the washing wastewater in the washing step, and the ion exchange waste liquid in the ion exchange step.

20 According to the fourth aspect of the invention, the present invention provides a molecular sieve preparation system, comprising a synthesis unit, a crystallization unit, a separation unit, a washing unit, a wastewater recovery and recycling unit, and an optional ion exchange unit.

25 The synthesis unit is used for contacting a silicon source and an alkali source as well as an optional aluminum source and an optional titanium source in water for reaction;

the crystallization unit is used for crystallizing the mixture from the synthesis unit;

30

the separation unit is used for carrying out a solid-liquid separation on the

mixture as obtained from the crystallization unit to produce a liquid phase and a solid phase; the produced liquid phase is delivered into the wastewater recovery and recycling unit as wastewater;

5 in the washing unit, the solid phase as obtained from the separation unit is washed with a washing water to produce a molecular sieve and washing wastewater; the washing wastewater is delivered into the wastewater recovery and recycling unit as wastewater;

10 the ion exchange unit is used for contacting the molecular sieve as obtained from the washing unit with the ion exchange liquid to carry out an ion exchange, from which an ion exchanged molecular sieve and an ion exchange waste liquid are obtained; the ion exchange waste liquid is delivered into the wastewater recovery and recycling unit;

15

the said wastewater recovery and recycling unit is used for treating wastewater; the said wastewater recovery and recycling unit includes a first precipitation reaction unit, a first solid-liquid separation unit, a second precipitation reaction unit, a second solid-liquid separation unit and an
20 electrodialysis unit;

the first precipitation reaction unit is used for contacting the wastewater with at least one acid or at least one alkali so that the silicon in the wastewater forms a colloid; a mixture containing a colloid is thus obtained;

25

the first solid-liquid separation unit is used for carrying out a solid-liquid separation on the mixture containing a colloid as obtained from the first precipitation reaction unit; a silicon-containing solid phase and a first liquid phase are thus obtained;

30

the second precipitation reaction unit is used for regulating the pH value of

the first liquid phase to 8 or more and introducing CO_3^{2-} and/or Ca^{2+} into the first liquid phase so that at least a part of the metal elements in the first liquid phase form a precipitate;

- 5 the second solid-liquid separation unit is used for carrying out a solid-liquid separation on the mixture as obtained from the second precipitation reaction unit to obtain a solid phase and a second liquid phase;

the electrodialysis unit is used to carrying out an electrodialysis treatment,
10 preferably a bipolar membrane electrodialysis treatment, more preferably a treatment of a common electrodialysis and a bipolar membrane electrodialysis in series, on at least a part of the second liquid phase to produce an acid liquor and/or alkali liquor.

- 15 By the method of the present invention, a higher silicon recovery rate can be reached in the treatment of the silicon-containing wastewater produced from the preparation process of a silicon-containing molecular sieve or a catalyst, particularly the wastewater having a relatively high silicon content (such as washing wastewater and ion exchange waste liquid), even without a dependence
20 on a flocculant. In the meanwhile, the method of the present invention can achieve a higher wastewater utilization rate, and basically no wastewater or an extremely low volume of wastewater is discharged. In the meanwhile, the discharged solid wastes are in a very low amount.

25 **Brief description of the drawings**

The drawings which are provided for a further understanding of the invention constitute a part of the specification. The drawings are used to explain the present invention together with the following specific embodiments but do
30 not constitute restrictions on the invention.

FIG.1 is an embodiment of the treatment of the second liquid phase by using a dual-chamber bipolar membrane electrodialysis.

FIG.2 is another embodiment of the treatment of the second liquid phase by using a dual-chamber bipolar membrane electrodialysis.

FIG.3 is an embodiment of the treatment of the second liquid phase by using a triple-chamber bipolar membrane electrodialysis.

FIG.4 is an embodiment of the treatment of the second liquid phase by using a common electrodialysis-triple-chamber bipolar membrane electrodialysis.

FIG. 5 is used to illustrate a method for the preparation of a molecular sieve and a molecular sieve preparation system according to the present invention.

FIG. 6 is the photo of SEM of the Na molecular sieve prepared by using fresh water and fresh alkali liquor as the control group in Example 1.

FIG. 7 is the photo of SEM of the Na molecular sieve prepared by using the desalted water, the recovered silicon source and the recovered alkali source in Example 1.

Description of the reference signs

- 1: anion exchange layer of the bipolar membrane
- 2: cation exchange layer of the bipolar membrane
- 3: cation exchange membrane
- 4: positive electrode
- 5: negative electrode
- 6: anion exchange membrane
- A: aqueous electrolyte solution

B: the second liquid phase

C: water

D: acid liquor

E: alkali liquor

5 F: desalted water

Specific embodiments

10 According to the first aspect of the present invention, the present invention provides a treatment method for silicon-containing wastewater, comprising step (1): the silicon-containing wastewater is contacted with at least one acid or at least one alkali so that at least a part of the silicon elements in the silicon-containing wastewater form a colloid. A mixture containing a colloid
15 is thus obtained.

The said silicon-containing wastewater comes from the preparation of a molecular sieve or a catalyst. The said molecular sieve can be various kinds of common silicon-containing molecular sieves, such as a Y molecular sieve,
20 X molecular sieve, A molecular sieve, MCM molecular sieve, ZSM molecular sieve (such as ZHP molecular sieve), a mordenite molecular sieve, a beta molecular sieve and a titanium silicalite molecular sieve. The catalyst can be an FCC catalyst

25 The silicon-containing wastewater can be the crystallization mother liquid, the washing wastewater produced in the washing step, the ion exchange waste liquid produced in the ion exchange process or a mixture of two or more of the above in the preparation of a molecular sieve or a catalyst. It can also be the exchange waste liquid and/or the washing waste liquid in the preparation
30 of an FCC catalyst. The method of the present invention is especially suitable for treating a silicon-containing waste liquid with a relatively high silicon

content, for example, treating the silicon-containing waste liquid with a content of silicon element of 10mg/L or more (such as 10-15000mg/L), preferably 50mg/L or more, and particularly preferably the silicon-containing waste liquid with a content of silicon element of 100mg/L or more. The silicon-containing waste liquid with a relatively high silicon content can specifically be a crystallization mother liquid produced in crystallization, washing wastewater produced in the washing step, an ion exchange waste liquid produced in ion exchange process or a mixture of two or more of the above, and a washing waste liquid from the preparation of a catalyst.

10

The acid and the alkali are used for precipitating the silicon element in the silicon-containing wastewater by forming a colloid. The prior art shows that the silicon colloid obtained by using a conventional method is a material difficult to be filtered. In case of the filtration using a plate and frame filter, a phenomenon such as a penetrating filtration or a filter cloth blockage easily happens. Therefore, a flocculant and/or a filter aid is often used. However, compared with the use of acidified aluminum sulfate, $AlCl_3$ and polyaluminum chloride, on the one hand, the use of acid or alkali in the present invention can enable the silicon colloid as formed to possess a better filtration performance so that the need for the flocculant and the filter aid is omitted. Moreover, since the product is mainly a silicon colloid, it is convenient to recover and recycle the product. On the other hand, it can also reach a higher silicon precipitation rate, and thereby achieves a higher silicon recovery rate.

25

The acid is preferably an inorganic acid. The specific examples may include but are not limited to hydrochloric acid, sulfuric acid, nitric acid and phosphoric acid. Preferably, the acid is sulfuric acid and/or hydrochloric acid. The acid is provided in the form of an aqueous solution, the concentration of which is not particularly limited. It can be a conventional concentration according to the specific kind of acid, preferably 0.5-20wt.%, more

30

preferably 1-10wt.%, and even more preferably 2-5wt.%.

The alkali is preferably an inorganic alkali, more preferably selected from alkali hydroxide and ammonia water, and even preferably selected from sodium hydroxide, potassium hydroxide and ammonia water, and most preferably sodium hydroxide. The alkali is preferably provided in the form of an aqueous solution, the concentration of which is not particularly limited. It can be a conventional concentration according to the specific kind of the alkali.

The specific amounts of the acid and the alkali can be selected according to the kind of acid and alkali and the properties of the silicon-containing wastewater to meet the requirement of the formation of a colloid by the silicon in the silicon-containing wastewater. In general, the amount of the acid or the alkali keeps the pH value of the silicon-containing wastewater within the range of 2-9, preferably within the range of 3-9, more preferably within the range of 3-6.9. Preferably, the silicon-containing wastewater is contacted with at least one acid, wherein the amount of the said acid keeps the pH value of the silicon-containing wastewater within the range of 4-7.5, preferably within the range of 5-6.9. In addition, the specific range of the pH value can further be optimized according to the specific source of the silicon-containing wastewater. In one embodiment, the silicon-containing wastewater comes from the preparation of a Y molecular sieve, wherein the amount of the said acid or alkali preferably keeps the pH value of the silicon-containing wastewater within the range of 6.5-7.5. In another embodiment, the silicon-containing wastewater comes from the preparation of a ZSM molecular sieve, wherein the amount of the said acid or alkali preferably keeps the pH value of the silicon-containing wastewater within the range of 4.5-7. In another embodiment, the silicon-containing wastewater comes from the preparation of a titanium silicalite molecular sieve, wherein the amount of the said acid or alkali preferably keeps the pH value of the silicon-containing

wastewater within the range of 6-7.

The silicon-containing wastewater may be contacted with at least one acid or at least one alkali at a temperature of 10-60°C, preferably 40-50°C, with the
5 requirement that the contact period is sufficient for most of the silicon in the silicon-containing wastewater to form a colloid. Generally, the contact period can be 0.5-8 hours, preferably 3-5 hours. For further improving the filtration performance and further improving the removal rate of silicon, the mixture produced from the above contact is preferably aged after the contact of the
10 silicon-containing wastewater with acid or alkali is completed. The aging can be carried out at a temperature of 0-95°C, preferably 40-85°C. The period for the said aging may be 5-24 hours.

The treatment method for the silicon-containing wastewater according to the
15 present invention comprises step (2): the mixture containing a colloid produced in step (1) is subjected to a solid-liquid separation to produce a silicon-containing solid phase and a first liquid phase.

In step (2), the mixture containing a colloid produced in step (1) can be
20 separated by using a conventional solid-liquid separation method, such as filtration, centrifugation or a combination of two or more separation methods. Preferably a filtration method is used for separating the mixture containing a colloid produced in step (1). A variety of common filter media can be used in the filtration, for example, one selected from a fabric, a porous material, a
25 solid particle layer and a porous membrane, or a combination of two or more of the above. Said porous membrane can be an organic membrane, an inorganic membrane or a combination of two or more kinds of porous membranes. Said inorganic membrane can be a ceramic membrane and/or a metal membrane; the organic membrane can be a hollow fiber membrane.
30 Preferably, a fabric can be used as the filter medium. The filtration can be carried out in a common filtration device, such as a plate and frame filter and

a belt filter.

Generally, the water content of the silicon-containing solid phase as obtained under the said solid-liquid separation conditions is less than 45wt.%, for example 30-40wt.%. The solid-liquid separation can be carried out at the ambient temperature or also under heating conditions. Generally, the solid-liquid separation can be carried out at a temperature of 20-80 °C, preferably at the ambient temperature (i.e., 15-40°C). The period of the solid-liquid separation can be selected according to the solid-liquid separation modes, without any specific limitation.

The silicon-containing solid phase as obtained from the solid-liquid separation of the mixture containing a colloid produced in step (1) can serve as the silicon source for the synthesis of a silicon-containing molecular sieve.

The treatment method for the silicon-containing wastewater according to the present invention comprises step (3): the pH value of the first liquid phase is regulated to 8 or more; CO_3^{2-} and/or Ca^{2+} is optionally introduced into the first liquid phase so that at least a part of the metal elements in the first liquid phase forms a precipitate;

CO_3^{2-} can be introduced into the first liquid phase by adding a water-soluble carbonate into the first liquid phase. "Water-soluble" means that the solubility in water is 1g or more. Said water-soluble carbonate are preferably selected from the alkali salts and ammonium salts of carbonic acid. More preferably, the water-soluble carbonate is selected from sodium carbonate, potassium carbonate and ammonium carbonate. Even preferably, the water-soluble carbonate is sodium carbonate.

The object of introducing CO_3^{2-} into the first liquid phase is to make the calcium and magnesium ions in the first liquid phase form a precipitate, and

thereby reduce the hardness of the first liquid phase. The introduction amount of CO_3^{2-} can be selected according to the content of metal elements in the first liquid phase. In general, the amount of CO_3^{2-} introduced into the first liquid phase can be 0.1-20mmol/L, preferably 1-15mmol/L.

5

When the first liquid phase further comprises silicon element, Ca^{2+} is preferably introduced into the first liquid phase so that the silicon in the first liquid phase and calcium form calcium silicate which precipitates from the first liquid phase. Generally, Ca^{2+} is introduced into the first liquid phase
10 when the content of Si in the first liquid phase is 50mg/L or more, preferably 80-150mg/L. The introduction amount of Ca^{2+} is determined by the content of Si in the first liquid phase. In general, the amount of Ca^{2+} introduced into the first liquid phase can be 0.1-10mmol/L, preferably 1-5mmol/L.

- 15 The introduction of Ca^{2+} can be achieved by adding one or more of calcium sulfate, calcium chloride, calcium hydroxide and calcium oxide into the first liquid phase.

In step (3), the pH value of the first liquid phase is generally regulated to 8 or
20 more, more preferably 9 or more (for example, 9-12), even preferably 10.5-11.5, which is thus beneficial to the precipitation of metal ions in the first liquid phase. The pH value of the first liquid phase can be regulated by adding at least one alkali to the first liquid phase. The alkali can be selected from alkali hydroxide, alkali earth hydroxide and ammonia water, preferably
25 from sodium hydroxide, potassium hydroxide, calcium hydroxide and ammonia water, more preferably sodium hydroxide. The alkali is preferably provided in the form of an aqueous solution, the concentration of which is not particularly limited. It can be a conventional concentration according to the specific kind of the alkali.

30

The object of the step (3) is mainly to reduce the content of calcium and

magnesium ions, silicon element and other metal ions that can form precipitates in the wastewater. A person skilled in the art can understand that it is possible to omit step (3) when the content of the above ions in the wastewater is low or the wastewater is free of the above elements.

5

The treatment method for the silicon-containing wastewater according to the present invention comprises step (4): a solid phase and a second liquid phase are obtained from the solid-liquid separation of the mixture produced from step (3).

10

In step (4), a conventional solid-liquid separation method can be used to separate the mixture obtained in step (3), such as filtration, centrifugation or a combination of two or more above separation methods. Preferably, the mixture obtained in step (3) is separated by a filtration method. A variety of
15 common filter media can be used in the filtration, for example, one selected from a fabric, a porous material, a solid particle layer and a porous membrane or a combination of two or more of the above. Said porous membrane can be an organic membrane, an inorganic membrane or a combination of the above two. Said inorganic membrane can be a ceramic membrane and/or a metal
20 membrane; the organic membrane can be a hollow fiber membrane. Preferably, a porous membrane is used as the filter medium.

In step (4), the said solid-liquid separation conditions generally make the water content of the solid phase as produced 20wt.% or less. The solid-liquid
25 separation can be carried out at the ambient temperature or also under heating conditions, preferably at the ambient temperature.

The solid phase obtained in step (4) can be discharged out. The second liquid phase obtained in step (4) has a low ion content and can be used as the
30 washing water for the preparation of a molecular sieve. The second liquid phase can also be further treated.

The step (4) is used for carrying out a solid-liquid separation on the mixture obtained from the step (3). A person skilled in the art can understand that the present method does not comprise step (4) correspondingly when step (3) is not comprised.

The treatment method for the silicon-containing wastewater according to the present invention comprises step (5): at least a part of the second liquid phase is subjected to an electrodialysis to produce an acid liquor, an alkali liquor and/or desalted water. An acid liquor, an alkali liquor and/or desalted water can be produced by an electrodialysis of the second liquid phase. Therein the acid liquor can be used in the molecular sieve exchange process, for example, the acid liquor can ionically exchange with a non-hydrogen molecular sieve as an ion exchange liquid to produce a hydrogen molecular sieve. The alkali liquor can be used as the alkali in the synthesis process of a molecular sieve.

The electrodialysis method is not particularly limited in the present invention. It can be a bipolar membrane electrodialysis or a combination of a bipolar membrane electrodialysis and a common electrodialysis.

The bipolar membrane electrodialysis can be a dual-chamber bipolar membrane electrodialysis or a triple-chamber bipolar membrane electrodialysis. The membrane stack used in the said dual-chamber bipolar membrane electrodialysis can be composed of a bipolar membrane and a cation exchange membrane or an anion exchange membrane. The membrane stack used in the said triple-chamber bipolar membrane electrodialysis can be composed of a bipolar membrane, a cation exchange membrane and an anion exchange membrane.

Specifically, the membrane stack of the dual-chamber bipolar membrane electrodialysis can be composed of at least two bipolar membranes and at least one cation exchange membrane, and the bipolar membranes and the

cation exchange membrane are alternately arranged. In the practical operation, as shown in FIG. 1, at least two bipolar membranes and at least one cation exchange membrane 3 are arranged between the positive electrode 4 and the negative electrode 5, and the bipolar membranes and the cation exchange membrane 3 are alternately arranged; the second liquid phase B enters the acid chamber between the cation exchange layer 2 of the bipolar membranes and the cation exchange membrane 3; water C enters the alkali chamber between the anion exchange layer 1 of the bipolar membranes and the cation exchange membrane 3; the aqueous electrolyte solution A is filled into the electrode chamber between the positive electrode 4 and the anion exchange layer 1 of the bipolar membranes and the electrode chamber between the negative electrode 5 and the cation exchange layer 2 of the bipolar membranes; a direct current is applied between the positive electrode 4 and the negative electrode 5 for an electrodialysis treatment. Thus, the acid liquor D is obtained in the acid chamber and the alkali liquor E is obtained in the alkali chamber.

The membrane stack of the dual-chamber bipolar membrane electrodialysis can also be composed of at least two bipolar membranes and at least one anion exchange membrane, and the bipolar membranes and the anion exchange membrane are arranged alternately. In the practical operation, as shown in FIG. 2, at least two bipolar membranes and at least one anion exchange membrane 6 are arranged between the positive electrode 4 and the negative electrode 5, and the bipolar membranes and the anion exchange membrane 6 are alternately arranged; water C enters the acid chamber between the cation exchange layer 2 of the bipolar membranes and the anion exchange membrane 6; the second liquid phase B enters the alkali chamber between the anion exchange layer 1 of the bipolar membranes and the anion exchange membrane 6; the aqueous electrolyte solution A is filled into the electrode chamber between the positive electrode 4 and the anion exchange layer 1 of the bipolar membranes and the electrode chamber between the

negative electrode 5 and the cation exchange layer 2 of the bipolar membranes; a direct current is applied between the positive electrode 4 and the negative electrode 5 for an electrodialysis treatment. Thus, the acid liquor D is obtained in the acid chamber and the alkali liquor E is obtained in the alkali chamber.

The membrane stack of the triple-chamber bipolar membrane electrodialysis can be composed of at least two bipolar membranes, at least one cation exchange membrane and at least one anion exchange membrane, wherein the cation exchange membrane and the anion exchange membrane in pair separate the bipolar membranes from each other. In the practical operation, as shown in FIG. 3, at least two bipolar membranes and at least one cation exchange membrane 3 and at least one anion exchange membrane 6 are arranged between the positive electrode 4 and the negative electrode 5, wherein the cation exchange membrane 3 and the anion exchange membrane 6 in pair separate the bipolar membranes from each other; the second liquid phase B enters the salt chamber between the cation exchange membrane 3 and the anion exchange membrane 6; water C enters the acid chamber between the cation exchange layer 2 of the bipolar membranes and the anion exchange membrane 6 and the alkali chamber between the anion exchange layer 1 of the bipolar membranes and the cation exchange membrane 3; the aqueous electrolyte solution A is filled into the electrode chamber between the positive electrode 4 and the anion exchange layer 1 of the bipolar membranes and the electrode chamber between the negative electrode 5 and the cation exchange layer 2 of the bipolar membranes; a direct current is applied between the positive electrode 4 and the negative electrode 5 for an electrodialysis treatment. Thus, the acid liquor D is obtained in the acid chamber; the alkali liquor E is obtained in the alkali chamber, and the desalted water F is obtained in the salt chamber.

Preferably, the second liquid phase is treated with a triple-chamber bipolar

membrane electrodialysis. The produced acid liquor can be used in the ion exchange process of the molecular sieve; the produced alkali liquor can be used as the alkali source in the synthesis process of the molecular sieve; the produced desalted water can be used as the water for one, two or three of the following processes: the molecular sieve synthesis process, the crystallization process and the washing process.

In a preferred embodiment of the invention, the triple-chamber bipolar membrane electrodialysis is combined with the common electrodialysis, wherein the common electrodialysis is located upstream of the triple-chamber bipolar membrane electrodialysis. That is, the second liquid phase enters the common electrodialysis for an electrodialysis, from which a concentrate and a first desalted water are obtained. The concentrate enters the bipolar membrane electrodialysis for a bipolar membrane electrodialysis. The first desalted water obtained from the common electrodialysis is recycled as the water for the molecular sieve synthesis process and/or the washing water for the washing process. Specifically, as shown in FIG.4, the second liquid phase enters the feed liquid chamber of the common electrodialysis for an electrodialysis, from which a concentrate and a first desalted water are respectively produced. The first desalted water can be recycled as the water for the molecular sieve synthesis process, the water for the crystallization process and/or the washing water for the washing process. The concentrate enters the salt chamber of the bipolar membrane electrodialysis for a bipolar membrane electrodialysis, from which an acid liquor, an alkali liquor and a second desalted water are produced. The acid liquor can be used in the ion exchange process of the molecular sieve; the alkali liquor can be used as the alkali source in the synthesis process of the molecular sieve; the second desalted water can be used as the water for the synthesis process of the molecular sieve, the water for the crystallization process and/or the washing water for the washing process.

In the present invention, "common electrodialysis" refers to the electrodialysis wherein no bipolar membrane is used in the membrane stack. "Bipolar membrane electrodialysis" refers to the electrodialysis wherein at least a part of the membrane units in the membrane stack comprises a bipolar
5 membrane. The electrodialysis wherein a common electrodialysis and a triple-chamber bipolar membrane electrodialysis are connected in series in the above preferable manner is called as a common electrodialysis-triple-chamber bipolar membrane electrodialysis.

- 10 According to the method of the present invention, the voltage applied to each membrane unit in the electrodialysis can be 0.1-8V, preferably 1-6V, more preferably 2-5V and even preferably 2-3V for the bipolar membrane electrodialysis. The voltage applied to each membrane unit can be 0.1-8V, preferably 1-6V, more preferably to 2-5V and even preferably 2-3V for the
15 common electrodialysis.

According to the method of the present invention, the cation exchange membrane in the bipolar membrane electrodialysis and the common electrodialysis is a styrene-type homogeneous cation exchange membrane
20 when the silicon-containing wastewater comprises quaternary ammonium ions. The inventor of the present invention found in the study that when a homogeneous cation exchange membrane was used for an electrodialysis, the migration speed of the quaternary ammonium ions was closely associated with the material of the homogeneous cation exchange membrane, as was
25 different from inorganic ions such as Na^+ ; when a poly(ether-ether-ketone) homogeneous cation exchange membrane, perfluoroethylene sulfonic acid homogeneous cation exchange membrane or polysulfone homogeneous cation exchange membrane was used for an electrodialysis, no good electrodialysis effect could be achieved even if a high voltage was applied on the membrane
30 unit; the quaternary ammonium ion content in the produced desalted water was still very high. Basically, it was impossible to achieve the effect of

reducing the quaternary ammonium ion content, and the removal rate of the quaternary ammonium ions was less than 10%. However, a good electrodialysis effect could be achieved when a styrene-type homogeneous cation exchange was used. The quaternary ammonium ion content in the produced desalted water was significantly reduced as quaternary ammonium ions were enriched in the alkali liquor. The removal rate of the quaternary ammonium ions was $\geq 92\%$ or even $\geq 95\%$.

The ion exchange capacity of the styrene-type homogeneous cation exchange membrane is not particularly limited. It can be a conventional selection, such as 1-3meq/g dry membrane, preferably 1.5-3meq/g dry membrane and more preferably 1.8-2.6meq/g dry membrane. According to the method of the present invention, the membrane surface resistance of the styrene-type cation exchange membrane can be $1-15\Omega\cdot\text{cm}^2$, preferably $2-12\Omega\cdot\text{cm}^2$. According to the method of the invention, the membrane surface resistance of the styrene-type homogeneous cation exchange membrane is more preferably $4-9\Omega\cdot\text{cm}^2$ for further improving the electrodialysis effect.

According to the method of the present invention, the use of the above styrene-type homogeneous cation exchange membrane can also achieve a better electrodialysis effect compared with other cation exchange membranes for the silicon-containing wastewater which does not comprise quaternary ammonium ions. Compared with heterogeneous cation exchange membranes, the styrene-type homogeneous cation exchange membrane not only can achieve a better electrodialysis effect but also can achieve a longer service life of the membranes, and thereby prolong the stable operation time of the electrodialyzer, improve the production efficiency and reduce the operation energy consumption.

According to the method of the present invention, the kinds of the bipolar membranes and the anion exchange membrane are not particularly limited.

Conventional membranes can be used. As for the anion exchange membrane, further improving the service life of the membrane, a homogeneous anion exchange membrane is preferred, for example, one of a styrene-type anion exchange membrane, a polysulfone-type anion exchange membrane, poly(ether-ether-ketone) anion exchange membrane and a perfluoroethylene sulfonic acid anion exchange membrane or the combinations of two or more of the above, preferably a styrene-type anion exchange membrane. According to the method of the invention, the specific parameters of the anion exchange membrane can be conventionally selected without any specific limitation. For example, the ion exchange capacity of the anion exchange membrane can be 0.5-5meq/g dry membrane, preferably 1-4meq/g dry membrane, and more preferably 2-2.5meq/g dry membrane. The membrane surface resistance of the anion exchange membrane can be 1-15 $\Omega \cdot \text{cm}^2$, preferably 2-12 $\Omega \cdot \text{cm}^2$.

Generally, the said quaternary ammonium ion can be a quaternary ammonium ion as represented by formula I,



In formula I, R_1 , R_2 , R_3 and R_4 may independently be C_1 - C_5 alkyl and C_6 - C_{12} aryl. The C_1 - C_5 alkyl includes C_1 - C_5 linear alkyl and C_3 - C_5 branched alkyl. The specific examples include methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, n-amyl, isoamyl, tert-amyl and neo-amyl. Specific examples of the C_6 - C_{12} aryl include but are not limited to: phenyl, naphthyl, 4-methylphenyl, 2-methylphenyl, 3-methylphenyl, 4-ethylphenyl, 2-ethylphenyl and 3-ethylphenyl.

Preferably, the quaternary ammonium ion can be tetramethyl-ammonium ion, tetraethylammonium ion, tetrapropylammonium ion, and tetrabutyl ammonium ion. As a preferable example, the quaternary ammonium ion is

tetrapropylammonium ion.

The quaternary ammonium ion can be derived from quaternary ammonium hydroxide and/or quaternary ammonium salt. The anion of the quaternary ammonium salt can be a common anion, such as a halogen ion, preferably a chloride or bromide ion, which is able to form a water-soluble salt with the quaternary ammonium ion.

The silicon-containing wastewater which comprises quaternary ammonium ions can be, for example, the wastewater derived from the preparation of a molecular sieve using quaternary ammonium hydroxide as the template. The specific examples of a molecular sieve using quaternary ammonium hydroxide as the template may include but are not limited to a titanium silicalite molecular sieve, a beta molecular sieve and a ZSM molecular sieve. The specific method for the preparation of a molecular sieve using quaternary ammonium hydroxide as the template is known in the field, for example, see the preparation methods as disclosed in CN1167082A, CN1239015A and CN1239016A.

The use of the method of the present invention for treating the silicon-containing wastewater produced in the preparation of a molecular sieve can achieve an effective reuse of the recoverable resources in the silicon-containing wastewater with a high utilization rate of the wastewater. Basically no wastewater or an extremely low volume of wastewater is discharged. In the meanwhile, the discharged solid wastes are in a very low amount.

According to the second aspect of the present invention, the invention further provides a method for the utilization of a silicon-containing wastewater, wherein the silicon-containing wastewater comes from the preparation of a molecular sieve. The method comprises the treatment of the

silicon-containing wastewater by the method according to the first aspect of the present invention.

Therein, the silicon-containing solid phase obtained in step (2) is recycled as
5 the raw material for a molecular sieve synthesis;

at least a part of the second liquid phase obtained in step (4) is recycled as the washing water in the washing process of the molecular sieve;

10 the acid liquor obtained in step (5) is recycled in the ion exchange process of the molecular sieve (for example, as the ion exchange liquid of the non-hydrogen molecular sieve for preparing a hydrogen molecular sieve); the alkali liquor obtained in step (5) is recycled as the alkali source in the molecular sieve synthesis.

15

When the silicon-containing wastewater is treated using the method according to the first aspect of the present invention, in case that step (5) adopts the method of a triple-chamber bipolar membrane electrodialysis or a common electrodialysis-triple-chamber bipolar membrane electrodialysis for
20 treating the second liquid phase, in addition to the use of the acid liquor obtained from electrodialysis in the ion exchange process of the molecular sieve and the reuse of the alkali liquor obtained from the bipolar membrane electrodialysis as the alkali source in the molecular sieve synthesis, the desalted water can also be recycled as the water for the molecular sieve
25 synthesis process and/or as the washing water in the washing process.

According to the third aspect of the invention, the present invention provides a method for the preparation of a molecular sieve, comprising a synthesis step, a crystallization step, a separation step, a washing step, a wastewater
30 recovery and recycling step, and an optional ion exchange step.

In the synthesis process, the silicon source and the alkali source as well as the optional aluminum source and the optional titanium source are contacted in water for reaction;

- 5 in the crystallization step, the mixture obtained from the synthesis step is crystallized;

in the separation step, the mixture obtained from the crystallization step is subjected to a solid-liquid separation to produce a solid phase and a liquid
10 phase;

in the washing step, the solid phase obtained from the separation step is washed with the washing water to produce a molecular sieve and washing
wastewater;

15

in the ion exchange step, the molecular sieve is contacted with the ion exchange liquid. After the ion exchange, the solid-liquid separation is carried out to produce an ion exchanged molecular sieve and an ion exchange waste
liquid;

20

in the wastewater recovery and recycling step, wastewater is collected and treated using the method according to the first aspect of the present invention. The wastewater is one of the liquid phase in the separation step, the washing wastewater in the washing step and the ion exchange waste liquid in the ion
25 exchange step or mixtures of two or more of the above waste liquids, preferably the washing wastewater in the washing step and the ion exchange waste liquid in the ion exchange step. The liquid phase in the separation step can be treated using the method according to the first aspect of the invention or using other methods to recover the silicon element therein. The waste
30 liquid from which the silicon element is recovered is treated using the method according to the first aspect of the invention. In the present invention,

"optional" refers to "comprise or not comprise" or "include or not include".

In a preferred embodiment, a part of the alkali source in the synthesis step preferably comes from the alkali liquor obtained in the wastewater recovery
5 and recycling step.

In a preferred embodiment, in the electrodialysis treatment of the second liquid phase with a bipolar membrane electrodialysis or a common electrodialysis-triple-chamber bipolar membrane electrodialysis, a part of the
10 water used in the synthesis step preferably comes from the desalted water obtained in the electrodialysis.

In a preferred embodiment, a part of the washing water in the separation and washing step preferably comes from the second liquid phase obtained in the
15 wastewater recovery and recycling step.

In a preferred embodiment, the ion exchange fluid in the ion exchange step is an acid liquor. A part of the acid liquor comes from the acid liquor obtained in the wastewater recovery and recycling step.
20

According to the method for the preparation of a molecular sieve according to the present invention, all of the second liquid phase can be used as the washing water in the separation and washing step, or subjected to a bipolar membrane electrodialysis treatment. Or a part of the second liquid phase can
25 be used as the washing water in the molecular sieve washing process and the rest of the second liquid phase is subjected to a bipolar membrane electrodialysis treatment.

According to the method for the preparation of a molecular sieve according to the present invention, the specific operation conditions of the synthesis step
30 and the crystallization step can be conventionally selected without any

specific limitation. The separation method adopted in the separation step can be a common solid-liquid separation method in the present field, such as filtration, without any specific limitation.

- 5 The method for the preparation of a molecular sieve according to the present invention not only improves the utilization rate of silicon but also achieves a higher water recovery and a comprehensive reuse of resources while significantly reducing the amount of wastewater and wastes produced in the preparation of the molecular sieve.

10

According to the fourth aspect of the invention, as shown in FIG.5, the present invention provides a molecular sieve preparation system, comprising a synthesis unit, a crystallization unit, a separation unit, a washing unit, a wastewater recovery and recycling unit, and an optional ion exchange unit.

15

The said synthesis unit is used for contacting the silicon source and the alkali source as well as the optional aluminum source and the optional titanium source in water for reaction. The synthesis unit generally comprises a reactor for contacting the silicon source and the alkali source as well as the optional
20 aluminum source in water for reaction. The said reactor can be a conventional reactor without any specific limitation.

The crystallization unit is used for crystallizing the mixture from the synthesis unit. The crystallization unit can adopt a conventional
25 crystallization tank.

The separation unit is used for carrying out a solid-liquid separation on the mixture obtained in the crystallization unit to produce a solid phase and a liquid phase, and delivering the liquid phase into the wastewater recovery and
30 recycling unit. The separation unit can adopt a conventional solid-liquid separation device, such as a plate and frame filter, belt filter.

The washing unit is used for washing the solid phase obtained in the separation unit to produce a molecular sieve and washing wastewater. The washing wastewater is delivered into the wastewater recovery and recycling unit. The separation unit and the washing unit can be carried out in different devices or share one device.

The ion exchange unit is used for contacting the molecular sieve obtained in the separation and washing unit with the ion exchange liquid for an ion exchange. An ion exchanged molecular sieve and an ion exchange waste liquid are thus produced. The ion exchange waste liquid is delivered into the wastewater recovery and recycling unit. The said ion exchange can be carried out in various common methods of ion exchange. For example, the molecular sieve can be mixed with the ion exchange liquid for an ion exchange. The kind of the ion exchange fluid can be selected according to the type of the desired molecular sieve. For example, an acid liquor can be contacted with a non-hydrogen molecular sieve to produce a hydrogen molecular sieve.

The wastewater recovery and recycling unit is used for treating the wastewater. As shown in FIG.5, the wastewater recovery and recycling unit includes a first precipitation reaction unit, a first solid-liquid separation unit, an optional second precipitation reaction unit, an optional second solid-liquid separation unit, and an optional electrodialysis unit.

The first precipitation reaction unit is used for contacting the wastewater with at least one acid or at least one alkali so that the silicon in the wastewater forms a colloid. Thus a mixture containing a colloid is obtained. The first precipitation reaction unit can adopt various common precipitation reactors. The methods and conditions for contacting the wastewater with at least one acid or at least one alkali so that the silicon in the wastewater forms a colloid have been described in details as above. No more details are provided herein.

The first solid-liquid separation unit is used for carrying out a solid-liquid separation on the mixture containing a colloid obtained in the first precipitation reaction unit to produce a silicon-containing solid phase and a first liquid phase. The said first solid-liquid separation unit may include a filter device, a centrifugal device or a combination of two or more separation devices, preferably comprising a filter device, to separate the mixture containing a colloid. The filter device can adopt a variety of common filter media, for example, one selected from a fabric, a porous material, a solid particle layer and a porous membrane or a combination of two or more of the above. The said porous membrane can be an organic membrane, an inorganic membrane or a combination of the above two. The said inorganic membrane can be a ceramic membrane and/or a metal membrane; the organic membrane can be a hollow fiber membrane. Preferably, a fabric is used as the filter medium. The said filter device can specifically be a plate and frame filter and/or a belt filter.

The second precipitation reaction unit is used for regulating the pH value of the first liquid phase to 8 or more and introducing CO_3^{2-} and/or Ca^{2+} into the first liquid phase so that at least a part of the metal elements in the first liquid phase can form a precipitate. The said second precipitation reaction unit can adopt a conventional sedimentation reactor without any special limitation. The method and conditions for adjusting the pH value of the first liquid phase to 8 or more and introducing CO_3^{2-} and/or Ca^{2+} to the first liquid phase so that at least a part of the metal elements in the first liquid phase can form a precipitate have been described in details as above. No more details are provided herein.

The second solid-liquid separation unit is used for carrying out a solid-liquid separation on the mixture obtained in the second precipitation reaction unit to produce a solid phase and a second liquid phase. The said second solid-liquid

separation unit may include a filter device, a centrifugal device or a combination of two or more separation devices, preferably comprising a filter device. The filter device can adopt a variety of common filter media, for example, one selected from a fabric, a porous material, a solid particle layer and a porous membrane or a combination of two or more of the above. The said porous membrane can be an organic membrane, an inorganic membrane or a combination of the above two. The said inorganic membrane can be a ceramic membrane and/or a metal membrane; the organic membrane can be a hollow fiber membrane. Preferably, a fabric is used as the filter medium.

10

The electrodialysis unit is used for an electrodialysis of at least a part of the second liquid phase to obtain an acid liquor and an alkali liquor. The electrodialyser used in the electrodialysis unit can be a conventional bipolar membrane electrodialyser or a combination of a common electrodialysis and a bipolar membrane electrodialysis. The said bipolar membrane electrodialyser can be a dual-chamber bipolar membrane electrodialyser or a triple-chamber bipolar membrane electrodialyser. The membrane stack of the dual-chamber bipolar membrane electrodialyser can be composed of a bipolar membrane and a cation exchange membrane or an anion exchange membrane. The membrane stack of the triple-chamber bipolar membrane electrodialyser can be composed of a bipolar membrane, a cation exchange membrane and an anion exchange membrane. The electrodialyser and the operation method thereof have been described in details as above in combination with FIG.1 to FIG.4. No more details are provided herein.

25

According to the molecular sieve preparation system of the present invention, preferably, the wastewater recovery and recycling unit further includes a solid phase material delivery pipeline for delivering the silicon-containing solid phase into the synthesis unit as a silicon source, thereby achieving a reuse of the silicon-containing solid phase as recovered.

30

According to the molecular sieve preparation system of the present invention, preferably, the wastewater recovery and recycling unit further includes a liquid phase material delivery pipeline for delivering at least a part of the second liquid phase into the washing unit as the washing water.

5

According to the molecular sieve preparation system of the present invention, preferably, the wastewater recovery and recycling unit further includes an acid liquid delivery pipeline for delivering at least a part of the acid liquor into the ion exchange unit as the ion exchange liquid.

10

According to the molecular sieve preparation system of the present invention, preferably, the wastewater recovery and recycling unit further includes an alkali liquid material delivery pipeline for delivering at least a part of the alkali liquor into the synthesis unit as an alkali source.

15

According to the molecular sieve preparation system of the present invention, when the electrodialysis unit uses a triple-chamber bipolar membrane electrodialyser or a conventional electrodialyser-triple-chamber bipolar membrane electrodialyser, the wastewater recovery and recycling unit further includes a desalted water delivery pipeline for delivering at least a part of the desalted water or at least a part of the further desalted water into the synthesis unit as water for synthesis.

20

This invention is explained in details as below in combination with examples, which however does not limit the protection scope of the present invention.

25

In the following examples and comparative examples, the contents of various elements in the silicon-containing wastewater and the treated water were determined in the method of inductively coupled plasma (ICP). The content of quaternary ammonium ions in the wastewater and the treated water was determined in the method of titration method. The relative crystallinity of the

30

molecular sieve was determined according to the method disclosed on pages 414-415 of 《*Analysis Method of Petrochemical Engineering* 》 (RIPP Test Method) (Yang Cuiding, Science Press, 1990).

5 Examples 1-7 are used to illustrate the invention.

Example 1

10 The silicon-containing wastewater treated in the present example is the primary wastewater of the washing wastewater produced in the preparation process of a hydrogen ZHP molecular sieve. The kinds of the elements therein and the contents thereof are listed in Table 1.

15 The bipolar membrane used in the present example is of type BP-1 purchased from Japanese ASTOM Company; the cation exchange membrane is a styrene-type homogeneous cation exchange membrane (with an ion exchange capacity of 2.51meq/g dry membrane and membrane surface resistance (25°C, 0.1mol/L NaCl aqueous solution, the same below) of 4.59Ω·cm²) purchased from Hebei Guangya Company; the anion exchange membrane is a
20 styrene-type homogeneous anion exchange membrane (with an ion exchange capacity of 2.45meq/g dry membrane and membrane surface resistance of 9.46Ω·cm²) purchased from Hebei Guangya Company.

25 The following flow process is adopted in the present example to treat the silicon-containing wastewater.

(1) Sulphuric acid (with a mass concentration of 3.5%) was added to the silicon-containing wastewater to regulate the pH value of the silicon-containing wastewater to 6.9 before stirring for reaction for 5 hours at
30 room temperature (25°C, the same below) to produce a mixture containing a silicon colloid.

(2) The mixture containing a silicon colloid obtained in step (1) was filtered in a plate and frame filter. The filtration residue was then washed until the pH of the filtrate was 6.5. A silicon-containing filtration residue (water content of 40 wt.%) and a filtrate were thus obtained. The silica content in the filtration residue was 95 wt.% based on the total amount of the silicon element in the silicon-containing wastewater. Thus it could be used as a silicon source in the synthesis process of the molecular sieve. The results of component analysis for the produced filtrate **a** are shown in Table 1.

(3) Sodium carbonate and calcium oxide were added to the filtrate obtained in step (2). At the same time, the pH value of the filtrate was regulated to 10.5 by adding an aqueous solution of sodium hydroxide (with a mass concentration of 40%) to the filtrate before stirring for reaction at room temperature for 2 hours. Therein, the addition amount of sodium carbonate was 15mmol/L and the addition amount of calcium oxide was 7mmol/L based on the total volume of filtrate obtained in step (2).

(4) The mixture obtained in step (3) was filtered by a membrane (with the membrane pore size being 50nm) to produce a filtration residue and a filtrate. The results of component analysis for the produced filtrate **b** are shown in Table 2.

(5) The filtrate obtained in step (4) was delivered into the triple-chamber bipolar membrane electrodialyzer as shown in FIG.3 for a bipolar membrane electrodialysis (the employed electrode liquid was a Na_2SO_4 aqueous solution of 3 wt.%) to produce an acid liquor, an alkali liquor and desalted water. Therein, in the bipolar membrane electrodialysis, the voltage applied to each membrane unit was regulated to 2.5V. The electrodialysis lasted 5 hours at a temperature of 35°C. The constitution and contents of the elements in the produced desalted water are listed in Table 3. The desalted

water can be used as the water for a molecular sieve synthesis. The produced acid liquor having a concentration of 2.5 wt.% can be used as an ion exchange liquid for an ion exchange with the molecular sieve to produce a hydrogen molecular sieve. The produced alkali liquor can be concentrated into an alkali liquor having a concentration of 10wt.% which can be used as an alkali source for a molecular sieve synthesis. Table 4 show the structural parameters of the Na molecular sieve prepared using fresh water and a fresh alkali liquor of the control group and the Na molecular sieve prepared using the recovered desalted water, the recovered silicon source and the recovered alkali source of Example 1. FIG.6 is the SEM photo of the Na molecular sieve prepared in the control group. FIG.7 is the SEM photo of the Na molecular sieve prepared using the recovered desalted water, the recovered silicon source and the recovered alkali source.

The results of Table 4, FIG.6 and FIG.7 demonstrate that there is no significant difference in the structure and appearance between the Na molecular sieve prepared using the recovered desalted water, the recovered silicon source and the recovered alkali source in Example 1 and the molecular sieve prepared using the corresponding fresh raw materials. The above indicates that the treatment of wastewater from the preparation of a molecular sieve using the method of the present invention can effectively recover and recycle various useful materials.

Comparative Example 1

A method identical to the method in Example 1 was adopted for treating the silicon-containing wastewater. The difference lies in that sulphuric acid was replaced with sulfated aluminum sulfate in step (1) so that the pH value of the silicon-containing wastewater was regulated to 6.9 before reacting for 2 hours at room temperature. A mixture containing a silicon colloid was thus produced. The results of the component analysis of the filtrate **a** are shown in Table 1.

Comparative Example 2

A method identical to the method in Example 1 was adopted for treating the silicon-containing wastewater. The difference lies in that the membrane
5 filtration was carried out directly in step (3) without an addition of sodium carbonate, calcium oxide and sodium hydroxide to produce a filtration residue and filtrate **b**. The results of component analysis for the produced filtrate **b** are shown in Table 2.

10 Example 2

A method identical to the method in Example 1 was adopted for treating the silicon-containing wastewater. The difference lies in that sulphuric acid (with a mass concentration of 3.5%) was added to the silicon-containing
15 wastewater in step (1) to regulate the pH value of the silicon-containing wastewater to 4.8 before stirring for reaction for 5 hours at room temperature (25°C, the same below). A mixture containing a silicon colloid was thus obtained. The filtration residue having a silica content of 96 wt.% produced in step (2) could be used as the silicon source in the molecular sieve synthesis
20 process. The results of the component analysis of the filtrate **a** are shown in Table 1.

Comparative Example 3

25 A method identical to the method in Example 2 was adopted for treating the silicon-containing wastewater. The difference lies in that sulphuric acid was replaced with sulfated aluminum sulfate in step (1) so that the pH value of the silicon-containing wastewater was regulated to 4.8 before reacting for 5 hours at room temperature. A mixture containing a silicon colloid was thus produced.
30 The results of the component analysis of the filtrate **a** are shown in Table 1.

Example 3

A method identical to the method in Example 1 was adopted for treating the silicon-containing wastewater. The difference lies in that sulphuric acid (with a mass concentration of 3.5%) was added to the silicon-containing wastewater in step (1) to regulate the pH value of the silicon-containing wastewater to 8.8 before stirring for reaction for 5 hours at room temperature (25°C, the same below). A mixture containing a silicon colloid was thus obtained. The filtration residue having a silica content of 93 wt.% produced in step (2) could be used as the silicon source in the molecular sieve synthesis process. The results of the component analysis of the filtrate **a** are shown in Table 1.

Table 1 Constitution of the silicon-containing wastewater and filtrate a

	Na, mg/L	Ca, mg/L	Si, mg/L	Mg, mg/L	Al, mg/L
Silicon-containing wastewater	7200	33.1	10300	5.9	3.0
Example 1(filtrate a)	6187	21.8	120	4.2	0.8
Comparative Example 1(filtrate a)	4777	26.0	286	6.5	38.9
Example 2(filtrate a)	5743	38.8	94	8.2	0.8
Comparative Example 2(filtrate a)	5309	33.5	922	8.7	68.4
Example 3(filtrate a)	4981	23.8	226	5.9	1.0

Table 2 Constitution of filtrate b

	Na, mg/L	Ca, mg/L	Si, mg/L	Mg, mg/L	Al, mg/L
Example 1 (filtrate b)	7510	2.7	34	<1.0	<1.0
Comparative Example 2 (filtrate b)	6135	20.9	117	4.2	0.7

5

Table 3 Constitution of the silicon-containing wastewater and the produced desalted water

	Na, mg/L	Ca, mg/L	Si, mg/L	Mg, mg/L	Al, mg/L
Silicon-containing wastewater	7200	33.1	10300	5.9	3.0

Example 1 (desalted water)	510	3.2	31	<1.0	<1.0
Example 2 (desalted water)	500	3.0	28	<1.0	<1.0
Example 3 (desalted water)	550	3.5	34	<1.0	<1.0

Table 4 Structural parameters of the Na molecular sieve

	Relative crystallinity, %	SiO ₂ , wt. %	Al ₂ O ₃ , wt. %
Control group	110.1	95.8	3.62
Example 1	110.9	96.1	3.68

5 As can be seen from the results of Table 1, the content of silicon in the filtrate obtained in Comparative Example 1 and Comparative Example 3 is still relatively high, which results in a low recovery rate of silicon and an extra introduction of aluminum. Ca²⁺ and CO₃²⁻ are not introduced in Comparative Example 2, and the use of the membrane filtration alone does not achieve the
10 effect of a deep desilication. Moreover, when the content of silicon and aluminum is high in the filtrate, silicon and aluminum can easily scale on the surface of the ion exchange membrane and/or the bipolar membrane of electrodialysis, which has an adverse effect on the electrodialysis effect, and also significantly shortens the service life of the ion exchange membrane
15 and/or the bipolar membrane. The method of the present invention can significantly improve the recovery rate of silicon.

Example 4

20 The silicon-containing wastewater treated in the present example is a mixture of the washing waste water produced in the preparation of a hydrogen ZHP

molecular sieve and the ion exchange waste liquid produced in ion exchange process. The kinds of the elements therein and the contents thereof are listed in Table 5.

5 A method identical to the method in Example 1 was adopted for treating the silicon-containing wastewater. The difference lies in that the common electrodialysis-triple-chamber bipolar membrane electrodialysis device as shown in FIG.4 was adopted in step (5) for the treatment (the electrode liquid used being a Na_2SO_4 aqueous solution of 3 wt.%). The electrodialysis lasted 6
10 hours. Moreover, the cation exchange membrane used herein was a styrene-type homogeneous cation exchange membrane (with an ion exchange capacity of 2.5meq/g dry membrane and a membrane surface resistance of $8\Omega\cdot\text{cm}^2$) purchased from Beijing Tingrun Membrane Technology Development Co., LTD. The anion exchange membrane used herein was a
15 homogeneous anion exchange membrane (with an ion exchange capacity of 2.5meq/g dry membrane and a membrane surface resistance of $2.36\Omega\cdot\text{cm}^2$) purchased from Beijing Tingrun Membrane Technology Development Co., LTD. The voltage applied to each membrane unit was regulated to 2V in the common electrodialysis; the voltage applied to each membrane unit was
20 regulated to 3V in the triple-chamber bipolar membrane electrodialysis. The temperature in both the common electrodialyzer and the bipolar membrane electrodialyzer was controlled as 35 °C. The constitution of the elements in the desalted water produced from the common electrodialysis and the bipolar membrane electrodialysis and the contents thereof are listed in Table 5.

25

Table 5 Constitution of the silicon-containing wastewater and the produced desalted water

	Na, mg/L	Ca, mg/L	Si, mg/L	Mg, mg/L	Al, mg/L
Silicon-containing wastewater	2342	38.1	656	2.5	5.8
Example 4	56	2.3	27	<1.0	<1.0

(desalted water)					
------------------	--	--	--	--	--

From the results of table 5, it can be seen that the use of the composite process of the common electrodialysis-bipolar membrane electrodialysis on the one hand has better effects in improving the concentration and in
5 desalination with a lower content of impurities in the desalted water, which is advantageous in reuse. On the other hand, the common electrodialysis can protect the bipolar membrane electrodialysis. In addition to an impurity removal, the pH value in the common electrodialysis changes less, and the silicon and aluminum remained in the filtrate do not settle due to the change
10 of pH value, which is beneficial to the stable operation of electrodialysis.

Example 5

The silicon-containing wastewater treated in the present example is the
15 washing wastewater produced in the preparation process of a CDY molecular sieve. The kinds of the elements therein and the contents thereof are listed in Table 6.

The bipolar membrane used in the present example is of type BP-1 purchased
20 from Japanese ASTOM Company; the cation exchange membrane is a styrene-type homogeneous cation exchange membrane purchased from Hebei Guangya Company (the same as Example 1); the anion exchange membrane is a styrene-type homogeneous anion exchange membrane purchased from Hebei Guangya Company (the same as Example 1).

25

The following flow process was adopted in the present example to treat the silicon-containing wastewater.

(1) An aqueous solution of sodium hydroxide (with a mass concentration of
30 3.5%) was added to the silicon-containing wastewater to regulate the pH

value of the silicon-containing wastewater to 6.5 before stirring for reaction for 3 hours at a temperature of 50°C to produce a mixture containing an aluminosilica colloid.

5 (2) The mixture containing a silicon colloid produced in step (1) was delivered to a plate and frame filter for a filtration. The filtration residue was washed to produce a silicon-containing filtration residue (with water content of 36wt.%) and a filtrate. Therein the purity of silica in the filtration residue was 97wt.% based on the total amount of the silicon element in the
10 silicon-containing wastewater. Thus it could be used as the silicon source in the synthesis process of the molecular sieve. The results of component analysis for the filtrate a are shown in Table 6.

(3) Sodium carbonate was added to the filtrate obtained in step (2). At the
15 same time, the pH value of the filtrate was regulated to 10 by adding ammonia water to the filtrate before stirring for reaction for 3 hours at room temperature. Therein, the addition amount of sodium carbonate was 15mmol/L based on the total volume of filtrate obtained in step (2).

20 (4) The mixture obtained in step (3) was filtered by a membrane to produce a filtration residue and a filtrate b.

(5) The filtrate obtained in step (4) was delivered into the triple-chamber bipolar membrane electrodialyzer as shown in FIG.3 for treatment (the
25 employed electrode liquid being a Na₂SO₄ aqueous solution of 3 wt.%) to produce an acid liquor, an alkali liquor and desalted water. Therein the voltage applied to each membrane unit was adjusted to 3V. The electrodialysis lasted 2 hours at a temperature of 35°C. The constitution and contents of the elements in the produced desalted water are listed in Table 7.
30 The desalted water can be used as the water for a molecular sieve synthesis. The produced acid liquor having a concentration of 3.14 wt.% can be used as

the ion exchange liquid for an ion exchange with the molecular sieve to produce a hydrogen molecular sieve. The produced alkali liquor can be concentrated into an alkali liquor having a concentration of 10wt.% which can be used as the alkali source for a molecular sieve synthesis.

5

Table 6 Constitution of the silicon-containing wastewater and filtrate a

	Ca, mg/L	Mg, mg/L	Si, mg/L	Al, mg/L	Fe, mg/L	RE, mg/L	Na, mg/L
Silicon-containing wastewater	20	8.2	89.1	18.9	<0.1	133	5476
Example 5 (filtrate a)	19.9	8.2	5.8	<0.1	<0.1	102	5139

Table 7 Constitution of the silicon-containing wastewater and the
10 produced desalted water

	Ca, mg/L	Mg, mg/L	Si, mg/L	Al, mg/L	Fe, mg/L	RE, mg/L	Na, mg/L
Silicon-containing wastewater	20	8.2	89.1	18.9	<0.1	133	5476
Example 5 (desalted water)	5.3	<0.1	2.7	<0.1	<0.1	<1.0	259

Example 6

- 15 A method identical to the method in Example 5 was adopted for treating the silicon-containing wastewater. The difference lies in that the pH value was regulated to 5.5 in step (1) before stirring for reaction for 3 hours at a temperature of 50°C. A mixture containing an aluminosilica colloid was thus obtained. Filtrate a was obtained by filtration. The component analysis of the

filtrate is found in Table 8. The purity of silica in the filtration residue was 95wt.%. Thus it could be used as the silicon source in the synthesis process of a molecular sieve.

5 Table 8 Constitution of the silicon-containing wastewater and filtrate a

	Ca, mg/L	Mg, mg/L	Si, mg/L	Al, mg/L	Fe, mg/L	RE, mg/L	Na, mg/L
Silicon-containing wastewater	20	8.2	89.1	18.9	<0.1	133	5476
Example 6 (filtrate a)	16.8	6.7	35.9	36.2	<0.1	132	5031

The results of Examples 1 to 6 demonstrate that the use of the method of the present invention for treating the silicon-containing wastewater produced in the preparation of the molecular sieve can achieve a relatively higher silicon recovery rate and water recovery rate. Basically no wastewater and a very low amount of solid wastes are discharged, as realizes the reasonable reuse of the wastewater.

15 Example 7

The silicon-containing wastewater treated in the present example is the exchange wastewater produced from the preparation of an FCC catalyst. The kinds of the elements therein and the contents thereof are listed in Table 9.

20

The method as depicted in FIG.4 was used in the present example for electrodialysis. The cation exchange membrane used herein is a styrene-type homogeneous cation exchange membrane purchased from Hebei Guangya Company (the same as Example 1); the anion exchange membrane used
25 herein is a homogeneous styrene-type anion exchange membrane purchased

from Hebei Guangya Company (the same as Example 1). The bipolar membrane is a bipolar membrane of type BP-1 purchased from Japanese Tokuyama Company.

5 The following process is used in the present example for treating the wastewater.

(1) The pH value of the wastewater was regulated to 5.5~6.0 by adding a NaOH solution (the concentration of NaOH being 3wt.%) into the
10 silicon-containing wastewater. The reaction lasted 5 hours at 80°C under stirring. A mixture containing a silicon colloid was thus obtained.

(2) The mixture containing a silicon colloid obtained in step (1) was delivered into a plate and frame filter for filtration, from which a silicon-containing
15 filtration residue (with water content of 80wt.%) and filtrate a were produced. Therein the content of silicon oxide and alumina in the filtration residue was greater than 95 wt.%. Thus it could be used as the silicon source in the synthesis process of a molecular sieve. The results of component analysis for the produced filtrate a are shown in Table 9.

20

(3) After calcium oxide was added into the filtrate obtained in step (2) and evenly mixed, sodium carbonate was added. At the same time, the pH value of the filtrate was regulated to 10.5 by adding an aqueous solution of sodium hydroxide (with a mass concentration of 40%) into the filtrate. The reaction
25 lasted 2 hours at room temperature under stirring. Therein, the addition amount of calcium oxide was 7mmol/L and the addition amount of sodium carbonate was 15mmol/L based on the total volume of filtrate obtained in step (2).

30 (4) The mixture obtained in step (3) was filtered by a membrane (with the membrane pore size being 50nm) to produce a filtration residue and filtrate b.

The results of component analysis for the filtrate b are shown in Table 9.

(5) The filtrate obtained in step (4) was delivered into the common electrodialysis-triple-chamber bipolar membrane electrodialysis device as shown in FIG.4 for treatment (The employed electrode liquid being a Na_2SO_4 aqueous solution of 5wt.%). The electrodialysis lasted 60 minutes. Therein, the voltage applied to each membrane unit was regulated to 1V in the common electrodialysis; the voltage applied to each membrane unit was regulated to 2.5V in the triple-chamber bipolar membrane electrodialysis. The temperature in both the common electrodialyzer and the bipolar membrane electrodialyzer was controlled as 35 °C. The constitution of the elements in the desalted water produced from the common electrodialysis and the contents thereof are listed in Table 10.

Table 9 Constitution of the silicon-containing wastewater, filtrate a and filtrate b

	Ca, mg/L	Mg, mg/L	Si, mg/L	Al, mg/L	Fe, mg/L	RE, mg/L	Na, mg/L
Silicon-containing wastewater	20	8.2	89.1	18.9	<0.1	133	5076
Example 7 (filtrate a)	19.9	8.2	15.8	<0.1	<0.1	102	5439
Example 7 (filtrate b)	4.5	0.2	2.8	<0.1	<0.1	<0.1	6239

Table 10 Constitution of the silicon-containing wastewater and the produced desalted water

	Ca, mg/L	Mg, mg/L	Si, mg/L	Al, mg/L	Fe, mg/L	RE, mg/L	Na, mg/L
Silicon-containing wastewater	20	8.2	89.1	18.9	<0.1	133	5476

Example 7 (desalted water)	5.3	<0.1	2.7	<0.1	<0.1	<1.0	259
-------------------------------	-----	------	-----	------	------	------	-----

The results of Example 7 demonstrate that the use of the method of the present invention for treating the silicon-containing wastewater produced in the preparation of a catalyst can achieve a relatively higher silicon recovery rate and water recovery rate. Moreover, basically no wastewater and a very low amount of solid wastes are discharged, as realizes a reasonable reuse of the wastewater.

Claims

1. A treatment method for a silicon-containing wastewater, wherein the
5 silicon-containing wastewater comes from the preparation of a molecular
sieve or a catalyst, comprising the following steps:

Step (1): the silicon-containing wastewater is contacted with at least one acid
or at least one alkali, so that at least a part of the silicon elements in the
10 silicon-containing wastewater form a colloid, and a mixture containing a
colloid is obtained;

Steps (2): the mixture containing a colloid as obtained in step (1) is subjected
to a solid-liquid separation to produce a silicon-containing solid phase and a
15 first liquid phase;

Step (3): the pH value of the first liquid phase is regulated to 8 or more, and
 CO_3^{2-} and/or Ca^{2+} are introduced into the first liquid phase so that at least a
part of the metal elements in the first liquid phase form a precipitate;
20

Steps (4): the mixture as obtained by step (3) is subjected to a solid-liquid
separation to produce a solid phase and a second liquid phase;

Step (5): at least a part of the second liquid phase is subjected to an
25 electrodialysis treatment to produce an acid liquor, an alkali liquor and/or
desalted water.

2. The method according to Claim 1, wherein, in step (1), the amount of the
acid or the alkali keeps the pH value of the silicon-containing wastewater
30 within the range of 2-9, preferably within the range of 3-9, more preferably
within the range of 3-6.9;

preferably, the silicon-containing wastewater is contacted with at least one acid, wherein the amount of said acid keeps the pH value of the silicon-containing wastewater within the range of 4-7.5, preferably within the
5 range of 5-6.9.

3. The method according to Claim 1 or Claim 2, wherein, in Step (1), the acid is selected from the group consisting of hydrochloric acid, sulfuric acid, nitric acid and phosphoric acid, preferably is sulfuric acid and/or hydrochloric acid;
10 or

in Step (1), the alkali is selected from alkali hydroxide and ammonia water, preferably sodium hydroxide, potassium hydroxide and ammonia water.

15 4. The method according to Claim 1, wherein the amount of CO_3^{2-} introduced into the first liquid phase is 0.1-20mmol/L, preferably 1-15mmol/L, in Step (3).

5. The method according to Claim 1 or Claim 4, wherein the method for
20 introducing CO_3^{2-} into the first liquid phase comprises adding a water-soluble carbonate to the first liquid phase, preferably adding one or more selected from alkali carbonate and ammonium carbonate into the first liquid phase.

6. The method according to any one of Claim 1 to Claim 5, wherein the
25 content of Si in the first liquid phase is 50mg/L or more, preferably 80-150mg/L, and the method further comprises introducing Ca^{2+} into the first liquid phase

7. The method according to Claim 1 or Claim 6, wherein the amount of Ca^{2+}
30 introduced into the first liquid phase is 0.1-10mmol/L, preferably 1-5mmol/L.

8. The method according to any one of Claim 1 and Claim 4 to Claim 7, wherein the method for introducing Ca^{2+} into the first liquid phase comprises adding one or more of calcium sulfate, calcium chloride, calcium hydroxide and calcium oxide into the first liquid phase.

5

9. The method according to Claim 1, wherein the pH value of the first liquid phase is regulated to 8-11 in Step (3).

10. The method according to Claim 1 or Claim 9, wherein the pH value of the first liquid phase is regulated by adding alkali into the first liquid phase in Step (3), and the said alkali is one or more selected from the group consisting of calcium hydroxide, sodium hydroxide and ammonia water.

11. The method according to Claim 1, wherein the electrodialysis at least comprises a bipolar membrane electrodialysis in Step (5);

preferably, the electrodialysis at least comprises a triple-chamber bipolar membrane electrodialysis so that the second liquid phase is separated into an acid liquor, an alkali liquor and desalted water through electrodialysis;

20

more preferably, the said electrodialysis is a series connection of a common electrodialysis and a bipolar membrane electrodialysis; the said second liquid phase is subjected to electrodialysis in the common electrodialysis to produce a concentrate and a first desalted water; the said concentrate enters the bipolar membrane electrodialysis for a bipolar membrane electrodialysis, from which an acid liquor, an alkali liquor and a second desalted water are produced.

25

12. The method according to any one of Claim 1 to Claim 11, wherein the silicon-containing wastewater is one of the liquid phase produced in the separation step of the preparation of a molecular sieve, the waste liquid

30

produced in the washing step and the ion exchange waste liquid produced in the ion exchange step in the preparation of a molecular sieve or the mixtures of two or more of the above waste liquids

5 13. The method according to any one of Claim 1 to Claim 12, wherein the content of silicon element in the silicon-containing wastewater is 10-15000mg/L, preferably 50mg/L or more, more preferably 80mg/L or more, and even preferably 100mg/L or more.

10 14. The method according to any one of Claim 1 to Claim 13, wherein the said molecular sieve is one or more selected from the group consisting of a Y molecular sieve, an X molecular sieve, an A molecular sieve, an MCM molecular sieve, a ZSM molecular sieve, a mordenite molecular sieve, a beta molecular sieve and a titanium silicalite molecular sieve.

15

15. The method according to any one of Claim 1 to Claim 14, wherein the ion exchange membrane used in the electrodialysis is a styrene-type homogeneous ion exchange membrane.

20 16. A method for the utilization of a silicon-containing wastewater, wherein the silicon-containing wastewater comes from the preparation of a molecular sieve, and the method comprises the treatment of the silicon-containing wastewater according to the method of any one of Claim 1 to Claim 15.

25 wherein the silicon-containing solid phase obtained in step (2) is recycled as the raw material for a molecular sieve synthesis;

at least a part of the second liquid phase obtained in step (4) is recycled as the washing water in the washing process of the molecular sieve;

30

the acid liquor obtained in step (5) is recycled as the ion exchange liquid in

the ion exchange process of the molecular sieve; and the alkali liquor obtained in step (5) is recycled as the alkali source in the molecular sieve synthesis.

- 5 17. The method according to Claim 16, wherein step (5) further produces desalted water which is recycled as the washing water in the molecular sieve synthesis and/or the washing process of the molecular sieve.

- 10 18. A method for the preparation of a molecular sieve, comprising a synthesis step, a crystallization step, a separation step, a washing step, a wastewater recovery and recycling step, and an optional ion exchange step.

in the synthesis step, a silicon source and an alkali source as well as an optional aluminum source and an optional titanium source are contacted in
15 water for reaction;

in the crystallization step, a mixture obtained from the synthesis step is crystallized;

- 20 in the separation step, a mixture obtained from the crystallization step is subjected to a solid-liquid separation to produce a solid phase and a liquid phase;

in the washing step, the solid phase obtained from the separation step is
25 washed with the washing water to obtain a molecular sieve and washing wastewater;

in the ion exchange step, the molecular sieve is contacted with an ion exchange liquid for carrying out the solid-liquid separation after an ion
30 exchange to produce an ion exchanged molecular sieve and an ion exchange waste liquid;

in the wastewater recovery and recycling step, wastewater is collected and treated using the method according to the method of any one of Claim 1 to Claim 15, and the wastewater is the liquid phase in the separation step, the washing wastewater in the washing step, and the ion exchange waste liquid in the ion exchange step.

19. The method according to Claim 18, wherein a part of the silicon source in the synthesis step comes from the silicon-containing solid phase produced in the wastewater recovery and recycling step.

20. The method according to Claim 18 or Claim 19, wherein a part of the alkali source in the synthesis step comes from the alkali liquor produced in the wastewater recovery and recycling step.

21. The method according to one of Claim 18 to Claim 20, wherein a part of the washing water in the separation and washing step comes from the second liquid phase and/or the desalted water produced in the wastewater recovery and recycling step.

22. The method according to any one of Claim 18 to Claim 21, wherein the ion exchange liquid in the ion exchange step is an acid liquor, and a part of the said acid liquor comes from the acid liquor produced in the wastewater recovery and recycling step.

23. The method according to any one of Claim 18 to Claim 22, wherein at least a part of the water used in the synthesis step comes from the desalted water produced in the wastewater recovery and recycling step.

24. A molecular sieve preparation system, comprising a synthesis unit, a crystallization unit, a separation unit, a washing unit, a wastewater recovery

and recycling unit, and an optional ion exchange unit, wherein

the synthesis unit is used for contacting a silicon source and an alkali source as well as an optional aluminum source and an optional titanium source in
5 water for reaction;

the crystallization unit is used for crystallizing a mixture from the synthesis unit;

10 the separation unit is used for carrying out a solid-liquid separation on the mixture obtained from the crystallization unit to produce a liquid phase and a solid phase; and the produced liquid phase is delivered into the wastewater recovery and recycling unit as wastewater;

15 in the washing unit, the solid phase obtained from the separation unit is washed with a washing water to produce a molecular sieve and washing wastewater; and the said washing wastewater is delivered into the wastewater recovery and recycling unit as wastewater;

20 the ion exchange unit is used for contacting the molecular sieve obtained from the washing unit with the ion exchange liquid to carry out an ion exchange, from which an ion exchanged molecular sieve and an ion exchange waste liquid are obtained; and the ion exchange waste liquid is delivered into the wastewater recovery and recycling unit;

25

the wastewater recovery and recycling unit is used for treating wastewater; the said wastewater recovery and recycling unit includes a first precipitation reaction unit, a first solid-liquid separation unit, a second precipitation reaction unit, a second solid-liquid separation unit, and an electrodialysis

30 unit;

the first precipitation reaction unit is used for contacting the wastewater with at least one acid or at least one alkali so that the silicon in the wastewater forms a colloid; and a mixture containing a colloid is thus obtained;

- 5 the first solid-liquid separation unit is used for carrying out a solid-liquid separation on the mixture containing a colloid obtained from the first precipitation reaction unit; and a silicon-containing solid phase and a first liquid phase are thus obtained;
- 10 the second precipitation reaction unit is used for regulating the pH value of the first liquid phase to 8 or more and introducing CO_3^{2-} and/or Ca^{2+} into the first liquid phase so that at least a part of the metal elements in the first liquid phase form a precipitate;
- 15 the second solid-liquid separation unit is used for carrying out a solid-liquid separation on the mixture obtained from the second precipitation reaction unit to obtain a solid phase and a second liquid phase;

- the electrodialysis unit is used to carrying out an electrodialysis, preferably a
- 20 bipolar membrane electrodialysis, more preferably a treatment of a common electrodialysis and a bipolar membrane electrodialysis in series, on at least a part of the second liquid phase to produce an acid liquor, an alkali liquor and/or desalted water.

- 25 25. The system according to Claim 24, wherein the wastewater recovery and recycling unit further includes one of the following pipelines or combinations of two or more of the following pipelines:

- a solid phase material delivery pipeline for delivering the silicon-containing
- 30 solid phase into the synthesis unit as a silicon source;

a liquid phase material delivery pipeline for delivering at least a part of the second liquid phase into the washing unit as the washing water;

5 an acid liquid delivery pipeline for delivering at least a part of the acid liquor into the ion exchange unit as the ion exchange liquid;

an alkali liquid material delivery pipeline for delivering at least a part of the alkali liquor into the synthesis unit as an alkali source;

10 a desalted water delivery pipeline for delivering at least a part of the desalted water into the synthesis unit as water for synthesis.