

FORMING MOLD FOR MAKING POLYVINYL CHLORIDE FOAMED WOOD-LIKE SLATS

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

The present invention relates to slat forming technology and more particularly, to a forming mold for making polyvinyl chloride foamed wood-like slats.

2. Description of the Related Art

10 In the past, curtain slats were mainly made of aluminum or iron flakes after being processed into curved sections, and then painted on the surface. However, such conventional slats have the disadvantages of high raw material costs, heavy weight of the finished product, and easy absorption of heat, resulting in poor thermal insulation effects. In order to improve the above problems, some developers have
15 developed slats made of plastic raw materials such as polyvinyl chloride foam materials to achieve the goals of cost reduction, light weight, and good thermal insulation. However, the forming molds currently used for making PVC foamed slats mainly use a one-in-one-out design, that is, there is only one inlet and one outlet, which will cause the problem of low production efficiency.

20 SUMMARY OF THE INVENTION

The present invention has been accomplished under the circumstances in view. It is the main object of the present invention to provide a forming mold for making polyvinyl chloride foamed wood-like slats, which can effectively improve production efficiency.

25 To achieve this and other objects of the present invention, a forming mold

for making polyvinyl chloride foamed wood-like slats comprises an inlet, an outlet, and two main flow passages symmetrically arranged with respect to a central axis. The main flow passages each have an inlet section and an outlet section. The inlet section of each main flow passage is connected to the inlet. The extension direction
5 of the inlet section of each main flow passage respectively defines with the central axis a first included angle therebetween. The sum of the angles of the two first included angles ranges from 44.2 to 48.8 degrees. The outlet sections of the main flow passages each have one end respectively connected to one respective outlet. Furthermore, the width of each main flow passage gradually increases from the inlet
10 toward the outlets, and the height of each main flow passage gradually reduces from the inlet toward the outlets.

As can be known from the above, the forming mold of the present invention uses a one-in two-out design and is matched with the symmetrical configuration of the two main flow passages to effectively improve production
15 efficiency and to make the manufactured product have the characteristics of stable quality.

Preferably, the height of the inlet section of each main flow passage is consistent from beginning to end.

Preferably, the width of the outlet section of each main flow passage is
20 consistent from beginning to end, the extending direction of the outlet section of each main flow passage is parallel to the central axis, and the height of the outlet section of each main flow passage is consistent from beginning to end.

Preferably, the two main flow passages each comprise a front connection section connected to the associating inlet section, a rear connection section
25 connected to the associating outlet section, and a middle connection section

connected between the front connection section and the rear connection section. The height of the front connection section of each main flow passages gradually reduces from the associating inlet section toward the associating middle connection section, and the width of the front connection sections is consistent from beginning to end.

5 The extension direction of each front connection section respectively defines with the central axis a second included angle therebetween, and the sum of the angles of the two second included angles ranges from 36.9 to 61.9 degrees. The height of the middle connection section of each main flow passages gradually reduces from the associating front connection section toward the associating rear connection section,

10 and the width of the middle connection section of each main flow passage gradually increases from the associating front connection section toward the associating rear connection section. A third included angle is respectively defined between the extension direction of the inner wall of each of the two middle connection sections and the central axis, and the sum of the angles of the two third included angles

15 ranges from 5.7 to 8.6 degrees. A fourth included angle is respectively defined between the extension direction of the outer wall of each of the two middle connection sections and the central axis, and the sum of the angles of the two fourth included angles ranges from 28.1 to 41.1 degrees. The height of the rear connection section of each main flow passages gradually reduces from the associating middle

20 connection section toward the associating outlet section, and the width of the rear connection section of each main flow passages is consistent from beginning to end.

With the above technical characteristics, after the polyvinyl chloride foam material is injected into the inlet, the polyvinyl chloride foam material can quickly and stably pass through the main flow passages, and then the shape of the product is formed

25 from the outlet.

Preferably, the forming mold further comprises a sub flow passage and two branch flow passages. The sub flow passage is located between the rear connection sections of the two main flow passages and extends straight down from the top surface of the forming mold. The two branch flow passages each have one
5 end thereof respectively communicating with the rear connection sections of the two main flow passages, and an opposite end thereof commonly communicating with the bottom end of the sub flow passage. With the above technical characteristics, a skin material is injected into the sub flow passage, and then the skin material flows from the sub flow passage through the two branch flow passages to the rear connection
10 sections of the two main flow passages respectively, and the skin material is then mixed with the polyvinyl chloride foam material passing therethrough to form the skin layer of the product.

The detailed structure, characteristics, assembly or use method of the forming mold for making polyvinyl chloride foamed wood-like slats provided by the
15 present invention will be described in the detailed description of the subsequent preferred embodiment. However, those with ordinary skill in the art of the present invention should be able to understand that the detailed descriptions and the specific preferred embodiment listed in the implementation of the present invention are only used to illustrate the present invention and are not intended to limit the scope of the
20 patent application of the present invention.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a top view of a forming mold for making polyvinyl chloride foamed wood-like slats in accordance with the present invention.

FIG. 2 is a side view of the forming mold for making polyvinyl chloride
25 foamed wood-like slats in accordance with the present invention.

FIG. 3 is a top view of the first die block and the second die block of the forming mold in accordance with the present invention.

FIG. 4 is an end view of the second die block of the forming mold in accordance with the present invention.

5 FIG. 5 is a sectional side view of the first die block and the second die block of the forming mold in accordance with the present invention.

FIG. 6 is a top view of the third die block of the forming mold in accordance with the present invention.

FIG. 7 is an end view of the third die block of the forming mold in
10 accordance with the present invention.

FIG. 8 is a sectional side view of the third die block of the forming mold in accordance with the present invention.

FIG. 9 is a top view of the fourth die block of the forming mold in accordance with the present invention.

15 FIG. 10 is an end view of the fourth die block of the forming mold in accordance with the present invention.

FIG. 11 is a sectional side view of the fourth die block of the forming mold in accordance with the present invention.

FIG. 12 is a top view of the fifth die block of the forming mold in
20 accordance with the present invention.

FIG. 13 is an end view of the fifth die block of the forming mold in accordance with the present invention.

FIG. 14 is a sectional side view of the fifth die block of the forming mold in accordance with the present invention.

25 FIG. 15 is a top view of the sixth die block of the forming mold in

accordance with the present invention.

FIG. 16 is an end view of the sixth die block of the forming mold in accordance with the present invention.

FIG. 17 is a sectional side view of the sixth die block of the forming mold
5 in accordance with the present invention.

DETAILED DESCRIPTION OF THE INVENTION

The applicant first explains here, in the entire specification, including the preferred embodiment and the drawings, the terms related to directionality are based on the directions in the drawings. Second, in the embodiment and the drawings to be
10 described below, the same component numbers represent the same or similar components or their structural features.

Referring to FIG. 1 and FIG. 2, a forming mold **10** has one inlet **12** and two outlets **14**, wherein the inlet **12** has an opening angle α between 105 and 115 degrees (see FIG. 3). The forming mold **10** of the present invention further has two
15 main flow passages **16**, and the two main flow passages **16** are symmetrically arranged with respect to a central axis **A**. The height of the two main flow passages **16** gradually decreases from the inlet **12** toward the outlets **14** (see FIG. 2). The width of the two main flow passages **16** gradually increases from the inlet **12** toward the outlets **14** (see FIG. 1).

20 Furthermore, the two main flow passages **16** each have an inlet section **18**. The inlet sections **18** of the two main flow passages **16** each have one end thereof commonly connected to the inlet **12**, as shown in FIG. 4 and FIG. 5. The cross-sectional shape of the two inlet sections **18** is trapezoidal. The height **H1a** of the inner wall of the two inlet sections **18** is 20mm, and the height **H1b** of the outer
25 wall of the two inlet sections **18** is 14.01mm, both of which are consistent from

beginning to end. As for the width **W1** of the two inlet sections **18** is also consistent from beginning to end (**W1** is 42mm in this embodiment). In addition, as shown in FIG. 3, the length direction of the two inlet sections **18** and the central axis **A** respectively have a first included angle **θ1**, and the sum of the angles of the two first included angles **θ1** ranges from 44.2-48.8 degrees (The smallest sum of angles is 44.2 degrees, and the largest sum of angles is 48.8 degrees).

As shown in FIG. 1 and 2, the two main flow passages **16** each have an outlet section **20**. the outlet section **20** of each of the two main flow passages **16** has one end thereof connected to one respective outlet **14**. The two outlet sections **20** have a rectangular cross-sectional shape. As shown in FIG. 16 and 17, the height **H2** of the two outlet sections **20** is consistent from beginning to end (the height **H2** in this embodiment is 2.8mm). The width **W2** of the two outlet sections **20** is consistent from beginning to end (the width **W2** in this embodiment is 51mm). In addition, as shown in FIG. 15, the extending direction of the two outlet sections **20** is parallel to the central axis **A**.

As shown in FIG. 1 and FIG. 2, each main flow passage **16** has a front connection section **22**, a middle connection section **24** and a rear connection section **26**. One end of the front connection section **22** is connected to the inlet section **18**, and the middle connection section **24** is connected between the front connection section **22** and the rear connection section **26**. One end of the rear connection section **26** is connected to the outlet section **20**.

As shown in FIG. 7 and FIG. 8, the height **H3** of the front connection section **22** gradually reduces from the inlet section **18** toward the middle connection section **24** (the height **H3** in this embodiment gradually reduces from 19.99mm to 13.4mm), and the width **W3** of the front connection section **22** is consistent from

beginning to end (the width **W3** in this embodiment is 44mm). In addition, as shown in FIG. 6, a second included angle **02** is respectively defined between the extension direction of each of the two front connection sections **22** and the central axis **A**. The sum of the angles of the two second included angles **02** ranges from 36.9 to 61.9 degrees (the minimum total is 36.9 degrees, and the maximum total angle is 61.9 degrees).

As shown in FIG. 10 and FIG. 11, the height **H4** of the middle connection section **24** gradually reduces from the front connection section **22** toward the rear connection section **26** (the height **H4** in this embodiment gradually reduces from 13.4mm to 8.4mm), and the width **W4** of the middle connection section **24** gradually increases from the front connection section **22** toward the rear connection section **26** (the width **W4** in this embodiment gradually increases from 44mm to 51mm). Furthermore, as shown in FIG. 9, a third included angle **03** is respectively defined between the extension direction of the inner wall of each of the two middle connection sections **24** and the central axis **A**. The sum of the angles of the two third included angles **03** ranges from 5.7 to 8.6 degrees (the minimum total is 5.6 degrees, and the maximum total angle is 8.6 degrees). A fourth included angle **04** is respectively defined between the extension direction of the outer wall of each of the two middle connection sections **24** and the central axis **A**. The sum of the angles of the two fourth included angles **04** ranges from 28.1 to 41.1 degrees (the minimum total is 28.1degrees, and the maximum total is 41.1 degrees).

As shown in FIGS. 12-14, the height **H5** of the two rear connection sections **26** respectively gradually reduces from the respective middle connection section **24** toward the respective outlet section **20** (the height **H5** in this embodiment gradually reduces from 8.2mm to 2.4mm), and the width **W5** of the rear connection

section **25** gradually increases from the middle connection section **24** toward the outlet section **20** (the width **W5** in this embodiment gradually increases from 50.6mm to 51mm).

On the other hand, as shown in FIG. 1, the forming mold **10** of the present invention is composed of six die blocks, which are, sequentially from front to back, the first die block **32**, the second die block **34**, the third die block **36**, the fourth die block **38**, the fifth die block **40**, and the sixth die block **42**. In terms of length, the length **L1** of the first die block **32** is 70mm, the length **L2** of the second die block **34** is 25-35mm, the length **L3** of the third die block **36** is 20-30mm, the length **L4** of the fourth die block **38** is 20-30mm, the length **L5** of the fifth die block **40** is 25-30mm, and the length **L6** of the sixth die block **42** is 30-40mm. In addition to the configuration of the main flow passages **16**, the inlet **12** is located at first die block **32**, the inlet sections **18** are located at the first die block **32** and the second die block **34**, the front connection sections **22** are located at the third die block **36**, the middle connection sections **24** are located at the fourth die block **38**, the rear connection sections **26** are located at the fifth die block **40**, and the outlet sections **20** are located at the sixth die block **42**.

In addition, as shown in FIG. 1 and FIG. 2, the forming mold **10** of the present invention further has a sub flow passage **28** and two branch flow passages **30**. The sub flow passage **28** is located between the rear connection sections **26** of the two main flow passages **16** and extends straight down from the top surface of the fifth die block **40**. One end of the two branch flow passages **30** communicates with the bottom end of the sub flow passage **28**, and the other end of the two branch flow passages **30** communicates with the rear connection sections **26** of the two main flow passages **16** in a one-to-one manner.

In use, the polyvinyl chloride foam material with a specific gravity of 1.550-1.750 and high foaming characteristics is injected into the inlet **12**, and then the polyvinyl chloride foam material flows from the inlet **12** to the two main flow passages **16**. Then, in the process of flowing through two main flow passages **16**, on the one hand, by the change in height of the two main flow passages **16** and on the other hand, by the change in width and angle of the two main flow passages **16**, the polyvinyl chloride foam material is gradually squeezed, and the product shape is formed when the polyvinyl chloride foam material is finally discharged by two outlets **14**. As for the size of the product is $63.5\text{mm}\pm0.2\text{mm}$ (width) $\times$ $2.8\text{mm}\pm0.1\text{mm}$ (thickness), the weight is $28\text{g}\pm1\text{g}$ per inch, and the surface hardness is more than 85A Shore. In addition, in the process of the polyvinyl chloride foam material flowing through the two main flow passages **16**, a skin material (such as PVC, ABS, ASA, etc.) with a specific gravity of 1.450 to 1.650 and high strength and low foaming characteristics is injected into the sub flow passage **28**, so that the skin material flows from the sub flow passage **28** through the two branch flow passages **30** to the rear connection sections **26** of the two main flow passages **16** respectively, and the skin material is then mixed with the polyvinyl chloride foam material passing therethrough to form the skin layer of the product.

In conclusion, the forming mold **10** of the present invention uses a one-in two-out design and is matched with the symmetrical configuration and special angle design of the two main flow passages **16** to allow the PVC foam material to pass through quickly and stably so as to form the shape of the product and make the manufactured product have the characteristics of light weight, good hardness, strong rigidity and stable quality.

WHAT IS CLAIMED IS:

1. A forming mold for making polyvinyl chloride foamed wood-like slats, comprising an inlet, two outlets and two main flow passages, said main flow passages being symmetrically arranged with respect to a central axis, said two main
5 flow passages each comprising an inlet section and an outlet section, said inlet sections of said two main flow passages each having one end thereof commonly connected to said inlet, the extension direction of said inlet section of each of said two main flow passages respectively defining with said central axis a first included angle therebetween, the sum of the angles of the two said first included angles
10 ranging from 44.2 to 48.8 degrees, said outlet section of each of said main flow passage having one end thereof connected to one respective said outlet, the width of said two main flow passages gradually increasing from said inlet toward said outlets, the height of said two main flow passages gradually reducing from said inlet toward said outlets.

15

2. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 1, wherein the width of said inlet section of each of said two main flow passages is consistent from beginning to end.

20

3. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 1, wherein the height of said inlet section of each of said two main flow passages is consistent from beginning to end.

4. The forming mold for making polyvinyl chloride foamed wood-like
25 slats as claimed in claim 1, wherein the width of said outlet section of each of said

two main flow passages is consistent from beginning to end, and the extending direction of said outlet section of each of said two main flow passages is parallel to said central axis.

5 5. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 1, wherein the height of said outlet section of each of said two main flow passages is consistent from beginning to end.

6. The forming mold for making polyvinyl chloride foamed wood-like
10 slats as claimed in claim 1, wherein said two main flow passages each comprise a front connection section, a middle connection section and a rear connection section, said front connection section having one end thereof connected to the associating said inlet section, said middle connection section being connected between said front connection section and said rear connection section, said rear connection section
15 having one end thereof connected to the associating said outlet section.

7. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein the width of said front connection section of each of said two main flow passages gradually increases from the associating said
20 inlet section toward the associating said middle connection section.

8. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 7, wherein the extension direction of each of said two front connection sections respectively defines with said central axis a second included
25 angle therebetween, and the sum of the angles of said two second included angles

ranges from 36.9 to 61.9 degrees.

9. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein the height of said front connection section of
5 each of said two main flow passages gradually reduces from the associating said inlet section to the associating said middle connection section.

10. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein the width of said middle connection section of
10 each of said two main flow passages gradually increases from the associating said front connection section toward the associating said rear connection section.

11. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 10, wherein a third included angle is respectively defined
15 between the extension direction of an inner wall of each of said two middle connection sections and said central axis, and the sum of the angles of said two third included angles ranges from 5.7 to 8.6 degrees; a fourth included angle is respectively defined between the extension direction of an opposing outer wall of each of said two middle connection sections and said central axis, and the sum of the
20 angles of said two fourth included angles ranges from 28.1 to 41.1degrees.

12. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein the height of said middle connection section of each of said two main flow passages gradually reduces from the associating said
25 front connection section to the associating said rear connection section.

13. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein the width of said rear connection section of each of said two main flow passages gradually increases from the associating said middle
5 connection section toward the associating said outlet section.

14. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein the height of said rear connection section of each of said two main flow passages gradually reduces from the associating said
10 middle connection section to the associating said outlet section.

15. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, further comprising a sub flow passage and two branch flow passages, said sub flow passage being located between said rear connection
15 sections of said two main flow passages and extending straight down from a top surface of said forming mold, said two branch flow passages each having one end thereof respectively communicating with said rear connection sections of said two main flow passages and an opposite end thereof commonly communicating with a bottom end of said sub flow passage.

20

16. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 15, wherein said inlet is located at a first die block of said forming mold, said inlet sections are located at said first die block and a second die block of said forming mold that is connected to said first die block, said front
25 connection sections are located at a third die block of said forming mold that is

connected to said second die block, said middle connection sections are located at a fourth die block of said forming mold that is connected to said third die block, said rear connection sections, said sub flow passage and said branch flow passages are located at a fifth die block of said forming mold that is connected to said fourth die
5 block, and said outlet sections are located at a sixth die block of said forming mold that is connected to said fifth die block.

17. The forming mold for making polyvinyl chloride foamed wood-like slats as claimed in claim 6, wherein said inlet is located at a first die block of said
10 forming mold, said inlet sections are located at said first die block and a second die block of said forming mold that is connected to said first die block, said front connection sections are located at a third die block of said forming mold that is connected to said second die block, said middle connection sections are located at a fourth die block of said forming mold that is connected to said third die block, said
15 rear connection sections are located at a fifth die block of said forming mold that is connected to said fourth die block, and said outlet sections are located at a sixth die block of said forming mold that is connected to said fifth die block.