

Description

This invention relates to a process for the preparation of dispersant viscosity index improver for use in lubricating oil compositions.

Lubricating oil viscosity index improvers which have dispersant properties are known in the art, as taught by Klovsky in U.S. Patent No. 4,141,847. Klovsky's viscosity index improver is prepared by reacting a selectively hydrogenated star-shaped polymer having at least four arms of polymers or copolymers of diolefins and monoalkenyl arenes with alpha-beta unsaturated carboxylic acid or acid derivative, and then reacting the resulting intermediate with an amine.

The process incorporated by Klovsky to produce his viscosity index improver includes reacting the selectively hydrogenated star-shaped polymer with an alpha-beta unsaturated carboxylic acid or acid derivative at a temperature of between about 150 °C and about 300 °C for one to twenty hours, in a solvent containing 1% to 10% by weight polymer. The product of this functionalisation reaction is then reacted with a C₁ to C₁₈ amine containing one to eight nitrogen atoms. Although the product of Klovsky's process offered a significant advance in the art of lubricating oil additives, it has the disadvantage of requiring that large volumes of materials be held at high temperatures for extended reaction times. This causes the operating costs for Klovsky's process to be relatively high.

Attempts have been made to accomplish the functionalisation of the base polymer in a more economical fashion by reacting the selectively hydrogenated polymer with the functional groups in an extruder. An example of such an attempt is Hayashi et al.'s U.S. Patent No. 4,670,173. Hayashi reacts a hydrogenated block copolymer with an unsaturated carboxylic acid in the presence of a free radical initiator. The reaction is performed in either a solvent-free system or in a solution. The reaction may be carried out in any suitable vessel, device or apparatus, but is desirably performed in the absence of a solvent in an extruder, a Banbury mixer, a two-roll mill, or the like. The product of the functionalisation process is then reacted with a primary amine-containing compound in either a solvent, or in a solvent free system.

Hayashi also teaches that an optional and important aspect of his invention is that the blending device imparts high mechanical energy to such an extent that sufficient force is applied to the copolymer chains to cause scission or breakage thereof. This scission is said to be useful when the block copolymer is of higher molecular weight than that which is desired.

As opposed to being an advantage, however, this scission has now been found to be a disadvantage. Further, it has been found that in addition to scission, imparting high mechanical energy causes coupling and crosslinking of the base polymer causing a certain portion of the resultant functionalised polymer to have a significantly higher molecular weight than the initial polymer. Because of coupling, crosslinking and scission, the functionalised polymer produced by the reaction of the polymers and the functionalisation agent upon imparting high mechanical energy has a broad molecular weight distribution. The rate at which polymers degrade while in service as a lubricating oil viscosity index improver is a strong function of the polymer's molecular weight, with high molecular weight polymers degrading much more rapidly than lower molecular weight polymers. The "thickening effect" is also a strong function of molecular weight with high molecular weight polymers having a much greater effect on composition viscosity than low molecular weight polymers. A polymeric viscosity index improver with a broad molecular weight distribution will therefore lose thickening effect more rapidly as the polymer ages in service than a viscosity index improver with a narrow molecular weight distribution. It is therefore very desirable to have a viscosity index improver which has a narrow molecular weight range.

An advantage of Hayashi's process is that it may be carried out in a conventional extruder at a relatively high throughput when compared to solution functionalisation processes.

A process having this advantage, with a reduced level of scission, crosslinking and coupling is desirable for the production of lubricating oil viscosity index improvers-dispersants.

Accordingly the present invention provides a process for the preparation of a dispersant viscosity index improver aminated polymer comprising the steps of:

(a) producing a functionalised polymer by grafting an alpha-beta unsaturated carboxylic moiety selected from the group consisting of acids, anhydrides and esters, to a base polymer selected from the group consisting of i) selectively hydrogenated block copolymers comprising one or more blocks comprising predominantly conjugated diolefin monomer units, and one or more blocks comprising predominantly monoalkenyl arene monomer units, and ii) hydrogenated polymers comprising conjugated diolefin monomer units, where the functionalisation is performed in a device capable of imparting high mechanical energy and is performed in the presence of from 3.0% to 15% by weight based on the amount of base polymer of a diluent oil;

(b) reacting the functionalised polymer with an amine to form an aminated polymer; and

(c) recovering the aminated polymer.

Base polymers-suitable for functionalisation and amination by the process of this invention include homopolymers and copolymers of alphaolefins containing from 1 to 10 carbon atoms, hydrogenated homopolymers and copolymers of diolefins containing from 4 to 12 carbon atoms, and hydrogenated
 5 copolymers of one or more conjugated diolefins and one or more monoalkenyl aromatic hydrocarbons containing from 8 to 16 carbon atoms. The base polymer may be of a star or linear structure. Hydrogenated polymers may be hydrogenated selectively, completely or partially. Hydrogenated polymers of conjugated diolefins and copolymers of conjugated diolefins and monoalkenyl arenes are preferably hydrogenated such that greater than 90% of the initial ethylenic unsaturation is removed by hydrogenation. Preferably, the
 10 hydrogenated polymers are substantially free of ethylenic unsaturation.

Selective hydrogenation refers to processes which hydrogenate a substantial portion of the ethylenic unsaturation and a substantial portion of the initial aromatic unsaturation is left unhydrogenated. As used herein, a hydrocarbon polymer substantially free of ethylenic unsaturation will be a hydrocarbon polymer containing, on average, less than about 10 carbon-carbon ethylenic double bonds per polymer chain.
 15 Polymers containing more than this amount of ethylenic unsaturation will, under certain conditions, exhibit excessive crosslinking during a functionalisation reaction when the functionalisation is completed in a blending apparatus capable of imparting high mechanical shear.

Useful hydrocarbon polymers include those prepared in bulk, suspension, solution or emulsion. As is well known, polymerisation of monomers to produce hydrocarbon polymers may be accomplished using
 20 free-radical, cationic and anionic initiators or polymerisation catalysts.

A wide range of molecular weight polymers can be utilised as the base polymer of the present invention. In general, the higher the molecular weight of the polymer, the less polymer will be required to achieve a given viscosity in a lubricating oil composition. The configuration of the polymer also effects the acceptable molecular weight. A base polymer of higher molecular weight will generally be acceptable if it is
 25 of a star configuration than if it were of a linear configuration. Also, the incorporation of monoalkenyl arene polymer blocks will reduce the maximum molecular weight.

Number average molecular weights in the range from 500,000 to 3,000,000 may for example be suitable and from 600,000 to 2,000,000 are preferred, and from 600,000 to 1,200,000 are most preferred for the base polymer when the base polymer is a star-configuration hydrogenated polymer of one or more
 30 conjugated olefins or a star configuration polymer of one or more alpha olefins. For base polymers which are linear copolymers containing more than about 15% by weight of monoalkenyl arenes, number average molecular weights in the range from 80,000 to 150,000 may for example be suitable and from 85,000 to 110,000 are preferred. When the base polymer is a star configuration copolymer containing more than about 3% by weight of monoalkenyl arenes, the molecular weight is preferably in the range 500,000 to
 35 1,500,000. When the base polymer is a copolymer of monoalkenyl arene and polymerised alpha olefins, hydrogenated polymerised diolefins or combination thereof, the amount of monoalkenyl arene in the base polymer is preferably from 15% to 40% by weight of the base copolymer. The number average molecular weights, as used herein, refers to the number average molecular weight as measured by Gel Permeation Chromatography ("GPC") with a polystyrene standard.

Advantageously, the base polymer may be a selectively hydrogenated linear block copolymer containing at least one block comprising predominantly conjugated diolefin monomer units and at least one block comprising predominantly monoalkenyl arene monomer units, the base polymer having a monoalkenyl arene content of from 15% to 40% by weight, a number average molecular in the range from 80,000 to 150,000 as measured by GPC with a polystyrene standard wherein the ethylenic unsaturation of the base
 45 polymer has been reduced to less than 20% of the original ethylenic unsaturation by hydrogenation, or a star configuration base polymer which is a hydrogenated homopolymer of a conjugated diene wherein the unsaturation has been reduced to less than 20% of the original unsaturation by hydrogenation, and the number average molecular weight of the arms of the base polymer is in the range from 30,000 to 75,000 as measured by GPC with a polystyrene standard.

The minimum molecular weights preferred for functionalisation and amination by the method of the present invention is also limited by the molecular weight necessary for the particular base polymer to be a solid at ambient temperature and atmospheric pressure. Normally liquid polymers; ie, polymers which are liquid at ambient temperature and pressure do not generally, process well in blending equipment capable of imparting high mechanical energy such as an extruder. As a result, polymers having a molecular weight
 55 sufficiently high to be solid at ambient temperatures and pressures will, generally, be used in the method of this invention. Moreover, it should be noted that chemical, thermal and shear degradation which occurs in the blending apparatus increases with increasing molecular weight of the polymer. The amount of degradation is significantly reduced with the method of this invention and, as a result, the method of this

invention may be practised with higher molecular weight polymers than has been practicable in the extruder processing of the prior art. Generally, however, the method of this invention will not be used with polymers having a sufficiently large molecular weight as to result in more than about 30% degradation of the polymer during the extruder grafting process.

5 Polymers which are acceptable as the base polymer of the present invention include the hydrogenated derivatives of homopolymers and copolymers such as are described in U.S. Patent Nos. 3,135,716; 3,150,209; 3,496,154; 3,498,960; 4,145,298 and 4,238,202. In general, the polymers taught by these patents may be polymers of one or more conjugated dienes containing from 4 to 12 carbon atoms such as 1,3-butadiene, isoprene, piperylene, methylpentadiene, phenylbutadiene, 3,4-dimethyl-1,3-hexadiene, and 4,5-
10 diethyl-1,3-octadiene. Preferred conjugated diolefins are those containing 4 to 8 carbon atoms. Moreover, one or more of the hydrogen atoms in the conjugated diolefins may be substituted with halogen. The polymers taught by these patents may also be copolymers of one or more of the aforementioned conjugated diolefins and one or more other monomers. Other monomers which may be used include aryl-substituted olefins such as styrene, various alkyl-substituted styrenes, alkoxy-substituted styrenes, vinyl
15 naphthalene, and alkyl-substituted vinyl naphthalenes. The polymers taught by these references which may be hydrogenated and which would then be useful in the method of the present invention include random polymers, tapered polymers and block copolymers.

Polymers useful in the method of the present invention also include hydrogenated and selectively hydrogenated derivatives of block copolymers such as are taught, for example, in U.S. Patents Nos.
20 3,231,635; 3,265,765; 3,322,856 and 3,772,196.

Polymers which are acceptable as the base polymer further include hydrogenated and selectively hydrogenated derivatives of star-shaped polymers such as are taught, for example, in U.S. Patent Nos. 4,033,888; 4,077,893; 4,141,847; 4,391,949 and 4,444,953. Star-shaped polymers are alternatively referred to as radial polymers, and may also properly be called branched polymers.

25 Linear block copolymers which may be hydrogenated and then functionalised with the method of this invention may, for example be represented by the following general formula:



30 wherein:


A is a polymeric block comprising predominantly monoalkenyl arene (aromatic hydrocarbon) monomer units;

B is a polymeric block comprising predominantly conjugated diolefin monomer units;

x and z are, independently, 0 or 1; and

35 y is an integer in the range 1 to 15.

Radial polymers which may be hydrogenated and then functionalised with the method of this invention may be represented, for example, by the following general formulae:



wherein:

A, B, x, y and z are as previously defined;

n is an integer in the range 3 to 30;

45 C is the core of the radial polymer formed with a polyfunctional coupling agent;

B' is a polymeric block comprising predominantly conjugated diolefin units, which B' may be the same or different from B; and

n' and n'' are integers representing the number of each type of arm and the sum of (n' + n'') is in the range from 3 to 30.

50 Preferably in base polymers employed in the process of the invention, the conjugated diolefin is isoprene and the monoalkenyl arene, where applicable, is styrene.

As used herein in connection with polymer block composition, predominantly means that the specified monomer or monomer type which is the principle component in that polymer block is present in an amount of at least 85% by weight of the block.

55 Base polymers prepared with diolefins will contain ethylenic unsaturation, and such polymers will be hydrogenated prior to reacting the base polymers with an alpha-beta ethylenically unsaturated compound containing carboxyl or carboxyl derivative functionality in the process of this invention. When the polymer is hydrogenated, the hydrogenation may be accomplished using any of the techniques known in the prior art.

For example, the hydrogenation may be accomplished using any of the techniques known in the prior art. For example, the hydrogenation may be accomplished such that both ethylenic and aromatic unsaturation is converted (saturated) using methods such as those taught, for example, in U.S. Patents Nos. 3,113,986 and 3,700,633 or the hydrogenation may be accomplished selectively such that a significant portion of the ethylenic unsaturation is converted while little or no aromatic unsaturation is converted as taught, for example in U.S. Patents Nos. 3,634,595; 3,670,054; 3,700,633 and Re 27,145. Any of these methods could also be used to hydrogenate polymers which contain only ethylenic unsaturation and which are free of aromatic unsaturation.

In general any suitable liquid hydrocarbon may be used as a diluent for the polymer being modified in the method of this invention. A liquid hydrocarbon will be a suitable diluent if it is compatible with olefin or polyolefin polymers but not compatible with aromatic hydrocarbon polymers. Such a diluent would tend to swell the olefin monomer portion of the polymer without affecting the aromatic hydrocarbon monomer portion of the polymer when the polymer contains an aromatic portion. The liquid hydrocarbon may be a pure compound but generally will be a blend of compounds such as would be contained in a petroleum distillate fraction. It is, however, important that the diluent remain liquid throughout the processing. It is, therefore, important that the diluent have a boiling point above the maximum temperature that will be encountered during the processing steps. Preferably, the diluent will be a neutral petroleum distillate fraction boiling generally in the fuel oil and/or lubricating oil boiling ranges. Most preferably, the diluent will have a specific gravity of about 0.9, an ASTM IBP of about 710 °F (377 °C) and an ASTM 90% boiling point of about 865 °F (463 °C). Low aromatic and non-aromatic processing oils are generally preferred. "Shellflex 371" (trade mark), a processing oil available from Shell Oil Company, Houston, Texas, is an example of a preferred processing oil.

The diluent oil is present in an amount from 3% to 15% by weight based on the base polymer. Preferably, the diluent oil is present in an amount from 5% to 12% and most preferably from 6% to 11% by weight. Lower amounts of diluent than 3% do not result in significant benefits over diluent-free processes. Higher levels of diluent than 15% result in lower efficiencies of the functionalisation and amination reactions. Lower reaction efficiencies result in unreacted reactants being present in the product composition. These reactants are generally undesirable components in the product compositions. Higher amounts of diluent oil also needlessly dilute the finished product, resulting in high costs, higher volumes, more cold flow and more difficult handling without advantage.

Carboxyl or carboxyl derivative functionality is imparted into the base polymer by contacting the base polymer in an extruder with an alpha-beta ethylenically unsaturated carboxylic acid reagent. Suitable alpha-beta carboxylic acid reagents include the carboxylic acids per se, anhydrides and esters. The carboxylic acid reagent may be either monobasic or polybasic in nature. When the carboxylic acid reagent is polybasic, it is preferably dibasic, although tribasic and tetrabasic acids can be used. In general, the carboxylic acid reagent may be linear, branched, cyclic, substituted cyclic, aromatic, or substituted aromatic. In general, the acid portion of the carboxylic acid reagent may conveniently contain from 1 to 12 carbon atoms. Useful monobasic alpha-beta unsaturated carboxylic acids include acrylic acid, methacrylic acid, cinnamic acid, crotonic acid and 2-phenylpropenoic acid. Useful dibasic acids include maleic acid, fumaric acid, mesaconic acid, itaconic acid and citraconic acid. Functional derivatives corresponding to each of the useful acids are well known in the art and their respective equivalents of the acid for purposes of functionalising a polymer are taught, for example, in U.S. Patents Nos. 4,578,429 and 4,670,173. Similarly, methods of making such functional derivatives are also well known to those of ordinary skill in the art. For example, ester derivatives useful in the method of this invention can be made by esterifying monohydric alcohols or epoxides with any of the aforescribed acids. The corresponding anhydride can be prepared by dehydrating the acid. The alpha-beta unsaturated carboxylic acid moiety is preferably maleic anhydride.

In general, a sufficient amount of carboxylic acid reagent will be combined with the polymer to incorporate from 1 to 50 functional groups, on average, per polymer chain. In this regard, it should be noted that the reaction between the carboxylic acid reagent and the polymer frequently will not proceed to completion. As a result, the amount of carboxylic acid reagent actually used will, generally, exceed the amount which is desired to be grafted to the base polymer by from 10 to 50%. Preferably, the amount of the alpha-beta unsaturated carboxylic moiety is sufficient to result in at least on average one carboxylic functional group per polymer molecule and not more than 5% by weight carboxylic functional groups as percent by weight of the base polymer.


Any of the free radical initiators known in the prior art to be effective in a grafting reaction of the type herein contemplated can be used as in step (a) of the method for this invention. Suitable free radical initiators include the various organic peroxides and hydroperoxides as well as the various organic azo

compounds. Typical organic peroxides include benzoyl peroxide, t-butyl peroxyvalate, 2,4-dichlorobenzoyl peroxide, decanoylperoxide, propionyl peroxide, hydroxyheptyl peroxide, cyclohexanone peroxide, t-butylperbenzoate, dicumyl peroxide and lauroyl peroxide. Typical hydroperoxides include t-butyl hydroperoxide and 2,5-dimethyl-2,5-di(t-butylperoxy)hexane. Typical organic azo initiators include 2,2-azobis(2-methylpropionitrile), 2,2-azobis(2-methylvaleronitrile), and 4,4'-azobis(4-cyanovaleric acid). In general, the free radical initiator will be used in a concentration within the range from 0.05 to 0.50 wt% based on polymer. Particularly preferred free radical initiators include di t-butylperoxide; ethyl 3,3-di(tertbutyl peroxy) cyclohexane; 1,1-bis(t-butylperoxy) 3,3,5-trimethylcyclohexane; t-butyl cumyl peroxide and 2,5-dimethyl-2,5-di(t-butylperoxy) hexane.

The polymer, diluent, carboxylic acid reagent and free radical initiator will be contacted at a temperature and pressure sufficient to ensure that both the polymer and the carboxylic acid reagent are in the liquid or molten phase when the reaction occurs. The reactants will be contacted in a blending device capable of imparting high mechanical energy such as an extruder, a Banbury mixer or a sigma blade mixer. These devices are referred to herein as extruders. Generally, sufficient mechanical energy, at the concentration of free radical initiator employed, will be imparted to cause at least a portion of the polymer chains to scission or break. The amount of polymer actually degraded is, however, found to be significantly reduced in the method of this invention (e.g. relative to Hayashi, discussed above).

This modified polymer is then reacted with certain amines to form the oil-soluble product of the present invention. The resulting products provide the dispersant function of the additive. Dispersant properties as used herein, refers to the ability to maintain sludge in suspension in lubricating oil.

The amine employed in this invention can be branched or unbranched, saturated, aliphatic, primary or secondary amines containing 1 to 18 nitrogen atoms, preferably a mono- or diamine, such as ethyl amine, butylamine, s-butylamine, and diethylamine, but including higher polyamines such as alkylene polyamines, wherein pairs of nitrogen atoms are joined by alkylene groups of 2 to 4 carbon atoms where one or more of the amine groups have one or more alkyl groups on the nitrogen atom. Preferred polyamines are of the formula:



where x is 2 to 4

R¹ is hydrogen or an alkyl group comprising 1 to 12 carbon atoms

R² are independently selected alkyl groups comprising 1 to 12 carbon atoms. Examples of such preferred polyamines include N-aminoalkyl piperazines, e.g. N-(2-aminoethyl) piperazine. Particularly preferred polyamines include diethylaminopropylamine dimethylaminopropylamine, dibutylaminopropylamine, dipropylaminopropylamine, dipentylaminopropylamine, dimethylaminoethylamine, dibutylaminoethylamine, dipropylaminoethylamine, dipentylaminoethylamine, N,N-dimethylaminopropyl N'-methylamine, N,N-dimethylaminopropyl N'-ethylamine, N,N-dimethylaminoethyl N'-methylamine and N,N'-diethylaminoethyl N'-ethylamine. The amine is most preferably diethylaminopropylamine.

The molar ratio of amine to carboxylic moiety grafted to the base polymer is typically in the range 0.1:1 to 2:1, preferably at least 0.5:1, e.g. 0.5:1 to 1.5:1, most preferably about 1:1. Amidisation is typically performed at a temperature in the range 150 °C to 250 °C, e.g. from 15 seconds to 3.0 minutes.

The amount of amine incorporated in the viscosity index improver dispersant is preferably at least, on the average, one amine group per polymer molecule and not more than that required to result in a polymer containing 2.0% by weight nitrogen content. Most preferably, the animated polymer contains less than 0.5% by weight nitrogen. The maximum amount of amine beneficially incorporated in the viscosity index improver-dispersant is limited by the tendency of the polymer to attach itself to too many particles, and itself act like a sludge.

In both reaction steps of functionalisation and amination it is much preferred that the reactions take place in the absence of oxygen. A nitrogen blanket is often used to accomplish this result. The reason for performing the reaction in the absence of oxygen is that the resulting additive may be more oxidatively unstable if any oxygen is present during the formation of the additive.

If excess amine is employed, then it may be desirable to remove the excess from the reaction product. The excess amine may be removed in the extruder by applying a vacuum or with a stripping gas stream,

which is subsequently vented from the extruder in a specially designed vent section.

The invention also provides a lubricating oil composition comprising a major proportion of a lubricating oil and a minor proportion of an animated polymer prepared by the process of the invention.

The invention will be further understood from the following description of an embodiment of a process in accordance therewith which is made by way of illustration only with reference to the accompanying drawings, and from the specific examples thereafter. In the drawings:-

Figure 1 is a schematic flow diagram of a functionalisation and animation process in accordance with the invention.

An embodiment of the invention wherein an extruder is used as the blending apparatus is illustrated in Figure 1. Referring to Figure 1, a solid particulate polymer feed is fed to extruder 101 through feed hopper 102. In the extruder, the polymer is heated at least to a temperature at which the polymer becomes molten so that the reaction of the polymer and the carboxylic acid reagent will occur when the polymer is in the molten phase. As is well known, extruders generally contain a plurality of stages and both the temperature and channel depth of the screw may be varied in each of the stages. In general, and in the method of this invention, the temperature may, for example, range from 160 to 250 °C, depending upon the particular base polymer being processed, while the reaction between the base polymer and the carboxylic acid reagent takes place. Variation of the temperature in the different stages of the extruder is not necessary to the method of this invention and the temperature will therefore be maintained as nearly constant as possible as the polymer passes through the extruder except that the temperature in the inlet zone, i.e., the zone or zones where the feed materials are introduced may, generally, be maintained somewhat below the reaction zone temperature to maximise the life of the free radical initiator thereby improving grafting efficiency. Also in the extruder, the polymer feed is transported from the feed inlet 102 to the extruder outlet 103 with one or more extruder screws not illustrated. In general, the channel depth may be varied within the range from 0.0005 to 0.5 times the diameter of the screw housing with maximum depths occurring in those areas where the components are reacted and then again at or near the outlet of the extruder where the melt is devolatilised. In transition, the channel depth may be varied to ensure that the desired degree of mechanical shear and mixing have been imparted on the materials being processed.

As the base polymer passes through the blending apparatus, the extruder in the embodiment illustrated in Figure 1, the base polymer first will be combined with a suitable diluent introduced into the extruder through line 104. The diluent is supplied from a suitable vessel 105 through lines 106-106 with pump 107. The amount of diluent actually introduced into the extruder may be controlled with valve means 108. The amount of diluent introduced will range from 3 to 15 wt% based on the amount of base polymer feed to the extruder. Introduction of the diluent into the extruder before the carboxylic acid reagent or the free radical initiator is important to the method of this invention since the solvent or diluent is effective in reducing the amount of scission or degradation of the polymer. Additionally, the solvent or diluent is effective in reducing the amount of crosslinking or coupling that would otherwise occur. Although it has not been proven it is believed that the diluent effectively reduces degradation as a result of interaction between the diluent and that portion of the polymer where the grafting reaction occurs by reducing the melt temperature of the polymer and effectively reduces crosslinking or coupling by capping free radical sites on the polymer that might otherwise combine. Generally the diluent will be introduced to the blending apparatus at a point within the range from about 1 D to about 6 D downstream from the point at which the polymer is fed into the extruder, D being the inside diameter of the housing of the blending apparatus, in the embodiment illustrated in the Figure.

As the base polymer feed and diluent continue through the extruder, they are next contacted either with a carboxylic acid reagent or a free radical initiator. In the embodiment illustrated, the polymer and diluent are next contacted with the carboxylic acid reagent. Adding of the carboxylic acid reagent prior to adding the free radical initiator is preferred since it has been discovered that addition of the free radical initiator prior to the carboxylic reagent will, generally, result in an increased amount of crosslinked or coupled polymer in the product recovered from the blending apparatus. In the embodiment illustrated, the carboxylic acid reagent is introduced into the extruder through line 109. The carboxylic acid reagent is supplied from a suitable storage vessel 110 through lines 111-111 with pump 112. The amount of carboxylic acid reagent introduced into the blending apparatus may be controlled with suitable valve means 113. In general, the carboxylic acid reagent could be fed to the blending apparatus as a solid, as a liquid, or as a solution in a suitable solvent. With respect to feeding as a liquid, it should be noted that certain of the carboxylic acid reagents heretofore noted as operable are normally liquid. Those which are solid, however, could be heated and fed in the molten phase. In general, carboxylic acid reagent will be introduced into the blending apparatus at a concentration sufficient to incorporate from about 1 to about 50 moles of carboxylic acid reagent, on average, per mole of polymer. As indicated supra, the amount of carboxylic acid reagent

introduced into the blending apparatus will, generally, be from about 10 to about 50% more than that required for stoichiometric addition of the carboxylic acid reagent in the amount desired. In general, the carboxylic acid reagent will be introduced into the extruder at a point downstream of the point where the diluent is introduced and within the range from about 1 D to about 8 D downstream of the point where the polymer feed is introduced to the extruder, D being the diameter of the housing for the blending apparatus, in the embodiment illustrated, the screw housing of the extruder. In general, the temperature in the blending apparatus at the point at which the carboxylic acid reagent is introduced is not critical to the method of the present invention. For reasons more fully explained below, the polymer will, preferably, be at a temperature below about 210°C when the carboxylic acid reagent is introduced.

As the polymer, diluent and, in the embodiment illustrated, the carboxylic acid reagent continue to move through the blending apparatus, the blend is next contacted with a free radical initiator introduced into the extruder through line 114. The free radical initiator is fed from a suitable storage vessel 115 through lines 116-116 with pump 117. The amount of free radical initiator actually introduced into the extruder may be controlled with a suitable valve means 118. The free radical initiator may be fed to the blending apparatus in its natural state, i.e. as a liquid or a solid, or as a solution. Most of the free radical initiators contemplated for use in the method of the present invention are normally liquid and will, generally, be introduced into the extruder in this state. As is well known in the prior art, free radical initiators such as those contemplated for use herein generally have a very short half life at elevated temperatures and frequently even decompose at temperatures within the range of those contemplated for use herein. As a result, it is important to the method of the present invention to introduce the free radical initiator into the blending apparatus at as low a temperature as reasonably practicable and then relatively quickly thereafter bringing the temperature of the entire blend up to the desired reaction temperature so as to ensure maximum efficiency during the grafting reaction. In this regard, maximum reaction efficiency is generally realised when the temperature of the blend with which the free radical initiator is initially contacted is within the range from 160 to 210°C. As a result, and as indicated above, the initial stages of the blending apparatus will be maintained at a temperature within this range so as to ensure maximum reaction efficiency. The temperature, will, however, be raised to the desired reaction temperature, as quickly after the free radical initiator is added as is practicable. The free radical initiator will be added at a point downstream of the point where the diluent is introduced and within the range from about 5 D to about 16 D from the point at which the polymer is introduced in to the blending apparatus where D is the diameter of the housing for the blender or, as in the embodiment illustrated, the housing of the screw or screws in the extruder.

As indicated above, the channel depth of the extruder screw or screws will, generally, be at or near a maximum in that portion of the apparatus immediately after which the polymer feed is introduced. In fact, this maximum dimension will, generally, be maintained until both the diluent and the carboxylic acid reagent are introduced. The channel depth will, generally, be reduced in one or more steps prior to addition of the free radical initiator and then will be further reduced after the free radical initiator is introduced. Generally, the channel depth will again begin to increase after the grafting reaction has been completed reaching a second maximum or near maximum to facilitate devolatilisation at or near the blending apparatus exit. The channel depth will, of course, generally vary somewhat during the reaction stages-such variation being well known and appreciated in the extruder processing arts. The zone 119 within which the grafting reaction occurs will have a length within the range from about 1 D to about 6 D, D being the diameter of the housing as previously defined.

As the polymer with the carboxylic acid functionality grafted to it, diluent, and free radical initiator continue to move through the blending apparatus, the blend is next contacted with an amine. The amine is introduced into the extruder through line 120. The amine is fed from a suitable storage vessel, 121, through lines 122-122 with pump 123. The amount of amine actually introduced into the extruder may be controlled with a suitable valve means 124. The amine may be fed into the blending apparatus in its natural state, i.e. as a liquid or a solid, or as a solution. The amine could also be diluted with a diluent such as a lubricating oil, or a white mineral oil to aid in lubrication of the pump, 123.

The reaction between the amine and the acid functionality which is grafted onto the polymer occurs within a reaction zone, 125.

As indicated supra, the channel depth in the blending apparatus will, generally, be varied after the grafting reaction is completed as the modified polymer passes from the reaction zone 125 to the blending apparatus outlet 103. Generally, the first such variation in channel depth will be accomplished prior to devolatilization of excess reactants and in the embodiment illustrated in Figure 1 the first such change occurs in zone 126. The second such variation will be made to facilitate pelletization in zone 127 and/or zone 128. It will, of course, be appreciated that changes in channel depth can readily be accomplished,

when an extruder is used as the blending apparatus, by changing the screw or screws configuration. Similarly, when other types of blending apparatus are used such changes can be easily accomplished by changing the blender or agitator configuration.

The effluent from the reaction zone will contain unreacted carboxylic acid reagent and unreacted amine when the grafting reaction and the amination reaction do not proceed to completion. Because many of the carboxylic acid reagents and amines useful in the method of this invention may be detrimental to a lubricating oil viscosity index improver if allowed to remain in the polymer product in an ungrafted state, at least a portion of the unreacted carboxylic acid reagent and amine should be separated from the polymer product prior to use. In general, any of the conventional techniques known in the prior art such as stripping and extraction may be used. Frequently, however, a portion of the unreacted carboxylic acid reagent may be separated from the graft reaction zone effluent simply by venting the effluent after the grafting reaction is completed. In the embodiment illustrated in the Figure, a vent 129 is provided in the first zone 126 after the grafting zone for this purpose. In the embodiment illustrated, the vapors passing through vent 129 are passed through lines 130-130 to a steam eductor 131 where the vapors are combined with steam introduced through line 132. The steam eductor will pull a vacuum on the vent. In general, the vent outlet pressure should be within the range from about 20 to about 300 torr (2,666 to 40,000 Pa.s). The vapor-steam mixture is then passed to a condenser 133 through line 134 where the steam vapor mixture is condensed and recovered as a liquid through line 135. Other methods of recovering or disposing of the vapor are known in the prior art and could also be utilized. The vapor will contain in addition to unreacted carboxylic acid reagent, free radical initiator decomposition products, unreacted amines, low molecular weight polymer formed as a result of degradation and the like. In general, venting of the grafting reactor effluent will remove from about 20 to about 80% of the unreacted carboxylic acid reagent and unreacted amines contained in the effluent. The temperature in the zone where the effluent is vented could, of course, be increased to increase the vapor pressure of the components to be vented.

The lubricating oil viscosity improver-dispersant product will be recovered in pellet form and any of the suitable recovery means known in the prior art may be used for this purpose. In the embodiment illustrated in Figure 1, an underwater pelletizer with a tempered water system is shown. Referring again to Figure 1, the functionalized polymer exits the blending apparatus 101 through a suitable outlet 103 and is introduced into the underwater pelletizer at 136 where it is combined with water circulating through lines 137-137. In the embodiment illustrated in Figure 1, the polymer-water mixture is then passed to spin dryer 138 through lines 139-139. In the spin dryer the polymer pellets are generally dried to a water content within the range from about 100 to about 500 ppm, based on polymer, and then recovered through line 140. Water separated from the polymer pellets may then be returned to a slurry water bath 141 through lines not illustrated from where it may then be recirculate through lines 137-137. Makeup water may be added to the slurry water bath 141 as required using means not illustrated. In those cases where a lower water content would be required, other drying means could be employed. Also, to the extent that the content of unreacted carboxylic acid reagent in the recovered product is higher than desired for the lubricating oil viscosity index improver-dispersant, the recovered polymer could be further processed using techniques well known in the prior art to further reduce the content of unreacted carboxylic acid reagent.

The process of the present invention has the desirable feature of being operable in standard polymer handling equipment. Further, the residence time of the process is only about 15 seconds to about 3 minutes. This is a distinct advantage over prior art solution functionalization and amination processes. The process results in significantly lower levels of scission, crosslinking and coupling, than prior art extrusion functionalization and amination methods. The product of the present process therefore has a narrower molecular weight distribution than products of prior art extrusion methods. The narrower molecular weight distribution minimizes the rate of degradation of the polymer in lubricating oil service, and therefore maximizes the retention of the "thickening" effect of the polymer. This advantage is evidenced by lower shear loss or DIN loss. The product of the present process also has excellent viscosity index improving properties and excellent dispersant characteristics.

Examples

A hydrogenated isoprene-styrene diblock copolymer was used in the examples which was 36% by weight styrene and had a molecular weight of 93,000. Hydrogenation had reduced the ethylenic unsaturation to less than 1.0% of the original ethylenic unsaturation.

A low molecular weight star polymer was used in the example which was a hydrogenated homopolymer of polyisoprene with an average of 15 arms per molecule, and having arms with a number average molecular weight of 35,000 each. Hydrogenation had reduced the unsaturation to less than 1.0% of the initial

unsaturation.

A high molecular weight star polymer was used which was a hydrogenated homopolymer of polyisoprene with an average of 15 arms per molecule, and with a number average molecular weight of each arm of 65,000. Hydrogenation had reduced the unsaturation to less than 1.0% of the initial unsaturation.

Diethylaminopropylamine ("DAP") was the amine used in all of the examples. The alpha-beta unsaturated carboxyl moiety used was maleic anhydride ("MA"). A 67% by weight solution of MA in acetone was used. The diluent oil used was an HVI-100 neutral oil.

The peroxide utilized as the free-radical initiator in these examples was 2,5-dimethyl-2,5-bis(tertbutyl peroxy) hexane which is available under the trade mark "Lupersol 101" from Lucidol Pennwalt Chemicals. The peroxide was utilized as 50% by weight solution in HVI-100 neutral oil ("HVI" denotes high viscosity index).

A two inch (5cm) Welding Engineering Inc. extruder was used to prepare the example compositions. The extruder was a non-intermeshing twin screw extruder with a single vent and an underwater face cutter. The feed rate for each run was 100 lb/hr (45.4 kg/hr) and the screw speed was 120 rpm. Polymer was fed to the extruder using a Conair feeder with a variable speed auger. Peroxide was injected 12 diameters downstream of the feed port, and MA was injected 6 diameters downstream of the feed port. Dilution oil, when it was utilized, was also injected 6 diameters downstream of the feed port. The amine solution was injected 17 diameters downstream of the feed port.

An air-driven William's pneumatic plunger pump was used to inject the amine solution for the examples incorporating the diblock copolymer and the high molecular weight star polymer. A Zenith-Nichols gear pump, Model BPB-4391-1.168 was used to inject the amine solution in the preparation of the compositions containing the low molecular weight star-shaped polymer. The gear pump is preferred because use of the pneumatic plunger pump resulted in surges in the feed rate whereas the gear pump did not. The gear pump required that the amine be diluted to a 50% by weight solution in mineral oil to lubricate the pump.

The devolatilization port was operated at pressures in the range 50 to 150 torr (6,666 to 20,000 Pa.s).

The product was pelletized using a Gala underwater pelletization system. Pellets were recovered in trays from a spin dryer.

In the following examples GPC analyses were performed on the aminated polymers.

Maleated polymers were analyzed by hot press, IR techniques. For star-shaped polymers, a spike of hydrogenated styrene-styrene triblock copolymer was added as a reference peak.

Bound amine was determined by a hot press infrared technique similar to that used for maleic anhydride analysis.

Total nitrogen was determined by coulometric analysis.

Hydrogenated Diblock

The hydrogenated diblock copolymer of isoprene and styrene was aminated in the Welding Engineering extruder described above, using the amounts of peroxide, oil, MA and amine listed in Table 1. The amounts are in percent weights based on the amount of base polymer. The total degradation, and degradation to high molecular weight polymer was measured and is also included in Table 1. This example demonstrates significant decreases in degradation when diluent oil is present during the functionalization process.

TABLE 1
Hydrogenated Isoprene-Styrene Diblock Copolymer

Composition	Peroxide %w	Oil %w	MA %w	DAP Added %w	DAP Bound %w	Total Nitrogen %w	Degradation	
							Total %w	HMP %w
1	0.15	10	1.6	2.1	1.0	0.18	27	6.5
C1	0.15	0	1.6	2.1	1.4	0.11	38	7.0
2	0.25	10	1.6	1.8	1.6	0.43	35	9.8
C2	0.25	0	1.6	1.8	1.5	0.43	46	11.5

55 Low Molecular Weight Star Polymer

The hydrogenated star-shaped polyisoprene polymer was functionalised with MA, using initiator "Lupersol 101", and reacted with DAP in the Welding Engineering extruder as described above. The amounts of

the components, and the measured degradation are listed in Table 2. The low molecular weight star-shaped polymer has a low viscosity and cold flows easily. It is therefore obtained in bales. The bales were chopped into 1.27 cm (0.5 inch) strips and then granulated to produce chips. These chips were then dusted with 5-10 %w of crumbs of the hydrogenated diblock isoprene-styrene copolymer used in compositions 1, 2, C1 and C2. The dusted chips were then stored in a refrigerator at a temperature in the range from 10 to 20 °F (-12 to -6 °C) until they were functionalised.

10

15

20

25

30

35

40

45

50

55

TABLE 2
Low Molecular Weight Star-Shaped Polymer

Composition	Peroxide %w	Oil %w	MA %w	DAP Added %w	DAP Bound %w	Total Nitrogen %w	Degradation Total %w	HMP %w
3	0.15	8	2.0	3.0	1.3	0.61	11	4
C3	0.15	0	2.0	3.0	1.6	0.57	26	11
4	0.15	8	1.5	2.4	0.6	0.43	14	6
C4	0.15	0	1.5	2.4	1.3	0.46	27	12
5	0.10	8	1.4	1.8	0.9	0.38	12	7
C5	0.10	0	1.4	1.8	1.7	0.40	26	6

This example demonstrates a significant impact of the presence of 8% by weight of the diluent oil on the degradation of the polymer.

55 High Molecular weight Star-Shaped Polymer

Table 3 summarises the composition and properties of Compositions 6 and C6, in which the base polymer is the high molecular weight star-shaped polymer.

The HMP for the high molecular weight polymer could not be determined by the modified GPC methods due to poor resolution with polymers of such high molecular weight.

Again, it can be seen that the presence of diluent oil has a significant impact on the extent of degradation.

TABLE 3
High Molecular Weight Star-Shaped Polymer

Composition	Peroxide %w	Oil %w	MA %w	DAP Added %w	DAP Bound %w	Total Nitrogen %w	Degradation %w
6	0.17	10	2.0	3.0	2.3	0.6	22
C6	0.17	0	2.0	3.0	2.3	0.6	37

Shear Loss Example

The effect of the present invention on shear loss ("DIN loss") was determined in this example. The low molecular weight star-shaped base polymer described above was aminated utilising varying amounts of diluent oil, peroxide, MA and DAP, according to Table 4. The Welding Engineering extruder described above was utilised as was the process described above. Comparative Compositions C7 and C8 were prepared without diluent oil, and Comparative Composition C9 was prepared using 2% by weight, based on the base polymer, of diluent oil. Compositions 7, 8 and 9 were prepared using 6% by weight diluent oil and composition 10, 11 and 12 were prepared using 10% by weight diluent oil. The DIN losses were measured on a Kurt Orbahn Diesel Injector Test according to ASTM D3945-86.

It can be seen from Table 4 that the process of the present invention results in DIN losses of less than 15% by weight. In the preferred embodiment of about 10% diluent oil the DIN loss was less than 12% by weight. Prior art extrusion amination resulted in DIN losses of greater than 16% by weight.

TABLE 4

Composition	Oil Level %w	DIN Loss %w	Peroxide %w	MA Added %w	DAP Added %w	Total Nitrogen %w
C7	0	20.2	0.15	1.5	1.7	0.36
C8	0	16.3	0.10	1.4	1.8	0.40
C9	2	17.7	0.10	1.1	1.5	0.35
7	6	13.8	0.10	1.5	1.8	0.42
8	6	11.0	0.10	1.1	1.5	0.38
9	6	10.9	0.10	1.1	1.5	0.37
10	10	9.2	0.10	1.4	1.8	0.38
11	10	11.9	0.10	1.1	1.5	0.39
12	10	9.3	0.10	1.1	1.5	0.38

Claims

Claims for the following Contracting States : BE, CH, DE, FR, GB, IT, LI, NL, SE

1. A process for the preparation of a dispersant viscosity index improver aminated polymer comprising the steps of:

(a) producing a functionalized polymer by grafting an alpha-beta unsaturated carboxylic moiety selected from the group consisting of acids, anhydrides and esters, to a base polymer selected from the group consisting of i) selectively hydrogenated block copolymers comprising one or more blocks comprising predominantly conjugated diolefin monomer units, and one or more blocks comprising predominantly monalkenyl arene monomer units, and ii) hydrogenated polymers comprising con-



TABLE 4

Composition	Oil Level %w	DIN Loss %w	Peroxide %w	MA Added %w	DAP Added %w	Total Nitrogen %w
C7	0	20.2	0.15	1.5	1.7	0.36
C8	0	16.3	0.10	1.4	1.8	0.40
C9	2	17.7	0.10	1.1	1.5	0.35
7	6	13.8	0.10	1.5	1.8	0.42
8	6	11.0	0.10	1.1	1.5	0.38
9	6	10.9	0.10	1.1	1.5	0.37
10	10	9.2	0.10	1.4	1.8	0.38
11	10	11.9	0.10	1.1	1.5	0.39
12	10	9.3	0.10	1.1	1.5	0.38

Claims

50 Claims for the following Contracting States : BE, CH, DE, FR, GB, IT, LI, NL, SE

1. A process for the preparation of a dispersant viscosity index improver aminated polymer comprising the steps of:

55 (a) producing a functionalized polymer by grafting an alpha-beta unsaturated carboxylic moiety selected from the group consisting of acids, anhydrides and esters, to a base polymer selected from the group consisting of i) selectively hydrogenated block copolymers comprising one or more blocks comprising predominantly conjugated diolefin monomer units, and one or more blocks comprising predominantly monalkenyl arene monomer units, and ii) hydrogenated polymers comprising con-



jugated diolefin monomer units, where the functionalization is performed in a device capable of imparting high mechanical energy and is performed in the presence of from 3.0% to 15% by weight based on the amount of base polymer of a diluent oil;

(b) reacting the functionalized polymer with an amine to form an aminated polymer; and

(c) recovering the aminated polymer.

2. A process according to Claim 1 wherein step (a) is performed in the presence of a free radical initiator selected from the group consisting of 2,5-dimethyl-2,5-bis(tert butylperoxy) hexane, ethyl 3,3-di-(tertbutyl peroxy) cyclohexane, di-tertbutyl peroxide, tert butylcumyl peroxide, and 1,1-bis(tert butyl peroxy)-3,3,5-trimethylcyclo-hexane.
3. A process according to Claim 1 or 2 wherein the amine is diethyl-aminopropylamine.
4. A process according to Claim 1, 2 or 3 wherein the base polymer is a selectively hydrogenated linear block copolymer containing at least one block comprising predominantly conjugated diolefin monomer units and at least one block comprising predominantly monoalkenyl arene monomer units, the base polymer having a monoalkenyl arene content of from 15% to 40% by weight, a number average molecular weight in the range from 80,000 to 150,000 as measured by GPC with a polystyrene standard wherein the ethylenic unsaturation of the base polymer has been reduced to less than 20% of the original ethylenic unsaturation by hydrogenation, or a star configuration base polymer which is a hydrogenated homopolymer of a conjugated diene wherein the unsaturation has been reduced to less than 20% of the original unsaturation by hydrogenation, and the number average molecular weight of the arms of the base polymer is in the range from 30,000 to 75,000 as measured by GPC with a polystyrene standard.
5. A process according to Claim 4 wherein the conjugated diolefin is isoprene, and the monoalkenyl arene is styrene.
6. A process according to any one of Claims 1 to 5 wherein the alpha-beta unsaturated carboxylic moiety is maleic anhydride.
7. A process according to any one of Claims 1 to 6 wherein the molar ratio of amine to carboxylic moiety is in the range from 0.1:1 to 2:1.
8. A process according to any one of Claims 1 to 7 wherein the amount of alpha-beta unsaturated carboxylic moiety is sufficient to result in at least on the average one carboxylic functional group per polymer molecule and not more than 5% by weight carboxylic functional groups as percent by weight of the base polymer.
9. A process according to any one of Claims 1 to 8 wherein the amount of amine is sufficient to result in at least on the average one amine group per polymer molecule and not more than 2.0% by weight nitrogen in the aminated polymer.
10. A lubricating oil composition comprising a major proportion of a lubricating oil and a minor proportion of an aminated polymer whenever prepared by a process according to any of Claims 1 to 9.

Claims for the following Contracting State : ES

1. A process for the preparation of a dispersant viscosity index improver aminated polymer comprising the steps of:
 - (a) producing a functionalized polymer by grafting an alpha-beta unsaturated carboxylic moiety selected from the group consisting of acids, anhydrides and esters, to a base polymer selected from the group consisting of i) selectively hydrogenated block copolymers comprising one or more blocks comprising predominantly conjugated diolefin monomer units, and one or more blocks comprising predominantly monoalkenyl arene monomer units, and ii) hydrogenated polymers comprising conjugated diolefin monomer units, where the functionalization is performed in a device capable of imparting high mechanical energy and is performed in the presence of from 3.0% to 15% by weight based on the amount of base polymer of a diluent oil;



- (b) reacting the functionalized polymer with an amine to form an aminated polymer; and
 (c) recovering the aminated polymer.

2. A process according to Claim 1 wherein step (a) is performed in the presence of a free radical initiator selected from the group consisting of 2,5-dimethyl-2,5-bis(tert butylperoxy) hexane, ethyl 3,3-di(tertbutyl peroxy) cyclohexane, di-tertbutyl peroxide, tert butylcumyl peroxide, and 1,1-bis(tert butyl peroxy)-3,3,5-trimethylcyclo-hexane.
3. A process according to Claim 1 or 2 wherein the amine is diethyl-aminopropylamine.
4. A process according to Claim 1, 2 or 3 wherein the base polymer is a selectively hydrogenated linear block copolymer containing at least one block comprising predominantly conjugated diolefin monomer units and at least one block comprising predominantly monoalkenyl arene monomer units, the base polymer having a monoalkenyl arene content of from 15% to 40% by weight, a number average molecular weight in the range from 80,000 to 150,000 as measured by GPC with a polystyrene standard wherein the ethylenic unsaturation of the base polymer has been reduced to less than 20% of the original ethylenic unsaturation by hydrogenation, or a star configuration base polymer which is a hydrogenated homopolymer of a conjugated diene wherein the unsaturation has been reduced to less than 20% of the original unsaturation by hydrogenation, and the number average molecular weight of the arms of the base polymer is in the range from 30,000 to 75,000 as measured by GPC with a polystyrene standard.
5. A process according to Claim 4 wherein the conjugated diolefin is isoprene, and the monoalkenyl arene is styrene.
6. A process according to any one of Claims 1 to 5 wherein the alpha-beta unsaturated carboxylic moiety is maleic anhydride.
7. A process according to any one of Claims 1 to 6 wherein the molar ratio of amine to carboxylic moiety is in the range from 0.1:1 to 2:1.
8. A process according to any one of Claims 1 to 7 wherein the amount of alpha-beta unsaturated carboxylic moiety is sufficient to result in at least on the average one carboxylic functional group per polymer molecule and not more than 5% by weight carboxylic functional groups as percent by weight of the base polymer.
9. A process according to any one of Claims 1 to 8 wherein the amount of amine is sufficient to result in at least on the average one amine group per polymer molecule and not more than 2.0% by weight nitrogen in the aminated polymer.
10. A process for the preparation of a lubricating oil composition which comprises mixing a major proportion of a lubricating oil and a minor proportion of an aminated polymer whenever prepared by a process according to any of Claims 1 to 9.

Patentansprüche

Patentansprüche für folgende Vertragsstaaten : BE, CH, DE, FR, GB, IT, LI, NL, SE

1. Ein Verfahren für die Herstellung eines aminierten Polymerdispersionsmittels zur Verbesserung des Viskositätsindexes, welches die folgenden Schritte umfasst:
 - (a) Herstellen eines funktionalisierten Polymers durch Aufpropfen einer alpha-beta-ungesättigten Carbonsäureeinheit, ausgewählt aus der Gruppe, die sich aus Säuren, Anhydriden und Estern zusammensetzt, auf ein Basispolymer, ausgewählt aus der Gruppe, die sich zusammensetzt aus
 - i) selektiv hydrierten Blockcopolymeren, die einen oder mehrere, überwiegend konjugierte Diolefinmonomereinheiten enthaltende(n) Blöcke/(Block) und einen oder mehrere, überwiegend Monoalkenylarenmonomereinheiten enthaltende(n) Blöcke/(Block) beinhalten, und
 - ii) hydrierte Polymere, die konjugierte Diolefinmonomereinheiten beinhalten, wobei die Funktionalisierung in einer Vorrichtung, die geeignet zum Übertragen beachtlicher mechanischer Energie ist, und in Anwesenheit von 3,0 bis 15 Gewichtsprozent eines Verdünnungsöls, bezogen auf die



Menge an Basispolymer, durchgeführt wird;

- (b) Umsetzen des funktionalisierten Polymers mit einem Amin, um ein aminiertes Polymer zu bilden; und
- (c) Gewinnen des aminierten Polymers.

5

2. Ein Verfahren gemäß Anspruch 1, wobei Schritt (a) in der Anwesenheit eines Radikalinitiators durchgeführt wird, welcher aus der Gruppe ausgewählt ist, die beinhaltet:

2,5-Dimethyl-2,5-bis-(tert.-butylperoxy)-hexan, Ethyl-3,3-Di-(tert.-butylperoxy)-cyclohexan, Di-tert.-butylperoxid, tert.-Butylcumylperoxid, und 1,1-Bis-(tert.-butylperoxy)-3,3,5-trimethylcyclohexan.

10

3. Ein Verfahren gemäß Anspruch 1 oder 2, wobei das Amin Diethylaminopropylamin ist.

15

4. Ein Verfahren gemäß Anspruch 1, 2 oder 3, wobei das Basispolymer ein selektiv hydriertes, unverzweigtes Blockcopolymer ist, das mindestens einen Block beinhaltet, der überwiegend konjugierte Diolefinmonomereinheiten enthält, und mindestens einen Block, der überwiegend Monoalkenylarenmonomereinheiten enthält, wobei das Basispolymer einen Monoalkenylarengengehalt zwischen 15 und 40 Gewichtsprozent und einen zahlengemittelten Molekulargewichtsmittelwert im Bereich von 80 000 und 150 000, wie durch GPC mit einem Polystyrol-Standard gemessen, aufweist, wobei die ethylenische Ungesättigtheit des Basispolymers durch Hydrierung auf weniger als 20 % der ursprünglichen ethylenischen Ungesättigtheit erniedrigt worden ist, oder wobei das Basispolymer ein solches mit Sternkonfiguration ist, welches ein hydriertes Homopolymer eines konjugierten Diens darstellt, wobei die Ungesättigtheit durch Hydrierung auf weniger als 20 % der ursprünglichen Ungesättigtheit erniedrigt worden ist und der zahlengemittelte Molekulargewichtsmittelwert der Arme des Basispolymers im Bereich von 30 000 bis 75 000 liegt, wie durch GPC mit einem Polystyrol-Standard gemessen.

25

5. Ein Verfahren gemäß Anspruch 4, wobei das konjugierte Diolefin Isopren und das Monoalkenylaren Styrol ist.

30

6. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 5, wobei die alpha-beta-ungesättigte Carbonsäureeinheit Maleinsäureanhydrid ist.

7. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 6, wobei das molare Verhältnis von Amin zu Carbonsäureeinheit im Bereich von 0,1:1 bis 2:1 liegt.

35

8. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 7, wobei die Menge an alpha-beta-ungesättigter Carbonsäureeinheit ausreichend ist, um im Durchschnitt mindestens eine funktionelle Carboxylgruppe auf ein Polymermolekül, und, bezogen auf das Gewicht des Basispolymers, nicht mehr als 5 Gewichtsprozent funktionelle Carbonsäuregruppen zu ergeben.

40

9. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 8, wobei die Menge an Amin ausreichend ist, um im Durchschnitt mindestens eine Aminogruppe auf ein Polymermolekül und nicht mehr als 2,0 Gewichtsprozent Stickstoff im aminierten Polymer zu ergeben.

45

10. Eine Schmierölszusammensetzung, welche eine größere Anteilsmenge ein Schmieröls und eine kleinere Anteilsmenge eines aminierten Polymers, soweit es durch ein Verfahren gemäß irgend einem der Ansprüche 1 bis 9 hergestellt wurde, beinhaltet.

Patentansprüche für folgenden Vertragsstaat : ES

50

1. Ein Verfahren für die Herstellung eines aminierten Polymerdispersionsmittels zur Verbesserung des Viskositätsindex, welches die folgenden Schritte umfasst:

(a) Herstellen eines funktionalisierten Polymers durch Aufpropfen einer alpha-beta-ungesättigten Carbonsäureeinheit, ausgewählt aus der Gruppe, die sich aus Säuren, Anhydriden und Estern zusammensetzt, auf ein Basispolymer, ausgewählt aus der Gruppe, die sich zusammensetzt aus

55

i) selektiv hydrierten Blockcopolymeren, die einen oder mehrere, überwiegend konjugierte Diolefinmonomereinheiten enthaltende(n) Blöcke/(Block) und einen oder mehrere, überwiegend Monoalkenylarenmonomereinheiten enthaltende(n) Blöcke/(Block) beinhalten, und



ii) hydrierte Polymere, die konjugierte Diolefinmonomereinheiten beinhalten, wobei die Funktionalisierung in einer Vorrichtung, die geeignet zum Übertragen beachtlicher mechanischer Energie ist, und in Anwesenheit von 3,0 bis 15 Gewichtsprozent eines Verdünnungsöls, bezogen auf die Menge an Basispolymer, durchgeführt wird;

- 5 (b) Umsetzen des funktionalisierten Polymers mit einem Amin, um ein aminiertes Polymer zu bilden; und
(c) Gewinnen des aminierten Polymers.

2. Ein Verfahren gemäß Anspruch 1, wobei Schritt (a) in der Anwesenheit eines Radikalinitiators durchgeführt wird, welcher aus der Gruppe ausgewählt ist, die beinhaltet:
10 2,5-Dimethyl-2,5-bis-(tert.-butylperoxy)-hexan, Ethyl-3,3-di-(tert.-butylperoxy)-cyclohexan, Di-tert.-butylperoxid, tert.-Butylcumylperoxid, und 1,1-Bis-(tert.-butylperoxy)-3,3,5-trimethylcyclohexan.

3. Ein Verfahren gemäß Anspruch 1 oder 2, wobei das Amin Diethylaminopropylamin ist.

4. Ein Verfahren gemäß Anspruch 1, 2 oder 3, wobei das Basispolymer ein selektiv hydriertes, unverzweigtes Blockcopolymer ist, das mindestens einen Block beinhaltet, der überwiegend konjugierte Diolefinmonomereinheiten enthält und mindestens einen Block, der überwiegend Monoalkenylarenmonomereinheiten enthält, wobei das Basispolymer einen Monoalkenylarengesamtgehalt zwischen 15 und 40 Gewichtsprozent und einen zahlengemittelten Molekulargewichtsmittelwert im Bereich von 80 000 und 150 000, wie durch GPC mit einem Polystyrol-Standard gemessen, aufweist, wobei die ethylenische Ungesättigtheit des Basispolymers durch Hydrierung auf weniger als 20 % der ursprünglichen ethylenischen Ungesättigtheit erniedrigt worden ist, oder wobei das Basispolymer ein solches mit Sternkonfiguration ist, welches ein hydriertes Homopolymer eines konjugierten Diens darstellt, wobei die Ungesättigtheit durch Hydrierung auf weniger als 20 % der ursprünglichen Ungesättigtheit erniedrigt worden ist und der zahlengemittelte Molekulargewichtsmittelwert der Arme des Basispolymers im Bereich von 30 000 bis 75 000 liegt, wie durch GPC mit einem Polystyrol-Standard gemessen.

5. Ein Verfahren gemäß Anspruch 4, wobei das konjugierte Diolefin Isopren und das Monoalkenylaren Styrol ist.

6. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 5, wobei die alpha-beta-ungesättigte Carbonsäureeinheit Maleinsäureanhydrid ist.

7. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 6, wobei das molare Verhältnis von Amin zu Carbonsäureeinheit im Bereich von 0,1:1 bis 2:1 liegt.

8. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 7, wobei die Menge an alpha-beta-ungesättigter Carbonsäureeinheit ausreichend ist, um im Durchschnitt mindestens eine funktionelle Carboxylgruppe auf ein Polymermolekül, und, bezogen auf das Gewicht des Basispolymers, nicht mehr als 5 Gewichtsprozent funktionelle Carbonsäuregruppen zu ergeben.

9. Ein Verfahren gemäß irgendeinem der Ansprüche 1 bis 8, wobei die Menge an Amin ausreichend ist, um im Durchschnitt mindestens eine Aminogruppe auf ein Polymermolekül und nicht mehr als 2,0 Gewichtsprozent Stickstoff im aminierten Polymer zu ergeben.

10. Ein Verfahren zur Herstellung einer Schmierölzusammensetzung, welches das Mischen einer größeren Anteilsmenge eines Schmieröls und einer kleineren Anteilsmenge eines aminierten Polymers, soweit es durch ein Verfahren gemäß irgend einem der Ansprüche 1 bis 9 hergestellt wurde, beinhaltet.

Revendications

Revendications pour les Etats contractants suivants : BE, CH, DE, FR, GB, IT, LI, NL, SE

1. Un procédé pour la préparation d'un polymère aminé du type additif dispersant améliorant l'indice de viscosité, comportant les étapes de :

(a) préparer un polymère fonctionnalisé en greffant une partie carboxylique alpha-béta insaturée choisie dans le groupe constitué des acides, des anhydrides et des esters, à un polymère de base choisi dans le groupe constitué de i) des copolymères séquencés sélectivement hydrogénés



- comportant une ou plusieurs séquences renfermant, de façon prédominante, des motifs monomères dioléfiniques conjugués, et un ou plus d'une séquence comportant, de façon prédominante, des motifs monomères du type monoalcényl-arène, et ii) des polymères hydrogénés comportant des motifs monomères dioléfiniques conjugués, la fonctionnalisation étant réalisée dans un dispositif capable de conférer une énergie mécanique élevée et étant mise en oeuvre en présence de 3,0% à 15% en poids, en se basant sur la quantité du polymère de base, d'une huile diluante ;
- (b) réagir le polymère fonctionnalisé avec une amine afin de former un polymère aminé ; et
- (c) récupérer le polymère aminé.
2. Un procédé selon la revendication 1, dans lequel l'étape (a) est mise en oeuvre en présence d'un initiateur de radicaux libres choisis dans le groupe constitué par le 2,5-diméthyl-2,5-bis(tert butyl-peroxy) hexane, le 3,3-di(tert-butyl peroxy)cyclohexane d'éthyle, le peroxyde de di-tert-butyle, le peroxyde de tert-butylcumyle, et le 1,1-bis(tert-butyl-peroxy)-3,3,5-triméthylcyclo-hexane.
 3. Un procédé selon la revendication 1 ou 2, dans lequel l'amine est la diéthyl-aminopropylamine.
 4. Un procédé selon la revendication 1, 2 ou 3, dans lequel le polymère de base est un copolymère séquencé linéaire, sélectivement hydrogéné, renfermant au moins une séquence comportant de façon prédominante des motifs monomères dioléfiniques conjugués et au moins une séquence comportant, de façon prédominante, des motifs monomères du type monoalcényl-arène, le polymère de base présentant une teneur en monoalcényl-arène de 15% à 40% en poids, un poids moléculaire moyen en nombre dans la gamme de 80 000 à 150 000 tel que mesuré par GPC avec un polystyrène normalisé dans lequel l'insaturation éthylénique du polymère de base a été réduite à moins de 20% de l'insaturation éthylénique d'origine par hydrogénation, ou bien un polymère de base à configuration en étoile, qui est un homopolymère hydrogéné d'un diène conjugué dans lequel l'insaturation a été réduite à moins de 20% de l'insaturation d'origine par hydrogénation, et le poids moléculaire moyen en nombre des ramifications du polymère de base se situe dans la gamme de 30 000 à 75 000 tel que mesuré par GPC à l'aide d'un polystyrène normalisé.
 5. Un procédé selon la revendication 4, dans lequel la dioléfine conjuguée est l'isoprène, et le monoalcényl-arène est le styrène.
 6. Un procédé selon l'une quelconque des revendications 1 à 5, dans lequel la partie carboxylique à insaturation alpha-béta est l'anhydride maléique.
 7. Un procédé selon l'une quelconque des revendications 1 à 6 dans lequel le rapport molaire de l'amine à la partie carboxylique se situe dans la gamme de 0,1:1 à 2:1.
 8. Un procédé selon l'une quelconque des revendications 1 à 7, dans lequel la quantité de la partie carboxylique à insaturation alpha-béta est suffisante pour se traduire par au moins un groupe fonctionnel carboxylique en moyenne par molécule polymère et pas plus de 5% en poids de groupes fonctionnels carboxyliques en pourcentage en poids du polymère de base.
 9. Un procédé selon l'une quelconque des revendications 1 à 8, dans lequel la quantité d'amine est suffisante pour se traduire par au moins un groupe aminé en moyenne par molécule de polymère et pas plus de 2,0% en poids d'azote dans le polymère aminé.
 10. Une composition d'huile lubrifiante comportant une proportion prépondérante d'une huile lubrifiante et une proportion plus faible d'un polymère aminé, lorsqu'il est préparé par un procédé selon l'une quelconque des revendications 1 à 9.

Revendications pour l'Etat contractant suivant : ES

1. Un procédé pour la préparation d'un polymère aminé du type additif dispersant améliorant l'indice de viscosité, comportant les étapes de :
 - (a) préparer un polymère fonctionnalisé en greffant une partie carboxylique alpha-béta insaturée choisie dans le groupe constitué des acides, des anhydrides et des esters, à un polymère de base choisi dans le groupe constitué de i) des copolymères séquencés sélectivement hydrogénés



- comportant une ou plusieurs séquences renfermant, de façon prédominante, des motifs monomères dioléfiniques conjugués, et un ou plus d'une séquence comportant, de façon prédominante, des motifs monomères du type monoalcényle-arène, et ii) des polymères hydrogénés comportant des motifs monomères dioléfiniques conjugués, la fonctionnalisation étant réalisée dans un dispositif capable de conférer une énergie mécanique élevée et étant mise en oeuvre en présence de 3,0% à 15% en poids, en se basant sur la quantité du polymère de base, d'une huile diluante ;
- (b) réagir le polymère fonctionnalisé avec une amine afin de former un polymère aminé ; et
- (c) récupérer le polymère aminé.
2. Un procédé selon la revendication 1, dans lequel l'étape (a) est mise en oeuvre en présence d'un initiateur de radicaux libres choisis dans le groupe constitué par le 2,5-diméthyl-2,5-bis(tert butyl-peroxy) hexane, le 3,3-di(tert-butyl peroxy)cyclohexane d'éthyle, le peroxyde de di-tert-butyle, le peroxyde de tert-butylcumyle, et le 1,1-bis(tert-butyl-peroxy)-3,3,5-triméthylcyclo-hexane.
 3. Un procédé selon la revendication 1 ou 2, dans lequel l'amine est la diéthyl-aminopropylamine.
 4. Un procédé selon la revendication 1, 2 ou 3, dans lequel le polymère de base est un copolymère séquencé linéaire, sélectivement hydrogéné, renfermant au moins une séquence comportant de façon prédominante des motifs monomères dioléfiniques conjugués et au moins une séquence comportant, de façon prédominante, des motifs monomères du type monoalcényle-arène, le polymère de base présentant une teneur en monoalcényle-arène de 15% à 40% en poids, un poids moléculaire moyen en nombre dans la gamme de 80 000 à 150 000 tel que mesuré par GPC avec une polystyrène normalisé dans lequel l'insaturation éthylénique du polymère de base a été réduite à moins de 20% de l'insaturation éthylénique d'origine par hydrogénation, ou bien un polymère de base à configuration en étoile, qui est un homopolymère hydrogéné d'un diène conjugué dans lequel l'insaturation a été réduite à moins de 20% de l'insaturation d'origine par hydrogénation, et le poids moléculaire moyen en nombre des ramifications du polymère de base se situe dans la gamme de 30 000 à 75 000 tel que mesuré par GPC à l'aide d'un polystyrène normalisé.
 5. Un procédé selon la revendication 4, dans lequel la dioléfine conjuguée est l'isoprène, et le monoalcényle-arène est le styrène.
 6. Un procédé selon l'une quelconque des revendications 1 à 5, dans lequel la partie carboxylique à insaturation alpha-béta est l'anhydride maléique.
 7. Un procédé selon l'une quelconque des revendications 1 à 6 dans lequel le rapport molaire de l'amine à la partie carboxylique se situe dans la gamme de 0,1:1 à 2:1.
 8. Un procédé selon l'une quelconque des revendications 1 à 7, dans lequel la quantité de la partie carboxylique à insaturation alpha-béta est suffisante pour se traduire par au moins un groupe fonctionnel carboxylique en moyenne par molécule polymère et pas plus de 5% en poids de groupes fonctionnels carboxyliques en pourcentage en poids du polymère de base.
 9. Un procédé selon l'une quelconque des revendications 1 à 8, dans lequel la quantité d'amine est suffisante pour se traduire par au moins un groupe aminé en moyenne par molécule de polymère et pas plus de 2,0% en poids d'azote dans le polymère aminé.
 10. Un procédé pour la préparation d'une composition d'huile lubrifiante, qui comporte le mélange d'une proportion prépondérante d'une huile lubrifiante et d'une proportion plus faible d'un polymère aminé chaque fois qu'il est préparé par un procédé selon l'une quelconque des revendications 1 à 9.