

Description

The invention relates to improvements in the manufacture of alkyl arsines, including branched alkyl arsines and substituted alkyl arsines.

In prior art, alkyl arsines were made by multi-step processes involving the reaction of organometallic compounds or lithium alkyls with inorganic arsenic compounds using oxygenated solvents such as diethyl ether. A disadvantage of such prior art processes was the difficulty of separating alkyl arsine products from impurities, particularly from oxygenated solvents or from other metallic compounds. For use of alkyl arsines as arsenic source instead of arsine in metal organic chemical vapor deposition (MOCVD) processes for manufacture of semiconductor devices, there is a need to provide alkyl arsines of extremely high purity. Metallic impurities or oxygenated organic impurities can be especially detrimental to operation of electronic devices made by MOCVD processes, even when such impurities are present only in very small amounts.

It has been proposed by Gigauri R.D. et al., to conduct a hydroarsenation of crotonaldehyde with a dialkyl arsine. The dialkyl arsine is added to the carbon carbon double bond of crotonaldehyde (Chemical Abstracts, Vol. 96, 1982, 6822y).

According to the present invention, a process is provided comprising synthesis of alkyl arsine or aralkyl arsine by acid catalyzed reaction of an arsine with an olefin or an aryl substituted olefin having at least 3 carbon atoms.

The invention is a method for making alkyl arsines by catalytic reaction of an arsine and an olefin having at least three carbon atoms, without the need for metal-containing reactants or catalysts or solvents which would cause metallic or oxygenated impurities in the product. Thus, alkyl arsine products of very high purity, especially with respect to absence of metal impurities, can be obtained more easily by using the process of the invention.

According to the invention, an olefin in the presence of an acid catalyst reacts with arsine to produce mono and di-substituted arsines or with a mono-hydrocarbon substituted arsine to produce a di-substituted arsine.

Without being bound by theoretical explanation, it is supposed that the acid catalyst causes the olefin reactant to form an intermediate carbonium ion at the ethylenic double bond, which in turn reacts with the arsine reactant to form the alkyl arsine or aralkyl arsine. The carbonium ion intermediate theory is consistent with the observation that arsine does not add to a terminal carbon atom when the alkyl arsine is formed by the process of the invention.

The term olefin as used herein includes hydrocarbons having a single ethylenic double bond such as normal and branched chain aliphatic olefins, cycloaliphatic olefins, and aryl substituted olefins. Olefins containing at least three carbon atoms are used. Olefins containing three to 12 carbon atoms are preferred.

Normal and branched chain aliphatic olefins most preferred for making mono- and di-alkyl arsines according to the invention include, for example, propene, 1-butene, 2-butene, 2-methyl-1-propene (isobutylene), 2-methyl-1-butene, 2,3-dimethyl-1-butene, 2-ethyl-1-butene, 2-methyl-1-pentene, 2,4,4-trimethyl-1-pentene, 1-decene, 1-dodecene, 2,4,4,6,6-pentamethyl-1-heptene.

Cycloaliphatic olefins useful as olefin reactants in the invention include, for example, cyclopentene, cyclohexene, cyclooctene, 2-methylcyclopentene, 2-methylcyclohexene, and the like. Aryl substituted alkyl olefins that can be used include styrene, alpha-methylstyrene, 4-methylstyrene.

The invention is useful for making compounds which are useful as organometallic sources of arsenic to be used in processes comprising metalorganic chemical vapor deposition (MOCVD) in the manufacture of semiconductor devices such as solar cells. Also, the invention is useful for making higher alkyl or aralkyl arsines which are useful as intermediates for making alkyl or aralkyl arsonic acid by oxidation of the alkyl arsine intermediates. Alkylarsonic and aralkylarsonic acids are useful for example as flotation agents in processes for concentration of tin ores.

An arsine and an olefin react by acid catalyzed addition of arsine to olefin at the double bond. When the selected olefin has a terminal ethylenic double bond, as in 1-butene, for example, the arsine adds to the second carbon atom. When an internal olefin or a cyclic olefin is selected, the addition may occur at either of the ethylenic carbon atoms. In the case of addition of arsine to a non-symmetrical internal olefin, such as 2-methyl-2-butene for example, isomeric alkyl arsine products are to be expected.

The acid catalyst may be an organic or inorganic non-oxidizing strong acid such as alkanesulfonic acids, e.g. methanesulfonic acid, ethanesulfonic acid, arylsulfonic acids, e.g. benzenesulfonic acid, toluenesulfonic acid, trifluoroacetic acid, phosphoric acid, sulfuric acid, hydrogen fluoride. Lower alkanesulfonic acids containing 1 to 4 carbon atoms are preferred.

As non-oxidizing strong acid catalysts for the process of the invention we may use solid or liquid acid catalysts in contact with at least the olefin reactant. The acid may be dissolved in the olefin or in solution

with the olefin in a single phase liquid system. For example, the olefin may be dissolved in a hydrocarbon solvent with a hydrocarbon-soluble acid such as octane sulfonic acid or dodecylbenzene sulfonic acid. The single phase liquid is contacted with gaseous arsine under pressure to carry out the reaction.

The acid may be a solid or a liquid which is immiscible with the organic liquid phase containing the olefin reactant. When an immiscible liquid catalyst is used, it may be a liquid non-oxidizing strong acid such as H_3PO_4 or it may be an aqueous solution of a non-oxidizing strong acid.

When a monoalkyl arsine is used as the arsine reactant, that arsine may be in solution with the olefin.

In a preferred embodiment of the invention the reaction is carried out with arsine gas in contact with a liquid which has two immiscible liquid phases. One liquid phase is an aqueous phase which contains the acid catalyst. Arsine is dissolved to some extent in this aqueous phase. The other liquid phase is an organic phase which contains the olefin, and an organic solvent when a solvent is used. To increase the reaction rate the two liquid phases can be mixed efficiently by vigorous agitation as by stirring during the reaction. Use of an organic solvent is preferred as a vehicle for the olefin reactant and as a solvent for the alkyl arsine products. A large amount of the acid catalyst in aqueous solution is used to increase the amount of catalyst in contact with the organic phase during the reaction. To avoid oxidation of arsine reactant and the alkyl or aralkyl arsine products, oxidizing agents are excluded from the reactor.

Use of an inert organic solvent for the olefin reactant and the alkyl arsine products is preferred but not always necessary. Inert hydrocarbons having boiling points above $60^\circ C$ are preferred solvents. Paraffinic hydrocarbons such as the normal and branched alkanes having 6 to 12 carbon atoms are suitable solvents. A solvent having boiling point well apart from those of the monoalkyl and dialkyl arsine products should be selected for ease of product separation.

The addition reaction is preferably carried out under pressure when either reactant is a gas. Reactor pressures in the range from 7 to 70 atmospheres will usually be suitable in such cases. The reactor is conveniently pressurized with arsine when arsine gas is the arsine reactant. It is preferred to use a liquid inert solvent for gaseous olefins. A molar excess of arsine to olefin is maintained during the reaction. Reaction temperatures in the range from about $25^\circ C$ to $100^\circ C$ may be used and a reaction temperature from 60 to $95^\circ C$ is usually preferred.

A convenient reactor for the process of the invention is an autoclave with stirring means for constant agitation of the reaction mixture during the reaction. The time for reaction will depend upon selected reactants and reaction conditions. About four hours is sufficient under the conditions used in the examples described below.

EXAMPLE 1

An autoclave reactor having approximately 3.8 liter capacity is charged with 400 grams of isobutylene reactant, 600 grams of n-octane solvent and 1000 grams of aqueous 70% methanesulfonic acid catalyst. The reactor is pressurized to about 12.3 atmospheres at room temperature by addition of arsine reactant in molar excess with respect to isobutylene. The autoclave is sealed and its contents are heated at $80-95^\circ C$ with constant agitation for four hours reaction time. The contents are then cooled to $8^\circ C$ before the reactor is opened. Unreacted arsine is vented from the reactor. By gas chromatographic analysis of the liquid reaction product mixture, yields of 350 grams mono-1,1-dimethylethylarsine (36.6% yield) and 85 grams bis(1,1-dimethylethyl)arsine (6.3% yield) are measured. The organic phase separated from the liquid product mixture is washed with water, dried and then distilled at $68-69^\circ C$ to separate the mono-1,1-dimethylethylarsine. The bis(dimethylethyl)arsine is separated by further distillation of the reaction product.

EXAMPLES 2 - 8

By the process described in Example 1, except with variations as shown in Table 1, other monoalkyl and dialkyl arsines are synthesized.

TABLE 1

<u>Example</u>	<u>Olefin Reactant</u>	<u>Arsine Reactant</u>	<u>Solvent</u>	<u>Catalyst</u>	<u>Products</u>
1	isobutylene	AsH ₃	n-octane	methanesulfonic acid	mono- and bis(1,1-dimethylethyl)arsines
2	2-methyl-1-butene	AsH ₃	n-octane	methanesulfonic acid	mono- and bis(1,1-dimethylpropyl)arsines
3	2-methyl-1-pentene	AsH ₃	n-decane	ethanesulfonic acid	mono- and bis(1,1-dimethylbutyl)arsines
4	2,4,4-trimethyl-1-pentene	AsH ₃	n-octane	methanesulfonic acid	mono- and bis(1,1,3,3-tetramethylbutyl)arsines
5	2,4,4,6,6-pentamethyl-1-heptene	AsH ₃	dodecane	butanesulfonic acid	mono- and bis(1,1,3,3,5,5-hexamethylhexyl)arsines
6	2-methyl-1-heptene	AsH ₃	n-octane	methanesulfonic acid	mono- and di(1,1-dimethylhexyl)arsines
7	1-decene	AsH ₃	n-octane	ethanesulfonic acid	mono- and di(1-methylnonyl)arsines

TABLE 1 (continued)

<u>Example</u>	<u>Olefin Reactant</u>	<u>Arsine Reactant</u>	<u>Solvent</u>	<u>Catalyst</u>	<u>Products</u>
8	isobutylene	1-methylethyl* arsine	n-octane	methanesulfonic acid	1-methylethyl- 1,1-dimethyl- ethylarsine

* The 1-methylethylarsine reactant is dissolved in the organic liquid phase and the autoclave is operated at autogenic pressure.

Examples of compounds that can be produced by the process of the invention include but are not limited to mono 1-methylethylarsine, mono 1-methylpropylarsine, mono 1,1-dimethylethylarsine, mono 1-methylbutylarsine, mono 1,1-dimethylpropylarsine, mono 1,1-dimethylbutylarsine, mono 1,1-diethylethylarsine, mono 1,1,2-trimethylpropylarsine, mono 1,1,3,3-tetramethylbutylarsine, mono 1-methylheptylarsine, mono 1-methylnonylarsine, mono α -methylbenzylarsine, mono α , α -dimethylbenzylarsine, mono α -methyl(4-methylbenzyl)arsine, bis(1-methylethyl)arsine, bis(1-methylpropyl)arsine, bis(1,1-dimethylethyl)arsine, bis(1-

methylbutyl)arsine, bis(1,1-dimethylpropyl)arsine, bis(1,1-dimethylbutyl)arsine, bis(1,1,3,3-tetramethylbutyl)arsine and bis(α -methylbenzyl)arsine.

In some embodiments of the invention an olefin is reacted with a mono alkylarsine to form dialkylsubstituted arsines. For example, isobutylene is reacted, respectively, with mono 1,1-dimethylethylarsine to form bis(1,1-dimethylethyl)arsine, with mono 1-methylethylarsine to form 1-methylethyl-1,1-dimethylethylarsine, and mono methylarsine to form methyl, 1,1-dimethylethylarsine. Additional examples of dialkyl substituted arsines that may be prepared by such combination of reactants include but are not limited to methyl-1-methylpropylarsine, methyl-1,1-dimethylpropylarsine and 1-methylethyl-1,1-dimethylpropylarsine.

The monoalkyl and dialkyl arsine products obtained by the process of the invention can be readily separated from the liquid reaction product mixture by phase separation and distillation of the organic phase. The very high purity requirements for use of the alkylarsines in MOCVD may require subsequent further purification, which can be readily accomplished by redistillation. Because no metal-containing reactants have been used for the synthesis, there is no need for removal of metals from products made by the process of the invention.

Claims

1. A process for preparing alkyl arsine or aralkyl arsine by acid catalyzed reaction of an arsine with an olefin or an aryl substituted olefin having at least 3 carbon atoms.
2. A process defined by claim 1 wherein the olefin contains 3 to 12 carbon atoms.
3. A process defined by Claim 1 wherein the acid catalyst is a non-oxidizing strong acid catalyst.
4. A process defined by Claim 1 wherein the defined reaction is carried out using a liquid reaction mixture comprising an olefin or substituted olefin and a catalyst in contact with arsine gas under pressure.
5. A process defined by Claim 4 wherein the liquid reaction mixture further comprises an inert liquid solvent for the olefin and the alkyl arsine products.
6. A process defined by Claim 5 wherein the solvent is a hydrocarbon having boiling point above 60 °C.
7. A process defined by Claim 1 wherein the olefin is isobutylene.
8. A process defined by Claim 7 wherein the acid catalyst is a non-oxidizing strong acid catalyst in aqueous medium.
9. A process defined by Claim 8 wherein the strong acid catalyst is an alkanesulfonic acid containing one to four carbon atoms.
10. A process defined by Claim 8 wherein the synthesis is carried out under pressure in the range from 7 to 70 atmospheres and at a reaction temperature in the range from 25 °C to 100 °C.

Patentansprüche

1. Verfahren zur Herstellung von Alkylarsin oder Aralkylarsin durch säurekatalysierte Reaktion eines Arsins mit einem Olefin oder einem Aryl-substituierten Olefin mit mindestens 3 Kohlenstoffatomen.
2. Verfahren nach Anspruch 1, wobei das Olefin 3 bis 12 Kohlenstoffatome enthält.
3. Verfahren nach Anspruch 1, wobei der Säurekatalysator ein nicht oxidierender, starker Säurekatalysator ist.
4. Verfahren nach Anspruch 1, wobei die definierte Reaktion unter Verwendung einer flüssigen Reaktionsmischung ausgeführt wird, umfassend ein Olefin oder substituiertes Olefin und einen Katalysator in Kontakt mit Arsingas unter Druck.



methylbutyl)arsine, bis(1,1-dimethylpropyl)arsine, bis(1,1-dimethylbutyl)arsine, bis(1,1,3,3-tetramethylbutyl)arsine and bis(α -methylbenzyl)arsine.

In some embodiments of the invention an olefin is reacted with a mono alkylarsine to form dialkylsubstituted arsines. For example, isobutylene is reacted, respectively, with mono 1,1-dimethylethylarsine to form bis(1,1-dimethylethyl)arsine, with mono 1-methylethylarsine to form 1-methylethyl-1,1-dimethylethylarsine, and mono methylarsine to form methyl, 1,1-dimethylethylarsine. Additional examples of dialkyl substituted arsines that may be prepared by such combination of reactants include but are not limited to methyl-1-methylpropylarsine, methyl-1,1-dimethylpropylarsine and 1-methylethyl-1,1-dimethylpropylarsine.

The monoalkyl and dialkyl arsine products obtained by the process of the invention can be readily separated from the liquid reaction product mixture by phase separation and distillation of the organic phase. The very high purity requirements for use of the alkylarsines in MOCVD may require subsequent further purification, which can be readily accomplished by redistillation. Because no metal-containing reactants have been used for the synthesis, there is no need for removal of metals from products made by the process of the invention.

Claims

1. A process for preparing alkyl arsine or aralkyl arsine by acid catalyzed reaction of an arsine with an olefin or an aryl substituted olefin having at least 3 carbon atoms.
2. A process defined by claim 1 wherein the olefin contains 3 to 12 carbon atoms.
3. A process defined by Claim 1 wherein the acid catalyst is a non-oxidizing strong acid catalyst.
4. A process defined by Claim 1 wherein the defined reaction is carried out using a liquid reaction mixture comprising an olefin or substituted olefin and a catalyst in contact with arsine gas under pressure.
5. A process defined by Claim 4 wherein the liquid reaction mixture further comprises an inert liquid solvent for the olefin and the alkyl arsine products.
6. A process defined by Claim 5 wherein the solvent is a hydrocarbon having boiling point above 60 °C.
7. A process defined by Claim 1 wherein the olefin is isobutylene.
8. A process defined by Claim 7 wherein the acid catalyst is a non-oxidizing strong acid catalyst in aqueous medium.
9. A process defined by Claim 8 wherein the strong acid catalyst is an alkanesulfonic acid containing one to four carbon atoms.
10. A process defined by Claim 8 wherein the synthesis is carried out under pressure in the range from 7 to 70 atmospheres and at a reaction temperature in the range from 25 °C to 100 °C.

Patentansprüche

1. Verfahren zur Herstellung von Alkylarsin oder Aralkylarsin durch säurekatalysierte Reaktion eines Arsins mit einem Olefin oder einem Aryl-substituierten Olefin mit mindestens 3 Kohlenstoffatomen.
2. Verfahren nach Anspruch 1, wobei das Olefin 3 bis 12 Kohlenstoffatome enthält.
3. Verfahren nach Anspruch 1, wobei der Säurekatalysator ein nicht oxidierender, starker Säurekatalysator ist.
4. Verfahren nach Anspruch 1, wobei die definierte Reaktion unter Verwendung einer flüssigen Reaktionsmischung ausgeführt wird, umfassend ein Olefin oder substituiertes Olefin und einen Katalysator in Kontakt mit Arsingas unter Druck.



5. Verfahren nach Anspruch 4, wobei die flüssige Reaktionsmischung ferner ein inertes flüssiges Lösungsmittel für das Olefin und die Alkylarsinprodukte umfaßt.
6. Verfahren nach Anspruch 5, wobei das Lösungsmittel ein Kohlenwasserstoff mit einem Siedepunkt über 60 °C ist.
7. Verfahren nach Anspruch 1, wobei das Olefin Isobutylene ist.
8. Verfahren nach Anspruch 7, wobei der Säurekatalysator ein nicht oxidierender, starker Säurekatalysator in wässrigem Medium ist.
9. Verfahren nach Anspruch 8, wobei der starke Säurekatalysator eine Alkansulfonsäure ist, die ein bis vier Kohlenstoffatome enthält.
10. Verfahren nach Anspruch 8, wobei die Synthese unter Druck im Bereich von 7 bis 70 Atmosphären und bei einer Reaktionstemperatur im Bereich von 25 °C bis 100 °C durchgeführt wird.

Revendications

1. Procédé de préparation d'alkylarsine ou d'aralkylarsine par réaction, catalysée par un acide, d'une arsine avec une oléfine ou une oléfine aryl-substituée comportant au moins 3 atomes de carbone.
2. Procédé selon la revendication 1, dans lequel l'oléfine contient 3 à 12 atomes de carbone.
3. Procédé selon la revendication 1, dans lequel le catalyseur acide est un catalyseur acide fort non oxydant.
4. Procédé selon la revendication 1, dans lequel la réaction définie est réalisée à l'aide d'un mélange réactionnel liquide comprenant une oléfine ou une oléfine substituée et un catalyseur en contact avec une arsine gazeuse, sous pression.
5. Procédé selon la revendication 4, dans lequel le mélange réactionnel liquide comprend en outre un solvant liquide inerte pour l'oléfine et les produits alkylarsines.
6. Procédé selon la revendication 5, dans lequel le solvant est un hydrocarbure ayant un point d'ébullition supérieur à 60 °C.
7. Procédé selon la revendication 1, dans lequel l'oléfine est l'isobutylène.
8. Procédé selon la revendication 7, dans lequel le catalyseur acide est un catalyseur acide fort non oxydant dans un milieu aqueux.
9. Procédé selon la revendication 8, dans lequel le catalyseur acide fort est un acide alcanesulfonique contenant 1 à 4 atomes de carbone.
10. Procédé selon la revendication 8, dans lequel la synthèse est réalisée sous une pression dans la gamme de 7 à 70 atm et à une température réactionnelle dans la gamme de 25 °C à 100 °C.