POLISHING COMPOSITION AND METHOD FOR HIGH SILICON NITRIDE TO SILICON OXIDE REMOVAL RATE RATIOS

FIELD OF THE INVENTION

[0001] This invention pertains to a polishing composition and a method for polishing a substrate using the same.

BACKGROUND OF THE INVENTION

[0002] As a method for isolating elements of a semiconductor device, a great deal of attention is being directed towards a shallow trench isolation (STI) process where a silicon nitride layer is formed on a silicon substrate, shallow trenches are formed via etching or photolithography, and a dielectric layer is deposited to fill the trenches. Due to variation in the depth of trenches, or lines, formed in this manner, it is typically necessary to deposit an excess of dielectric material on top of the substrate to ensure complete filling of all trenches.

[0003] The excess dielectric material (e.g., an oxide) is then typically removed by a chemical-mechanical planarization process to expose the silicon nitride layer. When the silicon nitride layer is exposed, the largest area of the substrate exposed to the chemical-mechanical polishing system comprises silicon nitride, which must then be polished to achieve a highly planar and uniform surface. Generally, past practice has been to emphasize selectivity for oxide polishing in preference to silicon nitride polishing. Thus, the silicon nitride layer has served as a stopping layer during the chemical-mechanical planarization process, as the overall polishing rate has decreased upon exposure of the silicon nitride layer. Oxide line widths are becoming smaller as etching technology progresses. As oxide lines widths decrease, it is often desirable to utilize polishing systems having selectivity for silicon nitride over oxide polishing, which can minimize defectivity in the oxide lines formed on the substrate surface.

[0004] Compositions and methods for planarizing or polishing the surface of a substrate are well known in the art. Polishing compositions (also known as polishing slurries) typically contain an abrasive material in a liquid carrier and are applied to a surface by contacting the surface with a polishing pad saturated with the polishing composition. Typical abrasive materials include silicon dioxide, cerium oxide, aluminum oxide, zirconium oxide, and tin oxide. U.S. Patent 5,527,423, for example, describes a method for chemically-mechanically polishing a metal layer by contacting the surface with a polishing

slurry comprising high purity fine metal oxide particles in an aqueous medium. Polishing compositions are typically used in conjunction with polishing pads (e.g., a polishing cloth or disk). Suitable polishing pads are described in U.S. Patents 6,062,968, 6,117,000, and 6,126,532, which disclose the use of sintered polyurethane polishing pads having an open-celled porous network, and U.S. Patent 5,489,233, which discloses the use of solid polishing pads having a surface texture or pattern. Instead of or in addition to being suspended in the polishing composition, the abrasive material may be incorporated into the polishing pad. U.S. Patent 5,958,794 discloses a fixed abrasive polishing pad.

[0005] Several chemical-mechanical polishing (CMP) compositions for polishing substrates containing low dielectric constant materials (e.g., oxide) are known. For example, U.S. Patent 6,043,155 discloses a cerium oxide-based slurry for inorganic and organic insulating films, having selectivity for silicon dioxide versus silicon nitride polishing. U.S. Patent Application Publication 2002/0168857 A1 discloses a method for manufacturing a semiconductor device in which silicon dioxide is deposited on a silicon nitride film patterned with trenches, and a two-stage chemical-mechanical polishing process is then performed to selectively remove overlying silicon dioxide, thus leaving trenches filled with silicon dioxide. Thus, there remains a need in the art for polishing compositions and methods having the reverse selectivity, for selectively removing silicon nitride over underlying dielectric components.

[0006] The invention provides such a composition and method. These and other advantages of the invention, as well as additional inventive features, will be apparent from the description of the invention provided herein.

BRIEF SUMMARY OF THE INVENTION

[0007] The present invention provides an improved CMP polishing composition that affords high selectivity for removal of silicon nitride relative to silicon dioxide and polysilicon. A chemical-mechanical polishing (CMP) composition of the present invention has a pH of 7 or less (e.g., a pH in the range of 4 to 7) and comprises a cationic abrasive, a cationic polymer, an inorganic halide salt, and an aqueous carrier.

Preferred cationic abrasives include alumina, titania, zirconia, ceria, and doped silica. Optionally, the composition can include an aminocarboxylic acid.

[0008] Preferred cationic polymers include a cationic homopolymer, a cationic copolymer comprising at least one cationic monomer and at least one nonionic monomer, and a combination thereof. A particularly preferred cationic polymer is a polydiallyldimethylammonium halide.

[0009] Inorganic halide salts useful in the compositions of the invention include alkali metal halides, ammonium halides, and the like. A particularly preferred inorganic halide salt is ammonium chloride.

[0010] Preferably, the composition comprises an amount of cationic abrasive in the range of 0.01 to 5 percent by weight. The cationic polymer preferably is present in the composition in an amount in the range of 0.1 to 500 ppm. The inorganic halide salt is present in the composition in an amount in the range of 100 to 1000 ppm.

[0011] A chemical-mechanical polishing (CMP) method of the present invention comprises contacting a surface of a substrate with a polishing pad and a CMP composition, and causing relative motion between the polishing pad and the substrate with a portion of the CMP composition therebetween to abrade at least a portion of the surface. The CMP composition has a pH of 7 or less and comprises a cationic abrasive, a cationic polymer, an inorganic halide salt, and an aqueous carrier.

[0012] When utilized to polish a surface comprising silicon nitride, silicon dioxide, and polysilicon, the compositions and methods of the present invention selectively abrade silicon nitride from the surface relative to silicon dioxide and polysilicon. For example, silicon nitride can be abraded from the surface at a removal rate in the range of 6 to 60 times the rate at which silicon dioxide is abraded from the surface, and at rates that significantly exceed the removal rate of polysilicon from the surface.

DETAILED DESCRIPTION OF THE INVENTION

[0013] The invention provides a chemical-mechanical polishing composition having a pH of 7 or less and comprising (a) a cationic abrasive, such as ceria, (b) a cationic polymer, which can be a homopolymer or copolymer, (c) an inorganic halide salt, such as an ammonium halide, and (d) an aqueous carrier, such as water. The polishing composition desirably allows for selective removal of silicon nitride in preference to silicon dioxide and/or polysilicon during planarization of substrates comprising silicon nitride, silicon dioxide, and polysilicon.

[0014] The term "cationic abrasive", in the context of the invention, refers to abrasive particles having a positive surface charge at the pH of the polishing composition. The surface charge of an abrasive particle can vary with pH. A desirable cationic abrasive is a cationic metal oxide abrasive. Preferably, the cationic metal oxide abrasive is selected from the group consisting of ceria, alumina, zirconia, titania, doped silica, and mixtures thereof. More preferably, the abrasive is ceria or zirconia. Most preferably, the abrasive is ceria.

[0015] The cationic metal oxide abrasive can be produced by any suitable process. Suitable processes for producing cationic metal oxide abrasive particles useful in the context of the invention include pyrolytic and hydrothermal processes. Fumed metal oxides can be produced from volatile precursors (e.g., metal halides) in a pyrogenic process by hydrolysis and/or oxidation of the precursors in a high temperature flame (H_2/air or H_2/CH_4/air) to produce the metal oxide of interest. Fumed metal oxides can be prepared from nonvolatile precursors by dissolving or dispersing the precursor in a suitable solvent such as water, alcohol, or acid-based solvent. The solution containing the precursor can be sprayed into a high temperature flame using a droplet generator, and the metal oxide can then be collected. Typical droplet generators include bi-fluid atomizers, high-pressure spray nozzles, and ultrasonic atomizers.

[0016] The cationic metal oxide abrasive can be a doped silica, for example, alumina-doped silica. Alumina-doped silicas are generally prepared by a co-fuming process in which mixtures of silicon tetrachloride and aluminum chloride are subjected to vapor phase hydrolysis, thus forming composite particles comprising aluminum oxide and silicon dioxide. Generally, silica particles have a negative, or anionic, surface charge, at a pH above the isoelectric point of the silica particles (e.g., pH 3.5 or higher). The presence of an appropriate second metal oxide (e.g., aluminum oxide) renders the doped silica particles cationic. Desirably, 0.01 wt.% or more (e.g., 0.2 wt.% or more, or 0.3 wt.% or more) of a second metal oxide is present in the doped silica particles. Preferably, 2 wt.% or less (e.g., 1.5 wt.% or less, or 1 wt.% or less) of a second metal oxide is present in the doped silica particles. Examples of alumina-doped silicas are the MOX 80 and MOX 170 products (both containing 1% alumina) available from Degussa.

[0017] As noted above, the cationic metal oxide abrasive can be produced by a hydrothermal process. In a hydrothermal process, a metal salt (e.g., a nitrate) having the same oxidation level as the desired metal oxide is dissolved in water, treated with a base

(e.g., ammonium hydroxide), and subjected to conditions of elevated temperature and pressure. The hydrothermal process results in the conversion of the metal salt into the corresponding metal oxide.

[0018] Alternatively, a metal salt having a lower oxidation level than the desired metal oxide can be used in conjunction with an oxidizing agent in a hydrothermal process. For example, U.S. Patent 5,389,352 discloses a process for preparing cerium oxide, which process comprises forming an aqueous solution comprised of a water-soluble trivalent cerium salt and an oxidizing agent, and then aging the solution as a liquid phase for a time during which the trivalent cerium salt is oxidized to cerium oxide particles.

[0019] Dopants comprising a second metal salt can be added to the first metal salt during a hydrothermal process to produce a doped metal oxide containing the second metal compound. Preferred dopants are selected from the group consisting of nickel, cobalt, manganese, iron, aluminum, chromium, and zinc. Any suitable amount of the second metal salt can be added to the first metal salt during the execution of a hydrothermal process. If a dopant is desired, typically 1 ppm or more (e.g., 10 ppm or more, or 50 ppm or more, or even 100 ppm or more) of a dopant can be added to the first metal salt during a hydrothermal process. Preferably, 10000 ppm or less (e.g., 5000 ppm or less, or 1000 ppm or less, or 500 ppm or less) of a dopant can be added to the first metal salt during a hydrothermal process.

[0020] The cationic abrasive particles desirably have an average particle size (typically, average particle diameter of the smallest spheres encompassing the particles) of at least 10 nm or more (e.g., 10 to 1000 nm). Preferably, the abrasive particles have an average particle size of 50 nm or more (e.g., 50 to 500 nm, or even 50 to 300 nm). More preferably, the abrasive particles have an average particle size of 1000 nm or less (e.g., 800 nm or less, or 500 nm or less, or even 300 nm or less).

[0021] The cationic abrasive can be present in the polishing composition in any suitable amount. The amount of cationic abrasive present in the polishing composition typically is 0.001 wt.% or more (e.g., 0.005 wt.% or more, or 0.01 wt.% or more) based on the weight of the liquid carrier and any components dissolved or suspended therein. The amount of cationic abrasive present in the polishing composition preferably is 5 wt.% or less (e.g., 2 wt.% or less, or 1 wt.% or less) based on the weight of the liquid carrier and any

components dissolved or suspended therein. More preferably, the amount of cationic abrasive present in the polishing composition is 0.01 wt.% to 1 wt.%.

[0022] The abrasive desirably is suspended in the polishing composition, more specifically in the water component of the polishing composition. When the abrasive is suspended in the polishing composition, the abrasive preferably is colloidally stable. The term colloid refers to the suspension of abrasive particles in the liquid carrier. Colloidal stability refers to the maintenance of that suspension over time. In the context of this invention, an abrasive is considered colloidally stable if, when the abrasive is placed into a 100 ml graduated cylinder and allowed to stand without agitation for a time of 2 hours, the difference between the concentration of particles in the bottom 50 ml of the graduated cylinder ([B] in terms of g/ml) and the concentration of particles in the top 50 ml of the graduated cylinder ([T] in terms of g/ml) divided by the initial concentration of particles in the abrasive composition ([C] in terms of g/ml) is less than or equal to 0.5 (i.e., $\{[B] - [T]\}/[C] \leq 0.5$). The value of [B]-[T]/[C] desirably is less than or equal to 0.3, and preferably is less than or equal to 0.1.

[0023] The cationic polymers suitable for use in the compositions and methods of the present invention can be a cationic homopolymer or a cationic copolymer. Without wishing to be bound by any particular theory, it is believed that the cationic polymer is preferentially adsorbed onto the surface of silicon dioxide. The cationic polymer is believed to form a protective film on a silicon dioxide surface to inhibit contact of the polishing composition with the silicon dioxide surface, thereby reducing the removal rate of silicon dioxide while advantageously not significantly affecting the rate of silicon nitride removal.

[0024] The cationic homopolymer can be any suitable cationic homopolymer consisting essentially of cationic monomer repeat units. For example, the cationic polymer can be any suitable cationic polymer consisting essentially of cationic repeat units comprising nitrogen, including but not limited to monomers comprising basic amine groups and quaternized amine groups. The basic amine groups or quaternized amine groups can be acyclic or incorporated into a ring structure. It is also suitable for the cationic polymer to be further modified by alkylation, acylation, ethoxylation, or other chemical reaction, in order to alter the solubility, viscosity, or other physical parameter of the cationic polymer. Preferably, the cationic polymer is selected from the group consisting of polyethyleneimine, ethoxylated polyethyleneimine, polydiallyldimethylammonium halide, poly(amidoamine),

poly(methacryloxyloxyethyltrimethylammonium) chloride, poly(methacryloyloxyethyldimethylbenzylammonium) chloride, poly(vinylpyrrolidone), poly(vinylimidazole), poly(vinylpyridine), and poly(vinylamine). More preferably, the cationic polymer is polyethyleneimine.

[0025] In some embodiments, the cationic polymer can be a cationic homopolymer consisting essentially of monomers comprising sulfonium groups. Sulfonium groups comprise a sulfur atom substituted with three carbon atoms, with the sulfur atom having a positive charge. Non-limiting examples of cationic polymers and cationic monomers comprising sulfonium groups are disclosed in U.S. Patent 4,528,384.

[0026] In other embodiments, the cationic polymer can be a cationic homopolymer consisting essentially of monomers comprising phosphonium groups. Phosphonium groups comprise a phosphorous atom substituted with four carbon atoms, with the phosphorous atom having a positive charge. Non-limiting example of cationic polymers and cationic monomers comprising phosphonium groups are disclosed in U.S. Patent 5,439,617.

[0027] In yet other embodiments, the cationic homopolymer can be a transition metal oligomer having a net positive charge. For example, aluminum compounds can form cationic oligomeric species such as "poly-aluminum chloride," which refers to a class of soluble aluminum products in which aluminum chloride has been partly reacted with base, and which contains some of the highly cationic oligomers of aluminum. Other non-limiting examples of transition metal oligomers are found in, for example, "Comprehensive Organometallic Chemistry II," E. W. Abelm, F. G. A. Stone, and G. Wilkinson, eds., Pergamon Press (1995).

[0028] Alternatively, in some embodiments the cationic polymer can be a copolymer comprising at least one cationic monomer and at least one nonionic monomer, wherein the at least one cationic monomer comprises either more than 50% of the copolymer on a molar basis or 50% or less of the copolymer on a molar basis. The cationic and nonionic monomers can be any suitable cationic and nonionic monomers.

[0029] For example, the cationic monomer can be any suitable cationic monomer(s) comprising nitrogen, including but not limited to monomers comprising basic amine groups and quaternized amine groups. The basic amine groups or quaternized amine groups can be acyclic or can be incorporated into a ring structure. Examples of cationic monomers useful in the context of the invention include but are not limited to ethyleneimine,

diallyldimethylammonium halide, methacryloxyloxyethyltrimethylammonium chloride, methacryloyloxyethyldimethylbenzylammonium chloride, 2-aminoethyl methacrylate, N-(3-aminopropyl)methacrylate, vinylimidazole, vinylpyridine, vinylamine, and amidoamines. The cationic monomers can comprise sulfonium and phosphonium groups. Sulfonium groups and phosphonium groups suitable for incorporation into the copolymers can be as set forth above. Preferably, the cationic monomer is ethyleneimine.

[0030] The nonionic monomer, for example, can be any suitable nonionic monomer(s), including but not limited to ethylene, propylene, ethylene oxide, propylene oxide, styrene, epichlorohydrin, acrylamide, and mixtures thereof.

[0031] The cationic copolymer can be prepared by any suitable technique. For example, the copolymer can be produced by free radical, cationic, anionic, or condensation polymerization. The copolymer can be a random copolymer, alternating copolymer, periodic copolymer, block copolymer (e.g., AB, ABA, ABC, etc.), graft copolymer, or comb copolymer. The cationic copolymer can be further modified by alkylation, acylation, ethoxylation, or other chemical reaction, in order to alter the solubility, viscosity, or other physical parameter of the copolymer.

[0032] The cationic polymer (i.e., cationic homopolymer or copolymer) can have any suitable average molecular weight. Preferably, the cationic polymer will have an average molecular weight of 1,000 Daltons or more (e.g., 5,000 Daltons or more, or 10,000 Daltons or more, or 50,000 Daltons or more, or even 100,000 Daltons or more).

[0033] The amount of cationic polymer in the polishing composition depends on the nature of the cationic polymer. When the cationic polymer is a cationic homopolymer or a cationic copolymer comprising at least one cationic monomer and at least one nonionic monomer, wherein the cationic monomer comprises more than 50% of the cationic copolymer on a molar basis, then the amount of cationic polymer in the polishing composition is 0.1 ppm to 50 ppm based on the total weight of the polishing composition. Typically, the amount of cationic polymer will be 0.5 ppm or more (e.g., 1 ppm or more). Thus, the amount of cationic polymer in the polishing composition can be 0.5 ppm to 45 ppm (e.g., 1 ppm to 40 ppm), or 2 ppm to 35 ppm (e.g., 3 ppm to 30 ppm). When the cationic polymer is a cationic copolymer comprising at least one cationic monomer and at least one nonionic monomer, wherein the cationic monomer comprises 50% or less of the cationic copolymer on a molar basis, the amount of cationic polymer in the polishing

composition can be 0.1 ppm to 200 ppm, based on the total weight of the polishing composition. In such an embodiment, typically the amount of cationic polymer will be 0.1 ppm to 200 ppm (e.g., 5 ppm to 200 ppm), or 10 ppm to 150 ppm (e.g., 20 ppm to 100 ppm). If the amount of the cationic polymer in the polishing composition is too low, then no effect resulting from addition of the cationic polymer is observed. If the amount of the cationic polymer in the polishing composition is too high, then suppression of silicon nitride removal occurs, thus lowering the ratio of silicon nitride removal to that of silicon dioxide removal, as well as reducing the overall polishing rate for the substrate below useful levels.

[0034] The cationic homopolymers and cationic copolymers of the invention provides for similar selectivity for removal of silicon nitride in preference to silicon dioxide in the chemical-mechanical polishing of substrates comprising silicon nitride and silicon oxide. Generally, the use of higher concentrations of the cationic copolymers in polishing compositions is required to achieve similar polishing performance as compared to polishing compositions comprising cationic homopolymers. Despite possible disadvantages of a requirement for use of larger amounts of cationic copolymers as compared to cationic homopolymers in polishing compositions, such as cost and supply requirements, the greater precision achievable in formulation of the polishing compositions having higher concentrations of cationic copolymers during the manufacturing process may be advantageous in some circumstances.

[0035] The polishing composition has a pH of 7 or less (e.g., 6 or less). Preferably, the polishing composition has a pH of 1 or more (e.g., 2 or more, or 3 or more). Even more preferably, the polishing composition has a pH of 4 to 7 (e.g., 4 to 6). The polishing composition optionally comprises pH adjusting agents, for example, potassium hydroxide, ammonium hydroxide, alkylammonium hydroxides, and/or nitric acid. The polishing composition can optionally comprise pH buffering systems, for example, ammonium acetate or disodium citrate. Many such pH buffering systems are well known in the art.

[0036] The polishing compositions of the invention also comprise an inorganic halide salt. Preferred inorganic halide salts include alkali metal halides (e.g., sodium halides and/or potassium halides) and ammonium halides. Preferably, the halides are chlorides, bromides and/or iodides. A particularly preferred halide salt is ammonium chloride.

[0037] Typically, the inorganic halide salts are present in the composition in an amount in the range of 100 to 1000 ppm. In some embodiments, the inorganic halide is present in an amount in the range of 200 to 600 ppm.

[0038] The polishing composition optionally can also include a carboxylic acid, preferably an amino carboxylic acid. Carboxylic acids useful in the polishing composition include monocarboxylic and dicarboxylic acids and their salts. The carboxylic acid can further comprise functional groups selected from the group consisting of hydroxyl, carbonyl, halogen, amine, and nitrogen-containing aromatic heterocycle. Examples of suitable carboxylic acids include acetic acid, propionic acid, butyric acid, benzoic acid, formic acid, malonic acid, succinic acid, tartaric acid, lactic acid, phthalic acid, salicylic acid, anthranilic acid, citric acid, glycolic acid, fumaric acid, lauric acid, pyruvic acid, stearic acid, chloroacetic acid, dichloroacetic acid, 2-pyridinecarboxylic acid, 2-piperidinecarboxylic acid, glycine, alanine, 3-aminopropionic acid, 4-aminobutyric acid, derivatives thereof, salts thereof, and combinations thereof.

[0039] The polishing composition can comprise any suitable amount of the carboxylic acid and when present typically comprises 10 ppm or more (e.g., 10 to 1000 ppm). Preferably, the amount of carboxylic acid present in the polishing composition will be 1000 ppm or less (e.g., 800 ppm or less, or 600 ppm or less).

[0040] It will be appreciated that the aforementioned carboxylic acids can exist in the form of a salt (e.g., a metal salt, an ammonium salt, or the like), an acid, or as a partial salt thereof. For example, tartrates include tartaric acid, as well as mono- and di-salts thereof. Furthermore, carboxylic acids including basic functional groups can exist in the form of an acid salt of the basic functional group. For example, glycines include glycine, as well as monoacid salts thereof. Furthermore, some carboxylic acids can function both as an acid and as a chelating agent (e.g., certain amino acids and the like).

[0041] The carboxylic acid can serve one or more different functions in the polishing composition. The carboxylic acid in conjunction with the cationic polymer can enhance selectivity for removal of silicon nitride in preference to removal of silicon dioxide observed with the use of the inventive polishing composition by suppression of silicon dioxide removal. The carboxylic acid further can buffer the pH of the system and improves the colloidal stability of the polishing composition

[0042] The polishing composition optionally further comprises one or more other additives. Such additives include any suitable surfactant and/or rheological control agent, including viscosity enhancing agents and coagulants (e.g., polymeric rheological control agents, such as, for example, urethane polymers), acrylates comprising one or more acrylic subunits (e.g., vinyl acrylates and styrene acrylates), and polymers, copolymers, and oligomers thereof, and salts thereof. Suitable surfactants include, for example, cationic surfactants, anionic surfactants, anionic polyelectrolytes, nonionic surfactants, amphoteric surfactants, fluorinated surfactants, mixtures thereof, and the like.

[0043] The polishing composition optionally can further comprise a biocide. The biocide can be any suitable biocide, for example an isothiazolinone biocide. The amount of biocide used in the polishing composition typically is 1 ppm to 500 ppm, and preferably is 10 ppm to 200 ppm.

[0044] The polishing composition can be prepared by any suitable technique, many of which are known to those skilled in the art. The polishing composition can be prepared in a batch or continuous process. Generally, the polishing composition can be prepared by combining the components thereof in any order. The term "component" as used herein includes individual ingredients (e.g., acids, bases, etc.) as well as any combination of ingredients (e.g., acids, bases, surfactants, etc.).

[0045] For example, the cationic abrasive can be dispersed in water. The cationic homopolymer or copolymer, inorganic halide salt, and optional carboxylic acid can then be added, and mixed by any method that is capable of incorporating the components into the polishing composition. The polishing composition can be prepared prior to use, with one or more components, such as the cationic homopolymer or copolymer, added to the polishing composition just before use (e.g., within 1 minute before use, or within 1 hour before use, or within 7 days before use). The pH can be adjusted at any suitable time. The polishing composition also can be prepared by mixing the components at the surface of the substrate during the polishing operation.

[0046] The polishing composition also can be provided as a concentrate which is intended to be diluted with an appropriate amount of water prior to use. In such an embodiment, the polishing composition concentrate can comprise a cationic abrasive, a cationic homopolymer or copolymer, a carboxylic acid, and water in amounts such that, upon dilution of the concentrate with an appropriate amount of water, each component of

the polishing composition will be present in the polishing composition in an amount within the appropriate range recited above for each component. For example, the cationic abrasive, a cationic homopolymer or copolymer, and carboxylic acid can each be present in the concentrate in an amount that is 2 times (e.g., 3 times, 4 times, or 5 times) greater than the concentration recited above for each component so that, when the concentrate is diluted with an equal volume of water (e.g., 2 equal volumes water, 3 equal volumes of water, or 4 equal volumes of water, respectively), each component will be present in the polishing composition in an amount within the ranges set forth above for each component. Furthermore, as will be understood by those of ordinary skill in the art, the concentrate can contain an appropriate fraction of the water present in the final polishing composition in order to ensure that the cationic homopolymer or copolymer, optional carboxylic acid, and other suitable additives are at least partially or fully dissolved in the concentrate.

[0047] The invention further provides a method of chemically-mechanically polishing a substrate comprising (i) contacting a substrate with a polishing pad and the polishing composition described herein, and (ii) causing relative motion between the polishing pad and the substrate with a portion of the CMP composition therebetween to abrade at least a portion of the substrate to polish the substrate.

[0048] The method of the invention can be used to polish any suitable substrate, and is especially useful for polishing substrates comprising silicon nitride and silicon dioxide. Suitable substrates include wafers used in the semiconductor industry. The polishing composition is particularly well-suited for planarizing or polishing a substrate that has undergone shallow trench isolation (STI) processing. STI processing typically involves providing a silicon substrate on which is deposited a layer of silicon nitride. Trenches are etched onto a substrate comprising an overlying layer of silicon nitride following photolithography, and an excess of silicon dioxide is deposited thereon. The substrate is then subjected to planarization until the surface layer of silicon nitride is substantially removed, such that the silicon oxide remaining in the trenches is approximately level with the edges of the trenches. Desirably, the planarization or polishing is carried out in STI processing with the polishing composition of the invention, preferably such that the silicon nitride is substantially removed and the silicon dioxide is adequately planarized without excessive erosion of silicon dioxide within the trenches.

[0049] The polishing method of the invention is particularly suited for use in conjunction with a chemical-mechanical polishing apparatus. Typically, the CMP apparatus comprises a platen, which, when in use, is in motion and has a velocity that results from orbital, linear, or circular motion, a polishing pad in contact with the platen and moving with the platen when in motion, and a carrier that holds a substrate to be polished by contacting and moving relative to the surface of the polishing pad. The polishing of the substrate takes place by the substrate being placed in contact with the polishing pad and the polishing composition of the invention and then the polishing pad moving relative to the substrate, so as to abrade at least a portion of the substrate to polish the substrate.

[0050] A substrate can be planarized or polished with the chemical-mechanical polishing composition with any suitable polishing pad (e.g., polishing surface). Suitable polishing pads include, for example, woven and non-woven polishing pads. Moreover, suitable polishing pads can comprise any suitable polymer of varying density, hardness, thickness, compressibility, ability to rebound upon compression, and compression modulus. Suitable polymers include, for example, polyvinylchloride, polyvinylfluoride, nylon, fluorocarbon, polycarbonate, polyester, polyacrylate, polyether, polyethylene, polyamide, polyurethane, polystyrene, polypropylene, coformed products thereof, and mixtures thereof.

[0051] Desirably, the CMP apparatus further comprises an in situ polishing endpoint detection system, many of which are known in the art. Techniques for inspecting and monitoring the polishing process by analyzing light or other radiation reflected from a surface of the workpiece are known in the art. Such methods are described, for example, in U.S. Patent 5,196,353, U.S. Patent 5,433,651, U.S. Patent 5,609,511, U.S. Patent 5,643,046, U.S. Patent 5,658,183, U.S. Patent 5,730,642, U.S. Patent 5,838,447, U.S. Patent 5,872,633, U.S. Patent 5,893,796, U.S. Patent 5,949,927, and U.S. Patent 5,964,643. Desirably, the inspection or monitoring of the progress of the polishing process with respect to a workpiece being polished enables the determination of the polishing end-point, i.e., the determination of when to terminate the polishing process with respect to a particular workpiece.

[0052] The following examples further illustrate the invention but, of course, should not be construed as in any way limiting its scope.

[0053] In the examples below, unless otherwise noted, the polishing runs utilized a 50.8 cm (20 inch) diameter polishing tool with 27.6 kPa (4 psi) downforce pressure of the

substrate against the polishing pad, 60 rpm platen speed, 56 rpm carrier speed, 200 mL/min polishing composition flow rate, and use of in-situ conditioning of a concentric grooved CMP pad.

EXAMPLE 1

[0054] This example shows the effect of increasing amounts of a polyethyleneimine having an average molecular weight of 2000 Daltons on removal rates for silicon nitride and silicon dioxide layers observed with the polishing compositions of the invention.

[0055] Similar silicon nitride layers and silicon dioxide layers were separately polished with six different polishing compositions (Compositions 1A-1F). Each of the compositions comprised 0.4 wt.% ceria and 400 ppm of 4-aminobutyric acid at a pH of 4.9 in water. Composition 1A (control) contained no further ingredients (e.g., no polyethyleneimine). Compositions 1B-1F (invention) further comprised varying amounts of polyethyleneimine as set forth in Table 1. Following use of the polishing compositions, the silicon nitride ("nitride") and silicon dioxide ("oxide") removal rates were determined, and the selectivities, defined as the ratio of the silicon nitride to silicon dioxide removal rates, were calculated. The results are set forth in Table 1.

Table 1: Effect of increasing levels of polyethyleneimine on silicon nitride and silicon dioxide removal rates

Polishing Composition	Polyethyleneimine (ppm)	Nitride Rate (Å/min)	Oxide Rate (Å/min)	Selectivity
1A (control)	None (control)	950	640	1.5
1B (invention)	1	970	310	3.1
1C (invention)	2	930	180	5.2
1D (invention)	4	920	90	10.2
1E (invention)	6	350	60	5.8
1F (invention)	10	24	10	2.4

[0056] As is apparent from the data set forth in Table 1, increasing the amount of polyethyleneimine from none up to 4 ppm resulted in a negligible decrease in the removal rate of silicon nitride, while the removal rate for silicon dioxide decreased by approximately 86%. The selectivity as defined by the ratio of silicon nitride to silicon oxide removal rate increased from 1.5, with no polyethyleneimine present in the polishing composition, to 10.2, with 4 ppm of polyethyleneimine present in the polishing composition. Increasing the amount of polyethyleneimine in the polishing composition to 10 ppm resulted in a

significant reduction in the removal rate for both layers. Thus, the results of this example demonstrate the dependence of silicon nitride and silicon dioxide removal rate on the amount of the cationic polymer in the polishing composition of the invention.

EXAMPLE 2

[0057] This example shows the effect of different cationic polymers on removal rates for silicon nitride and silicon dioxide layers observed with the polishing compositions of the invention.

[0058] Six different polishing compositions were used to separately chemically-mechanically polish similar silicon nitride layers and silicon dioxide layers (Compositions 2A-2F). Each of the compositions comprised 0.4 wt.% ceria and 400 ppm of 4-aminobutyric acid at a pH of 4.9 in water. Composition 2A (control) contained no further ingredients (e.g., no cationic polymer). Composition 2B (invention) additionally contained 8.5 ppm of polyethyleneimine (average molecular weight 25,000 Daltons). Composition 2C (invention) additionally contained 15 ppm of polydiallyldimethylammonium chloride (average molecular weight 60,000 Daltons). Composition 2D (invention) additionally contained 10 ppm of 80% ethoxylated polyethyleneimine (average molecular weight 50,000 Daltons). Composition 2E (invention) additionally contained 25 ppm of polyamidoamine (average molecular weight 1,000,000 Daltons). Following use of the polishing compositions, the silicon nitride ("nitride") and silicon dioxide ("oxide") removal rates were determined, and the selectivities, defined by the ratio of the silicon nitride to silicon dioxide removal rates, were calculated. The results are set forth in Table 2.

Table 2: Effect of different cationic polymers on silicon nitride and silicon dioxide removal rates

Polishing Composition	Nitride Rate (Å/min)	Oxide Rate (Å/min)	Selectivity
2A (control)	1012	558	1.8
2B (invention)	861	33	26
2C (invention)	876	65	13
2D (invention)	1023	85	12
2E (invention)	1200	156	7.7

[0059] As is apparent from the results set forth in Table 2, all of the inventive polishing compositions decreased the removal rate for silicon dioxide compared with the removal rate

for silicon nitride, while maintaining high removal rates for silicon nitride, as compared to the control polishing composition. The use of polyethyleneimine with an average molecular weight of 25,000 Daltons (Polishing Composition 2B) notably reduced the removal rate for silicon dioxide approximately 17 times, while reducing the silicon nitride removal rate only approximately 15%, as compared to the control polishing composition. Thus, the results of this example demonstrate the effects on removal rates for silicon nitride layers and silicon dioxide layers achievable by the polishing composition of the invention.

EXAMPLE 3

[0060] This example shows the effect of cationic polymers comprising different proportions of a cationic monomer and nonionic monomer on removal rates for silicon nitride and silicon dioxide layers observed with the polishing compositions of the invention.

[0061] Five different polishing compositions were used to separately chemically-mechanically polish similar silicon nitride and silicon dioxide layers (Compositions 3A, 3B, 3C, 3D, and 3E). Each of the compositions comprised ceria and copolymers of acrylamide and diallyldimethylammonium chloride ("DADMAC") in water in which the molar fraction of DADMAC units in the copolymers was different. Composition 3A contained 20 ppm of a 5 mole % DADMAC copolymer with acrylamide. Composition 3B contained 20 ppm of a 15 mole % DADMAC copolymer with acrylamide. Composition 3C contained 20 ppm of a 30 mole % DADMAC copolymer with acrylamide. Composition 3D contained 20 ppm of a 100 mole % DADMAC copolymer with acrylamide (i.e., a homopolymer of DADMAC). Composition 3E contained 100 ppm of a 30 mole % DADMAC copolymer with acrylamide. Following use of the polishing compositions, the silicon nitride ("nitride") and silicon dioxide ("oxide") removal rates were determined, and the selectivities, defined as the ratio of the silicon nitride to silicon dioxide removal rates, were calculated. The results are set forth in Table 3.

Table 3: Effect of cationic copolymer of silicon nitride and silicon dioxide removal rates

Polishing Composition	Cationic Polymer Amount (ppm)	Cationic Monomer Mole %	Nitride Rate (Å/min)	Oxide Rate (Å/min)	Selectivity
3A	20	5	1008	2000	0.5
3B	20	15	1005	1732	0.6
3C	20	30	1009	851	1.2
3D	20	100	497	56	8.9
3E	100	30	1032	63	16.4

[0062] As is apparent from the results set forth in Table 3, increasing the molar fraction of cationic monomer in the copolymer from 5 mole % to 30 mole % (Polishing Compositions 3A-3C) resulted in an approximately 2.4-fold reduction in the oxide removal rate, with negligible effect on nitride rate. The use of the same amount of the corresponding cationic homopolymer (Polishing Composition 3D) reduced the removal rate of nitride approximately 2-fold as compared to compositions comprising the cationic copolymers, but improved the selectivity to 8.9. The use of a greater amount (i.e., 100 ppm) of a 30 mole % DADMAC-acrylamide copolymer (Polishing Composition 3E) improved the selectivity ratio to 16.4 with a negligible effect on nitride rate. Thus, the results of this example demonstrate the effects on removal rates for silicon nitride layers and silicon dioxide layers achievable by the polishing composition of the invention.

EXAMPLE 4

[0063] A slurry comprising 0.2 percent by weight ceria, 7.5 ppm of polyDADMAC (weight average molecular weight, M_w, <100,000 Daltons), and 500 ppm of ammonium chloride, in deionized water a pH of 5 was used to separately polish wafers comprising silicon nitride, borophosphorus silicate glass (BPSG), and polycrystalline silicon (polysilicon). The polishing conditions were as follows: 3 psi down force, platen rotation speed of 63 rpm, polishing pad rotation speed of 57 rpm, 100 mL per minute slurry flow rate, on a Mirra CMP apparatus using a standard polyurethane polishing pad, polishing time of 1 minute. The composition afforded a silicon nitride removal rate of 877 Å/min, a polysilicon removal rate of 248 Å/min, and a BPSG removal rate of 3709Å/min. The ratio of silicon nitride removal rate-to-polysilicon removal rate was 3.5:1. These results demonstrate the effectiveness of the CMP compositions of the invention for providing selective removal of silicon nitride relative to polysilicon.

EXAMPLE 5

[0064] A series of slurries comprising 0.2 percent by weight ceria, 10 ppm of polyDADMAC (M_w: <100,000 Daltons), 400 ppm of aminobutyric acid, and amounts of ammonium chloride varying from 0 (comparative) to 500 ppm, in deionized water a pH of 5 were used to separately polish wafers comprising silicon nitride and a silicon dioxide formed from plasma-enhanced tetraethylorthosilicate, (PETEOS). The polishing conditions were as follows: 3.1 psi down force, platen rotation speed of 60 rpm, polishing pad rotation speed of 56 rpm, 150 mL per minute slurry flow rate, on a Logitech CMP apparatus using a standard polyurethane polishing pad, polishing time of 1 minute. The composition afforded a silicon nitride removal rates ranging from 1000 Å/min in the absence of ammonium chloride to 1250 at 500 ppm of ammonium chloride. The corresponding silicon oxide removal rates varied from 140 Å/min to 20 Å/min as ammonium chloride increased from zero to 500 ppm.

EXAMPLE 6

[0065] A slurry comprising 0.2 percent by weight ceria, 10 ppm of polyDADMAC (M_w: 100,000 to 200,000 Daltons), 400 ppm of aminobutyric acid, and 500 ppm of ammonium chloride, in deionized water a pH of 5 was used to polish wafers comprising silicon nitride and polycrystalline silicon (polysilicon). The polishing conditions were as follows: 4 psi down force, platen rotation speed of 75 rpm, polishing pad rotation speed of 68 rpm, 150 mL per minute slurry flow rate, on a Logitech CMP apparatus using a standard polyurethane polishing pad, polishing time of 1 minute. The composition afforded a silicon nitride removal rate of 1370 Å/min and a polysilicon removal rate of 53 Å/min. The ratio of silicon nitride removal rate-to-polysilicon removal rate was 26:1. These results demonstrate the effectiveness of the CMP compositions of the invention for providing selective removal of silicon nitride relative to polysilicon.

CLAIMS

1. A chemical-mechanical polishing (CMP) composition suitable for polishing a substrate comprising silicon, silicon nitride, and silicon dioxide, the composition comprising:

(a) a cationic abrasive;

(b) a cationic polymer;

(c) an inorganic halide salt; and

(d) an aqueous carrier;

the composition having a pH of 7 or less.

2. The composition of claim 1 wherein the cationic abrasive is selected from the group consisting of alumina, titania, zirconia, ceria, and doped silica.

3. The composition of claim 1 wherein the cationic abrasive is ceria.

4. The composition of claim 1 wherein the cationic polymer is selected from the group consisting of a cationic homopolymer, a cationic copolymer comprising at least one cationic monomer and at least one nonionic monomer, and a combination thereof.

5. The composition of claim 1 wherein the cationic polymer is a polydiallyldimethylammonium halide.

6. The composition of claim 1 wherein the inorganic halide salt is ammonium chloride.

7. The composition of claim 1 wherein the cationic abrasive is present in the composition in an amount in the range of 0.01 to 5 percent by weight.

8. The composition of claim 1 wherein the cationic polymer is present in the composition in an amount in the range of 0.1 to 500 ppm.

9. The composition of claim 1 wherein the inorganic halide salt is present in the composition in an amount in the range of 100 to 1000 ppm.

10. The composition of claim 1 wherein the composition has a pH in the range of 4 to 7.

11. The composition of claim 1 wherein the composition further comprises an aminocarboxylic acid.

12. A chemical-mechanical polishing composition suitable for polishing substrates comprising silicon, silicon nitride, and silicon dioxide, the composition comprising:

(a) 0.01 to 1 percent by weight of ceria;

(b) 1 to 20 ppm of a polydiallyldimethylammonium halide;

(c) 100 to 1000 ppm of ammonium chloride; and

(d) an aqueous carrier;

the composition having a pH in the range of 4 to 7.

13. The composition of claim 12 wherein the composition further comprises an amino carboxylic acid.

14. A chemical-mechanical polishing (CMP) method for polishing a substrate, the method comprising the steps of:

(a) contacting a surface of a substrate with a polishing pad and a CMP composition having a pH of 7 or less, the CMP composition comprising a cationic abrasive, a cationic polymer, an inorganic halide salt, an aqueous carrier;

(b) causing relative motion between the polishing pad and the substrate with a portion of the CMP composition therebetween to abrade at least a portion of the surface.

15. The method of claim 14 wherein the cationic abrasive is selected from the group consisting of alumina, titania, zirconia, ceria, and doped silica.

16. The method of claim 14 wherein the cationic polymer is selected from the group consisting of a cationic homopolymer, a cationic copolymer comprising at least one cationic monomer and at least one nonionic monomer, and a combination thereof.

17. The method of claim 14 wherein the cationic abrasive is present in the composition in an amount in the range of 0.01 to 5 percent by weight.

18. The method of claim 14 wherein the cationic polymer is present in the composition in an amount in the range of 0.1 to 500 ppm.

19. The method of claim 14 wherein the inorganic halide salt is present in the composition in an amount in the range of 100 to 1000 ppm.

20. The method of claim 14 wherein the CMP composition further comprises an aminocarboxylic acid.

21. A chemical-mechanical polishing (CMP) method for selectively abrading silicon nitride in the presence of silicon dioxide, the method comprising the steps of:

(a) contacting a surface of a substrate comprising silicon nitride and silicon dioxide with a polishing pad and a CMP composition having a pH of 7 or less, the CMP composition comprising a cationic abrasive, a cationic polymer, an inorganic halide salt, an aqueous carrier;

(b) causing relative motion between the polishing pad and the substrate with a portion of the CMP composition therebetween to abrade silicon nitride from the surface at a removal rate in the range of 6 to 60 times the rate at which silicon dioxide is abraded from the surface.

22. The method of claim 21 wherein the composition further comprises an aminocarboxylic acid.

23. A chemical-mechanical polishing (CMP) method for selectively abrading silicon nitride in the presence of polysilicon, the method comprising the steps of:

(a) contacting a surface of a substrate comprising silicon nitride and polysilicon with a polishing pad and a CMP composition having a pH of 7 or less, the CMP composition comprising a cationic abrasive, a cationic polymer, an inorganic halide salt, an aqueous carrier;

(b) causing relative motion between the polishing pad and the substrate with a portion of the CMP composition therebetween to abrade silicon nitride from the surface at a removal rate exceeding the rate at which polysilicon is abraded from the surface.

24. The method of claim 23 wherein the composition further comprises an aminocarboxylic acid.