CLAIMS

[Claim 1] A coating composition for undercoating, comprising:

an acryl resin; and

an epoxy resin, wherein

the acryl resin has a solubility parameter of 9.0 or more and 12 or less and a weight average molecular weight of 1,000 or more and 95,000 or less, and

wherein the epoxy resin has a solubility parameter of 10 or more and 12 or less and a weight average molecular weight of 250 or more and 2,500 or less, and

wherein a content of the acryl resin is 4 parts by mass or more and 60 parts by mass or less relative to 100 parts by mass of a content of the epoxy resin.

[Claim 2] The coating composition for undercoating according to claim 1, further comprising an amine-type curing agent.

[Claim 3] The coating composition for undercoating according to claim 2, further comprising a curing accelerator, wherein a content of the curing accelerator is 0.1 part by mass or more and 16 parts by mass or less relative to 100 parts by mass of a content of the epoxy resin.

[Claim 4] The coating composition for undercoating according to claim 2, wherein

the coating composition for undercoating is a two-liquid type coating composition for undercoating consisting of a first agent and a second agent,

wherein the first agent contains the acryl resin and the epoxy resin, and

wherein the second agent contains the amine-type curing agent.

[Claim 5] The coating composition for undercoating according to claim 1, further comprising a mica, wherein a content of the mica is 2 parts by mass or more and

95 parts by mass or less relative to 100 parts by mass of a total content of the acryl resin and the epoxy resin.

[Claim 6] A coating film formed from the coating composition for undercoating according to any one of claims 1 to 5.

[Claim 7] A method for forming a coating film, comprising forming an undercoating on a substrate with the coating composition for undercoating according to any one of claims 1 to 5.

[Claim 8] A method for forming a multilayer coating film, comprising:

forming an undercoating film on a substrate with the coating composition for undercoating according to any one of claims 1 to 5; and

forming a finish coating film on the undercoating film with a coating composition for finish coating.

[Claim 9] An article, comprising an undercoating film formed from the coating composition for undercoating according to any one of claims 1 to 5.

[Claim 10] The article according to claim 9, further comprising a finish coating film on the undercoating film.