

ABSTRACT OF THE DISCLOSURE

Monolayer and multilayer polyester film which
comprises at least one layer of a heat-sealing polyester
5 which is crystallizable to the extent of allowing
mixtures thereof to be made with other crystallizable
polyesters for crystallization without sticking is
disclosed. The heat-sealing polyester is polyethylene
terephthalate modified with about 7-15 mol %
10 cyclohexanedimethanol. In multilayered films, another
layer of readily crystallizable polyethylene
terephthalate is used.

15

Figure 1