

SUBSTRATE HAVING A CHARGED ZONE IN AN INSULATING BURIED LAYER

OBJECT OF THE INVENTION

5 The invention relates to a substrate comprising a base wafer, an insulating layer and a top semiconductor layer, that can be used in electronic devices, notably in memories.

BACKGROUND OF THE INVENTION

10 DRAM memory is typically made of one transistor and one capacitor cell (1T1C). While the transistor functions as pass, the capacitor is used for charge storage. The capacitor can be either a trench configuration or a stacked capacitor. A certain novel class of DRAM memories can be comprised of only one transistor, without need for capacitor, and hence is
15 referred to as capacitor-less DRAM, 1T, or 1T-RAM. Such memory types are usually based on Semiconductor on Insulator (SeOI)-like substrates, where the transistor through its floating body characteristics acts as both control transitory and charge storage device. Examples of such type are the "Floating Body Cell" (FBC), or the "zero-capacitor RAM" (zRAM) though other
20 variations exist.

A typical 1T memory is illustrated on Fig. 1.

The SeOI substrate comprises from its base to its top a base wafer 10, an insulating layer 20 and a top semiconductor layer 30, also called "useful layer".

25 The memory device is made of transistors made on the semiconductor useful layer 30. The source S and drain D are made in the useful layer 30, whereas the gate G is deposited on an insulating layer on the useful layer 30.

For certain class of 1T memory that requires back-bias, such as the FBC, an electrode E is also installed on the rear side of the substrate, i.e. on
30 the base wafer.

During operation of the 1T memory, charges (holes) are injected from the channel near the drain region via impact ionization into the body of the transistor. The presence of these positive charges shifts the V_t of the transistor lower and changes the current-voltage characteristics. This shift is
5 used to detect or "read" the state of the cell, being either "1" or "0"

1T memory being a volatile memory, a periodic refresh is carried out in order to restore charge, and hence programming state, to the transistor. Charge is mainly lost through various leakage mechanisms, and the rate of charge loss determines the retention time of the memory cell. If such time is
10 short, extensive refreshing is needed resulting in high power consumption and poor yield. Therefore it is highly desirable to extend the retention time of the cell, i.e., charge retention in the transistor as much as practical. To that end, the rear electrode E can be used to apply a negative voltage in order to keep the charges in the transistor body as long as possible, e.g., near back
15 interface in the 1T design.

However, the installation of the rear electrode requires additional processing and complex circuits that makes it expensive.

There is thus a need for a SeOI like substrate that allows increasing the retention time of the 1T memories, at a lower cost.

20

SUMMARY OF THE INVENTION

A first object of the invention is a substrate comprising successively a base wafer, an insulating layer and a top semiconductor layer, characterised in that the insulating layer comprises at least a zone wherein the density of
25 charges is in absolute value higher than 10^{10} charges/cm².

By "zone" is meant here either the whole insulating layer itself, or a layer forming part of the insulating layer, or discrete islands embedded in the insulating layer.

According to a first embodiment of the invention, the insulating layer is made of a material chosen among the group consisting of silicon oxide, silicon nitride or high k materials.

According to a second embodiment, the insulating layer comprises a charge confining layer between two diffusion barrier layers, wherein the charge confining layer has a density of charges in absolute value higher than 10^{10} charges/cm². Preferably, the charge confining layer is made of silicon nitride and the diffusion barrier layers are made of silicon oxide. Alternatively, the charge confining layer is made of silicon oxide and the diffusion barrier layers are made of silicon nitride.

According to a third embodiment of the invention, the insulating layer comprises charge trapping islands, wherein the charge trapping islands have a total density of charges in absolute value higher than 10^{10} charges/cm². The insulating layer is advantageously made of silicon oxide and the charge trapping islands are made of silicon.

The charges comprised in the insulating layer are preferably at least partially provided by ions. A first possibility is that the density of charges is negative and the ions are chosen among the group consisting of fluorine and chlorine ions. A second possibility is that the density of charges is positive and the ions are chosen among the group consisting of boron and phosphor ions.

A second object of the invention is a semiconductor structure comprising a 1TRAM memory, comprising a floating body region on an insulating layer, wherein the insulating layer comprises a zone exhibiting a density of charges in absolute value higher than 10^{10} charges/cm².

A third object of the invention relates to a process for manufacturing a substrate comprising successively a base wafer, an insulating layer and a top semiconductor layer, characterized in that it includes the step of charging at least a zone of the insulating layer so that said zone exhibits a density of charges in absolute value higher than 10^{10} charges/cm².

According to a first embodiment of the process, the charging step comprises doping the insulating layer.

According to another embodiment, the charging step comprises implanting ions in the insulating layer through the top semiconductor layer.

5 Alternatively, the process comprises the steps of:

- forming the insulating layer on the base wafer or on a donor wafer,
- bonding the base wafer and the donor wafer, the insulating layer being at the interface,

and the charging step is carried out before the bonding step.

10 The charging step may comprise an electron bombardment of the insulating layer, or a plasma treatment of the insulating layer.

Alternatively, the step of forming the insulating layer comprises forming a first diffusion barrier layer, a charge confining layer and a second diffusion barrier layers.

15 The charging step can comprise a plasma activation of the charge confining layer.

In a variant, the charging step comprises growing a doped charge confining layer, wherein the dopant is chosen among the group consisting of boron, phosphor, chlorine and fluorine, and the concentration of the dopant is
20 higher than $10^{10}/\text{cm}^2$.

The charge confining layer is preferably made of silicon nitride and the diffusion barrier layers are made of silicon oxide.

According to another embodiment of the invention, the process comprises, prior to the bonding step, forming charge trapping islands in the
25 insulating layer. For instance, the charge trapping islands are made of silicon.

A fourth object of the invention is a process for charging the insulating layer of a substrate comprising successively a base substrate, an insulating layer and a top semiconductor layer, characterized in that the insulating layer
30 comprises atomic species with a density higher than 10^{10} atoms/ cm^2 , wherein

the atomic species are able to change into ions under injection of charges carriers into the insulating layer.

BRIEF DESCRIPTION OF THE DRAWINGS

5 Other characteristics, objects, and advantages of the invention will appear clearer in reading the description below, which is illustrated by the following figures:

- Figure 1 shows a 1T memory according to the prior art;
- Figure 2 illustrates the steps for making a SeOI substrate with the
10 SmartCut™ process;
- Figure 3 illustrates a first embodiment of the SeOI-like substrate according to the invention;
- Figure 4 illustrates a second embodiment;
- Figure 5 illustrates a third embodiment of the invention.

15

DETAILED DESCRIPTION OF THE INVENTION

The general idea of the invention is to replace the rear electrode with a charge located in the SeOI-like structure, under the interface between the useful layer and the insulating layer. A negatively charged insulating layer
20 plays the same role as the rear electrode, i.e. creating a negative voltage in the SeOI structure for retaining the holes near the insulating layer.

Conversely, a positively charged insulating layer is able to retain electrons, in certain types of 1TRAM which utilize PMOS transistors and hence electron charge.

25 Standard structure

A standard substrate of the SeOI type is provided. Such a structure comprises a base wafer 1, an insulating layer 2 and a top layer 3.

The base wafer 1 can be made of a bulk or composite material.

The insulating layer 2 is made of a material having electrically insulating properties. By "insulating layer" is meant in this text a single layer or a stack of different materials having dielectric properties.

The insulating layer 2 is usually an oxide, such as silicon oxide (SiO_2).
5 In this case, it is usually called "BOX" (Buried Oxide layer).

The insulating layer 2 can also be made of silicon nitride, an oxide-nitride combination, or of a "high k" material, such as hafnium oxide.

The thickness of the insulating layer is typically comprised between 10 and 5000 angstroms.

10 The top semiconductor layer 3, also called "useful" or "active" layer, is made of a semiconductor material, such as silicon.

Such a SeOI substrate can be made by a Smart Cut™ process, or by any other possible process.

The Smart Cut™ process is described in detail in US patent 5,374,564.
15 Referring to Fig. 2, it typically comprises the following steps:

- a) Providing a base wafer 1 and a donor wafer 4 made of a semiconductor material;
- b) Oxidizing one or both of the wafers – preferably the donor wafer 4, thus creating the insulating layer 2 on the donor wafer 4;
- 20 c) Implanting ions in the donor wafer in order to create a weakness zone 40 at a depth corresponding to the thickness of the active layer 3;
- d) Bonding the donor wafer 4 to the base wafer 1 with the insulating layer 2 at the interface;
- e) Splitting the donor wafer according to the weakness zone 40, thus
25 transferring the top layer 3 to the base wafer 1.

The insulating layer 2 has a density of charges in absolute value higher than 10^{10} charges/cm², for example higher than 10^{11} charges/cm².

This charge can be measured using a pseudo-MOS technique or mercury-FET measurement.

The density of charges is positive when the charges are positive (such as holes); the density of charges is negative when the charges are negative (such as electrons).

5 It must be noted that the buried oxide layer in a conventional SeOI-like substrate is usually slightly charged but this charge is minimized in order to avoid electrical losses in the base wafer, as explained for example in application US2006/0166451.

10 In the following description, it is assumed that the charges that have to be retained near the insulating layer are holes (i.e. positive) and thus that the insulating layer has to be negatively charged. Other retention modes such as in the transistor body or near the top channel can benefit from similar approach.

However, the invention applies conversely to the problem of retaining electrons near the insulating layer using a positively charged insulating layer.

15 First embodiment – Charged BOX layer

In this embodiment, the charged zone is the insulating layer itself.

The insulating layer is preferably made of silicon oxide: it can thus be called "BOX".

20 Referring to Fig. 3, the charged BOX layer 2 typically comprises ions such as chlorine or fluorine.

If the BOX layer 2 is intended to be positively charged, it comprises ions such as boron or phosphor.

Provided that the process targets a full activation of the ions, the density of ions is similar to the density of charges.

25 The ions can be spread uniformly within the BOX layer.

Alternatively, they can be concentrated around a determined depth inside the BOX layer.

30 The ions can be implanted in the insulating layer after forming the SeOI substrate (through the top layer 3), or before the bonding of the donor wafer and the base wafer.

During the implantation step, ions are implanted inside the insulating layer. The skilled person is able to adjust the parameters of implantation (namely dose and energy of the ions) in order to obtain an implantation profile with a maximum concentration at a determined depth, inside the
5 insulating layer.

Implant energies can be in the range of 1 keV to 300 keV, for example 10keV-100keV, and dose can be in the range of 10^{13} to 10^{17} atoms/cm².

Typically one type of species is implanted, but more than one can be used if specific chemical compounds are needed.

10 Alternatively, a plasma treatment can be carried out on the insulating layer 2 before bonding the donor and the base wafer.

The conditions of such a plasma treatment are typically: a power between 300 W and 1kW, for instance 535 W, a pressure between 10 and 500 mT, typically about 50 mT, a flow from 100 to 300 sccm, preferably
15 about 200 sccm, a temperature comprised between 23 and 30°C, preferably 27°C, and a process time from 3 to 60 seconds, typically about 30 seconds.

Alternatively, electron bombardment of the layer 2, in the configuration where it is a surface layer of a wafer, directly before bonding, can impart negative charge to this layer 2.

20 Second embodiment – The charged zone is a charge confining layer between diffusion barrier layer(s)

In reference to Fig. 3, the SeOI substrate can advantageously comprise an insulating layer 2 comprised of a charge confining layer 5, confined on one or both sides with diffusion barrier layers 6 made of a material that is
25 able to prevent the diffusion of ions or charges within the substrate.

To prevent diffusion and hence dissipation of the charge, both top and bottom barrier layers are needed.

For instance, a charge confining layer 5 made of silicon oxide is between two barrier layers 6 made of silicon nitride. This configuration is
30 particularly useful when the negative ions are fluorine, which diffuse in SiO₂.

Alternatively, the charge confining layer 5 may be made of silicon nitride and the barrier layers 6 are made of silicon oxide.

This structure can be made by constructing the charge confining layer 5, and barrier layers 6, prior to bonding, on either donor or base wafer.

5 The insulating layer 2 can be constructed fully on one wafer before bonding, by depositing successively a first barrier layer 6, the charge confining layer 5, and the second barrier layer 6.

10 Alternatively, a first barrier layer 6 and the charge confining layer 5 can be deposited on one of the wafers, the second barrier layer being deposited on the other wafer. The wafers are then bonded with the charge confining layer 5 at the interface.

The implication of either arrangement is the use of oxide-to-silicon bonding versus oxide-to-oxide bonding.

15 The barrier layers 6 can be made by thin film deposition such as LPCVD or PECVD with thicknesses in the range of 10 to 500 angstroms.

The charge confining layer 5 is preferably formed, prior to bonding, by plasma activation of a layer deposited on a barrier layer.

20 Alternatively, the charge confining layer 5 can be formed by depositing a doped layer of oxide or nitride on a wafer having a deposited insulating layer (namely the first barrier layer 6), by a technique such as LPCVD (low pressure chemical vapor deposition), or PECVD (plasma enhanced chemical vapor deposition), prior to bonding to a second wafer with a top insulating layer (namely the second barrier layer 6).

25 The charged doped layer 5 is thus embedded in the two insulating layers 6.

The dopant is chosen among boron, phosphor, chlorine and fluorine, with a dopant concentration higher than $10^{10}/\text{cm}^2$, for example higher than $10^{11}/\text{cm}^2$.

30 The thickness of the charge confining layer can be on order of 10 to 1000 angstroms.

The stack 6, 5, 6 of Fig. 4 is also known as "ONO" ("Oxide Nitride Oxide"). It is for instance used in certain type of 1T memory, named "SOONO" (Silicon On ONO), and also in non-volatile flash memories; however in this case this stack is not a buried insulating layer but a floating-gate insulating layer and it is not charged.

Third embodiment – The charged zone consists of embedded charge trapping islands

As compared to the second embodiment where the charge is uniformly distributed in the charge confining layer 5, in this third embodiment, the charge is localized in islands 7 embedded in the insulating layer 2. This configuration is shown in Fig. 4.

The islands 7 can be formed by implantation of the desired ion, such as chlorine or fluorine, into the insulating layer 2 with some critical dose which may be followed by anneal during which precipitation and formation of nuclei of the Si-F (for example) phase is formed.

This implantation step can be carried out before or after bonding, and implies the same doses as in the first embodiment.

Alternatively, silicon can be implanted in an insulating layer made of SiO₂ or Si₃N₄, thus forming charge trapping islands made of silicon.

Also, growth of a doped charge layer followed by annealing is more suitable due to control of dopant concentration directly through thin film deposition.

If the islands 7 are not charged while they are formed, they can be charged later. For example, it is possible to inject electrons in the islands, either applying a high voltage to the structure or bombarding it with electrons.

Another possibility is to implant ions in the islands.

Fourth embodiment – Ferroelectric material

According to a fourth embodiment of the invention, the insulating layer of the SeOI substrate comprises a ferroelectric material, such as oxides of lead and zirconium and/or titan Pb(Zr_xTi_{1-x})O₃ with x between 0 and 1.

Alternatively, the insulating layer is made of a stack of such ferroelectric materials.

Indeed, ferroelectric materials have the property of exhibiting a spontaneous dipole moment and hence to create a permanent electric field in the substrate.

The electric field must be oriented such as to accumulate holes at the interface between the insulating layer and the top layer.

Fifth embodiment – Electrically active defects in the insulating layer

Another possibility is to create electrically active defects in or at the insulating layer, for instance defects resulting in a charge density of interface traps (DIT) between the insulating layer and the adjacent layer.

Following the fabrication of the structure of the substrate, additional electrical charge may be injected into the insulating layer – for instance, by implantation, or by applying an electrical field by means of electrode plates put into close contact with the substrate. The charge may thus be trapped by the atomic species, which become ions according to the above example. Such charge injection may, for instance, be applied in order to tune the charge level.

In principle, such a SeOI substrate is expected to have a permanent density of charges during the whole life duration of the FBC memory.

However, it must be noted that, depending on the techniques used, the charges in the insulating layer might be dissipated, for example during the fabrication of the transistor on the SeOI substrate.

Indeed, the fabrication process involves thermal treatments at higher temperature – typically at 600°C or more – such that the charges are dissipated.

In such a case also, charge injection as described above may be used for tuning the charge level and, for example restore the initial charge level.

For example, the atomic species that had been implanted into the insulating layer may become neutral, but remain in the insulating layer.

The insulating layer thus keeps a feature (i.e. the presence of atomic species) that distinguishes it from the known SeOI substrates, and is able to
5 be charged again, after the fabrication of the transistor.

The SeOI substrate with a charged insulating layer that has been described above can be used for making a 1TRAM memory. To that end, the source and drain of the transistor are made in the top semiconductor layer, whereas the gate is deposited on an insulating layer on the top
10 semiconductor layer.

If necessary, i.e. if the charges of the insulating layer have been dissipating during the fabrication of the transistor, a step of charging again the insulating layer can be carried out.

This 1T device then comprises an insulating layer whose density of
15 charges is substantially permanent during the whole lifetime of the device.

Also, the charged insulating layer and the SeOI substrate are generally provided before the devices are formed in the top layer, but it is also possible, for instance in case of 3D integration of devices, to first form the
20 device in an initial substrate and then form the SeOI substrate of the invention by transferring a top portion of this initial substrate onto a base wafer, the charged insulating layer being positioned in-between.

The SeOI substrate with a charged insulating layer that has been
25 described above can also be used for other type of applications, like for instance as a substrate for receiving or comprising image sensor devices. As mentioned in US5227313, for such application it is usual to dope, for instance with boron, the top layer of a SeOI substrate in order to form electrical potential that will drive the photogenerated charges toward the
30 sensor itself. But the formation of appropriate boron concentration profile

across the thickness of the top layer could be problematic. For instance, it should take into account diffusion of the dopant that will occur during the sensor devices manufacturing steps that involve exposure of the substrate to relatively high temperature. This problem could be advantageously solved by

5 replacing the boron doping or completing a reduced boron doping of the top layer by the charged insulating layer according to the invention. In that case, the type of charge would be selected to drive away the photogenerated charges from the top layer/insulating layer interface toward the active elements of the image sensor devices. In "Backside lighting" applications, the

10 base wafer of the SeOI substrate could be selected to be transparent (e.g. made of glass or quartz); or it can be eliminated after the formation of the sensor devices, as described in US5244817.

CLAIMS

1. Substrate comprising successively a base wafer (1), an insulating layer (2) and a top semiconductor layer (3), **characterised** in that the
5 insulating layer (2) comprises at least a zone wherein the density of charges is in absolute value higher than 10^{10} charges/cm².
2. Substrate according to claim 1, characterized in that the insulating layer (2) is made of a material chosen among the group consisting of silicon oxide, silicon nitride or high k materials.
- 10 3. Substrate according to claim 1, characterized in that the insulating layer (2) comprises a charge confining layer (5) between two diffusion barrier layers (6), wherein the charge confining layer (5) has a density of charges in absolute value higher than 10^{10} charges/cm².
4. Substrate according to the preceding claim, characterized in that
15 the charge confining layer (5) is made of silicon nitride and the diffusion barrier layers are made of silicon oxide.
5. Substrate according to claim 3, characterized in that the charge confining layer (5) is made of silicon oxide and the diffusion barrier layers (6) are made of silicon nitride.
- 20 6. Substrate according to claim 1, characterized in that the insulating layer (2) comprises charge trapping islands (7), wherein the charge trapping islands (7) have a total density of charges in absolute value higher than 10^{10} charges/cm².
7. Substrate according to claim 6, characterized in that the insulating
25 layer (2) is made of silicon oxide and the charge trapping islands (7) are made of silicon.
8. Substrate according to one of claims 1 to 7, characterized in that the charges are at least partially provided by ions.

9. Substrate according to claim 8, characterized in that the density of charges is negative and the ions are chosen among the group consisting of fluorine and chlorine ions.

10. Substrate according to claim 8, characterized in that the density of charges is positive and the ions are chosen among the group consisting of boron and phosphor ions.

11. Semiconductor structure comprising a 1TRAM memory, comprising a floating body region on an insulating layer (2), **characterized** in that the insulating layer (2) comprises a zone exhibiting a density of charges in absolute value higher than 10^{10} charges/cm².

12. Process for manufacturing a substrate comprising successively a base wafer (1), an insulating layer (2) and a top semiconductor layer (3), **characterized** in that it includes the step of charging at least a zone of the insulating layer (2) so that said zone exhibits a density of charges in absolute value higher than 10^{10} charges/cm².

13. Process according to claim 12, characterized in that the charging step comprises doping the insulating layer (2).

14. Process according to claim 12, characterized in that the charging step comprises implanting ions in the insulating layer (2) through the top semiconductor layer (3).

15. Process according to claim 12, characterized in that it comprises:

- forming the insulating layer (2) on the base wafer (1) or on a donor wafer (4)

- bonding the base wafer (1) and the donor wafer (4), the insulating layer (2) being at the interface,

and in that the charging step is carried out before the bonding step.

16. Process according to claim 15, characterized in that the charging step comprises an electron bombardment of the insulating layer (2).

17. Process according to claim 15, characterized in that the charging step comprises a plasma treatment of the insulating layer (2).

18. Process according to claim 15, characterized in that the step of forming the insulating layer (2) comprises forming a first diffusion barrier layer (6), a charge confining layer (5) and a second diffusion barrier layers (6).

5 19. Process according to claim 18, characterized in that the charging step comprises a plasma activation of the charge confining layer (5).

20. Process according to claim 18, characterized in that the charging step comprises growing a doped charge confining layer (5), wherein the dopant is chosen among the group consisting of boron, phosphor, chlorine
10 and fluorine, and the concentration of the dopant is higher than $10^{10}/\text{cm}^2$.

21. Process according to one of claims 18 to 20, characterized in that the charge confining layer (5) is made of silicon nitride and the diffusion barrier layers (6) are made of silicon oxide.

22. Process according to claim 15, characterized in that it comprises,
15 prior to the bonding step, forming charge trapping islands (7) in the insulating layer (2).

23. Process according to claim 22, characterized in that the charge trapping islands (7) are made of silicon.

24. Process for charging the insulating layer (2) of a substrate
20 comprising successively a base substrate (1), an insulating layer (2) and a top semiconductor layer (3), **characterized** in that the insulating layer (2) comprises atomic species with a density higher than 10^{10} atoms/cm², wherein the atomic species are able to change into ions under injection of charges carriers into the insulating layer (2).