

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 March 2006 (23.03.2006)

PCT

(10) International Publication Number
WO 2006/030029 A1

(51) International Patent Classification:

C08G 18/38 (2006.01) **C09D 175/04** (2006.01)
C08G 18/50 (2006.01)

(21) International Application Number:

PCT/EP2005/054628

(22) International Filing Date:

16 September 2005 (16.09.2005)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

04077582.7 17 September 2004 (17.09.2004) EP

(71) Applicant (for all designated States except US): **Akzo Nobel Coatings International B.V.** [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **STAPPERS, Franciscus Hubertus Maria** [NL/NL]; Riemsdijkstraat 86, Wageningen, NL-6701 BC (NL). **VAN DIJK, Joseph Theodorus Maria** [NL/NL]; Lage Morsweg 19, Leiden, NL-2332 XA (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COATING COMPOSITION BASED ON THIOL-NCO CURING

(57) Abstract: Coating composition comprising one or more polythiols and one or more polyisocyanates and a latent base catalyst which is activatable by moisture, wherein the equivalence ratio NCO : SH is between 1 :2 and 2:1. The latent catalyst is selected from the group of oxazolidine, aldimine, ketimine, and enamine. The latent catalyst is present in an amount of up to 20% relative to the weight of the curable material. The composition further comprises one or more photoinitiators in an amount of up to 4% relative to the weight of the curable material.



WO 2006/030029 A1