

ABSTRACT

This supporting sheet has a substrate, and an adhesive layer laminated to the substrate, wherein the surface roughness (Ra) of the surface of the substrate on the side on which the adhesive layer is provided is 0.4 μm or less, and the surface roughness (Ra) of the surface of the substrate on the opposite side from the side on which the adhesive layer is provided is greater than the surface roughness of the surface on the side on which the adhesive layer is provided, and is from 0.053 to 0.48 μm . A composite sheet for protective film formation includes this supporting sheet, and also has a film for protective film formation provided on the adhesive layer in the supporting sheet.