



- (51) **International Patent Classification:** Not classified
- (21) **International Application Number:**  
PCT/US2013/052677
- (22) **International Filing Date:**  
30 July 2013 (30.07.2013)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**  
2012-170999 1 August 2012 (01.08.2012) JP
- (71) **Applicant:** 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).
- (72) **Inventors; and**
- (71) **Applicants :** UEDA, Saori [JP/JP]; 6-7-29 Kitashinagawa, Shinagawa-ku, Tokyo 141-8684 (JP). SUGIYAMA, Naota [JP/JP]; 6-7-29 Kitashinagawa, Shinagawa-ku, Tokyo 141-8684 (JP). TAKAMATSU, Yorinobu [JP/JP]; 6-7-29 Kitashinagawa, Shinagawa-ku, Tokyo 141-8684 (JP).
- (74) **Agents:** LOWN, Jean A., et al.; 3M Center Office of Intellectual Property Counsel Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).


(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

**Published:**

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) **Title:** ANTI-SMUDGE HARD COAT AND ANTI-SMUDGE HARD COAT PRECURSOR



**Fig. 1**

(57) **Abstract:** A hard coat including a nanoparticle mixture and a binder, the nanoparticles constituting from 40 to 95 mass% of an entire mass of the hard coat; from 10 to 50 mass% of the nanoparticles having an average particle size within a range of 2 to 200 nm; from 50 to 90 mass% of the nanoparticles having an average particle size within a range of 60 to 400 nm; a ratio of the average particle size of nanoparticles having an average particle size within the range of 60 to 400 nm to the average particle size of nanoparticles having an average particle size within the range of 2 to 200 nm being within a range of 2:1 to 200:1; and the binder including a polyfunctional fluorinated (meth)acrylic compound, a reaction product thereof, or a combination thereof. The polyfunctional fluorinated (meth)acrylic compound comprises cyclic siloxane units. The particle size distribution of the nanoparticles is bimodal or multimodal.