What is claimed is:

1. A non-aqueous dispersion comprising a continuous phase and a dispersed phase, wherein the dispersed phase comprises a dispersion polymerization reaction product prepared from a reaction mixture comprising an ethylenically unsaturated monomer, an acrylic polymer stabilizer, and an aliphatic polyester stabilized seed polymer, wherein the acrylic polymer stabilizer comprises 75 weight % or greater (meth)acrylic monomer.

2. The non-aqueous dispersion of Claim 1, wherein the acrylic polymer stabilizer comprises 90 weight % or greater (meth)acrylic monomer.

3. The non-aqueous dispersion of either of Claims 1 or 2, wherein the acrylic polymer stabilizer comprises 95 weight % or greater (meth)acrylic monomer.

4. The non-aqueous dispersion of any one of Claims 1 to 3, wherein the acrylic polymer stabilizer is nonlinear.

5. The non-aqueous dispersion of any one of Claims 1 to 4, wherein the polyester has a carbon to oxygen ratio of 4:1 to 20:1.

6. The non-aqueous dispersion of any one of Claims 1 to 5, wherein the polyester comprises poly-12-hydroxystearic acid.

7. The non-aqueous dispersion of any one of Claims 1 to 6, wherein the polyester has a weight average molecular weight of 10,000 to 30,000.

8. The non-aqueous dispersion of any one of Claims 1 to 7, wherein the continuous phase is substantially free of volatile organic compounds.

9. The non-aqueous dispersion of any one of Claims 1 to 8, wherein the continuous phase comprises a reactive diluent.

10. The non-aqueous dispersion of any one of Claims 1 to 9, wherein the particles have an average particle size of 180 nm or less.

11. The non-aqueous dispersion of any one of Claims 1 to 10, wherein said non-aqueous dispersion does not form seeds when subjected to the seed test.

12. A coating comprising the non-aqueous dispersion of any one of Claims 1 to 11.