THE USE OF MILL-DRYING AND DEAGGLOMERATION TO PRODUCE THERMALLY STABLE ALUMINUM TRIHYDROXIDE PARTICLES FROM AN ATH-CONTAINING SLURRY

FIELD OF THE INVENTION

[0001] The present invention relates to the production of mineral flame retardants. More particularly the present invention relates to a novel process for the production of aluminum hydroxide flame retardants having improved thermal stability.

BACKGROUND OF THE INVENTION

[0002] Aluminum hydroxide has a variety of alternative names such as aluminum hydrate, aluminum trihydrate etc., but is commonly referred to as ATH. ATH particles, finds many uses as a filler in many materials such as, for example, papers, resins, rubber, plastics etc. These products find use in diverse commercial applications such as cable and wire sheaths, conveyor belts, thermoplastics moldings, adhesives, etc. ATH is typically used to improve the flame retardancy of such materials and also acts as a smoke suppressant. ATH also commonly finds use as a flame retardant in resins used to fabricate printed wiring circuit boards. Thus, the thermal stability of the ATH is a quality closely monitored by end users. For example, in printed circuit board applications, the thermal stability of the laminates used in constructing the boards must be sufficiently high to allow lead free soldering.

[0003] Methods for the synthesis and production of ATH are well known in the art. However, the demand for tailor made ATH grades is increasing, and the current processes are not capable of producing all of these grades. Thus, as the demand for tailor made ATH grades increases, the demand for processes to produce these grades is also increasing.

SUMMARY OF THE INVENTION

[0004] While empirical evidence indicates that the thermal stability of an ATH is linked to the total soda content of the ATH, the inventors hereof have discovered and believe, while not wishing to be bound by theory, that the improved thermal stability of the ATH of the present invention is linked to the non-soluble soda content, which is typically in the range of from about 70 to about 99wt.%, based on the weight of the total soda, of the total soda content, with the remainder being soluble soda.

[0005] The inventors hereof also believe, while not wishing to be bound by theory, that the wettability of ATH particles with resins depends on the morphology of the ATH particles, and the inventors hereof have unexpectedly discovered that by using the process of the present invention, ATH particles having an improved wettability in relation to ATH particles currently available can be produced. While not wishing to be bound by theory, the inventors

hereof believe that this improved wettability is attributable to an improvement in the morphology of the ATH particles produced by the process disclosed herein.

[0006] The inventors hereof further believe, while not wishing to be bound by theory, believe that this improved morphology is attributable to the total specific pore volume and/or the median pore radius ("r_{50}") of the ATH product particles. The inventors hereof believe that, for a given polymer molecule, an ATH product having a higher structured aggregate contains more and bigger pores and seems to be more difficult to wet, leading to difficulties (higher variations of the power draw on the motor) during compounding in kneaders like Buss Ko-kneaders or twin-screw extruders or other machines known in the art and used to this purpose. Therefore, the inventors hereof have discovered that an ATH filler characterized by smaller median pore sizes and/or lower total pore volumes correlates with an improved wetting with polymeric materials and thus results in improved compounding behavior, i.e. less variations of the power draw of the engines (motors) of compounding machines used to compound a flame retarded resin containing the ATH filler. The inventors hereof have discovered that the process of the present invention is especially well-suited for producing an ATH having these characteristics.

[0007] Thus, the present invention relates to a process comprising mill-drying a slurry to produce mill-dried ATH particles comprising agglomerates, and then deagglomerating said mill-dried ATH particles to produce ATH product particles. In this embodiment, the slurry typically contains in the range of from about 1 to about 85 wt.%, based on the total weight of the slurry, ATH particles, and the mill-drying and deagglomeration is conducted under conditions effective at producing ATH product particles have a median pore radius ("r_{50}"), i.e. a pore radius at 50% of the relative specific pore volume, in the range of from about 0.09 to about 0.33μm and the electrical conductivity of the ATH product particles is less than about 200 μS/cm, measured in water at 10wt.% of the ATH in water.

[0008] In another embodiment, the present invention relates to process comprising mill-drying slurry to produce mill dried ATH, and then deagglomerating said mill-dried ATH particles to produce ATH product particles. In this embodiment, the ATH product particles so produced have a V_{max}, i.e. maximum specific pore volume at about 1000 bar, in the range of from about 300 to about 700 mm^3/g and/or an r_{50}, i.e. a pore radius at 50% of the relative specific pore volume, in the range of from about 0.09 to about 0.33μm, and one or more, preferably two or more, and more preferably three or more, in some embodiments all, of the following characteristics: i) a d_{50} of from about 0.5 to about 2.5 μm; ii) a total soda content of less than about 0.4wt.%, based on the total weight of the ATH product particles; iii) an oil

absorption of less than about 50%, as determined by ISO 787-5:1980; and iv) a specific surface area (BET) as determined by DIN-66132 of from about 1 to about 15 m^2/g, wherein the electrical conductivity of the ATH product particles is less than about 200 μS/cm, measured in water at 10wt.% of the ATH in water.

[0009] The ATH product particles produced by the present invention are useful as flame retardants, sometimes referred to as flame retardant fillers or simply filler or fillers, in a variety of flame retarded resin formulations.

[0010] In some embodiments, the ATH product particles of the present invention are further characterized as having a soluble soda content of less than about 0.1 wt.%.

DETAILED DESCRIPTION OF THE INVENTION

[0011] It should be noted that all particle diameter measurements, i.e. d_{50}, disclosed herein were measured by laser diffraction using a Cilas 1064 L laser spectrometer from Quantachrome. Generally, the procedure used herein to measure the d_{50}, can be practiced by first introducing a suitable water-dispersant solution (preparation see below) into the sample-preparation vessel of the apparatus. The standard measurement called "Particle Expert" is then selected, the measurement model "Range 1" is also selected, and apparatus-internal parameters, which apply to the expected particle size distribution, are then chosen. It should be noted that during the measurements the sample is typically exposed to ultrasound for about 60 seconds during the dispersion and during the measurement. After a background measurement has taken place, from about 75 to about 100 mg of the sample to be analyzed is placed in the sample vessel with the water/dispersant solution and the measurement started. The water/dispersant solution can be prepared by first preparing a concentrate from 500 g Calgon, available from KMF Laborchemie, with 3 liters of CAL Polysalt, available from BASF. This solution is made up to 10 liters with deionized water. 100 ml of this original 10 liters is taken and in turn diluted further to 10 liters with deionized water, and this final solution is used as the water-dispersant solution described above.

Slurry

[0012] In some embodiments of the present invention a slurry, containing ATH particles is mill-dried to produce mill-dried ATH particles that are subsequently subjected to a deagglomeration treatment. The slurry used in the practice of the present invention typically contains in the range of from about 1 to about 85wt.% ATH particles, based on the total weight of the slurry. In preferred embodiments, the slurry contains in the range of from about 25 to about 70 wt.% ATH particles, more preferably in the range of from about 55 to about 65 wt.% ATH particles, both on the same basis. In other preferred embodiments, the slurry

contains in the range of from about 40 to about 60 wt.% ATH particles, more preferably in the range of from about 45 to about 55 wt.% ATH particles, both on the same basis. In still other preferred embodiments, the slurry contains in the range of from about 25 to about 50 wt.% ATH particles, more preferably in the range of from about 30 to about 45 wt.% ATH particles, both on the same basis.

[0013] The slurry used in the practice of the present invention can be obtained from any process used to produce ATH particles. Preferably the slurry is obtained from a process that involves producing ATH particles through precipitation and filtration. In an exemplary embodiment, the slurry is obtained from a process that comprises dissolving crude aluminum hydroxide in caustic soda to form a sodium aluminate liquor, which is cooled and filtered thus forming a sodium aluminate liquor useful in this exemplary embodiment. The sodium aluminate liquor thus produced typically has a molar ratio of Na_2O to Al_2O_3 in the range of from about 1.4:1 to about 1.55:1. In order to precipitate ATH particles from the sodium aluminate liquor, ATH seed particles are added to the sodium aluminate liquor in an amount in the range of from about 1 g of ATH seed particles per liter of sodium aluminate liquor to about 3 g of ATH seed particles per liter of sodium aluminate liquor thus forming a process mixture. The ATH seed particles are added to the sodium aluminate liquor when the sodium aluminate liquor is at a liquor temperature of from about 45 to about 80°C. After the addition of the ATH seed particles, the process mixture is stirred for about 100 h or alternatively until the molar ratio of Na_2O to Al_2O_3 is in the range of from about 2.2 : 1 to about 3.5 : 1, thus forming an ATH suspension. The obtained ATH suspension typically comprises from about 80 to about 160 g/l ATH, based on the suspension. However, the ATH concentration can be varied to fall within the ranges described above. The obtained ATH suspension is then filtered and washed to remove impurities therefrom, thus forming a filter cake. The filter cake can be washed one, or in some embodiments more than one, times with water, preferably de-salted water. The filter cake can be re-slurried with water to form a slurry, or in another preferred embodiment, at least one, preferably only one, dispersing agent is added to the filter cake to form a slurry having an ATH concentration in the above-described ranges. It should be noted that it is also within the scope of the present invention to re-slurry the filter cake with a combination of water and a dispersing agent. Non-limiting examples of dispersing agents suitable for use herein include polyacrylates, organic acids, naphtalensulfonate / formaldehyde condensate, fatty-alcohol-polyglycol-ether, polypropylene-ethylenoxid, polyglycol-ester, polyamine- ethylenoxid, phosphate, polyvinylalcohole. If the slurry comprises a dispersing agent, the slurry may contain up to

about 85 wt.% ATH, based on the total weight of the slurry, because of the effects of the dispersing agent. In this embodiment, the remainder of the slurry (i.e. not including the ATH particles and the dispersing agent(s)) is typically water, although some reagents, contaminants, etc. may be present from precipitation.

ATH Particles in the Slurry

[0014] In some embodiments, the BET of the ATH particles in the slurry is in the range of from about 1.0 to about 4.0 m^2/g. In these embodiments, it is preferred that the ATH particles in the slurry have a BET in the range of from about 1.5 to about 2.5 m^2/g. In these embodiments, the ATH particles in the slurry can also be, and preferably are, characterized by a d_{50} in the range of from about 1.8 to about 3.5 μm, preferably in the range of from about 1.8 to about 2.5 μm, which is coarser than the ATH product particles produced herein.

[0015] In other embodiments, the BET of the ATH particles in the slurry is in the range of from about 4.0 to about 8.0 m^2/g, preferably in the range of from about 5 to about 7 m^2/g. In these embodiments, the ATH particles in the slurry can also be, and preferably are, characterized by a d_{50} in the range of from about 1.5 to about 2.5 μm, preferably in the range of from about 1.6 to about 2.0 μm, which is coarser than the ATH product particles produced herein.

[0016] In still other embodiments, the BET of the ATH particles in the slurry is in the range of from about 8.0 to about 14 m^2/g, preferably in the range of from about 9 to about 12 m^2/g. In these embodiments, the ATH particles in the slurry can also be, and preferably are, characterized by a d_{50} in the range of from about 1.5 to about 2.0 μm, preferably in the range of from about 1.5 to about 1.8 μm, which is coarser than the ATH product particles produced herein.

[0017] By coarser than the ATH product particles, it is meant that the upper limit of the d_{50} value of the ATH particles in the slurry is generally at least about 0.2 μm higher than the upper limit of the d_{50} of the ATH product particles produced herein.

[0018] The ATH particles in the slurry used in the present invention can also be characterized, and preferably are characterized by, a total soda content of less than about 0.2 wt.%, based on the ATH particles in the slurry. In preferred embodiments, if the soluble soda content is a characteristic of the ATH particles, the total soda content is less than 0.18 wt.%, more preferably less than 0.12 wt.%, based on the total weight of the ATH particles in the slurry. The total soda content of the ATH can be measured by using a flame photometer M7DC from Dr. Bruno Lange GmbH, Düsseldorf/Germany. In the present invention, the total soda content of the ATH particles was measured by first adding 1 g of ATH particles

into a quartz glass bowl, then adding 3 ml of concentrated sulfuric acid to the quartz glass bowl, and carefully agitating the contents of the glass bowl with a glass rod. The mixture is then observed, and if the ATH-crystals do not completely dissolve, another 3 ml of concentrated sulfuric acid is added and the contents mixed again. The bowl is then heated on a heating plate until the excess sulfuric acid is completely evaporated. The contents of the quartz glass bowl are then cooled to about room temperature, and about 50 ml of deionized water is added to dissolve any salts in the bowl. The contents of the bowl are then maintained at increased temperature for about 20 minutes until the salts are dissolved. The contents of the glass bowl are then cooled to about 20°C, transferred into a 500 ml measuring flask, which is then filled up with deionized water and homogenized by shaking. The solution in the 500 ml measuring flask is then analyzed with the flame photometer for total soda content of the ATH particles.

[0019] The ATH particles in the slurry used in the present invention can also be characterized, and preferably are characterized by, a soluble soda content of less than about 0.1 wt.%, based on the ATH particles in the slurry. In other embodiments, the ATH particles can be further characterized as having a soluble soda content in the range of from greater than about 0.001 to about 0.1 wt.%, in some embodiments in the range of from about 0.02 to about 0.1 wt.%, both based on the ATH particles in the slurry. While in other embodiments, the ATH particles can be further characterized as having a soluble soda content in the range of from about 0.001 to less than 0.04 wt%, based on the ATH particles in the slurry, in some embodiments in the range of from about 0.001 to less than 0.03 wt%, in other embodiments in the range of from about 0.001 to less than 0.02 wt%, all on the same basis. The soluble soda content is measured via flame photometry. To measure the soluble soda content, a solution of the sample was prepared as follows: 20 g of the sample are transferred into a 1000 ml measuring flask and leached out with about 250 ml of deionized water for about 45 minutes on a water bath at approx. 95°C. The flask is then cooled to 20°C, filled to the calibration mark with deionized water, and homogenized by shaking. After settling of the sample, a clear solution forms in the flask neck, and, with the help of a filtration syringe or by using a centrifuge, as much of the solution as needed for the measurement in the flame photometer can be removed from the flask.

[0020] The ATH particles in the slurry used in the practice of the present invention can also be described as having a non-soluble soda content, as described herein, in the range of from about 70 to about 99.8% of the total soda content, with the remainder being soluble soda. The inventors hereof have unexpectedly discovered that the thermal stability of an ATH is

linked to the soda content of the ATH. While empirical evidence indicates that the thermal stability is linked to the total soda content of the ATH, the inventors hereof, while not wishing to be bound by theory, believe that the improved thermal stability of the ATH particles produced by the process of the present invention is linked to the non-soluble soda content, which is typically in the range of from about 70 to about 99.8wt.% of the total soda content, with the remainder being soluble soda. In some embodiments of the present invention, the total soda content of the ATH particles in the slurry used in the practice of the present invention is typically in the range of less than about 0.20wt.%, based on the ATH particles in the slurry, preferably in the range of less than about 0.18wt.%, more preferably in the range of less than about 0.12wt.%, both on the same basis. In other embodiments of the present invention, the total soda content of the ATH particles in the slurry used in the practice of the present invention is typically in the range of less than about 0.30wt.%, based on the ATH particles in the slurry, preferably in the range of less than about 0.25wt.%, more preferably in the range of less than about 0.20wt.%, both on the same basis. In still other embodiments of the present invention, the total soda content of the ATH particles in the slurry used in the practice of the present invention is typically in the range of less than about 0.40wt.%, based on the ATH particles in the slurry, preferably in the range of less than about 0.30wt.%, more preferably in the range of less than about 0.25wt.%, both on the same basis.

Mill-Drying

[0021] As discussed above, the present invention involves mill-drying a slurry to produce mill-dried ATH particles, wherein the ATH particles in the slurry have specific properties, as described above. "Mill-drying" and "mill-dried" as used herein, it is meant that the slurry is dried in a turbulent hot air-stream in a mill-drying unit. The mill-drying unit comprises a rotor that is firmly mounted on a solid shaft that rotates at a high circumferential speed. The rotational movement in connection with a high air through-put converts the through-flowing hot air into extremely fast air vortices which take up the mixture to be dried, i.e. the slurry, accelerate it, and distribute and dry the mixture thus producing mill-dried ATH particles. After having been dried completely, the mill-dried ATH particles are transported via the turbulent air out of the mill and preferably separated from the hot air and vapors by using conventional filter systems. In another embodiment of the present invention, after having been dried completely, the mill-dried ATH particles are transported via the turbulent air through an air classifier which is integrated into the mill, and are then transported via the turbulent air out of the mill and separated from the hot air and vapors by using conventional filter systems.

[0022] The throughput of the hot air used to dry the slurry is typically greater than about 3,000 Bm^3/h, preferably greater than about to about 5,000 Bm^3/h, more preferably from about 3,000 Bm^3/h to about 40,000 Bm^3/h, and most preferably from about 5,000 Bm^3/h to about 30,000 Bm^3/h.

[0023] In order to achieve throughputs this high, the rotor of the mill-drying unit typically has a circumferential speed of greater than about 40 m/sec, preferably greater than about 60 m/sec, more preferably greater than 70 m/sec, and most preferably in a range of about 70 m/sec to about 140 m/sec. The high rotational speed of the motor and high throughput of hot air results in the hot air stream having a Reynolds number greater than about 3,000.

[0024] The temperature of the hot air stream used to mill dry the slurry is generally greater than about 150°C, preferably greater than about 270°C. In a more preferred embodiment, the temperature of the hot air stream is in the range of from about 150°C to about 550°C, most preferably in the range of from about 270°C to about 500°C.

[0025] In preferred embodiments, the mill-drying of the slurry produces mill-dried ATH particles that have a larger BET specific surface area, as determined by DIN-66132, then the starting ATH particles in the slurry. Typically, the BET of the mill-dried ATH are more than about 10% greater than the ATH particles in the slurry. Preferably the BET of the mill-dried ATH is in the range of from about 10% to about 40% greater than the ATH particles in the slurry. More preferably the BET of the mill-dried ATH particles is in the range of from about 10% to about 25% greater than the ATH particles in the slurry.

[0026] The mill-dried ATH particles thus produced can be used "as is" in many applications. However, in some embodiments, the mill-dried ATH particles are further processed to reduce, or in some embodiments eliminate, agglomerates. The formation of agglomerates is common in ATH particle production processes, and their presence can, and in some applications does, deleteriously affect the performance of the ATH particles in a resin. Therefore, the reduction, preferably elimination, of agglomerates is highly desired by ATH producers.

[0027] In the practice of the present invention, the number of agglomerates, or degree of agglomeration, present in the mill-dried ATH particles are reduced by subjecting the mill-dried ATH particles to a deagglomeration treatment.

DEAGGLOMERATION

[0028] By deagglomeration, it is meant that the mill-dried ATH particles are subjected to a further treatment wherein the number of agglomerates, or degree of agglomeration, present in the mill-dried ATH particles are reduced (i.e. the number of agglomerates present in the mill-

dried ATH particles is greater than the number of agglomerates present in the ATH product particles), in some embodiments substantially eliminated, with little reduction in the particle size of the mill-dried ATH. By "little particle size reduction" it is meant that the d_{50} of the ATH product particles is greater than or equal to 90% of the mill-dried ATH particles. In preferred embodiments, the d_{50} of the dry-milled ATH is in the range of from about 90% to about 95% of the mill-dried ATH particles, more preferably within the range of from about 95% to about 99% of the mill-dried ATH particles.

[0029] In the practice of the present invention, the number of agglomerates, or degree of agglomeration, in the mill-dried ATH particles is reduced by using air classifiers or pin mills. Air classifiers suitable for use herein include those using gravitational forces, centrifugal forces, inertial forces, or any combination thereof, to classify the ATH product particles. The use of these classifiers is well known in the art, and one having ordinary skill in the art and knowledge of the final product size can readily select classifiers containing suitable screens and/or sieves.

[0030] Pin Mills suitable for use herein include dry and wet pin mills. As with air classifiers, the use of pin mills is well known in the art, and one having ordinary skill in the art and knowledge of the final ATH product particles properties can readily select the best pin mill to fit a particular application.

[0031] The deagglomeration of the mill-dried ATH is conducted under conditions effective at producing ATH product particles, discussed below.

ATH Product Particles According to the Present Invention

[0032] In general, the process of the present invention produces ATH product particles that are generally characterized as having a specific total specific pore volume and/or median pore radius ("r_{50}") in addition to one or more, preferably two or more, and more preferably three or more, in some embodiments all, of the following characteristics: i) a d_{50} of from about 0.5 to about 2.5 μm; ii) a total soda content of less than about 0.4wt.%, based on the total weight of the ATH product particles; iii) an oil absorption of less than about 50%, as determined by ISO 787-5:1980; and iv) a specific surface area (BET) as determined by DIN-66132 of from about 1 to about 15 m^2/g, wherein the electrical conductivity of the ATH product particles is less than about 200 μS/cm, measured in water at 10wt.% of the ATH in water.

[0033] As stated above, the inventors hereof believe that, for a given polymer molecule, ATH particles having a higher structured aggregate contain more and bigger pores and seems to be more difficult to wet, leading to difficulties (higher variations of the power draw on the motor) during compounding in kneaders like Buss Ko-kneaders or twin-screw extruders or

other machines known in the art and used to this purpose. The inventors hereof have discovered that the process of the present invention is especially suited for producing ATH product particles characterized by smaller median pore sizes and/or lower total pore volumes, which correlates with an improved wetting with polymeric materials and thus results in improved compounding behavior, i.e. less variations of the power draw of the engines (motors) of compounding machines used to compound a flame retarded resin containing the ATH filler.

[0034] The r_{50} and the specific pore volume at about 1000 bar ("V_{max}") of the ATH product particles can be derived from mercury porosimetry. The theory of mercury porosimetry is based on the physical principle that a non-reactive, non-wetting liquid will not penetrate pores until sufficient pressure is applied to force its entrance. Thus, the higher the pressure necessary for the liquid to enter the pores, the smaller the pore size. A smaller pore size and/or a lower total specific pore volume were found to correlate to better wettability of the ATH product particles. The pore size of the ATH product particles produced herein can be calculated from data derived from mercury porosimetry using a Porosimeter 2000 from Carlo Erba Strumentazione, Italy. According to the manual of the Porosimeter 2000, the following equation is used to calculate the pore radius r from the measured pressure p: $r = -2 \gamma \cos(\theta)/p$; wherein θ is the wetting angle and γ is the surface tension. The measurements taken herein used a value of 141.3° for θ and γ was set to 480 dyn/cm.

[0035] In order to improve the repeatability of the measurements, the pore size of the mill-dried ATH particles was calculated from the second ATH intrusion test run, as described in the manual of the Porosimeter 2000. The second test run was used because the inventors observed that an amount of mercury having the volume V_0 remains in the sample of the mill-dried ATH particles after extrusion, i.e. after release of the pressure to ambient pressure. Thus, the r_{50} can be derived from this data as explained below.

[0036] In the first test run, a sample of ATH product particles produced by the process of the present invention was prepared as described in the manual of the Porosimeter 2000, and the pore volume was measured as a function of the applied intrusion pressure p using a maximum pressure of 1000 bar. The pressure was released and allowed to reach ambient pressure upon completion of the first test run. A second intrusion test run (according to the manual of the Porosimeter 2000) utilizing the same ATH product particle sample, unadulterated, from the first test run was performed, where the measurement of the specific pore volume V(p) of the second test run takes the volume V_0 as a new starting volume, which is then set to zero for the second test run.

[0037] In the second intrusion test run, the measurement of the specific pore volume V(p) of the sample was again performed as a function of the applied intrusion pressure using a maximum pressure of 1000 bar. The pore volume at about 1000 bar, i.e. the maximum pressure used in the measurement, is referred to as V_{max} herein.

[0038] From the second ATH product particle intrusion test run, the pore radius r was calculated by the Porosimeter 2000 according to the formula $r = -2 \gamma \cos(\theta)/p$; wherein θ is the wetting angle, γ is the surface tension and p the intrusion pressure. For all r-measurements taken herein, a value of 141.3° for θ was used and γ was set to 480 dyn/cm. If desired, the specific pore volume can be plotted against the pore radius r for a graphical depiction of the results generated. The pore radius at 50% of the relative specific pore volume, by definition, is called median pore radius r_{50} herein.

[0039] For a graphical representation of r_{50} and V_{max}, please see United States Provisional Patent Applications 60/818,632; 60/818,633; 60/818,670; 60/815,515; and 60/818,426, which are all incorporated herein in their entirety.

[0040] The procedure described above was repeated using samples of ATH product particles produced by the process of the present invention, and the ATH product particles thus produced were found to have an r_{50}, i.e. a pore radius at 50% of the relative specific pore volume, in the range of from about 0.09 to about 0.33μm. In some embodiments of the present invention, the r_{50} of the ATH product particles is in the range of from about 0.20 to about 0.33μm, preferably in the range of from about 0.2 to about 0.3μm. In other embodiments, the r_{50} is in the range of from about 0.185 to about 0.325μm, preferably in the range of from about 0.185 to about 0.25μm. In still other preferred embodiments, the r_{50} is in the range of from about 0.09 to about 0.21μm, more preferably in the range of from about 0.09 to about 0.165μm.

[0041] The ATH product particles produced by the process of the present invention can also be characterized as having a V_{max}, i.e. maximum specific pore volume at about 1000 bar, in the range of from about 300 to about 700 mm^3/g. In some embodiments of the present invention, the V_{max} of the ATH product particles is in the range of from about 390 to about 480 mm^3/g, preferably in the range of from about 410 to about 450 mm^3/g. In other embodiments, the V_{max} is in the range of from about 400 to about 600 mm^3/g, preferably in the range of from about 450 to about 550 mm^3/g. In yet other embodiments, the V_{max} is in the range of from about 300 to about 700 mm^3/g, preferably in the range of from about 350 to about 550 mm^3/g.

[0042] The ATH product particles produced by the process of the present invention can also be characterized as having an oil absorption, as determined by ISO 787-5:1980, of less than bout 50%, sometimes in the range of from about 1 to about 50%. In some embodiments, the ATH product particles produced by the process of the present invention are characterized as having an oil absorption in the range of from about 23 to about 30%, preferably in the range of from about 24% to about 29%, more preferably in the range of from about 25% to about 28%. In other embodiments, the ATH product particles produced by the process of the present invention are characterized as having an oil absorption in the range of from about 25% to about 40%, preferably in the range of from about 25% to about 35%, more preferably in the range of from about 26% to about 30%. In still other embodiments, the ATH product particles produced by the process of the present invention are characterized as having an oil absorption in the range of from about 25 to about 50%, preferably in the range of from about 26% to about 40%, more preferably in the range of from about 27% to about 32%. In other embodiments, the oil absorption of the ATH product particles produced by the process of the present invention is in the range of from about 19% to about 23%, and in still other embodiments, the oil absorption of the mill-dried ATH particles produced is in the range of from about 21% to about 25%.

[0043] The ATH product particles produced by the process of the present invention can also be characterized as having a BET specific surface area, as determined by DIN-66132, in the range of from about 1 to 15 m^2/g. In some embodiments, the ATH product particles produced by the process of the present invention have a BET specific surface in the range of from about 3 to about 6 m^2/g, preferably in the range of from about 3.5 to about 5.5 m^2/g. In other embodiments, the ATH product particles produced by the process of the present invention have a BET specific surface of in the range of from about 6 to about 9 m^2/g, preferably in the range of from about 6.5 to about 8.5 m^2/g. In still other embodiments, the ATH product particles produced by the process of the present invention have a BET specific surface in the range of from about 9 to about 15 m^2/g, preferably in the range of from about 10.5 to about 12.5 m^2/g.

[0044] The ATH product particles produced by the process of the present invention can also be characterized as having a d_{50} in the range of from about 0.5 to 2.5 μm. In some embodiments, the ATH product particles produced by the process of the present invention produced by the present invention have a d_{50} in the range of from about 1.5 to about 2.5 μm, preferably in the range of from about 1.8 to about 2.2 μm. In other embodiments, the ATH product particles produced by the process of the present invention have a d_{50} in the range of

from about 1.3 to about 2.0 μm, preferably in the range of from about 1.4 to about 1.8 μm. In still other embodiments, the ATH product particles produced by the process of the present invention have a d_{50} in the range of from about 0.9 to about 1.8 μm, more preferably in the range of from about 1.1 to about 1.5 μm.

[0045] The ATH product particles produced by the process of the present invention can also be characterized as having a total soda content of less than about 0.4 wt.%, based on the ATH product particles. In some embodiments, if the soluble soda content is a characteristic of the ATH product particles, the total soda content is less than about 0.20 wt.%, preferably less than about 0.18 wt.%, more preferably less than 0.12 wt.%, based on the total weight of the ATH product particles. In other embodiments, if the soluble soda content is a characteristic of the ATH product particles, the total soda content is less than about 0.30, preferably less than about 0.25 wt.%, more preferably less than 0.20 wt.%, based on the total weight of the ATH product particles. In other embodiments, if the soluble soda content is a characteristic of the ATH product particles, the total soda content is less than about 0.40, preferably less than about 0.30 wt.%, more preferably less than 0.25 wt.%, based on the total weight of the ATH product particles. The total soda content can be measured according to the procedure outlined above.

[0046] The ATH product particles produced by the process of the present invention can also be characterized as having a specific thermal stability, as described in Tables 1, 2, and 3, below.

Table 1		
	1 wt.% TGA (°C)	2 wt.% TGA (°C)
Typical	210-225	220-235
Preferred	210-220	220-230
More Preferred	214-218	224-228
Table 2		
	1 wt.% TGA (°C)	2 wt.% TGA (°C)
Typical	200-215	210-225
Preferred	200-210	210-220
More Preferred	200-205	210-215
Table 3		
	1 wt.% TGA (°C)	2 wt.% TGA (°C)
Typical	195-210	205-220
Preferred	195-205	205-215
More Preferred	195-200	205-210

[0047] Thermal stability, as used herein, refers to release of water of the ATH product particles and can be assessed directly by several thermoanalytical methods such as

thermogravimetric analysis ("TGA"), and in the present invention, the thermal stability of the ATH product particles was measured via TGA. Prior to the measurement, the mill-dried ATH particle samples were dried in an oven for 4 hours at about 105°C to remove surface moisture. The TGA measurement was then performed with a Mettler Toledo by using a 70 µl alumina crucible (initial weight of about 12 mg) under N_2 (70 ml per minute) with the following heating rate: 30°C to 150°C at 10°C per min, 150°C to 350°C at 1°C per min, 350°C to 600°C at 10°C per min. The TGA temperature of the ATH product particles (pre-dried as described above) was measured at 1wt.% loss and 2wt.% loss, both based on the weight of the mill-dried ATH particles. It should be noted that the TGA measurements described above were taken using a lid to cover the crucible.

[0048] The ATH product particles produced by the process of the present invention can also be characterized as having an electrical conductivity in the range of less than about 200 µS/cm, in some embodiments less than 150 µS/cm, and in other embodiments, less than 100 µS/cm. In other embodiments, the electrical conductivity of the ATH product particles is in the range of about 10 to about 45 µS/cm. It should be noted that all electrical conductivity measurements were conducted on a solution comprising water and about at 10wt.% ATH product particles, based on the solution, as described below.

[0049] The electrical conductivity was measured by the following procedure using a MultiLab 540 conductivity measuring instrument from Wissenschaftlich-Technische-Werkstätten GmbH, Weilheim/Germany: 10 g of the sample to be analyzed and 90 ml deionized water (of ambient temperature) are shaken in a 100 ml Erlenmeyer flask on a GFL 3015 shaking device available from Gesellschaft for Labortechnik mbH, Burgwedel/Germany for 10 minutes at maximum performance. Then the conductivity electrode is immersed in the suspension and the electrical conductivity is measured.

[0050] The ATH product particles produced by the process of the present invention can also be characterized as having a soluble soda content of less than about 0.1 wt.%, based on the mill-dried ATH particles. In other embodiments, the ATH product particles can be further characterized as having a soluble soda content in the range of from greater than about 0.001 to about 0.1 wt.%, in some embodiments in the range of from about 0.02 to about 0.1 wt.%, both based on the ATH product particles. While in other embodiments, the ATH product particles can be further characterized as having a soluble soda content in the range of from about 0.001 to less than 0.03 wt%, in some embodiments in the range of from about 0.001 to less than 0.04 wt%, in other embodiments in the range of from about 0.001 to less than 0.02

wt%, all on the same basis. The soluble soda content can be measured according to the procedure outlined above.

[0051] The ATH product particles produced by the process of the present invention can be, and preferably are, characterized by the non-soluble soda content. While empirical evidence indicates that the thermal stability of an ATH is linked to the total soda content of the ATH, the inventors hereof have discovered and believe, while not wishing to be bound by theory, that the improved thermal stability of the ATH product particles produced by the process of the present invention is linked to the non-soluble soda content. The non-soluble soda content of the ATH product particles of the present invention is typically in the range of from about 70 to about 99.8% of the total soda content of the ATH product particles, with the remainder being soluble soda. In some embodiments of the present invention, the total soda content of the ATH product particles is typically in the range of less than about 0.20wt.%, based on the ATH product particles preferably in the range of less than about 0.18wt.%, based on the ATH product particles, more preferably in the range of less than about 0.12wt.%, on the same basis. In other embodiments of the present invention, the total soda content of the ATH product particles is typically in the range of less than about 0.30wt.%, based on the ATH product particles, preferably in the range of less than about 0.25wt.%, based on the ATH product particles, more preferably in the range of less than about 0.20wt.%, on the same basis. In still other embodiments of the present invention, the total soda content of the ATH product particles is typically in the range of less than about 0.40wt.%, based on the ATH product particles, preferably in the range of less than about 0.30wt.%, based on the ATH product particles, more preferably in the range of less than about 0.25wt.%, on the same basis.

Use of the ATH Product Particles

[0052] The ATH particles according to the present invention can also be used as a flame retardant in a variety of synthetic resins. These flame retarded polymer formulation typically comprise at least one synthetic resin and a flame retarding amount of ATH product particles produced according to the present invention. In some applications, the flame retarded polymer formulation can be molded and/or extruded.

[0053] In most applications, a flame retarding amount of the ATH product particles is generally in the range of from about 5 wt% to about 90wt%, based on the weight of the flame retarded polymer formulation, preferably in the range of from about 20wt% to about 70wt%, on the same basis. In a most preferred embodiment, a flame retarding amount is in the range of from about 30wt% to about 65wt% of the mill-dried ATH particles, on the same basis.

Thus, flame retarded polymer formulations containing ATH product particles produced according to the present invention typically comprises in the range of from about 10 to about 95wt.% of the at least one synthetic resin, based on the weight of the flame retarded polymer formulation, preferably in the range of from about 30 to about 40wt.% of the flame retarded polymer formulation, more preferably in the range of from about 35 to about 70wt.% of the at least one synthetic resin, all on the same basis.

[0054] Non-limiting examples of thermoplastic resins where the ATH product particles find use include polyethylene, ethylene-propylene copolymer, polymers and copolymers of C_2 to C_8 olefins (α-olefin) such as polybutene, poly(4-methylpentene-1) or the like, copolymers of these olefins and diene, ethylene-acrylate copolymer, polystyrene, ABS resin, AAS resin, AS resin, MBS resin, ethylene-vinyl chloride copolymer resin, ethylene-vinyl acetate copolymer resin, ethylene-vinyl chloride-vinyl acetate graft polymer resin, vinylidene chloride, polyvinyl chloride, chlorinated polyethylene, vinyl chloride-propylene copolymer, vinyl acetate resin, phenoxy resin, and the like. Further examples of suitable synthetic resins include thermosetting resins such as epoxy resin, phenol resin, melamine resin, unsaturated polyester resin, alkyd resin and urea resin and natural or synthetic rubbers such as EPDM, butyl rubber, isoprene rubber, SBR, NIR, urethane rubber, polybutadiene rubber, acrylic rubber, silicone rubber, fluoro-elastomer, NBR and chloro-sulfonated polyethylene are also included. Further included are polymeric suspensions (latices).

[0055] Preferably, the synthetic resin is a polyethylene-based resins such as high-density polyethylene, low-density polyethylene, linear low-density polyethylene, ultra low-density polyethylene, EVA (ethylene-vinyl acetate resin), EEA (ethylene-ethyl acrylate resin), EMA (ethylene-methyl acrylate copolymer resin), EAA (ethylene-acrylic acid copolymer resin) and ultra high molecular weight polyethylene; and polymers and copolymers of C_2 to C_8 olefins (α-olefin) such as polybutene and poly(4-methylpentene-1), polyvinyl chloride and rubbers. In a more preferred embodiment, the synthetic resin is a polyethylene-based resin.

[0056] The flame retarded polymer formulation can also contain other additives commonly used in the art. Non-limiting examples of other additives that are suitable for use in the flame retarded polymer formulations of the present invention include extrusion aids such as polyethylene waxes, Si-based extrusion aids, fatty acids; coupling agents such as amino-, vinyl- or alkyl silanes or maleic acid grafted polymers; barium stearate or calcium stearate; organoperoxides; dyes; pigments; fillers; blowing agents; deodorants; thermal stabilizers; antioxidants; antistatic agents; reinforcing agents; metal scavengers or deactivators; impact modifiers; processing aids; mold release aids, lubricants; anti-blocking agents; other flame

retardants; UV stabilizers; plasticizers; flow aids; and the like. If desired, nucleating agents such as calcium silicate or indigo can be included in the flame retarded polymer formulations also. The proportions of the other optional additives are conventional and can be varied to suit the needs of any given situation.

[0057] The methods of incorporation and addition of the components of the flame-retarded polymer formulation and the method by which the molding is conducted is not critical to the present invention and can be any known in the art so long as the method selected involves uniform mixing and molding. For example, each of the above components, and optional additives if used, can be mixed using a Buss Ko-kneader, internal mixers, Farrel continuous mixers or twin screw extruders or in some cases also single screw extruders or two roll mills, and then the flame retarded polymer formulation molded in a subsequent processing step. Further, the molded article of the flame-retardant polymer formulation may be used after fabrication for applications such as stretch processing, emboss processing, coating, printing, plating, perforation or cutting. The kneaded mixture can also be inflation-molded, injection-molded, extrusion-molded, blow-molded, press-molded, rotation-molded or calender-molded.

[0058] In the case of an extruded article, any extrusion technique known to be effective with the synthetic resin(s) used in the flame retarded polymer formulation can be employed. In one exemplary technique, the synthetic resin, ATH product particles, and optional components, if chosen, are compounded in a compounding machine to form the flame-retardant resin formulation. The flame-retardant resin formulation is then heated to a molten state in an extruder, and the molten flame-retardant resin formulation is then extruded through a selected die to form an extruded article or to coat for example a metal wire or a glass fiber used for data transmission.

[0059] In some embodiments, the synthetic resin is selected from epoxy resins, novolac resins, phosphorous containing resins like DOPO, brominated epoxy resins, unsaturated polyester resins and vinyl esters. In this embodiment, a flame retarding amount of ATH product particles is in the range of from about 5 to about 200 parts per hundred resin ("phr") of the ATH product particles. In preferred embodiments, the flame retarded formulation comprises from about 15 to about 100 phr preferably from about 15 to about 75 phr, more preferably from about 20 to about 55 phr, of the ATH product particles. In this embodiment, the flame retarded polymer formulation can also contain other additives commonly used in the art with these particular resins. Non-limiting examples of other additives that are suitable for use in this flame retarded polymer formulation include other flame retardants based e.g. on bromine, phosphorous or nitrogen; solvents, curing agents like hardeners or accelerators,

dispersing agents or phosphorous compounds, fine silica, clay or talc. The proportions of the other optional additives are conventional and can be varied to suit the needs of any given situation. The preferred methods of incorporation and addition of the components of this flame retarded polymer formulation is by high shear mixing. For example, by using shearing a head mixer manufactured for example by the Silverson Company. Further processing of the resin-filler mix to the "prepreg" stage and then to the cured laminate is common state of the art and described in the literature, for example in the "Handbook of Epoxide Resins", published by the McGraw-Hill Book Company, which is incorporated herein in its entirety by reference.

[0060] The above description is directed to several embodiments of the present invention. Those skilled in the art will recognize that other means, which are equally effective, could be devised for carrying out the spirit of this invention. It should also be noted that preferred embodiments of the present invention contemplate that all ranges discussed herein include ranges from any lower amount to any higher amount. For example, when discussing the oil absorption of the ATH product particles, it is contemplated that ranges from about 30% to about 32%, about 19% to about 25%, about 21% to about 27%, etc. are within the scope of the present invention.

WHAT IS CLAIMED:

1. A process for producing mill-dried ATH particles comprising:
   a) mill drying a slurry to produce mill dried ATH particles comprising agglomerates; and
   b) reducing the number of agglomerates present in said mill-dried ATH particles to produce ATH product particles,
   wherein the slurry contains in the range of from about 1 to about 85 wt.% ATH particles and wherein the ATH product particles have a V_{max} in the range of from about 300 to about 700 mm^3/g and/or an r_{50} in the range of from about 0.09 to about 0.33μm, and one or more of the following characteristics: i) a d_{50} of from about 0.5 to about 2.5 μm; ii) a total soda content of less than about 0.4wt.%, based on the total weight of the dry-milled ATH particles; iii) an oil absorption of less than about 50%, as determined by ISO 787-5:1980; and iv) a specific surface area (BET) as determined by DIN-66132 of from about 1 to about 15 m^2/g, wherein the electrical conductivity of the mill-dried ATH particles is less than about 200 μS/cm, measured in water at 10wt.% of the ATH in water.
2. The process according to claim 1 wherein said slurry is obtained from a process that involves producing ATH particles through precipitation and filtration.
3. The process according to claim 1 wherein said slurry is obtained from a process that comprises dissolving aluminum hydroxide in caustic soda to form a sodium aluminate liquor; filtering the sodium aluminate solution to remove impurities; cooling and diluting the sodium aluminate liquor to an appropriate temperature and concentration; adding ATH seed particles to the sodium aluminate solution; allowing ATH particles to precipitate from the solution thus forming an ATH suspension containing in the range of from about 80 to about 160 g/l ATH, based on the suspension; filtering the ATH suspension thus forming a filter cake; optionally washing said filter cake one or more times with water before it is re-slurried; and re-slurrying said filter cake to form a slurry comprising in the range of from about 1 to about 85 wt.% ATH, based on the total weight of the slurry.
4. The process according to claim 3 wherein said filter cake is re-slurried by the addition of water, thus forming said slurry, said slurry containing in the range of from about 10 to about 35wt.% ATH, based on the total weight of the slurry.
5. The process according to claim 3 wherein said filter cake is re-slurried by adding a dispersing agent to the filter cake thus forming said slurry.

6. The process according to claim 1 wherein the BET of the ATH particles in the slurry is a) in the range of from about 1.0 to about 4.0 m^2/g or b) in the range of from about 4.0 to about 8.0 m^2/g, or c) in the range of from about 8.0 to about 14 m^2/g.
7. The process according to claim 6 wherein the ATH particles in the slurry have a d_{50} in the range of from about 1.5 to about 3.5 μm.
8. The process according to claim 7 wherein said slurry contains i) in the range of from about 25 to about 70 wt.% ATH particles; ii) in the range of from about 55 to about 65 wt.% ATH particles; iii) in the range of from about 40 to about 60 wt.% ATH particles; iv) in the range of from about 45 to about 55 wt.% ATH particles; v) in the range of from about 25 to about 50 wt.% ATH particles; or vi) in the range of from about 30 to about 45 wt.% ATH particles; wherein all wt.% are based on the total weight of the slurry.
9. The process according to claim 7 wherein the total soda content of the ATH particles in the slurry is less than about 0.2 wt.%, based on the ATH particles in the slurry.
10. The process according to any of claims 1, 7, or 9 wherein the ATH particles in the slurry have a soluble soda content of less than about 0.1 wt.%, based on the ATH particles in the slurry.
11. The process according to any of claims 1, 7 or 9 wherein the ATH particles in the slurry have a non-soluble soda content, as described herein, in the range of from about 70 to about 99.8% of the total soda content, with the remainder being soluble soda.
12. The process according to claim 1 wherein said the number agglomerates present in said mill-dried ATH particles is reduced through the use of i) a pin mill; ii) an air classifier; or iii) any combination thereof.
13. The process according to claim 12 wherein the d_{50} of the ATH product particles is greater than or equal to 90% of the d_{50} of the mill-dried ATH particles
14. The ATH product particles produced according to claim 1.
15. The ATH product particles according to claim 14 wherein said ATH product particles have an oil absorption in the range of from about 19 to about 23%.
16. The ATH product particles according to claim 14 wherein the ATH product particles have:
    a) a BET in the range of from about 3 to about 6 m^2/g, a d_{50} in the range of from about 1.5 to about 2.5 μm, an oil absorption in the range of from about 23 to about 30%, an r_{50} in the range of from about 0.2 to about 0.33μm, a V_{max} in the range of from about 390 to about 480 mm^3/g, a total soda content of less than about 0.2 wt.%, based on the mill-dried ATH particles, an electrical conductivity

in the range of less than about 100 μS/cm, a soluble soda content in the range of from 0.001 to less than 0.02 wt%, based on the mill-dried ATH particles, a non-soluble soda content in the range of from about 70 to about 99.8% of the total soda content of the mill-dried ATH and a thermal stability, determined by thermogravimetric analysis, as described in Table 1:

Table 1	
1 wt.% TGA (°C)	2 wt.% TGA (°C)
210-225	220-235

or

b) a BET in the range of from about 6 to about 9 m^2/g, a d_{50} in the range of from about 1.3 to about 2.0 μm, an oil absorption in the range of from about 25 to about 40%, an r_{50} in the range of from about 0.185 to about 0.325μm, a V_{max} in the range of from about 400 to about 600 mm^3/g, a total soda content of less than about 0.3 wt.%, based on the mill-dried ATH particles, an electrical conductivity in the range of less than about 150 μS/cm, a soluble soda content in the range of from 0.001 to less than 0.03 wt%, based on the mill-dried ATH particles, a non-soluble soda content in the range of from about 70 to about 99.8% of the total soda content of the mill-dried ATH and a thermal stability, determined by thermogravimetric analysis, as described in Table 2:

Table 2	
1 wt.% TGA (°C)	2 wt.% TGA (°C)
200-215	210-225

or

c) a BET in the range of from about 9 to about 15 m^2/g and a d_{50} in the range of from about 0.9 to about 1.8 μm, an oil absorption in the range of from about 25 to about 50%, an r_{50} in the range of from about 0.09 to about 0.21μm, a V_{max} in the range of from about 300 to about 700 mm^3/g, a total soda content of less than about 0.4 wt.%, based on the mill-dried ATH particles, an electrical conductivity in the range of less than about 200 μS/cm, a soluble soda content in the range of from 0.001 to less than 0.04 wt%, based on the mill-dried ATH particles, a non-soluble soda content in the range of from about 70 to about 99.8% of the total soda content of the dry-milled ATH and a thermal stability, determined by thermogravimetric analysis, as described in Table 3:

Table 3	
1 wt.% TGA (°C)	2 wt.% TGA (°C)
195-210	205-220

17. The process according to claim 10 wherein the ATH product particles have a soluble soda content of less than about 0.1 wt.%, based on the ATH particles in the slurry.
18. The process according to claim 11 wherein the ATH product particles have a non-soluble soda content, as described herein, in the range of from about 70 to about 99.8% of the total soda content, with the remainder being soluble soda.
19. A flame retarded polymer formulation comprising at least one synthetic resin and in the range of from about 5 wt% to about 90wt%, based on the weight of the flame retarded polymer formulation of the ATH product particles according to claim 16.
20. A molded or extruded article made from the flame retarded polymer formulation according to claim 19.