

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
25 January 2001 (25.01.2001)

PCT

(10) International Publication Number
WO 01/05892 A1

(51) International Patent Classification: C08L 97/02,
B27N 3/08 // (C08L 97/02, 3:02, 93:04)

(21) International Application Number: PCT/KR00/00159

(22) International Filing Date: 2 March 2000 (02.03.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
1999/29663 21 July 1999 (21.07.1999) KR
2000/32 3 January 2000 (03.01.2000) KR

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:
— With international search report.

(71) Applicants and
(72) Inventors: KIM, Young, Bok [KR/KR]; 692, Suyou 3-Dong, Kangbuk Gu, Seoul 142-073 (KR). KIM, Myung, Ja [KR/KR]; 692, Suyou 3-dong, Kangbuk Gu, Seoul 142-073 (KR).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(74) Agent: HONG, Byung-Eui; Rm. 1004, Shinbong Building, 736-6, Yoksam-dong Kangnam-ku, Seoul 135-080 (KR).



WO 01/05892 A1

(54) Title: MANUFACTURING METHOD OF SUBSTITUTE GOODS FOR PLASTIC WHICH MADE FROM NATURAL MATERIALS

(57) Abstract: A method for manufacturing plastic-substitute goods by using natural materials is disclosed. Agricultural byproducts and wood byproducts such as rice husks, rice plant stems, corn plant stems, bean plant stems, wheat plant stems, saw dust and the like are crushed into a particular size, then the crushed particles are mixed with natural adhesives (such as corn starch, potato starch and the like), and are coated with rosin or natural resins, and then a molding is carried out by applying a pressure in a molding machine, thereby manufacturing the plastic-substitute goods. The raw materials of the present invention are readily available from the rural areas, and the molding is carried out at a temperature of 100 - 300 degrees C.