

Description

The present invention in its most general form relates to fuel compositions for use in internal combustion engines of the spark-ignition type. In a particular aspect it relates to fuel compositions for use in spark-ignition engines, which compositions contain an additive effective in reducing valve seat recession in lead-free or low-lead fuels.

During the past decade, a general reduction in the use of organo-lead in gasoline has occurred. This is due in part to concern over health effects related to lead emissions and in part also to the need for unleaded gasoline to prevent poisoning of metal catalysts used to control exhaust emissions. For example, the use of lead in regular grade gasoline is due to be phased out in West Germany in mid-1988. However, in that country alone about one million cars would be unable to operate on regular grade unleaded gasoline because of the potential problem with valve seat damage or recession. This problem is particularly prevalent with certain (older) engines with soft, e.g. cast iron, exhaust valve seats. During operation of these engines with leaded gasoline, lead decomposition products act as a solid lubricant and prevent wear of the valve seat by the harder exhaust valve. If such engines are operated on unleaded gasoline, they lose the protection of the solid lubricant and severe valve seat wear can ensue. In extreme cases the valve seat can become so worn that the valve recedes to the point where it fails to open. Catastrophic engine failure is the result.

The problem of valve seat sinkage or recession has by now become well recognised in the art and a number of solutions to the problem have been proposed in patent publications. Representative of these may be mentioned EP-A-0207560 and WO 87/01126.

EP-A-0207560 discloses a gasoline composition comprising a major amount of a gasoline suitable for use in spark-ignition engines and a minor amount of an alkali metal or alkaline earth metal salt of a succinic acid derivative having as a substituent on at least one of its alpha-carbon atoms an unsubstituted or substituted aliphatic hydrocarbon group having from 20 to 200 carbon atoms, or of a succinic acid derivative having as a substituent on one of its alpha-carbon atoms an unsubstituted or substituted hydrocarbon group having from 20 to 200 carbon atoms which is connected to the other alpha-carbon atom by means of a hydrocarbon moiety having from 1 to 6 carbon atoms, forming a ring structure. The aforesaid compounds are reported to improve the flame speed in the cylinder of the engine, thereby improving combustion, and not to give rise to any fouling in the engine.

In Example 5 of this patent the use of the salt of the succinic acid derivative for reducing valve seat recession is illustrated.

WO 87/01126 discloses a fuel composition for internal combustion engines comprising a major amount of a liquid hydrocarbon fuel and a minor amount sufficient to reduce valve seat recession when the fuel is used in an internal combustion engine of

- (A) at least one hydrocarbon-soluble alkali or alkaline earth metal containing composition, and
- (B) at least one hydrocarbon-soluble ashless dispersant. The composition (A) may be an alkali metal or alkaline earth metal salt of a sulphur acid, for example a sulphonic acid, a phosphorous acid, a carboxylic acid or a phenol.

The use of metal borates as additives to fuels and/or lubricating oils is known from, for example, US-A-2,987,476 and GB-A-2173419. US-A-2,987,476 discloses that compositions of matter comprising inorganic boric acid compounds of a kind which readily form stable, clear dispersions of those inorganic boric acid compounds in liquid fuels and in base stocks used in formulating lubricating oils and greases are prepared by hydrolysing an organic ester of boric acid in the presence of a lyophilic ionic surface-active agent, a substantially non-polar organic liquid, and a water-miscible organic liquid, and, if desired recovering from the resulting mixture a dispersible inorganic boric acid compound. The products of this process are said to contain substantial amounts of boron in a form readily dispersible in liquid fuels and lubricant base stocks to form stable, clear dispersions, containing up to 10% by weight of the inorganic boric acid compound.

GB-A-2173419 discloses a method for producing an alkaline earth metal borate dispersion, comprising two steps of:

- (I) reacting at 20-100 °C a mixture of the following ingredients (A) to (E)
 - (A) 100 parts by weight of the oil-soluble neutral sulfonate of an alkaline earth metal;
 - (B) 10-100 parts by weight of the hydroxide or oxide of an alkaline earth metal;
 - (C) boric acid in an amount which is 0.5-6.5 mols per mol ingredient (B),
 - (D) 5-50 parts by weight of water and
 - (E) 50-200 parts by weight of a dilution solvent and then
- (II) heating the resulting reaction mixture to 100-200 °C to remove the water and a part of the diluent solvent as required. The particulate dispersions resulting are for use in fuel oils and lubricating oils.

We have now found that additives comprising alkali or alkaline earth metals salts, in the form of particulate dispersions thereof are desirable additives for lead free or low lead spark ignition engine fuels, in particular for reducing valve seat recession. The additives may also improve detergency and improve combustion by a spark aider type mechanism.

5 Potassium borate, for example, has been used in lubricating oil compositions. Thus, US Patent No. 3,997,454 discloses an extreme-pressure lubricating composition comprising an oil of lubricating viscosity having dispersed therein 1 to 60 weight percent of hydrated potassium borate microparticles having a boron-to-potassium ratio of about 2.5 to 4.5 and, optionally, from 0.01 to 5.0 weight percent of an antiwear agent selected from (a) zinc dihydrocarbyl dithiophosphates having from 4 to 20 carbon atoms in each
10 hydrocarbyl group, (b) a C_1 to C_{20} ester, C_1 to C_{20} amide, or C_1 to C_{20} amine salt of a dihydrocarbyl dithiophosphoric acid having from 4 to 20 carbon atoms in each hydrocarbyl group, or (c) mixtures thereof. However, to our knowledge, its use has never been proposed in connection with fuel compositions and its utility in this connection must be regarded as surprising.

Furthermore, it is known from DD 200521A and J53141184 for example to incorporate metal salts in
15 fuel additives, though not as particulate dispersions of the metal salts but as solutions thereof and not for the same purpose as the additives of the present invention.

Accordingly, the present invention provides a lead free or low lead fuel composition for use in internal combustion engines which composition comprises (A) a major amount of a fuel suitable for use in a spark ignition engine characterised in that the fuel composition further comprises (B) a minor amount of a
20 composition comprising an alkali or alkaline earth metal salt in the form of a particulate dispersion, provided that the alkali metal is not sodium

As regards component (A), the fuel is a fuel suitable for use in a spark ignition engine, for example an automobile engine, hereinafter referred to as gasolines, and the remainder of the description will in consequence be wholly devoted to such fuels. The gasoline may suitably comprise a hydrocarbon or
25 hydrocarbon mixture boiling essentially in the gasoline boiling range, i.e. from 30 to 230 °C.

The gasoline may comprise mixtures of saturated, olefinic and aromatic hydrocarbons. They may be derived for example from straight-run gasoline, synthetically produced aromatic hydrocarbon mixtures, thermally or catalytically cracked hydrocarbons, hydrocracked petroleum fractions or catalytically reformed hydrocarbons. Generally, the octane number of the gasoline will be greater than 65. A proportion of
30 hydrocarbons may be replaced for example by alcohols, ethers, ketones or esters.

As regards component (B) of the composition, the metal is either an alkali or alkaline earth metal, more preferably an alkali metal, provided the alkali metal is not sodium most preferably potassium. The salt may suitably be a salt of a carboxylic acid, carbonic acid or boric acid, though the salts of other acids may be employed. It is preferred to use water soluble salts. Examples of suitable salts include potassium acetate,
35 potassium bicarbonate, potassium carbonate and potassium borate.

The composition will preferably also include a carrier for the metal salt, which may suitably be a gasoline compatible high-boiling material. Suitable carrier materials include mineral oils which may be solvent refined or otherwise, synthetic lubricating oils, for example of the ester type, liquid polyolefins, for example low molecular weight polyisobutenes, or their oxidised or aminated derivatives, amino and hydroxy
40 derivatives of polyolefins, olefin copolymers, or hydrotreated base stocks sulphonates, succinimides, polyisobutene succinic anhydrides or their polycyclic alcohol derivatives, polyethers, polymethacrylates or PMP esters.

The metal salt is preferably incorporated in the carrier in the form of a particulate dispersion of the metal salt, suitably having a mean particle size of less than 1 micrometers, preferably less than 0.5
45 micrometers.

In a preferred embodiment of the present invention component (B) comprises either an alkali metal provided the alkali metal is not sodium or alkaline earth metal borate in the form of a particulate dispersion in a carrier, the molar ratio of boron to metal being in the range from 0.33 to about 4.5, preferably from 0.33 to 2.5, more preferably about 1:1.

50 Although the preparation of metal borate dispersions for use as component (B) of the fuel composition will be described in detail hereinafter, the preparation of boron-free metal salt dispersions may be accomplished in similar manner.

A suitable metal borate dispersion for use as component (B) of the fuel composition may be prepared by wholly or partially desolvating a solvent-in-carrier emulsion of a solution of metal hydroxide and boric acid to provide a boron to metal molar ratio of $Z/3$ (wherein Z is the valency of the metal) to 4.5.
55

Suitable solvents include hydrocarbon and substituted hydrocarbon solvents of relatively low boiling point and water. A preferred solvent is water.

Typically, using an alkali metal which is potassium as a representative example, the method may be effected by introducing into an inert, nonpolar carrier as hereinbefore described an aqueous solution of the alkali metal hydroxide and boric acid (metal borate solution) and preferably an emulsifier, vigorously agitating the mixture to provide an emulsion of the aqueous solution in the carrier and then heating at a temperature and for a time sufficient to provide the predetermined degree of dehydration in the emulsion. Suitably the temperature at which the emulsion is heated may be in the range from 60 to 230 °C, preferably from 80 to 140 °C, though lower temperatures may be used at sub-atmospheric pressures. However, it will usually be found convenient to operate at atmospheric pressure.

An alternative method for preparing the alkali metal borate dispersion comprises reacting an alkali metal carbonate-overbased carrier-soluble alkali metal sulphonate with boric acid to form an intermediate alkali metal borate reaction product. The amount of boric acid reacted with the alkali metal carbonate should be sufficient to prepare an alkali metal borate having a boron to alkali metal molar ratio of at least 5. The intermediate alkali metal borate is converted to the alkali metal borate of this invention by contacting the intermediate borate reaction product with a sufficient amount of alkali metal hydroxide to produce an alkali metal borate having a boron to alkali metal molar ratio between 0.33 and 4.5. The water content may thereafter be adjusted if so required. The reaction of the alkali metal carbonate-overbased metal sulphonate with boric acid and the subsequent reaction with alkali metal hydroxide may be conducted at a temperature in the range from 20 to 200 °C, preferably from 20 to 150 °C. A reaction diluent may be present during the two reaction stages and subsequently removed by conventional stripping steps.

As mentioned hereinbefore an emulsifier is preferably employed in the preparation of the emulsion. Suitable emulsifiers include neutral sulphonates, succinimides, polyisobutene succinic anhydrides and their polyhydric alcohol derivatives, polyethers, polyolefin amines and hydroxy derivatives, olefin copolymers, oxidised polybutenes and their aminated derivatives, polymethacrylates and PMP esters.

A further method of preparing an alkaline earth metal borate dispersion is described in GB-A-2173419.

The composition comprising component (B) of the fuel composition is preferably a concentrate, from 1 to 99%, preferably from 20 to 70%, by weight of which is the metal salt. Component (B) is preferably present in the fuel composition of the invention in an amount sufficient to provide at least 2 ppm, typically about 10 ppm by weight of metal, for example potassium, based on the total weight of the fuel composition.

In addition to the essential components (A) and (B), the fuel composition preferably also contains at least one fuel soluble detergent additive. Suitable detergents include polyolefin amines, for example polybutene amines, polyether amines, fatty acid amines, organic and metallic sulphonates of both the neutral and overbased types, and the like.

The fuel composition may also contain one or more rust inhibitors. Suitable rust inhibitors include for example succinic acid, carboxylic acids, phosphoric acid and derivatives of the aforesaid acids, amides, and the like.

Optionally the fuel composition may also contain one or more demulsifiers, for example a polyoxyalkylene glycol or a derivative thereof.

The fuel composition may also contain additives conventionally present in such compositions, for example one or more antioxidants.

Finally, the fuel composition may also contain a spark aider or cyclic variability reducer.

The detergent(s), rust inhibitor(s), demulsifier(s), antioxidant(s) and/or spark aider(s) may be added either directly to the fuel composition or as a component of the composition forming component (B) of the fuel composition.

The component (B) of the composition is used in combination with either a low-lead or lead-free gasoline, as component (A) of the composition.

The invention will now be further illustrated by reference to the following examples.

(A) PREPARATION OF COMPONENT (B)

(I) Preparation of Metal Borate Dispersions

Example 1

An inorganic phase, prepared by reacting an alkali metal hydroxide with boric acid in water at 40 °C was added to an organic phase comprising a dispersant (a pentaerythritol pibate ester) in a carrier (Example 1 - White Oil) in a homogeniser (a single stage laboratory homogeniser) over a period of 1 hour at 300-400 bar. The reactants were circulated through the homogeniser at 500-700 bar for a further 4 hours whereupon much of the water evaporated. The product, a clear liquid, was drained from the homogeniser

and used without further processing.

Specific combinations and charges are given in Table 1.

Table 1

	Example 1
Alkali metal Carrier Dispersant	Potassium White Oil an ester
Charges (g)	
Alkali metal hydroxide	127
Boric acid	142
Water	665
Carrier	504
Dispersant	116
Mole ratio alkali metal:boron	1:1
Alkali metal content (% b.w.)	7.9

(II) PREPARATION OF BORON-FREE METAL SALT DISPERSIONS

Examples 2 to 5

An aqueous solution of the potassium salt at a temperature of about 40°C was added to a mixture of carrier (SN100 base oil) and dispersant (a commercially available pentaerythritol monopibate ester) over a period of 30 minutes in a laboratory homogeniser (500 - 600 bar) for 2-3 hours, whereupon much of the water evaporated. The resulting liquid was drained from the homogeniser and used without further treatment.

Specific combinations and charges are given in Table 2.

Table 2

COMPOSITION	Example 2	Example 3	Example 4	Example 5
Metal salt	Potassium acetate	Potassium bicarbonate	Potassium carbonate	Potassium carbonate
Carrier	SN 100	SN 100	SN 100	SN 100
Dispersant	PMPE	PMPE	PMPE	PMPE
CHARGE (g)				
Metal salt	220	220	220	270
Water	665	665	665	665
Carrier	500	500	500	500
Dispersant	120	120	120	120
ANALYTICAL DATA				
% K (w/w)	6.15	3.70	10.96	14.83
% S (w/w)	0.47	0.55	0.46	0.42
% CO ₂ (w/w)	-	1.1	2.7	3.5
% H ₂ O (w/w)	6.8	2.6	5.4	4.2
% sediment (vol. in heptane)	0.02	0.02	0.16	0.12
V ₁₀₀ (cSt)(x10 ⁻⁶ m ² /s)	10.1	6.4	8.1	8.6
V ₄₀ (cSt)(x10 ⁻⁶ m ² /s)	55.4	37.7	44.0	45.2
TAN (mg KOH g ⁻¹)	0.91	13.7	20.5	9.9
TBN (mg KOH g ⁻¹)	93.3	52.4	155.7	161.0
AV (mg KOH g ⁻¹)	91.9	54.6	160.3	211.9

(B) Engine Testing(a) Engine

Valve seat recession tests were carried out in a Ford Industrial Engine having a 2.2 litre displacement.

(b) Basic Test Procedure

Literature has shown that exhaust valve seat recession is more likely to occur during high speed, high load conditions. The following test conditions were used in all tests:

Test Conditions	
Engine Speed RPM	2100 ± 20
Load	WOT (Wide-Open Throttle)
Tests were run for 40 hours.	

(c) Fuel

The base fuel was unleaded Indolene.

(d) Cylinder Head Rebuild

The cylinder head was rebuilt for each test. In each case, new exhaust valves, exhaust valve seat inserts, and intake valve seals were installed. Valve seat inserts were checked for hardness and only those between 10 and 20 Rockwell "C" hardness were selected for testing. Valve guides were either replaced or knurled and reamed as necessary to maintain specified clearances. In most cases, the exhaust valve guides were replaced every other cylinder head rebuild and the intake valve guides every third or fourth rebuild. Valve springs were replaced as necessary.

(e) Compositions Tested

The formulations of Examples 1, 3, and 5 were tested in combination with a detergent additive system which was used at 700 ppm by volume on the base fuel. The formulation of Example 1 was used at 122 ppm by volume and contributed 9.7 ppm w/v potassium to the test gasoline.

Comparison Test 1

Example 1 was repeated except that the composition (e) was omitted.

Comparison Test 2

Example 1 was repeated except that the composition (e) was omitted and in its place was used lead at a concentration of 0.15 g/l.

The results of Example 1 and Comparison Tests 1 and 2 are given in Table 3.

The results of Examples 3 and 5 together with those for the unleaded base are given in Table 4.

Table 3

Valve Seat Recession Test Results for Boronated Additives			
Fuel	Additive	Test Time (hours)	Average Valve Recession
			Master Valve 10 ⁻³ inch (mm)
Unleaded	None	40	28.0 (0.711)
Leaded	Pb 0.15 g l ⁻¹	40	0.8 (0.020)
Unleaded	Ex. 1	40	1.8 (0.046)

Table 4

Valve Seat Recession Test Results for Boron-Free Additives			
Fuel	Additive	Test Time (hours)	Average Valve Recession
			Master Valve 10 ⁻³ inch (mm)
Unleaded	None	40	28.7 (0.711)
Unleaded	Ex. 3	40	2.4 (0.061)
Unleaded	Ex. 5	40	1.3 (0.033)

The results reported in Tables 3 and 4 demonstrate that the additives according to the invention are effective for reducing valve seat recession in unleaded fuels.

Claims

1. A lead free or low lead fuel composition for use in internal combustion engines which composition comprises (A) a major amount of a fuel suitable for use in a spark ignition engine characterised in that the fuel composition further comprises (B) a minor amount of a composition comprising an alkali or



(d) Cylinder Head Rebuild

The cylinder head was rebuilt for each test. In each case, new exhaust valves, exhaust valve seat inserts, and intake valve seals were installed. Valve seat inserts were checked for hardness and only those between 10 and 20 Rockwell "C" hardness were selected for testing. Valve guides were either replaced or knurled and reamed as necessary to maintain specified clearances. In most cases, the exhaust valve guides were replaced every other cylinder head rebuild and the intake valve guides every third or fourth rebuild. Valve springs were replaced as necessary.

10 (e) Compositions Tested

The formulations of Examples 1, 3, and 5 were tested in combination with a detergent additive system which was used at 700 ppm by volume on the base fuel. The formulation of Example 1 was used at 122 ppm by volume and contributed 9.7 ppm w/v potassium to the test gasoline.

15 Comparison Test 1

Example 1 was repeated except that the composition (e) was omitted.

20 Comparison Test 2

Example 1 was repeated except that the composition (e) was omitted and in its place was used lead at a concentration of 0.15 g/l.

The results of Example 1 and Comparison Tests 1 and 2 are given in Table 3.

25 The results of Examples 3 and 5 together with those for the unleaded base are given in Table 4.

Table 3

Valve Seat Recession Test Results for Boronated Additives			
Fuel	Additive	Test Time (hours)	Average Valve Recession
			Master Valve 10 ⁻³ inch (mm)
Unleaded	None	40	28.0 (0.711)
Leaded	Pb 0.15 g/l ⁻¹	40	0.8 (0.020)
Unleaded	Ex. 1	40	1.8 (0.046)

Table 4

Valve Seat Recession Test Results for Boron-Free Additives			
Fuel	Additive	Test Time (hours)	Average Valve Recession
			Master Valve 10 ⁻³ inch (mm)
Unleaded	None	40	28.7 (0.711)
Unleaded	Ex. 3	40	2.4 (0.061)
Unleaded	Ex. 5	40	1.3 (0.033)

The results reported in Tables 3 and 4 demonstrate that the additives according to the invention are effective for reducing valve seat recession in unleaded fuels.

Claims

1. A lead free or low lead fuel composition for use in internal combustion engines which composition comprises (A) a major amount of a fuel suitable for use in a spark ignition engine characterised in that the fuel composition further comprises (B) a minor amount of a composition comprising an alkali or



alkaline earth metal salt in the form of a particulate dispersion, provided the alkali metal is not sodium

2. A fuel composition according to claim 1 wherein the metal salt of (B) is a salt of potassium.
- 5 3. A fuel composition according to any one of claims 1 and 2 wherein the metal salt of (B) is a salt of a carboxylic acid, carbonic acid or boric acid.
4. A fuel composition according to any one of the preceding claims wherein (B) incorporates a carrier for the metal salt.
- 10 5. A fuel composition according to claim 4 wherein the metal salt is incorporated in the carrier in the form of a particulate dispersion having a mean particle size of less than 1 micrometers
6. A fuel composition according to claim 5 wherein the mean particle size is less than 0.5 micrometers
- 15 7. A fuel composition according to any one of claims 4 to 6 wherein the metal salt is an alkali or alkaline earth metal borate.
8. A fuel composition according to claim 7 wherein the molar ratio of boron to metal is in the range from 0.33 to about 4.5.
- 20 9. A fuel composition according to claim 8 wherein the molar ratio of boron to metal is in the range from 0.33 to 2.5.
- 25 10. A fuel composition according to claim 9 wherein the molar ratio of boron to metal is about 1:1.
11. A fuel composition according to any one of claims 8 to 10 wherein the metal salt of (B) is a metal borate and (B) is prepared by wholly or partially desolvating a solvent-in-carrier emulsion of a solution of metal hydroxide and boric acid to provide a boron to metal molar ratio of $Z/3$ (wherein Z is the valency of the metal) to 4.5.
- 30 12. A fuel composition according to claim 11 wherein the metal salt of (B) is potassium borate and (B) is prepared by introducing into an inert, non polar carrier an aqueous solution of potassium hydroxide and boric acid and an emulsifier, vigorously agitating the mixture to provide an emulsion of the aqueous solution in the carrier and then heating at a temperature and for a time sufficient to provide the predetermined degree of dehydration in the emulsion.
- 35 13. A fuel composition according to any one of claims 8 to 10 wherein the metal salt of (B) is an alkali metal borate which is potassium borate and (B) is prepared by reacting an alkali metal carbonate-overbased carrier-soluble alkali metal sulphonate with boric acid in an amount sufficient to produce an intermediate alkali metal borate having a boron to alkali metal molar ratio of at least 5 and reacting the intermediate alkali metal borate with sufficient alkali metal hydroxide to produce an alkali metal borate having a boron to alkali metal molar ratio in the range from 0.33 to 4.5.
- 40 14. A fuel composition according to any one of the preceding claims wherein the amount of (B) in the fuel composition is sufficient to provide at least 2 ppm of metal based on the total weight of the fuel composition.
- 45 15. A fuel composition according to any one of claims 1 to 7 wherein the metal salt is either potassium carbonate or potassium bicarbonate.
- 50 16. The use of an alkali or alkaline earth metal salt provided the alkali metal is not sodium in the form of a particulate dispersion as a valve seat recession additive in a fuel composition which comprises (A) a major amount of a fuel suitable for use in an internal combustion engine and (B) a minor amount of a composition comprising said metal salt.
- 55

**Patentansprüche**

1. Bleifreie oder bleiarmer Kraftstoffzusammensetzung zur Verwendung in Verbrennungsmotoren, deren Zusammensetzung umfaßt (A) einen Hauptbestandteil eines zur Verwendung in funkengezündeten Motoren geeigneten Kraftstoffs, dadurch gekennzeichnet, daß die Kraftstoffzusammensetzung zusätzlich (B) einen geringeren Teil einer Zusammensetzung, umfassend ein Alkali- oder Erdalkalimetallsalz in Form einer teilchenförmigen Dispersion, umfaßt, mit der Maßgabe, daß das Alkalimetall nicht Natrium ist.
2. Kraftstoffzusammensetzung nach Anspruch 1, wobei das Metallsalz (B) ein Kaliumsalz ist.
3. Kraftstoffzusammensetzung nach einem der Ansprüche 1 und 2, wobei das Metallsalz von (B) ein Salz einer Carbonsäure, Kohlensäure oder Borsäure ist.
4. Kraftstoffzusammensetzung nach einem der vorangehenden Ansprüche, wobei (B) einen Träger für das Metallsalz einschließt.
5. Kraftstoffzusammensetzung nach Anspruch 4, wobei das Metallsalz in den Träger in Form einer teilchenförmigen Dispersion mit einer mittleren Teilchengröße von weniger als 1 µm eingemischt ist.
6. Kraftstoffzusammensetzung nach Anspruch 5, wobei der mittlere Teilchendurchmesser weniger als 0,5 µm beträgt.
7. Kraftstoffzusammensetzung nach einem der Ansprüche 4 bis 6, wobei das Metallsalz ein Alkali- oder Erdalkalimetallborat ist.
8. Kraftstoffzusammensetzung nach Anspruch 7, wobei das Molverhältnis von Bor zu Metall im Bereich von 0,33 bis etwa 4,5 liegt.
9. Kraftstoffzusammensetzung nach Anspruch 8, wobei das Molverhältnis von Bor zu Metall im Bereich von 0,33 bis 2,5 liegt.
10. Kraftstoffzusammensetzung nach Anspruch 9, wobei das Molverhältnis von Bor zu Metall etwa 1:1 beträgt.
11. Kraftstoffzusammensetzung nach einem der Ansprüche 8 bis 10, wobei das Metallsalz von (B) ein Metallborat ist und (B) völlig oder teilweise durch Desolvatisieren einer Lösungsmittel-in-Trägeremulsion einer Lösung von Metallhydroxid und Borsäure unter Bereitstellung eines Bor-zu-Metall-Molverhältnisses von Z/3 (wobei Z die Wertigkeit des Metalls darstellt) bis 4,5 hergestellt wird.
12. Kraftstoffzusammensetzung nach Anspruch 11, wobei das Metallsalz von (B) Kaliumborat ist und (B) hergestellt wird durch Einführung einer wässrigen Lösung von Kaliumhydroxid und Borsäure und einem Emulgator in einen inerten unpolaren Träger, heftiges Bewegen des Gemisches unter Bereitstellung einer Emulsion der wässrigen Lösung in dem Träger und anschließend Erhitzen bei einer Temperatur und für eine Zeit, die ausreicht, den vorbestimmten Grad an Entwässerung in der Emulsion bereitzustellen.
13. Kraftstoffzusammensetzung nach einem der Ansprüche 8 bis 10, wobei ein Metallsalz von (B) ein Alkalimetallborat ist, nämlich Kaliumborat und (B) hergestellt wird durch Umsetzen eines mit Alkalimetallcarbonat überbasifizierten, trägerlöslichen Alkalimetallsulfonats mit Borsäure in einer Menge, die ausreicht, um ein Alkalimetallboratzwischenprodukt mit einem Bor-zu-Alkalimetall-Verhältnis von mindestens 5 herzustellen und Umsetzen des Alkalimetallboratzwischenprodukts mit ausreichend Alkalimetallhydroxid unter Bereitstellung eines Alkalimetallborats mit einem Bor-zu-Alkalimetall-Verhältnis im Bereich von 0,33 bis 4,5.
14. Kraftstoffzusammensetzung nach einem der vorangehenden Ansprüche, wobei die Menge von (B) in der Kraftstoffzusammensetzung ausreicht, um mindestens 2 ppm Metall, bezogen auf das Gesamtgewicht der Kraftstoffzusammensetzung, bereitzustellen.



15. Kraftstoffzusammensetzung nach einem der Ansprüche 1 bis 7, wobei das Metallsalz entweder Kaliumcarbonat oder Kaliumbicarbonat ist.
16. Verwendung eines Alkali- oder Erdalkalimetallsalzes, mit der Maßgabe, daß das Alkalimetall nicht Natrium ist, in Form einer teilchenförmigen Dispersion in einer Kraftstoffzusammensetzung als Additiv zur Verminderung der Aushöhlung des Ventilsitzes, umfassend (A) einen Hauptanteil eines Kraftstoffs, geeignet zur Verwendung in einem Verbrennungsmotor und (B) einen geringeren Anteil einer das Metallsalz umfassenden Zusammensetzung.

10 Revendications

1. Composition de carburant sans plomb ou pauvre en plomb pour emploi dans des moteurs à combustion interne, composition qui comporte (A) une proportion majeure d'un carburant convenant pour emploi dans un moteur à allumage par étincelle caractérisée par le fait que la composition du carburant comporte en outre (B) une proportion mineure d'une composition comprenant un sel d'un métal alcalin ou alcalino-terreux sous la forme d'une dispersion particulaire, sous réserve que le métal alcalin ne soit pas le sodium.
2. Composition de carburant selon la revendication 1, dans laquelle le sel métallique de (B) est un sel de potassium.
3. Composition de carburant selon l'une quelconque des revendications 1 et 2 dans laquelle le sel métallique de (B) est un sel d'un acide carboxylique, d'un acide carbonique ou d'un acide borique.
4. Composition de carburant selon l'une quelconque des revendications précédentes, dans laquelle (B) contient un support pour le sel métallique.
5. Composition de carburant selon la revendication 4, dans laquelle le sel métallique est incorporé dans le support sous forme d'une dispersion particulaire présentant une granulométrie moyenne inférieure à 1 μm .
6. Composition de carburant selon la revendication 5, dans laquelle la granulométrie moyenne est inférieure à 0,5 μm .
7. Composition de carburant selon l'une quelconque des revendications 4 à 6, dans laquelle le sel métallique est un borate d'un métal alcalin ou alcalino-terreux.
8. Composition de carburant selon la revendication 7, dans laquelle le rapport molaire entre le bore et le métal se situe dans la gamme allant de 0,33 à environ 4,5.
9. Composition de carburant selon la revendication 8, dans laquelle le rapport molaire entre le bore et le métal se situe dans la gamme allant de 0,33 à 2,5.
10. Composition de carburant selon la revendication 9, dans laquelle le rapport molaire entre le bore et le métal est d'environ 1:1.
11. Composition de carburant selon l'une quelconque des revendications 8 à 10, dans laquelle le sel métallique de (B) est un borate métallique et dans laquelle on prépare (B) en dissolvant, complètement ou partiellement, une émulsion, du type solvant dans le support, d'une solution d'hydroxyde métallique et d'acide borique pour donner un rapport molaire bore-métal de $Z/3$ (où Z est la valence du métal) de 4,5.
12. Composition de carburant selon la revendication 11 dans laquelle le sel métallique de (B) est du borate de potassium et dans laquelle on prépare (B) en introduisant dans un support inerte, non polaire, une solution aqueuse d'hydroxyde de potassium et d'acide borique et un émulsifiant, en agitant vigoureusement le mélange pour obtenir une émulsion de la solution aqueuse dans le support puis en chauffant à une température et pendant une durée suffisantes pour obtenir le degré prédéterminé de déshydratation de l'émulsion.



- 5 13. Composition de carburant selon l'une quelconque des revendications 8 à 10, dans laquelle le sel métallique de (B) est un borate d'un métal alcalin qui est un borate de potassium et dans laquelle on prépare (B) en faisant réagir avec l'acide borique un sulfonate de métal alcalin, soluble dans le support et présentant un excès basique de carbonate de métal alcalin, dans une proportion suffisante pour donner un borate intermédiaire de métal alcalin présentant un rapport molaire bore-métal alcalin d'au moins 5 et en faisant réagir le borate intermédiaire de métal alcalin avec suffisamment d'hydroxyde de métal alcalin pour obtenir un borate de métal alcalin présentant un rapport molaire bore-métal alcalin de 0,33 à 4,5.
- 10 14. Composition de carburant selon l'une quelconque des revendications précédentes, dans laquelle la proportion de (B) dans la composition du carburant est suffisante pour donner au moins 2 ppm de métal sur la base du poids total de la composition de carburant.
- 15 15. Composition de carburant selon l'une quelconque des revendications 1 à 7, dans laquelle le sel métallique est soit du carbonate de potassium, soit du bicarbonate de potassium.
- 20 16. Emploi d'un sel d'un métal alcalin ou alcalino-terreux, sous réserve que le métal alcalin ne soit pas le sodium, sous forme d'une dispersion particulière comme additif empêchant le creusement du siège de soupape dans une composition de carburant qui comporte (A) une proportion majeure d'un carburant convenant pour emploi dans un moteur à combustion interne et (B) une proportion mineure d'une composition comprenant ledit sel métallique.

25

30

35

40

45

50

55