

Polyoxymethylene molding compositions

Abstract

5 Thermoplastic molding compositions, comprising

A) from 15 to 99.94% by weight of a polyoxymethylene homo- or copolymer

B) from 0.05 to 10% by weight of a nonpolar polypropylene wax,

10

C) from 0.01 to 5% by weight of at least one ester or amide of saturated or unsaturated aliphatic carboxylic acids having from 10 to 40 carbon atoms with saturated aliphatic alcohols or amines having from 2 to 40 carbon atoms,

15

D) from 0 to 80% by weight of other additives,

where the total of the percentages by weight of components A) to D) is always 100%.