



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08F 12/00, C08J 9/20, 9/12	A1	(11) International Publication Number: WO 98/01488 (43) International Publication Date: 15 January 1998 (15.01.98)
(21) International Application Number: PCT/EP97/03609 (22) International Filing Date: 3 July 1997 (03.07.97) (30) Priority Data: 96201905.5 4 July 1996 (04.07.96) EP (34) Countries for which the regional or international application was filed: GB et al. (71) Applicant (for all designated States except US): SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): CREVECOEUR, Jeroen, Joost [NL/NL]; TU Eindhoven, Den Dolech 2, NL-5612 AZ Eindhoven (NL). NEIJMAN, Eric, Wilhelmus, Johannes, Frederik [NL/NL]; BPM, Lijndonk 25, NL-4825 BG Breda (NL). NELISSEN, Laurentius, Nicolaas, Ida, Hubertus [NL/NL]; TU Eindhoven, Den Dolech 2, NL-5612 AZ Eindhoven (NL). ZUIDERVELD, Johannes, Maria [NL/NL]; BPM, Lijndonk 25, NL-4825 BG Breda (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> 9806248-2
(54) Title: PROCESS FOR THE PREPARATION OF POLYMER PARTICLES (57) Abstract Process for the preparation of polymer particles containing a vinylarene polymer, which process comprises reacting a vinylarene monomer together with a copolymerisable compound containing a polar moiety and a vinyl moiety to a conversion degree of 20 to 70 %; suspending the pre-polymerised mass; and polymerising the vinylarene monomer in the suspended droplets.		