

Claims

1. Polyesters obtained from internal epoxides that are derived from internal olefins comprising 10 to 24 carbon atoms, or from diols that are derived from that internal epoxides, and saturated
5 linear aliphatic dicarboxylic acids comprising 5 to 13 carbon atoms.
2. The polyesters according to claim 1, wherein the internal olefin comprises not more than 30 mol%, preferably not more than 20 mol%, of double bonds being in the alpha-position.
- 10 3. The polyesters according to claim 1 or 2, wherein the internal olefin comprises 12 to 20 carbon atoms, preferably 14 to 18 carbon atoms.
4. The polyesters according to any one of claims 1 to 3, wherein the dicarboxylic acid is a saturated linear aliphatic dicarboxylic acid selected from the group consisting of glutaric acid
15 (pentanedioic acid), 2,2-dimethylglutaric acid (2,2-dimethylpentanedioic acid), adipic acid (hexanedioic acid), 2,4,4-trimethyladipic acid (2,4,4-trimethylhexanedioic acid), pimelic acid (heptanedioic acid), suberic acid (octanedioic acid), azelaic acid (nonanedioic acid), sebacic acid (decanedioic acid), undecanedioic acid, dodecanedioic acid, brassylic acid (tridecanedioic acid) and mixtures thereof; preferred are azelaic acid (nonanedioic acid), sebacic acid (decanedioic
20 acid), dodecanedioic acid and mixtures thereof.
5. The polyesters according to any one of claims 1 to 4, wherein the polyesters are characterized by a melting point of equal to or below -15°C, preferably equal to or below -25°C; more preferably they do not have any melting point.
25
6. The polyesters according to any one of claims 1 to 5, wherein the polyesters are characterized by a glass transition temperature of equal to or below -50°C.
7. The polyesters according to any one of claims 1 to 6, having a number-average molecular
30 weight M_n in the range of 1,000 to 15,000 g/mol, determined by size exclusion chromatography (SEC) using polymethylmethacrylate standards.
8. The polyesters according to any one of claims 1 to 7, characterized by a KV100 in the range of 40 to 2000 cSt, preferably in the range of 100 to 1000 cSt.
35
9. The polyesters according to any one of claims 1 to 8, wherein the molar ratio of carbon to oxygen, calculated by summing up the number of carbon atoms present in the diol and in the diacid

- 20 -

monomers and dividing the resulting numbers by four as being the number of oxygen atoms in the resulting diester unit, is in the range of 4:1 to 12:1.

10. Use of the polyesters according to any one of claims 1 to 9 as base oils in lubricant
5 formulations, especially in gear oil formulations.
11. Lubricating composition, comprising:
- 10 (A) 20 to 60% by weight of at least one polyester prepared from internal epoxides that are derived from internal olefins comprising 10 to 24 carbon atoms, or from diols that are derived from that internal epoxides, and saturated linear aliphatic diacids comprising 5 to 13 carbon atoms;
- (B) 40 to 80% by weight of a base oil selected from the group consisting of API Group II oils, API Group III oils, API Group IV oils, and mixtures thereof; and
- 15 (C) 0 to 5% by weight of one or more additives, based on the total weight of the lubricating composition.
12. Lubricating composition according to claim 11, wherein the internal olefin of component (A) comprises 12 to 20 carbon atoms, preferably 14 to 18 carbon atoms.
- 20 13. Lubricating composition according to claim 11 or 12, characterized in that the one or more further additives (C) are selected from the group consisting of pour point depressants, dispersants, defoamers, detergents, demulsifiers, antioxidants, antiwear additives, extreme pressure additives, friction modifiers, anticorrosion additives, dyes and mixtures thereof.
- 25 14. Method for preparing the polyesters according to any one of claims 1 to 9, the process comprising the steps of:
- (a) isomerizing an alpha-olefin comprising 10 to 24 carbon atoms, preferably 12 to 20 carbon atoms, more preferably 14 to 18 carbon atoms, to an internal olefin;
- (b) epoxidizing the internal olefin retrieved under step (a);
- 30 (c1) reacting the internal epoxide retrieved under step (b) with a saturated linear aliphatic dicarboxylic acid comprising 5 to 13 carbon atoms, or
- (c2) transferring the internal epoxide retrieved under step (b) to the corresponding diol and reacting the diol with a dicarboxylic acid comprising 5 to 13 carbon atoms; and
- (d) isolating the desired polyester.

35