

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H05K 9/00	A1	(11) International Publication Number: WO 99/40770 (43) International Publication Date: 12 August 1999 (12.08.99)
(21) International Application Number: PCT/NL99/00056 (22) International Filing Date: 3 February 1999 (03.02.99) (30) Priority Data: 1008197 4 February 1998 (04.02.98) NL (71) Applicant (for all designated States except US): STORK SCREENS B.V. [NL/NL]; Raamstraat 3, NL-5831 AT Boxmeer (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): BERGSHOEFF, Pieter, Dick [NL/NL]; De Weertjes 1019, NL-6605 RA Wijchen (NL). MACHIELSE, Jacob, Joost [NL/NL]; Van Vlieten- straat 151, NL-5975 SE Sevenum (NL). BLANKENBORG, Stephanus, Gerardus, Johannes [NL/NL]; Veemarkt 10, NL-6511 ZD Nijmegen (NL). (74) Agent: VOLMER, J., C.; Exter Polak & Charlois B.V., P.O. Box 3241, NL-2280 GE Rijswijk (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>In English translation (filed in Dutch).</i>
(54) Title: METHOD OF FABRICATING A SUPPORT PROVIDED WITH SHIELDING AGAINST INTERFERING RADIATION, AND SHIELDING MATERIAL (57) Abstract <p>A method of fabricating a support provided with shielding against interfering radiation, such as electromagnetic radiation, according to the invention involves a metallized plastic substrate, the metal comprising tin, being placed into an injection mould, and a plastic being injected into the mould to form the support. The tin-coated plastic substrate can be deformed very readily, so that it can be deformed three-dimensionally without its shielding characteristics being impaired.</p>		