

An Endothermic Heat Shield Composition And A Method For The Preparation Thereof

Field of Invention

The present invention relates to an endothermic heat shield composition and a method for the preparation thereof. More specifically, the present invention provides an endothermic heat shield composition, comprising at least 50 wt/wt% hydrated salt and at least one filler material, wherein the salt is in the form of hydrated salt particles which are fused to each other.

Background of the Invention

Prior art publications disclose intumescent and/or endothermic heat shield compositions containing hydrated salts. However, the hydrated salts therein are in aggregate form and do not have a chemical relationship (a fused relationship), with the surrounding salts. In order to contain the hydrated salts within these compositions, the prior art utilizes various binder materials for holding the hydrated salt aggregates together, thereby forming a solid composition. Furthermore, since the hydrate salt aggregates do not have a fused relationship, the grain size of the hydrated salts disclosed by the prior art is of importance. Moreover, as will become evident from the discussion below, the prior art does not disclose heating the hydrated salts during preparation to a temperature at which they become liquid.

U.S. Patent 5,082,877 discloses an ablative protective composition containing a polymeric binder component and an ablative component. The above patent requires the presence of a binder in addition to limiting the temperature at which the process of preparation is carried out. In column 6, lines 54-60 of this patent, it is stated "When preparing the novel heat/fire protective material, it is critical that the temperatures employed during preparation do not result in the decomposition of the aluminum sulfate hydrate. As stated earlier, according to CRC Handbook of Chemistry and Physics, 57th ed., aluminum sulfate hydrate decomposes at 86.5 °C. As such, if processing temperatures exceed 86.5 °C, the heat/fire protective properties of the resulting composition will significantly diminish." In contrast to U.S. 5,082,877, the present invention utilizes temperatures exceeding 86°C (in the case of aluminum sulfate hydrate), and does not require binders for holding the salt grains together.

U.S. Patent 4,632,865 describes and claims an insulation material for use in heat protective



devices which comprises a structure having two or more layers, arranged so that the external layer has a higher melting temperature or temperature of dehydration than any layer, the external layer comprising:

- an inorganic salt selected from the group consisting of $\text{Al}_2(\text{SO}_4)_3 \cdot 16-18\text{H}_2\text{O}$, $\text{KAl}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$, and $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$, and
- a binder selected from the group consisting of natural rubber, neoprene rubber, silicone rubber, polyester resin, epoxy resin, phenolic resin and hydraulic cement.

U.S. No. 4,632,865 specifies that the temperature for preparing the above material should not exceed the hydration temperature

U.S. Patent 4,462,831 discloses a non-refractory ablative, fire- and heat-protection material for a one time use, comprising an organic binder selected from the group consisting of natural and synthetic polymers, rubbers, natural and synthetic resins, natural and synthetic asphalts and bitumens including latexes, solutions of the above substances or mixtures thereof, and a filler consisting of hydrated aluminum sulfate of the general formula $\text{Al}_2(\text{SO}_4)_3 \cdot n\text{H}_2\text{O}$ wherein $n=14-18$ in an amount of more than 75% by weight of the material, the filler being free of any cementitious material.

U.S. Patent 4,122,059 discloses a composition of matter, including a mixture of fire-resistant materials, which mixture comprises a hydraulic cement and an inorganic salt hydrate selected from the group consisting of aluminum sulfate hydrate and ferrous sulfate hydrate and which mixture has been uniformly distributed in a synthetic, organic polymer and which mixture comprises from about 5% to about 80% by weight of said hydrated salt, from about 1% to about 10% by weight of a hydraulic cement, and about 1% to about 10% of aluminum silica, the percentages being based upon the total weight of said mixture.

The above patent states that "The powders when exposed to flame or heat convert to refractory substances. Water from the hydrate is driven off into contact with the cement with the resulting setting of the cement...". U.S. 4,122,059 requires the cement to act as a binder since there is no chemical relationship between the inorganic salt hydrates. Furthermore, it should be noted that the conversion of the powders into refractory substances does not occur during the manufacturing process, but rather during an event of fire.

In U.S. patent 5,104,917 heat ablative compositions are described and claimed which



comprise a binder and a filler, including a combination of aluminum sulfate hydrate and aluminum ammonium sulfate hydrate. The combination produces a synergistic effect on the fire protection rating of the composition. The binder may be chosen from inorganic or organic binders. Examples of binders according to the above patent are natural and synthetic rubbers.

The above patent further states that "The acidic character of aluminum sulfate hydrate has numerous consequences on the performance of the heat ablative composition. The acidity may cause the destruction of the binder, which results in decreased F.P.R.'s. Aluminum sulfate hydrate's acidity may also result in cracking, brittleness and total loss of impact resistance of the binder, and loss of tensile strength, compressive strength or bending strength in the finished ablative product. The excess acidity may result in erosion or destruction by oxidation of the substructure to which the ablative composition is applied."


In contrast to the above, the stability of the composition according to the present invention is based on the mechanical strength, which results from the bonds within the crystal/fused structure of the hydrate salt. The filler component of the present invention is stable and does not chemically react with the hydrate salt.

Canadian patent 2,228,479 describes and claims a fireproof sealing system based on molten adhesives, containing a) a molten adhesive; b) binders; c) substances forming a carbon structure in the event of a fire; d) flame-protecting agents; and e) a component which swells in the event of a fire; and a process for the flameproof sealing of objects or apertures by the application of such sealing systems.

The above patent utilizes heat to melt the thermoplastic components which function as binders.

As shown above, the prior art does not teach a heat shield material in which the hydrated salt particles are fused to each other. Thus, in accordance with the prior art, binder materials are needed for holding the hydrated salt particles together.

It is therefore an object of the present invention to provide a new and improved heat shield composition and method for producing the same which overcomes the disadvantages of the prior art which necessitate the utilization of binder materials. In contrast to the prior art, the present invention utilizes the crystal formation of the hydrated salt in combination with waste products. The



elimination of binder materials significantly reduces the manufacturing cost of the heat shield composition.

Thus, according to the present invention, an endothermic heat shield composition is provided, comprising at least 50 wt/wt% hydrated salt and at least one filler material, wherein the hydrated salt particles are fused to each other, wherein said fused state is formed as a result of the heating of the hydrated salt to at least the temperature at which said salt is in liquid form and the subsequent cooling thereof.

According to the present invention, the hydrated salts are selected from the group consisting of $\text{Al}_2(\text{SO}_4)_3 \cdot 16-18\text{H}_2\text{O}$; $\text{NH}_4\text{Fe}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$; $\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$; $\text{NaAl}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$; $\text{AlNH}_4(\text{SO}_4)_2 \cdot 12-24\text{H}_2\text{O}$; $\text{Na}_2\text{SO}_4 \cdot 10\text{H}_2\text{O}$; $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$; $(\text{NH}_4)_2\text{SO}_4 \cdot 12\text{H}_2\text{O}$; $\text{KAl}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$; $\text{Na}_2\text{SiO}_3 \cdot 9\text{H}_2\text{O}$; $\text{Mg}(\text{NO}_2)_2 \cdot 6\text{H}_2\text{O}$; NaNO_2 ; $\text{Na}_2\text{CO}_3 \cdot 7\text{H}_2\text{O}$; and mixtures thereof.

In a further preferred embodiment, the present invention provides an endothermic heat shield composition, wherein at least 50% of the hydrated salt is hydrated aluminum sulfate. This sulfate is easy to obtain and is relatively inexpensive.

In a preferred embodiment, the filler material is a material selected from the group consisting of an organic component and an inorganic component and mixtures thereof.

In an even further preferred embodiment, the organic component is a solid cellulose-based component. Specifically, the solid cellulose-based component is selected from the group consisting of wood particles and paper particles.

In the present invention; the solid cellulose-based component preferably present in an amount ranging from about 5 wt/wt% to 30 wt/wt%.

In another preferred embodiment, the inorganic component is inert, highly porous and light weight. Specifically, the inorganic component is Vermiculite or Perlite and is preferably present in an amount ranging from about 5 wt/wt% to 30 wt/wt%. It should be noted that other porous solid volcanic materials can be used in accordance with the present invention.

The present invention also provides an endothermic heat shield composition wherein the organic component is sugar molasses preferably present in an amount of up to 20 wt/wt%.

In a further preferred embodiment, the inorganic component may be glass fibers or ceramic



fibers which are preferably present in an amount of up to 10 wt/wt%.

In another preferred embodiment, the inorganic component is selected from the group consisting of titanium dioxide, magnesium oxide and aluminum oxide which is preferably present in an amount of up to 30 wt/wt%.

In another aspect of the present invention, a method is provided for preparing an endothermic heat shield composition, which comprises at least 50 wt/wt% hydrated salt and at least one filler material, the method comprising the steps of:

- a) heating the hydrated salt to the temperature at which it liquefies;
- b) adding at least one filler material; and
- c) cooling the mixture to form a composition wherein the hydrated salt particles are fused to each other.

In this aspect of the present invention, there is provided a method, wherein the hydrated salt is selected from the group consisting of $\text{Al}_2(\text{SO}_4)_3 \cdot 16-18\text{H}_2\text{O}$; $\text{NH}_4\text{Fe}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$; $\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$; $\text{NaAl}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$; $\text{AlNH}_4(\text{SO}_4)_2 \cdot 12-24\text{H}_2\text{O}$; $\text{Na}_2\text{SO}_4 \cdot 10\text{H}_2\text{O}$; $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$; $(\text{NH}_4)_2\text{SO}_4 \cdot 12\text{H}_2\text{O}$; $\text{KAl}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$; $\text{Na}_2\text{SiO}_3 \cdot 9\text{H}_2\text{O}$; $\text{Mg}(\text{NO}_2)_2 \cdot 6\text{H}_2\text{O}$; NaNO_2 ; $\text{Na}_2\text{CO}_3 \cdot 7\text{H}_2\text{O}$; and mixtures thereof.

In a most preferred embodiment of this aspect of the present invention, at least 50% of the hydrated salt is hydrated aluminum sulfate.

In a preferred method of this aspect of the present invention, the filler material is a material selected from the group consisting of an organic component and an inorganic component.

In another preferred method of this aspect of the present invention, the organic component is a solid cellulose-based component. Specifically, the solid cellulose-based component is selected from the group consisting of wood particles and paper particles. The cellulose-based component is preferably present in an amount ranging from about 5 wt/wt% to 30 wt/wt%.

In another preferred method according to this aspect of the present invention, the inorganic component is inert, highly porous and light weight. Specifically, the inorganic component is Vermiculite or Perlite and is preferably present in an amount ranging from about 5 wt/wt% to 30 wt/wt%.

In an even further preferred method of this aspect of the present invention, the organic component is sugar molasses preferably present in an amount of up to 20 wt/wt%.

In a further preferred embodiment method of this aspect of the present invention, the



inorganic component may glass fibers or ceramic fibers which are preferably present in an amount of up to 10 wt/wt%.

In another preferred embodiment method of this aspect of the present invention, the inorganic component is selected from the group consisting of titanium dioxide, magnesium oxide and aluminum oxide which is preferably present in an amount of up to 30 wt/wt%.

In a preferred method of this aspect of the present invention, a further step is provided for adding up to about 10 wt/wt% of water to the hydrated salt prior to heating.

The composition of the present invention contains a filler which is trapped within the fused structure of the hydrated salt. The function of the filler is important when the composition is exposed to high temperatures, since the filler assists the composition in retaining its solidified state and not reverting back to the liquid state it possessed during preparation.

In the present invention, preferable fillers are cellulose-based, such as wood or paper particles since they exhibit high absorption properties

Most of the compositions of the material of the present invention also have intumescent properties, in addition to endothermic properties.

An intumescent composition, when heated to the temperature at which the agent intumesces, results in the composition expanding many times its original volume, forming a charred layer which provides a protective barrier from the source of the heat, as well as from the heat itself.

The combination of intumescent and endothermic properties is important since the intumescent characteristics of a composition allows the expansion thereof, whereby upon exposure to heat an outer protective barrier is formed allowing the isolation of the inner part of the composition. The endothermic characteristics significantly increase the difference in temperature between the inner and outer parts of the composition, thereby isolating the object contained within the composition from fire and heat.

The composition of the material also includes fillers which enhance the composition's expansion and the formation of the outer protective layer. An example of such a filler is sugar molasses, which is a by-product of sugar production. Furthermore, the fillers of the present invention promote the viscosity characteristics of the composition, thereby inhibiting the composition from changing into the liquid phase



A theoretical disadvantage of the intumescent, endothermic composition of the material of the present invention is its dependency on temperature. As the temperature rises, the composition shifts/moves towards its liquid state. Presumably, the above dependency contradicts the composition's role of protection at high temperatures. However, the composition, in fact, does act as a protective material.

The powder/particles which are a part of the composition of the present invention play a key role in retaining the composition in a semi-liquid state. Two types of temperature elevation at high temperatures are to be considered. One is a gradual, uniform elevation in which the composition may revert to the semi-liquid state it had during production, but not reaching a liquid state. The second is a quick elevation, such as would occur in the case of a fire in which the outer section of the composition becomes rigid and dry, thereby protecting the inner segment from liquefying.


The organic components of the present invention include waste products produced from filing plywood and wood. MDF and ground paper can also be used as the organic component. The porosity characteristics of the above components appear to play a key role in the absorption of the liquid hydrated salt by these components. The present inventor also found that the small size of the above components is important in enhancing the isolation provided by the heat shield composition of the present invention. In addition to the above components being inexpensive, a further advantage exists in using them since it is difficult to discard them since they are dispersed by the wind.

The present invention demonstrates that the use of small cellulose particles having low specific weight and high absorption potential permits their use in small amounts in the composition. Apparently, the small cellulose particles promote the formation of bubbles in a homogeneous manner.

The inorganic components of the present invention include vermiculite and Perlite which enhance the composition's resistance due to their low molecular weight, which is a result of high porosity and their stability at relatively high temperatures.

The present invention utilizes the small waste particles which are the waste products of processes utilizing Vermiculite and Perlite. As described in relation to the organic components, the small size of the components and their use are advantageous for the present invention.

The method the present invention for preparation of a solid heat shield composition allows



the solidification and crystallization of the hydrate salt.

The composition of the present invention has a molecular structure which is different from known isolation materials. According to the present invention, the components (hydrate salt and filler material) are heated to a temperature at which a liquid is produced. On the other hand, according to the prior art, no heat is utilized to promote bonds between the hydrate salt and therefore various binders are required to maintain the salts in close vicinity to each other.

Some of the hydrated salts of the present invention, such as aluminum sulfate, decompose when exposed to a temperature at which they liquefy, and then become soluble in the water released. Other hydrated salts of the present invention, such as magnesium nitrate hexahydrate, liquefy without the step of decomposing.

As can be seen, the present invention achieves a fused structure formed by the interactions between the hydrated salts. The above structure allows for the stability of the composition without the utilization of binders which increase the cost. In addition, the use of binders may reduce over time the stability of the solid material due to the aging of the organic binder in the presence of the hydrate fillers.

The simplified method of preparation according to the present invention also allows for a rapid solidification period of the composition enabling its use thereof shortly after the preparation process has been completed.

The uses of the composition according to the present invention are numerous. The composition can be used in the construction of buildings, safes, airplanes, automobiles, ships and the like.

In a preferred method of using the above described endothermic material, a modular fire protector can be constructed. In such a case, a method for producing a modular fire protector, in accordance with the present invention, comprises the steps of: providing a double metal wall; and providing a plurality of thermal protective layers associated with the double metal wall, the plurality of thermal protective layers having at least one layer of intumescent material. Preferably, holes internally covered by a plastic sheet of material are provided for permitting the intumescent material to traverse the double metal wall after the plastic sheet has melted during a period when the environment surrounding the double metal wall becomes heated. More preferably, a major portion



of the intumescent material is present in the vicinity of the holes. Most preferably, a step is provided in the double metal wall.

Furthermore, according to the present invention, apparatus for producing a modular fire protector comprises: a double metal wall; and a plurality of thermal protective layers associated with the double metal wall, the plurality of thermal protective layers having at least one layer of intumescent material. Preferably, the double metal wall includes holes internally covered by a plastic sheet of material for permitting the intumescent material to traverse the double metal wall after the plastic sheet has melted during a period when the environment surrounding the double metal wall becomes heated. More preferably, a major portion of the intumescent material is present in the vicinity of the holes. Most preferably, the double metal wall includes a step.

Brief Description of the Drawings

Embodiments of the present invention are described by way of example with reference to the accompanying drawing wherein the Figure is a flow chart diagram representing, an embodiment of the present invention.

Fig. 2 is a schematic diagram of apparatus for producing a modular fire protector in accordance with one embodiment of the present invention;

Fig 2A is a schematic diagram of a connector according to one embodiment of the present invention associated with the embodiment of the modular fire protector shown in Figs. 1 and 6 according to one embodiment of the present invention;

Fig. 3 is a cross-section diagram of apparatus for producing a modular fire protector in accordance with an embodiment of the present invention;

Fig. 4 is a diagram of a side view of apparatus for producing a modular fire protector in accordance with an embodiment of the present invention;

Fig 5. is a diagram of a pin/connector connection made in accordance with an embodiment of the present invention;

Fig. 6 is a diagram of a screw connector or apparatus for producing a connection in accordance with an embodiment of the present invention;

Fig. 7 is a further diagram of apparatus for producing a connection in accordance with an



embodiment of the present invention.

Like reference numerals and designations in the various drawings refer to like elements.

Detailed Description of the Drawing:

Fig. 1 is a schematic illustration of a manufacturing line in accordance with the present invention.

Referring now to the figure, hydrated salts 10 are placed in a melting container 16 and heated by a heat source 12 to the temperature at which the solid salts become liquid. A liquid, water-based solution 14 may be added into container 16 prior to the application of heat.

When the contents of container 16 are in liquid form, the hot, liquid solution 22 is transferred to a second container 20 in which mixing means (not shown), combine said hot liquid solution with a solid, cellulose-based, organic component 18, which is preferably a waste product and with a solid inorganic granular component 22. Component 22 may include materials which promote intumescent characteristics, as well as including glass fibers (other fibers may also be used) which can increase the strength of the end product.

The contents of container 20 are then transferred in semi-liquid state 26 to a predetermined form of application. The form of application is dependent on the shape of the end product. More specifically, the mixture 26 can be applied by hand 28, spraying 30, casting 32, plate rolling 34, or by plate pressing 36.

As will be realized, mixture 26 can be applied onto or into numerous items. Once mixture 26 is applied and allowed to cool 38 it is in the form of a solid final product 40 which is ready for use.

Referring now to Fig. 2, reference numeral 110 designates an embodiment of apparatus for producing a modular fire protector in accordance with the present invention. As can be seen from the drawing, the apparatus comprises metal walls 112 and 114 as well as connectors 116 provided for connecting the apparatus to the required set up. Thus, in such a manner, apparatus 110 can be positioned in the required location.



Turning to Fig. 3, numeral 120 designates an embodiment of apparatus for producing a modular fire protector in accordance with the present invention wherein a cross-sectional view is shown. Metal walls 112 and 114 designate external and internal walls respectively and are provided with connectors 116A and 116B, while active insulating layer 22 comprising intumescent/endothermic material is covered by passive insulating layers 124 and 126. As can be seen from Fig. 3, perpendicular active insulating layers 128A and 128B comprising intumescent/endothermic material are provided and traverse holes or bores 130A and 130B provided in walls 132A and 132B respectively. Preferably, the present embodiment of the present invention is provided with a step wall member 134A and 134B at its ends respectively for facilitating positioning the modular fire protector. Thus, according to the present invention, holes or bores 130A and 130B are provided in step wall members 134A and 134B.

Fig. 4 provides a side view of the embodiment shown in Fig. 3. As can be seen from the figure, cover or seal 136 comprising thermo-plastic material, etc. is provided in accordance with the present invention for providing support and ensuring that the intumescent/endothermic material stays within the modular fire protector.

Various connectors can be used to connect the modular fire protectors to required structures or to position the modular fire protectors in a certain location. Fig. 5 shows pin/connector arrangement for use to connect the modular fire protectors in a certain location. Pin 142 is inserted in the hole or bore 144 or connector 146 as well in the bore or hole of connector 148 thus securing the modular fire protector 159 into position. Usually, the pin/connector arrangement is used internal to the volume to which protection is provided.

Figs. 6 and 7 show embodiments of screw connectors, submerged screw connectors 152 surrounded by intumescent/endothermic material 154 and screw connector channel 162 respectively. Screw connector channel 162 is lined with thermo-plastic material adjacent to which is intumescent/endothermic material layer 164.

When an occurrence of high temperature takes place, for example, the out-break of a fire or other production of heat or high temperature gases or environment, covers or seals 36 melt. This permits the intumescent/endothermic material to exit the modular fire protector 110 by traversing or flowing out of holes or bores 130A or 130B. The intumescent/endothermic material that exits



modular fire protector 110 fills spaces or deformations that are produced by onset of the high temperatures. Furthermore, thermo-plastic material lining channel 162 melts and intumescent/endothermic material present in layer 164 substantially seals the screw and channel 162. In such a manner, the protection provided by the modular fire protector can substantially be maintained.

Additionally, standard components can be used together with the modular fire protectors. Usually, suitable drilled holes or bores will be produced in the modular fire protectors to accommodate the use of the standard components.

The modular fire protectors and their use permit protected areas to be simply constructed and facilitate their disassembly and construction.

In addition, it should be noted that means mentioned in this specification refer to suitable means for carrying out the present invention.

Furthermore, it should be pointed out that the present invention includes as well the method for operating the apparatus disclosed with reference to the above-described figures.

It is believed that the advantages and improved results furnished by the method and apparatus of the present invention are apparent from the foregoing description of the invention. Various changes and modifications may be made without departing from the spirit and scope of the invention as described in the claims that follow the Examples.

While the invention will now be described in connection with certain preferred embodiments in the following examples so that aspects thereof may be more fully understood and appreciated, it is not intended to limit the invention to these particular embodiments. On the contrary, it is intended to cover all alternatives, modifications and equivalents as may be included within the scope of the invention as defined by the appended claims. Thus, the following examples which include preferred embodiments will serve to illustrate the practice of this invention. It is understood however, that the details shown are by way of example and for purposes of illustrative discussion of preferred embodiments of the present invention only and are presented for providing what is believed to be the most useful and readily understood description of formulation procedures as well as of the principles and conceptual aspects of the invention.



Example 1

87 wt/wt% of aluminum sulfate hydrate was heated to about 95°C-105°C. Once a liquid state was achieved, the following components were added while mixing:

13 wt/wt% chipboard and MDF particles powder (waste product).

The resulting semi-liquid mixture was rolled into a plate and cooled for 10 minutes.

Example 2

74 wt/wt% of aluminum sulfate hydrate was combined with 4 wt/wt% of sugar molasses, 5 wt/wt% water and heated to about 95°C-105°C. Once a liquid state was achieved, the following components were added while mixing:

14 wt/wt% wood particles (waste product)

3 wt/wt% $\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$.

The resulting semi-liquid mixture was pressed into a plate and cooled for 10 minutes.

Example 3

85 wt/wt% of potassium aluminum sulfate hydrate was combined with 2 wt/wt % of water and heated to about 95°C-105°C. Once a semi-liquid state was achieved, the following solid components were added while mixing:

11 wt/wt% MDF powder (waste product)

2 wt/wt % glass fibers.

The resulting semi-liquid mixture was pressed into a plate and cooled for 10 minutes.

Example 4

83 wt/wt% of $\text{Na}_2\text{CO}_3 \cdot 7\text{H}_2\text{O}$ was combined with 7 wt/wt% water and heated to about 60°C. Once a liquid state was achieved, 8 wt/wt% wood particles were added. The semi-liquid mixture was poured into a box. Cooling was carried out at around -20°C. The resulting composition does not have intumescent characteristics, however acts as an insulator at relatively low temperatures



Example 5

85 wt/wt% of magnesium nitrate hexahydrate was combined with 4 wt/wt% of water and heated to about 95°C. Once a semi-liquid state was achieved, 11 wt/wt% paper powder (waste product) was added.

The resulting semi-liquid mixture was pressed into a plate and cooled for 10 minutes.

Example 6

60 wt/w %t of aluminum sulfate 18 hydrate was combined with 3 wt/wt% of sugar molasses, 3 wt/wt% water, 5 wt/wt% of borax $\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$ and 5 wt/wt% of magnesium nitrate hexahydrate which were all mixed and heated to about 95°C-105°C. Once a semi-liquid state was achieved, the following components were added while mixing:

10 wt/wt% chip-board and MDF powder/particles (waste product)

5 wt/wt% of vermiculite waste powder

5 wt/wt% of magnesium oxide

2 wt/wt% of titanium oxide

2 wt/wt % glass fibers.

The resulting mixture was pressed into a mold and cooled for 10 minutes

It will be evident to those skilled in the art that the invention is not limited to the details of the foregoing illustrative examples and that the present invention may be embodied in other specific forms without departing from the essential attributes thereof, and it is therefore desired that the present embodiments and examples be considered in all respects as illustrative and not restrictive, reference being made to the appended claims, rather than to the foregoing description, and all chances which come within the meaning and range of equivalency of the claims are therefore intended to be embraced therein.

This Sheet Has Been Replaced





WHAT IS CLAIMED IS:

1. A method for producing a modular fire protector comprising the steps of:
 - a) providing a double metal wall; and
 - b) providing a plurality of thermal protective layers associated with said double metal wall, said plurality of protective layers having at least one layer of intumescent material.
2. A method according to claim 1 including providing holes internally covered by a plastic sheet of material for permitting the intumescent material to traverse said double metal wall after the plastic sheet has melted during a period when the environment surrounding said double metal wall becomes heated.
3. A method according to claim 2 including the provision that a major portion of the intumescent material is present in the vicinity of said holes.
4. A method according to claim 2 including providing a step in the double metal wall.
5. Apparatus for producing a modular fire protector comprising:
 - a) a double metal wall; and
 - b) a plurality of thermal protective layers associated with said double metal wall, said thermal protective layers having at least one layer of intumescent material.
6. Apparatus according to claim 5 wherein said double metal wall includes holes internally covered by a plastic sheet of material for permitting the intumescent material to traverse said double metal wall after the plastic sheet has melted during a period when the environment surrounding said double metal wall becomes heated.
7. Apparatus according to claim 6 wherein a major portion of the intumescent material is present in the vicinity of the holes.
8. Apparatus according to claim 6 wherein said double metal wall includes a step.

This Sheet Has Been Replaced

