

WO 2004/063815

PCT/US2002/015551

TITLE: METHOD AND SYSTEM FOR FABRICATING NANOSCALE PATTERNS IN LIGHT CURABLE COMPOSITIONS USING AN ELECTRIC FIELD

BACKGROUND OF THE INVENTION

1. **Field of the Invention**

This invention generally relates to the area of low cost, high-resolution, high-throughput lithography with the potential to make structures that are below 100nm in size.

2. **Description of the Relevant Art**

Optical lithography techniques are currently used to make microelectronic devices. However, these methods are reaching their limits in resolution. Sub-micron scale lithography has been a critical process in the microelectronics industry. The use of sub-micron scale lithography allows manufacturers to meet the increased demand for smaller and more densely packed electronic components on chips. The finest structures producible in the microelectronics industry are currently on the order of about 0.13 μm . It is expected that in the coming years, the microelectronics industry will pursue structures that are smaller than 0.05 μm (50 nm). Further, there are emerging applications of nanometer scale lithography in the areas of opto-electronics and magnetic storage. For example, photonic crystals and high-density patterned magnetic memory of the order of terabytes per square inch require nanometer scale lithography.

For making sub-50 nm structures, optical lithography techniques may require the use of very short wavelengths of light (for instance 13.2 nm). At these short wavelengths, few, if any, materials are optically transparent and therefore imaging systems typically have to be constructed using complicated reflective optics [1]. Furthermore, obtaining a light source that has sufficient output intensity at these wavelengths of light is difficult. Such systems lead to extremely complicated equipment and processes that appear to be prohibitively expensive. High-resolution e-beam lithography techniques, though very precise, typically are too slow for high-volume commercial applications.

One of the main challenges with current imprint lithography technologies is the need to establish direct contact between the template (master) and the substrate. This may lead to defects, low process yields, and low template life. Additionally, the template in imprint lithography typically is the same size as the eventual structures on the substrate (1X), as compared to 4X masks typically used in optical lithography. The cost of preparing the template and the life of the template are issues that may make imprint lithography impractical. Hence there exists a need for improved lithography techniques that address the challenges associated with optical lithography, e-beam lithography and imprint lithography for creating very high-resolution features.

SUMMARY OF THE INVENTION

In one embodiment, patterned structures may be created on a substrate using imprint lithography. The process involves applying a polymerizable composition to the upper surface of the substrate. The substrate may be a substrate used to prepare a semiconductor device. Examples of substrates include, but are not limited to, Si wafers, GaAs wafers, SiGeC wafers, or an InP wafers. The polymerizable composition may be an ultraviolet light curable composition. The ultraviolet light curable composition may include a polymerizable monomer and a photoinitiator. The composition may be spin coated onto the substrate.

WO 2004/063815

PCT/US2002/015551

After the substrate has been coated with the polymerizable composition a template may be placed above the polymerizable composition. The template is formed from an electrically conductive material. The template may also be substantially transparent to visible and/or ultraviolet light. The template may be formed of a combination of an electrically conductive material coupled to a non-conductive material. Both the electrically
5 conductive material and the non-conductive material may be substantially transparent to light. In one embodiment, the template may be formed of indium tin oxide and fused silica. The template includes a pattern of structures. The pattern of structures are complimentary to the pattern of structures which are to be produced on the substrate. At least a portion of the structures may have a feature size of less than about 100 nm.

An electric field may be applied between the template and the substrate. The application of the electric
10 field may create a static force that attracts at least a portion of the polymerizable composition toward the template. The portions of the polymerizable composition that are attracted to the template are complementary to the pattern of structures imprinted on the template. In one embodiment, the portions of the polymerizable composition that are attracted to the template come into contact with the template, while the remaining portions do not contact the template. Alternatively, neither the attracted portions nor the remaining portions of the polymerizable composition
15 come into contact with the template. The attracted portions, however, extend toward the template while the un-attracted portions do not extend to the same extent that the attracted portions extend toward the template.

The polymerizable composition may be polymerized using an appropriate curing technique. For example, the polymerizable composition may include a photoinitiator and be curable by exposure to activating light while an electric field is applied to the template and the substrate. As used herein "activating light" means light that may
20 affect a chemical change. Activating light may include ultraviolet light (e.g., light having a wavelength between about 300 nm to about 400 nm), actinic light, visible light or infrared light. Generally, any wavelength of light capable of affecting a chemical change may be classified as activating. Chemical changes may be manifested in a number of forms. A chemical change may include, but is not limited to, any chemical reaction that causes a polymerization or a cross-linking reaction to take place. The activating light may be passed through the template
25 prior to reaching the composition. In this manner the polymerizable composition may be cured to form structures complementary to the structures formed on the template. Alternatively, the polymerizable composition may be cured by applying heat to the composition, while an electric field is applied to the template and the substrate.

After the polymerizable composition is cured, the structures may be further defined by etching the cured polymerizable composition. Etching may improve the aspect ratio of the structures. Any of the commonly used
30 etching techniques may be used, including reactive ion etching.

In one embodiment, the template may be positioned less than about 1 μm from the polymerizable composition. The substrate should therefore have a planarity of less than about 1 μm , preferable less than about 0.25 μm . As used herein planarity is defined as the variance in curvature over the surface of the substrate. For example, a planarity of 1 μm indicates that the curvature of the surface varies by 1 μm above and/or below a center
35 point which defines a planar surface.

To achieve a surface having a planarity of less than about 1 μm , the substrate may be placed on an apparatus configured to alter the shape of the substrate. The apparatus may include a holder configured to couple to and support the substrate. The apparatus may also include a plurality of pressure application devices coupled to the holder. The pressure application devices may be configured to apply a deforming force to the holder such that
40 the shape of the holder is altered. The substrate may be coupled to the holder such that the changes in the shape of the holder may be imparted to the substrate. In this manner, the planarity of the substrate may be altered to conform

WO 2004/063815

PCT/US2002/015551

to the desired planarity. The apparatus may include a programmable controller. The programmable controller may include a detection device configured to determine the planarity of the substrate. The controller may further be configured to operate the pressure application devices to alter the planarity of the substrate based on the determined planarity.

5

BRIEF DESCRIPTION OF THE DRAWINGS

Other objects and advantages of the invention will become apparent upon reading the following detailed description and upon reference to the accompanying drawings in which:

Fig. 1 depicts a template positioned over a substrate for electric field based lithography using UV curable compositions;

10

Fig. 2 depicts a schematic of a process for forming nanoscale structures using direct contact with a template;

Fig. 3 depicts a schematic of a process for forming nanoscale structures using non-direct contact with a template;

15

Fig. 4 depicts a substrate holder configured to alter the planarity of the substrate; and

Fig. 5 depicts an apparatus for positioning a template over a substrate.

While the invention is susceptible to various modifications and alternative forms, specific embodiments thereof are shown by way of example in the drawings and will herein be described in detail. It should be understood, however, that the drawings and detailed description thereto are not intended to limit the invention to the particular form disclosed, but on the contrary, the intention is to cover all modifications, equivalents and alternatives falling within the spirit and scope of the present invention as defined by the appended claims.

20

DETAILED DESCRIPTION OF THE INVENTION

Recently imprint lithography techniques with UV curable liquids [2, 3, 4, 5] and polymers [6] have been described for preparing nanoscale structures. These techniques may potentially be significantly lower cost than optical lithography techniques for sub-50 nm resolution. Recent research [7, 8] has also investigated the possibility of applying electric fields and van der Waals attractions between a template that possesses topography and a substrate that contains a polymeric material to form nanoscale structures. This research has been for systems of polymeric material that may be heated to temperatures that are slightly above their glass transition temperature. These viscous polymeric materials tend to react very slowly to the electric fields (order of several minutes) making them less desirable for commercial applications.

25

30

The embodiments described herein may potentially create lithographic patterned structures quickly (in a time of less than about 1 second). The structures may have sizes of tens of nanometers. The structures may be created by curing a polymerizable composition (e.g., a spin-coated UV curable liquid) in the presence of electric fields. Curing the polymerizable composition then sets the pattern of structures on the substrate. The pattern may be created by placing a template with a specific nanometer-scale topography at a carefully controlled nanoscale distance from the surface of a thin layer of the liquid on a substrate. If all or a portion of the desired structures are regularly repeating patterns (such as an array of dots), the pattern on the template may be considerably larger than the size of the desired repeating structures. The template may be formed using direct write e-beam lithography. The template may be used repeatedly in a high-throughput process to replicate nanostructures onto substrates. In one embodiment, the template may be fabricated from a conducting material such as Indium Tin Oxide that is also

35

40

WO 2004/063815

PCT/US2002/015551

transparent to UV light. The template fabrication process is similar to that of phase shift photomasks for optical lithography; phase shift masks require an etch step that creates a topography on the template.

5 The replication of the pattern on the template may be achieved by applying an electric field between the template and the substrate. Because the liquid and air (or vacuum) have different dielectric constants and the electric field varies locally due to the presence of the topography of the template, an electrostatic force may be generated that attracts regions of the liquid toward the template. At high electric field strengths, the polymerizable composition may be made to attach to the template and dewet from the substrate at certain points. This polymerizable composition may be hardened in place by polymerization of the composition. The template may be treated with a low energy self-assembled monolayer film (e.g., a fluorinated surfactant) to aid in detachment of the
10 template the polymerized composition.

It may be possible to control the electric field, the design of the topography of the template and the proximity of the template to the liquid surface so as to create a pattern in the polymerizable composition that does not come into contact with the surface of the template. This technique may eliminate the need for mechanical separation of the template from the polymerized composition. This technique may also eliminate a potential source
15 of defects in the pattern. In the absence of contact, however, the liquid may not form sharp, high-resolution structures that are as well defined as in the case of contact. This may be addressed by first creating structures in the polymerizable composition that are partially defined at a given electric field. Subsequently, the gap may be increased between the template and substrate while simultaneously increasing the magnitude of the electric field to "draw-out" the liquid to form clearly defined structures without requiring contact.

20 The polymerizable composition may be deposited on top of a hard-baked resist material to lead to a bi-layer process. Such a bi-layer process allows for the formation of low aspect ratio, high-resolution structures using the electrical fields followed by an anisotropic etch that results in high-aspect ratio, high-resolution structures. Such a bi-layer process may also be used to perform a "metal lift-off process" to deposit a metal on the substrate such that the metal is left behind after lift-off in the trench areas of the originally created structures.

25 By using a low viscosity polymerizable composition, the pattern formation due to the electric field may be fast (e.g., less than about 1 sec.), and the structure may be rapidly cured. Avoiding temperature variations in the substrate and the polymerizable composition may also avoid undesirable pattern distortion that makes nano-resolution layer-to-layer alignment impractical. In addition, as mentioned above, it is possible to quickly form a pattern without contact with the template, thus eliminating defects associated with imprint methods that require
30 direct contact.

Figure 1 depicts an embodiment of the template and the substrate designs. The template may be formed from a material that is transparent to activating light to allow curing of the polymerizable composition by exposure to activating light. Forming the template from a transparent material may also allow the use of established optical techniques to measure the gap between template and substrate and to measure overlay marks to perform overlay
35 alignment and magnification correction during formation of the structures. The template may also be thermally and mechanically stable to provide nano-resolution patterning capability. The template may also include an electrically conducting material to allow electric fields to be generated at the template-substrate interface.

In one embodiment, depicted in Figure 1, a thick blank of fused silica has been chosen as the base material for the template. Indium Tin Oxide (ITO) may be deposited onto the fused Silica. ITO is transparent to visible and
40 UV light and is a conducting material. ITO may be patterned using high-resolution e-beam lithography. A low-surface energy coating (for example, a fluorine containing self-assembly monolayer) may be coated onto the

template to improve the release characteristics between the template and the polymerized composition. The substrate may include standard wafer materials such as Si, GaAs, SiGeC and InP. A UV curable liquid may be used as the polymerizable composition. The polymerizable composition may be spin coated onto the wafer. An optional transfer layer may be placed between the wafer and the liquid layer. This transfer layer may be used for bi-layer
 5 process. The transfer layer material properties and thickness may be chosen to allow for the creation of high-aspect ratio structures from low-aspect ratio structures created in the cured liquid material. An electric field may be generated between the template and substrate by connecting ITO to a voltage source.

In Figures 2 and 3, two variants of the above-described process are presented. In each variant, it is assumed that a desired uniform gap may be maintained between the template and the substrate. An electric field of
 10 the desired magnitude may be applied resulting in the attraction of the polymerizable composition towards the raised portions of the template. In Figure 2, the gap and field magnitudes are such that the polymerizable composition makes direct contact and adheres to the template. A UV curing process may be used to harden the liquid in that configuration. Once the structures have been formed, the template is separated from the substrate by either increasing the uniform gap till the separation is achieved, or by initiating a peel and pull motion wherein the
 15 template is peeled away from the substrate starting at one edge of the template. Prior to its use, the template is assumed to be treated with a low-surface energy monolayer that assists in the separation step.

In Figure 3, the gap and field magnitudes are chosen such that the liquid achieves a topography that is essentially the same as that of the template. This topography may be achieved without making direct contact with the template. A UV curing process may be used to harden the liquid in that configuration. In both the processes of
 20 Figures 2 and 3, a subsequent etch process may be used to eliminate the residual layer of the UV cured material. A further etch may also be used if a transfer layer is present between the UV cured material and the wafer as shown in Figures 2 and 3. As mentioned earlier, such a transfer layer may be used to obtain high-aspect ratio structures from a low aspect ratio structure created in the UV cured material.

Figures 4 illustrates mechanical devices that may increase the planarity of the substrate. The template may
 25 be formed from high-quality optical flats of fused-silica with Indium Tin Oxide deposited on the fused silica. Therefore, the template typically possess extremely high planarity. The substrates typically have low planarity. Sources of variations in the planarity of the substrate include poor finishing of the back side of the wafer, the presence of particular contaminants trapped between the wafer and the wafer chuck, and wafer distortions caused by thermal processing of the wafer. In one embodiment, the substrate may be mounted on a chuck whose top surface
 30 shape may be altered by a large array of piezoelectric actuators. The chuck thickness may be such that accurate corrections in surface topography of up to a few microns may be achieved. The substrate may be mounted to the chuck such that it substantially conforms to the shape of the chuck. Once the substrate is loaded on to the chuck, a sensing system (e.g., an optical surface topography measurement system) may be used to map the top surface of the substrate accurately. Once the surface topology is known, the array of piezoelectric actuators may be actuated to
 35 rectify the topography variations such that the upper surface of the substrate exhibits a planarity of less than about 1 μm . Since the template is assumed to be made from an optically flat material, this leads to template and substrate that are high quality planar surfaces.

The mechanical device in Figure 5 may be used to perform a high-resolution gap control at the template-substrate interface. This device may control two tilting degrees of freedom (about orthogonal axes that lie on the
 40 surface of the template) and the vertical translation degree of freedom of the template. The magnitude of the gap between the template and the substrate may be measured in real-time. These real-time measurements may be used

WO 2004/063815

PCT/US2002/015551

to identify the corrective template motions required about the tilting degrees of freedom and the vertical displacement degree of freedom. The three gap measurements may be obtained by using a broadband optical interferometric approach that is similar to the one used for measuring thicknesses of thin films and thin film stacks. This approach of capacitive sensing may also be used for measuring these three gaps.

Further modifications and alternative embodiments of various aspects of the invention will be apparent to those skilled in the art in view of this description. Accordingly, this description is to be construed as illustrative only and is for the purpose of teaching those skilled in the art the general manner of carrying out the invention. It is to be understood that the forms of the invention shown and described herein are to be taken as the presently preferred embodiments. Elements and materials may be substituted for those illustrated and described herein, parts and processes may be reversed, and certain features of the invention may be utilized independently, all as would be apparent to one skilled in the art after having the benefit of this description of the invention. Changes may be made in the elements described herein without departing from the spirit and scope of the invention as described in the following claims.

REFERENCES

The following references are specifically incorporated herein by reference

1. "Getting More from Moore's," Gary Stix, Scientific American, April 2001.
2. "Step and Flash Imprint Lithography: An alternative approach to high resolution patterning," M. Colburn, S. Johnson, M. Stewart, S. Damle, B. J. Choi, T. Bailey, M. Wedlake, T. Michaelson, S.V. Sreenivasan, J. Ekerdt, C.G. Willson, Proc. SPIE Vol. 3676, 379-389, 1999.
3. "Design of Orientation Stages for Step and Flash Imprint Lithography," B. J. Choi, S. Johnson, M. Colburn, S.V. Sreenivasan, C. G. Willson, To appear in J. of Precision Engineering.
4. U.S. Patent Application No. 09/266,663 entitled "Step and Flash Imprint Lithography" to Grant Willson and Matt Colburn.
5. U.S. Patent Application No. 09/698,317 entitled "High Precision Orientation Alignment and Gap Control Stages for Imprint Lithography Processes" to B.J. Choi, S.V. Sreenivasan and Steve Johnson.
6. "Large area high density quantized magnetic disks fabricated using nanoimprint lithography," W. Wu, B. Cui, X. Y. Sun, W. Zhang, L. Zhunag, and S. Y. Chou., J. Vac Sci Technol B 16 (6) 3825-3829 Nov-Dec 1998
7. "Lithographically-induced Self-assembly of Periodic Polymer Micropillar Arrays," S. Y. Chou, L. Zhuang, J Vac Sci Tech B 17 (6), 3197-3202, 1999
8. "Large Area Domain Alignment in Block Copolymer Thin Films Using Electric Fields," P. Mansky, J. DeRouchey, J. Mays, M. Pitsikalis, T. Morkved, H. Jaeger and T. Russell, Macromolecules 13, 4399 (1998).

CLAIMS:

1. A method of creating a desired pattern on a body, said method comprising:

arranging a liquid to be between a template and said body;

orienting said template proximate to said liquid;

defining an electric field, having a magnitude associated therewith, between said substrate and said template; and

increasing a distance between said substrate and said template while concurrently increasing said magnitude of said electric field to form a contiguous region of said liquid.

2. The method as recited in claim 1 wherein said pattern comprises a topology selected from the group of topologies consisting of recessed and protruded, smooth, and planarized.

3. The method as recited in claim 1 wherein increasing said distance further includes moving said liquid away from said body, toward said template, wherein said liquid abstains from contact with said template.

5. The method as recited in claim 1 wherein arranging said liquid further includes arranging a low viscosity liquid between said template and said body.

6. The method as recited in claim 1 further including providing said template with an electrically conducting material.

7. The method as recited in claim 1 wherein defining said electric field further includes forming a first pattern differing from said desired pattern.

8. The method as recited in claim 1 wherein orientating said template further includes positioning said template spaced-apart from said liquid.

9. The method as recited in claim 1 further including solidifying said liquid.

10. The method as recited in claim 9 wherein solidifying further includes solidifying said liquid in the presence of said electric field.

11. A method of creating a desired pattern on a body, said method comprising:

disposing a liquid between a template and said body;
orientating said template proximate to said liquid;
defining an electric field, having a magnitude associated therewith, between said substrate and said template; and

increasing a distance between said substrate and said template while concurrently increasing said magnitude of said electric field such that said liquid moves toward said template and forms a contiguous region.

12. The method as recited in claim 11 wherein said pattern comprises a topology selected from the group of

topologies consisting of recessed and protruded, smoothed, and planarized.

13. The method as recited in claim 11 further includes having said liquid abstain from contact with said template.

14. The method as recited in claim 11 wherein defining said electric field further includes forming a first pattern differing from said desired pattern.

15. The method as recited in claim 11 further including polymerizing said liquid, with said liquid comprising a polymerizable composition.

16. The method as recited in claim 15 wherein polymerizing said liquid occurs in the presence of said electric field.

17. A method of creating a desired pattern on a body, said method comprising:

disposing a polymerizable liquid on said body;

orientating a template proximate to said polymerizable liquid;

defining an electric field, having a magnitude associated therewith, between said substrate and said template;

increasing a distance between said substrate and said template while concurrently increasing said magnitude of said electric field to form a contiguous region of said liquid; and

polymerizing said polymerizable liquid.

18. The method as recited in claim 17 wherein disposing said liquid further includes disposing a low viscosity liquid.

19. The method as recited in claim 17 further including providing said template with an electrically conducting material.

20. The method as recited in claim 17 wherein polymerizing said liquid occurs in the presence of said electric field.

21. The method as recited in claim 17 wherein defining said electric field further includes forming a first pattern differing from said desired pattern.

22. An apparatus for altering a shape of a substrate, comprising:

a holder configured to couple to and support the substrate;

a plurality of pressure application devices coupled to the holder, wherein the pressure application devices are configured to apply a deforming force to the holder such that a shape of the holder is altered during use;

wherein the substrate is coupled to the holder such that the shape of the substrate substantially conforms to the shape of the holder during use.

23. The apparatus of claim 22 wherein the holder comprises a vacuum chuck.

24. The apparatus of claim 22 wherein the pressure application devices comprise piezoelectric actuators.

25. The apparatus of claim 22 further comprising a detector configured to measure the planarity of the substrate during use.

26. The apparatus of claim 22 wherein the substrate comprises a silicon wafer.

27. The apparatus of claim 22 wherein the substrate comprises a GaAs wafer.

28. The apparatus of claim 22 wherein the substrate comprises an SiGeC wafer.

29. The apparatus of claim 22 wherein the substrate comprises an InP wafer.