

THERMAL BARRIER COATINGS AND PROCESSES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] The present application claims the benefit of U.S. Provisional Patent Application No. 61/942,984 filed February 21, 2014, the disclosures of which is expressly incorporated herein by reference.

TECHNICAL FIELD

[0002] The field of art to which this invention generally pertains is thermal spray process coating.

BACKGROUND

[0003] Thermal spraying is a coating process in which various materials in heated or melted form are sprayed onto a surface. The coating material is generally heated by electrical plasma or arc. Coating materials used include such things as metals, alloys, and ceramics, among others. Depending on the intended use, coating quality is typically measured by such things as density, porosity, sintering resistance, thermal conductivity, strain tolerance, etc. Many things can influence these and other coating properties, such as particulars of the coating material used, particulars of the plasma gas used, flow rates, power levels, torch distance, particulars of the substrate, etc. Because of their properties, these types of coatings are generally used to protect structural materials against high temperatures, corrosion, erosion, wear, etc. Thus, there is a continuing search for ways to improve the properties and performance of these coatings, for these uses, as well as others.

[0004] The methods and materials described herein meet the challenges described above, including, among other things, improved coating properties and performance..

BRIEF SUMMARY

[0005] A method of applying a thermal barrier coating to an article is described including thermally spraying plasma heated particle coating materials onto the surface

of the article to produce a porous, segmented thermal barrier coating having a density less than about 88% of the theoretical density.

[0006] Additional embodiments include: the method described above where the coating materials are applied with a cascaded plasma gun or a conventional thermal spray plasma gun for example 9M or F4 guns; the method described above where the coating materials are applied with a cascaded arc gun technology such as SinplexPro™ plasma gun or a TriplexPro™ plasma gun; the method described above where argon is used as a primary plasma gas; the method described above where hydrogen is used as a secondary plasma gas; the method described above where the plasma enthalpy is about 14,000 KJ/Kg to about 24,000 KJ/Kg; the method described above where the plasma enthalpy is about 18, 000 KJ/Kg; the method described above where the ratio of argon to hydrogen is about 6:1 to about 18:1; the method described above where the ratio of argon to hydrogen is about 9:1 to about 12:1; the method described above where the feeding rate of the coating material is about 30g/min to about 180g/min; the method described above where the feeding rate is about 60g/min to about 120g/min; the method described above where the average sprayed particle temperature is about 2700°C to about 3300°C; the method described above where the average sprayed particle temperature is about 2700°C to about 3000°C; the method described above where the average sprayed particle velocity is about 180m/s to about 280m/s; the method described above where the method of claim 30, wherein the average sprayed particle velocity is about 190m/s to about 250m/s; the method described above where the coating has a density equal to or less than about 4.9g/cc; the method described above where the coating has a density of about 4.2g/cc to about 4.9g/cc; the method described above where the coating has a density of about 3.0g/cc to about 5.5g/cc; the method described above where the coating has at least about 5 macrocracks per linear inch; the method described above where the coating has about 5 and to about 60 macrocracks per linear inch; the method described above where the coating has a porosity greater than about 5% by volume, preferably up to 20% by volume, and could go up to 25% by volume; the method described above where the coating material comprises zirconium oxide stabilized with one or more of magnesia, ceria, yttria, ytterbia, dysposia, gadolia, erbia, neodymia, lanthanum oxide, and/or strontium oxide, typically in amounts of about 5 to about 75 weight %, preferably about 5 to about 50 weight %, and more preferably about 5 to about 15 weight %; the method described above where hafnium

oxide is substituted for at least part of (or all of) the zirconium oxide; the method described above where the coating material is yttria stabilized zirconia.

[0007] Additional embodiments also include: the method described above including applying at least one oxidation resistant bond coat on the article; the method described above where including applying a dense legacy yttria stabilized zirconia layer on top of the bond coat; the method described above including applying a dense segmented yttria stabilized zirconia layer on top of the bond coat; the method described above including applying at least one intermediate coating on top of the bond coat; the method described above including applying at least one top coating on top of the bond coat; the method described above where the intermediate coating comprises at least one layer of legacy porous yttria stabilized zirconia, dense coatings, porous segmented coatings, and/or dense segmented coatings; the method described above where the top coating comprises at least one layer of legacy porous yttria stabilized zirconia, dense coatings, porous segmented coatings, and/or dense segmented coatings; the method described above including applying at least one porous segmented coating as an intermediate coating; the method described above including applying at least one porous segmented coating as a top coating; the method described above where the bond coat is up to about 200 microns thick; the method described above where the intermediate coating is up to about 400 microns thick; the method described above where the intermediate coating is between about 50 microns and 400 microns thick; the method described above where the top coating is up to about 800 microns thick; the method described above where the top coating is between about 100 microns and about 800 microns thick; the method described above where the intermediate coating comprises at least one layer of strain tolerant coating; the method described above where the bond coat comprises MCRAIY, where M is Ni, Co and/or Fe; the method described above where the bond coat is NiCr, NiAl, and/or NiCrAlY; the method described above where the bond coat additionally contains small amounts, for example, trace to 0.6 weight percent of Re, Hf, and/or Si; the method described above where the coating has decreased thermal conductivity when compared to legacy zirconia thermal barrier coatings, high strain tolerance when compared to legacy zirconia thermal barrier coatings, high sintering resistance and/or improved thermal cycle life when compared to legacy zirconia thermal barrier coatings; the method described above where the particles have a particle size of between about 10 microns and about 176 microns; the method described above where the apparent density of the

coating material or powder is between about 1.0 grams/cc and about 3.0 g/cc; the method described above where the total impurity of oxides in the particles is less than about 0.5 % by weight; the method described above where the oxides are from a group comprising but not limited to SiO_2 , Al_2O_3 , iron oxide, sodium oxide, CaO , MgO and/or TiO_2 ; the method described above where the total impurity of oxides in the particles is less than about 0.15 % by weight; the method described above where the powder contains less than about 0.05 % by weight uranium and/or thorium; the method described above where the powder contains less than about 0.02 % by weight uranium and/or thorium; the method described above where the powder comprises a bimodal distribution containing about 75% by weight plasma densified particles and about 25% by weight spray dried powder; the method described above where the plasma densified powder are about $11\mu\text{m}$ to about $75\mu\text{m}$ in diameter and the spray dried powder are about $75\mu\text{m}$ to about $180\mu\text{m}$ in diameter. Additionally, the powder can be plasma densified, agglomerated and sintered, fused and crushed, or spray dried, or any combination of these in varying percentages.

[0008] Articles coated with porous, segmented thermal barrier coatings are also described where the coatings have a density less than about 88% of the theoretical density.

[0009] Additional embodiments include: the article described above where the coating has a density of about 3.0 g/cc to about 5.5g/cc, about 5 macrocracks per linear inch to about 60 microcracks per linear inch, and a porosity between about 5% by volume up to about 25% by volume; the article described above where the coating includes zirconium oxide stabilized with one or more of magnesia, ceria, yttria, ytterbia, dysposia, gadolia, erbia, neodymia, lanthanum oxide, and/or strontium oxide; the article described above where hafnium oxide is substituted for at least part of the zirconium oxide; the article described above where the coating comprises yttria stabilized zirconia; the article described above including at least one oxidation resistant bond coat on the article; the article described above including a dense legacy or segmented yttria stabilized zirconia layer on top of the bond coat; the article described above including at least one intermediate coating on top of the bond coat; the article described above including at least one top coating on top of the bond coat; the article described above containing at least one porous segmented coating as an intermediate or top coating.

[0010] Other exemplary embodiments and advantages of the present invention may be ascertained by reviewing the present disclosure and the accompanying drawing.

BRIEF DESCRIPTION OF THE DRAWINGS

[0011] The present invention is further described in the detailed description which follows, in reference to the noted plurality of drawings by way of non-limiting examples of exemplary embodiments of the present invention, and wherein:

[0012] Figures 1A, 1B and 1C show schematic representations of various coated articles as described herein.

[0013] Figure 2 shows typical thermal barrier coatings.

[0014] Figure 3 shows a typical thermal barrier coating as described herein.

DETAILED DESCRIPTION

[0015] The particulars shown herein are by way of example and for purposes of illustrative discussion of the various embodiments of the present invention only and are presented in the cause of providing what is believed to be the most useful and readily understood description of the principles and conceptual aspects of the invention. In this regard, no attempt is made to show details of the invention in more detail than is necessary for a fundamental understanding of the invention, the description making apparent to those skilled in the art how the several forms of the invention may be embodied in practice.

[0016] The present invention will now be described by reference to more detailed embodiments. This invention may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art.

[0017] Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. The terminology used in the description of the invention herein is for describing particular embodiments only and is not intended to be limiting of the invention. As used in the description of the invention and the appended claims, the singular forms “a,” “an,” and “the” are intended to include the plural forms as

well, unless the context clearly indicates otherwise. All publications, patent applications, patents, and other references mentioned herein are expressly incorporated by reference in their entirety.

[0018] Unless otherwise indicated, all numbers expressing quantities of ingredients, reaction conditions, and so forth used in the specification and claims are to be understood as being modified in all instances by the term “about.” Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification and attached claims are approximations that may vary depending upon the desired properties sought to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should be construed in light of the number of significant digits and ordinary rounding approaches.

[0019] Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements. Every numerical range given throughout this specification will include every narrower numerical range that falls within such broader numerical range, as if such narrower numerical ranges were all expressly written herein.

[0020] Additional advantages of the invention will be set forth in part in the description which follows, and in part will be obvious from the description, or may be learned by practice of the invention. It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the invention, as claimed.

[0021] Thermal barrier coatings are well known including those with vertical cracks. There are numerous publications and patents disclosing thermal barrier coatings with vertical cracks. However, such coatings typically have a dense microstructure. For example, US Patent No. 5,073,433 to Taylor and US Patent No. 8,197,950 to Taylor et al. disclose segmented coatings having a density of 5.47g/cc (grams/cubic centimeter) to 5.55g/cc which is greater than 88% of the theoretical density. The disclosure of each of these US patents is herein expressly incorporated by reference in its entirety.

[0022] Coatings and methods of making such coatings are described herein where the coating advantageously is highly strain tolerant and has low thermal conductivity. The coating is also advantageously a sintering resistant thermal barrier coating for high temperature applications which can protect a metallic component and utilize one or more oxidation resistant bond coats.

[0023] Figure 1A shows a basic structure as described herein, where a substrate material (10) is coated with a thermal barrier top coat (11) as also described herein. Other options shown in Figures 1B and 1C include multilayer versions, including the addition of a bond coat (12) on the substrate and optional intermediate layers (13).

[0024] Fig. 2 shows a typical dense vertically cracked thermal barrier coating (TBC) coating as described, for example, in *Advances in Thermal Spray Coatings for Gas Turbines and Energy Generation: A Review*, Journal of Thermal Spray Technology, Volume 22(5), pages 564-576, June 2013, the disclosure of which is herein expressly incorporated by reference in its entirety. Referring to Fig. 2, the substrate material (21) is shown coated with the thermal barrier coating (22). Pores (23) and macrocracks (24) can also be seen.

[0025] Fig. 3 shows a polished cross-section of a porous and segmented plasma sprayed zirconium oxide-yttrium oxide (YSZ) coating in accordance with the invention and having a porosity of about 20% and about 35 vertical macrocracks per inch. Referring to Fig. 3, the substrate material (31) is shown coated with the thermal barrier coating (32). Pores (33) and macrocracks (34) can also be seen.

[0026] It would be advantageous to make an air plasma spray segmented coating with a coating density less than 88% of the theoretical density. This type of coating can be made by controlling the particle melting status and the stress levels in order to increase the porosity of the coating. The increased porosity can advantageously increase the coating sintering resistance, lower the thermal conductivity and contribute to the strain tolerance enhancement, especially when combined with vertical cracks.

[0027] The articles described herein include a thermal barrier coating having a decreased thermal conductivity, a higher strain tolerance, a higher sintering resistance and improved thermal cyclic fatigue resistance compared to prior coatings. The thermal barrier coating can be made which has a porous and vertically segmented microstructure. This coating can, for example, advantageously be a yttria stabilized zirconia (YSZ) coating have a typical density ranging from 4.2g/cc to 4.9g/cc or

where the coating has a density of about 3.0g/cc to about 5.5g/cc; and with a vertical cracks density of between about 5 and about 60 macrocracks per linear inch. These coating typically have a thermal cycle life that is between 1.4 and 1.6 times higher than traditionally dense segmented thermal barrier coatings. The coatings can be plasma sprayed using conventional thermal spraying techniques and equipment modified as described herein.

[0028] Non-limiting examples of coatings made in accordance with the invention include the following:

EXAMPLE

[0029] A porous segmented yttria stabilized zirconia thermal barrier coating is formed by plasma spraying a YSZ spherical powder. The YSZ powder consists of 7 weight percent yttria and a balance of zirconia having a particle size ranging from 5 μ m to 180 μ m and preferably between 11 μ m and 125 μ m. A possible bimodal distribution can utilize 75wt% plasma densified material (particles size ranging from 11 μ m-75 μ m) with 25 wt% of spray dried material (particle size ranging from 75 μ m-180 μ m). A possible straight material can utilize plasma densified YSZ powder with particle size 11 μ m -110 μ m. The YSZ powder is injected into the plasma torch radially. In embodiments the plasma torch utilizes cascaded gun technology and can be a TriplexPro™- 210 plasma gun, SinplexPro™ plasma gun, or even a conventional plasma gun such as an F4 gun or 9MB gun made by Oerlikon Metco. A plasma gun utilizing cascaded gun technology is preferred when the coating is to be applied over a metallic or ceramic composite substrate.

[0030] During plasma spraying, the plasma spraying parameters should be controlled so that some particle are fully melted and some particles will be only partially melted or remain un-melted. Typically, the substrate should be preheated to about 500⁰ C before applying the coating on the same.

[0031] The YSZ coating applied in this way can advantageously have a desirable porosity and be composed of fully melted splats, as well as partially melted and un-melted particles. This YSZ coating can also advantageously have a density ranging from about 4.2g/cc to about 4.9g/cc (i.e., less than 88% of the theoretical density) and can include between about 5 and about 60 vertical macrocracks per linear inch measured in a line parallel to the surface of the substrate. The YSZ coating can also be expected to exhibit desirable properties such as low thermal conductivity, greatly improved sintering resistance and enhanced strain tolerance.

[0032] In the above example, a coating utilizing 7-8 weight percent (wt%) YSZ materials and made by the known Oerlikon Metco HOSP process has been demonstrated. However, the invention is not so limited and can be extended to many different zirconium oxide thermal barrier systems using various powder manufacturing processes.

[0033] In non-limiting examples, many types of material systems can be utilized such as: zirconium oxide systems stabilized with one or more combinations of magnesia, ceria, yttria, ytterbia, dysposia, gadolia, erbia, neodymia, lanthanum oxide, strontium oxide. Hafnium oxide can be substituted for part or all of zirconium oxide.

[0034] In addition, many types of material manufacturing processes can be used such as a manufacturing process which utilizes spray dried powder manufacturing routes or processes (0-100 wt% pre-alloyed or 0-100 wt% unreacted constituents) with an organic binder; spray dried and sintered materials; spray dried and plasma densified materials; as well as a chemical precipitated blend of two or more of various manufacturing routes. A blend of fused and crushed materials made in accordance with one or more of these three manufacturing routes can also be utilized.

[0035] In non-limiting examples, the powder properties can include the following: a particle size of between about 10 and about 176 microns; apparent density of between about 1.0 grams/cc-and about 3.0 g/cc; a purity wherein a total impurity of oxides such as SiO₂, Al₂O₃, iron oxide, sodium oxide, CaO, MgO and TiO₂ is under 0.5 wt% and preferably less than 0.15 wt%; a radioactivity that is less than 0.05 wt% uranium and thorium and preferably less than 0.02 wt%; a possible bimodal distribution can utilize 75 wt% plasma densified material (particles size ranging from 11µm-75µm) with 25 wt% of spray dried material (particle size ranging from 75µm-180µm).

[0036] In non-limiting examples, the coating can be either a duel layer system which utilizes an oxidation resistant bond coat and a porous segmented top coat or a multi-layer system which utilizes dense legacies_of 7-8 wt% YSZ or even a dense segmented YSZ on top of oxidation resistant bond coat. The coating can also be a multi-layer coating with varied coating microstructures including one or more intermediate coatings and one or more top coatings on an oxidation resistant bond coat substrate. The intermediate coatings can be one or several layers of the legacy porous YSZ coatings, dense coatings, porous segmented coatings, dense segmented coatings or any combination of the same. The top coating or coatings can be one or several layers of the legacy porous YSZ coating, dense coatings, porous segmented

coatings, dense segmented coatings or any combination of the same. In the multilayer coating applications, the one or more porous segmented coatings can at least appear as either an intermediate coating or a top coating layer. Typical coating thickness can include a bond coat of up to 200 microns, an intermediate coating of between about 50 and 400 microns, and a top coat of between about 100 and about 800 microns.

[0037] In non-limiting embodiments, the bond coating layers can typically be NiCr, NiAl, NiCrAlY or other MCrAlY containing materials where M stand for combinations of Ni, Co and/or Iron. The MCrAlY's may also contain trace amount of Re, Hf, Si.

[0038] The coated articles produced have a porous, segmented thermal barrier coating where the coating has a density less than about 88% of the theoretical density. Additional non-limiting embodiments include: the article described above where the coating has a density equal to or less than about 4.9g/cc; the article described above where the coating has a density of about 4.2g/cc to about 4.9g/cc; the article described above where the coating has a density of about 3.0g/cc to about 5.5g/cc; the article described above where the coating has at least about 5 macrocracks per linear inch; the article described above where the coating has about 5 and to about 60 macrocracks per linear inch; the article described above where the coating has a porosity greater than about 5% by volume, preferably up to 20% by volume, and could go up to 25% by volume; the article described above where the coating comprises zirconium oxide stabilized with one or more of magnesia, ceria, yttria, ytterbia, dysposia, gadolia, erbia, neodymia, lanthanum oxide, and/or strontium oxide; the article described above where hafnium oxide is substituted for at least part of the zirconium oxide; the article described above where the coating is yttria stabilized zirconia;

[0039] Additional non-limiting embodiments also include: the article described above including at least one oxidation resistant bond coat on the article; the article described above including a dense legacy 7-8 weight percent yttria stabilized zirconia layer on top of the bond coat; the article described above including a dense segmented yttria stabilized zirconia layer on top of the bond coat; the article described above including at least one intermediate coating on top of the bond coat; the article described above including at least one top coating on top of the bond coat; the article described above where the intermediate coating comprises at least one layer of legacy porous yttria stabilized zirconia, dense coatings, porous segmented coatings, and/or dense

segmented coatings; the article and method described above where the intermediate layers can be: 1) traditional 5 to 10 weight % YSZ coating structures, 2) dense YSZ with less than 5 % porosity or 3) dense, segmented YSZ; the article described above where the top coating comprises at least one layer of legacy porous yttria stabilized zirconia, dense coatings, porous segmented coatings, and/or dense segmented coatings; the article described above containing at least one porous segmented coating as an intermediate coating; the article described above containing at least one porous segmented coating as a top coating; the article described above where the bond coat is up to about 200 microns thick; the article described above where the intermediate coating is up to about 400 microns thick; the article described above where the intermediate coating is between about 50 microns and 400 microns thick; the article described above where the top coating is up to about 800 microns thick; the article described above where the top coating is between about 100 microns and about 800 microns thick; the article described above where the intermediate coating comprises at least one layer of strain tolerant coating; the article described above where the bond coat comprises MCRAIY, where M is Ni, Co and/or Fe; the article described above where the bond coat is NiCr, NiAl, and/or NiCrAlY; the article described above where the bond coat additionally contains small amounts, for example trace to 0.6 weight percent of Re, Hf, and/or Si; the article described above where the coating has decreased thermal conductivity when compared to legacy zirconia thermal barrier coatings, high strain tolerance when compared to legacy zirconia thermal barrier coatings, high sintering resistance and/or improved thermal cycle life when compared to legacy zirconia thermal barrier coatings.

[0040] It should be noted that the type of powder manufacturing process can effect coating microstructure. Powder purity, powder particle size, heat input into powder, as well as the inter relationship between powder and spray parameters can effect coating microstructure and also be configured to achieve optimum microstructure such as a porous and segmented TBC.

[0041] Additionally, one should be mindful of the importance of semi-melted, and un-melted metal oxide particles entrapped within thermal barrier coating for reduced thermal conductivity, improved sintering resistance and added thermal cyclic life.

[0042] In accordance with an advantageous embodiment of the invention, a porous segmented coating can be formed by utilizing a SinplexPro™ plasma gun with a 9 mm

spraying nozzle. Argon and hydrogen are used as the primary and the secondary plasma gases, respectively. The plasma enthalpy used can range from 14000 KJ/Kg (kiloJoules /kilogram) to 24000KJ/Kg, preferably 18000KJ/Kg. The ratio of argon and hydrogen can be between 6-18, preferably 9-12. The feeding rate can range from 30g/min (grams/minute) to 180g/min, preferably 60g/min-120g/min. The average particle temperature and velocity can range from 2700°C -3300°C, 180m/s (meters/second) - 280m/s, respectively. Preferably, the average temperature is between 2700 °C-3000 °C and an average velocity is between 190m/s-250m/s.

[0043] It is noted that the foregoing examples have been provided merely for the purpose of explanation and are in no way to be construed as limiting of the present invention. While the present invention has been described with reference to an exemplary embodiment, it is understood that the words which have been used herein are words of description and illustration, rather than words of limitation. Changes may be made, within the purview of the appended claims, as presently stated and as amended, without departing from the scope and spirit of the present invention in its aspects. Although the present invention has been described herein with reference to particular means, materials and embodiments, the present invention is not intended to be limited to the particulars disclosed herein; rather, the present invention extends to all functionally equivalent structures, methods and uses, such as are within the scope of the appended claims.

WHAT IS CLAIMED:

1. A method of applying a thermal barrier coating to an article comprising thermally spraying plasma heated powder coating materials onto the surface of the article to produce a porous, segmented thermal barrier coating having a density less than about 88% of the theoretical density.
2. The method of claim 1, wherein the coating has a density of about 3.0 g/cc to about 5.5g/cc., about 5 macrocracks per linear inch to about 60 microcracks per linear inch, and a porosity between about 5% by volume up to about 25% by volume.
3. The method of claim 1, wherein the coating material comprises zirconium oxide stabilized with one or more of magnesia, ceria, yttria, ytterbia, dysposia, gadolinia, erbia, neodymia, lanthanum oxide, and/or strontium oxide.
4. The method of claim 1, wherein hafnium oxide is substituted for at least part of the zirconium oxide.
5. The method of claim 1, including applying at least one oxidation resistant bond coat on the article.
6. The method of claim 1, including applying a dense legacy or segmented yttria stabilized zirconia layer on top of the bond coat.
7. The method of claim 1, including applying at least one intermediate coating on top of the bond coat.
8. The method of claim 1, including applying at least one top coating on top of the bond coat.
9. The method of claim 7, including applying at least one porous segmented coating as an intermediate coating.
10. The method of claim 8, including applying at least one porous segmented coating as a top coating.
11. An article coated with a porous, segmented thermal barrier coating, wherein the coating has a density less than about 88% of the theoretical density.
12. The article of claim 11, wherein the coating has a density of about 3.0 g/cc to about 5.5g/cc, about 5 macrocracks per linear inch to about 60 microcracks per linear inch, and a porosity between about 5% by volume up to about 25% by volume.

13. The article of claim 11, wherein the coating comprises zirconium oxide stabilized with one or more of magnesia, ceria, yttria, ytterbia, dysposia, gadolia, erbia, neodymia, lanthanum oxide, and/or strontium oxide.
14. The article of claim 13, wherein hafnium oxide is substituted for at least part of the zirconium oxide.
15. The article of claim 11, wherein the coating comprises yttria stabilized zirconia.
16. The article of claim 11, including at least one oxidation resistant bond coat on the article.
17. The article of claim 16, including a dense legacy or segmented yttria stabilized zirconia layer on top of the bond coat.
18. The article of claim 16, including at least one intermediate coating on top of the bond coat.
19. The article of claim 16, containing at least one porous segmented coating as an intermediate or top coating.