

PO-8916
MD06-26A

CONTINUOUS PROCESSES FOR THE PRODUCTION OF ETHOXYLATES

5

FIELD OF THE INVENTION

The present invention relates in general to polymerization, and more specifically, to improved processes for the production of ethoxylates useful in or as surfactants and detergents.

10

BACKGROUND OF THE INVENTION

Alkyl and alkylaryl ethoxylates are widely used in the detergents industry with world consumption estimated to be in the range of 2,600 kilotons, including the alcohol ether sulfates, (based upon data contained in "Alternatives to Nonylphenol Ethoxylates, Review of Toxicity, biodegradation & Technical-Economic Aspects",
15 Environment Canada, Final Report May 28, 2002 prepared by P.M. Campbell) found at <http://www.c2p2online.com/documents/FinalNPEAlternativesPublicReport.pdf> and the rate of growth between 2003 and 2008 is projected at about 3.4 percent.

Worldwide, the majority of ethoxylates used in detergents are produced via
20 semi-batch processes utilizing base catalysis, typically potassium hydroxide ("KOH"). As such ethoxylates are commodity materials, the production economics and capability to manufacture the precursors are important determinants of profitability. Currently, only a small fraction of such surfactants are produced with specialized catalysts which give a narrow molecular weight distribution. Processes employing
25 such "peaked catalysts" are reported to have higher manufacturing costs, likely related to higher catalyst costs and the need for catalyst removal following the ethoxylation process. Although the narrow distribution products from such processes can give higher performance in most applications, the cost driven focus of the detergent industry dictates the use of the KOH-catalyzed, wide distribution products because the
30 benefits of enhanced performance are not sufficient to offset the increased costs.

The semi-batch process is the industry standard and although it has been optimized and refined, there remain disadvantages to the use of this process. The semi-batch process operates with a headspace of ethylene oxide and an inerting gas and there are several nonproductive steps in the reactor sequence. Because pure

ethylene oxide can present a hazard, the headspace must be inerted with nitrogen or low oxygen content gas and at the end of the cycle this inerting gas which may contain traces of ethylene oxide must be wasted. In the sequence of nonproductive steps: the alcohol is charged followed by catalyst and then the base is converted to the potassium or sodium alkoxide by stripping to remove water after the mixture is heated
5 to process temperature. After oxide addition and digestion, the product is pumped from the reactor. Overall, the nonproductive steps can account for 50% of the reactor cycle time.

The use of double metal cyanide ("DMC") catalysts for the production of
10 alkoxylates has been known since General Tire's development in the 1960's. In the 1970's, Herold in U.S. Pat. No. 3,829,505, described the preparation of high molecular weight diols, triols etc., using double metal cyanide catalysts. However, the catalyst activity, coupled with catalyst cost and the difficulty of removing catalyst residues from the polyol product, prevented commercialization of the products. There
15 was limited utilization of the DMC technology until the 1990's when Le-Khac, in U.S. Pat. Nos. 5,470,813 and 5,482,908, demonstrated both improved catalysts and processes technologies that lowered the cost of production for polyols to be competitive with that for potassium hydroxide-based process for a wide range of polyols. However, even with these advancements, DMC catalyst technology has been
20 applied mostly to the production of mixed oxide and all propylene oxide-based polyols.

Because of its unique features, the DMC catalyst provides a poor distribution of ethylene oxide when the equivalent weight of the base polyol is greater than about 800. The production of ethylene oxide ("EO") capped polyols suitable for use in
25 polyurethanes requires either a two-stage system of DMC and potassium hydroxide or potassium hydroxide alone as the catalyst. Thus, although DMC catalysts are very effective for the production of ethoxylates when the starter equivalent weight is less than about 800, these capped low molecular weight polyols are not widely used for the production of polyurethanes.

30 The use of DMC as a catalyst for the production of semi-batch ethoxylates is disclosed in a number of patents and patent applications. For example, U.S. Pat. No. 6,821,308, issued Combs et al., teaches the alkoxylation of alcohols with DMC.

Although they demonstrate the use of propylene oxide as the alkylene oxide, Combs et al. do not teach or suggest the use of pure ethylene oxide.

WO 00/14045 in the name of Grosch et al., teaches the preparation of ethoxylates of fatty alcohols using supported DMC catalysts along with
5 propoxylation. Grosch et al. limit the range of alcohols used to C₆-C₂₄, thus eliminating the C₁-C₅ alcohols likely because the lower molecular weight alcohols would act as inhibitors for catalyst activation in the semi-batch process.

Ruland et al., in Example 1 of U.S. Published Patent Application No. 2005/0215452, ethoxylate a 2-propylheptanol with five moles of ethylene oxide in the
10 presence of a DMC catalyst. The polyethers of Ruland et al., have an ethylene oxide block followed by a mixed oxide block.

U.S. Published Patent Application No. 2005/0014979, in the name of Eleveld et al., discloses the use of DMC to prepare ethoxylated alcohols. It is likely that the process disclosed by Eleveld et al. will be unable to provide the economics needed to
15 supply the majority of commodity surfactants, because many of the current highly optimized KOH processes operate in a heat exchange-limited mode and the use of another catalyst will not offset this limitation and this process retains the nonproductive steps of the semibatch process. Eleveld et al. report that DMC catalyzed semi-batch processes give narrow polydispersities in comparison with
20 potassium hydroxide catalyzed processes; however, they do not disclose a method for surfactants having equivalent polydispersities.

Walker et al., in WO 01/04178, give several examples of ethoxylation. The batch or semibatch process was used for starters having a specific type of unsaturation which is modified if potassium hydroxide catalysis is used.

25 U.S. Pat. No. 6,642,423, issued to Clement et al., teaches ethoxylation with a DMC catalyst. The '423 patent discloses feeding a first block of ethylene oxide followed by other blocks of propylene oxide or mixed oxides. An activation period from several minutes to hours is required from this process.

Wulff et al., in U.S. Published Patent Application No. 2006/0052648, disclose
30 various ethoxylates and other alkoxylates of 2-propylheptanol including certain process conditions for activation and mixture of inert gases with ethylene oxide. This application teaches the use of several nonproductive process steps.

WO 2006/002807 in the name of Ostrowski et al., discloses a continuous two-stage process for the production of polyols with mixed oxide segments. These products are developed for the slab polyurethane industry in which different polyether blocks within the same molecule may affect foam processing.

5 Wehmeyer et al., in U.S. Published Patent Application No.2006/0058482, disclose a continuous process for the production of mixed-oxide block polyols with a supported catalyst.

Thus, there remains a need for improved surfactant production processes. Such a process would be without starter molecular weight limitations and would not
10 require a catalyst activation step to increase reactor productivity.

SUMMARY OF THE INVENTION

Accordingly, the present invention provides a continuous process for the production of ethoxylates with a molecular weight distribution essentially equivalent
15 to that of ethoxylates produced via a semi-batch process using basic catalysis (potassium hydroxide). The inventive continuous processes produce an ethoxylate from a $C_1 - C_{26}$ non-phenolic alcohol in the presence of a double metal cyanide ("DMC") catalyst. The inventive multi-stage continuous process produces an ethoxylate product with a molecular weight distribution that is the same or narrower
20 as that of the equivalent base-catalyzed ethoxylate. The inventive single-stage continuous process produces ethoxylate products having only a slightly broader molecular weight distribution than the multi-stage process. The essentially equivalent molecular weight distribution possible with the inventive multi-stage continuous process may provide advantages where the ethoxylate product is used in or as a
25 surfactant.

These and other advantages and benefits of the present invention will be apparent from the Detailed Description of the Invention herein below.

BRIEF DESCRIPTION OF THE FIGURES

30 The present invention will now be described for purposes of illustration and not limitation in conjunction with the figures, wherein:

Figure 1 is a gel permeation chromatograph comparing the polydispersity of two mixed oxide triols;

Figure 2 is a gel permeation chromatograph comparing the polydispersity of two all propylene oxide diols;

Figure 3a is a diagram of a continuous stirred reactor ("CSTR") partitioned with a perforated plate;

5 Figure 3b is a top view of a perforated plate;

Figure 4a is a diagram of a continuous stirred reactor ("CSTR") partitioned with a rotation disk;

Figure 4b is a top view of a rotation disk;

Figure 5 is a gel permeation chromatograph comparing the polydispersity of polyols produced by base catalysis. a DMC-catalyzed semi-batch process, the inventive single stage DMC-catalyzed process and the inventive multi-stage DMC-catalyzed process; and

Figure 6 is a gel permeation chromatograph comparing the polydispersity of polyol produced base catalysis and the inventive single stage DMC-catalyzed process.

15

DETAILED DESCRIPTION OF THE INVENTION

The present invention will now be described for purposes of illustration and not limitation. Except in the operating examples, or where otherwise indicated, all numbers expressing quantities, percentages, OH numbers, functionalities and so forth in the specification are to be understood as being modified in all instances by the term "about." Equivalent weights and molecular weights given herein in Daltons (Da) are number average equivalent weights and number average molecular weights respectively, unless indicated otherwise.

The present invention provides a multi-stage continuous process for the production of an ethoxylate involving preparing a mixture of a $C_1 - C_{26}$ non-phenolic alcohol and a double metal cyanide ("DMC") catalyst, establishing ethoxylation conditions in a first continuous stirred tank reactor ("CSTR"), continuously feeding ethylene oxide and the mixture of $C_1 - C_{26}$ non-phenolic alcohol and DMC catalyst to the first CSTR reactor under conditions suitable to produce an ethoxylate, continuously feeding the reaction mixture from the first CSTR reactor and further ethylene oxide to a second CSTR reactor or to a tubular reactor under conditions suitable to produce an ethoxylate product and continuously withdrawing the ethoxylate product from the second CSTR reactor or tubular reactor to a collection

vessel, wherein the ethoxylate product has a molecular weight distribution that is essentially equivalent to that of the same ethoxylate product produced by basic catalysis.

The present invention also provides a multi-stage continuous process for the
5 production of an ethoxylate involving preparing a mixture of a $C_1 - C_{26}$ non-phenolic alcohol and a double metal cyanide ("DMC") catalyst, establishing ethoxylation conditions in a first portion of a partitioned continuous stirred tank reactor ("CSTR"), continuously feeding ethylene oxide and the mixture of $C_1 - C_{26}$ non-phenolic alcohol and DMC catalyst to the first portion of the CSTR reactor under conditions suitable to
10 produce an ethoxylate, continuously forcing the reaction mixture from the first portion of the CSTR reactor into a second portion of the CSTR reactor and adding further ethylene oxide under conditions suitable to produce an ethoxylate product and continuously withdrawing the ethoxylate product from the second portion of the CSTR reactor to a collection vessel, wherein the ethoxylate product has a molecular
15 weight distribution that is essentially equivalent to that of the same ethoxylate product produced by basic catalysis.

The present invention further provides a single-stage continuous process for the production of an ethoxylate involving preparing a mixture of a $C_1 - C_{26}$ non-phenolic alcohol and a double metal cyanide ("DMC") catalyst, establishing
20 ethoxylation conditions in a reactor, continuously feeding ethylene oxide and the mixture of $C_1 - C_{26}$ non-phenolic alcohol and DMC catalyst to the reactor under conditions suitable to produce an ethoxylate, continuously feeding further ethylene oxide to the reactor under conditions suitable to produce an ethoxylate product and continuously withdrawing the ethoxylate product from the reactor to a collection
25 vessel, wherein the ethoxylate product has a molecular weight distribution that is substantially similar to that of the same ethoxylate product produced by basic catalysis.

The present invention yet further provides an improved process for the production of a surfactant, the improvement involving including the ethoxylate
30 product produced by either of the inventive multi-stage continuous processes or by the inventive single-stage process.

The present inventors have found that the polydispersities of the ethoxylates prepared with a continuous process using DMC catalysis are similar to those obtained

using a semi-batch potassium hydroxide-catalyzed process. It is surprising that the inventive multi-stage continuous process is able to produce an ethoxylate with the same or narrower molecular weight distribution as compared to the equivalent commercial base-catalyzed ethoxylate.

5 Such similar polydispersities are unexpected based on the published art and on the knowledge of those skilled in the art, regarding polydispersities of the polypropylene oxide polyols and mixed polyethylene oxide-polypropylene oxide polyols. With such polymers, the polydispersities are typically wider for the continuous products (DMC) process than the polydispersities of the products
10 produced in the semibatch (KOH) process. Figure 1 compares the polydispersity of a 3,200 MW KOH-catalyzed triol with an 11.5 percent ethylene oxide content and a 3,000 MW DMC-catalyzed triol with an ethylene oxide content of 7.4 percent. Figure 2 compares the polydispersity of 1,000 MW all propylene oxide diols made by KOH catalysis and by DMC catalysis. In both cases, the DMC-catalyzed materials show a
15 broader polydispersity.

As those skilled in the art are aware in transitioning from one manufacturing process to another, one of the key requirements is that the products have similar properties. It is known in the art that the relative surfactancy of a given weight of ethoxylates is related to the product distribution of the ethoxylates and thus it is
20 desirable to maintain consistent properties. The inventive continuous processes provide the desired product quality combined with increases in productivity.

The inventive continuous processes eliminate the nonproductive sequences required for the semi-batch process. Once the startup is achieved, the reactor is fully utilized for alkoxylation. The catalyst, starter and ethylene oxide are continuously
25 charged with no heat-up or water removal stages. The addition of the starter at ambient temperature is an advantage as the heat of reaction is used to bring it to process temperature. The catalyst in the reactor has on-going activity and new catalyst is continually activated as the process proceeds. The products flows from the reactor and the last traces of ethylene oxide are eliminated either in the piping system,
30 in a short pipe reactor or in the product analysis tank. If the system is equipped with analytical instruments such as a near-infrared detector, product variability is low as incremental starter and ethylene oxide weight changes can be made to maintain product quality.

At the end of each of these processes, the product may contain a low level of unreacted ethylene oxide. The oxide level continues to decrease as the product flows from the reactor by pipes to product analysis tanks. An alternative to the use of these lines would be a pipe or plug-flow reactor in which no oxide is added. In addition,
5 any residual oxide would continue to be reduced while the ethoxylate was in the product tank.

Preferred initiators or starters (the terms are used interchangeably herein) in the inventive single-stage and multi-stage processes are non-phenolic alcohols of from 1 to 20 carbon atoms and more preferably from 9 to 13 carbon atoms. The non-
10 phenolic alcohol may have a number of carbon atoms in the present invention in an amount ranging between any combination of these values, inclusive of the recited values. The non-phenolic alcohol may be a primary, secondary or tertiary alcohol.

Other suitable initiators include alcohols derived from coconut oil, palm oil, soybean oil etc. and hydroxyl-containing materials such as castor oil, hydroxylated
15 vegetable oils, hydroxymethyl stearate and esters such as methyl ricinoleate (derived from castor oil). Other starters include hydroxylated esters such as hydroxyethyl acrylate or hydroxypropyl acrylate.

The processes of the present invention may employ any double metal cyanide ("DMC") catalyst. Double metal cyanide complex catalysts are non-stoichiometric
20 complexes of a low molecular weight organic complexing agent and optionally other complexing agents with a double metal cyanide salt, e.g. zinc hexacyanocobaltate. Suitable DMC catalysts are known to those skilled in the art. Exemplary DMC catalysts include those suitable for preparation of low unsaturation polyoxyalkylene polyether polyols, such as disclosed in U.S. Pat. Nos. 3,427,256; 3,427,334;
(3,427,335; 3,829,505; 4,472,560; 4,477,589; and 5,158,922, the entire contents of
25 each of which are incorporated herein by reference. The DMC catalysts more preferred in the process of the present invention are those capable of preparing "ultra-low" unsaturation polyether polyols. Such catalysts are disclosed in U.S. Pat. Nos. 5,470,813 and 5,482,908, 5,545,601, 6,689,710 and 6,764,978, the entire contents of
30 each of which are incorporated herein by reference. Particularly preferred in the inventive process are those zinc hexacyanocobaltate catalysts prepared by the processes described in U.S. Pat. No. 5,482,908.

The DMC catalyst concentration is chosen so as to ensure good control of the ethoxylation reaction under given reaction conditions. The catalyst concentration is preferably from 5 ppm to 1,000 ppm, more preferably in the range of from 10 ppm to 500 ppm, and most preferably in the range from 20 ppm to 100 ppm, based on the
5 final ethoxylate weight. The ethoxylation in the process of the present invention may occur in the presence of DMC catalyst in an amount ranging between any combination of these values, inclusive of the recited values.

Although the inventors herein believe that the term "establishing ethoxylation conditions" in an oxyalkylation reactor is self-explanatory, such conditions are
10 established when the reactor temperature, ethylene oxide pressure, catalyst level, degree of catalyst activation, presence of oxyalkylatable compounds within the reactor, etc., are such that upon addition of unreacted ethylene oxide to the reactor, ethoxylation takes place. By the term "continuously introducing" with respect to addition of ethoxylation oxide and starter herein is meant truly continuous, or an
15 incremental addition which provides substantially the same results as continuous addition of these components. The terms "starter" and "initiator" as used herein are the same unless otherwise indicated.

The ethoxylates produced by the inventive process preferably have a number average molecular weight of from 200 Da to 20,000 Da, more preferably from 250 Da
20 to 12,000 Da, most preferably from 350 Da to 650 Da. The ethoxylates produced by the inventive process may have a number average molecular weight ranging between any combination of these values, inclusive of the recited values. The ethoxylates produced by the inventive processes may preferably find use in or as surfactants.

The inventive multi-stage processes may take place in a continuous stirred
25 tank reactor (1st stage) connected to a tubular (pipe or flow) reactor (2nd stage) or connected to a second CSTR or other type of reactor. The multi-stage process may also take place in a partitioned CSTR reactor allowing a single vessel to serve as a multi-stage CSTR by partitioning the reactor into separate compartments.

Figure 3a is a diagram of such a partitioned CSTR reactor **10** useful in the
30 present invention. The CSTR reactor is physically partitioned into two (or more) compartments by a perforated plate **24** (or plates) shown in Fig. 3b. Catalyst/initiator slurry **12** and ethylene oxide **14** are fed into the lower compartment and reacted in that chamber to form the backbone of the polyol molecule. This polyol intermediate is

forced to flow upward through the openings 26 of the perforated plate 24 to the upper compartment continuously. A separate feed 16 can be introduced into the upper compartment for a second reaction. The final product 18 is overflowed from the top of the reactor 10. Additional stages may be added similarly, if required. The agitator blades 20 for both compartments are anchored in a common shaft 22. Not shown are re-circulation loops (for cooling) and/or heat exchange surfaces (cooling jacket or coils) which may be added as needed.

Alternatively, as shown in Figure 4a, a rotation disk 44 (or disks) may be anchored on the agitator shaft 42 and serve as a partition (or partitions) for the reactor 30. As described above, catalyst/initiator slurry 32 and ethylene oxide 34 are fed into the lower compartment and reacted in that chamber to form the backbone of the polyol molecule. As shown in Figure 4b, the gap between the reactor wall 36 and the rim of disk 44 serves as an open space for liquid flow from the lower to the upper compartment. This design is more flexible because the location of the disk 44 (i.e. the volume ratio of the partitioned compartments) can be adjusted. A separate feed can be introduced into the upper compartment for a second reaction. The final product 38 is overflowed from the top of the reactor 30. Baffles 46 may optionally be added.

It is expected that one skilled in the art could combine different types of reactors to produce a multistage reactor train which would give the desired product distribution. For example, other type of reactors that were originally developed for the semibatch alkoxylation processes could be easily modified for the continuous process including Venturi Loop reactors and spray tower loop reactors as given in: <http://adt.lib.swin.edu.au/uploads/approved/adt-VSWT20050610.140607/public/02chapter1-4.pdf>. Staged reactors and the compartmentalized reactors, such as those disclosed in U.S. Pat. No. 7,012,164, (See Figures 1-4) and variants thereof should be especially suitable for use in the inventive processes for producing ethoxylates.

EXAMPLES

The present invention is further illustrated, but is not to be limited, by the following examples. All quantities given in "parts" and "percents" are understood to be by weight, unless otherwise indicated. In all examples herein using a DMC catalyst, the catalyst was made according to U.S. Pat. No. 5,482,908. NEODOL 25, a

blend of C₁₂, C₁₃, C₁₄ and C₁₅ high purity primary alcohols which is commercially available from Shell was used in the Examples.

Examples C1, C2, 3, 4 and 5

5 Example C1 was a product from a commercial process utilizing KOH/NaOH as catalyst. Example C2 was a product from a DMC-catalyzed semi-batch process with a NEODOL 25 starter.

 Example 3 was a product from a single stage DMC-catalyzed process with NEODOL 25 starter. A 35-hydroxyl number propoxylate of NEODOL 25 containing
10 30 ppm of DMC catalyst was charged to a one-gallon CSTR stainless steel reactor equipped with a mechanical agitator and slowly heated. Once the reactor temperature reached 130°C, an initial charge of ethylene oxide was charged to the reactor over several minutes. After 10 minutes, the pressure in the reactor decreased indicating that the DMC catalyst was active. The ethylene oxide feed was restarted and set at a
15 rate of 19.4 g/min (equivalent to a two-hour residence time). After establishing the oxide feed, a feed containing NEODOL 25 and 131 ppm DMC catalyst was started at a rate of 10.2 g/min.

 The DMC catalyst was added to the NEODOL 25 as a dry powder and remained dispersed in the NEODOL 25 by constant agitation of the NEODOL 25/
20 DMC catalyst feed vessel. The DMC concentration in the NEODOL 25 was sufficient to provide 45 ppm in the final product. When the pressure in the reactor reached 50 psia, a valve at the top of the reactor was opened to a back pressure regulator and the contents of the liquid full reactor were allowed to flow out of the reactor. The polyether coming out of the reactor was passed through a steam-heated
25 line before being collected in a heated and stirred jacketed vessel. The ethylene oxide and NEODOL 25 /catalyst feeds continued for approximately 22 hours at which point both the feeds were stopped. A sample of the collected product had a measured hydroxyl number of 94.5 mg KOH/g and a polydispersity of 1.17.

 In Example 4, a 114-hydroxyl number ethoxylate of NEODOL 25 containing
30 45 ppm of DMC catalyst was charged to a one-gallon CSTR stainless steel reactor equipped with a mechanical agitator and to a two-gallon CSTR stainless steel reactor equipped with a mechanical agitator and both reactors were slowly heated. The ethylene oxide feed to the one-gallon reactor was started and set at a rate of 16.7

g/min (equivalent to a 1.5 hr residence time in the one gallon reactor). After establishing the oxide feed, a feed containing NEODOL 25 and 144 ppm DMC catalyst was started at a rate of 23.95 g/min.

When the pressure in the reactor reached 50 psia, a valve at the top of the
5 reactor was opened to a back pressure regulator and the contents of the liquid full reactor were allowed to flow out of the reactor. The polyether coming out of the one-gallon reactor was directed into the bottom of the two-gallon reactor. The ethylene oxide was then started to the two-gallon reactor at a rate of 16.7 g/min, equivalent to a 2.1 hr residence time in the two-gallon reactor. The polyether coming out of the
10 liquid full two-gallon reactor was passed through a second back pressure regulator and onto a steam-heated line before being collected in a heated and stirred jacketed vessel. The ethylene oxide and NEODOL 25 /catalyst feeds continued for approximately 9 hours at which point the feeds to both reactors were stopped. A sample of the collected product had a hydroxyl number of 115 mgKOH/g and a
15 polydispersity of 1.10.

For Example 5, the reaction from Example 4 was continued by re-charging the NEODOL 25 and DMC catalyst vessel with a mixture of NEODOL 25 and DMC catalyst that contained 176 ppm catalyst. The ethylene oxide (18.1 g/min) and NEODOL 25 /DMC catalyst mixture (18.9 g/min) feeds were restarted to the one-
20 gallon reactor, equivalent to a residence time of 1.6 hours in the one-gallon reactor. A short time later, the ethylene oxide feed (17.9 g/min) to the two-gallon reactor was restarted, equivalent to a 2.2 hr residence time in the two-gallon reactor. The polyether was continuously removed from the two-gallon reactor and collected in a manner similar to Example 4. The feeds were continued for 9 hours at which point
25 the feeds to both reactors were stopped. A sample of the collected product had a hydroxyl number of 99.4 mgKOH/g and a polydispersity of 1.09.

As will be apparent to one skilled in the art from a review of Table I below and Figure 5, the polydispersity of the polyols produced by the inventive multi-stage process (Example 5, dashed line with two dots) is essentially equivalent (i.e., no
30 broader) than that of the base catalyzed control (Example C1, solid line). The polyol produced by the DMC-catalyzed single stage process (Example 3, dashed line) had a slightly broader polydispersity than that of the base catalyzed control (Example C1,

solid line). Example C2 (dotted line) shows the polydispersity of a DMC-catalyzed semi-batch process produced polyol.

Table I

	Ex. C1	Ex. C2	Ex. 3	Ex. 4	Ex. 5
moles EO/mole alcohol	9	9	9	6.6	9
process characterization	commercial	semi-batch	single stage	multi-stage continuous	multi-stage continuous
Continuous starter (Sc)	none	none	NEODOL 25	NEODOL 25	NEODOL 25
Catalyst Type	KOH/NaOH	DMC	DMC	DMC	DMC
Catalyst Conc. in Sc (ppm)	-----	-----	87	144	176
Final Catalyst (ppm)	-----	30	30	60	60
Starter Feed rate (g/min)	-----	-----	10.2	23.95	18.9
Hydroxyl No. (mg KOH/g)	93.4	90.1	94.5	115	99.4
Viscosity @ 60°C (cst)	26.8	25.6	23.1	16.5	21.5
MW distribution Dispersity	1.13	1.06	1.17	1.1	1.085
Mn	634	612	711	556	633
Mw	715	647	831	611	687
Mp	734	644	868	638	724
Mz	792	728	964	663	737

5

Examples C6 and 7

Example C6 was the product from a commercial process utilizing KOH/NaOH as catalyst.

In Example 7, the reaction from Example 3 was continued by re-charging the NEODOL 25 and DMC catalyst vessel with a mixture of NEODOL 25 and DMC catalyst that contained 108 ppm catalyst. The ethylene oxide was re-started at a rate of 17.3 g/min and the NEODOL 25 /DMC catalyst mixture was fed at 12.4 g/min, equivalent to a two-hour residence time. The polyether was continuously removed from the reactor and collected in a manner similar to Example 3. The feeds were continued for 18 hours at which time the reaction was stopped. A sample of the collected product had a hydroxyl number of 114 mgKOH/g and a polydispersity of 1.14.

As can be appreciated by those skilled in the art upon review of Table II below and of Figure 6, the ethoxylate product produced by the inventive single stage process (Example 7, dashed line) had a polydispersity that was about the same as that of the base catalyzed product (Example C6, solid line).

20

Table II

	Ex. C6	Ex. 7
moles EO/mole alcohol	6.6	6.6
process characterization	commercial	single stage
Continuous starter (Sc)	none	NEODOL 25
Catalyst Type	KOH/NaOH	DMC
Catalyst Conc. in Sc (ppm)	-----	108
Final Catalyst (ppm)	-----	45
Starter Feed rate (g/min)	-----	12.4
Hydroxyl No. (mg KOH/g)	118	114
Viscosity @ 60°C (cst)	15.9	19
MW distribution Dispersity	1.13	1.14
Mn	538	601
Mw	610	687
Mp	614	718
Mz	687	774

The amount of unreacted alcohol remaining in an alkyl ethoxylate is an important parameter because these alcohols are reported to more odorous than the corresponding ethoxylates therefore, it is important to minimize any odor. The relative amounts of these residual alcohols are given below in Table III for some of the polyols produced according to the processes of the Examples. These data show the relative amounts of unreacted alcohols remaining in the products produced by the commercial (potassium hydroxide-catalyzed semi-batch process), the inventive single-stage DMC-catalyzed continuous process and the inventive multi-stage DMC-catalyzed continuous process.

As can be appreciated by reference to Table III below, although the inventive single stage DMC-catalyzed continuous process (Examples 3 and 7) produced somewhat higher levels of unreacted alcohol than were found in the commercial, base-catalyzed semi-batch, processes (Comparative Examples 1 and 6), the inventive multi-stage DMC-catalyzed continuous process produced amounts (Example 5) that were less than or equivalent to the amounts found in the commercial products (Comparative Examples 1 and 6).

Another potential advantage of the inventive multi-stage process is that the distributions had a slight "peaked shape" in which the amounts of the homologs around the targets of 6.5 and 9 moles of EO were higher than in the commercial

products (*See*, Cox, M.F., "Ethylene Oxide Derived Surfactants", Proceeding of the 3rd World Conference on Detergents (1993)).

Table III

	Ex. C1	Ex. 3	Ex. 5	Ex. C6	Ex. 7
Process/ Product	Commercial C ₁₃ -9 EO	Single-stage C ₁₃ -9 EO	multi-stage C ₁₃ -9 EO	Commercial C ₁₃ -6.6 EO	Single-stage C ₁₃ -6.6 EO
	% Area	% Area	% Area	% Area	% Area
EO Analog					
C ₁₃ Alcohol	1.0	2.7	1.0	2.4	4.4
1EO	N.D.	N.D.	N.D.	5.7	N.D.
2EO					
3EO	5.3	7.3	4.2	9.2	8.4
4EO	7.2	7.6	5.4	10.6	8.8
5EO	8.1	7.8	6.4	10.9	9.3
6EO	8.8	7.9	7.5	10.4	9.5
7EO	9.5	7.8	7.9	9.9	9.5
8EO	9.9	7.8	8.9	9.5	9.3
9EO	9.5	7.9	9.8	8.3	9.2
10EO	8.9	7.9	10.0	7.4	8.9
11EO	8.2	7.5	9.9	5.8	7.7
12EO	7.1	7.1	9.0	4.4	6.5
13EO	5.8	6.3	7.6	3.1	5.0
14EO	4.5	5.4	5.9	2.1	3.7
15EO	3.4	4.5	4.0	1.4	2.6
16EO	2.4	4.0	2.5	0.8	1.8
17EO	1.5	3.3	1.1	0.5	

5 N.D. – not determined

The foregoing examples of the present invention are offered for the purpose of illustration and not limitation. It will be apparent to those skilled in the art that the embodiments described herein may be modified or revised in various ways without departing from the spirit and scope of the invention. The scope of the invention is to be measured by the appended claims.

10

CLAIMS:

1. A continuous process for the production of an ethoxylate comprising:
preparing a mixture of a C₁ – C₂₆ non-phenolic alcohol and a double metal cyanide
5 (“DMC”) catalyst;
establishing ethoxylation conditions in a reaction zone of a reactor system comprising
one or more reactors and at least one reaction zone;
continuously feeding ethylene oxide and the mixture of C₁ – C₂₆ non-phenolic alcohol
and DMC catalyst to said reaction zone of the reactor system comprising one
10 or more reactors under conditions suitable to produce an ethoxylate in a
reaction mixture;
continuously feeding additional ethylene oxide to the reaction mixture in the reactor
system comprising one or more reactors under conditions suitable to produce
an ethoxylate product; and
15 continuously withdrawing the ethoxylate product from the reactor system comprising
one or more reactors to a collection vessel,
wherein the ethoxylate product has a molecular weight distribution that is essentially
equivalent to that of the same ethoxylate product produced via a semi-batch process
by basic catalysis.

2. The process of Claim 1, wherein the continuous process is a multi-stage
continuous process, and the reactor system comprises a first continuous stirred tank
reactor and either a second continuous stirred tank reactor (“CSTR”) or a tubular
reactor, and each of said reactors has a said reaction zone.

3. The multi-stage continuous process of Claim 2, wherein:
ethoxylation conditions are established in the reaction zone of said first continuous
stirred tank reactor;
ethylene oxide and the mixture of C₁-C₂₆ non-phenolic alcohol and DMC catalyst are
30 continuously fed to the reaction zone of said first continuous stirred tank
reactor;
the reaction mixture from the reaction zone of said first continuous stirred tank reactor
is continuously fed to the reaction zone of said second continuous stirred tank
reactor or to the reaction zone of the tubular reactor; and

the ethoxylate product is continuously withdrawn from the reaction zone of said
second continuous stirred tank reactor or said tubular reactor to a collection
vessel.

4. The multi-stage continuous process of any one of Claims 2 to 3, wherein the
 $C_1 - C_{26}$ non-phenolic alcohol is a primary alcohol.

5. The multi-stage continuous process of any one of Claims 2 to 4, wherein the
 $C_1 - C_{26}$ non-phenolic alcohol is a secondary or tertiary alcohol.

6. The multi-stage continuous process of any one of Claim 2 to 5, wherein the C_1
 $- C_{26}$ non-phenolic alcohol contains from 9 to 13 carbon atoms.

7. The multi-stage continuous process of any one of Claims 2 to 6, wherein the
 $C_1 - C_{26}$ non-phenolic alcohol is a monofunctional primary alcohol comprising a
mixture of $C_{12} - C_{15}$ monofunctional primary alcohols.

8. The multi-stage continuous process of any one of Claim 2 to 7, wherein the C_1
 $- C_{26}$ non-phenolic alcohol is selected from the group consisting of alcohols derived
from coconut oil, palm oil, soybean oil, castor oil, hydroxylated vegetable oils,
hydroxymethyl stearate, hydroxyalkyl acrylate and methyl ricinoleate.

9. The multi-stage continuous process of any one of Claims 2 to 8, wherein the
tubular reactor is a pipe reactor or a plug flow reactor.

10. The multi-stage continuous process of any one of Claims 2 to 9, further
including a step of continuously feeding the product from the second CSTR reactor or
tubular reactor to a third reactor under conditions suitable to produce an ethoxylate
product.

11. The multi-stage continuous process of Claim 10, wherein the third reactor is a
CSTR reactor or a tubular reactor.

12. The multi-stage continuous process of any one of Claims 2 to 11, wherein the ethoxylate product has a number average molecular weight of from about 200 Da to about 20,000 Da.

5

13. The multi-stage continuous process of any one of Claims 2 to 11, wherein the ethoxylate product has a number average molecular weight of from about 250 Da to about 12,000 Da.

10

14. The multi-stage continuous process of any one of Claim 2 to 11, wherein the ethoxylate product has a number average molecular weight of from about 350 Da to about 650 Da.

15

15. The process of Claim 1, wherein the continuous process is a multi-stage continuous process, and the reactor system comprises a partitioned continuous stirred tank reactor ("CSTR"), and said partitioned continuous stirred tank reactor comprises at least a first reaction zone and a second reaction zone.

20

16. The process of Claim 15, wherein:

ethoxylation conditions are established in the first reaction zone of said partitioned continuous stirred tank reactor ("CSTR");

ethylene oxide and the mixture of C₁-C₂₆ non-phenolic alcohol and DMC catalyst are continuously fed to the first reaction zone of said partitioned continuous stirred tank reactor ("CSTR");

25

the reaction mixture from the first reaction zone of said partitioned continuous stirred tank reactor ("CSTR") is continuously forced into the second reaction zone of said partitioned continuous stirred tank reactor ("CSTR");

the ethoxylate product is continuously withdrawn from the second reaction zone of said partitioned continuous stirred tank reactor ("CSTR") to a collection vessel.

30

17. The multi-stage continuous process of any one of Claims 15 to 16, wherein the continuous stirred tank reactor ("CSTR") is partitioned with one or more perforated plates and/or rotation disks.

18. The multi-stage continuous process of any one of Claims 16 to 17, wherein the $C_1 - C_{26}$ non-phenolic alcohol is a primary alcohol.

5

19. The multi-stage continuous process of any one of Claims 16 to 18, wherein the $C_1 - C_{26}$ non-phenolic alcohol is a secondary or tertiary alcohol.

10

20. The multi-stage continuous process of any one of Claims 16 to 19, wherein the $C_1 - C_{26}$ non-phenolic alcohol contains from 9 to 13 carbon atoms.

21. The multi-stage continuous process of any one of Claims 16 to 20, wherein the $C_1 - C_{26}$ non-phenolic alcohol is a monofunctional primary alcohol comprising a mixture of $C_{12} - C_{15}$ monofunctional primary alcohols.

15

22. The multi-stage continuous process of any one of Claims 16 to 21, wherein the $C_1 - C_{26}$ non-phenolic alcohol is selected from the group consisting of alcohols derived from coconut oil, palm oil, soybean oil, castor oil, hydroxylated vegetable oils, hydroxymethyl stearate, hydroxyalkyl acrylate and methyl ricinoleate.

20

23. The multi-stage continuous process of any one of Claims 16 to 22, wherein the ethoxylate product has a number average molecular weight of from about 200 Da to about 20,000 Da.

25

24. The multi-stage continuous process of any one of Claims 16 to 22, wherein the ethoxylate product has a number average molecular weight of from about 250 Da to about 12,000 Da.

30

25. The multi-stage continuous process of any one of Claims 16 to 22, wherein the ethoxylate product has a number average molecular weight of from about 350 Da to about 650 Da.

26. The process of Claim 1, wherein said continuous process is a single stage continuous process and the reactor system comprises one reactor.

27. The single-stage continuous process according to Claim 26, wherein the C₁ – C₂₆ non-phenolic alcohol is a primary alcohol.

5

28. The single-stage continuous process of any one of Claims 26 to 27, wherein the C₁ – C₂₆ non-phenolic alcohol is a secondary or tertiary alcohol.

29. The single-stage continuous process of any one of Claims 26 to 28, wherein the C₁ – C₂₆ non-phenolic alcohol contains from 9 to 13 carbon atoms.

10

30. The single-stage continuous process of any one of Claims 26 to 29, wherein the C₁ – C₂₆ non-phenolic alcohol is a monofunctional primary alcohol comprising a mixture of C₁₂ – C₁₅ monofunctional primary alcohols.

15

31. The single-stage continuous process of any one of Claims 26 to 30, wherein the C₁ – C₂₆ non-phenolic alcohol is selected from the group consisting of alcohols derived from coconut oil, palm oil, soybean oil, castor oil, hydroxylated vegetable oils, hydroxymethyl stearate, hydroxyalkyl acrylate and methyl ricinoleate.

20

32. The single-stage continuous process of any one of Claims 26 to 31, wherein the ethoxylate product has a number average molecular weight of from about 200 Da to about 20,000 Da.

33. The single-stage continuous process of any one of Claims 26 to 31, wherein the ethoxylate product has a number average molecular weight of from about 250 Da to about 12,000 Da.

25

34. The single-stage continuous process of any one of Claims 26 to 31, wherein the ethoxylate product has a number average molecular weight of from about 350 Da to about 650 Da.

30

35. The single-stage continuous process of any one of Claims 26 to 31, wherein the reactor is a pipe reactor or a plug flow reactor.

36. In a process for the production of a surfactant, the improvement comprising
5 including the ethoxylate product produced by the multi-stage continuous process
according to Claim 2.

37. In a process for the production of a surfactant, the improvement comprising
10 including the ethoxylate product produced by the multi-stage continuous process
according to Claim 15.

38. In a process for the production of a surfactant, the improvement comprising
including the ethoxylate product produced by the single-stage process continuous
process according to Claim 26.