
This Sheet Has Been Replaced



FILTERS EMPLOYING POROUS STRONGLY ACIDIC POLYMERS

RELATED APPLICATION

This application claims the benefit of U.S. Provisional Application No. 60/097,215, filed on August 20, 1998, the entire teachings of which are incorporated
5 herein by reference.

BACKGROUND OF THE INVENTION

In this age of increased air pollution, the removal of chemicals from the air we breathe is a concern of everyone. In addition, in the fabrication electronic materials and of devices such as semiconductors, there is a requirement for
10 uncontaminated air of high quality.

Gas phase filtration is commonly accomplished using activated carbon manufactured in various ways. One approach uses a carbon/adhesive slurry to glue the carbon to the substrate. The adhesive decreases carbon performance by forming a film on its surface.

15 A second approach involves carbonizing an organic based web by heating, followed by carbon activation. This material is expensive and has relatively low adsorption capacity.

A third approach involves forming a slurry of carbon powders and fibers into sheets by a process analogous to a wet papermaking process. This material has a

medium-to-high cost, and has an undesirable high pressure drop. Moreover, chemically impregnated carbon particles cannot be efficiently used in conjunction with an aqueous process, as the aqueous nature of the process either washes away the chemical used to impregnate the carbon, or reacts undesirably with the
5 impregnating or active chemical groups thereby rendering it inoperative. In general, however, filter materials which do not incorporate chemically active groups perform far less effectively than those which do include chemically active groups.

None of these approaches fully achieve the desired properties which provide a clean, cost effective, high efficiency, low pressure drop, adsorptive composite.

10 SUMMARY OF THE INVENTION

The present invention comprises a clean, cost effective, high efficiency, low pressure drop, adsorptive, filter comprising a high surface area, highly acidic chemically impregnated adsorbent. A preferred embodiment of the invention can employ a non-woven composite material having acidic functional groups that bind
15 to airborne bases. The invention can be used in lithography systems which employ materials that are sensitive to impurities, such as molecular bases present in the air circulating through semiconductor wafer processing equipment. A large number of bases including ammonia, NMP, triethylamine pyridine, and others, can be maintained at concentrations below 2 ppb in a tool cluster filtered with the present
20 invention. The invention also includes methods for forming the filter comprising, for example, the dry application of an active adsorbent to a non-woven carrier material, which is then heated and calendered with cover sheets.

In a preferred embodiment of this invention the non-woven carrier materials can be polyester non-wovens, and the adsorbent can include sulfonated divinyl
25 benzene styrene copolymer. Another preferred embodiment employs carboxylic functional groups. The acidic groups have at least 1 milliequivalent/gram acidity level or higher and preferably at least 4.0 milliequivalents/gram or higher. The polymers used are porous, preferably having a pore size in the range of 50-400 angstroms and a surface area of 20m²/g or higher.

The dry processing of a non-woven polyester batting allows for even distribution of adsorbent particles throughout the depth of the polyester batting. This provides an increased bed depth at a very low pressure drop, which is highly desirable since a twofold increase in bed depth can increase the filter's breakthrough time (time to failure) fourfold when using these thin fabric based sulfonic beds.

Thus, the invention provides a clean, cost effective, high efficiency, low pressure drop, adsorptive non-woven filter composite, and a method for forming said composite. The novel filter composite is particularly useful for the removal of base contaminants in an air stream, which contaminants can be gaseous or vaporous.

10 Particulates will also be removed if greater than the pore size of the filter. The filter has a service life of at least 12 months with a pressure drop to reduce power consumption and minimize impact on the systems operation. For example, a high pressure drop filter can require a longer time for a lithography system to equilibrate the temperature and humidity after filter replacement.

15 In an alternative embodiment, the filter uses both sulfonated divinyl benzene styrene copolymer and an activated carbon as the adsorbent. Activated carbon is discussed in greater detail in U.S. Patent No. 5,582,865 titled "Non-Woven Filter Composite." The entire contents of this patent is incorporated herein by reference. The filter in this preferred embodiment has two (or more) layers, one of activated

20 carbon and one of sulfonated divinyl benzene styrene copolymer beads. Additionally, two or more materials can be mixed to provide the filter system of the present invention.

In another preferred embodiment a synthetic carbon material, such as that described in U.S. Patent No. 5,834,114, the contents of which are incorporated

25 herein by reference, can be coated with the materials of the present invention to provide a porous acidic filter in accordance with the invention.

A detection system and method of use for determining when the filter needs to be replaced by detecting base contaminants in air is described in U.S. Patent Application No. 09/232,199 entitled "Detection of Base Contaminants in Gas

30 Samples", filed on January 14, 1999 with Oleg Kishkovich, et al as inventors. Also

U.S. Patent Application No. 08/795,949 entitled "Detecting of Base Contaminants", filed February 28, 1997 with Oleg Kishkovich, et al as inventors and U.S. Patent Application No. 08/996,790 entitled "Protection of Semiconductor Fabrication and Similar Sensitive Processes", filed December 23, 1997 with Oleg Kishkovich, et al as inventors can also be used with the present invention. These patent applications disclose the protection of a DUV lithography processes using chemically amplified photoresists which are sensitive to amines in the air. These patent applications are incorporated in the present application in their entirety by reference.

A preferred embodiment of a method of fabricating a filter element having a large surface area and the desired flow characteristics involves the use of a powdered material that is deposited in sequential layers one on top of the other. Following the deposit of each layer of powdered material, a binder material is delivered onto each layer of powdered material using a printing technique in accordance with a computer model of the three dimensional filter element being formed. Following the sequential application of all of the required powder layers and binder material to form the part in question, the unbound powder is appropriately removed, resulting in the formation of the desired three dimensional filter element. This technique provides for the fabrication of complex unitary or composite filter elements having high surface area that are formed with a very high degree of resolution.

BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing and other objects, features and advantages of the invention will be apparent from the following more particular description of preferred embodiments of the invention, as illustrated in the accompanying drawings in which like reference characters refer to the same parts throughout the different views. The drawings are not necessarily to scale, emphasis instead being placed upon illustrating the principles of the invention.

FIG. 1 is a perspective view of the apparatus of this invention before heating and calendaring;

This Sheet Has Been Replaced



FIG. 2A is a perspective view of the apparatus of this invention after heating and calendaring;

FIG. 2B is a perspective view of the apparatus of this invention after heating and calendaring with a cover sheet;

5 FIG. 3A is a perspective view of the apparatus of this invention in a square or rectangular containment structure showing the creases of the pleated structure;

FIG. 3B is a top view of the apparatus of this invention showing its pleated structure;

FIG. 4 is a top view of the apparatus of this invention with a high first pass
10 efficiency multi-pleat pack panel filter in a square or rectangular containment structure;

FIG. 5A is a top view of the apparatus of this invention in a radially pleated cylindrical containment structure;

FIG. 5B is top view of the apparatus of this invention in a media-wrapped
15 cylindrical filter; and

FIG. 6 is a perspective view of a process of producing a filter of the invention.

FIG. 7 is a pleated filter made in accordance with the invention.

FIG. 8 is a graphical illustration comprising the base removal efficiency of
20 filters previously available and a filter made in accordance with the invention.

FIG. 9 is a process for fabricating a filter in accordance with a preferred embodiment of the invention.

FIG. 10 illustrates an example of a three dimensional filter fabricated in accordance with the process.

25 DETAILED DESCRIPTION OF THE INVENTION

Referring to FIG. 1, a portion of a composite 16 is shown. The composite 16 has a cover sheet 66 and a middle layer 62. In a preferred embodiment, the cover sheet 66 is a polyester non woven having a binder to fiber ratio of 55/44 and a thickness of 0.024 inches. The middle layer 62 is air-laid polyester non woven

This Sheet Has Been Replaced



having a thickness of 0.25 inches and binder to fiber ratio of 35%/65%. The composite is impregnated with a porous acidic polymer material that binds readily with molecular bases in air flowing through the filter.

The structure of FIG. 2A can be used directly in this form as the composite
5 filter element. The composite 16, in a preferred embodiment employs a second cover sheet 80, provided on the surface of middle layer 62, opposite to the first cover sheet 66 backing 12, as shown in FIG. 2B. Alternatively, a second cover sheet 14a, can be provided over the backing layer 12, as shown in FIG. 2C. The cover sheet can be a filtering or non-filtering non-woven polyester, polyamide or polypropylene
10 material or other similar materials. If the cover sheet is a filtering material, it serves to provide some filtering of the air entering the composite structure for removal of particulate materials in the air stream. The cover can also serve to retain the porous acidic polymer material such as a sulfonated divinyl benzene styrene copolymer, which can be in bead form, within the middle layer or batting 62. The cover sheets
15 can also be chemically inert materials such as polypropylene.

The composite 16, can be contained within any suitable container or frame work for installation in an intended position for filtering operation, typically in the form of a removable or replaceable filter element. For many purposes, it is preferable to increase the surface area of the filter material exposed to an incident air
20 flow, and for this purpose the composite can be pleated to provide the increased surface area.

One embodiment is shown in FIG. 3A, in which the composite material forms an air filter 15 or 17. The filter material is pleated into an accordion like structure 19 as shown in FIG. 3B, contained within a square or rectangular container
25 18, having a front 21, and back 23, which are open to an air stream shown by arrow 22. The pleating 20 is substantially perpendicular to the air flow. FIG. 3A shows the structure in a front or back view. FIG. 3B shows a cutaway top view of a filter structure.

An alternative embodiment is shown in FIG. 4 wherein a plurality of pleated
30 composite elements 24, are sequentially disposed within container 18, to provide a

This Sheet Has Been Replaced



multi-stage filter through which the air can pass. As in the above embodiment, the pleats 20, of the elements 24, are substantially perpendicular to the direction of air flow 22.

A further embodiment is shown in FIG. 5A, wherein the composite structure 16, is disposed in a cylindrical configuration and retained within a cylindrical container 28. The pleats 20, are as described above, substantially perpendicular to a radially directed air flow. A further embodiment is shown in FIG. 5B wherein the composite structure is wound in a spiral configuration 30, contained within a generally cylindrical container 28.

10 In a preferred embodiment, adsorbent particles are evenly distributed throughout the non-woven or fiber matrix or polyester batting. An example of an adsorbent particle includes but is not limited to sulfonated divinyl benzene styrene copolymer.

In a preferred embodiment, the ion exchange strongly acidic preliminary catalyst has the important properties including a particle size of between 0.3 and 1.2 mm, a porosity of approximately 0.30 ml/g, and an average pore diameter of 250 Å. The catalyst preferably has a higher porosity of up to 300 ml/g, or higher. In addition in a preferred embodiment has the properties of concentration of acid sites of approximately 1.8 meq/ml and surface area of 45 m²/g. One such catalyst is sold under the tradename AMBERLYST® 15DRY or AMBERLYST® 35DRY by 20 Rohm and Haas.

Overall, the dry processing of the fiber matrix, which includes the combination of the fluidized bed sulfonated divinyl benzene styrene copolymer deposition process, the inherent stratification of the batting's density, and the even 25 distribution of the sulfonated divinyl benzene styrene copolymer particles as well as stratification of the sulfonated divinyl benzene styrene copolymer particle size, allows for a fabric architecture having an increased bed depth at a very low pressure drop, which is highly desirable due to its high first pass efficiency coupled with its low operating cost.

The term "efficiency" as employed herein is defined by the formula $X-Y/X$ wherein X is the upstream concentration of pollutant, and Y is the downstream concentration of pollutant.

It is recognized that the filter can have a mix of an activated carbon and the preliminary catalyst material discussed above. This combination has sufficient porosity and strongly acidic groups to provide easy permanent removal of medium and strong bases and sufficient retention of weak bases from the airborne base contaminants. The filter can also include a porous polymer material.

The filter as described is employed in filtering the air in environments such as semiconductor fabrication systems where there is a requirement for uncontaminated air of high quality.

Referring to Fig. 6, the middle air-laid polyester non woven lay 62 is collated to a cover sheet 66. The adsorbent particles 60 are positioned on a fiber matrix 62 from a fluidized bed 64. The sulfonated divinyl benzene styrene copolymer particles 60 are evenly stratified throughout the depth of the batting 62. As discussed above, an increased bed depth of adsorbent particles distributed throughout the batting is highly desirable as it increases residence time, increases exposure of the adsorbent particle surfaces, provides a low pressure drop, as well as substantially increasing the lifetime of the filter.

The adsorbent particles 60 distributed in the matrix 62 are then heated, preferably using two zones 68, 70 of infrared energy at different wavelengths. The batting 62 is heated to an overall average temperature of between 250° and 350° F.

The infrared energy causes the adsorbent particles to adhere to the batting at points where the particles contact the batting. This procedure avoids the necessity of raising the temperature of the entire batting to a point at, or near, the melting point of the polyester batting, which could cause the batting to melt and collapse thereby encasing the particles and destroying their chemical activity.

The batting 62 is then calendared using a pair of calender rolls 76,78. The first of these rolls 76 can be temperature controlled which allows the heating and calendaring steps to be carried out at a steady temperature of around 140°, and

This Sheet Has Been Replaced



prevents overheating and subsequent melting of cover sheet and prevents over calendaring of the fabric. The second roll, roll 78, is a rubber roll having a durometer that avoids crushing of the adsorbent particles.

Furthermore, when the temperature controlled roller 76 is used, the pressure
5 at which the batting is 2000 pounds across the 26 inch distance. Higher calendaring pressures can crush the particles particularly when those particles are activated carbon based, thereby forming dust, which cannot be retained in the filter composite and can consequently pass into the gas stream.

In addition, a synthetic non-woven cover sheet 80, which helps to maintain
10 the sulfonated divinyl benzene styrene copolymer in the batting, may be calendared with the batting 62, as discussed above. After the filter is formed, gussets or spacers are placed in the filter. The filter is sealed into a metal box.

Optionally, the material may be conducted over an upper roller 84 to
facilitate cooling the material prior to further processing. The method of
15 manufacture for an activated carbon filter is described in detail in U.S. Patent No. 5,582,865 titled "Non-Woven Filter Composite." The entire contents of this patent is incorporated herein by reference.

While the above described method is a preferred method of creating the
filter, it is recognized that other techniques can be used. Some of these techniques
20 include those developed by Hoechst such as that described in U.S. Patent No. 5,605,746, the entire contents of which is incorporated herein by reference or KX Media. The common feature in all these methods are the incorporation of a chemically active sorbent into a porous media structure.

A pleated filter structure 220 using the porous acidic polymer of the present
25 invention is illustrated in FIG. 7. This is a pleated system open on both sides of a rectangular frame 228 with a length 222, width 224 and depth such that it can be used as a replacement filter in stack filter systems. The filter has a removal efficiency of over 99% at 1000 ppb.

FIG. 8 graphically illustrates the removal efficiency for three different filters.
30 The graphs represent removal efficiency as a function of time at 20 ppm of NH_3 .

This Sheet Has Been Replaced




concentration upstream from the filter. Filter size is ~12"x12"x6". Air flow is ~100 cfm. Considering service life data only, it appears that filter #3 performed best. However, if additional data is considered, the conclusion is not so simple. Pressure drop of filter #1 was 0.2"WC; for filter #2 was 0.3"WC; and for filter #3 was
5 1.0"WC. Filters #1 and #2 are very close to tool manufacturer's specifications, but #3 creates an excessive pressure drop that interferes with tool's proper ECU functioning. Excessive pressure drop is undesirable for multiple reasons. For example, it increases fan load and power consumption, reduces airflow through the tool and positive pressure inside the enclosure. Thus filter #1 made in accordance
10 with the present invention provided a substantial improvement in service life while providing a pressure drop that is compatible with tool operation.

Another preferred embodiment of the invention involves the fabrication of high surface area filter elements using a three dimensional printing technique as described in U.S. Patent Nos. 5,204,055, 5,340,656, and 5,387,380, the entire
15 contents of these patents being incorporated herein by reference.

Such a method of fabrication of a filter element is illustrated in connection with FIG. 9. The process 200 includes forming a three dimensional model 202 of the filter element such that the dimensions are well defined. The first layer of the powder material used to form the filter is placed 204 the printer apparatus. A binder
20 is then delivered 206 onto the powder material resulting in the binding of selected regions thereof. Steps 204 and 206 are repeated a number of times until the high surface area filter is formed. Finally, the excess material is removed 210. An illustrative example of a high surface area filter made in accordance with this method is shown in the example 240 of FIG. 10. The binder can be an acid
25 polymerizable or acid cross linkable liquid.

While this invention has been particularly shown and described with references to preferred embodiments thereof, it will be understood by those skilled in the art that various changes in form and details may be made therein without departing from the spirit and scope of the invention as defined by the appended
30 claims.

This Sheet Has Been Replaced




CLAIMS

What is claimed is:

1. A fluid-permeable filter comprising:
a porous particulate material formed with a copolymer having an
acidic functional group such that the group can react with a reagent; and
a filter element having the porous particulate material.
2. The filter of Claim 1 wherein the particulate material comprises a porous
divinyl benzene styrene copolymer having a sulfonic acid group
3. The filter of Claim 1 wherein the acidic group has an acidity level of at least
1 milliequivalent/gram.
4. The filter of Claim 1 wherein the material has a pore size in the range of 50-
400 angstroms.
5. The filter of Claim 1 wherein the acidic functional group comprises a
carboxylic acid.
6. The filter of Claim 1 wherein the filter comprises a pleated filter .
7. The filter of Claim 1 wherein the filter element has a surface area of 20 m²/g
or higher.

This Sheet Has Been Replaced



8. A porous filter comprising:
a filter having a porous material selected from the group of particles,
threads, yarns, ribbons, fibers or filaments of a polymer,
the polymer comprising an acid functional group selected from the
5 group consisting of a sulfonic or carboxylic acid.
9. The filter of Claim 8 wherein the material has an area of 20 m²/g.
10. A method of filtering air for a fabrication facility needing uncontaminated air
of high quality, comprising the steps of:
providing a non-woven carrier material having a top surface and
10 having thermo-plastic fibers of lower fiber density relative to the fiber
density of the resultant composite; the woven carrier retaining adsorbent
particles of a sulfonated divinyl benzene styrene copolymer;
flowing air through the filter with the surfaces of said distributed
adsorbent particles being exposed for contact with passing air; and
15 removing the base contaminants from the air with the sulfonated
material.
11. A method for forming a vapor absorptive non-woven air filter comprising
thermo-plastic fibers and adsorptive particles, said composite having a fiber
density, comprising the steps of:
20 providing a non-woven carrier material having a surface and
comprising thermo-plastic fibers;
applying adsorbent particles of an acidic polymer to said surface of
said carrier material.

This Sheet Has Been Replaced



* C L M S *


12. The method of Claim 11 further comprising heating said carrier material and applied adsorbent particles; and
calendering the heated carrier material with said adsorbent particles distributed therein;
- 5 wherein said heating and calendering steps are performed for a period of time and under a pressure selected to be sufficient for said adsorbent particles to become retained within said heated and calendered carrier material to form a calendered composite having an open fibrous structure of said given fiber density with the surfaces of said distributed adsorbent
- 10 particles being substantially exposed for contact with air passing through said calendered composite, said resulting non-woven air filter composite being characterized by a pressure drop sufficient for use as an air filter.
13. The method of Claim 11 wherein the acidic polymer comprises a sulfonated copolymer.
- 15 14. The method of Claim 11 wherein the acidic polymer comprises a carboxylic copolymer.
15. An adsorptive, filter composite comprising:
a porous sulfonated divinyl benzene styrene copolymer beads having sulfonic acid functional side groups used to remove molecular bases from
- 20 air.
16. The filter composite of Claim 15 wherein the filter removes molecular base materials from a semiconductor processing tool
17. The filter composite of Claim 15 wherein the beads have a surface area of 20 m²/g or greater.

This Sheet Has Been Replaced

18. The filter composite of Claim 15 further comprising a binder material.
19. A filter element comprising alternating layers of a powder material and a binder.
20. The filter element of Claim 19 wherein the binder includes an acid-polymerizable or acid-cross-linkable liquid.
21. The filter element of Claim 20 wherein the powder material includes divinyl benzene styrene copolymer.
22. The filter element of Claim 19 wherein the filter element is a component of a semiconductor processing tool.
23. The filter element of Claim 22 wherein the semiconductor processing tool includes a deep-ultraviolet photolithography device.
24. A method for filtering molecular base contaminants from air in semiconductor processing equipment comprising passing air through a filter element comprising alternating layers of a powder material and a binder.
25. The method of Claim 24 wherein the binder includes an acid-polymerizable or acid-cross-linkable liquid.
26. The method of Claim 25 wherein the powder material includes divinyl benzene styrene copolymer.
27. The method of Claim 26 wherein the air is delivered to a deep-ultraviolet photolithography tool after passing through the filter element.



This Sheet Has Been Replaced



28. A method for forming a filter element comprising the steps of:
- a) forming a layer of adsorbent powder material;
 - b) delivering binder onto selected regions of the layer of adsorbent powder material to bond the regions of adsorbent material in accordance with a programmed model; and
 - c) repeating steps (a) and (b) until a filter element matching the programmed model is formed.
29. The method of Claim 28 wherein the binder includes an acid-polymerizable or acid-cross-linkable liquid.
30. The method of Claim 29 wherein the powder material includes divinyl benzene styrene copolymer.
31. The method of Claim 28 further comprising the step of removing excess powder.

