Method For Manufacturing A Crystalline Layer Of PZT Material, And Substrate For Epitaxially Growing A Crystalline Layer Of PZT Material

FIELD OF THE INVENTION

The present invention relates to a process for producing a crystalline layer of lead zirconate titanate (PZT) material and a substrate for the epitaxial growth of such a crystalline layer of PZT material.

PRIOR ART

Certain materials are not currently available as a crystalline substrate let alone as a monocrystalline substrate in the form of a large-diameter wafer. Moreover, certain materials may be available in large diameter but not with certain characteristics or specifications in terms of quality, in particular with regard to the density of defects or the required electrical or optical properties.

SUMMARY OF THE INVENTION

Embodiments of the present invention aim to overcome these limitations of the prior art by providing a process for producing a crystalline layer of PZT material, preferably a monocrystalline layer of PZT material, and a substrate for the epitaxial growth of such a crystalline layer of PZT material, preferably of such a monocrystalline layer of PZT material. In this way it is possible to address the problem of size of the crystalline or even monocrystalline substrates of PZT material currently available.

An aspect of the present invention provides a process for producing a crystalline layer of PZT material, the process comprising a~~the~~ transfer of a monocrystalline seed layer of $SrTiO_3$ material to a carrier substrate of silicon material, and followed by an epitaxial growth of the crystalline layer of PZT material on the monocrystalline seed layer of $SrTiO_3$ material, wherein the carrier substrate of silicon material comprises a detachable interface configured to withstand mechanical and/or thermal stresses during the epitaxial growth and to be detached by means of a laser debonding technique and/or chemical attack and/or by means of mechanical stress after the epitaxial growth.

In advantageous embodiments, the crystalline layer of PZT material is monocrystalline.

CLAIMS

1. A process for producing a crystalline layer of PZT material, the process comprising:

the a transfer of a monocrystalline seed layer of $SrTiO_3$ material to a carrier substrate of silicon material, ; and

followed by an epitaxial growth of the crystalline layer of PZT material on the monocrystalline seed layer of $SrTiO_3$ material,

wherein the carrier substrate of silicon material comprises a detachable interface configured to withstand mechanical and/or thermal stresses during the epitaxial growth and to be detached by means of a laser debonding technique and/or chemical attack and/or by means of mechanical stress after the epitaxial growth.

2. The process as claimed in claim 1, wherein the monocrystalline seed layer has a thickness of less than 10 µm, preferably less than 2 µm, and more preferably less than 0.2 µm.

3. The process as claimed in claim 1 or 2, wherein the transfer of the monocrystalline seed layer of $SrTiO_3$ material to the carrier substrate of silicon material comprises a step of joining a monocrystalline substrate of $SrTiO_3$ material to the carrier substrate followed a step of thinning said monocrystalline substrate of $SrTiO_3$ material.

4. The process as claimed in claim 3, wherein the thinning step comprises the formation of a weakened zone delimiting a portion of the monocrystalline substrate of $SrTiO_3$ material intended to be transferred to the carrier substrate of silicon material.

5. The process as claimed in claim 4, wherein the formation of the weakened zone is obtained by implanting atomic and/or ionic species.

6. The process as claimed in claim 4 or 5, wherein the thinning step comprises detaching at the weakened zone so as to transfer said portion of the monocrystalline substrate of $SrTiO_3$ material to the carrier substrate of silicon material, in particular the detaching comprises the application of a thermal and/or mechanical stress.

7. The process as claimed in any one of claims 3 to 6, wherein the joining step is a molecular adhesion step.

8. The process as claimed in one of the preceding claims, wherein the monocrystalline seed layer of $SrTiO_3$ material is in the form of a plurality of tiles each transferred to the carrier substrate of silicon material.

~~9. A substrate for epitaxial growth of a crystalline layer of PZT material characterized in that it comprises a monocrystalline seed layer of $SrTiO_3$ material on a carrier substrate of silicon material, wherein the carrier substrate of silicon material includes a detachable interface configured to be detached by means of a laser debonding technique and/or chemical attack and/or by means of mechanical stress.~~

~~10. The substrate for epitaxial growth of a crystalline layer of PZT material as claimed in claim 9, wherein the monocrystalline seed layer of $SrTiO_3$ material is present in the form of a plurality of tiles.~~