

SPECIFICATION

AK-9401

TITLE OF THE INVENTION

METHOD FOR INJECTION MOLDING POLYETHYLENE TEREPHTHALATE

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

The present invention relates to a method for injection molding an uncrystallized or crystallized polyethylene terephthalate into a desired molded form such as preform, with pre-drying omitted.

10 2. Background Art

A pellet of the polyethylene terephthalate (PET) produced by bulk polymerizing of ethylene glycol with terephthalic acid or dimethyl terephthalate is an uncrystallized and transparent material. The PET whose
15 moisture content does not reach an equilibrium has further moisture-absorption characteristics and thus when the PET is molten in a moisture absorbed condition, a hydrolysis develops to cause the PET not to be molded.

An uncrystallized PET pellet, when heated to a
20 temperature above its glass transition point (T_g), becomes softened somewhat to have an adhesive characteristics. The adhesive characteristics causes the PET pellets to be poorly bitten into a screw and thus not to be fed when molding. On the other hand, a crystallized PET pellet, even at a
25 temperature above its T_g , is not softened, thereby keeping

This Sheet Has Been Replaced



- 1 -

REPLACED SHEETS SG

☒ Description	: paged 1 to paged 17
☒ Claim(s)	: paged 18 to paged 20
☒ Drawing(s)	: paged to paged
☒ Abstract	: paged 21 to paged

hardness and having no adhesive characteristics.

Thus, material manufacturers dry an uncrystallized PET pellet at a temperature of 150 to 160°C to produce a dehumidified and crystallized PET pellet which is sold as a commercially available molding material. This causes an ordinary and commercially available PET to become more expensive than an uncrystallized PET. The uncrystallized PET, which has been sold by some of material manufacturers, has been dried to effect dehumidification and crystallization by molding manufacturers before use. Therefore, the crystallized PET described herein means a dried commercially available product, while the uncrystallized PET means an undried product. In molding a product using the PET as a material, even the crystallized PET has a moisture-absorption characteristics in nature and thus absorbs moisture content to some extent varying with control conditions before it is used as a molding material, thus it is customary to dry preliminarily the PET immediately before molding.

It takes about four hours to accomplish the preliminary drying at a temperature of 150°C. Both the increased usage of material per hour to improve a molding cycle efficiency, and the consideration to the prevention of a shortage of fed material even for a long time operation cause a dryer installed to an injection molding machine to become inevitably large in size and the power consumption



required for drying to tend to increase. Problems exist in that it takes a lot of time to make preparations before molding operation, and that a malfunctioned dryer affects seriously molding operation.

5 Then, injection molding means omitting the preliminary drying can be devised. As such molding means, there has been known a vent type molding machine in which an injection screw in a heating cylinder is divided into a first stage and a second stage, and the moisture content in a
10 molten resin in the first stage is removed to the outside through a vent opening provided between both the stages.


 In this well-known vent type molding machine, the screw groove of a feeding zone of the first stage leading from the rear end at which a hopper is located to a metering
15 zone at the front end is formed in a deep groove; pellets of the material resin fed from the hopper in a humid condition is molten due to heat insulation and compression while being sequentially fed by screw rotation; and then the groove leads through the metering zone having a shallow groove to the
20 second stage.

 The screw groove in the second stage is formed in a deep groove, so that when the molten resin is transferred to the groove, the pressure of the molten resin is reduced due to the rapid increase in the groove depth of the screw to
25 cause the moisture content in the resin to be vaporized, and

the moisture content wrapped in the resin by screw rotation to be separated, which moisture content is then sucked and removed through the vent opening by a vacuum pump. The molten resin whose moisture content has been removed in this manner is fed by screw rotation to a metering zone at the front end of the second stage, and then to a position in front of the screw to store, in a similar manner to an injection molding machine having an ordinary mechanism. The molten resin thus stored is injected and loaded into a cavity by the forward movement of the injection screw after stoppage of screw rotation.

Although, generally the employment of such vent type injection unit may allow even a material having a large moisture absorption to be molded without the preliminary drying, such unit is not applied to all of resins, and with respect to the PET, particularly an uncrystallized one, the pellet is softened and compressed in a feed zone to cause it to be accumulated, whereby the PET in the hopper cannot enter the zone, and the biting by the screw becomes extremely poor such that the material cannot be fed. As a result, it has been quite difficult to perform the injection molding without the necessity of the preliminary drying by employing a conventional vent type injection unit.

25 SUMMARY OF THE INVENTION



The present invention is devised to solve problems with the above-mentioned conventional PET injection molding, and it is an object of the invention to provide a method for injection molding the PET by which although a vent type
5 injection unit is employed as means for omitting preliminary drying, the unit does not develop a poor screw biting, and even when a molding material is an uncrystallized or crystallized PET, can feed a certain amount of the material at all times to injection mold a desired transparent molded
10 form such as a preform, and use the preform to produce a thin-wall container with a low cost.

The present invention according to the above-mentioned purpose employs a vent type injection unit in which an injection screw comprising a first stage and a second
15 stage is rotatably and movably mounted in a heating cylinder having a vent, and limits the feed rate of the material resin to a feed zone of the first stage of the vent type injection unit in such a manner that the material resin is not accumulated due to compression even if the material resin is
20 softened to an elastomeric state before reaching a compression zone in front of the feed zone. This limitation is effected by making the sectional area of the screw groove in a receiving zone at the feed zone rear end at which the hopper port of the first stage is located smaller than the
25 sectional area of the screw groove in the feed zone, in which



condition an uncrystallized or crystallized polyethylene terephthalate produced with the preliminary drying omitted is loaded in the hopper as a material resin to plasticate and inject.

5 Although it is preferable that the sectional area of the screw groove in the above-mentioned receiving zone 11 is set to no larger than $3/4$ the sectional area of the screw groove in feed zone, a smaller sectional area thus set causes the feed rate to become lower and the material metering time
10 to become longer than is required, so that it is most preferable that the former accounts for $2/3$ to $1/2$ the latter. In order to feed faster the PET, the screw is formed in a double screw to the halfway position of the compression zone, and then in a single screw from the compression zone to
15 the metering zone so as to set the screw pitch to a large value, thereby making sufficient the stretching of the molten resin to improve the vent effect in a vent opening of the second zone.

 In addition, the molding is performed in such a
20 manner that the heating temperature on the second stage side of the heating cylinder is set to a value lower than the heating temperature on the first stage side, thereby preventing acetaldehyde occurrence due to an overheated molten resin.

25 The removal of the moisture content in the resin



from the above-mentioned heating cylinder is performed by being sucked under a reduced pressure by means of a vacuum pump, which removal is not interrupted even when injecting during operation, and when injecting, the reduced pressure is
5 set to a value lower than that when plasticating, thereby preventing a vent up due to the forward movement of the injection screw. An injection molded preform is immediately or later transferred to a blowing mold, where it can be stretch-blow molded into a packaging container such as a
10 thin-wall bottle.

BRIEF DESCRIPTION OF THE DRAWINGS

Drawings show an example of a vent type injection unit capable of performing the injection molding method of
15 the present invention, in which:

Fig. 1 is a schematic longitudinal sectional and side view of the vent type injection unit according to the present invention, and

Fig. 2 is an enlarged side view of a screw provided
20 in the vent type injection unit of Fig. 1, in which a front end thereof is omitted.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In Figs., the numeral 1 indicates an injection
25 screw which is rotatably and movably inserted into a heating



cylinder 2. The injection screw 1 has a shape such that two screws having a deep groove section and a shallow groove section are reconnected to each other to form a single screw, and has a screw design such that a screw portion 10 located
5 in the rear portion of the heating cylinder 2 is made a first stage (10), while a screw 20 located in the front portion thereof is made a second stage (20).

The above-mentioned heating cylinder 2 includes a vent opening 3 on the wall portion on which the rear portion
10 of the second stage 20 is located, which opening is enclosed and connected with a vacuum pump (whose view is omitted). On the rear wall portion on which the rear portion of the first stage 10 is located, there is bored a feed port 4, which is mounted with a hopper 5 for a PET pellet (hereinafter simply
15 called a resin). On the outer periphery of the heating cylinder 2 and a nozzle 6, there are provided band heaters, though omitted in Figs., for heating a resin fed by screw rotation from the above-mentioned feed port 4.

Both the above-mentioned vent opening 3 and the
20 feed port 4 have an opening width with substantially the same size as the pitch of the screw they face.

Fig. 2 shows a screw design of the above-mentioned injection screw 1, in which the ratio of the first stage 10 to the second stage 20 in the overall length L is about 6:4,
25 thus the second stage 20 being formed shorter than the first



stage 10. The first stage 10 is divided into four zones of a receiving zone 11, a feed zone 12, a compression zone 13 and a metering zone 14 from the rear end, while the second stage 20 is divided into three zones of a feed zone 21, a compression zone 22 and a metering zone 23 from the rear end.

In the first stage 10 and the second stage 20, the screw is formed in a double screw up to the halfway position of the compression zones 13 and 22 except for the metering zones 14 and 23, whereby the feed of the material resin to the compression zones 13 and 22 by screw rotation is performed as fast as possible; while the screw in the metering zones 14 and 23 is formed in a single screw to widen the screw pitch in order to reduce as small as possible an un-uniformity of the molten resin.

In the first stage 10, the screw pitch P_1 of the receiving zone 11 is set to a value smaller than the screw pitch P_2 of the feed zone 12, while the screw pitch P_3 of the metering zone 14 is set to a value twice the above-mentioned screw pitch P_2 . The screw pitch of the feed zone 21 and the metering zone 23 of the second stage 20 is set in a similar manner to the screw pitch of the first stage 10.


The screw groove depth of the first stage 10 is set at the dimensions calculated from the screw groove depth of the feed zone 12. In order to limit the feed rate in the feed zone 12, the screw groove depth in the above-mentioned



receiving zone 11 is set to a shallow depth such that the sectional area of the screw groove in relation to the above-mentioned screw pitch P_1 becomes $2/3$ the sectional area of the screw groove of the feed zone 12; while the screw groove
5 depth in the metering zone 14 is set to a depth shallower than in the receiving zone 11 in order to stretch the molten resin by screw rotation.

The screw groove depth in the feed zone 21 of the second stage 20 is set to a deepest depth in order to
10 vaporize the moisture content in the molten resin by a rapid pressure reduction; while the screw groove depth in the metering zone 23 is set to a value deeper than in the metering zone 14 of the first zone 10, thereby making easy the feed of the molten resin by screw rotation.

15 To injection mold a molded article such as a preform using an uncrystallized PET by employing the vent type injection unit having the above-mentioned arrangement, first the temperature of the heating cylinder 2 that the second stage 20 holds is set to 270°C , and the temperature of
20 the heating cylinder 2 that the first stage 10 holds is set to 280°C . The undried and uncrystallized PET as a molded material is loaded in the above-mentioned hopper 5, and then the injection screw 1 is caused to rotate at a high speed (100 rpm). The atmospheric pressure of the opening 3 is
25 reduced to about -730 mm Hg by the vacuum pump.



The PET in the hopper 5 is fed by screw rotation into the receiving zone 11. The feed rate of the PET from the receiving zone 11 to the feed zone 12 is limited to a value accounting for $2/3$ the sectional area of the screw groove of the feed zone 12 determined by the above-mentioned screw groove sectional area setting, so that the PET in the feed zone 12 is not excessively accumulated, and thus even if the PET is softened to an elastomeric state, pellets are not massed with each other due to compression and not accumulate before the resin reaches the compression zone 13.

The PET softened in the feed zone 12 is compressed by the tapered surface of the compression zone 13 to cause it to be molten, stretched and temporarily plasticated, so that the PET is fed into the second stage 20 whose temperature is set to a value lower than the first stage 10. The screw groove of the feed zone 21 is formed in a deep groove, so that the pressure of the molten resin is reduced to cause the moisture content in the PET to be vaporized, and the moisture content wrapped in the molten PET by screw rotation to be separated, which moisture content is then sucked and removed through the vent opening 3 by the vacuum pump. The molten PET whose moisture content has been removed in this manner is fed by screw rotation to the metering zone 23 of the second stage 20 and further plasticated, and then fed to a position in front of the screw to store, in a similar manner to an



injection molding machine having an ordinary mechanism. As the molten PET is fed, the injection screw 1 is moved backwardly and stopped at a desired position to meter an amount required for injection. After metering, the molten resin is injected and loaded into a mold by forwardly moving the injection screw 1. Then the atmospheric pressure of the vent opening 3 is changed to about -650 mm Hg and maintained by the vacuum pump during injection operation. The atmospheric pressure can be easily controlled by taking the outer air into a suction line through valve operation.

The preform thus injection molded was transparent similarly to the case where a preliminary drying is performed before injection molding, and has no cloudiness due to hydrolysis, and also has an acetaldehyde occurrence within an allowable range.

An example of the specifications of the vent type injection unit of the present invention will be shown hereinafter:

20 Injection screw (double screw)

Screw length (L)	:	1670 mm
Screw outside diameter (D)	:	64 mm
L/D of Screw	:	26

	First stage	(Length)	(Screw minor dia.)	Screw pitch
25	Screw	998 mm		



	Receiving zone	128 mm	52.0 mm	32.0 mm
	Feed zone	646 mm	45.0 mm	38.5 mm
	Compression			
	zone	64 mm		
5	Metering zone	160 mm	57.2 mm	77.0 mm
	Second stage	(Length)	(Screw minor dia.)	Screw pitch
	Screw	672 mm		
	Feed zone	448 mm	43.2 mm	38.5 mm
	Compression			
10	zone	64 mm		
	Metering zone	160 mm	56.0 mm	77.0 mm
	Screw revolution speed	:	100 rpm	
	Injection stroke	:	120 mm	

15 When the PET is crystallized one, it is softened in
the feed zone 12 more slowly and transferred to the
compression zone 13 faster than the uncrystallized PET,
thereby tending to be apt to develop an uneven melting.
However, this problem can be solved by setting the
20 compression zone 13 to a length longer somewhat than the
above-mentioned numerical value.

The employment of the above-mentioned vent type
injection unit allows the injection molded preform to be
molded into a thin-wall packaging container such as a bottle
25 by the well-known stretch-blow molding. The well-known



stretch-blow molding is broadly classified into a molding method called the so-called two stage type in which the injection molding of the preform and the stretch-blow molding of the preform into a container are performed in separate
5 processes, and a molding method called the so-called one stage type in which the injection molding of the preform through the stretch-blow molding of the preform into a container are continuously performed, in either of both the methods, the PET preform produced by the injection molding
10 with the preliminary drying omitted can be molded into a thin-wall container as with the PET preform injection molded after being dried.

The following shows molding conditions in a case where with an injection molded preform held at its neck to a
15 limit in which its shape can be kept, the preform is released from a cavity and a core, transferred to a blowing mold when the surface temperature of the preform is being raised due to an internal potential heat, and immediately stretch-blow molded to mold a thin-wall container:

20

Material resin : UNIPET RY523 (manufactured by Unipet Co., Ltd.)

Molded form : flat bottle

Dimensions : overall height 250 mm

25

port inside dia. 23.5 mm



length under neck 230 mm

body outside dia. 90x50 mm

body wall thickness 0.4 mm

weight 36 g

5 Preform

Dimensions : Overall height 142 mm

port inside dia. 23.5 mm

length under neck 230 mm

body wall thickness 2.9 mm

10 body upper portion outside dia 28 mm

body lower end outside dia. 24 mm

draft 2/122

Preform molding conditions

Injection cylinder temperature

15 First stage : Front 285°C, middle 285°C, rear 280°C

Second stage: Front 270°C, rear 270°C

Nozzle temperature : 270°C

Injection mold temperature (set value)

Cavity mold : 15°C

20 Core mold : 15°C

Injection pressure (dwell) : 75 kg/cm²

Loading dwell time : 6.0 sec.

Cooling time : 2.8 sec.

Releasing temp. : 60 to 70°C (preform surface

25 temperature)



Stretch-blow molding conditions

Mold temperature (set value) : 20°C

Stretch-blowing temperature : 88°C (preform surface
temperature)

5 Blowing pressure (stretching) : 20 kg/cm²

Blowing time : 2.0 sec.

Percent of stretch:

Longitudinal (axial direction) 190 %

Lateral (radial direction) 360 x 200 %

10

As described above, according to the present invention, the injection molding of an uncrystallized PET and that of a crystallized PET with the preliminary drying omitted can be performed by the employment of the vent type
15 injection unit, thereby allowing a molded article having little hydrolysis to be obtained. A molded article developing little acetaldehyde due to overheating is obtained so that the uncrystallized PET having a lower commercial price can be utilized as a molding material, whereby the
20 material cost is reduced and the running cost required for the preliminary drying can be saved even for the crystallized PET, thereby allowing the price of a packaging container using the PET as a material to be reduced. The present invention has a further advantage in that the injection
25 molding itself requires no complex operation and can be



performed by employing conventional molding technologies as they are, thereby having a significantly high utility value in industrial field.





WHAT IS CLAIMED IS:

1. A method for injection molding polyethylene terephthalate as a material resin which is undried, characterized in that a vent type injection unit is employed
5 in which an injection screw comprising a first stage and a second stage is rotatably and movably mounted in a heating cylinder having a vent, and the feed rate of the material resin to a feed zone of the first stage of the vent type injection unit is limited in such a manner that the material
10 resin is not accumulated due to compression even if the material resin is softened before reaching a compression zone in front of the feed zone; and that this limitation is effected by making a sectional area of the screw groove in a receiving zone at the feed zone rear end at which a hopper
15 port of the first stage is located smaller than a sectional area of the screw groove in the feed zone, in which condition an uncrystallized polyethylene terephthalate with the preliminary drying omitted is loaded in the hopper as the material resin to plasticate and inject.

20

2. A method for injection molding polyethylene terephthalate as set forth in claim 1, wherein the sectional area of the screw groove in the above-mentioned receiving zone is set to no larger than $3/4$ the sectional area of the
25 screw groove in feed zone, and the screw is formed in a





double screw to the halfway position of the compression zone,
and then in a single screw from the compression zone to the
metering zone so as to set the screw pitch to a large value,
thereby making sufficient the stretching of a molten resin to
5 improve the vent effect in the vent of the second zone.

3. A method for injection molding polyethylene
terephthalate as set forth in claim 1, wherein the removal of
the moisture content in the resin from the heating cylinder
10 is performed by being sucked under a reduced pressure by
means of a vacuum pump, which removal is not interrupted even
when injecting during operation, and when injecting, the
reduced pressure is set to a lower value when plasticating,
thereby preventing a vent up due to the forward movement of
15 the injection screw.


4. A method for injection molding polyethylene
terephthalate as set forth in claim 1, wherein the heating
temperature on the second stage side of the heating cylinder
20 is set to a value lower than the heating temperature on the
first stage side, thereby preventing the molten PET from
being overheated.

5. A method for injection molding polyethylene
25 terephthalate as set forth in claim 1, wherein the molding



material is a crystallized polyethylene terephthalate produced with preliminary drying omitted.

6. A method for injection molding polyethylene
- 5 terephthalate as set forth in claim 1, wherein a molded article is a preform of a thin-wall packaging container molded by stretch-blow molding.



ABSTRACT

A method for injection molding polyethylene terephthalate by employing a vent type injection unit as means for omitting preliminary drying the resin, wherein the unit does not develop a poor screw biting, and even when a molding material is an undried uncrystallized or crystallized PET, can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container with a low cost.



FIG-1





FIG-2



REPLACED SHEETS		SG
☒ Description	: paged 1 to paged 17	
☒ Claim(s)	: paged 18 to paged 20	
☒ Drawing(s)	: paged 1 to paged 1	
☒ Abstract	: paged 21 to paged 1	

- 1 -

REPLACEMENT SHEETS		SG
☒ Description	: paged 1 to paged 17	
☒ Claim(s)	: paged 18 to paged 20	
☒ Drawing(s)	: paged 1 to paged 1	
☒ Abstract	: paged 21 to paged 1	
DATE OF RECEIPT		22 NOV 1996

SPECIFICATION

This is the replacement sheet

TITLE OF THE INVENTION

Date: 22 NOV 1996

METHOD FOR INJECTION MOLDING POLYETHYLENE TEREPHTHALATE

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a method for injection molding an uncrystallized or crystallized polyethylene terephthalate into a desired molded form such as preform, with pre-drying omitted.


2. Background Art

A pellet of the polyethylene terephthalate (PET) produced by bulk polymerizing of ethylene glycol with terephthalic acid or dimethyl terephthalate is an uncrystallized and transparent material. The PET whose moisture content does not reach an equilibrium has further moisture-absorption characteristics and thus when the PET is molten in a moisture absorbed condition, a hydrolysis develops to cause the PET not to be molded.

An uncrystallized PET pellet, when heated to a temperature above its glass transition point (T_g), becomes softened somewhat to have an adhesive characteristics. The adhesive characteristics causes the PET pellets to be poorly bitten into a screw and thus not to be fed when molding. On the other hand, a crystallized PET pellet, even at a temperature above its T_g , is not softened, thereby keeping

This Sheet Has Been Replaced





- 2 -

hardness and having no adhesive characteristics.

Thus, material manufacturers dry an uncrystallized PET pellet at a temperature of 150 to 160°C to produce a dehumidified and crystallized PET pellet which is sold as a commercially available molding material. This causes an ordinary and commercially available PET to become more expensive than an uncrystallized PET. The uncrystallized PET, which has been sold by some of material manufacturers, has been dried to effect dehumidification and crystallization by molding manufacturers before use. Therefore, the crystallized PET described herein means a dried commercially available product, while the uncrystallized PET means an undried product. In molding a product using the PET as a material, even the crystallized PET has a moisture-absorption characteristics in nature and thus absorbs moisture content to some extent varying with control conditions before it is used as a molding material, thus it is customary to dry preliminarily the PET immediately before molding.

It takes about four hours to accomplish the preliminary drying at a temperature of 150°C. Both the increased usage of material per hour to improve a molding cycle efficiency, and the consideration to the prevention of a shortage of fed material even for a long time operation cause a dryer installed to an injection molding machine to become inevitably large in size and the power consumption

This Sheet Has Been Replaced



22 NOV 1996

- 3 -

required for drying to tend to increase. Problems exist in that it takes a lot of time to make preparations before molding operation, and that a malfunctioned dryer affects seriously molding operation.

Then, injection molding means omitting the preliminary drying can be devised. As such molding means, there has been known a vent type molding machine in which an injection screw in a heating cylinder is divided into a first stage and a second stage, and the moisture content in a molten resin in the first stage is removed to the outside through a vent opening provided between both the stages.

In this well-known vent type molding machine, the screw groove of a feeding zone of the first stage leading from the rear end at which a hopper is located to a metering zone at the front end is formed in a deep groove; pellets of the material resin fed from the hopper in a humid condition is molten due to heat insulation and compression while being sequentially fed by screw rotation; and then the groove leads through the metering zone having a shallow groove to the second stage.

The screw groove in the second stage is formed in a deep groove, so that when the molten resin is transferred to the groove, the pressure of the molten resin is reduced due to the rapid increase in the groove depth of the screw to cause the moisture content in the resin to be vaporized, and

This Sheet Has Been Replaced

22 NOV 1996

- 4 -

the moisture content wrapped in the resin by screw rotation to be separated, which moisture content is then sucked and removed through the vent opening by a vacuum pump. The molten resin whose moisture content has been removed in this manner is fed by screw rotation to a metering zone at the front end of the second stage, and then to a position in front of the screw to store, in a similar manner to an injection molding machine having an ordinary mechanism. The molten resin thus stored is injected and loaded into a cavity by the forward movement of the injection screw after stoppage of screw rotation.

Although, generally the employment of such vent type injection unit may allow even a material having a large moisture absorption to be molded without the preliminary drying, such unit is not applied to all of resins, and with respect to the PET, particularly an uncrystallized one, the pellet is softened and compressed in a feed zone to cause it to be accumulated, whereby the PET in the hopper cannot enter the zone, and the biting by the screw becomes extremely poor such that the material cannot be fed. As a result, it has been quite difficult to perform the injection molding without the necessity of the preliminary drying by employing a conventional vent type injection unit.

SUMMARY OF THE INVENTION

This Sheet Has Been Replaced



REPLACEMENT SHEET

22 NOV 1996

- 5 -

The present invention is devised to solve problems with the above-mentioned conventional PET injection molding, and it is an object of the invention to provide a method for injection molding the PET by which although a vent type injection unit is employed as means for omitting preliminary drying, the unit does not develop a poor screw biting, and even when a molding material is an uncrystallized or crystallized PET, can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container with a low cost.

The present invention according to the above-mentioned purpose employs a vent type injection unit in which an injection screw comprising a first stage and a second stage is rotatably and movably mounted in a heating cylinder having a vent, and limits the feed rate of the material resin to a feed zone of the first stage of the vent type injection unit in such a manner that the material resin is not accumulated due to compression even if the material resin is softened to an elastomeric state before reaching a compression zone in front of the feed zone. This limitation is effected by making the sectional area of the screw groove in a receiving zone at the feed zone rear end at which the hopper port of the first stage is located smaller than the sectional area of the screw groove in the feed zone, in which

This Sheet Has Been Replaced



REPLACEMENT SHEET

22 NOV 1996

- 6 -


condition an uncrystallized or crystallized polyethylene terephthalate produced with the preliminary drying omitted is loaded in the hopper as a material resin to plasticate and inject.

Although it is preferable that the sectional area of the screw groove in the above-mentioned receiving zone 11 is set to no larger than $3/4$ the sectional area of the screw groove in feed zone, a smaller sectional area thus set causes the feed rate to become lower and the material metering time to become longer than is required, so that it is most preferable that the former accounts for $2/3$ to $1/2$ the latter. In order to feed faster the PET, the screw is formed in a double screw to the halfway position of the compression zone, and then in a single screw from the compression zone to the metering zone so as to set the screw pitch to a large value, thereby making sufficient the stretching of the molten resin to improve the vent effect in a vent opening of the second zone.

In addition, the molding is performed in such a manner that the heating temperature on the second stage side of the heating cylinder is set to a value lower than the heating temperature on the first stage side, thereby preventing acetaldehyde occurrence due to an overheated molten resin.

The removal of the moisture content in the resin

This Sheet Has Been Replaced



REPLACEMENT SHEET

22 NOV 1996

- 7 -

from the above-mentioned heating cylinder is performed by being sucked under a reduced pressure by means of a vacuum pump, which removal is not interrupted even when injecting during operation, and when injecting, the reduced pressure is set to a value lower than that when plasticating, thereby preventing a vent up due to the forward movement of the injection screw. An injection molded preform is immediately or later transferred to a blowing mold, where it can be stretch-blow molded into a packaging container such as a thin-wall bottle.

BRIEF DESCRIPTION OF THE DRAWINGS

Drawings show an example of a vent type injection unit capable of performing the injection molding method of the present invention, in which:

Fig. 1 is a schematic longitudinal sectional and side view of the vent type injection unit according to the present invention, and

Fig. 2 is an enlarged side view of a screw provided in the vent type injection unit of Fig. 1, in which a front end thereof is omitted.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In Figs., the numeral 1 indicates an injection screw which is rotatably and movably inserted into a heating

This Sheet Has Been Replaced



22 NOV 1996

- 8 -

cylinder 2. The injection screw 1 has a shape such that two screws having a deep groove section and a shallow groove section are reconnected to each other to form a single screw, and has a screw design such that a screw portion 10 located in the rear portion of the heating cylinder 2 is made a first stage (10), while a screw 20 located in the front portion thereof is made a second stage (20).

The above-mentioned heating cylinder 2 includes a vent opening 3 on the wall portion on which the rear portion of the second stage 20 is located, which opening is enclosed and connected with a vacuum pump (whose view is omitted). On the rear wall portion on which the rear portion of the first stage 10 is located, there is bored a feed port 4, which is mounted with a hopper 5 for a PET pellet (hereinafter simply called a resin). On the outer periphery of the heating cylinder 2 and a nozzle 6, there are provided band heaters, though omitted in Figs., for heating a resin fed by screw rotation from the above-mentioned feed port 4.

Both the above-mentioned vent opening 3 and the feed port 4 have an opening width with substantially the same size as the pitch of the screw they face.

Fig. 2 shows a screw design of the above-mentioned injection screw 1, in which the ratio of the first stage 10 to the second stage 20 in the overall length L is about 6:4, thus the second stage 20 being formed shorter than the first

This Sheet Has Been Replaced



22 NOV 1996

- 9 -

stage 10. The first stage 10 is divided into four zones of a receiving zone 11, a feed zone 12, a compression zone 13 and a metering zone 14 from the rear end, while the second stage 20 is divided into three zones of a feed zone 21, a compression zone 22 and a metering zone 23 from the rear end.

In the first stage 10 and the second stage 20, the screw is formed in a double screw up to the halfway position of the compression zones 13 and 22 except for the metering zones 14 and 23, whereby the feed of the material resin to the compression zones 13 and 22 by screw rotation is performed as fast as possible; while the screw in the metering zones 14 and 23 is formed in a single screw to widen the screw pitch in order to reduce as small as possible an un-uniformity of the molten resin.

In the first stage 10, the screw pitch P_1 of the receiving zone 11 is set to a value smaller than the screw pitch P_2 of the feed zone 12, while the screw pitch P_3 of the metering zone 14 is set to a value twice the above-mentioned screw pitch P_2 . The screw pitch of the feed zone 21 and the metering zone 23 of the second stage 20 is set in a similar manner to the screw pitch of the first stage 10.

The screw groove depth of the first stage 10 is set at the dimensions calculated from the screw groove depth of the feed zone 12. In order to limit the feed rate in the feed zone 12, the screw groove depth in the above-mentioned

This Sheet Has Been Replaced



REPLACEMENT SHEET

22 NOV 1996

- 10 -


receiving zone 11 is set to a shallow depth such that the sectional area of the screw groove in relation to the above-mentioned screw pitch P_1 becomes $2/3$ the sectional area of the screw groove of the feed zone 12; while the screw groove depth in the metering zone 14 is set to a depth shallower than in the receiving zone 11 in order to stretch the molten resin by screw rotation.

The screw groove depth in the feed zone 21 of the second stage 20 is set to a deepest depth in order to vaporize the moisture content in the molten resin by a rapid pressure reduction; while the screw groove depth in the metering zone 23 is set to a value deeper than in the metering zone 14 of the first zone 10, thereby making easy the feed of the molten resin by screw rotation.

To injection mold a molded article such as a preform using an uncrystallized PET by employing the vent type injection unit having the above-mentioned arrangement, first the temperature of the heating cylinder 2 that the second stage 20 holds is set to 270°C , and the temperature of the heating cylinder 2 that the first stage 10 holds is set to 280°C . The undried and uncrystallized PET as a molded material is loaded in the above-mentioned hopper 5, and then the injection screw 1 is caused to rotate at a high speed (100 rpm). The atmospheric pressure of the opening 3 is reduced to about -730 mm Hg by the vacuum pump.

This Sheet Has Been Replaced






- 11 -

The PET in the hopper 5 is fed by screw rotation into the receiving zone 11. The feed rate of the PET from the receiving zone 11 to the feed zone 12 is limited to a value accounting for $2/3$ the sectional area of the screw groove of the feed zone 12 determined by the above-mentioned screw groove sectional area setting, so that the PET in the feed zone 12 is not excessively accumulated, and thus even if the PET is softened to an elastomeric state, pellets are not massed with each other due to compression and not accumulate before the resin reaches the compression zone 13.

The PET softened in the feed zone 12 is compressed by the tapered surface of the compression zone 13 to cause it to be molten, stretched and temporarily plasticated, so that the PET is fed into the second stage 20 whose temperature is set to a value lower than the first stage 10. The screw groove of the feed zone 21 is formed in a deep groove, so that the pressure of the molten resin is reduced to cause the moisture content in the PET to be vaporized, and the moisture content wrapped in the molten PET by screw rotation to be separated, which moisture content is then sucked and removed through the vent opening 3 by the vacuum pump. The molten PET whose moisture content has been removed in this manner is fed by screw rotation to the metering zone 23 of the second stage 20 and further plasticated, and then fed to a position in front of the screw to store, in a similar manner to an

This Sheet Has Been Replaced





- 12 -

injection molding machine having an ordinary mechanism. As the molten PET is fed, the injection screw 1 is moved backwardly and stopped at a desired position to meter an amount required for injection. After metering, the molten resin is injected and loaded into a mold by forwardly moving the injection screw 1. Then the atmospheric pressure of the vent opening 3 is changed to about -650 mm Hg and maintained by the vacuum pump during injection operation. The atmospheric pressure can be easily controlled by taking the outer air into a suction line through valve operation.

The preform thus injection molded was transparent similarly to the case where a preliminary drying is performed before injection molding, and has no cloudiness due to hydrolysis, and also has an acetaldehyde occurrence within an allowable range.

An example of the specifications of the vent type injection unit of the present invention will be shown hereinafter:

Injection screw (double screw)

Screw length (L)	:	1670 mm
Screw outside diameter (D)	:	64 mm
L/D of Screw	:	26

First stage	(Length)	(Screw minor dia.)	Screw pitch
Screw	998 mm		

This Sheet Has Been Replaced



REPLACEMENT SHEET

22 NOV 1996

- 13 -

Receiving zone	128 mm	52.0 mm	32.0 mm
Feed zone	646 mm	45.0 mm	38.5 mm
Compression			
zone	64 mm		
Metering zone	160 mm	57.2 mm	77.0 mm
Second stage	(Length)	(Screw minor dia.)	Screw pitch
Screw	672 mm		
Feed zone	448 mm	43.2 mm	38.5 mm
Compression			
zone	64 mm		
Metering zone	160 mm	56.0 mm	77.0 mm
Screw revolution speed	:	100 rpm	
Injection stroke	:	120 mm	

When the PET is crystallized one, it is softened in the feed zone 12 more slowly and transferred to the compression zone 13 faster than the uncrystallized PET, thereby tending to be apt to develop an uneven melting. However, this problem can be solved by setting the compression zone 13 to a length longer somewhat than the above-mentioned numerical value.

The employment of the above-mentioned vent type injection unit allows the injection molded preform to be molded into a thin-wall packaging container such as a bottle by the well-known stretch-blow molding. The well-known

This Sheet Has Been Replaced



22 NOV 1996

- 14 -


stretch-blow molding is broadly classified into a molding method called the so-called two stage type in which the injection molding of the preform and the stretch-blow molding of the preform into a container are performed in separate processes, and a molding method called the so-called one stage type in which the injection molding of the preform through the stretch-blow molding of the preform into a container are continuously performed, in either of both the methods, the PET preform produced by the injection molding with the preliminary drying omitted can be molded into a thin-wall container as with the PET preform injection molded after being dried.

The following shows molding conditions in a case where with an injection molded preform held at its neck to a limit in which its shape can be kept, the preform is released from a cavity and a core, transferred to a blowing mold when the surface temperature of the preform is being raised due to an internal potential heat, and immediately stretch-blow molded to mold a thin-wall container:

Material resin	:	UNIPET RY523 (manufactured by Unipet Co., Ltd.)
Molded form	:	flat bottle
Dimensions	:	overall height 250 mm port inside dia. 23.5 mm

This Sheet Has Been Replaced





length under neck 230 mm
body outside dia. 90x50 mm
body wall thickness 0.4 mm
weight 36 g

Preform

Dimensions : Overall height 142 mm
port inside dia. 23.5 mm
length under neck 230 mm
body wall thickness 2.9 mm
body upper portion outside dia 28 mm
body lower end outside dia. 24 mm
draft 2/122

Preform molding conditions

Injection cylinder temperature

First stage : Front 285°C, middle 285°C, rear 280°C

Second stage: Front 270°C, rear 270°C

Nozzle temperature : 270°C

Injection mold temperature (set value)

Cavity mold : 15°C

Core mold : 15°C

Injection pressure (dwell) : 75 kg/cm²


Loading dwell time : 6.0 sec.

Cooling time : 2.8 sec.

Releasing temp. : 60 to 70°C (preform surface
temperature)

This Sheet Has Been Replaced





Stretch-blow molding conditions

Mold temperature (set value) : 20°C

Stretch-blowing temperature : 88°C (preform surface
temperature)

Blowing pressure (stretching) : 20 kg/cm²

Blowing time : 2.0 sec.

Percent of stretch:

Longitudinal (axial direction) 190 %

Lateral (radial direction) 360 x 200 %

As described above, according to the present invention, the injection molding of an uncrystallized PET and that of a crystallized PET with the preliminary drying omitted can be performed by the employment of the vent type injection unit, thereby allowing a molded article having little hydrolysis to be obtained. A molded article developing little acetaldehyde due to overheating is obtained so that the uncrystallized PET having a lower commercial price can be utilized as a molding material, whereby the material cost is reduced and the running cost required for the preliminary drying can be saved even for the crystallized PET, thereby allowing the price of a packaging container using the PET as a material to be reduced. The present invention has a further advantage in that the injection molding itself requires no complex operation and can be

This Sheet Has Been Replaced



- 17 -

REPLACEMENT SHEET

22 NOV 1996

performed by employing conventional molding technologies as they are, thereby having a significantly high utility value in industrial field.

This Sheet Has Been Replaced





- 18 -

REPLACEMENT SHEET

22 NOV 1996

WHAT IS CLAIMED IS:

1. A method for injection molding polyethylene terephthalate as a material resin which is undried, characterized in that a vent type injection unit is employed in which an injection screw comprising a first stage and a second stage is rotatably and movably mounted in a heating cylinder having a vent, and the feed rate of the material resin to a feed zone of the first stage of the vent type injection unit is limited in such a manner that the material resin is not accumulated due to compression even if the material resin is softened before reaching a compression zone in front of the feed zone; and that this limitation is effected by making a sectional area of the screw groove in a receiving zone at the feed zone rear end at which a hopper port of the first stage is located smaller than a sectional area of the screw groove in the feed zone, in which condition an uncrystallized polyethylene terephthalate with the preliminary drying omitted is loaded in the hopper as the material resin to plasticate and inject.

2. A method for injection molding polyethylene terephthalate as set forth in claim 1, wherein the sectional area of the screw groove in the above-mentioned receiving zone is set to no larger than $3/4$ the sectional area of the screw groove in feed zone, and the screw is formed in a

This Sheet Has Been Replaced





- 19 -

REPLACEMENT SHEET

22 NOV 1996

double screw to the halfway position of the compression zone, and then in a single screw from the compression zone to the metering zone so as to set the screw pitch to a large value, thereby making sufficient the stretching of a molten resin to improve the vent effect in the vent of the second zone.

3. A method for injection molding polyethylene terephthalate as set forth in claim 1, wherein the removal of the moisture content in the resin from the heating cylinder is performed by being sucked under a reduced pressure by means of a vacuum pump, which removal is not interrupted even when injecting during operation, and when injecting, the reduced pressure is set to a lower value when plasticating, thereby preventing a vent up due to the forward movement of the injection screw.

4. A method for injection molding polyethylene terephthalate as set forth in claim 1, wherein the heating temperature on the second stage side of the heating cylinder is set to a value lower than the heating temperature on the first stage side, thereby preventing the molten PET from being overheated.

5. A method for injection molding polyethylene terephthalate as set forth in claim 1, wherein the molding

This Sheet Has Been Replaced





- 20 -


REPLACEMENT SHEET

22 NOV 1996

material is a crystallized polyethylene terephthalate produced with preliminary drying omitted.

6. A method for injection molding polyethylene terephthalate as set forth in claim 1, wherein a molded article is a preform of a thin-wall packaging container molded by stretch-blow molding.

This Sheet Has Been Replaced



22 NOV 1996

- 21 -


METHOD FOR INJECTION MOLDING POLYETHYLENE TEREPHTHALATE

ABSTRACT

A method for injection molding polyethylene terephthalate by employing a vent type injection unit as means for omitting preliminary drying the resin, wherein the unit does not develop a poor screw biting, and even when a molding material is an undried uncrystallized or crystallized PET, can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container with a low cost.

FIGURE 2.

This Sheet Has Been Replaced



REPLACEMENT SHEET

22 NOV 1996

- 1 -

FIG-1





FIG-2



This Sheet Has Been Replaced



REPLACED SHEETS SG

☒ Description : paged 1 to paged 11
☒ Claim(s) : paged 11 to paged 13
☒ Drawing(s) : paged 1 to paged 14
☒ Abstract : paged 14 to paged 14

- 1 -

REPLACEMENT SHEETS SG

☒ Description : paged 1 to paged 11
☒ Claim(s) : paged 11 to paged 13
☒ Drawing(s) : paged 1 to paged 14
☒ Abstract : paged 14 to paged 14

DATE OF RECEIPT 05 JUL 1997

**METHOD FOR INJECTION MOLDING
POLYETHYLENE TEREPHTHALATE****REPLACEMENT SHEET**

05 JUL 1997

BACKGROUND OF THE INVENTION**1. Field of the Invention**

The present invention relates to a method for injection molding an uncrystallized or crystallized polyethylene terephthalate into a desired molded form such as preform, with pre-drying omitted.

2. Background Art

A pellet of the polyethylene terephthalate (PET) produced by bulk polymerizing of ethylene glycol with terephthalic acid or dimethyl terephthalate is an uncrystallized and transparent material. The PET whose moisture content does not reach an equilibrium has further moisture-absorption characteristics and thus when the PET is molten in a moisture absorbed condition, a hydrolysis develops to prevent the PET from being molded.

An uncrystallized PET pellet, when heated to a temperature above its glass transition point (T_g), becomes softened somewhat to have an adhesive characteristics. The adhesive characteristics causes the PET pellets to be poorly bitten into by a screw and thus not to be fed when molding. On the other hand, a crystallized PET pellet, even at a temperature above its T_g , is not softened, thereby keeping its hardness and having no adhesive characteristics.

Thus, material manufacturers dry an uncrystallized PET pellet at a temperature of 150° to 160° C. to produce a dehumidified and crystallized PET pellet which is sold as a commercially available molding material. This causes the ordinary and commercially available PET to become more expensive than an uncrystallized PET. The uncrystallized PET, which has been sold by some of material manufacturers, has to be dried to effect dehumidification and crystal-

This Sheet Has Been Replaced



05 JUL 1997

- 2 -

lization by molding manufacturers before use. Therefore, the crystallized PET described herein means a dried commercially available product, while the uncrystallized PET means an undried product. In molding a product using the PET as a material, even the crystallized PET has moisture-absorption characteristics and thus absorbs moisture to some extent varying with control conditions before it is used as a molding material; thus it is customary to dry preliminarily the PET immediately before molding.

It takes about four hours to accomplish the preliminary drying at a temperature of 150° C. Both the increased usage of material per hour to improve molding cycle efficiency, and the prevention of a shortage of fed material during a long time operation causes a dryer installed to an injection molding machine to become inevitably large in size and the power consumption required for drying to tend to increase. Problems exist in that it takes a lot of time to make preparations before the molding operation, and that a malfunctioned dryer affects seriously the molding operation.

Injection molding means omitting the preliminary drying can be devised. As such molding means, there has been known a vent type molding machine in which an injection screw in a heating cylinder is divided into a first stage and a second stage, and the moisture content in a molten resin in the first stage is removed to the outside through a vent opening provided between both the stages.

In this well-known vent type molding machine, the screw groove of a feeding zone of the first stage leading from the rear end at which a hopper is located to a metering zone at the front end is formed in a deep groove; pellets of the material resin fed from the hopper in a humid condition are molten due to shearing heat and compression while being sequentially fed by screw rotation; and then the groove leads through the metering zone having a shallow groove to the second stage.

This Sheet Has Been Replaced



05 JUL 1997

- 3 -

The screw groove in the second stage is formed in a deep groove, so that when the molten resin is transferred to the groove, the pressure of the molten resin is reduced due to the rapid increase in the groove depth of the screw to cause the moisture content in the resin to be vaporized, and the moisture content in the resin by screw rotation to be separated, which moisture content is then sucked and removed through the vent opening by a vacuum pump. The molten resin whose moisture content has been removed in this manner is fed by screw rotation to a metering zone at the front end of the second stage, and then to a position in front of the screw to a store, in a similar manner to an injection molding machine having an ordinary mechanism. The molten resin thus stored is injected and loaded into a cavity by the forward movement of the injection screw after stoppage of screw rotation.

Although generally the employment of such vent type injection unit may allow even a material having a large amount of moisture absorption to be molded without the preliminary drying, such unit is not applied to all resins, and with respect to the PET, particularly an uncrystallized one, the pellet is softened and compressed in a feed zone to cause it to be accumulated, whereby the PET in the hopper cannot enter the zone, and the biting by the screw becomes extremely poor such that the material cannot be fed. As a result, it has been quite difficult to perform injection molding without the necessity of the preliminary drying by employing a conventional vent type injection unit.

SUMMARY OF THE INVENTION

The present invention is devised to solve problems with the above-mentioned conventional PET injection molding, and it is an object of the invention to provide a method for injection molding the PET by which although a vent type injection unit is employed as means for omitting preliminary drying, the unit does not develop a poor screw biting, and even when a molding material is an uncrystallized or crystallized PET, it can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container with a low cost.



05 JUL 1997

- 4 -

The present invention according to the above-mentioned purpose employs a vent type injection unit in which an injection screw comprising a first stage and a second stage is rotatably and movably mounted in a heating cylinder having a vent, and limits the feed rate of the material resin to a feed zone of the first stage of the vent type injection unit in such a manner that the material resin does not accumulate due to compression even if the material resin is softened to an elastomeric state before reaching a compression zone in front of the feed zone. This limitation is effected by making the sectional area of the screw groove in a receiving zone at the feed zone rear end at which the hopper port of the first stage is located smaller than the sectional area of the screw groove in the feed zone, in which condition an uncrystallized or crystallized polyethylene terephthalate produced with the preliminary drying omitted is loaded in the hopper as a material resin to be plasticated and injected.

Although it is preferable that the sectional area of the screw groove in the above-mentioned receiving zone 11 is set to no larger than $\frac{3}{4}$ the sectional area of the screw groove in feed zone, a smaller sectional area thus set causes the feed rate to become lower and the material metering time to become longer than is required, so that it is most preferable that the former accounts for $\frac{2}{3}$ to $\frac{1}{2}$ the latter. In order to feed the PET faster, the screw is formed in a double screw to the halfway position of the compression zone, and then in a single screw from the compression zone to the metering zone so as to set the screw pitch to a large value, thereby making the stretching of the molten resin sufficient to improve the vent effect in a vent opening of the second zone.

In addition, the molding is performed in such a manner that the heating temperature on the second stage side of the heating cylinder is set to a value lower than the heating temperature on the first stage side, thereby preventing acetaldehyde occurrence due to an overheated molten resin.



05 JUL 1997

- 5 -

The removal of the moisture content in the resin from the above-mentioned heating cylinder is performed by being sucked under a reduced pressure by means of a vacuum pump, which removal is not interrupted even when injecting during operation, and when injecting, the reduced pressure is set to a value lower than that when plasticating, thereby preventing a vent up due to the forward movement of the injection screw. An injection molded preform is immediately or later transferred to a blowing mold, where it can be stretch-blow molded into a packaging container such as a thin-wall bottle.

BRIEF DESCRIPTION OF THE DRAWINGS

Drawings show an example of a vent type injection unit capable of performing the injection molding method of the present invention, in which:

FIG. 1 is a schematic longitudinal sectional and side view of the vent type injection unit according to the present invention, and

FIG. 2 is an enlarged side view of a screw provided in the vent type injection unit of FIG. 1, in which a front end thereof is omitted.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In the Figures, the numeral 1 indicates an injection screw which is rotatably and movably inserted into a heating cylinder 2. The injection screw 1 has a shape such that two screws having a deep groove section and a shallow groove section are connected to each other to form a single screw, and has a screw design such that a screw portion 10 located in the rear portion of the heating cylinder 2 comprises a first stage (10), while a screw 20 located in the front portion thereof comprises a second stage (20).



05 JUL 1997

- 6 -

The above-mentioned heating cylinder 2 includes a vent opening 3 on the wall portion on which the rear portion of the second stage 20 is located, which opening is enclosed and connected with a vacuum pump (whose view is omitted). On the rear wall portion on which the rear portion of the first stage 10 is located, there is bored a feed port 4, which is mounted with a hopper 5 for PET pellets (hereinafter simply called a resin). On the outer periphery of the heating cylinder 2 and a nozzle 6, there are provided band heaters, though omitted in Figs., for heating the resin fed by screw rotation from the above-mentioned feed port 4.

Both the above-mentioned vent opening 3 and the feed port 4 have an opening width with substantially the same size as the pitch of the screw they face.

FIG. 2 shows a screw design of the above-mentioned injection screw 1, in which the ratio of the first stage 10 to the second stage 20 in the overall length L is about 6:4, thus the second stage 20 is formed shorter than the first stage 10. The first stage 10 is divided into four zones which are, from the rear, a receiving zone 11, a feed zone 12, a compression zone 13 and a metering zone 14, while the second stage 20 is divided into three zones from the rear which are a feed zone 21, a compression zone 22 and a metering zone 23.

In the first stage 10 and the second stage 20, the screw is formed in a double screw up to the halfway position of the compression zones 13 and 22 except for the metering zones 14 and 23, whereby the feed of the material resin to the compression zones 13 and 22 by screw rotation is performed as fast as possible; while the screw in the metering zones 14 and 23 is formed in a single screw to widen the screw pitch in order to reduce as small as possible a non-uniformity of the molten resin.

In the first stage 10, the screw pitch P_1 of the receiving zone 11 is set to a value smaller than the screw pitch P_2 of the feed zone 12, while the screw pitch P_3 of the metering zone 14 is set to a value twice the above-mentioned screw pitch P_2 . The screw pitch of the feed zone 21 and the metering zone 23 of the second stage 20 is set in a similar manner to the screw pitch of the first stage 10.

This Sheet Has Been Replaced



05 JUL 1997

- 7 -


The screw groove depth in the feed zone 21 of the second stage 20 is set to a deepest depth in order to vaporize the moisture content in the molten resin by a rapid pressure reduction; while the screw groove depth in the metering zone 23 is set to a value deeper than in the metering zone 14 of the first zone 10, thereby making easy the feed of the molten resin by screw rotation.

To injection mold a molded article such as a preform using an uncrystallized PET by employing the vent type injection unit having the above-mentioned arrangement, first the temperature of the heating cylinder 2 containing the second stage 20 is set to 270° C., and the temperature of the heating cylinder 2 containing the first stage 10 holds is set to 280° C. The undried and uncrystallized PET as a molded material is loaded in the above-mentioned hopper 5, and then the injection screw 1 is caused to rotate at a high speed (100 rpm). The pressure of the opening 3 is reduced to about -730 mm Hg by the vacuum pump.

The PET in the hopper 5 is fed by screw rotation into the receiving zone 11. The feed rate of the PET from the receiving zone 11 to the feed zone 12 is limited as a result of the sectional areas of the zones, so that the PET in the feed zone 12 does not excessively accumulate, and thus even if the PET is softened to an elastomeric state, pellets are not massed with each other due to compression and not accumulate before the resin reaches the compression zone 13.

The PET softened in the feed zone 12 is compressed by the tapered surface of the compression zone 13 to cause it to be molten, stretched and temporarily plasticated, so that the PET is fed into the second stage 20 whose temperature is set to a value lower than the first stage 10. The screw groove of the feed zone 21 is formed in a deep groove, so that the pressure of the molten resin is reduced to cause the moisture content in the PET to vaporize, and the moisture content in the molten PET to be separated therefrom, which moisture content is then sucked and removed through the vent opening 3 by the vacuum pump. The molten PET whose moisture content has been removed in this manner is fed by screw

This Sheet Has Been Replaced



rotation to the metering zone ²³ of the second stage 20 and further plasticated, and then fed to a position in front of the screw to a store, in a similar manner to an injection molding machine having an ordinary mechanism. As the molten PET is fed, the injection screw 1 is moved backwardly and stopped at a desired position to meter an amount required for injection. After metering, the molten resin is injected and loaded into a mold by forwardly moving the injection screw 1. Then the pressure of the vent opening 3 is changed to about -650 mm Hg and maintained by the vacuum pump during the injection operation. The atmospheric pressure can be easily controlled by taking the outer air into a suction line through valve operation.

The preform thus injection molded was transparent similar to the case where a preliminary drying is performed before injection molding, and has no cloudiness due to hydrolysis, and also has an acetaldehyde content within an allowable range.

An example of the specifications of the vent type injection unit of the present invention will be shown hereinafter:

Injection screw (double screw)

Screw length (L)	1670 mm
Screw outside diameter (D)	64 mm
L/D of Screw	26

	(Length)	(Screw minor dia.)	Screw pitch
--	----------	--------------------	-------------

First stage

Screw	998 mm		
Receiving zone	128 mm	52.0 mm	32.0 mm
Feed zone	646 mm	45.0 mm	38.5 mm
Compression zone	64 mm		
Metering zone	160 mm	57.2 mm	77.0 mm

Second stage

Screw	672 mm		
Feed zone	448 mm	43.2 mm	38.5 mm
Compression zone	64 mm		
Metering zone	160 mm	56.0 mm	77.0 mm

Screw revolution speed	100 rpm
Injection stroke	120 mm

REPLACEMENT SHEET

05 JUL 1997

This Sheet Has Been Replaced



When the PET is crystallized it is softened in the feed zone 12 more slowly and transferred to the compression zone 13 faster than the uncrystallized PET, thereby tending to develop an uneven melting. However, this problem can be solved by setting the compression zone 13 to a length somewhat longer than the above-mentioned numerical value.

The employment of the above-mentioned vent type injection unit allows the injection molded preform to be molded into a thin-wall packaging container such as a bottle by the well-known stretch-blow molding. The well-known stretch-blow molding is broadly classified into a so-called two stage type in which the injection molding of the preform and the stretch-blow molding of the preform into a container are performed in separate processes, and a so-called one stage type in which the injection molding of the preform through the stretch-blow molding of the preform into a container are continuously performed. In either of both the methods, the PET preform produced by the injection molding with the preliminary drying omitted can be molded into a thin-wall container in the same manner as with the PET preform injection molded after being dried.


The following shows molding conditions in a case where with an injection molded preform held at its neck to a limit in which its shape can be kept, the preform is released from a cavity and a core, transferred to a blowing mold when the surface temperature of the preform is being raised due to an internal potential heat, and immediately stretch-blow molded to mold a thin-wall container.

Material resin: UNIPET RY523 (manufactured by Unipet Co., Ltd.)


Molded form: flat bottle

Dimensions:

overall height 250 mm
port inside dia. 23.5 mm
length under neck 230 mm
body outside dia. 90×50 mm
body wall thickness 0.4 mm
weight 36 g



This Sheet Has Been Replaced




Preform

- 10 -

Dimensions:

Overall height 142 mm
port inside dia. 23.5 mm
length under neck 122 mm
body wall thickness 2.9 mm
body upper portion outside dia 28 mm
body lower end outside dia. 24 mm
draft 2/122



Preform molding conditions

Injection cylinder temperature

First stage: Front 285° C., middle 285° C., rear 280° C.

Second stage: Front 270° C., rear 270° C.

Nozzle temperature: 270° C.

Injection mold temperature (set value)

Cavity mold: 15° C.

Core mold: 15° C.


Injection pressure (dwell): 75 kg/cm²

Loading dwell time: 6.0 sec.

Cooling time: 2.8 sec.

Releasing temp.: 60° to 70° C. (preform surface temperature)

This Sheet Has Been Replaced



Stretch-blow molding conditions

Mold temperature (set value): 20° C.

Stretch-blowing temperature: 88° C. (preform surface temperature)

Blowing pressure (stretching): 20 kg/cm²

Blowing time: 2.0 sec.

Percent of stretch:

Longitudinal (axial direction): 190%

Lateral (radial direction): 360×200%

As described above, according to the present invention, the injection molding of an uncrystallized PET and that of a crystallized PET with the preliminary drying omitted can be performed by the employment of the vent type injection unit, thereby allowing a molded article having little hydrolysis to be obtained. A molded article having developing little acetaldehyde due to overheating is obtained so that uncrystallized PET having a lower commercial price can be utilized

as a molding material, whereby the material cost is reduced and the running cost required for the preliminary drying can be saved even using the crystallized PET, thereby allowing the price of a packaging container made from the PET as a material to be reduced. The present invention has a further advantage in that the injection molding itself requires no complex operation and can be performed by employing conventional molding technologies, thereby having a significantly high utility value in this industrial field.

What is claimed is:


1. A method of injection molding an undried polyethylene terephthalate employing a vent-type injection unit comprising a heating cylinder having an inside wall, a vent, a hopper and an injection screw rotatably and movably mounted in the cylinder, the length of said injection screw being divided into sequential first and second stages, each of said first and second stages being divided in sequence into a feed zone, a compression zone and a metering zone, said first stage also having a receiving zone connected to said feed zone of said first stage and receiving said undried polyethylene terephthalate from the hopper, said vent being located at a position corresponding to the feed zone of the second stage, said method comprising

providing said undried polyethylene terephthalate in said hopper,

causing said screw to rotate to thereby convey any polyethylene terephthalate present in the area between said injection screw and the inside wall of the heating cylinder,

receiving said polyethylene terephthalate in the receiving zone of the first stage from the hopper,

feeding and plasticizing said polyethylene terephthalate, wherein the feeding rate of the polyethylene terephthalate is limited by an arrangement such that the depth of the screw groove in the receiving zone is shallower than the depth of the screw groove in the feed zone, thus making an area available between two adjacent screw flights for molding the polyethylene terephthalate smaller in the receiving zone than in the feed zone of said first stage. and





- 11 -

as a molding material, whereby the material cost is reduced and the running cost required for the preliminary drying can be saved even using the crystallized PET, thereby allowing the price of a packaging container made from the PET as a material to be reduced. The present invention has a further advantage in that the injection molding itself requires no complex operation and can be performed by employing conventional molding technologies, thereby having a significantly high utility value in this industrial field.

What is claimed is:

1. A method of injection molding an undried polyethylene terephthalate employing a vent-type injection unit comprising a heating cylinder having an inside wall, a vent, a hopper and an injection screw rotatably and movably mounted in the cylinder, the length of said injection screw being divided into sequential first and second stages, each of said first and second stages being divided in sequence into a feed zone, a compression zone and a metering zone, said first stage also having a receiving zone connected to said feed zone of said first stage and receiving said undried polyethylene terephthalate from the hopper, said vent being located at a position corresponding to the feed zone of the second stage, said method comprising

providing said undried polyethylene terephthalate in said hopper,

causing said screw to rotate to thereby convey any polyethylene terephthalate present in the area between said injection screw and the inside wall of the heating cylinder,

receiving said polyethylene terephthalate in the receiving zone of the first stage from the hopper,

feeding and plasticizing said polyethylene terephthalate, wherein the feeding rate of the polyethylene terephthalate is limited by an arrangement such that the depth of the screw groove in the receiving zone is shallower than the depth of the screw groove in the feed zone, thus making an area available between two adjacent screw flights for molding the polyethylene terephthalate smaller in the receiving zone than in the feed zone of said first stage, and

REPLACEMENT SHEET

05 JUL 1997

This Sheet Has Been Replaced





* C L M S *

- 12 -

REPLACEMENT SHEET

05 JUL 1997

removing volatile substances from the polyethylene terephthalate through the vent.

2. A method of injection molding an undried polyethylene terephthalate according to claim 1, wherein said area available for said polyethylene terephthalate in said receiving zone is not more than $\frac{3}{4}$ of said area available for said polyethylene terephthalate in said feed zone of the first stage, and wherein the injection screw in said receiving zone of the first stage, in each of said feeding zones of said first and second stages and in the first half of each of said compression zones of said first and second stages is formed in a double screw, and the injection screw in an area from said first half of each of said compression zones of said first and second stages to each of said metering zones of said first and second stages is formed in a single screw so as to effectively mix and stretch the plasticized polyethylene terephthalate.

3. A method of injection molding an undried polyethylene terephthalate to claim 1, wherein a reduced pressure is established at said vent whereby moisture contained in said undried polyethylene terephthalate is removed from said vent-type injection unit and extent of the reduced pressure is varied during the injection molding to a lower value.


4. A method for injection molding an undried polyethylene terephthalate as set forth in claim 3, wherein the heating cylinder is heated such that the temperature in the first stage is greater than the temperature in the second stage.

5. A method for injection molding an undried polyethylene terephthalate as set forth in claim 4, wherein the an undried polyethylene terephthalate is undried, crystallized polyethylene terephthalate.

6. A method for injection molding an undried polyethylene terephthalate as set forth in claim 4, wherein the undried polyethylene terephthalate is uncrystallized polyethylene terephthalate.


7. A method for injection molding an undried polyethylene terephthalate as set forth in claim 1, wherein a preform of a thin-wall packaging container to be molded by stretch-blow molding is injection molded.

This Sheet Has Been Replaced





- 13 -



8. A method of injection molding an undried polyethylene terephthalate to claim 1, wherein a reduced pressure is established at said vent whereby moisture contained in said undried polyethylene terephthalate is removed from said vent-type injection unit and extent of the reduced pressure is varied during the injection molding to a lower value.

9. A method for injection molding an undried polyethylene terephthalate as set forth in claim 1, wherein the heating cylinder is heated such that the temperature in the first stage is greater than the temperature in the second stage.

10. A method for invention molding an undried polyethylene terephthalate as set forth in claim 1, wherein the undried polyethylene terephthalate is undried, crystallized polyethylene terephthalate.

11. A method for injection molding an undried polyethylene terephthalate as set forth in claim 1, wherein the undried polyethylene terephthalate is uncrystallized polyethylene terephthalate.

This Sheet Has Been Replaced



REPLACEMENT SHEET

05 JUL 1997

- 14 -


METHOD FOR INJECTION MOLDING POLYETHYLENE
TEREPHTHALATE

ABSTRACT

A method for injection molding polyethylene terephthalate by employing a vent type injection unit as means for omitting preliminary drying the resin, wherein the unit does not develop a poor screw biting, and even when the molding material is undried uncrystallized or crystallized PET, can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container at a low cost.


FIGURE 1.

This Sheet Has Been Replaced




05 JUL 1997

FIG-1




F I G - 2



This Sheet Has Been Replaced





- 1 -

REPLACEMENT SHEETS		SG
☒ Description	: paged 1 to paged 11	
☒ Claim(s)	: paged 12 to paged 14	
☒ Drawing(s)	: paged 1 to paged 2	
☒ Abstract	: paged 15 to paged 2	
DATE OF RECEIPT		14 JUL 1998

METHOD FOR INJECTION MOLDING POLYETHYLENE TEREPHTHALATE

BACKGROUND OF THE INVENTION

1. Field of the Invention


The present invention relates to a method for injection molding an uncrystallized or crystallized polyethylene terephthalate into a desired molded form such as preform, with pre-drying omitted.

2. Background Art

A pellet of the polyethylene terephthalate (PET) produced by bulk polymerizing of ethylene glycol with terephthalic acid or dimethyl terephthalate is an uncrystallized and transparent material. The PET whose moisture content does not reach an equilibrium has further moisture-absorption characteristics and thus when the PET is molten in a moisture absorbed condition, a hydrolysis develops to prevent the PET from being molded.

An uncrystallized PET pellet, when heated to a temperature above its glass transition point (T_g), becomes softened somewhat to have an adhesive characteristics. The adhesive characteristics causes the PET pellets to be poorly bitten into by a screw and thus not to be fed when molding. On the other hand, a crystallized PET pellet, even at a temperature above its T_g , is not softened, thereby keeping its hardness and having no adhesive characteristics.

Thus, material manufacturers dry an uncrystallized PET pellet at a temperature of 150° to 160° C. to produce a dehumidified and crystallized PET pellet which is sold as a commercially available molding material. This causes the ordinary and commercially available PET to become more expensive than an uncrystallized PET. The uncrystallized PET, which has been sold by some of material manufacturers, has to be dried to effect dehumidification and crystal-



- 2 -

lization by molding manufacturers before use. Therefore, the crystallized PET described herein means a dried commercially available product, while the uncrystallized PET means an undried product. In molding a product using the PET as a material, even the crystallized PET has moisture-absorption characteristics and thus absorbs moisture to some extent varying with control conditions before it is used as a molding material; thus it is customary to dry preliminarily the PET immediately before molding.

It takes about four hours to accomplish the preliminary drying at a temperature of 150° C. Both the increased usage of material per hour to improve molding cycle efficiency, and the prevention of a shortage of fed material during a long time operation causes a dryer installed to an injection molding machine to become inevitably large in size and the power consumption required for drying to tend to increase. Problems exist in that it takes a lot of time to make preparations before the molding operation, and that a malfunctioned dryer affects seriously the molding operation.

Injection molding means omitting the preliminary drying can be devised. As such molding means, there has been known a vent type molding machine in which an injection screw in a heating cylinder is divided into a first stage and a second stage, and the moisture content in a molten resin in the first stage is removed to the outside through a vent opening provided between both the stages.

In this well-known vent type molding machine, the screw groove of a feeding zone of the first stage leading from the rear end at which a hopper is located to a metering zone at the front end is formed in a deep groove; pellets of the material resin fed from the hopper in a humid condition are molten due to shearing heat and compression while being sequentially fed by screw rotation; and then the groove leads through the metering zone having a shallow groove to the second stage.

14 JUL 1998

- 3 -

The screw groove in the second stage is formed in a deep groove, so that when the molten resin is transferred to the groove, the pressure of the molten resin is reduced due to the rapid increase in the groove depth of the screw to cause the moisture content in the resin to be vaporized, and the moisture content in the resin by screw rotation to be separated, which moisture content is then sucked and removed through the vent opening by a vacuum pump. The molten resin whose moisture content has been removed in this manner is fed by screw rotation to a metering zone at the front end of the second stage, and then to a position in front of the screw to a store, in a similar manner to an injection molding machine having an ordinary mechanism. The molten resin thus stored is injected and loaded into a cavity by the forward movement of the injection screw after stoppage of screw rotation.

Although generally the employment of such vent type injection unit may allow even a material having a large amount of moisture absorption to be molded without the preliminary drying, such unit is not applied to all resins, and with respect to the PET, particularly an uncrystallized one, the pellet is softened and compressed in a feed zone to cause it to be accumulated, whereby the PET in the hopper cannot enter the zone, and the biting by the screw becomes extremely poor such that the material cannot be fed. As a result, it has been quite difficult to perform injection molding without the necessity of the preliminary drying by employing a conventional vent type injection unit.

SUMMARY OF THE INVENTION

The present invention is devised to solve problems with the above-mentioned conventional PET injection molding, and it is an object of the invention to provide a method for injection molding the PET by which although a vent type injection unit is employed as means for omitting preliminary drying, the unit does not develop a poor screw biting, and even when a molding material is an uncrystallized or crystallized PET, it can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container with a low cost.

14 JUL 1998

- 4 -

The present invention according to the above-mentioned purpose employs a vent type injection unit in which an injection screw comprising a first stage and a second stage is rotatably and movably mounted in a heating cylinder having a vent, and limits the feed rate of the material resin to a feed zone of the first stage of the vent type injection unit in such a manner that the material resin does not accumulate due to compression even if the material resin is softened to an elastomeric state before reaching a compression zone in front of the feed zone. This limitation is effected by making the sectional area of the screw groove in a receiving zone at the feed zone rear end at which the hopper port of the first stage is located smaller than the sectional area of the screw groove in the feed zone, in which condition an uncrystallized or crystallized polyethylene terephthalate produced with the preliminary drying omitted is loaded in the hopper as a material resin to be plasticated and injected.

Although it is preferable that the sectional area of the screw groove in the above-mentioned receiving zone 11 is set to no larger than $\frac{3}{4}$ the sectional area of the screw groove in feed zone, a smaller sectional area thus set causes the feed rate to become lower and the material metering time to become longer than is required, so that it is most preferable that the former accounts for $\frac{2}{3}$ to $\frac{1}{2}$ the latter. In order to feed the PET faster, the screw is formed in a double screw to the halfway position of the compression zone, and then in a single screw from the compression zone to the metering zone so as to set the screw pitch to a large value, thereby making the stretching of the molten resin sufficient to improve the vent effect in a vent opening of the second zone.

In addition, the molding is performed in such a manner that the heating temperature on the second stage side of the heating cylinder is set to a value lower than the heating temperature on the first stage side, thereby preventing acetaldehyde occurrence due to an overheated molten resin.

14 JUL 1998

- 5 -

The removal of the moisture content in the resin from the above-mentioned heating cylinder is performed by being sucked under a reduced pressure by means of a vacuum pump, which removal is not interrupted even when injecting during operation, and when injecting, the reduced pressure is set to a value lower than that when plasticating, thereby preventing a vent up due to the forward movement of the injection screw. An injection molded preform is immediately or later transferred to a blowing mold, where it can be stretch-blow molded into a packaging container such as a thin-wall bottle.

BRIEF DESCRIPTION OF THE DRAWINGS

Drawings show an example of a vent type injection unit capable of performing the injection molding method of the present invention, in which:

FIG. 1 is a schematic longitudinal sectional and side view of the vent type injection unit according to the present invention, and

FIG. 2 is an enlarged side view of a screw provided in the vent type injection unit of FIG. 1, in which a front end thereof is omitted.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In the Figures, the numeral 1 indicates an injection screw which is rotatably and movably inserted into a heating cylinder 2. The injection screw 1 has a shape such that two screws having a deep groove section and a shallow groove section are connected to each other to form a single screw, and has a screw design such that a screw portion 10 located in the rear portion of the heating cylinder 2 comprises a first stage (10), while a screw 20 located in the front portion thereof comprises a second stage (20).

14 JUL 1998

- 6 -

The above-mentioned heating cylinder 2 includes a vent opening 3 on the wall portion on which the rear portion of the second stage 20 is located, which opening is enclosed and connected with a vacuum pump (whose view is omitted). On the rear wall portion on which the rear portion of the first stage 10 is located, there is bored a feed port 4, which is mounted with a hopper 5 for PET pellets (hereinafter simply called a resin). On the outer periphery of the heating cylinder 2 and a nozzle 6, there are provided band heaters, though omitted in Figs., for heating the resin fed by screw rotation from the above-mentioned feed port 4.

Both the above-mentioned vent opening 3 and the feed port 4 have an opening width with substantially the same size as the pitch of the screw they face.

FIG. 2 shows a screw design of the above-mentioned injection screw 1, in which the ratio of the first stage 10 to the second stage 20 in the overall length L is about 6:4, thus the second stage 20 is formed shorter than the first stage 10. The first stage 10 is divided into four zones which are, from the rear, a receiving zone 11, a feed zone 12, a compression zone 13 and a metering zone 14, while the second stage 20 is divided into three zones from the rear which are a feed zone 21, a compression zone 22 and a metering zone 23.

In the first stage 10 and the second stage 20, the screw is formed in a double screw up to the halfway position of the compression zones 13 and 22 except for the metering zones 14 and 23, whereby the feed of the material resin to the compression zones 13 and 22 by screw rotation is performed as fast as possible; while the screw in the metering zones 14 and 23 is formed in a single screw to widen the screw pitch in order to reduce as small as possible a non-uniformity of the molten resin.

In the first stage 10, the screw pitch P_1 of the receiving zone 11 is set to a value smaller than the screw pitch P_2 of the feed zone 12, while the screw pitch P_3 of the metering zone 14 is set to a value twice the above-mentioned screw pitch P_2 . The screw pitch of the feed zone 21 and the metering zone 23 of the second stage 20 is set in a similar manner to the screw pitch of the first stage 10.

14 JUL 1998

- 7 -

The screw groove depth of the first stage 10 is set at the dimension calculated from the screw groove depth of the feed zone 12. In order to limit the feed rate in the feed zone 12, the screw groove depth in the above-mentioned receiving zone 11 is set to a shallow depth such that the sectional area of the screw groove in relation to the above-mentioned screw pitch P_1 becomes $\frac{2}{3}$ the sectional area of the screw groove of the feed zone 12; while the screw groove depth in the metering zone 14 is set to a depth shallower than in the receiving zone 11 in order to stretch the molten resin by screw rotation.

The screw groove depth in the feed zone 21 of the second stage 20 is set to a deepest depth in order to vaporize the moisture content in the molten resin by a rapid pressure reduction; while the screw groove depth in the metering zone 23 is set to a value deeper than in the metering zone 14 of the first zone 10, thereby making easy the feed of the molten resin by screw rotation.

To injection mold a molded article such as a preform using an uncrystallized PET by employing the vent type injection unit having the above-mentioned arrangement, first the temperature of the heating cylinder 2 containing the second stage 20 is set to 270° C., and the temperature of the heating cylinder 2 containing the first stage 10 holds is set to 280° C. The undried and uncrystallized PET as a molded material is loaded in the above-mentioned hopper 5, and then the injection screw 1 is caused to rotate at a high speed (100 rpm). The pressure of the opening 3 is reduced to about -730 mm Hg by the vacuum pump.

The PET in the hopper 5 is fed by screw rotation into the receiving zone 11. The feed rate of the PET from the receiving zone 11 to the feed zone 12 is limited as a result of the sectional areas of the zones, so that the PET in the feed zone 12 does not excessively accumulate, and thus even if the PET is softened to an elastomeric state, pellets are not massed with each other due to compression and not accumulate before the resin reaches the compression zone 13.

The PET softened in the feed zone 12 is compressed by the tapered surface of the compression zone 13 to cause it to

14 JUL 1998

be molten, stretched and temporarily plasticated, so that the PET is fed into the second stage 20 whose temperature is set to a value lower than the first stage 10. The screw groove of the feed zone 21 is formed in a deep groove, so that the pressure of the molten resin is reduced to cause the moisture content in the PET to vaporize, and the moisture content in the molten PET to be separated therefrom, which moisture content is then sucked and removed through the vent opening 3 by the vacuum pump. The molten PET whose moisture content has been removed in this manner is fed by screw rotation to the metering zone 23 of the second stage 20 and further plasticated, and then fed to a position in front of the screw to a store, in a similar manner to an injection molding machine having an ordinary mechanism. As the molten PET is fed, the injection screw 1 is moved backwardly and stopped at a desired position to meter an amount required for injection. After metering, the molten resin is injected and loaded into a mold by forwardly moving the injection screw 1. Then the pressure of the vent opening 3 is changed to about -650 mm Hg and maintained by the vacuum pump during the injection operation. The atmospheric pressure can be easily controlled by taking the outer air into a suction line through valve operation.

The preform thus injection molded was transparent similar to the case where a preliminary drying is performed before injection molding, and has no cloudiness due to hydrolysis, and also has an acetaldehyde content within an allowable range.

14 JUL 1998

- 9 -

An example of the specifications of the vent type injection unit of the present invention will be shown hereinafter:

Injection screw (double screw)

Screw length (L)	1670 mm
Screw outside diameter (D)	64 mm
L/D of Screw	26

	(Length)	(Screw minor dia.)	Screw pitch
<u>First stage</u>			
Screw	998 mm		
Receiving zone	128 mm	52.0 mm	32.0 mm
Feed zone	646 mm	45.0 mm	38.5 mm
Compression zone	64 mm		
Metering zone	160 mm	57.2 mm	77.0 mm
<u>Second stage</u>			
Screw	672 mm		
Feed zone	448 mm	43.2 mm	38.5 mm
Compression zone	64 mm		
Metering zone	160 mm	56.0 mm	77.0 mm
Screw revolution speed	100 rpm		
Injection stroke	120 mm		

When the PET is crystallized it is softened in the feed zone 12 more slowly and transferred to the compression zone 13 faster than the uncrystallized PET, thereby tending to develop an uneven melting. However, this problem can be solved by setting the compression zone 13 to a length somewhat longer than the above-mentioned numerical value.

The employment of the above-mentioned vent type injection unit allows the injection molded preform to be molded into a thin-wall packaging container such as a bottle by the well-known stretch-blow molding. The well-known stretch-blow molding is broadly classified into a so-called two stage type in which the injection molding of the preform and the stretch-blow molding of the preform into a container are performed in separate processes, and a so-called one stage

14 JUL 1998

- 10 -

type in which the injection molding of the preform through the stretch-blow molding of the preform into a container are continuously performed. In either of both the methods, the PET preform produced by the injection molding with the preliminary drying omitted can be molded into a thin-wall container in the same manner as with the PET preform injection molded after being dried.

The following shows molding conditions in a case where with an injection molded preform held at its neck to a limit in which its shape can be kept, the preform is released from a cavity and a core, transferred to a blowing mold when the surface temperature of the preform is being raised due to an internal potential heat, and immediately stretch-blow molded to mold a thin-wall container.

Material resin: UNIPET RY523 (manufactured by Unipet Co., Ltd.)

Molded form: flat bottle

Dimensions:

overall height 250 mm
port inside dia. 23.5 mm
length under neck 230 mm
body outside dia. 90×50 mm
body wall thickness 0.4 mm
weight 36 g

Preform

Dimensions:

Overall height 142 mm
port inside dia. 23.5 mm
length under neck 122 mm
body wall thickness 2.9 mm
body upper portion outside dia 28 mm
body lower end outside dia. 24 mm
draft 2/122

Preform molding conditions


Injection cylinder temperature

First stage: Front 285° C., middle 285° C., rear 280° C.

Second stage: Front 270° C., rear 270° C.

Nozzle temperature: 270° C.

Injection mold temperature (set value)



Cavity mold: 15° C.

Core mold: 15° C.

Injection pressure (dwell): 75 kg/cm²

Loading dwell time: 6.0 sec.

Cooling time: 2.8 sec.

Releasing temp.: 60° to 70° C. (preform surface temperature)

Stretch-blow molding conditions

Mold temperature (set value): 20° C.

Stretch-blowing temperature: 88° C. (preform surface temperature)

Blowing pressure (stretching): 20 kg/cm²

Blowing time: 2.0 sec.

Percent of stretch:

Longitudinal (axial direction): 190%

Lateral (radial direction): 360×200%

As described above, according to the present invention, the injection molding of an uncrystallized PET and that of a crystallized PET with the preliminary drying omitted can be performed by the employment of the vent type injection unit, thereby allowing a molded article having little hydrolysis to be obtained. A molded article having developing little acetaldehyde due to overheating is obtained so that uncrystallized PET having a lower commercial price can be utilized as a molding material, whereby the material cost is reduced and the running cost required for the preliminary drying can be saved even using the crystallized PET, thereby allowing the price of a packaging container made from the PET as a material to be reduced. The present invention has a further advantage in that the injection molding itself requires no complex operation and can be performed by employing conventional molding technologies, thereby having a significantly high utility value in this industrial field.



14 JUL 1998

- 12 -

What is claimed is:

1. A method of injection molding an undried polyethylene terephthalate employing a vent-type injection unit comprising a heating cylinder having an inside wall, a vent, a hopper and an injection screw rotatably and movably mounted in the cylinder, the length of said injection screw being divided into sequential first and second stages, each of said first and second stages being divided in sequence into a feed zone, a compression zone and a metering zone, said first stage also having a receiving zone connected to said feed zone of said first stage and receiving said undried polyethylene terephthalate from the hopper, said vent being located at a position corresponding to the feed zone of the second stage, said method comprising

providing said undried polyethylene terephthalate in said hopper,

causing said screw to rotate to thereby convey any polyethylene terephthalate present in the area between said injection screw and the inside wall of the heating cylinder,

receiving said polyethylene terephthalate in the receiving zone of the first stage from the hopper,

feeding and plasticizing said polyethylene terephthalate, wherein the feeding rate of the polyethylene terephthalate is limited by an arrangement such that the depth of the screw groove in the receiving zone is shallower than the depth of the screw groove in the feed zone, thus making an area available between two adjacent screw flights for molding the polyethylene terephthalate smaller in the receiving zone than in the feed zone of said first stage. and

removing volatile substances from the polyethylene terephthalate through the vent.

2. A method of injection molding an undried polyethylene terephthalate according to claim 1, wherein said area available for said polyethylene terephthalate in said receiving zone is not more than $\frac{3}{4}$ of said area available for said polyethylene terephthalate in said feed zone of the first



stage, and wherein the injection screw in said receiving zone of the first stage, in each of said feeding zones of said first and second stages and in the first half of each of said compression zones of said first and second stages is formed in a double screw, and the injection screw in an area from said first half of each of said compression zones of said first and second stages to each of said metering zones of said first and second stages is formed in a single screw so as to effectively mix and stretch the plasticized polyethylene terephthalate.

3. A method of injection molding an undried polyethylene terephthalate to claim 1, wherein a reduced pressure is established at said vent whereby moisture contained in said undried polyethylene terephthalate is removed from said vent-type injection unit and extent of the reduced pressure is varied during the injection molding to a lower value.

4. A method for injection molding an undried polyethylene terephthalate as set forth in claim 3, wherein the heating cylinder is heated such that the temperature in the first stage is greater than the temperature in the second stage.

5. A method for injection molding an undried polyethylene terephthalate as set forth in claim 4, wherein the an undried polyethylene terephthalate is undried, crystallized polyethylene terephthalate.

6. A method for injection molding an undried polyethylene terephthalate as set forth in claim 4, wherein the undried polyethylene terephthalate is uncrystallized polyethylene terephthalate.

7. A method for injection molding an undried polyethylene terephthalate as set forth in claim 1, wherein a preform of a thin-wall packaging container to be molded by stretch-blow molding is injection molded.

8. A method of injection molding an undried polyethylene terephthalate to claim 1, wherein a reduced pressure is established at said vent whereby moisture contained in said undried polyethylene terephthalate is removed from said vent-type injection unit and extent of the reduced pressure is varied during the injection molding to a lower value.

REPLACEMENT SHEET

14 JUL 1998



REPLACEMENT SHEET

14 JUL 1998

- 14 -

9. A method for injection molding an undried polyethylene terephthalate as set forth in claim 1, wherein the heating cylinder is heated such that the temperature in the first stage is greater than the temperature in the second stage.

10. A method for invention molding an undried polyethylene terephthalate as set forth in claim 1, wherein the undried polyethylene terephthalate is undried, crystallized polyethylene terephthalate.

11. A method for injection molding an undried polyethylene terephthalate as set forth in claim 1, wherein the undried polyethylene terephthalate is uncrystallized polyethylene terephthalate.

ABSTRACT

REPLACEMENT SHEET

14 JUL 1998

METHOD FOR INJECTION MOLDING POLYETHYLENE TEREPHTALATE

A method for injection molding polyethylene terephtalate by employing a vent type injection unit as means for omitting preliminary drying the resin, wherein the unit does not develop a poor screw biting, and even when the molding material is an undried uncrystallized or crystallized PET, can feed a certain amount of the material at all times to injection mold a desired transparent molded form such as a preform, and use the preform to produce a thin-wall container at a low cost.

FIGURE 1

14 JUL 1998

- 1 -

FIG-1




FIG-2

