

Multi-Block Copolymers

Field of the invention

- 5 The present invention relates to multi-block copolymers and methods of production thereof.

Background

- 10 Thermoplastic elastomers (TPE), also known as thermoplastic rubbers, are a class of block copolymers which consist of different polymer blocks with both thermoplastic and elastomeric properties. The fundamental difference between thermoset and thermoplastic elastomers is the type of the cross-linking points which contribute to high elastic properties.
- The polystyrene-*b*-polybutadiene-*b*-polystyrene (SBS), which is composed of polymer blocks
- 15 of conjugated diene monomer (butadiene) and vinyl aromatic monomer (styrene), is considered the most successfully commercialized thermoplastic elastomer. However, SBS and its derivatives are non-degradable and the raw materials are currently acquired from fossil oil. In terms of manufacturing, due to the fact that there are carbon double bonds in each repeat unit of the polybutadiene block. SBS and its derivative undergo thermal
- 20 crosslinking reactions at high temperature. This results in increasing viscosity during processing and ultimately jeopardises the high elastic property owing to over-high crosslinking density.


- There has been commercially successful copolyester elastomers, such as Hytrel, a
- 25 trademarked product of DuPont Company in the United States, which has been used to make solid tires and other automotive parts. Conventionally, this kind of copolyester elastomers usually consist of polybutylene terephthalate (PBT, as the hard crystalline domain) and any one of a wide range of polyesters or polyethers as the soft/flexible matrix, such as polytetramethylene ether glycol. However, the preparation of PBT relies on a multi-
- 30 step polycondensation reactions, which are very slow (low polymerization rate) and energy consuming processes. Also, when polyethers are chosen to be the soft/flexible domain, the copolyester elastomers are hardly degradable (e.g. Hytrel).

- The present invention relates to multi-block copolymers with tailorable elastomeric properties
- 35 and degradable backbones, as an alternative to SBS and its derivatives.

Summary of the invention

- In a first aspect, the invention provides a multi-block copolymer comprising at least blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B is comprises copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the multi-block copolymer is characterised by one or more of features (i) to (iii):
- (i) a degree of crystallinity (χ) of block A of no more than 20% as determined by DSC; and/or
 - (ii) a degree of crystallinity (χ) of block A of no more than 20% as determined by WAXS; and/or
 - (iii) a measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B.

- In a second aspect, the invention provides a 'one-pot' method for producing a multi-block copolymer comprising blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B is comprises copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the method comprises forming a reaction mixture comprising:
- i. an epoxide;
 - II. an anhydride or carbon dioxide; and
 - iii. a lactone and/or a lactide; and
 - iv. a catalytic system comprising a catalyst of formula (I) and an initiator;
- such that polymerisation occurs to form a multi-block copolymer comprising blocks A-B-A or B-A-B, wherein the catalyst is of formula (I):



wherein:

- [M] is a metal complex having at least one metal atom M coordinated by a ligand system; M is Zn, Cr, Co, Mn, Mg, Fe, Ti, Ca, Ge, Al, Mo, W, Ru, Ni or V; Z is absent, or is independently selected from -E-, -EX(E)-, or -EX(E)E-, each E is independently selected from O, S or NR^Z , wherein R^Z is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl;

Z is absent, or is independently selected from $-E-$, $-EX(E)-$, or $-EX(E)E-$, each E is independently selected from O, S or NR^Z , wherein R^Z is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl;

5 X is C or S

R is hydrogen, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl, alkylheteroaryl, silyl or a polymer; and when Z is absent, R may additionally be selected from halide, phosphinate, azide and nitrate; and

10 wherein the initiator is a multifunctional protic compound comprising at least two moieties independently selected from $-OH$, $-SH$, $-C(O)OH$ or $-NH-$, or wherein the initiator is water.

In a fourth aspect of the invention, there is provided a polymer obtainable from the method according to the third aspect of the invention.

15

In a fifth aspect of the invention, there is provided a polymer of the first, second or fourth aspects of the invention for use as a packaging material, a biomedical material, a sealant, an adhesive, an engineering material or the like.

20 **Brief Description of the Figures**

Figure 1 illustrates ROCOP and ROP reactions catalysed by complex 1.

25 Figure 2 shows (A) Diagram illustrating the chemoselective sequence controlled polymerization; (B) Reactions corresponding to the steps illustrated in (A).

Figure 3 shows a representative ATR-IR spectrum acquired during (PDL-*b*-PCHPE-*b*-PDL) formation (Table 3, entry 2). PA resonance is at 1790 cm^{-1} , PCHPE resonance is at $1065\text{-}1068\text{ cm}^{-1}$, ϵ -DL resonance is at 1735 cm^{-1} and PDL resonance is at 1190 cm^{-1} .

30

Figure 4 shows a scheme illustrating the reactions proposed to occur during sequence-selective polymerizations. Where $[Zn][Zn]$ is the active site of complex 1 and 'P' is a propagating polymer chain.

35 Figure 5 shows a SEC traces of polymer aliquots before and after propagation of the PDL block (Table 3, # 3) and b) Overlay of the SEC RI and UV outputs (inter-detector delay was corrected using toluene as internal standard).

Figure 6 shows DSC thermograms of (A) PDL-*b*-PCHPE-*b*-PDL (Table 3, #3) and (B) PCHPE/PDL blend (Table 3, #1 and #6).

5 Figure 7 shows stress-strain curves of multi-block copolyesters #1-3 in Table 4.

Figure 8 shows strain recovery repeatability after different maximum strains (400 % and 500 %) upon heating to 45 °C and subsequent cooling to 18 °C.

10 Figure 9 shows uniaxial reversible shape transformations were observed during the cold-draw deformation at 18 °C (from A to B) and subsequent heating (45 °C)/cooling (18 °C) cycle (from B to C).

Figure 10 shows (A) Cyclic tensile stress-strain behaviour of the 42 wt% PCHPE-*b*-PDL multi-block copolyester. The sample bar was relaxed at room temperature (19 °C) freely to reach a constant strain before the second extension was conducted. (B) Cyclic tensile stress-strain behaviour of the SBS containing 48 wt% of polystyrene from literature.

15

Figure 11 shows an ATR-IR spectrum acquired during PDL-*b*-PvCHC-*b*-PCHPE-*b*-PvCHC-*b*-PDL pentablock copolymer formation.

20

Detailed Description

The invention relates to multi-block copolymers which are capable of providing thermoplastic elastomeric properties. The multi-block copolymers may comprise a polyester or polycarbonate, which is preferably rigid and amorphous domain, either dispersing in a soft/flexible polyester matrix or forming a bicontinuous nanostructure with the soft/flexible polyester domain. Accordingly, the multi-block copolymers of the invention may comprise a phase separated nanostructure, resulting in them being thermoplastics that have the rubber-like elasticity but can also be molded and remolded like plastics.

25

30

The inventors have surprisingly found that it is possible to produce multi-block copolymers comprising, using a single catalytic system, either by the subsequent addition of monomer, or by a “one-pot” method in which all of the monomers are present in the reaction mixture at the start of the reaction.

35

Various terms as used herein are as defined below.

For the purpose of the invention, an aliphatic group is a hydrocarbon moiety that may be straight chain or branched and may be completely saturated, or contain one or more units of unsaturation, but which is not aromatic. The term “unsaturated” means a moiety that

5 has one or more double and/or triple bonds. The term “aliphatic” is therefore intended to encompass alkyl, alkenyl or alkynyl groups, and combinations thereof. An aliphatic group is preferably a C₁₋₂₀aliphatic group, that is an aliphatic group with 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an aliphatic group is a C₁₋₁₅aliphatic, more preferably a C₁₋₁₂aliphatic, more preferably a C₁₋₁₀aliphatic, even more

10 preferably a C₁₋₈aliphatic, such as a C₁₋₆aliphatic group.

An alkyl group is preferably a “C₁₋₂₀ alkyl group”, that is an alkyl group that is a straight or branched chain with 1 to 20 carbons. The alkyl group therefore has 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an alkyl group is a

15 C₁₋₁₅alkyl, preferably a C₁₋₁₂alkyl, more preferably a C₁₋₁₀alkyl, even more preferably a C₁₋₈alkyl, even more preferably a C₁₋₆alkyl group. In certain embodiments, an alkyl group is a “C₁₋₆ alkyl group”, that is an alkyl group that is a straight or branched chain with 1 to 6 carbons. The alkyl group therefore has 1, 2, 3, 4, 5 or 6 carbon atoms. Specifically, examples of “C₁₋₂₀ alkyl group” include methyl group, ethyl group, n-propyl group, iso-

20 propyl group, n-butyl group, iso-butyl group, sec-butyl group, tert-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, n-nonadecyl group, n-eicosyl group, 1,1-dimethylpropyl group, 1,2-dimethylpropyl group, 2,2-dimethylpropyl group, 1-

25 ethylpropyl group, n-hexyl group, 1-ethyl-2-methylpropyl group, 1,1,2-trimethylpropyl group, 1-ethylbutyl group, 1-methylbutyl group, 2-methylbutyl group, 1,1-dimethylbutyl group, 1,2-dimethylbutyl group, 2,2-dimethylbutyl group, 1,3-dimethylbutyl group, 2,3-dimethylbutyl group, 2-ethylbutyl group, 2-methylpentyl group, 3-methylpentyl group and the like. Alkenyl and alkynyl groups are preferably “C₂₋₂₀alkenyl” and “C₂₋₂₀alkynyl”

30 respectively, that is an alkenyl or alkynyl group which is a straight chain or branched chain with 2 to 20 carbons. The alkenyl or alkynyl group therefore has 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an alkenyl group or an alkynyl group is “C₂₋₁₅alkenyl” and “C₂₋₁₅alkynyl”, more preferably “C₂₋₁₂alkenyl” and “C₂₋₁₂alkynyl”, even more preferably “C₂₋₁₀alkenyl” and “C₂₋₁₀alkynyl”, even more preferably

35 “C₂₋₈alkenyl” and “C₂₋₈alkynyl”, most preferably “C₂₋₆alkenyl” and “C₂₋₆alkynyl” groups respectively.

A heteroaliphatic group is an aliphatic group as described above, which additionally contains one or more heteroatoms. Heteroaliphatic groups therefore preferably contain from 2 to 21 atoms, preferably from 2 to 16 atoms, more preferably from 2 to 13 atoms, more preferably from 2 to 11 atoms, more preferably from 2 to 9 atoms, even more preferably from 2 to 7 atoms, wherein at least one atom is a carbon atom. Particularly preferred heteroatoms are selected from O, S, N, P and Si. When heteroaliphatic groups have two or more heteroatoms, the heteroatoms may be the same or different.

An alicyclic group is a saturated or partially unsaturated cyclic aliphatic monocyclic or polycyclic (including fused, bridging and spiro-fused) ring system which has from 3 to 20 carbon atoms, that is an alicyclic group with 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an alicyclic group has from 3 to 15, more preferably from 3 to 12, even more preferably from 3 to 10, even more preferably from 3 to 8 carbon atoms. The term "alicyclic" encompasses cycloalkyl, cycloalkenyl and cycloalkynyl groups. It will be appreciated that the alicyclic group may comprise an alicyclic ring bearing one or more linking or non-linking alkyl substituents, such as -CH₂-cyclohexyl.

Cycloalkyl, cycloalkenyl and cycloalkynyl groups have from 3 to 20 carbon atoms. The cycloalkyl, cycloalkenyl and cycloalkynyl groups therefore have 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Cycloalkyl, cycloalkenyl and cycloalkynyl groups preferably have from 3 to 15, more preferably from 3 to 12, even more preferably from 3 to 10, even more preferably from 3 to 8 carbon atoms. When an alicyclic group has from 3 to 8 carbon atoms, this means that the alicyclic group has 3, 4, 5, 6, 7 or 8 carbon atoms. Specifically, examples of the C₃₋₂₀ cycloalkyl group include cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl, adamantyl and cyclooctyl. A heteroalicyclic group is an alicyclic group as defined above which has, in addition to carbon atoms, one or more ring heteroatoms, which are preferably selected from O, S, N, P and Si. Heteroalicyclic groups preferably contain from one to four heteroatoms, which may be the same or different. Heterocyclic groups preferably contain from 4 to 20 atoms, more preferably from 4 to 14 atoms, even more preferably from 4 to 12 atoms.

An aryl group is a monocyclic or polycyclic ring system having from 5 to 20 carbon atoms. An aryl group is preferably a "C₆₋₁₂ aryl group" and is an aryl group constituted by 6, 7, 8, 9, 10, 11 or 12 carbon atoms and includes condensed ring groups such as monocyclic ring group, or bicyclic ring group and the like. Specifically, examples of "C₆₋₁₀ aryl group" include phenyl group, biphenyl group, indenyl group, naphthyl group or azulenyl group

and the like. It should be noted that condensed rings such as indan and tetrahydro naphthalene are also included in the aryl group.

A heteroaryl group is an aryl group having, in addition to carbon atoms, from one to four
 5 ring heteroatoms which are preferably selected from O, S, N, P and Si. A heteroaryl group preferably has from 5 to 20, more preferably from 5 to 14 ring atoms. Specifically, examples of a heteroaryl group include pyridine, imidazole, N-methylimidazole and 4-dimethylaminopyridine.

10 Examples of alicyclic, heteroalicyclic, aryl and heteroaryl groups include but are not limited to cyclohexyl, phenyl, acridine, benzimidazole, benzofuran, benzothiophene, benzoxazole, benzothiazole, carbazole, cinnoline, dioxin, dioxane, dioxolane, dithiane, dithiazine, dithiazole, dithiolane, furan, imidazole, imidazoline, imidazolidine, indole, indoline, indolizine, indazole, isoindole, isoquinoline, isoxazole, isothiazole, morpholine,
 15 naphthyridine, oxazole, oxadiazole, oxathiazole, oxathiazolidine, oxazine, oxadiazine, phenazine, phenothiazine, phenoxazine, phthalazine, piperazine, piperidine, pteridine, purine, pyran, pyrazine, pyrazole, pyrazoline, pyrazolidine, pyridazine, pyridine, pyrimidine, pyrrole, pyrrolidine, pyrroline, quinoline, quinoxaline, quinazoline, quinolizine, tetrahydrofuran, tetrazine, tetrazole, thiophene, thiadiazine, thiadiazole, thiatriazole,
 20 thiazine, thiazole, thiomorpholine, thianaphthalene, thiopyran, triazine, triazole, and trithiane.

The term “halide” or “halogen” are used interchangeably and, as used herein mean a
 fluorine atom, a chlorine atom, a bromine atom, an iodine atom and the like, preferably a
 25 fluorine atom, a bromine atom or a chlorine atom, and more preferably a fluorine atom or a bromine atom.

A haloalkyl group is preferably a “C₁₋₂₀ haloalkyl group”, more preferably a “C₁₋₁₅ haloalkyl group”, more preferably a “C₁₋₁₂ haloalkyl group”, more preferably a “C₁₋₁₀ haloalkyl group”,
 30 even more preferably a “C₁₋₈ haloalkyl group”, even more preferably a “C₁₋₆ haloalkyl group” and is a C₁₋₂₀ alkyl, a C₁₋₁₅ alkyl, a C₁₋₁₂ alkyl, a C₁₋₁₀ alkyl, a C₁₋₈ alkyl, or a C₁₋₆ alkyl group, respectively, as described above substituted with at least one halogen atom, preferably 1, 2 or 3 halogen atom(s). Specifically, examples of “C₁₋₂₀ haloalkyl group” include fluoromethyl group, difluoromethyl group, trifluoromethyl group, fluoroethyl group,
 35 difluoroethyl group, trifluoroethyl group, chloromethyl group, bromomethyl group, iodomethyl group and the like.

An alkoxy group is preferably a "C₁₋₂₀ alkoxy group", more preferably a "C₁₋₁₅ alkoxy group", more preferably a "C₁₋₁₂ alkoxy group", more preferably a "C₁₋₁₀ alkoxy group", even more preferably a "C₁₋₈ alkoxy group", even more preferably a "C₁₋₆ alkoxy group" and is an oxy group that is bonded to the previously defined C₁₋₂₀ alkyl, C₁₋₁₅ alkyl, C₁₋₁₂ alkyl, C₁₋₁₀ alkyl, C₁₋₈ alkyl, or C₁₋₆ alkyl group respectively. Specifically, examples of "C₁₋₂₀ alkoxy group" include methoxy group, ethoxy group, n-propoxy group, iso-propoxy group, n-butoxy group, iso-butoxy group, sec-butoxy group, tert-butoxy group, n-pentyloxy group, iso-pentyloxy group, sec-pentyloxy group, n-hexyloxy group, iso-hexyloxy group, , n-hexyloxy group, n-heptyloxy group, n-octyloxy group, n-nonyloxy group, n-decyloxy group, n-undecyloxy group, n-dodecyloxy group, n-tridecyloxy group, n-tetradecyloxy group, n-pentadecyloxy group, n-hexadecyloxy group, n-heptadecyloxy group, n-octadecyloxy group, n-nonadecyloxy group, n-eicosyloxy group, 1,1-dimethylpropoxy group, 1,2-dimethylpropoxy group, 2,2-dimethylpropoxy group, 2-methylbutoxy group, 1-ethyl-2-methylpropoxy group, 1,1,2-trimethylpropoxy group, 1,1-dimethylbutoxy group, 1,2-dimethylbutoxy group, 2,2-dimethylbutoxy group, 2,3-dimethylbutoxy group, 1,3-dimethylbutoxy group, 2-ethylbutoxy group, 2-methylpentyloxy group, 3-methylpentyloxy group and the like.

An alkylthio group is preferably a "C₁₋₂₀ alkylthio group", more preferably a "C₁₋₁₅ alkylthio group", more preferably a "C₁₋₁₂ alkylthio group", more preferably a "C₁₋₁₀ alkylthio group", even more preferably a "C₁₋₈ alkylthio group", even more preferably a "C₁₋₆ alkylthio group" and is a thio (-S-) group that is bonded to the previously defined C₁₋₂₀ alkyl, C₁₋₁₅ alkyl, C₁₋₁₂ alkyl, C₁₋₁₀ alkyl, C₁₋₈ alkyl, or C₁₋₆ alkyl group respectively.

An alkylaryl group can comprise any of the alkyl or aryl groups discussed above. Preferably the alkylaryl group is a "C₆₋₁₂ aryl C₁₋₂₀ alkyl group", more preferably a preferably a "C₆₋₁₂ aryl C₁₋₁₆ alkyl group", even more preferably a "C₆₋₁₂ aryl C₁₋₆ alkyl group" and is an aryl group as defined above bonded at any position to an alkyl group as defined above. The point of attachment of the alkylaryl group to a molecule may be via the alkyl portion and thus, preferably, the alkylaryl group is -CH₂-Ph or -CH₂CH₂-Ph. An alkylaryl group can also be referred to as "aralkyl".

An alkylheteroaryl group can comprise any of the alkyl or heteroaryl groups discussed above. Preferably the alkylheteroaryl group is a "heteroaryl C₁₋₂₀ alkyl group", more preferably a preferably a "heteroaryl C₁₋₁₆ alkyl group", even more preferably a "heteroaryl C₁₋₆ alkyl group" and is a heteroaryl group as defined above bonded at any position to an alkyl group as defined above. The point of attachment of the alkylheteroaryl group to a

molecule may be via the alkyl portion. An alkylheteroaryl group can also be referred to as "heteroaralkyl".

5 An ether group is preferably a group OR_6 wherein R_6 can be an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_6 can be an unsubstituted aliphatic, alicyclic or aryl. Preferably, R_6 is an alkyl group selected from methyl, ethyl or propyl. A thioether group is preferably a group SR_6 wherein R_6 is as defined above.

10 A silyl group is preferably a group $-Si(R_7)_3$, wherein each R_7 can be independently an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, each R_7 is independently an unsubstituted aliphatic, alicyclic or aryl. Preferably, each R_7 is an alkyl group selected from methyl, ethyl or propyl. A silyl ether group is preferably a group $OSi(R_8)_3$ wherein each R_8 can be independently
15 an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, each R_8 can be independently an unsubstituted aliphatic, alicyclic or aryl. Preferably, each R_8 is an alkyl group selected from methyl, ethyl or propyl.

20 A nitrile group is a group CN.

An azide group is a group $-N_3$.

25 An imine group is a group $-CRNR$, preferably a group $-CHNR_9$ wherein R_9 is an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_9 is unsubstituted aliphatic, alicyclic or aryl. Preferably R_9 is an alkyl group selected from methyl, ethyl or propyl.

30 An acetylide group contains a triple bond $-C\equiv C-R_{10}$, preferably wherein R_{10} can be an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. For the purposes of the invention when R_{10} is alkyl, the triple bond can be present at any position along the alkyl chain. In certain embodiments, R_{10} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{10} is methyl, ethyl, propyl or phenyl.

35 An amino group is preferably $-NH_2$, $-NHR_{11}$ or $-N(R_{11})_2$ wherein R_{11} can be an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, , a silylalkyl, aryl or heteroaryl group as defined above. It will be appreciated that when the amino group is $N(R_{11})_2$, each R_{11} group can be independently selected from an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic a

silylalkyl group, heteroaryl or an aryl group as defined above. In certain embodiments, each R_{11} is independently an unsubstituted aliphatic, alicyclic or aryl. Preferably R_{11} is methyl, ethyl, propyl, SiMe_3 or phenyl. Where W of the chain transfer agent is amine, the amine is preferably NH_2 or NHR_{11} .

5

An alkylamino group may be a group $-\text{NHR}_{11}$ or $-\text{N}(\text{R}_{11})_2$ as defined above.

An amido group is preferably $-\text{NR}_{12}\text{C}(\text{O})-$ or $-\text{C}(\text{O})-\text{NR}_{12}-$ wherein R_{12} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined
10 above. In certain embodiments, R_{12} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{12} is hydrogen, methyl, ethyl, propyl or phenyl.

An ester group is preferably $-\text{OC}(\text{O})\text{R}_{13}-$ or $-\text{C}(\text{O})\text{OR}_{13}-$ wherein R_{13} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined
15 above. In certain embodiments, R_{13} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{13} is hydrogen, methyl, ethyl, propyl or phenyl.

A sulfoxide is preferably $-\text{SOR}_{14}$, a sulfonate group is preferably $-\text{OS}(\text{O})_2\text{R}_{14}$, a sulfinate group is preferably $-\text{S}(\text{O})\text{O}-\text{R}_{14}$, wherein R_{14} can be hydrogen, an aliphatic,
20 heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{14} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{14} is hydrogen, methyl, ethyl, propyl or phenyl.

A carboxylate group is preferably $\text{OC}(\text{O})\text{R}_{15}$, wherein R_{15} can be hydrogen, an aliphatic,
25 heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{15} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{15} is hydrogen, methyl, ethyl, propyl, butyl (for example n-butyl, isobutyl or tert-butyl), phenyl, pentafluorophenyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl,
30 trifluoromethyl or adamantyl.

An acetamide is preferably $\text{MeC}(\text{O})\text{N}(\text{R}_{16})_2$ wherein R_{16} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{16} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{16} is
35 hydrogen, methyl, ethyl, propyl or phenyl.

A phosphinate group is preferably a group $-\text{OP}(\text{O})(\text{R}_{17})_2$ wherein each R_{17} is independently selected from hydrogen, or an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{17} is aliphatic, alicyclic or aryl, which are optionally substituted by aliphatic, alicyclic, aryl or C_{1-6} alkoxy. Preferably R_{17} is optionally substituted aryl or C_{1-20} alkyl, more preferably phenyl optionally substituted by C_{1-6} alkoxy (preferably methoxy) or unsubstituted C_{1-20} alkyl (such as hexyl, octyl, decyl, dodecyl, tetradecyl, hexadecyl, stearyl).

It will be appreciated that where any of the above groups are present in a Lewis base G , one or more additional R^{G} groups may be present, as appropriate, to complete the valency. For example, in the context of an ether an additional R^{G} group may be present to give $\text{R}^{\text{G}}\text{OR}_6$, wherein R^{G} is hydrogen, an optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. Preferably, R^{G} is hydrogen or aliphatic, alicyclic or aryl.

Any of the aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, haloalkyl, alkoxy, alkylthio, alkylaryl, ether, ester, sulfoxide, sulfonate, sulfinate, carboxylate, silyl ether, imine, acetylide, amino, alkylamino, phosphinate or amido groups wherever mentioned in the definitions above, may optionally be substituted by halogen, hydroxyl, nitro, carbonate, alkoxy, aryloxy, heteroaryloxy, amino, alkylamino, imine, nitrile, acetylide, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl groups (for example, optionally substituted by halogen, hydroxyl, nitro, carbonate, alkoxy, amino, alkylamino, imine, nitrile or acetylide).

The term epoxide therefore relates to any compound comprising an epoxide moiety.


The term anhydride relates to any compound comprising an anhydride moiety in a ring system (i.e. a cyclic anhydride).

The term lactone relates to any cyclic compound comprising a $-\text{C}(\text{O})\text{O}-$ moiety in the ring.

The term lactide is a cyclic compound containing two ester groups.

The term "lactone and/or lactide" used herein encompasses a lactone, a lactide and a combination of a lactone and a lactide. Preferably, the term "lactone and/or lactide" means a lactone or a lactide.

An "initiator" as referred to herein acts in a method of the invention as a chain transfer agent and may therefore alternatively be referred to as a chain transfer agent (CTA). The chain transfer agent is a compound comprising at two moieties independently selected from -OH, -SH, -C(O)OH or -NH-, or water. For example, the CTA may be a compound
 5 of formula (II):



wherein Y is the core of the chain transfer agent and may be any group which can have one or more, preferably two or more "W" groups attached to it an optionally substituted moiety selected from the group consisting of aliphatic, heteroaliphatic,
 10 alicyclic, heteroalicyclic, aryl, heteroaryl, polyolefin, polyester, polyether, polycarbonate or combinations thereof; each W is independently selected from hydroxyl (-OH), amine (-NHR^w), thiol (-SH) or carboxylate (-C(O)OH), wherein R^w is hydrogen, optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl, or combinations thereof (i.e. aliphaticaryl, aliphaticheteroaryl, heteroaliphaticaryl, etc); and
 15 n is an integer which is at least 2. In preferred embodiments, n is an integer selected from 2 to 10 inclusive (i.e. n can be 2, 3, 4, 5, 6, 7, 8, 9 or 10), preferably from 2 to 10 inclusive. More preferably, n is an integer from 2 to 6 inclusive. In some embodiments, Y is an optionally substituted moiety selected from the group consisting of aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, polyolefin, polyester, polyether,
 20 polycarbonate or combinations thereof. For example, Y may be an optionally substituted araliphatic, heteroaraliphatic, aliphaticalicyclic etc. group. Preferably Y is selected from alkyl, heteroalkyl, alkenyl, heteroalkenyl, alkynyl, heteroalkynyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl and polyether. The group Y may optionally be substituted. In certain embodiments, Y is optionally substituted by halogen, nitrile, imine,
 25 nitro, aliphatic, acetyl, amido, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl. It will be appreciated that water, which does not have two distinct "-OH" groups, displays similar chain transfer properties to molecules which do have two distinct "-OH" groups.

When Y is a polymer (i.e. when Y comprises a polyolefin, polyester, polyether or
 30 polycarbonate group), the molecular weight (M_n) of such polymers are preferably less than 10,000 g/mol. Preferred polymers include poly(ethylene glycol) (PEG) and poly(lactic acid) (PLA).

In certain embodiments, each occurrence of W may be the same or different. In other
 35 embodiments, each occurrence of W is hydroxyl (i.e. the chain transfer agent is a polyol, for example a diol, a triol, a tetraol etc.). In other embodiments, each occurrence of W is amine (i.e. the chain transfer agent is a polyamine, for example a diamine, a triamine, a

tetraamine etc.). In other embodiments, each occurrence of W is carboxylic acid (i.e. the chain transfer agent is a polycarboxylic acid, for example a diacid, a triacid, a tetraacid etc.). In other embodiments, each occurrence of W is thiol (i.e. the chain transfer agent is a polythiol, for example a dithiol, a trithiol, a tetrathiol etc.). In other embodiments, the

5 chain transfer agent is water.

A single chain transfer agent or a mixture of chain transfer agents may be used.

Examples of chain transfer agents useful in the present invention include water, diols (for

10 example, 1,2-ethanediol, 1,2-propanediol, 1,3-propanediol, 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,2-diphenol, 1,3-diphenol, 1,4-diphenol, catechol and cyclohexenediol), triols (glycerol, benzenetriol, 1,2,4-butanetriol, tris(methylalcohol)propane, tris(methylalcohol)ethane, tris(methylalcohol)nitropropane, preferably glycerol or benzenetriol), tetraols (for example, calix[4]arene, 2,2-

15 bis(methylalcohol)-1,3-propanediol, preferably calix[4]arene), polyols (for example, D-(+)-glucose or D-sorbitol), dihydroxy terminated polyesters (for example polylactic acid), dihydroxy terminated polyethers (for example poly(ethylene glycol)), starch, lignin, diamines (for example 1,4-butanediamine), triamines, diamine terminated polyethers, diamine terminated polyesters, dicarboxylic acids (for example, maleic acid, malonic acid,

20 succinic acid, glutaric acid or terephthalic acid, preferably maleic acid, malonic acid, succinic acid, glutaric acid), tricarboxylic acids (for example, citric acid, 1,3,5-benzenetricarboxylic acid or 1,3,5-cyclohexanetricarboxylic acid, preferably citric acid), mono-thiols, dithiols, trithiols, and compounds having a mixture of hydroxyl, amine, carboxylic acid and thiol groups, for example lactic acid, glycolic acid, 3-hydroxypropionic

25 acid, natural amino acids, unnatural amino acids, monosaccharides, disaccharides, oligosaccharides and polysaccharides (including pyranose and furanose forms). In certain embodiments, the chain transfer agent is selected from cyclohexene diol, 1,2,4-butanetriol, tris(methylalcohol)propane, tris(methylalcohol)nitropropane, tris(methylalcohol)ethane, 2,2-bis(methylalcohol)-1,3-propanediol, 1,3,5-

30 benzenetricarboxylic acid, diphenylphosphinic acid, 1,3,5-cyclohexanetricarboxylic acid, 1,4-butanediamine, 1,6-hexanediol, D-sorbitol, 1-butylamine, terephthalic acid, D-(+)-glucose, 3,5-di-tert-butylbenzoic acid, 4-ethylbenzenesulfonic acid and water.

Crystallinity (χ) of block A may be calculated using the DSC procedure described herein.

35 If the polymer sample contains any crystalline material a melting peak is observed. If no melting peak is observed crystallinity is assumed at zero percent. If a melting point is observed, crystallinity may be calculated via the following equation:

$$\chi = \frac{\Delta H_m}{\Delta H_m^0} \times 100\%$$

Where ΔH_m is the integral of the melting peak using the integral function provided in the software (universal analysis, version 4.3A), with the unit of J/g; ΔH_m^0 is the amount of heat when 1 gram of 100% crystallized polylactone or polylactide is melted with the unit of J/g.

- 5 The value of ΔH_m^0 can be calculated by the extrapolation of the ΔH_m of polylactone or polylactide standards (with known crystallinity) to complete crystallinity. The ΔH_m values of different polylactone or polylactide standards are plotted against the crystallinity (χ) of these standards. Then the plots are extrapolated to a crystallinity of 100 %, where the corresponding ΔH_m value is defined as the ΔH_m^0 . In some instances, the value of ΔH_m^0 can be found in literature (Crescenzi.V, G. Manzini, Calzolari.G and C. Borri, Eur. Polym. J., 1972, 8, 449).

- Alternatively, crystallinity (χ) may be determined using a wide-angle X-ray scattering (WAXS) procedure as described in W. Hu *et al.*, *Macromolecules* 2002, 35, 5013-5024 or
 15 P. J. Rae *et al.*, *Polymer* 2004, 45, 7615-7625, the contents of which are incorporated herein by reference. CuK α ($\lambda = 0.154$ nm) X-ray is produced by a rotating anode X-ray generator (e.g. Rigaku ROTAFLEX RTP300) with a Cu target and a Ni filter. The goniometer was calibrated with NaCl to within 0.5°. Polymer samples are continuously scanned from 4 to 50° (or corresponding vector q) at a rate of 1 deg·min⁻¹. The X-ray data
 20 were first modelled using a form which include Lorentzian line shapes for the crystalline peaks and a lorentzian plus a quadratic form for the amorphous scattering. Then, the data were fit using the CPLOT nonlinear least-squares fitting routine over the scattering range. The crystallinity (χ) is calculated by this equation:

$$\chi = A_c/A_a \times 100\%$$

- 25 where A_a is the integral of the amorphous contribution and A_c is the integral of the crystalline peaks.

- In a first aspect, the invention provides a multi-block copolymer comprising at least blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a
 30 lactone and/or a lactide; and block B comprises a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the multi-block copolymer is characterised by one or more of features (i) to (iii):

- (i) a degree of crystallinity (χ) of block A of no more than 20% as determined by DSC; and/or
- (ii) a degree of crystallinity (χ) of block A of no more than 20% as determined by WAXS; and/or
- 5 (iii) a measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B.

In some embodiments, the multi-block copolymer has a measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B. Preferably, there is a difference of at least 20°C, at least 40°C, at least 60°C, at least 80°C or at least
 10 100°C between the T_g for blocks A and B.

Block B may have a T_g of $\geq 30^\circ\text{C}$, $\geq 40^\circ\text{C}$, or $\geq 50^\circ\text{C}$. In some embodiments, the T_g of block B is no more than 250 °C, no more than 200 °C, no more than 150 °C or no more than 100 °C. In some embodiments, block B has a T_g of 50°C to 70°C. From the processing
 15 perspective, where T_g is below 100 °C, processing can be conducted at much lower temperatures than 200 °C.

Block B of the multi-block copolymer is preferably substantially amorphous. Block B is considered to be substantially amorphous in the absence of detectable crystalline
 20 component therein. Block B may, for example, be determined to be substantially amorphous if no melting peaks can be observed in DSC or no sharp crystalline peaks can be observed in WAXS, utilising DSC and WAXS procedures corresponding to those as defined herein.

25 In a preferred embodiment, the multi-block copolymer is characterised by feature (i) or (ii) and feature (iii).

In some embodiments, the degree of crystallinity (χ) of block A is no more than 20%, no more than 15%, no more than 10% or no more than 5%, as determined by DSC.
 30

In some embodiments, the degree of crystallinity (χ) of block A is no more than 20%, no more than 15%, no more than 10% or no more than 5%, as determined by WAXS.

It will be appreciated that the polyester of block A and the copolyester or polycarbonate of
 35 block B may be directly or indirectly linked. For example, blocks A and B of a multi-block copolymer of the invention may be directly linked, or the multi-block copolymer may comprise linker groups and/or additional polymeric groups between blocks A and B.

Additional polymeric groups may, for example, be a polyester formed by polymerisation of a lactone and/or a lactide, a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, as described herein for any embodiment of block A or B. In addition, the multi-block copolymer may comprise more than the three blocks A-B-A or B-A-B. For example, the multiblock copolymer may comprise 5, 7 or more alternating blocks, such as A-B-A-B-A or A-B-A-B-A-B-A. Alternatively, the multi-block copolymer may comprise two or more linked triblock units A-B-A or B-A-B, for example in the form A-B-A-A-B-A or B-A-B-B-A-B. The blocks A-B-A or B-A-B may be linked via a linker, for example a urethane linker.

Alternatively, the multi-block copolymer may be comprise block in the form A-B-B-B-A or B-A-A-A-B, wherein adjacent A or B blocks may be distinct in identity and/or linked indirectly via a linker.

Within a multi-block copolymer of the invention, the weight content of block B, with reference to block A, may be from 10 to 90 wt%, preferably 20 to 80 wt%, more preferably 30 to 55 wt% or 30 to 50 wt%. The weight contents were calculated via the following equation:

$$\text{wt}\% = M_B / (a \times M_A + M_B) \times 100\%$$


where a is the molar ratio of the repeat units of blocks A and B, acquired from ^1H NMR ($a = [\text{m-A}]/[\text{m-B}]$); M_A is the molecular weight of m-A; M_B is the molecular weight of the m-B), wherein m-A and m-B represent the monomer, or monomer combinations, forming blocks A and B, respectively. In some embodiments, for example to produce tough plastics, the weight content of block B, with reference to block A, is 55wt% or more, e.g. 55-90 or 55-80 wt%. In some embodiments, for example to produce shape memory materials, the weight content of block B, with reference to block A, is 30-55, 35-55 or 35-50 wt%. In some embodiments, for example to produce thermoplastic elastomers, the weight content of block B, with reference to block A, is no more than 30wt%, e.g. 10-30 or 20-30 wt%.

In some embodiments, the multi-block copolymer of the invention may have a M_n (number average molecular weight) of, at least 1 kg/mol, preferably at least 10kg/mol. In some embodiments, the blocks A-B-A or B-A-B of a multi-block copolymer of the invention may have a M_n of, at least 1 kg/mol, preferably at least 10kg/mol.

In some embodiments, the multi-block copolymer of the invention may have a Young's modulus of 1 MPa to 7000 MPa. In some embodiments, the Young's modulus is from 10-


200 MPa, preferably 40-100 MPa. For example, this may in some embodiments apply where the weight content of block B, with reference to block A, is 30-55, 35-55 or 35-50 wt%. In other embodiments, the Young's modulus is from 1-10 MPa. For example, this may apply in some embodiments where the weight content of block B, with reference to
 5 block A, is no more than 30wt%, e.g. 10-30 or 20-30 wt%. In yet other embodiments, the Young's modulus is at least 50 MPa, for example 200 MPa to 7000 MPa, preferably 223 MPa to 6600 MPa. In some embodiments, the multi-block copolymer may have an elongation at break of 100% to 1200%, preferably at least 200%, for example 350% to 1000%. For example, this may in some embodiments apply where the weight content of
 10 block B, with reference to block A, is 55wt% or more, e.g. 55-90 or 55-80 wt%.


In preferred embodiments, the epoxide may have the following formula:



wherein each R₁, R₂, R₃ and R₄ is independently selected from hydrogen, halogen, nitro,
 15 alkoxy, aryloxy, heteroaryloxy, alkylamino, imine, nitrile, acetylide, carboxylate or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, branched alkyl heteroaryl, alkylaryl or alkylheteroaryl, or a polymeric species [e.g. polybis(phenol)A]; or two or more of R₁, R₂, R₃ and R₄ can be taken together to form a saturated, partially saturated or unsaturated 3 to 12 membered, optionally substituted ring system, optionally
 20 containing one or more heteroatoms.


Preferred examples of epoxides include propylene oxide, cyclohexene oxide, substituted cyclohexene oxides (such as limonene oxide, C₁₀H₁₆O, 2-(3,4-epoxycyclohexyl)ethyltrimethoxysilane, C₁₁H₂₂O or 4-vinyl-1-cyclohexene 1,2-epoxide,
 25 C₈H₁₂O), alkylene oxides (such as ethylene oxide and substituted ethylene oxides), substituted oxiranes (such as epichlorohydrin, 1,2-epoxybutane, glycidyl ethers), styrene oxide or substituted styrene oxides. For example, epoxides, may have the following structures:






R' wherein R' is optionally substituted C₂₋₁₂ (preferably C₂₋₈, more preferably C₂₋₆) aliphatic. The aliphatic is preferably alkyl. The alkyl is preferably a straight chain alkyl, which is preferably unsubstituted.

- 5 In preferred embodiments, the anhydride may have the following formula:





- wherein n is 1, 2, 3, 4, 5, or 6 (preferably 1 or 2), each R_{1'}, R_{2'}, R_{3'} and R_{4'} is independently selected from hydrogen, halogen, nitro, alkoxy, aryloxy, heteroaryloxy, alkylamino, imine, nitrile, acetylide, carboxylate or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, branched alkyl heteroaryl, alkylaryl or alkylheteroaryl, or a polymeric species (e.g. polybis(phenol)A); or two or more of R_{1'}, R_{2'}, R_{3'} and R_{4'} can be taken together to form a saturated, partially saturated or unsaturated 3 to 12 membered, optionally substituted ring system, optionally containing one or more heteroatoms, or can be taken together to form a double bond. Each Q is independently C, O, N or S, preferably C, wherein R_{3'} and R_{4'} are either present, or absent, and ===== can either be ===== or =====, according to the valency of Q. It will be appreciated that when Q is C, and ===== is =====. In some embodiments, the anhydride comprises an aromatic moiety. Preferable anhydrides include those set out below.




20


In preferred embodiments, the lactone may have the following formula:



wherein  represents a hydrocarbon ring having 2 to 20 (e.g. 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20, preferably at least 4, e.g. 4, 5 or 14) ring carbon atoms in addition to the carbon of the $-\text{C}(\text{O})\text{O}$ moiety, wherein the ring is saturated or contains one or more $\text{C}=\text{C}$ double bonds and wherein each saturated ring carbon atom is substituted by R_a and R_b and each unsaturated carbon atom is substituted by R_a , wherein R_a and R_b are independently selected from hydrogen, halogen, nitro, alkoxy, aryloxy, heteroaryloxy, alkylamino, imine, nitrile, acetylide, carboxylate or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, branched alkyl heteroaryl, alkylaryl or alkylheteroaryl. Two or more of R_a and R_b on adjacent ring carbon atoms can be taken together to form a saturated, partially saturated or unsaturated 3 to 15 membered, optionally substituted ring system, optionally containing one or more heteroatoms. Preferably, each instance of R_a and R_b is, independently, selected from hydrogen or alkyl. Preferably, at least one of R_a and R_b is selected from substituent other than hydrogen. Preferably, the lactone comprises one or more of an optionally substituted alkyl substituent (e.g. C_{1-10} alkyl, preferably C_{3-8} alkyl) on the hydrocarbon ring, an aromatic component or at least one $\text{C}=\text{C}$ double bond. Preferred lactones include those set out below:




In preferred embodiments, the lactide may have the following formula:




Wherein m' is 1, 2, 3, 4, 5, 6, 7, 8, 9 or 10, (preferably 1 or 2, more preferably, 1) and $\text{R}^{\text{L}3}$ and $\text{R}^{\text{L}4}$ are independently selected from hydrogen, halogen, hydroxyl, nitro, alkoxy, aryloxy, heteroaryloxy, amino, alkylamino, imine, nitrile, acetylide, carboxylate or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl. Two or more of $\text{R}^{\text{L}3}$ and $\text{R}^{\text{L}4}$ can be taken together to form a saturated, partially saturated or unsaturated 3 to 12 membered, optionally substituted ring

- system, optionally containing one or more heteroatoms, When m' is 2 or more, the R^{L3} and R^{L4} on each carbon atom may be the same or different or one or more R^{L3} and R^{L4} on adjacent carbon atoms can be absent, thereby forming a double or triple bond. It will be appreciated that while the compound has two moieties represented by $(-CR^{L3}R^{L4})_{m'}$, both
- 5 moieties will be identical. In particularly preferred embodiments, m' is 1, R^{L4} is H, and R^{L3} is H, hydroxyl or a C_{1-6} alkyl, preferably methyl. The stereochemistry of the moiety represented by $(-CR^{L3}R^{L4})_{m'}$ can either be the same (for example RR-lactide or SS-lactide), or different (for example, *meso*-lactide). The lactide may be a racemic mixture, or may be an optically pure isomer. Preferred lactides include those set out below:



Preferably, the lactide is *rac*-lactide:



- 15 Preferred optional substituents of the groups R^{L1} , R^{L2} , R^{L3} and R^{L4} include halogen, nitro, hydroxyl, unsubstituted aliphatic, unsubstituted heteroaliphatic unsubstituted aryl, unsubstituted heteroaryl, alkoxy, aryloxy, heteroaryloxy, amino, alkylamino, imine, nitrile, acetylide, and carboxylate.
- 20 In preferred embodiments, block A may comprise a polyester formed by polymerisation of ϵ -decalactone. Block B may, for example, comprise poly(cyclohexylene phthalic)ester, an alternating copolyester formed from polymerization of cyclohexene oxide and phthalic anhydride, a polycarbonate formed from polymerization of cyclohexene oxide or 4-vinyl-1-cyclohexene 1,2-epoxide and carbon dioxide (poly(cyclohexylene carbonate) (PCHC) or
- 25 poly(vinylcyclohexenecarbonate) (PvCHC), or a combination thereof. Preferably Block B comprises poly(cyclohexylene phthalic)ester.

- In any of the embodiments described above, block A may for example consist essentially of a polyester formed by polymerisation of a lactone and/or a lactide; block B may consist
- 30 essentially of a copolyester formed by polymerisation of an epoxide and an anhydride, or

a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, and blocks A and B may be directly linked.

5 A multi-block copolymer as described herein may, for example, be a multi-block polymer having a degree of crystallinity (χ) of no more than 20%, no more than 15%, no more than 10% or no more than 5% for the multi-block copolymer as a whole, as determined by WAXS or DSC.

10 In another aspect, the present invention provides a multi-block copolymer comprising at least blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B comprises a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the block B comprises an aromatic moiety and/or wherein the lactone is as defined herein and comprises one or
15 more of (i) one or more of R_a and R_b selected from a substituent other than hydrogen; (ii) an optionally substituted alkyl substituent (e.g. C_{1-10} alkyl, preferably C_{3-8} alkyl) on the hydrocarbon ring, (iii) an aromatic component; and (iv) at least one C=C double bond; and/or with the proviso that the lactone is not ϵ -caprolactone. It will be appreciated that embodiments described herein for blocks A and B apply *mutatis mutandis* to this aspect.

20


In some embodiments, block A may comprise a polyester formed by polymerisation of ϵ -decalactone. Block B may, for example, comprise poly(cyclohexylene phthalic)ester, an alternating copolyester formed from polymerization of cyclohexene oxide and phthalic anhydride, a polycarbonate formed from polymerization of cyclohexene oxide or 4-vinyl-1-
25 cyclohexene 1,2-epoxide and carbon dioxide (poly(cyclohexylene carbonate) (PCHC) or poly(vinylcyclohexenecarbonate) (PvCHC), or a combination thereof. Preferably Block B comprises poly(cyclohexylene phthalic)ester.

In some embodiments, block A consists essentially of a polyester formed by
30 polymerisation of a lactone and/or a lactide; block B consists essentially of a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, and blocks A and B are directly linked.

In a second aspect, the invention provides a 'one-pot' method for producing a multi-block
35 copolymer comprising at least blocks A-B-A, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B comprises a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate

formed by polymerisation of an epoxide and carbon dioxide, wherein the method comprises forming a reaction mixture comprising:

- i. an epoxide;
- II. an anhydride or carbon dioxide; and
- 5 iii. a lactone and/or a lactide; and
- iv. a catalytic system comprising a catalyst of formula (I) and an initiator;
- such that polymerisation occurs to form a multi-block copolymer comprising at least blocks A-B-A,
- wherein the catalyst is of formula (I):



wherein:

[M] is a metal complex having at least one metal atom M coordinated by a ligand system;

M is Zn, Cr, Co, Mn, Mg, Fe, Ti, Ca, Ge, Al, Mo, W, Ru, Ni or V;

Z is absent, or is independently selected from $-E-$, $-EX(E)-$, or $-EX(E)E-$.

15 each E is independently selected from O, S or NR^Z, wherein R^Z is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl;
X is C or S

R is hydrogen, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl, alkylheteroaryl, silyl or a polymer; and when Z is absent, R may additionally be selected from halide, phosphinate, azide and nitrate; wherein the initiator is a multifunctional protic compound comprising at least two moieties independently selected from -OH , -SH , -C(O)OH or -NH- , or wherein the initiator is water.

25

It will be appreciated that the definition of the catalyst system for use in the method of the present invention is not limiting and encompasses any catalyst of formula (I), in particular any catalyst of formula (I) suitable for polymerisation of an epoxide with carbon dioxide, or an anhydride, to form a polycarbonate polyol or polyester polyol respectively.

Such known catalyst systems generally comprise a metal, and a ligand. The metal can be selected from Zn, Ni, Ru, Mo, Fe, Mn, Mo, Cr, V, Co, Ti, W, Al, Ca, Ge or Mg. In preferred embodiments, the metal is Zn, Mg, or Co, more preferably Mg or Zn. The catalyst can comprises one or more metal atoms, such as two metal atoms. The ligand can be a

monodentate or poly dentate ligand, such as a bi-dentate, tri-dentate or tetradentate ligand.

In particular, the methods of the present invention can use a metal co-ordination
5 compound comprising the following tetradentate ligands as disclosed in WO2010/028362, the contents of which are incorporated herein by reference: salen derivatives; derivatives of salan ligands; bis-2-hydroxybenzamido derivatives; derivatives of the Trost ligand; porphyrin derivatives; derivatives of tetrabenzoporphyrin ligands; derivatives of corrole ligands; phthalocyaninate derivatives; and dibenzotetramethyltetraaza[14]annulene
10 derivatives.

The invention relates to catalysts comprising metal complexes comprising two or metal atoms complexed to one or more multidentate ligand(s) as disclosed in WO2012/037282, the contents of which are incorporated herein by reference.
15


The invention further encompasses the use of catalysts comprising bulky β -diiminate (BDI) ligands for example (BDI)-ZnOⁱPr as disclosed in Coates et al, J.A.C.S., (2001), 123, 3229-3238, the contents of which are incorporated herein by reference. An additional example of such a catalyst includes the salen Co(III)X/onium salt catalyst system as
20 disclosed in Lu et al, J.A.C.S., (2012), 134, 17739 – 17745, the contents of which are incorporated herein by reference.

The invention further encompasses catalysts comprising two metal atoms complexed to a multidentate ligand system as disclosed in WO2009/130470, WO2013/034750 and
25 WO2014/184578, the entire contents of which are incorporated herein by reference.

Other examples of known catalyst systems for use in the method of the present invention include (BDI)Zn-OAc as disclosed in R.C. Jeske, A.M. DiCiccio, G.W. Coates, *J. Am. Chem. Soc.* 2007, 129, 11330-11331, (salen)Cr-Cl as disclosed in D.J. Darensbourg, R.R. Poland, C. Escobedo, *Macromolecules* 2012, 45, 2242-2248, (salen)M-Cl, where M is Cr, Al, Co or Mn, as disclosed in C. Robert, F. De Montigny, C.M. Thomas, *Nature Comm.* 2011, 2, 586, (salen)-Co-O₂CPH as disclosed in M. DiCicco, G.W. Coates, *J. Am. Soc.* 2011, 133, 10724-10727, (Tp-porph)Al-Cl as disclosed in T. Aida, S. Inoue, *J. Am. Chem. Soc.* 1985, 107, 1358-1364 and T. Aida, K. Sanuki, S. Inoue, *Macromolecules* 1985, 18,
35 1049; (sal*)MCl where M is Al, Cr or Co as disclosed in E. Hosseini Nejad, C.G.W. van Melis, T.J. Vermeer, C.E. Koning, R. Duchateau, *Macromolecules*, 2012, 45, 1770-1776, (Ph-salen)Cr-Cl as disclosed in E. Hosseini Nejad, A. Paoniasari, C.E. Koning, R.

Duchateau, *Polym. Chem*, 2012, 3, 1308, the contents of all of which are incorporated herein by reference.

- In preferred embodiments of the first aspect, the catalyst of formula (I) is preferably a
 5 complex of formula (IA):



wherein

- R_1 and R_2 are independently hydrogen, halide, a nitro group, a nitrile group, an imine, an amine, an ether group, a silyl ether group, a thioether group, a sulfoxide group, a sulfinate group, or an acetylide group or an optionally substituted alkyl, alkenyl, alkynyl, haloalkyl, aryl, heteroaryl, alicyclic or heteroalicyclic;
- R_3 is optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, arylene, heteroarylene or cycloalkylene, wherein alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene and heteroalkynylene
 15 may optionally be interrupted by aryl, heteroaryl, alicyclic or heteroalicyclic;
- R_4 is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl;
- R_5 is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl;
- 20 E_1 is C, E_2 is O, S or NH or E_1 is N and E_2 is O;
- Z is absent, or is selected from $-E-$, $-EX(E)-$, or $-EX(E)E-$;
- X is C or S;
- E is $-O-$, $-S-$, or NR^Z , wherein R^Z is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl;
- 25 R is hydrogen, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl, alkylheteroaryl, silyl or a polymer; and when Z is absent, R may additionally be selected from halide, phosphinate, azide and nitro;

each G is independently absent or a neutral or anionic donor ligand which is a Lewis base, wherein when a G group is present, the G group may be associated with a single M as shown in formula (IA), or a single G group may be associated with both metal centres and form a bridge between the two metal centres; and

- 5 M is Zn(II), Cr(II), Co(II), Mn(II), Mg(II), Fe(II), Ti(II), Cr(III)-Z-R, Co(III)-Z-R, Mn(III)-Z-R, Fe(III)-Z-R, Ca(II), Ge(II), Al(III)-Z-R, Ti(III)-Z-R, V(III)-Z-R, Ge(IV)-(-Z-R)₂ or Ti(IV)-(-Z-R)₂.

- R₁ and R₂ are independently hydrogen, halide, a nitro group, a nitrile group, an imine, an amine, an ether group, a silyl ether group, a thioether group, a sulfoxide group, a sulfinate
 10 group, or an acetylide group or optionally substituted alkyl, alkenyl, alkynyl, haloalkyl, aryl, heteroaryl, alicyclic or heteroalicyclic. R₁ and R₂ may be the same or different. R₁ and R₂ are preferably independently selected from hydrogen, tBu, Me, CF₃, phenyl, F, Cl, Br, I, NMe₂, NEt₂, NO₂, OMe, OSiEt₃, CNMe, CN or CCPh, more preferably hydrogen, OMe, Me, NO₂, halogen or tBu (e.g. hydrogen or tBu). In certain embodiments, R₂ is hydrogen
 15 and R₁ is any one of the groups defined above, preferably NO₂, halogen, tBu, OMe or Me, more preferably tBu, OMe or Me.

- R₃ is a disubstituted alkyl, alkenyl, alkynyl, heteroalkyl, heteroalkenyl or heteroalkynyl group which may optionally be interrupted by an aryl, heteroaryl, alicyclic or heteroalicyclic group, or may be a disubstituted aryl or cycloalkyl group which acts as a bridging group
 20 between two nitrogen centres in the catalyst of formula (IA). Thus, where R₃ is a alkylene group, such as dimethylpropylene, the R₃ group has the structure -CH₂-C(CH₃)₂-CH₂-. The definitions of the alkyl, aryl, cycloalkyl etc groups set out above therefore also relate respectively to the alkylene, arylene, cycloalkylene etc groups set out for R₃. In certain embodiments, R₃ is optionally substituted alkylene, alkenylene, alkynylene,
 25 heteroalkylene, heteroalkenylene, heteroalkynylene, arylene, heteroarylene or cycloalkylene; wherein alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene and heteroalkynylene may optionally be interrupted by aryl, heteroaryl, alicyclic or heteroalicyclic. In particularly preferred embodiments, R₃ is a propylene group which is optionally substituted by aliphatic (preferably C₁₋₆alkyl) or aryl groups. Preferably R₃ is
 30 ethylene, 2,2-dimethylpropylene, propylene, butylene, phenylene, cyclohexylene or biphenylene, more preferably 2,2-dimethylpropylene. When R₃ is cyclohexylene, it can be the racemic, RR- or SS- forms.

R₄ is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl. Preferably R₄ is independently selected from

hydrogen, or optionally substituted alkyl, alkenyl, alkynyl, aryl or heteroaryl. Exemplary options for R_4 include H, Me, Et, Bn, iPr, tBu or Ph. More preferably, R_4 is hydrogen.

R_5 is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl. Preferably R_5 is independently selected from
 5 hydrogen, or optionally substituted aliphatic or aryl. More preferably, R_5 is selected from hydrogen, alkyl or aryl. Exemplary R_5 groups include hydrogen, methyl, trifluoromethyl, ethyl and phenyl (preferably hydrogen, trifluoromethyl and methyl). In particularly preferred embodiments, all instances of R_5 are hydrogen.

In certain embodiments, R_1 , R_2 , R_3 , R_4 and R_5 are each independently optionally
 10 substituted by halogen, hydroxyl, nitro, carbonate, alkoxy, aryloxy, heteroaryloxy, amino, alkylamino, imine, nitrile, acetylide, or unsubstituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl. Preferably R_1 , R_2 , R_3 , R_4 and R_5 are each independently optionally substituted by halogen, hydroxyl, nitro, carbonate, alkoxy, aryloxy, imine, nitrile, acetylide, unsubstituted aliphatic, unsubstituted alicyclic and
 15 unsubstituted aryl.

In certain embodiments, E_1 is C, E_2 is O, S or NH, and preferably E_2 is O. In other embodiments, E_1 is N and E_2 is O. In particularly preferred embodiments, E_1 is C and E_2 is O.

G is either present or absent. When G is not absent, it is a group which is capable of
 20 donating a lone pair of electrons (i.e. a Lewis base). In certain embodiments, G is a nitrogen containing Lewis base. Each G may independently be neutral or negatively charged. If G is negatively charged, then one or more positive counterions will be required to balance out the charge of the complex. Suitable positive counterions include group 1 metal ions (Na^+ , K^+ , etc), group 2 metal ions (Mg^{2+} , Ca^{2+} , etc), imidazolium ions,
 25 positively charged optionally substituted heteroaryl, heteroalicyclic or heteroaliphatic groups, ammonium ions (i.e. $\text{N}(\text{R}^{12})_4^+$), iminium ions (i.e. $(\text{R}^{12})_2\text{C}=\text{N}(\text{R}^{12})_2^+$, such as bis(triphenylphosphine)iminium ions) or phosphonium ions ($\text{P}(\text{R}^{12})_4^+$), wherein each R^{12} is independently selected from hydrogen or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl. Exemplary counterions include $[\text{H}-\text{B}]^+$ wherein
 30 B is selected from triethylamine, 1,8-diazabicyclo[5.4.0]undec-7-ene and 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-ene.

G is preferably independently selected from an optionally substituted heteroaliphatic group, an optionally substituted heteroalicyclic group, an optionally substituted heteroaryl group, a halide, hydroxide, hydride, a carboxylate, an ether, a thioether, carbene, a

phosphine, a phosphine oxide, an amine, an acetamide, acetonitrile, an ester, a sulfoxide, a sulfonate and water. More preferably, G is independently selected from water, an alcohol, a substituted or unsubstituted heteroaryl (imidazole, methyl imidazole, pyridine, 4-dimethylaminopyridine, pyrrole, pyrazole, etc), an ether (dimethyl ether, diethylether, cyclic ethers, etc), a thioether, carbene, a phosphine, a phosphine oxide, a substituted or unsubstituted heteroalicyclic (morpholine, piperidine, tetrahydrofuran, tetrahydrothiophene, etc), an amine, an alkyl amine (trimethylamine, triethylamine, etc), acetonitrile, an ester (ethyl acetate, etc), an acetamide (dimethylacetamide, etc), a sulfoxide (dimethylsulfoxide, etc), a carboxylate, a hydroxide, hydride, a halide, a nitrate, a sulfonate, etc. In some embodiments, one or both instances of G is independently selected from optionally substituted heteroaryl, optionally substituted heteroaliphatic, optionally substituted heteroalicyclic, halide, hydroxide, hydride, an ether, a thioether, carbene, a phosphine, a phosphine oxide, an amine, an alkyl amine, acetonitrile, an ester, an acetamide, a sulfoxide, a carboxylate, a nitrate or a sulfonate. In certain embodiments, G may be a halide; hydroxide; hydride; water; a heteroaryl, heteroalicyclic or carboxylate group which are optionally substituted by alkyl, alkenyl, alkynyl, alkoxy, halogen, hydroxyl, nitro or nitrile. In preferred embodiments, G is independently selected from halide; water; a heteroaryl optionally substituted by alkyl (e.g. methyl, ethyl etc), alkenyl, alkynyl, alkoxy (preferably methoxy), halogen, hydroxyl, nitro or nitrile. In some embodiments, one or both instances of G is negatively charged (for example, halide). In further embodiments, one or both instances of G is an optionally substituted heteroaryl. Exemplary G groups include chloride, bromide, pyridine, methylimidazole (for example N-methyl imidazole) and dimethylaminopyridine (for example, 4-methylaminopyridine).

Preferably G is absent.

It will be appreciated that when a G group is present, the G group may be associated with a single M metal centre as shown in formula (IA), or the G group may be associated with both metal centres and form a bridge between the two metal centres.

Preferably M is Zn(II), Cr(III), Cr(II), Co(III), Co(II), Mn(III), Mn(II), Mg(II), Fe(II), Fe(III), Ca(II), Ge(II), Ti(II), Al(III), Ti(III), V(III), Ge(IV) or Ti(IV), more preferably Zn(II), Cr(III), Co(II), Mn(II), Mg(II), Fe(II) or Fe(III), and most preferably Zn(II) or Mg(II). It will be appreciated that when M is Cr(III), Co(III), Mn(III) or Fe(III), the catalyst of formula (IA) will contain an additional –Z-R group co-ordinated to the metal centre, wherein –Z-R is as defined herein. It will also be appreciated that when M is Ge(IV) or Ti(IV), the catalyst of formula (IA) will contain two additional –Z-R groups co-ordinated to the metal centre,

wherein $-Z-R$ is as defined above. In certain embodiments, when M is Ge(IV) or Ti(IV), both G may be absent.

- The skilled person will also appreciate that each M may be the same (for example, both M may be Mg, Zn, Fe or Co) or each M may be different and can be present in any
- 5 combination (for example, Fe and Zn, Co and Zn, Mg and Fe, Co and Fe, Mg and Co, Cr and Mg, Cr and Zn, Mn and Mg, Mn and Zn, Mn and Fe, Cr and Fe, Cr and Co, Al and Mg, Al and Zn etc). When M is the same metal, it will be appreciated that each M may be in the same oxidation state (for example both M may be Co(II), Fe(II) or Fe(III)), or in a different oxidation state (for example, one M may be Co(II) and the other M may be
- 10 Co(III), one M may be Fe(II) and the other M may be Fe(III), or one M may be Cr(II) and the other M may be Cr(III)).

$-Z-$ is either absent or selected from $-E-$, $-E-X(E)-$ or $-E-X(E)-E-$.

X is C or S, preferably C.

E is O, S, or NR^Z .

- 15 When Z is $-E-X(E)-$, $-E-X(E)-$ is preferably $-O-(CO)-$, $-NR^Z-C(O)-$, $-O-C(=NR^Z)-$, $-O-C(S)-$, $-O-S(O)-$, $-NR^Z-S(O)-$ or $-O-S(=NR^Z)-$.

When Z is $-E-X(E)-E-$, $-E-X(E)-E-$ is preferably $-O-(CO)-O-$, $-NR^Z-C(O)-O-$, $-NR^Z-C(O)-NR^Z$, $-O-C(=NR^Z)-O-$, $-O-C(=NR^Z)-NR^Z$, $-O-C(S)-O-$, $-O-C(O)-NR^Z$, $-O-S(O)-O-$, $-NR^Z-S(O)-O-$, $-O-S(O)-NR^Z$.

- 20 Preferably, each occurrence of E is O.

In certain embodiments, each E is O and X is C.

Each NR^Z is independently H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl. Preferably NR^Z is hydrogen or C_{1-6} alkyl.

- 25 R is hydrogen, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl, alkylheteroaryl or silyl. Preferably, R is an optionally substituted alkyl, alkenyl, alkynyl, aryl, alkylaryl, cycloalkyl, cycloalkenyl, cycloalkynyl, heteroaryl, cycloheteroalkyl, alkylheteroaryl or silyl. More preferably, R is C_{1-12} alkyl, cycloalkyl or aryl (for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, tert-butyl, phenyl, cyclohexyl etc).

When $-Z-$ is absent, in addition to the above groups, R may also be a halide, phosphinate, azide or nitrate.

Preferably, R may be substituted by halogen, hydroxyl, nitro, unsubstituted aryl, unsubstituted alkyl, unsubstituted alkenyl, unsubstituted alkoxy and unsubstituted aryloxy.

- 5 For example, R may be an alkyl group substituted by halogen, for instance R may be CF_3 .

It will also be appreciated that R can be a polymer chain. For example, R may be a polycarbonate or a polyester.


The catalyst of formula (IA) has two or more occurrences of $-Z-R$, depending on the oxidation state of the metal M. Each $-Z-R$ may be the same, or different.





- 10 The skilled person will also understand that the moiety in the group -R which is attached to the group $-Z-$ will not be a heteroatom (for example, O, S or N) or a group $C=E'$, where E' is a heteroatom (for example O, S, or N).


- In particularly preferred embodiments, R_1 and R_2 are independently hydrogen, or optionally substituted alkyl, alkenyl, halogen, hydroxyl, nitro, alkoxy, aryl, heteroaryl, alkylaryl and alkylheteroaryl; R_3 is optionally substituted alkylene or arylene; R_4 is hydrogen, or optionally substituted alkyl or heteroaryl; R_5 is hydrogen or optionally substituted alkyl; E_1 is C and E_2 is O; M is Mg, Zn, Fe or Co; Z is either absent or selected from $-O-R$, $O-C(O)-R$ or $-OC(O)-O-R$; R is optionally substituted alkyl, alkenyl, cycloalkyl, aryl, heteroaryl, alkylaryl or alkylheteroaryl; or when Z is absent, R is phosphinate or halide; G is either absent, or is selected from optionally substituted heteroaryl or halide. It will be appreciated that when G is a halogen, a counterion must be present. Preferably, the counterion is $[H-B]^+$, wherein B is preferably selected from NEt_3 , 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU) and 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-ene (MTBD).

25


Exemplary catalysts of formula (IA) include:



 $[L^1Zn_2(OAc)_2]$  $[L^2Zn_2(OAc)_2]$  $[L^3Zn_2(OAc)_2]$  $[L^1Mg_2(OAc)_2]$

[L¹Co₂Cl₃]⁺ [B-H]⁻

[B-H]⁺ represents any counterion, for example,
 B may be NEt₃, 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU),
 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-ene (MTBD), etc

[L¹Co₂Cl₂Nu]


Nu = N-methylimidazole
 = pyridine
 = dimethylaminopyridine

- [L¹Mg₂Cl₂(methylimidazole)], [L¹Mg₂Cl₂(dimethylaminopyridine)],
 [L¹Mg₂Br₂(dimethylaminopyridine)], [L¹Zn₂(F₃CCOO)₂], [L¹Zn₂(OOCCH(CH₃)₃)₂],
 [L¹Zn₂(OC₆H₅)₂], [L¹Fe₂Cl₄], [L¹Co₂(OAc)₃], [L¹Zn₂(adamantyl carbonate)₂],
 5 [L¹Zn₂(pentafluorobenzoate)₂], [L¹Zn₂(diphenylphosphinate)₂], [L¹Zn₂(bis(4-methoxy)phenyl phosphinate)₂], [L¹Zn₂(hexanoate)₂], [L¹Zn₂(octanoate)₂],
 [L¹Zn₂(dodecanoate)₂], [L¹Mg₂(F₃CCOO)₂], [L¹Mg₂Br₂], [L¹Zn₂(C₆F₅)₂], [L¹Zn₂(C₆H₅)₂] and
 [L¹Zn₂(OiPr)₂], wherein L¹ is as illustrated above for L¹Zn₂OAc₂.
- 10 In some embodiments, when Z is absent or a group selected from -E-X(E)- or -E-X(E)E-, the catalyst system optionally comprises a compound [Y] which is capable converting the group -Z-R, wherein Z is absent or a group selected from -E-X(E)- or -E-X(E)E-, to a group -Z-R wherein Z is -E-.
- 15 The compound [Y] may be capable of converting the group -Z-R, wherein Z is absent or a group selected from -E-C(E)- or -E-C(E)E-, to a group -Z-R wherein Z is -E-. In other words, the compound [Y] may be capable of inserting into the bond between the metal atom in the metal complex [M] and the group -Z-R in order to switch the ligand attached to the metal atom from -R, -E-C(E)-R or E-C(E)-E-R to -E-R.

The compound [Y] may be a compound having a three, four or five membered saturated ring and at least one heteroatom selected from O, S or N. In preferred embodiments, the compound [Y] may be an epoxide, an aziridine, an episulfide, an oxetane, a thietane, an azetidine, a saturated furan, a saturated thiophene or a pyrrolidine.

5

In certain embodiments, the compound [Y] has the following formula:



wherein


A is O, S or NR^A ; (preferably A is O)

10

j is 1, 2, or 3;
 R^A is hydrogen, halogen, hydroxyl, alkoxy, aryloxy, heteroaryloxy, or aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl;

Each R^{A1} , R^{A2} , R^{A3} and R^{A4} is independently selected hydrogen, halogen, hydroxyl, nitro, alkoxy, aryloxy, heteroaryloxy, amino, alkylamino, imine, nitrile, acetylide, carboxylate or

15 optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl; or two or more of R^{A1} , R^{A2} , R^{A3} and R^{A4} can be taken together to form a saturated, partially saturated or unsaturated 3 to 12 membered, optionally substituted ring system, optionally containing one or more heteroatoms. For example, each R^{A1} , R^{A2} , R^{A3} and R^{A4} may be H; R^{A1} , R^{A2} and R^{A3} may be H and one or more R^{A4} may be aryl or aliphatic, preferably phenyl or alkyl; R^{A1} and R^{A4} may be H, and R^{A2} and R^{A3} may be taken together to form a six to 10 membered carbon ring (saturated, unsaturated or partially saturated. For example, the compound [Y] may be:



25

Preferred optional substituents of the groups R^{A1} , R^{A2} , R^{A3} and R^{A4} include halogen, nitro, hydroxyl, unsubstituted aliphatic, unsubstituted heteroaliphatic unsubstituted aryl,

unsubstituted heteroaryl, alkoxy, aryloxy, heteroaryloxy, amino, alkylamino, imine, nitrile, acetylide, and carboxylate.

5 In preferred embodiments, the compound [Y] is an epoxide. When the compound [Y] is an epoxide, it will be appreciated that it may be the same, or different, to the epoxide monomer to be polymerised. Preferably, the compound [Y] is an epoxide which is the same as the epoxide to be polymerised by the method of the first aspect.

10 In some embodiments of the catalyst of formula (IA), Z is absent, or is $-E-$; E is $-O-$, $-S-$, or NR^Z , wherein R^Z is H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl; and R is an optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or alkylheteroaryl. Preferably, Z is absent or is $-O-$, more preferably Z is absent.

15 Accordingly, preferred catalysts of formula (IA) include $[L^1Mg_2Cl_2(\text{methylimidazole})]$, $[L^1Mg_2Cl_2(\text{dimethylaminopyridine})]$, $[L^1Mg_2Br_2(\text{dimethylaminopyridine})]$, $[L^1Zn_2(C_6F_5)_2]$, and $[L^1Zn_2(C_6H_5)_2]$.

20 In a method of the second aspect of the invention, the initiator (CTA) may be present at a molar ratio of at least 1:1 relative to the catalyst of formula (I). For example, the molar loading of catalyst:initiator (CTA) is preferably 1:2 to 1:1000.

By "one-pot", it is meant that the multi-block copolymers comprising blocks A-B-A or B-A-B are formed *in situ*, in the presence of the catalytic system, without requiring any
25 sequential addition of monomer. In other words, all of the monomers are added to the reaction mixture, with the catalytic system, at the start of the reaction. The reaction will then selectively form multi-block copolymers from the pool of monomers available. It will be appreciated that inclusion of a multi-functional initiator is important in enable formation of tri-block copolymers in a one-pot process. It will be appreciated that, subsequent to the
30 formation of a multi-block copolymer comprising A-B-A or B-A-B, additional monomers and/or catalyst may be added to the reaction mixture, for example such that additional blocks are formed. For example, the method may comprise the step of adding additional monomer, selected from lactone, lactide; epoxide, anhydride, or carbon dioxide to the reaction mixture, subsequent to the formation of multi-block copolymer comprising A-B-A
35 or B-A-B.

The method of the second aspect of the invention may be carried out at a temperature of about 50 °C to about 200 °C, for example, from about 60 °C to about 140 °C, such as from about 80 °C to about 120 °C.

- 5 The method of the second aspect of the invention may be carried out under an inert atmosphere, for example under a nitrogen atmosphere.

It will be appreciated that the method of the second aspect of the invention may be used to prepare a multi-block copolymer as defined herein in relation to the first aspect of the
 10 invention. Accordingly, the method of the second aspect of the invention may form a multi-block copolymer comprising at least blocks A-B-A or B-A-B, wherein the multi-block copolymer is characterised by one or more of features (i) to (iii): (i) a degree of crystallinity (χ) of block A of no more than 20% as determined by DSC; and/or (ii) a degree of crystallinity (χ) of block A of no more than 20% as determined by WAXS; and/or (iii) a
 15 measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B. It will be appreciated that all embodiments described herein in relation to blocks A and B of the first aspect of the invention apply *mutatis mutandis* to the second aspect of the invention.

20 It will be appreciated that as an alternative to the one-pot method of the second aspect of the invention, a multi-block copolymer of the invention may be prepared by a sequential addition process for example as described in WO2014/184578, the contents of which are incorporated herein by reference.


25 In a third aspect, the invention provides a method for producing a multi-block copolymer comprising blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B comprises a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the multi-block copolymer is
 30 characterised by one or more of features (i) to (iii): (i) a degree of crystallinity (χ) of block A of no more than 20% as determined by DSC; and/or (ii) a degree of crystallinity (χ) of block A of no more than 20% as determined by WAXS; and/or (iii) a measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B, wherein the method comprises forming a reaction mixture comprising:

- 35 (a) forming a first block A or B by polymerizing first monomer or combination of monomers selected from
- (i). an epoxide and an anhydride;

- (ii). an epoxide and carbon dioxide; and
- (iii). a lactone and/or a lactide;

by contacting the monomer or combination of monomers in a reaction mixture with a catalytic system comprising a catalyst of formula (I) and an initiator;

- 5 (b) forming a multi-block copolymer comprising blocks A-B-A or B-A-B by adding second monomer or combination of monomers to the reaction mixture, wherein if the first monomer is (i) or (ii), the second monomer is (iii) and if the first monomer is a (iii), the second monomer is (i) or (ii) such that polymerisation occurs to form a multi-block copolymer comprising blocks A-B-A or B-A-B,
- 10 wherein the catalyst is of formula (I):



wherein:

[M] is a metal complex having at least one metal atom M coordinated by a ligand system;
M is Zn, Cr, Co, Mn, Mg, Fe, Ti, Ca, Ge, Al, Mo, W, Ru, Ni or V;

- 15 Z is absent, or is independently selected from $-E-$, $-EX(E)-$, or $-EX(E)E-$,
each E is independently selected from O, S or NR^Z , wherein R^Z is H, or optionally
substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylaryl or
alkylheteroaryl;
X is C or S
- 20 R is hydrogen, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic,
aryl, heteroaryl, alkylaryl, alkylheteroaryl, silyl or a polymer; and when Z is absent, R may
additionally be selected from halide, phosphinate, azide and nitrate; and
wherein the initiator is a multifunctional protic compound comprising at least two moieties
independently selected from $-OH$, $-SH$, $-C(O)OH$ or $-NH-$, or wherein the initiator is
- 25 water.

It will be appreciated that all embodiments described herein in relation to blocks A and B of the first aspect of the invention and the method of the second aspect of the invention apply *mutatis mutandis* to the third aspect of the invention.

- 30 In a fourth aspect of the invention, there is provided a polymer obtainable from the method according to the third aspect of the invention.

In a fifth aspect of the invention, there is provided a polymer of the first, second or fourth aspects of the invention for use as a packaging material, a biomedical material, a sealant,

an adhesive, an engineering material, a synthetic fibre, an automobile part or a foam or the like.

A wide range of mechanical properties can be achieved by simply changing the monomer composition used to form a multi-block copolymer of the invention, from tough plastics, shape memory materials to thermoplastic elastomers. For example, for tough plastics (e.g. wherein the weight content of block B, with reference to block A, is 55wt% or more such as PDL-*b*-PCHPE-*b*-PDL with 59-100 wt% of PCHPE), the young's modulus can be tailored from 223 MPa to 6600 MPa. Therefore, it is possible to be applied to packaging materials (like LDPE), synthetic fiber (like Nylon) or engineering plastics (like Acrylonitrile Butadiene Styrene, ABS). Shape memory materials (e.g. wherein the weight content of block B, with reference to block A, is 35-50wt%, such as PDL-*b*-PCHPE-*b*-PDL with ca 42 wt% of PCHPE) can be used in biomedical applications, such as self-tightening knots, orthopedic surgery, intravenous cannula, self-adjusting suture, vascular stent, etc. sealants, adhesives. Thermoplastic elastomers (e.g. wherein the weight content of block B, with reference to block A, is no more than 30wt%, such as PDL-*b*-PCHPE-*b*-PDL with ca 26 wt% or less of PCHPE) can replace the SBS TPE can be used in automobile parts, shoe soles, adhesives, electrical cable jacket, etc.

Examples

Abbreviations

	ATR-IR	attenuated total reflectance – infra red
25	CHD	1,2-cyclohexane diol
	CHO	cyclohexene oxide
	vCHO	4-Vinyl-1-cyclohexene 1,2-epoxide
	DCM	dichloromethane
	DSC	differential scanning calorimetry
30	ϵ -DL	ϵ -decalactone
	<i>rac</i> -LA	<i>rac</i> -lactide
	PA	phthalic anhydride
	PCHPE	poly(cyclohexylene phthalic)ester
	PDL	polydecalactone
35	PCHC	poly(cyclohexylene carbonate)
	PvCHC	poly(vinylcyclohexenecarbonate)
	ROCOP	ring opening copolymerization

ROP	ring opening polymerization
SAXS	small angle X-ray scattering
SEC	size exclusion chromatography
SEC-MALLS	SEC-multiple-angle-laser light scattering
5 THF	tetrahydrofuran
TOF	turnover frequency
WAXS	wide-angle X-ray scattering

SEC: The molecular weights and dispersities were characterized using an Agilent PL
 10 GPC-50 instrument, with GPC grade THF as the eluent at a flow rate of $1.0 \text{ mL} \cdot \text{min}^{-1}$ at 40°C . Two Polymer labs Mixed D columns were used in series. Near monodispersed polystyrene standards were used to calibrate the instrument. The polyesters were dissolved in GPC grade THF and filtered prior to analysis. Another GPC, Shimadzu LC-20AD, was used to characterize the molecular weights and dispersities using MALLS
 15 detector, with two Mixed Bed PSS SDV linear S columns and THF as the eluent, at a flow rate of $1.0 \text{ mL} \cdot \text{min}^{-1}$ at 30°C . The MALLS detector was calibrated by polystyrene standards and the dn/dc values were measured using an external RID detector (Knauer) with at least 3 different concentrations of the polymer to be analysed. Crude polymers were used for SEC characterization unless stated otherwise.

20

NMR: ^1H , $^{13}\text{C}\{^1\text{H}\}$, $^{31}\text{P}\{^1\text{H}\}$ and 2D NMR (HSQC, DOSY) spectra were recorded using a Bruker AV 400 MHz spectrometer at room temperature (unless otherwise stated). All the $^{31}\text{P}\{^1\text{H}\}$ NMR data used for end group calculation were recorded with extended relaxation delay (d_1) of 15 s (longest t_1 was determined to be 3s).

25

MALDI-ToF MS: MALDI-ToF spectra of polyesters were carried out on Waters/Micromass MALDI micro MX spectrometer. The polymer samples were dissolved in THF at a concentration of $1 \text{ mg} \cdot \text{mL}^{-1}$. Trans-2-[3-(4-tert-butylphenyl)-2-methyl-2-propenylidene]malononitrile (DCTB) was used as the matrix at a concentration of 10
 30 $\text{mg} \cdot \text{mL}^{-1}$ in THF. Potassium trifluoroacetate (KTFA) was used as the cationizing agent at a concentration of $1 \text{ mg} \cdot \text{mL}^{-1}$. The solutions of polymer, matrix and salt were mixed in a ratio of 1/1/1 (v/v/v), respectively. The mixed solution was spotted on a stainless steel MALDI plate repeatedly (5 times) and left to dry in the fume hood, overnight. The spectrum was recorded using reflectron mode.

35

In situ ATR-IR Spectroscopy: The polymerizations were monitored using a Mettler-Toledo ReactIR 4000 spectrometer equipped with a MCT detector and a silver halide DiComp probe.

- 5 Thermal Analyses: Thermal properties were measured using DSC Q2000 (TA Instruments, UK). A sealed empty crucible was used as a reference, and the DSC was calibrated using indium. Samples of multi-block copolymers, such as PDL-PCHPE-PDL, were heated from room temperature to 125 °C at a rate of 10 °C/min under helium flow and kept at 125 °C for 2 min to erase the thermal history. Then, the samples were cooled
10 to -100 °C at a rate of 10 °C/min and kept at -100 °C for another 2 min followed by a heating procedure from -100 °C to 130 °C at a rate of 10 °C/min. Each sample was run for three heating-cooling cycles. For new block copolymers, the temperature range for the experiments should be determined after evaluation by TGA. The upper limit on the temperature should be below the on-set of thermal degradation.

15

The glass transition temperatures (T_g) reported are taken from the third cycle. T_g values are taken from the 'steps' observed from the DSC trace, which correspond to the changes in heat capacity. The exact T_g value was taken to be the temperature in the middle of the incline of the 'steps' determined by the T_g transition function in the software (universal

20

analysis, version 4.3A).

- Crystallinity (χ) of block A may be calculated using the same DSC procedure. If the polymer sample contains any crystalline material a melting peak is observed. If no melting peak is observed crystallinity is assumed at zero percent. If a melting point is
25 observed, crystallinity may be calculated via the following equation:

$$\chi = \frac{\Delta H_m}{\Delta H_m^0} \times 100\%$$

Where ΔH_m is the integral of the melting peak using the integral function provided in the software (universal analysis, version 4.3A), with the unit of J/g; ΔH_m^0 is the amount of heat when 1 gram of 100% crystallized polylactone or polylactide is melted with the unit of J/g.

30

The value of ΔH_m^0 can be calculated by the extrapolation of the ΔH_m of polylactone or polylactide standards (with known crystallinity) to complete crystallinity. The ΔH_m values of different polylactone or polylactide standards are plotted against the crystallinity (χ) of these standards. Then the plots are extrapolated to a crystallinity of 100 %, where the

corresponding ΔH_m value is defined as the ΔH_m° . In some instances, the value of ΔH_m° can be found in literature (Crescenzi.V, G. Manzini, Calzolari.G and C. Borri, Eur. Polym. J., 1972, 8, 449).


- 5 Crystallinity (χ) may also be determined using a wide-angle X-ray scattering (WAXS) procedure as follows. CuK α ($\lambda = 0.154$ nm) X-ray is produced by a rotating anode X-ray generator (e.g. Rigaku ROTAFLEX RTP300) with a Cu target and a Ni filter. The goniometer was calibrated with NaCl to within 0.5° . The samples were continuously scanned from 4 to 50° (or corresponding vector q) at a rate of $1 \text{ deg} \cdot \text{min}^{-1}$. The X-ray data
10 were first modelled using a form which include Lorentzian line shapes for the crystalline peaks and a lorentzian plus a quadratic form for the amorphous scattering. Then, the data were fit using the CPlot nonlinear least-squares fitting routine over the scattering range. The crystallinity (χ) is calculated by this equation:

$$\chi = A_c/A_a \times 100\%$$

- 15 where A_a is the integral of the amorphous contribution and A_c is the integral of the crystalline peaks (described in W. Hu *et al.*, *Macromolecules* 2002, 35, 5013-5024 or P. J. Rae *et al*, *Polymer* 2004, 45, 7615-7625, the contents of which are incorporated herein by reference).
- 20 The molecular weight (M_n , number average molecular weight) of polymers can be measured by Gel Permeation Chromatography (GPC) using, for example, a GPC-60 manufactured by Polymer Labs, using THF as the eluent at a flow rate of 1 ml/min on Mixed B columns, manufactured by Polymer Labs. Narrow molecular weight polystyrene standards can be used to calibrate the instrument.
- 25 All solvents and reagents were obtained from commercial sources (Aldrich and Fischer) and used as received unless stated otherwise. Cyclohexene oxide (CHO) was fractionally distilled over calcium hydride once prior to use and stored under an inert atmosphere. 4-vinyl-1-cyclohexene 1,2-epoxide (vCHO) was dried over calcium hydride prior to the distillation under reduced pressure and stored under N_2 protection at -35°C . ϵ -
30 Decalactone (ϵ -DL) was dried over calcium hydride and stored under nitrogen. THF and toluene were distilled from sodium and stored under nitrogen. Phthalic anhydride (PA) was purified via dissolving in benzene and filtering the insoluble impurity (phthalic acid, proved by ^1H NMR) followed by a recrystallization from CHCl_3 and sublimation once. Trans-1,2-cyclohexanediol (CHD) was recrystallized from ethyl acetate and kept under a

nitrogen atmosphere. 2-Chloro-4,4,5,5-tetramethyl dioxaphospholane and 1,5,7-triazabicyclo[4.4.0]dec-5-ene (TBD) were used as received.

Preparation of di-zinc complex 1



5

The ligand H_2L may be prepared as described in WO2009/130470, the entire contents of which are incorporated herein by reference. To a precooled THF solution (-40°C , 5 mL) of H_2L (318.0 mg, 0.57 mmol.) was added a pre-cooled THF solution (-40°C , 2 mL) of diphenyl zinc (253 mg, 1.15 mmol.). After a few minutes the solution became cloudy. The mixture was allowed to react for 20 h at 25°C and as, then, the produce was filtered. It was washed with cold THF (10 mL) and was isolated as a white powder (381 mg, 0.46 mmol., 81% yield).

^1H NMR (TCE- d_2 , 403 K) δ : 7.40 (br, aryl-H, 6H), 7.00 (br, aryl-H, 4H), 5.22-3.90 (br, 4H), 3.60-2.30 (br, 16 H), 1.36 (br, ^tBu , 18H), 1.31 (br, CH_3 , 6H), 1.06 (br, CH_3 , 6H). ^{13}C NMR (TCE- d_2 , 403 K) δ : 128.1, 126.8, 63.5, 56.8, 31.4, 27.9 and 21.5. (To avoid signals being broadened due to the different complex conformations at low temperature, NMR was conducted at 403 K) Elemental Analysis: Calcd. (%): C, 66.10; N, 7.72; H, 6.70; Found (%): C, 66.03, H, 7.72, N, 6.66.

20

Complex **1** shows good performance for epoxide/anhydride ROCOP, with results for PA/CHO ROCOP using complex 1 and CHD shown in Table 1 below.

#	1: diol ^a	$M_{n,\text{theo}}$ ^b	$M_{n\text{SEC-PS}}$ ^c (Đ)	$M_{n\text{SEC-MALLS}}$ ^d (Đ)
1	1:2	12.3	5.3 (1.33)	9.3 (1.03)
2	1:4	6.2	2.9 (1.29)	5.2 (1.02)
3	1:6	4.1	2.3 (1.33)	3.6 (1.10)
4	1:8	3.1	1.8 (1.27)	2.9 (1.06)
5	1:10	2.5	1.6 (1.32)	2.5 (1.07)

- ^{a)}[1]:[PA]:[CHO] = 1:100:800, 100 °C, 3-4 h, PA conversion >99%. Diol refers to 1,2-cyclohexane diol (CHD); ^{b)}Determined on the basis of $\{([PA] + [CHO]) \times (\text{conversion of PA})\} / [CHD]$, with units of $\text{kg} \cdot \text{mol}^{-1}$; ^{c)}Determined by SEC calibrated using narrow MW polystyrene (PS) standards, with units of $\text{kg} \cdot \text{mol}^{-1}$; ^{d)}Determined by SEC-MALLS in THF
- 5 $(dn/dc = 0.133 \pm 0.001 \text{ mL} \cdot \text{g}^{-1})$, with units of $\text{kg} \cdot \text{mol}^{-1}$.

- TOF values of 25 h^{-1} and an excellent selectivity (>99%) for polyester (were observed). There was a high degrees of polymerization control, with polyesters having molecular weights (MW) which can be predicted from the quantity of added diol and narrow
- 10 dispersities (≤ 1.30), features which are indicative of fast and reversible chain transfer reactions. The polymerization control is further demonstrated by MALDI-ToF analysis which shows a single series of perfectly alternating polyester chains, end-capped by α , ω -dihydroxyl groups.
- 15 Complex 1, with CHD, was also tested, as a catalyst for the ROP of ϵ -DL, using CHO as the solvent. Results are shown in Table 2 below.

#	1: diol ^a	$M_{n, \text{theo}}$ ^b	$M_{n \text{SEC-PS}}$ ^c (Đ)	$M_{n \text{SEC-MALLS}}$ ^d (Đ)
1	1:2	17.0	14.0 (1.16)	13.4 (1.07)
2	1:4	8.5	7.8 (1.10)	6.8 (1.06)
3	1:6	5.7	6.7 (1.12)	4.7 (1.05)
4	1:8	4.3	5.3 (1.11)	3.5 (1.11)
5	1:10	3.4	4.3 (1.12)	3.0 (1.05)

- ^{a)}[1]:[ϵ -DL]:[CHO] = 1:200:800, 100 °C, 1.25 h, ϵ -DL conversion >95%. Diol refers to 1,2-cyclohexane diol (CHD); ^{b)}Determined on the basis of $\{[\epsilon\text{-DL}] \times (\text{conversion of } \epsilon\text{-DL})\} / [CHD]$, with units of $\text{kg} \cdot \text{mol}^{-1}$; ^{c)}Determined by SEC calibrated using narrow MW polystyrene (PS) standards, with units of $\text{kg} \cdot \text{mol}^{-1}$; ^{d)}Determined by SEC-MALLS, in THF,
- 20 $(dn/dc = 0.054 \pm 0.001 \text{ mL} \cdot \text{g}^{-1}$ for entry 1, $0.067 \pm 0.001 \text{ mL} \cdot \text{g}^{-1}$ for entry 2 and $0.072 \pm 0.002 \text{ mL} \cdot \text{g}^{-1}$ for entry 3-5), with units of $\text{kg} \cdot \text{mol}^{-1}$.

- Good activity was observed, with TOF values of 160 h^{-1} and no evidence for any epoxide
- 25 homopolymerization or insertion into the PDL chain.

Figure 1 illustrates the ROCOP and ROP reactions catalyzed by complex 1.

Example 1: Sequence controlled chemoselective terpolymerization of PA/CHO/ ϵ -DL using complex 1

Mixtures of lactone (ϵ -DL), epoxide (CHO) and anhydride (PA) monomers were reacted with the catalyst system comprising complex 1 and CHD. The terpolymerizations were all successful and an unexpected monomer selectivity was observed, resulting in the controlled formation of only ABA type block copolyesters. The chemoselective sequence controlled polymerisation is illustrated in Figure 2. Typical preparations of PDL-b-PCHPE-b-PDL triblock copolyesters are recited below.

- 10 To afford PDL-b-PCHPE-b-PDL triblock copolyesters with 33 wt% of PCHPE the complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (93.0 mg, 0.63 mmol), ϵ -DL (325.0 μ L, 1.88 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μ L, 8.91 mmol), under N₂ protection, in a screw-cap vial charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[ϵ -DL] was 1/2/800/50/100.

- To afford PDL-b-PCHPE-b-PDL triblock copolyesters with 42 wt% of PCHPE, the complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (186.0 mg, 1.26 mmol), ϵ -DL (650.0 μ L, 3.76 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μ L, 8.91 mmol), under N₂ protection, in a screw-cap vial charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[ϵ -DL] was 1/2/800/100/200.

- To afford PDL-b-PCHPE-b-PDL triblock copolyesters with 59 wt% of PCHPE, the complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (186.0 mg, 1.26 mmol), ϵ -DL (325.0 μ L, 1.88 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μ L, 8.91 mmol), under N₂ protection, in a screw-cap vial charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[ϵ -DL] was 1/2/800/100/100.

- To afford PDL-b-PCHPE-b-PDL triblock copolyesters with 81 wt% of PCHPE, the complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (279.0 mg, 1.89 mmol), ϵ -DL (162.5 μ L, 0.94 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μ L, 8.91 mmol), under N₂ protection, in a screw-cap vial charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[ϵ -DL] was 1/2/800/150/50.

In each case, the polymerization was terminated by cooling down to ambient temperature. Crude polymer was isolated by removal of the excess volatiles (CHO). Purified polyesters can be obtained by precipitation using cold MeOH.

5

Results obtained from polymerizations utilizing various monomer mixtures are show in Table 3 below.

#	[PA]:[ε-DL] ^a	% PCHPE ^b	M _{ntheo} ^c	M _{nexp} ^d	Đ ^d	T _g /°C ^e
1	0:100	0	8.5	6.9	1.20	-58
2	50:100	33	18.9	12.3	1.25	-49
3	100:200	42	28.0	15.9	1.21	-49;57
4	100:100	59	22.4	12.0	1.15	-47; 61
5	150:50	81	22.7	11.9	1.29	55
6	100:0	100	12.3	5.3	1.33	97

^a[1]:[CHD]:[CHO] = 1:2:800, 100 °C, PA and ε-DL conversion >95%; ^bWeight content of PCHPE block in the polyester (PDL-b-PCHPE-b-PDL); ^cDetermined by $\{([PA] + [CHO]) \times$
 10 (conversion of PA) + [ε-DL] × (conversion of ε-DL)} / [CHD] with units of kg·mol⁻¹;
^dDetermined by SEC using polystyrene calibration, with units of kg·mol⁻¹. MALLS is not
 suitable for such block copolymer analysis. [Described by Gores et al. in *Chromatography*
of Polymers (book) or Keller et al., *Journal of Liquid Chromatography & Related*
Technologies, 2010, 33, 1587-1600.] ^eDetermined after three heating-cooling cycles, on
 15 the third cycle.

The terpolymerizations were monitored by ATR-IR spectroscopy which showed that initially epoxide/anhydride ROCOP occurred, as shown by the disappearance of the diagnostic PA resonance at 1790 cm⁻¹ and the growth of the characteristic polyester
 20 (PCHPE) resonance (1065-1068 cm⁻¹). Figure 3 shows the ATR-IR spectrum acquired for Table 3, entry 2.

During this time, there was no change to any resonances associated with the lactone (ε-DL), a finding confirmed by aliquot analysis using ¹H NMR spectroscopy which only
 25 showed signals for perfectly alternating polyester (PCHPE) and residual ε-DL. Once the PA was consumed, as confirmed independently by ¹H NMR spectroscopy, and in the presence of excess CHO, the reaction entered the second phase whereby ε-DL ROP occurred leading to triblock polyester formation. During this stage, the ATR-IR monitoring


showed the decrease of the ϵ -DL resonance, at 1735 cm^{-1} , accompanied by the growth of the block of poly(decalone) as signalled by its resonance at 1190 cm^{-1} . The IR absorptions were all independently confirmed in control experiments using pure, isolated monomers/polymers.

5

The monomer sequence selectivity would not be expected on the basis of the TOF values for the two processes occurring independently. Figure 4 illustrates the key intermediates present during polymerization. P represents the growing polymer chain. The different rate of insertion of monomers into the zinc alkoxide intermediate, which is common to both
10 catalytic cycles, is considered to be responsible for the selectivity. Accordingly, the rate of PA insertion into the Zn-alkoxide bond is significantly faster than the insertion of ϵ -DL (i.e. $k_1 \gg k_3$). It is also relevant that the zinc-carboxylate intermediate, formed by PA insertion, does not react with lactones. Thus, the zinc-carboxylate intermediate can only react slowly with CHO to (re)form the zinc-alkoxide intermediate. Only, after the complete conversion
15 of PA and in the presence of some epoxide, does the zinc-alkoxide intermediate catalyze the ϵ -DL ROP.

In general terms, the nature of the polymer blocks formed in a method of the invention may be controlled depending on the moiety at the end of the growing polymer chain
20 attached to the metal complex [M], as well as the relative rates (k) at which monomers insert into the bond between the metal complex and the ligand $-Z-R$. Relative rates of insertion of monomers can be determined by exposing one or more of the monomers to a catalyst of formula (I), and monitoring the rate at which the monomer(s) is consumed, or the rate at which polymer is produced. This can be done, for example, using quantitative
25 spectroscopic or analytic techniques which are well known in the art, such as attenuated total reflectance IR spectroscopy (ATRIR), NMR, optical absorption spectroscopy, IR, or titration.

For example, in the scheme below, k_1 represents the rate of insertion of anhydride or CO_2 , k_2 represents the rate of insertion of epoxide and k_3 represent to rate of insertion of
30 lactone/lactide. P represents the growing polymer chain, and its' structure will depend on the identity of the monomers being polymerised. It will be understood that the relative rates of insertion will affect the order in which the blocks are produced.



In certain instances, k_1 may be faster than k_2 and k_3 may be faster than k_2 .

- To confirm the ABA polymer structure, aliquots were analyzed by SEC just before the
- 5 complete conversion of PA (ca. 95%) and after the propagation of PDL block (ca. 96% conv. of ϵ -DL) (Figure 5a). It is quite clear that after ϵ -DL ROP the polymer has a higher MW and that in both cases distributions are monomodal, with narrow dispersities. Since the block formed by ROCOP (PCHPE) has an aromatic repeat unit, analysis using SEC with a UV-detector also served to confirm that the PCHPE and PDL blocks were attached
- 10 to one another. Meanwhile, $^{31}\text{P}\{^1\text{H}\}$ NMR spectroscopy was used to distinguish the two different hydroxyl groups of the polymer blocks (from PCHPE and PDL, respectively) on the basis of their chemical shifts after reaction with excess 2-chloro-4,4,5,5-tetramethyl dioxaphospholane (using biphenol A as an internal standard). The spectra showed that there was a shift from a peak at 147.1 ppm, assigned to PCHPE end groups, after the first
- 15 phase of polymerization, to 149.2 ppm, assigned exclusively to PDL end groups for the ABA triblock. Furthermore, ^1H DOSY NMR spectrum showed that all NMR signals belong to a single copolymer with the same diffusion coefficient; in contrast to a blend of PCHPE/PDL, of near equivalent MW, which showed two different diffusion coefficients.
- 20 The copolymers showed T_g values tuneable over the range -59 to 61 °C. The homopolymers are both amorphous, with T_g values of -58 °C (PDL) and 97 °C (PCHPE), respectively. A blend of them showed identical T_g values to the homopolymers. In contrast, the copolyesters with low (33 wt%) or high (81 wt%) PCHPE compositions showed only a

single T_g , close to that of the dominant block material (PDL or PCHPE). Where the block composition was more evenly balanced (42-59 wt% PCHPE), two T_g values were observed, suggesting phase separation occurred.

5 Example 2: Sequence controlled chemoselective terpolymerization of PA/vCHO/ ϵ -DL using complex 1 to afford PDL-b-PvCHPE-b-PDL triblock copolyesters.

The complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (186.0 mg, 1.26 mmol), ϵ -DL (325.0 μ L, 1.88 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in vCHO) were dissolved in vCHO (884.0 μ L, 8.91 mmol), under N₂ protection, in a screw-cap vial charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h. The relative molar ratio of [1]/[CHD]/[vCHO]/[PA]/[ϵ -DL] was 1/2/800/100/100. The polymerization was terminated by cooling down to ambient temperature. The crude polymer was isolated by removal of the excess volatiles (CHO).
10
15 Purified polyesters can also be obtained by precipitation using cold MeOH. Results obtained from this polymerization are shown in Table 4, entry 1 below.

The terpolymerizations were monitored by ATR-IR spectroscopy which showed that initially epoxide/anhydride ROCOP occurred, as shown by the disappearance of the diagnostic PA resonance at 1790 cm⁻¹ and the growth of the characteristic polyester (PCHPE) resonance (1065-1068 cm⁻¹).
20

During this time, there was no change to any resonances associated with the lactone (ϵ -DL), a finding confirmed by aliquot analysis using ¹H NMR spectroscopy which only showed signals for perfectly alternating polyester (PCHPE) and residual ϵ -DL. Once the PA was consumed, as confirmed independently by ¹H NMR spectroscopy, and in the presence of excess CHO, the reaction entered the second phase whereby ϵ -DL ROP occurred leading to triblock polyester formation. During this stage, the ATR-IR monitoring showed the decrease of the ϵ -DL resonance, at 1735 cm⁻¹, accompanied by the growth of the block of poly(decactone) as signalled by its resonance at 1190 cm⁻¹. The IR absorptions were all independently confirmed in control experiments using pure, isolated monomers/polymers.
25
30

35 Example 3: Sequence controlled chemoselective terpolymerization of PA/CHO/*rac*-LA using complex 1 to afford PLA-b-PCHPE-b-PLA triblock copolyesters.

The complex **1** (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (186.0 mg, 1.26 mmol), *rac*-LA (271.0 mg, 1.88 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μ L, 8.91 mmol), under N₂ protection, in a screw-cap vial charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[*rac*-LA] was 1/2/800/100/100. The polymerization was terminated by cooling down to ambient temperature. The crude polymer was isolated by removal of the excess volatiles (CHO). Purified polyesters can also be obtained by precipitation using cold MeOH. Results obtained from this polymerization are shown in Table 4, entry 2 below.

10

Before the full conversion of PA, ¹H NMR spectroscopy only showed signals for perfectly alternating polyester (PCHPE) and residual *rac*-DL. Once the PA was consumed, as confirmed by ¹H NMR spectroscopy, and in the presence of excess CHO, the reaction entered the second phase whereby *rac*-DL ROP occurred leading to triblock polyester formation. Results obtained from this polymerization are shown in Table 4, entry 2 below.

15

Table 4.

#	Monomer combination	M_{nexp} of the first aliquot (Đ)	M_{nexp} (Đ)
1	PA/vCHO/ε-DL	4.2 (1.32)	12.8 (1.34)
2	PA/CHO/ <i>rac</i> -LA	2.5 (1.16)	6.0 (1.53)

20 Example 4: Synthesis of [PDL-b-PCHPE-b-PDL]_n multi-block copolyesters

25

Triblock copolyesters synthesized according to example 1 were chain extended to reach higher molecular weight (MW), according to the typical synthesis below. This resulted in the formation of multi-block copolyesters [PDL-b-PCHPE-b-PDL]_n with urethane linkages.

Typically, PDL-b-PCHPE-b-PDL triblock copolyester (3000.0 mg, 1.35×10^{-2} mmol), Sn(Oct)₂ (24.0 μ L, 4.73×10^{-2} mmol) and 4,4'-Methylenebis(phenyl isocyanate) (37.0 mg, 1.48×10^{-2} mmol) were dissolved in toluene (20 mL) under N₂ protection, in a schlenk tube charged with a stir bar. The mixture was then heated to 60 °C and left to react, under an inert atmosphere, for 2.0 h. Pure multi-block copolyester was obtained by precipitating using MeOH.

30

As shown in Table 5, the MWs are approximately doubled in all three samples, while the molecular weight distribution remains below 1.5. This observation suggests the successful chain extension in all three samples. SAXS was employed to characterized the phase-separated structure of the [PDL-*b*-PCHPE-*b*-PDL]_n multi-block copolyesters. Strong and sharp scattering peaks were observed in all three samples, confirming the nanophase separation structures. The 2θ of peaks for #1 #3 were identified to be 0.605°, 0.705° and 0.605°, respectively. Therefore, the size of the separated phases were calculated to be 14.6 nm, 12.4 nm and 13.9 nm, respectively.

Table 5. Chain extension reaction of the triblock copolyesters using MDI.

#	[PA]:[ε-DL]	wt% PCHPE	$M_{n\text{theo}}$ (kDa) ^a	$M_{n\text{exp}}$ (kDa) ^b	Đ	M_n (kDa) after chain extension (Đ) ^c	T_g (°C) ^d
1	50:250	26	47.2	34.6	1.19	56.6 (1.32)	-53
2	50:100	42	29.3	22.3	1.22	44.8 (1.47)	-49;57
3	50:50	59	20.8	19.4	1.21	48.1 (1.50)	-47;61

a) Determined by $\{([PA] + [CHO]) \times (\text{conversion of PA}) + [\epsilon\text{-DL}] \times (\text{conversion of } \epsilon\text{-DL})\}/[CHD]$; *b)* Determined by SEC calibrated using narrow MW polystyrene standards; *c)* Chain extension reaction was catalyzed by Sn(Oct)₂ with MDI as the chain extension agent at 60 °C; *d)* determined by DSC.

Example 5: Penta/Heptablock Copolyester: (PDL-*b*)-PCHPE-*b*-PDL-*b*-PCHPE-*b*-PDL-*b*-PCHPE-(*b*-PDL)

The block number of the block copolyesters is not limited to triblock. Block copolyesters with higher block number (such pentablock, heptablock, etc.) can also be prepared via a sequential addition method.

Typically, pentablock block copolyester (Table 6, entry 3) is synthesized according to the following procedure. Complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (186.0 mg, 1.26 mmol), ε-DL (410.0 μL, 2.52 mmol) and a stock solution of CHD (116.0 μL; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μL, 8.91 mmol), under N₂ protection, in an ampoule charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h to reach the full conversion of phthalic anhydride and ε-DL. Then additional phthalic anhydride (93.0 mg, 6.3×10^{-1} mmol) was added into the ampoule under N₂ flow. The mixture was allowed to react for another 2.0 h under N₂ protection at 100 °C. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[ε-DL]/[PA(2nd

addition)] was 1/2/800/100/200/50. The polymerization was terminated by cooling down to ambient temperature. The crude polymer was isolated by removal of the excess volatiles (CHO). Purified polyesters can also be obtained by precipitation using cold MeOH.

- 5 Typically, heptablock block copolyester (Table 6, entry 4) is synthesized according to the following procedure. Complex 1 (10.0 mg, 1.25×10^{-2} mmol), phthalic anhydride (186.0 mg, 1.26 mmol), ϵ -DL (325.0 μ L, 1.88 mmol) and a stock solution of CHD (116.0 μ L; 24.0 mg·mL⁻¹ in CHO) were dissolved in CHO (884.0 μ L, 8.91 mmol), under N₂ protection, in an ampoule charged with a stir bar. The mixture was then heated to 100 °C and left to react, under an inert atmosphere, for 4.0 h to reach the full conversion of phthalic anhydride and ϵ -DL. Then additional phthalic anhydride (93.0 mg, 6.3×10^{-1} mmol) and ϵ -DL (410.0 μ L, 2.52 mmol) was added into the ampoule under N₂ flow. The mixture was allowed to react for another 3.0 h under N₂ protection at 100 °C. The relative molar ratio of [1]/[CHD]/[CHO]/[PA]/[ϵ -DL]/[PA(2nd addition)]/[ϵ -DL(2nd addition)] was 1/2/800/100/200/50/200. The polymerization was terminated by cooling down to ambient temperature. The crude polymer was isolated by removal of the excess volatiles (CHO). Purified polyesters can also be obtained by precipitation using cold MeOH.

- The same sequential addition method described above can be applied to the preparation of block copolyester with more block numbers *via* repeatedly sequential addition.

Table 6. Molecular weight of block copolyesters with different block numbers.

#	block number	$M_{nSEC-PS}$ (Đ) ^a
1	monoblock	5.6 (1.29)
2	triblock	22.2 (1.26)
3	pentablock	25.4 (1.23)
4	heptablock	40.0 (1.31)

^a) Determined by SEC using polystyrene calibration, with units of kg·mol⁻¹.

- 25 Example 6: Tensile tests of [PDL-b-PCHPE-b-PDL]_n multi-block copolyesters with different composition

- Samples were prepared for tensile tests as follows. Solvent-cast polyester sheet was prepared from DCM solutions (2.2 g multi-block copolyester in 50 mL of DCM) in a Teflon mold. The solvent was slowly evaporated in a fume hood at room temperature for 2

weeks. Dumbbell-shaped sample bars were then cut out from the polyester sheet (35 mm in length, 2.1 mm in width and 0.4 mm in thickness) using a Zwick Punch (Zwick D-7900, Ulm-Einsingen Type 7102, Werk-Nr. 85688) with cutting blades. Mechanical properties including strength, elongation and Young's modulus were measured at ambient
5 temperature and humidity (21.8 °C and 21 %) on a Linkam TST350 Tensile Stress Tester instrument at 10 mm/min extension rate.

Different polyesters, such as [PDL-*b*-PCHPE-*b*-PDL]_n multi-block copolyester, PDL, PCHPE homopolyester and a blend of PDL/PCHPE, were used to prepare polyester
10 sample bars via solvent casting method in a Teflon mold. However, sample bars which are suitable for tensile test can only be made from PCHPE-*b*-PDL multi-block copolyester. PDL cannot sustain its shape due to its low T_g and amorphous nature. PCHPE is too brittle to be taken out of the mold and breaks easily upon cutting. The blend of PDL/PCHPE exhibits the same physical status as PDL homopolyester. Therefore, only
15 sample bars made from [PDL-*b*-PCHPE-*b*-PDL]_n multi-block copolyester were suitable for the tensile test. For block copolymers with phase-separated structure, the ratio between different blocks plays a role in determining the mechanical properties. To evaluate the mechanical properties of all three samples listed in Table 5 (#1-3), tensile tests were conducted.

20 The strain-stress curve of #1 (with 26 wt% of PCHPE block) exhibits the same shape as an elastomer (see Figure 7). No yield point can be observed. Also, the rather low Young's modulus (1.4 MPa) and residual strain ($\epsilon_r = 26\%$) after retraction demonstrate its excellent elasticity. However, due to the limited track length of the tensile tester used for this
25 experiment, only a 'maximum' strain of ca. 450 % was recorded rather than the strain at break. On the basis of the elastomer-like behaviour, it is reasonable to assume that #1 has an island-like phase-separated structure (PDL block as the matrix).

The stress-strain curve of the #2 displays a tensile behaviour similar to plastics rather than
30 elastomers before the strain reaches 100 % (an obvious yield point and yield stage can be observed in Figure 7). The Young's modulus was also derived from the initial slope of the stress-strain curve to be 65 MPa (one order of magnitude higher than #1) with a strain of 12% at the yield point. Interestingly, when the strain is above 100 %, the material exhibits similar strain-stress behaviour as elastomers. During the following retraction test, the
35 strain decreased to 205 % after being stretched to ca. 450 %. Moreover, if the sample bar was relaxed freely overnight, the residual strain can further decrease to ca. 100 %. This observation reveals that #2 performs as plastics at low strain range (0 ~ 100 %), while

behaves similar to elastomers at high strain range (> 100 %). As for #1, due to the limitation of the tensile tester, the maximum strain can only be recorded as 450 %. In order to roughly estimate the elongation at break, one sample bar was stretched uniaxially by hands to reach the break point and the elongation at break was recorded to be ca. 800 %.

When the weight content of PCHPE reaches 59 wt% (#3), the block copolyester exhibits the mechanical properties of plastics as indicated by the stress-strain curve (see Figure 7). A relatively high young's modulus (223 MPa) was recorded and a yield point appeared at the strain of 9 %. The sample bar broke at the strain of ca. 350 %, therefore no retraction test was carried out to measure the residual strain. Take the high PCHPE weight content and the plastics-like mechanical properties into account, it is reasonable to assume that #3 has an island-like phase-separated structure (PCHPE block as the matrix).

The mechanical properties of [PDL-b-PCHPE-b-PDL]_n multi-block copolyesters with different compositions are summarized in Table 7 below.

#	wt% PCHPE	Young's modulus (MPa)	ϵ at yield point (%)	ϵ_r (%) ^d	ϵ at break (%)
1	26	1.4	N.A. ^a	26	N.A. ^c
2	42	64	12	205	N.A. ^c
3	59	223	9	N.A. ^b	350

^{a)} no yield point was observed in this sample; ^{b)} retraction test was not carried out due to the breakage at 350 %; ^{c)} the track of the tensile tester used for this experiment was not long enough to break the samples; ^{d)} residual strains were obtained via the retraction test after reaching the strain of 450 %.

An unusual shape-memory effect was observed during the mechanical test of #2, which has the potential for biomedical applications, such as self-tightening knots, etc. The shape-memory effect of the [PDL-b-PCHPE-b-PDL]_n multi-block copolyester was characterized by repeatedly stretch the specimen to the strains of 400 or 500 % at ambient temperature (18 °C), which is below the T_g of the hard segment (ca. 55 °C). After reaching the predetermined maximum strain, the specimen was left to relax freely at ambient temperature for 30 min to get a constant strain (ϵ_c). After that, the specimen was placed on a heating plate (45 °C) for 30 s followed by cooling to ambient temperature. Figure 8 demonstrates the eight consecutive thermomechanical cycles (for the cycles 1-4, the maximum strain is 400 %, while for the cycles 5-8, the maximum strain is 500 %). A residual strain (see experimental section for the definition) over 100 % can be achieved

- after being stretched to $\epsilon = 400\%$ and a maximum residual strain of 140% was observed after being stretched to 500% . This residual strain value is impressive, especially considering that the deformation was conducted *via* the cold-drawing method while high strain residual values are normally achieved by stretching specimens at a temperature above transition temperature, followed by cooling the specimens to low temperature (e.g. $-20\text{ }^{\circ}\text{C}$) to fix the chain movement. Also, the specimen exhibited excellent strain recovery capability ($> 96\%$) after being heated to $45\text{ }^{\circ}\text{C}$ (the shape memory effect was also recorded by photos shown in Figure 9).
- As discussed above, #2 in Table 5 demonstrates interesting plastics-to-rubbers transition. This kind of phenomenon is quite rare and only be observed before in SBS elastomer and its derivatives, also known as the 'strain-induced plastics-to-rubbers transition'. Considering the similarity between PCHPE-*b*-PDL and SBS polymers (a combination of the aliphatic soft block with low T_g and the aromatic hard block with high T_g), it is reasonable to assume that the 'strain-induced plastics-to-rubbers transition' observed in both case shares the same mechanism. Basically, instead of forming the island-like phase-separated structure, bicontinuous phase-separated nanostructure was formed. Therefore, at low strains ($0 \sim 100\%$), the sample behaves like plastics owing to the presence of continuous PCHPE phase, during which the PCHPE continuous phase is also gradually deformed *via* shearing, kinking, destruction and orientation. Finally, the PCHPE continuous phase fragments into separated PCHPE domains randomly dispersed in the PDL matrix to afford rubber-like mechanical properties. To prove this hypothesis, the cyclic tensile test was conducted (see Figure 10A). The sample bar was first stretched to the strain of 450% to fragment the PCHPE continuous phase, followed by relaxing freely at room temperature ($19\text{ }^{\circ}\text{C}$) to reach a constant residual strain ($\epsilon_r = 80\%$). Then, the sample bar was stretched again with the same extension rate. In the 2nd stress-strain curve, no yield point was observed and a much lower young's modulus was recorded, which matches the mechanical properties of rubber/elastomers. Also, the cyclic tensile stress-strain curve obtained from #2 is comparable with the one obtained from SBS (with $48\text{ wt\%}$ of polystyrene) given by the literature (Figure 10B). Therefore, the strain-induced plastics-to-rubbers transition displayed by #2 is indeed resulting from the same bicontinuous phase deformation mechanism as SBS polymers.


A platform (increasing strain with constant stress) was observed after the yield point in both stress-strain curves of #2 and #3. The presence of this platform results from a type of segment movement known as the forced high elastic deformation (or cold drawing), which has been observed in many rigid amorphous polymers. This deformation occurs when

high external force is applied on the rigid amorphous polymers below T_g . The polymer segments are thus forced to shear, kink and re-orient. However, this deformation is not thermal dynamically favourable. So, the strain caused by the forced high elastic deformation is recoverable because the polymer segments tend to go back to the stage with lower free energy. This recovery process can either be achieved slowly below the T_g of the polymer or be accelerated by heating the polymer to a temperature above T_g . A key factor leading to the thermoplastic elastomer property is the phase separation effect. Phase separation means that within the block copolymers or polymer blends, different block/polymer species form separated regions of each species (usually in nanoscale) rather than miscible with each other. For example, in the case of PDL-*b*-PCHPE-*b*-PDL multi-block copolyesters, PCHPE blocks form a hard region, while PDL blocks form a soft region. Given certain composition (e.g. 26 wt% of PCHPE), PCHPE hard regions disperse in the continuous soft PDL region, leading to the island-like phase separated nanostructure. The separated PCHPE hard regions act as the physical crosslinking point during mechanical tests, affording the elastomer/rubber property. However, different from chemical crosslinking point, physical crosslinking point is reversible upon heating. Thus, PDL-*b*-PCHPE-*b*-PDL multi-block copolyesters display the property of thermoplastic elastomers.

20 Example 7: Property Comparison with PCHPE-*b*-PCL

Although ϵ -caprolactone (ϵ -CL) and ϵ -decalactone (ϵ -DL) have similar chemical structure and the homopolymer of both ϵ -caprolactone and ϵ -decalactone share the same glass transition temperature, no obvious elasticity was observed in the case of PCHPE-*b*-PCL. This is caused by the high crystallinity of the PCL block (usually, $\chi > 40\%$). Therefore, considering the high T_g of PCHPE ($\geq 60^\circ\text{C}$) and high crystallinity of PCL, both blocks in PCHPE-*b*-PCL can be classified as hard segments at certain temperature range ($T \leq -60^\circ\text{C}$ or $0^\circ\text{C} \leq T \leq 60^\circ\text{C}$) which makes the material (PCHPE-*b*-PCL) very brittle rather than elastic at ambient temperature (e.g. ca. 25°C). However, owing to the 5-carbon alkyl substituent, the homopolymer of ϵ -DL shows much less crystallinity (usually, $0\% \leq \chi \leq 20\%$) and soft polymer chains (at the temperature higher than -60°C) due to its low T_g . Therefore, different from PCHPE-*b*-PCL, PCHPE-*b*-PDL has both the hard segment (PCHPE) and the soft segment (PDL) at certain temperature range (e.g. $-60^\circ\text{C} \leq T \leq 120^\circ\text{C}$) to afford the special elastomer-like mechanical properties at ambient temperature (e.g. ca. 25°C).

Preparation of di-zinc complex 2



Zn(CF₃COO)₂.xH₂O was dried under a vacuum at 40°C in the presence of P₂O₅ for 24 h. the ligand H₂L (0.80 g, 1.45 mmol) was dissolved in methanol (70 mL) and Zn(CF₃COO)₂.xH₂O (0.85 g, 2.91 mmol) was added. The mixture was stirred for 18 hours and the methanol removed *in vacuo*. The product was taken up in dichloromethane (10 mL), filtered, and the solvent removed *in vacuo*. The product, a white powder, was dried under a vacuum at 40°C, in the presence of P₂O₅ for 10 h. White powder; yield: 0.96 g, 1.05 mmol, 74%.

¹H NMR (CDCl₃); δ 6.92(s, 4H, Ar-H), 4.32-4.26 (m, 4H, Ar-CH₂-N), 3.25 (d, *J* = 12.0 Hz, 4H, Ar-CH₂-N), 3.01(m, 4H, N-CH₂-C), 2.68 (d, *J* = 11.5 Hz, 4H, N-CH₂-C), 2.40 (t, *J* = 12.7 Hz, 4H, NH), 1.24 (s, 18H, Ar-CH₃), 1.18 (s, 6H, N-C-CH₃), 1.03 (s, 6H, N-C-CH₃)
EA: calculated for C₃₈H₅₄F₆N₄O₆Zn₂: C 50.29, H 6.00, N 6.17; Found: C 45.64, H 6.76, N 5.24
calculated for C₃₈H₅₄F₆N₄O₆Zn₂·5H₂O: C 46.75, H 6.47, N 5.62

Example 8: Sequence controlled chemoselective terpolymerization of CO₂/CHO/ε-DL using complex 2 to afford PDL-b-PCHC-b-PDL triblock copolymers with 31 wt% of PCHC

Complex 2 (0.02 g, 0.04 mmol), CHO (4.57 mL, 48 mmol) and ε-DL (1.72 mL, 8.8 mmol) were placed in a Schlenk tube, charged with a stirrer bar, under nitrogen. The relative molar ratios of [2]:[CHO]:[ε-DL] were 1:2000:200. The reaction mixture was de-gassed and then heated to 80 °C at 1 bar CO₂ pressure. After the allotted time, the CO₂ was removed by six vacuum/nitrogen cycles. The reaction was monitored by ¹H NMR spectroscopy and when the ring opening polymerisation had reached ~70%, the crude reaction mixture was exposed to air and a ¹H NMR spectrum of the crude mixture was recorded. The CHO was removed, under vacuum, and the polymer was purified by precipitation of a THF solution into methanol. Results obtained from this polymerization are shown in Table 8, entry 1 below.

Example 9: Sequence controlled chemoselective terpolymerization of CO₂/CHO/ε-DL using complex 2 to afford PDL-b-PCHC-b-PDL triblock copolymers with 50 wt% of PCHC

Complex 2 (0.02 g, 0.04 mmol), CHO (4.57 mL, 48 mmol) and ε-DL (0.86 mL, 4.4 mmol) were placed in a Schlenk tube, charged with a stirrer bar, under nitrogen. The relative molar ratios of [2]:[CHO]:[ε-DL] were 1:2000:100. The reaction mixture was de-gassed and then heated to 80 °C at 1 bar CO₂ pressure. After the allotted time, the CO₂ was removed by six vacuum/nitrogen cycles. The reaction was monitored by ¹H NMR spectroscopy and when the ring opening polymerisation had reached ~70%, the crude reaction mixture was exposed to air and a ¹H NMR spectrum of the crude mixture was recorded. The CHO was removed, under vacuum, and the polymer was purified by precipitation of a THF solution into methanol. Results obtained from this polymerization are shown in Table 8, entry 2 below.

Table 8

#	[CHO]:[ε-DL] ^a	% PCHC ^b	M _{ntheo} ^c	M _{nexp} ^d	Đ ^d	T _g /°C ^e
1	2000:200	1:2.2	15,900	6829	1.45	48
2	2000:200	1:1	27,700	7917	1.37	-

^{a)} Molar equivalent of monomers to catalysts; ^{b)} weight ratio of the PCHC block to PDL block, calculated based on the ¹H NMR spectra; ^{c)} theoretical molecular weight calculated according to the conversion of the monomers; ^{d)} experimental molecular weight and molecular weight distribution obtained from the SEC characterization; ^{e)} obtained from DSC characterization.

Example 10: Sequence controlled chemoselective terpolymerization of CO₂/PA/vCHO/ε-DL using complex 1 to afford PDL-b-PvCHC-b-PCHPE-b-PvCHC-b-PDL pentablock copolymers

25

Complex 1 (0.01 g, 0.012 mmol), PA (0.08 g, 0.57 mmol), ε-DL (0.86 mL, 4.6 mmol) and a stock solution of CHD (55.0 μL; 50 mg/mL in CHO) were dissolved in CHO (2.51 mL, 17.8 mmol), under nitrogen, in a Schlenk tube, charged with a stir bar. The relative molar ratios of [1]/[CHD]/[PA]/[VCHO]/[ε-DL] were 1/2/50/1550/400. The schlenk tube was then charged with 1 atm of CO₂. The solution was heated to 100 °C. Aliquots for ¹H NMR were taken during the polymerisation. After the allotted time, the atmosphere was changed to nitrogen using short N₂/vacuum cycles. After the allotted reaction time, the polymerization was terminated by cooling down to ambient temperature a ¹H NMR spectrum of the crude

mixture was recorded. The vCHO was removed, under vacuum, and the polymer was purified by precipitation of a THF solution into methanol. Results obtained from this polymerization are shown in Table 9, entry 1 below. The reaction of $\text{LZn}_2\text{Ph}_2/\text{CHD}$ with $\text{CO}_2/\text{PA}/\text{vCHO}/\epsilon\text{-DL}$ was also monitored by in-situ ATR-IR spectroscopy (see Figure 11).

5


Table 9


#	Monomers	TOF PE	TOF PC	TOF PL	M_n PE	M_n PC	M_n PL	PE:PC:PL exp	T_g °C
1	PA:vCHO: ϵ -DL 50:1550:200	38.5	51.6	7.2	804 (1.06)	1487 (1.15)	1953 (1.19)	1:3:5	-51

10


Claims

1. A multi-block copolymer comprising at least blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B comprises a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the multi-block copolymer is characterised by one or more of features (i) to (iii):
 - (i) a degree of crystallinity (χ) of block A of no more than 20% as determined by DSC; and/or
 - (ii) a degree of crystallinity (χ) of block A of no more than 20% as determined by WAXS; and/or
 - (iii) a measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B.
2. The multi-block copolymer of claim 1, wherein block B of the multi-block copolymer is amorphous.
3. The multi-block copolymer of claim 1, wherein:
 - (a) the copolymer has a measureable T_g for each of blocks A and B, with a difference of at least 10°C or at least 100°C between the T_g for blocks A and B; and/or
 - (b) block B has a T_g of $\geq 30^\circ\text{C}$, and no more than 250 °C; and/or
 - (c) the multi-block copolymer is characterised by feature (i) or (ii) and feature (iii); and/or
 - (d) the weight content of block B, with reference to block A, is from 10 to 90%, preferably 20 to 80%, more preferably 30 to 55%; and/or
 - (e) the multi-block copolymer has a M_n (number average molecular weight) of, at least 1 kg/mol, preferably at least 10kg/mol; and/or
 - (f) the multi-block copolymer has a Young's modulus of 1MPa to 7000MPa, preferably at least 50 MPa, for example 200MPa to 7000MPa, preferably 223 MPa to 6600 MPa; and/or
 - (g) the epoxide is



or  R' wherein R' is optionally substituted C_{2-12} , or a mixture thereof; and/or

(h) the anhydride is




mixture thereof; and/or

(i) the anhydride comprises an aromatic moiety; and/or


(j) the lactone comprises one or more of an optionally substituted alkyl substituent (e.g. C_{1-10} alkyl, preferably C_{3-8} alkyl) on the hydrocarbon ring, an aromatic component or at least one $C=C$ double bond; and/or

(k) the lactone is selected from:



, or a mixture thereof, or block A comprises a polyester formed by polymerisation of ϵ -decalactone; and/or


(l) the lactide is




(m) block B comprises: (a) poly(cyclohexylene phthalic)ester, an alternating copolyester formed from polymerization of cyclohexene oxide and phthalic anhydride; (b) a polycarbonate formed from polymerization of cyclohexene oxide and carbon dioxide or

4-vinyl-1-cyclohexene 1,2-epoxide and carbon dioxide; or a combination thereof, preferably wherein block B comprises poly(cyclohexylene phthalic)ester.

4. A multi-block copolymer comprising at least blocks A-B-A or B-A-B, wherein block A comprises a polyester formed by polymerisation of a lactone and/or a lactide; and block B comprises a copolyester formed by polymerisation of an epoxide and an anhydride, or a polycarbonate formed by polymerisation of an epoxide and carbon dioxide, wherein the block B comprises an aromatic moiety and/or wherein the lactone is as defined below and comprises one or more of (i) one or more of R_a and R_b selected from a substituent other than hydrogen; (ii) an optionally substituted alkyl substituent (e.g. C_{1-10} alkyl, preferably C_{3-8} alkyl) on the hydrocarbon ring, (iii) an aromatic component; and (iv) at least one C=C double bond; and/or with the proviso that the lactone is not ϵ -caprolactone; wherein the lactone has the following formula:



wherein  represents a hydrocarbon ring having 2 to 20, preferably at least 4, ring carbon atoms in addition to the carbon of the $-C(O)O$ moiety,

wherein the ring is saturated or contains one or more C=C double bonds and

wherein each saturated ring carbon atom is substituted by R_a and R_b and each unsaturated carbon atom is substituted by R_a , wherein R_a and R_b are independently selected from halogen, nitro, alkoxy, aryloxy, heteroaryloxy, alkylamino, imine, nitrile, acetylide, carboxylate or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, branched alkyl heteroaryl, alkylaryl or alkylheteroaryl, or wherein two or more of R_a and R_b on adjacent ring carbon atoms can be taken together to form a saturated, partially saturated or unsaturated 3 to 15 membered, optionally substituted ring system, optionally containing one or more heteroatoms, and wherein the multi-block copolymer is characterised by one or more of features (a) to (c):

(a) a degree of crystallinity (χ) of block A of no more than 20% as determined by DSC; and/or

(b) a degree of crystallinity (χ) of block A of no more than 20% as determined by WAXS; and/or

(c) a measureable T_g for each of blocks A and B, with a difference of at least 10°C between the T_g for blocks A and B.

5. The multi-block copolymer of claim 4, wherein:

(a) block A comprises a polyester formed by polymerisation of ϵ -decalactone; and/or

(b) block B comprises (i) poly(cyclohexylene phthalic)ester, an alternating copolyester formed from polymerization of cyclohexene oxide and phthalic anhydride; (ii) a polycarbonate formed from polymerization of cyclohexene oxide and carbon dioxide or 4-vinyl-1-cyclohexene 1,2-epoxide and carbon dioxide; or a combination thereof, preferably wherein block B comprises poly(cyclohexylene phthalic)ester.

6. The multi-block copolymer of claim 4, comprising the features of claim 1.

7. The multi-block copolymer of claim 6, comprising the features of claim 2 or 3.